

METHOD AND APPARATUS FOR NON-ABLATIVE, PHOTOACOUSTIC
COMPRESSION MACHINING IN TRANSPARENT MATERIALS USING
FILAMENTATION BY BURST ULTRAFast LASER PULSES

Background Of The Invention

- 5 The present invention relates to a non-ablative method and apparatus for drilling
stopped or through orifices beginning at any depth, or in any one of a set of stacked wafers,
plates or substrates, primarily, but not limited to, such transparent materials as glass,
sapphire, silicon such that the structural characteristics of the orifice and surrounding
material exceed that found in the prior art.
- 10 There is a huge demand for drilling multiple holes in a transparent substrate such
as one made of glass or a polycarbonate. One application of a drilled substrate is for use as a
filter for air monitoring, particle monitoring, cytology, chemotaxis, bioassays, and the such.
These commonly require orifices a few hundred nanometers to tens of micrometers in
diameter that remain identical to each other and have a hole to surface
- 15 area ratio that remains stable when produced in volume.

Currently, the prior art material processing systems produce orifices in substrates
such as glass by diamond drilling, or laser exposure techniques such as: ablative machining;
combined laser heating and cooling; and high speed laser scribing. All of the prior art
systems have low throughput times, do not work well with many of the new

20 exotic substrate materials, have problems with the opacity of multiple level substrate
stacks, cannot attain the close orifice spacing sought, propagate cracks in the material or
leave an unacceptable surface roughness on the orifice sides and surface surrounding the
point of initiation as detailed below.

In current manufacturing, the singulation, treatment of wafers or glass panels to develop orifices typically relies on diamond cutting routing or drilling.

Laser ablative machining is an active development area for singulation, dicing, scribing, cleaving, cutting, and facet treatment, but has disadvantages, particularly in

5 transparent materials, such as slow processing speed, generation of cracks, contamination by ablation debris, and moderated sized kerf width. Further, thermal transport during the laser interaction can lead to large regions of collateral thermal damage (i.e. heat affected zone). While laser ablation processes can be dramatically improved by selecting lasers with wavelengths that are strongly absorbed by the medium (for example, deep UV

10 excimer lasers or far-infrared CO₂ laser), the above disadvantages cannot be eliminated due to the aggressive interactions inherent in this physical ablation process. Alternatively, laser ablation can also be improved at the surface of transparent media by reducing the duration of the laser pulse. This is especially advantageous for lasers that are transparent inside the processing medium. When focused onto or inside

15 transparent materials, the high laser intensity induces nonlinear absorption effects to provide a dynamic opacity that can be controlled to accurately deposit appropriate laser energy into a small volume of the material as defined by the focal volume. The short duration of the pulse offers several further advantages over longer duration laser pulses such as eliminating plasma reflections and reducing collateral damage through the small
20 component of thermal diffusion and other heat transport effects during the much shorter time scale of such laser pulses. Femtosecond and picosecond laser ablation therefore offer significant benefits in machining of both opaque and transparent materials. However, machining of transparent materials with pulses even as short as tens to

hundreds of femtosecond is also associated with the formation of rough surfaces and microcracks in the vicinity of laser-formed orifices or trench that is especially problematic for brittle materials like Alumina glasses, doped dielectrics and optical crystals. Further, ablation debris will contaminate the nearby sample and surrounding
5 surfaces.

A kerf-free method of cutting or scribing glass and related materials for orifices relies on a combination of laser heating and cooling, for example, with a CO₂ laser and a water jet. Under appropriate conditions of heating and cooling in close proximity, high tensile stresses are generated that induces cracks deep into the material, that can be
10 propagated in flexible curvilinear paths by simply scanning the laser cooling sources across the surface. In this way, thermal-stress induced scribing provides a clean separation of the material without the disadvantages of a mechanical scribe or diamond saw, and with no component of laser ablation to generate debris. However, the method relies on stress-induced crack formation to direct the scribe and a mechanical or laser
15 means to initiate the crack formation. Short duration laser pulses generally offer the benefit of being able to propagate efficiently inside transparent materials, and locally induce modification inside the bulk by nonlinear absorption processes at the focal position of a lens. However, the propagation of ultrafast laser pulses (>5 MW peak power) in transparent optical media is complicated by the strong reshaping of the spatial
20 and temporal profile of the laser pulse through a combined action of linear and nonlinear effects such as group-velocity dispersion (GVD), linear diffraction, self-phase modulation (SPM), self-focusing, multiphoton/tunnel ionization (MPI/TI) of electrons from the valence band to the conduction band, plasma defocusing, and self-steepening.

These effects play out to varying degrees that depend on the laser parameters, material nonlinear properties, and the focusing condition into the material.

There are other high speed scribing techniques for flat panel display (FPD) glasses.

A 100-kHz Ti:sapphire chirped-pulse-amplified laser of frequency-doubled 780

5 nm, 300 fs, 100 μ J output was focused into the vicinity of the rear surface of a glass substrate to exceed the glass damage threshold, and generate voids by optical breakdown of the material. The voids reach the back surface due to the high repetition rate of the laser. The connected voids produce internal stresses and damage as well as surface ablation that facilitate dicing by mechanical stress or thermal shock in a direction along

10 the laser scribe line. While this method potentially offers fast scribe speeds of 300 mm/s, there exists a finite kerf width, surface damage, facet roughness, and ablation debris as the internally formed voids reach the surface.

Although laser processing has been successful in overcoming many of the limitations associated with diamond cutting, as mentioned above, new material

15 compositions have rendered the wafers and panels incapable of being laser scribed.

Henceforth, a fast, economical system for drilling through or stopped orifices in transparent materials emanating from the top or bottom surface, that avoids the drawbacks of existing prior art systems would fulfill a long felt need in the materials processing industry. This new invention utilizes and combines known and new

20 technologies in a unique and novel configuration to overcome the aforementioned problems and accomplish this.

Summary of the Invention

The general purpose of the present invention, which will be described subsequently in greater detail, is to provide an apparatus and method for producing orifices in transparent substrates, generally semiconductor materials such as Si wafers or materials such as glass or Sapphire, by using filamentation by burst of ultrafast laser pulses with specific adjustments of the laser parameters in conjunction with distributed focus lens assembly that creates a plurality of different foci wherein the principle focal waist never resides in or on the surface of the target; so as to create a filament in the material that develops an orifice in any or each member of a stacked array of the material wherein the orifice has a specified depth and width at a desired point of initiation and point of termination within the desired wafer, plate or substrate. While the present disclosure focuses primarily on the drilling of orifices it is understood that the system and method described herein are equally applicable to the machining processes of drilling, dicing, cutting and scribing targets.

A method and apparatus for drilling stopped or through orifices beginning at any depth, or in any one of a set of stacked wafers, plates or substrates, primarily, but not limited to, transparent materials such that the structural characteristics of the orifice and surrounding material exceed that found in the prior art. More particularly, to an apparatus and method of multiple orifice formation in any or each member of a stacked array of materials by a novel method using interference of burst of ultrafast laser pulses wherein the laser light and focusing parameters have been adjusted to create a filament inside the material that can create an orifice of specified depth and width at the desired point of initiation and point of termination.

A novel and unique technique to create nanometer to micrometer scale orifices in and through transparent material such as Si wafers, glass or Sapphire is disclosed. It has many of the advantages mentioned heretofore and many novel features that result in a new method of producing non-abatively drilled orifices in materials which is not

5 anticipated, rendered obvious, suggested, or even implied by any of the prior art, either alone or in any combination thereof Specifically, it offers the following huge advances over the prior art: smoother orifice sides, minimal microcrack propagation, longer/deeper orifice creation, non tapered orifices, nonlinear absorption, orifices with a consistent internal diameter, minimized entrance distortion and reduced collateral damage.

10 The subject matter of the present invention is particularly pointed out and distinctly claimed in the concluding portion of this specification. However, both the organization and method of operation, together with further advantages and objects thereof, may best be understood by reference to the following description taken in connection with accompanying drawings wherein like reference characters refer to like
15 elements. Other objects, features and aspects of the present invention are discussed in greater detail below.

Brief Description of the Drawings

FIG 1 is a diagrammatic representation of a prior art abative laser drilling arrangement wherein the principle focus occurs at the top surface of the transparent substrate;

20 FIG 2 is a perspective view of a an orifice formed by the drilling arrangement of FIG 1;

FIG 3 is a representative side view of a prior art ablative laser drilling arrangement wherein the principle focus occurs below the top surface of the transparent substrate;

FIG 4 is a perspective view of a an orifice formed by the drilling arrangement of FIG 3;

FIG 5 is a representative side view of an orifice ablatively drilled as the laser arrangement of FIG 1 wherein the primary focus occurs at the top surface of the transparent substrate;

FIG 6 is a diagrammatic representation of the laser drilling arrangement of the present invention wherein the primary focus occurs above the top surface of the transparent substrate;

FIG 7 is a perspective view of an orifice scribe in a transparent substrate formed by the laser drilling arrangement of the present invention;

FIG 8 is a representative side view of two orifices drilled by the laser arrangement of FIG 6;

FIG 9 is a diagrammatic representation of the prior art ablative laser drilling arrangement;

FIG 10 is is a diagrammatic representation of the present invention;

FIG 11 is a diagrammatic view of the present invention utilizing a distributed focus lens arrangement;

FIG 12 is a diagrammatic view of the present invention utilizing a distributed focus lens arrangement;

FIG 13 is a diagrammatic view of the present invention utilizing a distributed focus lens arrangement and the distribution of focal waists where the principal focus is above the target;

FIG 14 is a is a diagrammatic view of the present invention utilizing a distributed focus lens arrangement and the distribution of focal waists where the principal focus is below the target;

FIG 15 is a diagrammatic view of the present invention of FIG 13 wherein the orifice has been drilled;

FIG 16 is a diagrammatic view of the present invention utilizing a distributed focus lens arrangement and the distribution of focal waists where the principal focus is below

5 multiple targets; and

FIGS 17-19 show three various configurations of the distribution of laser energy.

Detailed Description

There has thus been outlined, rather broadly, the more important features of the invention in order that the detailed description thereof that follows may be better

10 understood and in order that the present contribution to the art may be better appreciated.

There are, of course, additional features of the invention that will be described hereinafter and which will form the subject matter of the claims appended hereto.

Various embodiments and aspects of the disclosure will be described with reference to details discussed below. The following description and drawings are

15 illustrative of the disclosure and are not to be construed as limiting the disclosure.

Numerous specific details are described to provide a thorough understanding of various embodiments of the present disclosure. However, in certain instances, well-known or conventional details are not described in order to provide a concise discussion of embodiments of the present disclosure.

20 In this respect, before explaining at least one embodiment of the invention in detail, it is to be understood that the invention is not limited in its application to the details of construction and to the arrangements of the components set forth in the following description or illustrated in the drawings. The invention is capable of other

embodiments and of being practiced and carried out in various ways. Also, it is to be understood that the phraseology and terminology employed herein are for the purpose of descriptions and should not be regarded as limiting.

Unless defined otherwise, all technical and scientific terms used herein are
5 intended to have the same meaning as commonly understood to one of ordinary skill in the art. Unless otherwise indicated, such as through context, as used herein, the following terms are intended to have the following meanings:

As used herein, the term ablative drilling refers to a method of machining a target (generally by cutting or drilling of a substrate by the removal of material) surface by
10 irradiating it with a laser beam. At low laser flux, the material is heated by the absorbed laser energy and evaporates or sublimates. At high laser flux, the material is typically converted to a plasma. Usually, laser ablation refers to removing material with a pulsed laser, but it is possible to ablate material with a continuous wave laser beam if the laser intensity is high enough. Ablative drilling or cutting techniques are characterized by the
15 creation of a debris field, the presence of a liquid/molten phase at some point during the material removal process, and the creation of an ejecta mound at the entrance and or exit of the feature.

As used herein, the term "photoacoustic drilling" refers to a method of machining a target (generally by cutting or drilling of a substrate from a solid by irradiating it with a
20 lower pulse energy light beam than is used in ablative drilling or cutting techniques. Through the processes of optical absorption followed by thermoelastic expansion, broadband acoustic waves are generated within the irradiated material to form a pathway of compressed material about the beam propagation axis (common with the axis of the

orifice) therein that is characterized by a smooth wall orifice, a minimized or eliminated ejecta and minimized microcrack formation in the material.

As used herein the term "optical efficiency" relates to the ratio of the fluence at the principle focal waist to the total incident fluence at the clear aperture of the focusing
5 element or assembly.

As used herein, the term "transparent" means a material that is at least partially transparent to an incident optical beam. More preferably, a transparent substrate is characterized by absorption depth that is sufficiently large to support the generation of an internal filament modified array by an incident beam according to embodiments
10 described herein. Stated otherwise, a material having an absorption spectrum and thickness such that at least a portion of the incident beam is transmitted in the linear absorption regime.

As used herein, the term "filament modified zone" refers to a filament region within a substrate characterized by a region of compression defined by the optical beam
15 path.

As used herein, the phrases "burst", "burst mode", or "burst pulses" refer to a collection of laser pulses having a relative temporal spacing that is substantially smaller than the repetition period of the laser. It is to be understood that the temporal spacing between pulses within a burst may be constant or variable and that the amplitude of
20 pulses within a burst may be variable, for example, for the purpose of creating optimized or pre-determined filament modified zones within the target material. In some embodiments, a burst of pulses may be formed with variations in the intensities or energies of the pulses making up the burst.

As used herein, the phrase "geometric focus" refers to the normal optical path along which light travels based on the curvature of the lens, with a beam waist located according to the simple lens equation common to optics. It is used to distinguish between the optical focus created by the position of the lenses and their relation to one another and
5 the constriction events created by thermal distortion in the target materials providing, in effect, a quasi-Rayleigh length on the order of up to 15 mm, which is particularly uncommon and related to the inventive nature of this work.

As used herein, the term "substrate" means a glass or a semiconductor and may be selected from the group consisting of transparent ceramics, polymers, transparent
10 conductors, wide bandgap glasses, crystals, crystalline quartz, diamond, sapphire, rare earth formulations, metal oxides for displays and amorphous oxides in polished or unpolished condition with or without coatings, and meant to cover any of the geometric configurations thereof such as but not limited to plates and wafers. The substrate may comprise two or more layers wherein a location of a beam focus of the focused laser
15 beam is selected to generate filament arrays within at least one of the two or more layers. The multilayer substrate may comprise multi-layer flat panel display glass, such as a liquid crystal display (LCD), flat panel display (FPD), and organic light emitting display (OLEO). The substrate may also be selected from the group consisting of autoglass, tubing, windows, biochips, optical sensors, planar lightwave circuits, optical fibers,
20 drinking glass ware, art glass, silicon, 111-V semiconductors, microelectronic chips, memory chips, sensor chips, electro-optical lenses, flat displays, handheld computing devices requiring strong cover materials, light emitting diodes (LED), laser diodes

(LD), and vertical cavity surface emitting laser (VCSEL). Targets or target materials are generally selected from substrates.

As used herein the "principal focal waist" refers to the most tightly focused and strongest focal intensity of the beam after final focusing (after passing through the final optical element assembly prior to light incidence upon the target). It may also be used interchangeably with the term "principal focus." The term "secondary focal waist" refers to any of the other foci in the distributed beam having a lesser intensity than the principal focal waist. It may also be used interchangeably with the term "secondary focus" or "secondary foci."

As used herein the term "filament" refers to any light beam traveling through a medium wherein the Kerr effect can be observed or measured.

As used herein, "laser filamentation" is the act of creating filaments in a material through the use of a laser.

As used herein the term "sacrificial layer" refers to a material that can be removeably applied to the target material.

As used herein the term "machining" or "modification" encompasses the processes of drilling orifices, cutting, scribing or dicing a surface or volume of a target or substrate.

As used herein the term "focal distribution" refers to spatiotemporal distribution of incident light rays passing through a lens assembly that in its aggregate is a positive lens. Generally, herein their subsequent convergence of spots of useful intensity as a function from the distance from the center of the focusing lens is discussed.

As used herein the terms "critical energy level," "threshold energy level" and "minimum energy level" all refer to the least amount of energy that must be put into or onto a target to initiate the occurrence of a transient process in the target material such as but not limited to ablative machining, photoacoustic machining, and the Kerr effect.

5 As used herein the term "aberrative lens" refers to a focusing lens that is not a perfect lens wherein the lens curvature in the x plane does not equal the lens curvature in the y plane so as to create a distributed focal pattern with incident light that passes through the lens. A positive aberrative lens is a focally converging lens and a negative aberrative lens is a focally diverging lens.

10 As used herein, the terms, "comprises" and "comprising" are to be construed as being inclusive and open ended, and not exclusive. Specifically, when used in the specification and claims, the terms, "comprises" and "comprising" and variations thereof mean the specified features, steps or components are included. These terms are not to be interpreted to exclude the presence of other features, steps or components.

15 As used herein, the term "exemplary" means "serving as an example, instance, or illustration," and should not be construed as preferred or advantageous over other configurations disclosed herein.

 As used herein, the terms "about" and "approximately" are meant to cover variations that may exist in the upper and lower limits of the ranges of values, such as
20 variations in properties, parameters, and dimensions. In one non-limiting example, the terms "about" and "approximately" mean plus or minus 10 percent or less.

 The main objective of the present invention is to provide fast, reliable and economical non-ablative laser machining technique to initiate orifices (stopped/blind or

through orifices) in the target material that may be initiated below or above a single of multiple stacked target material by filamentation by a burst/s of ultrafast laser pulses. Ultra short lasers offer high intensity to micromachine, to modify and to process surfaces cleanly by aggressively driving multi-photon, tunnel ionization, and electron-avalanche

5 processes. The issue at hand is how to put enough energy in the transparent material of the target, less than that used in ablative drilling, but beyond the critical energy level to initiate and maintain photoacoustic compression so as to create a filament that modifies the index of refraction at the focal points in the material and does not encounter optical breakdown (as encountered by the prior art ablative drilling systems) such that continued
10 refocusing of the laser beam in the target material can continue over long distances, enough so that even multiple stacked substrates can be drilled simultaneously with negligible taper over the drilled distance, a relatively smooth orifice wall and can initiate from above, below or within the target material.

Generally, in the prior art, laser ablation techniques that utilize a high energy
15 pulsed laser beam that is focused to a single principle focus above, within or at a surface of the material, have been used to machine transparent materials. As shown in FIG 1 the incident laser light beam 2 passes through a focusing assembly passing through a final focusing lens 4 so as to focus a non-distributed light beam 6 that has a focal waist 8 at the surface of the target 10. As can be seen in FIG 3, optionally, the non-distributed light
20 beam may be focused such that the focal waist resides within the target. Generally these techniques use a perfect spherical focusing lens 12, that is to say a lens that is non-aberated that has curvature in the X plane that equals the curvature in the Y plane ($C_x=C_y$) or alternatively with a focusing element assembly that produces a non

distributed beam having a single focus 14 as shown in FIG 9. This creates a tight beam spot that is then delivered on (FIG 1) or in the target substrate material 10. (FIG 3) FIG 2 illustrates the geometry of a machined slot 16 cut with the technique of FIG 1, and FIG 4 illustrates the geometry of an oblong orifice 18 made with the technique of FIG 3.

5 Propagation of intense ultrafast laser pulses in different optical media has been well studied. Nonlinear refractive index of a material is a function of laser intensity. Having an intense laser pulse with Gaussian profile, wherein the central part of the pulse has much higher intensity than the tails, means the refractive index varies for the central and surrounding areas of the material seeing the laser beam pulse. As a result, during
10 propagation of such laser pulse, the pulse collapses automatically. This nonlinear phenomenon is known in the industry as self-focusing. Self-focusing can be promoted also using a lens in the beam path. In the focal region the laser beam intensity reaches a value that is sufficient to cause multiple-ionization, tunnel ionization and avalanche ionization, which creates plasma in the material. Plasma causes the laser beam to defocus
15 and refocus back to form the next plasma volume. The inherent problem with a single focus in a non-distributed beam is that the process ends after the laser pulses lose all their energy and are unable to refocus as discussed below.

 This ablative method develops a filament in the material 10 of a length of up to 30 microns until it exceeds the optical breakdown threshold for that material and optical
20 breakdown (OB) 16 occurs. (FIG 9) At OB the maximum threshold fluence (the energy delivered per unit area, in units of J/m^2) is reached and the orifice diameter narrows and ablative machining or drilling ceases to proceed any deeper. This is the obvious drawback to using the prior art methods as they limit the size of the orifice that can be

drilled, cause a rough orifice wall and result in an orifice with a taper 22 having a different diameter at the top and bottom surfaces of the target 10. (FIG 5) This occurs because in ablative machining, the beam has central focus 8 (also referred to as a principle focal waist) at the surface of the target 10 causing localized heating and thermal

5 expansion therein heating the surface of the material 10 to its boiling point and generating a keyhole. The keyhole leads to a sudden increase in optical absorptivity quickly deepening the orifice. As the orifice deepens and the material boils, vapor generated erodes the molten walls blowing ejecta 20 out and further enlarging the orifice 22. As this occurs, the ablated material applies a pulse of high pressure to the surface underneath

10 it as it expands. The effect is similar to hitting the surface with a hammer and brittle materials are easily cracked. (Additionally, brittle materials are particularly sensitive to thermal fracture which is a feature exploited in thermal stress cracking but not desired in orifice drilling.) OB generally is reached when the debris is not ejected, a bubble is created in the orifice 22 or there is a violent ablation that cracks the target in the area of

15 the orifice 22. Any one or combination of these effects causes the beam 6 to scatter from this point or be fully absorbed not leaving enough beam power (fluence) to drill down through the material 10 any further. Additionally, this creates a distortion or roughness known as the ablative ejecta mound 20 found around the initiating point at the surface of the target substrate 10. (FIG 5)

20 Another problem with laser ablation techniques is that the orifices it drills are not of a uniform diameter as the laser beam filamentation changes its diameter as a function of distance. This is described as the Rayleigh range and is the distance along the

propagation direction of a beam from the focal waist to the place where the area of the cross section is doubled. This results in a tapered orifice 22 as shown in FIGS 2 and 5.

The present invention solves the optical breakdown problem, minimizes the orifice roughness and the ablative ejecta mound, and eliminates the tapering diameter

5 orifice.

The present disclosure provides devices, systems and methods for the processing of orifices in transparent materials by laser induced photoacoustic compression. Unlike previously known methods of laser material machining, embodiments of the present invention utilize an optical configuration that focuses the incident beam 2 in a distributed
10 manner along the longitudinal beam axis such that there is a linear alignment of the principal focus 8 and secondary foci 24 (coincident to the linear axis of the orifice but vertically displaced from the principle focus or focal waist) to allow the continual refocusing of the incident beam 2 as it travels through the material 10 thereby enabling the creation of a filament that modifies the index of refraction along the beam path in the
15 material 10 and does not encounter optical breakdown (as seen in the prior art ablative drilling systems both with and without the use of rudimentary filamentation) such that continued refocusing of the laser beam in the target material can continue over long distances. (FIG 6)

This distributed focusing method allows for the "dumping" or reduction of
20 unnecessary energy from the incident beam 2 found at the principle focal waist 8 by the creation of secondary foci 24 by the distributed focusing elements assembly 26, and by positioning the location of the principle focal waist 8 from on or in the material, to outside the material 10. This dumping of beam fluence combined with the linear

alignment of the principle focal waist 8 and secondary focal waists 24, enables the formation of filaments over distances well beyond those achieved to date using previously known methods (and well beyond 1 mm) while maintaining a sufficient laser intensity (fluence $\mu\text{J}/\text{cm}^2$) to accomplish actual modification and compression over the entire length of the filament zone. This distributed focusing method supports the formation of filaments with lengths well beyond one millimeter and yet maintaining an energy density beneath the optical breakdown threshold of the material with intensity enough so that even multiple stacked substrates can be drilled simultaneously across dissimilar materials (such as air or polymer gaps between layers of target material) with negligible taper over the drilled distance, (FIG 7) and a relatively smooth walled orifice wall that can be initiated from above, below or within the target material. Propagating a non-tapered wall slit 23 in a target 10 is accomplished by the relative movement of the target 10 while machining an orifice.

The optical density of the laser pulse initiates a self focusing phenomena and generates a filament of sufficient intensity to non-ablative initial photoacoustic compression in a zone within/about/around the filament so as to create a linear symmetrical void of substantially constant diameter coincident with the filament, and also causes successive self focusing and defocusing of said laser pulse that coupled with the energy input by the secondary focal waists of the distributed beam forms a filament that directs/guides the formation of the orifice across or through the specified regions of the target material. The resultant orifice can be formed without removal of material from the target, but rather by a photoacoustic compression of the target material about the periphery of the orifice formed.

It is known that the fluence levels at the surface of the target 10 are a function of the incident beam intensity and the specific distributed focusing elements assembly, and are adjusted for the specific target material/s, target/s thickness, desired speed of machining, total orifice depth and orifice diameter. Additionally, the depth of orifice drilled is dependant on the depth over which the laser energy is absorbed, and thus the amount of material removed by a single laser pulse, depends on the material's optical properties and the laser wavelength and pulse length. (For this reason a wide range of process parameters are listed herein with each particular substrate and matching application requiring empirical determination for the optimal results with the system and materials used.) As such, the entry point on the target 10 may undergo some minimal ablative ejecta mound formation 20 if the fluence levels at the surface are high enough to initiate momentary, localized ablative (vaporized) machining, although this plasma creation is not necessary. In certain circumstances it may be desirable to utilize a fluence level at the target surface that is intense enough to create the transient, momentary ablative drilling to give a broad bevelled entry yet have the remainder of the orifice 22 of uniform diameter FIG 8 as would be created by a distributed focus hybrid drilling method using an energy level that permits a momentary ablative technique followed by a continual photo acoustic compression technique. This can be accomplished by the present invention by selection of a fluence level at the target surface that balances the linear absorption against the non linear absorption of the beam in the material such that the fluence level required for ablative machining will be exhausted at the desired depth of the bevelled (or other geometric configuration). This hybrid technique will result in a minor ejecta mound 20 that can be eliminated if a sacrificial layer 30 is applied to the target

surface. Common sacrificial layers are resins or polymers such as but not limited to PVA, Methacrylate or PEG, and generally need only be in the range of 1 to 300 microns thick (although the 10 - 30 micron range would be utilized for transparent material machining) and are commonly applied by spraying the sacrificial layer onto the target

- 5 material. The sacrificial layer will inhibit the formation of an ejecta mound on the target
- 10 by preventing molten debris from attaching itself to the surface, attaching instead to the removable sacrificial material as is well known in the art.

To accomplish photoacoustic compression machining requires the following system:

- 10
- A burst pulse laser system capable of generating a beam comprising a programmable train of pulses containing from 2 to 50 subpulses within the burst pulse envelope. Further the laser system needs to be able to generate average power from 1 to 200 watts depending on the target material utilized, typically this range would be in the range of 50 to 100 watts for borosilicate glass.
- 15
- A distributed focusing element assembly (potentially comprising positive and negative lenses but having a positive focusing effect in the aggregate) capable of producing a weakly convergent, multi foci spatial beam profile where the incident fluence at the target material is sufficient to cause Kerr-effect self-focusing and propagation.
- 20
- An optical delivery system capable of delivering the beam to the target.

Commercial operation would also require translational capability of the material (or beam) relative to the optics (or vice versa) or coordinated/compound motion driven by a system control computer.

The use of this system to drill photoacoustic compression orifices requires the following conditions be manipulated for the specific target/s: the properties of the distributed focus element assembly; the burst pulsed laser beam characteristics; and the location of the principle focus.

5 The distributed focus element assembly 26 may be of a plethora of generally known focusing elements commonly employed in the art such as aspheric plates, telecentric lenses, non-telecentric lenses, aspheric lenses, annularly faceted lenses, custom ground aberrated (non-perfect) lenses, a combination of positive and negative lenses or a series of corrective plates (phase shift masking), any optical element tilted
10 with respect to the incident beam, and actively compensated optical elements capable of manipulating beam propagation. The principle focal waist of a candidate optical element assembly as discussed above, generally will not contain more than 90% nor less than 50% of incident beam fluence at the principle focal waist. (Although in specific instances the optical efficiency of the distributed focus element assembly 26 may approach 99%.)

15 FIG 10 illustrates a non-aspherical, aberrated lens 34 as would be used in the aforementioned process. The actual optical efficiency of the distributed focus element assembly 26 will have to be fine-tuned for each specific application. The users will create a set of empirical tables tailored for each transparent material, the physical configuration and characteristics of the target as well as the specific laser parameters.

20 Silicon Carbide, Gallium Phosphide, sapphire, strengthened glass etc., each have their own values. This table is experimentally determined by creating a filament within the material (adjusting the parameters of laser power, rep rate, focus position and lens characteristics as described above) and ensuring that there is sufficient fluence to induce

a plane of cleavage or axis of photoacoustic compression to create an orifice. A sample optical efficiency for drilling a 5 micron diameter through orifice (as illustrated in FIG 11) in a 2mm thick single, planar target made of borosilicate with a 1 micron, 50 watt laser outputting a burst pulse of 10 μ J energy having a frequency (rep rate) that would lie
5 in the 1 MHz range is 65% wherein the principle focal waist of the beam resides 1 mm off of the desired point of initiation.

It is to be noted that there is also a set of physical parameters that must be met by this photoacoustic compression drilling process. Looking at FIGS 11 and 12 it can be seen that the beam spot diameter 38 > the filament diameter 40 > the orifice diameter 42.
10 Additionally the distributed beam's primary focal waist 8 is never in or on the surface of the target material 10 into which a filament is created.

The location of the principal focal waist 8 is generally in the range of 500 micros to 300 mm off of the desired point of initiation. This is known as the energy dump distance 32. It also is determined by the creation an empirical table tailored for each
15 transparent material, the physical configuration and characteristics of the target as well as the laser parameters. It is extrapolated from the table created by the method noted above.

The laser beam energy properties are as follows: a pulse energy in the beam between .5 μ J to 1000 μ J the repetition rate from 1 Hz to 2 MHz (the rep rate defines the speed of sample movement and the spacing between neighboring filaments). The
20 diameter and length of the filament may be adjusted by changing the temporal energy distribution present within each burst envelope. FIGS 17-19 illustrate examples of three different temporal energy distributions of a burst pulsed laser signal. The rising and

falling burst envelope profiles of FIG 19 represent a particularly useful means of process control especially well adapted for removing thin metal layers from dielectric materials.

Looking at FIGS 13-16 collectively, the mechanism of the present invention can best be illustrated. Herein, burst picosecond pulsed light is used because the total amount of energy deposited in the target material is low and photoacoustic compression can proceed without cracking the material, and less heat is generated in the target material thus efficient smaller packets of energy are deposited in the material so that the material can be raised incrementally from the ground state to a maximally excited state without compromising the integrity of the material in the vicinity of the filament.

The actual physical process occurs as described herein. The principal focal waist of the incident light beam of the pulsed burst laser is delivered via a distributed focusing element assembly to a point in space above or below (but never within) the target material in which the filament is to be created. This will create on the target surface a spot as well as white light generation. The spot diameter on the target surface will exceed the filament diameter and the desired feature (orifice, slot, etc.) diameter. The amount of energy thus incident in the spot on surface being greater than the critical energy for producing the quadratic electro-optic effect (Kerr effect - where the change in the refractive index of the material is proportional to the applied electric field) but is lower than the critical energy required to induce ablative processes and more explicitly below the optical breakdown threshold of the material. Self-focusing occurs above a critical power that satisfies the relationship whereby the power is inverse to the product of the real and complex indices of refraction for the target material. Photoacoustic compression proceeds as a consequence of maintaining the required power in the target

material over time scales such that balancing between the self-focus condition and the optical breakdown condition can be maintained. This photoacoustic compression is the result of a uniform and high power filament formation and propagation process whereby material is rearranged in favor of removal via ablative processes. The extraordinarily

5 long filament thus produced is fomented by the presence of spatially extended secondary foci created by the distributed focusing element assembly, maintaining the self focusing effect without reaching optical breakdown. In this assembly, a large number of marginal and paraxial rays converge at different spatial locations relative to the principal focus. These secondary foci exist and extend into infinite space but are only of useful intensity
10 over a limited range that empirically corresponds to the thickness of the target. By focusing the energy of the second foci at a lower level below the substrate surface but at the active bottom face of the filament event. This allows the laser energy access to the bulk of the material while avoiding absorption by plasma and scattering by debris.

The distributed focal element assembly can be a single aberrated focal lens placed
15 in the path of the incident laser beam to develop what appears to be an unevenly distributed focus of the incident beam into a distributed focus beam path containing a principal focal waist and a series of linearly arranged secondary focal waists (foci). The alignment of these foci is collinear with the linear axis of the orifice 42. Note that the principal focal waist 8 is never on or in the target material 10. In FIG 13 the principal
20 focal waist is above the target material and in FIG 14 it is below the target material 10 as the orifice 42 may be initiated above or below the principal focal waist 8 by virtue of the symmetric and non-linear properties of the focused beam. Thus a beam spot 52 (approximately 10 [tm distance) resides on the surface of the target 10 and the weaker

secondary focal waists collinearly reside within the target because the material acts as the final optical element creating these focal points as the electric field of the laser alters the indices of refraction of the target. This distributed focus allows the amount of laser energy to be deposited in the material so as to form a filament line or zone 60. With

5 multiple linear aligned foci and by allowing the material to act as the final lens, the target material when bombarded with ultrafast burst pulse laser beams, undergoes numerous, successive, localized heatings which thermally induced changes in the material's local refractive index (specifically, the complex index) along the path of the linear aligned foci causing a lengthy untapered filament 60 to be developed in the target followed by an
10 acoustic compression wave that annularly compresses the material in the desired region creating a void and a ring of compressed material about the filamentation path. Then the beam refocuses and the refocused beam combined with the energy at the secondary focal waists maintains the critical energy level and this chain of events repeats itself so as to drill an orifice capable of 1500:1 aspect ratio. (length of orifice/diameter of orifice) with
15 little to no taper and an entrance orifice size and exit orifice size that are effectively the same diameter. This is unlike the prior art that focuses the energy on the top surface of or within the target material resulting in a short filamentation distance until the optical breakdown is reached and filamentation degrades or ceases.

FIG 16 illustrates the drilling of orifices in the bottom two of three planar targets
20 10 in a stacked configuration with an air gap between them wherein the principal focal waist 8 is positioned below the final target 10. The hole can be drilled from the top or the bottom or the middle of a multiple layer setup, but the drilling event always occurs the

same distance from the principal focal waist if the same lens set and curvature is used.

The focal waist is always outside of the material and never reaches the substrate surface.

The method of drilling orifices is through photoacoustic compression is accomplished by the following sequence of steps:

- 5 1. passing laser energy pulses from a laser source through a selected distributive-focus lens focusing assembly;
2. adjusting the relative distance and or angle of said distributive-focus lens focusing assembly in relation to a laser source so as to focus the laser energy pulses in a distributed focus configuration to create a principal focal waist and at least one secondary
- 10 focal waist;
3. adjusting the principal focal waist or the target such that the principle focal waist will not reside on or in the target that is being machined;
4. adjusting the focus such that the spot of laser fluence on the surface of the target that is located below or above said principal focal waist, has a diameter that is always
- 15 larger than a diameter of a filamentation that is formed in the target;
5. adjusting the fluence level of the secondary focal waists are of sufficient intensity and number to ensure propagation of a photoacoustic compressive machining through the desired volume of the target; and
6. applying at least one burst of laser pulses of a suitable wavelength, suitable burst
- 20 pulse rep rate and suitable burst pulse energy from the laser source to the target through the selected distributive-focus lens focusing assembly, wherein the total amount of pulse energy or fluence, applied to the target at a spot where the laser pulse contacts the point of initiation of machining on the target, is greater than the critical energy level required to

initiate and propagate photoacoustic compression machining, yet is lower than the threshold critical energy level required to initiate ablative machining; and

7. stopping the burst of laser pulses when the desired machining has been completed.

5 As mentioned earlier, there may be specific orifice configurations wherein a tapered entrance to the orifice may be desired. This is accomplished by initiation of the orifice with a laser fluence level that is capable of ablative machining for a desired distance and completing the drilling with a laser fluence level below the critical level for ablative machining yet above the critical level for photo-acoustic machining to the

10 desired depth in that material. This type of orifice formation may also utilize the application of a removable sacrificial layer on the surface of the target. This would allow the formation of the ejecta mound onto the sacrificial layer such that the ejecta mound could be removed along with the sacrificial layer at a later time. Such an orifice drilled by a hybrid ablative and photoacoustic compression method of machining would be

15 performed through the following steps, although the application of the sacrificial layer need be utilized and if utilized need not occur first:

1. applying a sacrificial layer to at least one surface of a target;
2. passing laser energy pulses from a laser source through a selected distributive-focus lens focusing assembly;

20 2. adjusting the relative distance and or angle of said distributive-focus lens focusing assembly in relation to a laser source so as to focus the laser energy pulses in a distributed focus configuration to create a principal focal waist and at least one secondary focal waist;

3. adjusting the principal focal waist or the target such that the principle focal waist will not reside on or in the target that is being machined;
4. adjusting the focus such that the spot of laser fluence on the surface of the target that is located below or above said principal focal waist;
- 5 5. adjusting the spot of laser fluence on the surface of the target such that it has a diameter that is always larger than a diameter of a filamentaion that is to formed in the target;
6. ensuring the fluence level of the secondary focal waists are of sufficient intensity and number to ensure propagation of a photoacoustic compressive machining through the
10 desired volume of the target; and
7. applying at least one burst of laser pulses of a suitable wavelength, suitable burst pulse rep rate and suitable burst pulse energy from the laser source to the target through the selected distributive-focus lens focusing assembly, wherein the total amount of pulse energy or fluence, applied to the target at a spot where the laser pulse contacts the point
15 of initiation of machining on the target, is greater that the critical energy level required to initiate ablative machining to the desired depth and thereafter the fluence energy at the bottom of the ablatively drilled orifice is greater than the critical energy level to initiate and propagate a filamentation and photoacoustic compression machining, yet is lower than the threshold critical energy level required to initiate ablative machining; and
20 8. stopping the burst of laser pulses and filamentation when the desired machining has been completed.

The various parameters of the laser properties, the location of the principal focal waist, and the final focusing lens arrangements as well as the characteristics of the orifice created are set forth in the following table. It is to be noted that they are represented in ranges as their values vary greatly with the type of the target material, its thickness and

- 5 the size and location of the desired orifice. The following chart details the ranges of the various system variables used to accomplish the drilling of uniform orifices in any of a plethora of transparent materials.

Laser Properties	
Wavelength	5 microns or less
Pulse width	10 nanoseconds or less
Freq (laser pulse repetition rate)	1Hz to 2 MegaHz
Ave power	200 — 1 watt
Number of sub pulses per burst	1 to 50
Sub pulse spacing	0.1 femtosecond to 10 microsecond
Pulse energy	.5 μ J to 10 micro Joules (μ J) (Ave power/rep rate) watts/l/sec
Orifice Properties	
Min Orifice Diameter	.5 microns
Max Orifice Diameter	5 mm
Max Orifice Depth	10 mm in borosilicate glass
Typical Aspect Ratio	1500:1
Max Aspect Ratio	2500:1
Aberated lens ratio	where the Cx:Cy ratio of the lenses are -5 to 4,000)
Orifice Sidewall Smoothness (Material Independent)	< 5 micron ave. roughness (e.g Si, SiC, SiN, GaAs, GaN, InGaP)
Orifice Side Wall Taper (Material Independent)	Negligible across 10,000 micron depth
Final Optical Assembly	
Ratio of Lens Focal Lengths	+300 to -300
Lens Optical Efficiency	50 to 99%
Beam Properties	
Focal Distribution	-5 to 4,000
M^2	1.00 - 5.00

As noted earlier the parameters above vary with the target. In the way of an operational exemplary, to drill a 3 micron hole 2 mm deep in a transparent substrate the following apparatus and parameters would be used: a 1064 nanometer wavelength laser; 65 watts of average power; 10 μ J pulse energy; 15 subpulses per burst; and a 1 MHz rep
5 rate. This would be focused with an aberated lens delivering distributed foci over 2 mm of space (filament active zone is 2mm long) focusing.5 microns to 100 mm above the top surface depending upon the material.

It is to be understood that the invention is not limited in its application to the arrangements of the components set forth in the following description or illustrated in the
10 drawings. The invention is capable of other embodiments and of being practiced and carried out with various different ordered steps. Also, it is to be understood that the phraseology and terminology employed herein are for the purpose of descriptions and should not be regarded as limiting. As such, those skilled in the art will appreciate that the conception, upon which this disclosure is based, may readily be utilized as a basis for
15 the designing of other structures, methods and systems for carrying out the several purposes of the present invention. It is important, therefore, that the claims be regarded as including such equivalent constructions insofar as they do not depart from the spirit and scope of the present invention.

CLAIMS

We claim:

1. A photo acoustic compression method for machining a transparent target material

5 comprising the following steps:

applying at least one burst of laser pulses of a suitable wavelength, suitable burst pulse rate and suitable burst pulse energy from a laser source to a target, wherein a total amount of pulse energy or fluence, applied to said target at a spot where the laser pulse contacts the point of initiation of machining on the target, is greater than the critical energy level required

10 to initiate and propagate photoacoustic compression machining, yet is lower than the threshold critical energy level required to initiate ablative machining.

2. The method of claim 1 further comprising the steps of:

first, passing said laser energy pulses through a selected distributive-focus lens focusing assembly prior to said application of laser pulses to said target and focusing said
15 laser energy pulses.

3. The method of claim 2 wherein said focusing comprises:

delivering said laser pulses to said target after adjustment of the relative distance and or angle of said distributive focus lens focusing assembly in relation to said laser source so as to focus said laser pulses in a distributed focus configuration so as to create a principal focal

20 waist and at least one secondary focal waist; and

adjusting the principal focal waist or said target such that the principal focal waist does not reside on or in said target that is being machined.

4. The process of claim 3 further comprising the steps of:

adjusting the focus such that said spot located below or above said principal focal

25 waist, has a diameter that is always larger than a diameter of a filamentation that is formed in the target.

5. The process of claim 3 wherein said target may be comprised of one or a set of transparent wafers, plates or substrates in a layered configuration; and

wherein machining of said target is the drilling of stopped or through orifices beginning at any depth and in any one of said set of wafers, plates or substrates in said layered 5 configuration.

6. The process of claim 1 wherein said target may be comprised of one or a set of transparent wafers, plates or substrates in a layered configuration; and

wherein machining of said target is the drilling of stopped or through orifices beginning at any depth and in any one of said set of wafers, plates or substrates in said layered 10 configuration.

7. The process of claim 3 wherein said focusing assembly is selected such that said fluence level of said secondary focal waists are of sufficient intensity and number to ensure propagation of said photoacoustic compressive machining through a desired volume of said target.

15 8. The process of claim 1 wherein said laser pulses have a burst frequency appropriate so as to maintain a selected transient effect arising from an interaction of a previous pulse with said target, said laser pulses having a pulse width of less than about 10 nanoseconds.

9. The method according to claim 1 including applying a sacrificial layer to a surface of said material prior to the said application of burst of laser pulses.

20 10. A hybrid ablative, and photo acoustic compression method for machining a transparent target material comprising the following steps:

applying at least one laser pulse burst of a specific wavelength, burst pulse rep rate and burst pulse energy from a laser source to a target, wherein a total amount of pulse energy or fluence, applied to said target at a spot where the laser pulse contacts the point of initiation of

25 machining on the target, is greater than the critical energy level required to initiate ablative machining for a desired depth and to initiate and propagate

photoacoustic compression machining therefrom.

11. The method of claim 10 further comprising the steps of:

first, passing said laser energy pulses through a selected distributive-focus lens
focusing assembly prior to said application of laser pulses to said target and focusing said
5 laser energy pulses.

12. The method of claim 11 wherein said focusing comprises:

delivering said laser pulses to said target after adjustment of the relative distance and or
angle of said distributive focus lens focusing assembly in relation to said laser source so as to focus
said laser pulses in a distributed focus configuration so as to create a principal focal

10 waist and at least one secondary focal waist; and

adjusting the principal focal waist or said target such that the principle focal waist does not
reside on or in said target that is being machined.

13. The process of claim 12 further comprising the steps of:

adjusting the focus such that said spot located below or above said principal focal
15 waist, has a diameter that is always larger than a diameter of a filamentaion that is formed in
the target.

14. The process of claim 13 wherein said target may be comprised of one or a set of
transparent wafers, plates or substrates in a layered configuration; and

wherein machining of said target is the drilling of stopped or through orifices
20 beginning at any depth and in any one of said set of wafers, plates or substrates in said layered
configuration.

15. The process of claim 10 wherein said target may be comprised of one or a set of
transparent wafers, plates or substrates in a layered configuration; and

wherein machining of said target is the drilling of stopped or through orifices
25 beginning at any depth and in any one of said set of wafers, plates or substrates in said layered
configuration.

16. The process of claim 12 wherein said focusing assembly is selected such that said fluence level of said secondary focal waists are of sufficient intensity and number to ensure propagation of said photoacoustic compressive machining through a desired volume of said target.

17. The process of claim 10 wherein said laser pulses have a burst frequency appropriate so as to maintain a selected transient effect arising from an interaction of a previous pulse with said target, said laser pulses having a pulse width of less than about 10 nanoseconds.

18. The method according to claim 10 including applying a sacrificial layer to a surface of said material prior to the said application of burst of laser pulses.

19. A photo acoustic compression method for machining a transparent target material comprising the following steps:

applying at least one burst of laser pulses of a suitable wavelength, suitable burst pulse rep rate and suitable burst pulse energy from a laser source through a selected distributive-focus lens focusing assembly;

delivering said laser pulses to said target after adjustment of the relative distance and or angle of said distributive focus lens focusing assembly in relation to said laser source so as to focus said laser pulses in a distributed focus configuration so as to create a principal focal waist and at least one secondary focal waist, wherein said laser pulse energy delivered to said target exceeds a critical power level necessary to initiate a Kerr Effect induced self focusing

so that a filament is produced in the target and a photoacoustic compression machining is initiated and then propagated in the material by the additional energy input by the secondary focal waists, and wherein the level of total energy input is below the level required to initiate ablative or vaporization based machining of the target material.