

Description

This invention relates to a substituted benzene derivative used as a component of liquid crystal and a liquid crystal composition containing the same, having superior characteristics.

5 Display devices having applied liquid crystals are those utilizing an electrooptical effect based on the dielectric anisotropy and electroconductive anisotropy of liquid crystal substances. Liquid crystal display modes include various ones such as dynamic scattering mode, twist nematic mode, supertwist nematic mode, phase transition mode, DAP mode, guest-host mode, etc. Properties required for liquid crystal substances used for liquid crystal displays vary depending on the respective liquid crystal display modes, but a broad mesomorphic range, stability to moisture, air, light, heat, electricity, etc. are commonly required for any of the display modes. Further, it is also required that the response of display elements is rapid and the devices can be driven at a voltage as low as possible when the substances are used for liquid crystal display devices. At present, however, there is no single compound which satisfies all of such requirements, but there have been practically used liquid crystal mixtures obtained by mixing several kinds of liquid crystal compounds or mixing them with compounds similar to liquid crystals compounds.

Recently, in order to provide a liquid crystal display element having a good pictoreal quality even in a multiplex number of 100 or more, it has been proposed to change the cell structure having the twist angle of the helical structure of liquid crystal molecule, combined with the polarizing plate to a new mode (e.g. Japanese patent application laid-open Nos. Sho 60-50511/1985, Sho 60-50454/1985, etc.)

20 The object of the present invention is to provide a liquid crystal compound suitable for a liquid crystal composition for liquid crystal display elements, particularly suitable to the above new mode structure.


The liquid crystal elements of a cell structure having enlarged the twist angle of liquid crystal molecules exhibits an entirely different effect in the values of physical properties obtained by choice of liquid crystal materials, from the those in the case of conventional 90° twist. Characteristics of liquid crystal display elements having enlarged the twist angle are shown in Fig. 1, as compared with those in the case of conventional 90° twist. Figs. 1a and 1b each show the viewing angle-dependency of voltage-transmittance characteristics in the cases of 90° twist and 180° twist. As seen from Figs. 1a and 1b, the element having a 180° twist structure is steep in the decay characteristics (γ characteristics) of the transmittance by impressed voltage; thus it is evidently improved in the characteristics as compared with the case of conventional 90° twist. This tendency is notable with increase in the twist angle. As described above, since an element structure having enlarged the twist angle affords a steepness to the decay characteristics by impression of voltage, the difference between the transmittance by impression of voltage and that by non-impression of voltage at the time of multiplex drive becomes large, thus a higher multiplex drive than the conventional one becomes possible.

However, as to the relationship between the γ characteristics in the case of 90° twist and the γ characteristics in the case of about 200° twist, the same tendency is not exhibited depending on liquid crystal materials, but there has appeared a phenomenon which does not apply to the following report that, in general, the γ characteristics in the case of 90° twist are better when the ratio of the elastic constants (K_{33}/K_{11}) is smaller (Euro Display 84 "Liquid crystal properties in relation to multiplexing requirements", Gunter Baur). This is presumed to be related to the change of the elastic constant and other factors due to the enlargement of twist angle, but it has not yet been theoretically elucidated. Fig. 2 shows the relationship between the ratio of the elastic constants and γ characteristics in the case of 180° twist and that in the case of 230° twist, with two compounds i.e. a pyrimidine compound and a PCH (phenylcyclohexane) compound, respectively. As seen from this figure, the pyrimidine compound having a smaller elastic constant exhibits inferior results of γ characteristics to those of the PCH compound. As described above, in the case of about 200° twist, a conventional thought is not applied to; hence it is necessary to choose liquid crystal materials from an entirely different way of thinking from that in the case of 90° twist cell structure. As described above, by enlarging the twist angle or selecting liquid crystal materials, a liquid crystal material having superior γ characteristics is obtained. However, as shown in Fig. 3, by improving γ characteristics, it has been found that the better the γ characteristics of liquid crystal materials, the smaller the response rate. When the response properties are taken into consideration, choice of only materials having superior γ characteristics is not always sufficient, but in order to obtain a liquid crystal display element having superior response properties, while retaining superior γ characteristics to a certain extent, a method of reducing the thickness of the liquid crystal layer can be considered.


Thus, when the thickness of the liquid crystal layer is reduced in order to improve response properties, the Δn of the material should be varied according to the thickness of the liquid crystal layer. For example, in the case of 200° twist, the product of the Δn of liquid crystal material by the thickness d of the liquid crystal phase; $\Delta n \cdot d$ is best in the vicinity of 0.96 μm ; hence when the liquid crystal layer has a thickness d of 7 μm , the Δn of the material should be adjusted to 0.137. Further, in order to make the thickness d of the liquid crystal layer 5 μm for improving the response rate, it is necessary to increase the Δn value greatly up to 0.192. As

described above, in order to correspond to the reduction in the thickness of the liquid crystal layer, the Δn of the material should be increased, but this case is accompanied with a problem of viscosity. As to the relationship between the Δn and the viscosity of liquid crystal materials so far reported, there has been clarified a tendency that the viscosity increases with increase in the Δn . In such a situation, among conventional materials, those having a large Δn value and yet a low viscosity have been very few.

As examples of compounds having a large optical anisotropy (Δn) value, used as a component of liquid crystal materials, compounds expressed by the following formulas (1)-(6) have been disclosed in the following references, respectively:




wherein R^3 and R^4 each represent an alkyl group or an alkoxy group.




wherein




represents




and R^5 and R^6 each represent a linear alkyl group.




wherein R^7 represents a linear alkyl group and X represents a halogen atom.



wherein R^8 and R^9 each represent a linear alkyl group.



wherein R^{10} and R^{11} each represent a linear alkyl group.



wherein R^{12} and R^{13} each represent a linear alkyl group.

(1) French patent application laid-open No. 2,141,438 (corresponding U.S. patent No. 3,925,482)

(2) Japanese patent application laid-open No. Sho 60-152427/1985 (corresponding U.S. patent No. 4,705,905)

(3) Japanese patent application laid-open No. Sho 61-260031/1986

(4) Japanese patent application laid-open No. Sho 60-204731 (1985) (corresponding U.S. patent No. 4,705,905)

(5) Japanese patent application laid-open No. Sho 58-110527 (1983) (corresponding to U.S. patent No. 4,528,114)


(6) Ditto

These tolan derivatives are said to have a large Δn value and a relatively low viscosity, but recently, those far exceeding the characteristics of these compounds are required.

SUMMARY OF THE INVENTION

The present invention resides in

a 4-substituted-4'-(1-alkynyl)tolan expressed by the formula (I)



wherein R^1 and R^2 each represent an alkyl group of 1 to 8 carbon atoms and one CH_2 group or two CH_2 groups not adjacent therein may be replaced by any one of O atom, $-\text{CO}-$ group, $-\text{CO}-\text{O}-$ group, $-\text{O}-\text{CO}-$ group or $-\text{CH}=\text{CH}-$ group; - A - represents unsubstituted 1,4-phenylene, 1,4-phenylene having one or two F, Cl or Br atoms or CN groups as substituents, 1,4-cyclohexylene, pyrimidine-2,5-diyl or 1,3-dioxane-2,5-diyl; X represents $-\text{COO}-$, $-\text{OCO}-$, $-\text{CH}_2\text{CH}_2-$, $-\text{OCH}_2-$, $-\text{CH}_2\text{O}-$, $-\text{CH}=\text{CH}-$ or a single bond; n represents 0 or 1 and when n represents 0, X represents a single bond; and Y represents H or F, and a liquid crystal composition containing the compound of the formula (I).

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1a shows a chart illustrating the angle-dependency of the voltage-transmittance characteristics of an element exhibiting a twist angle of 90° .

Fig. 1b shows a chart illustrating the angle-dependency of the voltage-transmittance characteristics of element exhibiting a twist angle of 180° .









Fig. 2 shows a chart illustrating the respective relationships between the ratio of elastic constants and γ characteristics of elements of 180° twist angle and 230° twist angle.

Fig. 3 shows a chart illustrating the relationship between the γ characteristics and the decay response rate of a conventional liquid crystal material.

Herein, $\gamma_{10^\circ 80\% \rightarrow 20\%}$ refers to γ characteristics in terms of a ratio of a voltage at a transmittance of 80% to that at a transmittance of 20°C at an angle of 10° against the normal.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENTS






The compound of the formula (I) includes compounds of the following formulas Ia to Ih as preferred compounds:



In these formulas, R^1 , R^2 , -A- and Y are as defined above.

Among the compounds of the above formulas, those of the formulas Ia, Ib, Ic and Ie are preferred. Further, among these compounds, those of the formulas Iba, Ibb, Ica, Icb and Iea in the following formulas are partic-

ularly preferred.




30 In the compounds of the above formulas, as to alkyl groups R^1 and R^2 , one CH_2 group or two $-CH_2$ groups not adjacent, present therein may be replaced by any one of O atom, $-CO$ group, $-CO-O-$ group, $-O-CO-$ group or $CH=CH-$ group, and the alkyl groups may be branched chain alkyl groups.

R^1 and R^2 are each preferably linear and have 1 to 8 carbon atoms. Further, R^2 is particularly preferred to be a linear, normal alkyl group the $-CH_2$ group in which is not replaced by O atom.

35 Compounds of the formula (I) having branched side chain groups R^1 and R^2 have an improved solubility in conventional liquid crystal base materials; hence they are important in some cases, and when they are optically active, they are important as a chiral dopant. The branched chain groups of such kind generally have at least one chain branch.

40 Among the compounds of the present invention, for example, two-ring compounds expressed by the formula Ia have an optical anisotropy Δn value as very large as about 0.35 and further a viscosity at $20^\circ C$ as low as about 22 cp and hence have well-balanced characteristics for liquid crystal materials. Hence it is possible to increase the Δn value of the liquid crystal composition containing the compound of the present invention without raising the viscosity of the composition.

45 Next, an embodiment of the production process of the compound of the present invention will be illustrated by the following equation:



In the above equation, R¹, R², -A-, n, X and Y are as defined above.

Namely, a substituted-phenylacetylene (II) obtained according to a known method (Chem. Ber., 89, 1755 (1956)) is reacted with a 4-(1-alkynyl)iodobenzene (IV) in the presence of a palladium catalyst such as bis(triphenylphosphine)palladium dichloride and copper iodide in a solvent of diethylamine according to a method of a literature (Tetrahedron Letters No. 50, pp 4467-70 (1975)), followed by purification according to a conventional method, to obtain the aimed compound of the formula (I).

The liquid crystal composition of the present invention consists of 2 to 25 kinds, preferably 3 to 15 kinds of components containing at least one member of the compound expressed by the formula (I). Components other than the compound of the formula (I) are preferred to be nematic liquid crystal substances. Examples of known compounds among such substances are particularly azoxybenzene compounds, benzyldeneaniline compounds, biphenyl compounds, terphenyl compounds, phenyl or cyclohexyl benzoate compounds, phenyl or cyclohexyl cyclohexanecarboxylate compounds, phenylcyclohexane compounds, cyclohexylbiphenyl compounds, cyclohexylcyclohexane compounds, cyclohexylnaphthalene compounds, 1,4-biscyclohexylbenzene compounds, 4,4'-biscyclohexylbiphenyl compounds, phenylpyrimidine compounds, cyclohexylpyrimidine compounds, phenylpyridazine compounds or cyclohexylpyridazine compounds, N-oxide compounds thereof, phenyldioxane compounds, cyclohexyldioxane compounds, phenyl-1,3-dithian compounds, cyclohexyl-1,3-dithian compounds, 1,2-diphenylethane compounds, 1-phenyl-2-cyclohexyl-ethane compounds, 1,2-dicyclohexylethane compounds, and in some cases, halogenated stilbene compounds, benzyl phenyl ether compounds, tolan compounds, substituted cinnamic acid compounds, etc.

Among these compounds, important compounds may be expressed by the formula



wherein L and E each represent carbocyclic or heterocyclic compounds belonging to groups consisting of 1,4-di-substituted benzenes, cyclohexane ring 4,4'-di-substituted biphenyls, phenylcyclohexanes, cyclohexylcyclohexanes, phenylbicyclohexanes, 2,5-di-substituted naphthalenes, dihydronaphthalenes, tetrahydronaphthalenes, quinazoline and tetrahydroquinazoline; G represents -CH=CH-, -N(O)=N-, -CH=CY-, -CH=N(O)-, -C=C-, -CH₂-CH₂-, -CO-O-, -CH₂O-, -CO-S-, -CH₂S-, -CH=N-, -COO-Phe-COO- or C-C single bond, Y representing a halogen (preferably chlorine) atom or -CN; and R' and R'' each represent alkyl, alkoxy, alkanoyloxy, alkoxycarbonyl or alkoxycarbonyloxy each of up to 18 carbon atoms, preferably up to 8 carbon atoms, or either one of R' and R'' represents CN, NC, NO₂, CF₃, F, Cl, or Br.

In most of these compounds, R' and R'' are different from each other, and either one of these groups represents, in most cases, an alkyl group or an alkoxy group. In these compounds, conventional substituents for these groups are usable. Most of the substances expressed by the formula (I') and mixtures thereof are commercially available. All of these substances can be obtained according to known methods disclosed in literatures.

The composition of the present invention contains at least one member of the compound of the formula (I) in a content of about 0.1 to 40% by weight based on the composition. A liquid crystal composition of the present invention containing at least one member of the compound of the formula (I) in a quantity of 10 to 30% by weight is particularly preferred.

The composition of the present invention itself is prepared in a conventional manner. In general, the constituting components are dissolved in one another, preferably at an elevated temperature.

Further, a superior liquid crystal element is provided using the compound of the present invention. Such an element is characterized in that a nematic liquid crystal having a positive dielectric anisotropy value and having a rotatory polarization substance added, is sealed between a pair of upper and lower electrode substrates opposed to each other; liquid crystal molecules form a 160-270°-twisted, helical structure in the thickness direction thereof; the polarization axis of polarizing plates provided placing the helical structure there-

between deviates within a range of 20 to 70° against the direction of liquid crystal molecule arrangement in the electrode substrates; the product of the thickness of the liquid crystal layer (d) by the optical anisotropy value of the liquid crystal layer (Δn), that is, $\Delta n \times d$, is in the range of 0.7 to 1.2 μm ; and a liquid crystal composition containing 0.1 to 40% by weight based on the composition, of at least one member of the tolan compound of the present invention.

The present invention will be described in more detail by way of Examples, but it should not be construed to be limited thereto. In Examples, CI point represents crystal-isotropic liquid phase transition point and NI point represents nematic phase-isotropic liquid phase transition point. All temperatures refer to °C.

Example 1

Preparation of 4-propyl-4'-(1-propynyl)tolan

4-Propylphenylacetylene (7.21 g, 0.05 mol) and 4-(1-propynyl)iodobenzene (12.1 g, 0.05 mol) were dissolved in diethylamine (30 cc), and then added copper iodide (0.29 g, 1.5 mmol) and dichlorobis(triphenyl)phosphinepalladium dichloride (0.53 g, 0.75 mmol). The resulted mixture was reacted with stirring in nitrogen gas current at about 20°C for 8 hours. After completion of the reaction, Water (100 ml) was added to the resulting reaction mixture. The resulting deposited mass was extracted with toluene (50 ml). The resulting toluene solution was washed with dilute hydrochloric acid, followed by water until the washing water became neutral. The resulting material was dried over anhydrous sodium sulfate. Toluene was distilled off from the toluene solution. The residue was then dissolved in a mixed solvent of n-hexane/methylene chloride (1 vol./1 vol.). The solution was subjected to column chromatography using silica gel as a fixed phase, and using the above mixed solvent as an eluent. Fractions showing a single spot were collected by TLC and the mixed solvent was distilled. The residue after distillation was recrystallized from ethyl alcohol (20 ml) to obtain the objective 4-propyl-4'-(1-propynyl)tolan (compound No. 1) (6.7 g). This compound exhibited liquid crystal phases (CI point: 87.7°C, NI point: 85.1°C).

The following compounds are prepared in the same manner as above:

Compound No. 2	4-ethyl-4'-(1-propynyl)tolan
No. 3	4-ethyl-4'-(1-butynyl)tolan
No. 4	4-ethyl-4'-(1-pentynyl)tolan
No. 5	4-ethyl-4'-(1-hexynyl)tolan
No. 6	4-ethyl-4'-(1-heptynyl)tolan
No. 7	4-ethyl-4'-(1-octynyl)tolan
No. 8	4-ethyl-4'-(1-nonynyl)tolan
No. 9	4-ethyl-4'-(1-decynyl)tolan
No.10	4-propyl-4'-(1-butynyl)tolan
No.11	4-propyl-4'-(1-pentynyl)tolan
No.12	4-propyl-4'-(1-hexynyl)tolan
No.13	4-propyl-4'-(1-heptynyl)tolan
No.14	4-propyl-4'-(1-octynyl)tolan
No.15	4-propyl-4'-(1-nonynyl)tolan
No.16	4-propyl-4'-(1-decynyl)tolan
No.17	4-butyl-4'-(1-propynyl)tolan
No.18	4-butyl-4'-(1-butynyl)tolan
No.19	4-butyl-4'-(1-pentynyl)tolan
No.20	4-butyl-4'-(1-hexynyl)tolan
No.21	4-butyl-4'-(1-heptynyl)tolan
No.22	4-butyl-4'-(1-octynyl)tolan
No. 23	4-butyl-4'-(1-nonynyl)tolan
No. 24	4-butyl-4'-(1-decynyl)tolan
No. 25	4-pentyl-4'-(1-propynyl)tolan

	No. 26	4-pentyl-4'-(1-butyryl)tolan (Cl point: 80.8°C, NI point: 46.1°C)
	No. 27	4-pentyl-4'-(1-pentyryl)tolan (Cl point: 76.2°C, NI point: 50.3°C)
5	No. 28	4-pentyl-4'-(1-hexyryl)tolan (Cl point: 75.4°C)
	No. 29	4-pentyl-4'-(1-heptyryl)tolan
	No. 30	4-pentyl-4'-(1-octyryl)tolan
10	No. 31	4-pentyl-4'-(1-nonyryl)tolan
	No. 32	4-pentyl-4'-(1-decyryl)tolan
	No. 33	4-hexyl-4'-(1-propyryl)tolan
	No. 34	4-hexyl-4'-(1-butyryl)tolan
	No. 35	4-hexyl-4'-(1-pentyryl)tolan
15	No. 36	4-hexyl-4'-(1-hexyryl)tolan
	No. 37	4-hexyl-4'-(1-heptyryl)tolan
	No. 38	4-hexyl-4'-(1-octyryl)tolan
	No. 39	4-hexyl-4'-(1-nonyryl)tolan
	No. 40	4-hexyl-4'-(1-decyryl)tolan
20	No. 41	4-heptyl-4'-(1-propyryl)tolan
	No. 42	4-heptyl-4'-(1-butyryl)tolan
	No. 43	4-heptyl-4'-(1-pentyryl)tolan
	No. 44	4-heptyl-4'-(1-hexyryl)tolan
	No. 45	4-heptyl-4'-(1-heptyryl)tolan
25	No. 46	4-heptyl-4'-(1-octyryl)tolan
	No. 47	4-heptyl-4'-(1-nonyryl)tolan
	No. 48	4-heptyl-4'-(1-decyryl)tolan
	No. 49	4-octyl-4'-(1-propyryl)tolan
	No. 50	4-octyl-4'-(1-butyryl)tolan
30	No. 51	4-octyl-4'-(1-pentyryl)tolan
	No. 52	4-octyl-4'-(1-hexyryl)tolan
	No. 53	4-octyl-4'-(1-heptyryl)tolan
	No. 54	4-octyl-4'-(1-octyryl)tolan
	No. 55	4-octyl-4'-(1-nonyryl)tolan
35	No. 56	4-octyl-4'-(1-decyryl)tolan

Example 2

Preparation of 4-(trans-4-propylcyclohexyl)-4'-(1-propyryl)tolan

40 Trans-4-propylcyclohexylphenylacetylene (2.3 g, 0.01 mol) and 4-(1-propyryl)iodobenzene (2.4 g, 0.01 mol) were dissolved in diethylamine (20 ml), and then added copper iodide (0.11 g, 0.15 mmol) and dichlorobis(triphenylphosphine)palladium dichloride (0.21 g, 0.3 mmol). The resulting mixture was subjected to reaction and purification operation in the same manner as in Example 1 to obtain the objective 4-(trans-4-propylcyclohexyl)-4'-(1-propyryl)tolan (compound No. 57) (1.8 g). (CS point: 118.9°C, SN point: 127.4°C, NI point: 245.1°C)

45 The following compounds are prepared in the same manner as above:

	Compound No. 58	4-(trans-4-ethylcyclohexyl)-4'-(1-propyryl)tolan
	No. 59	4-(trans-4-ethylcyclohexyl)-4'-(1-butyryl)tolan
	No. 60	4-(trans-4-ethylcyclohexyl)-4'-(1-pentyryl)tolan
50	No. 61	4-(trans-4-ethylcyclohexyl)-4'-(1-hexyryl)tolan
	No. 62	4-(trans-4-ethylcyclohexyl)-4'-(1-heptyryl)tolan
	No. 63	4-(trans-4-ethylcyclohexyl)-4'-(1-octyryl)tolan
	No. 64	4-(trans-4-ethylcyclohexyl)-4'-(1-nonyryl)tolan
	No. 65	4-(trans-4-ethylcyclohexyl)-4'-(1-decyryl)tolan
55	No. 66	4-(trans-4-propylcyclohexyl)-4'-(1-butyryl)tolan
	No. 67	4-(trans-4-propylcyclohexyl)-4'-(1-pentyryl)tolan
	No. 68	4-(trans-4-propylcyclohexyl)-4'-(1-hexyryl)tolan
	No. 69	4-(trans-4-propylcyclohexyl)-4'-(1-heptyryl)tolan
	No. 70	4-(trans-4-propylcyclohexyl)-4'-(1-octyryl)tolan

	No. 71	4-(trans-4-propylcyclohexyl)-4'-(1-nonyl)tolan
	No. 72	4-(trans-4-propylcyclohexyl)-4'-(1-decyl)tolan
	No. 73	4-(trans-4-butylcyclohexyl)-4'-(1-propyl)tolan
5	No. 74	4-(trans-4-butylcyclohexyl)-4'-(1-butyl)tolan
	No. 75	4-(trans-4-butylcyclohexyl)-4'-(1-pentyl)tolan
	No. 76	4-(trans-4-butylcyclohexyl)-4'-(1-hexyl)tolan
	No. 77	4-(trans-4-butylcyclohexyl)-4'-(1-heptyl)tolan
	No. 78	4-(trans-4-butylcyclohexyl)-4'-(1-octyl)tolan
10	No. 79	4-(trans-4-butylcyclohexyl)-4'-(1-nonyl)tolan
	No. 80	4-(trans-4-butylcyclohexyl)-4'-(decyl)tolan
	No. 81	4-(trans-4-pentylcyclohexyl)-4'-(propyl)tolan
	No. 82	4-(trans-4-pentylcyclohexyl)-4'-(butyl)tolan
	No. 83	4-(trans-4-pentylcyclohexyl)-4'-(1-pentyl)tolan
15	No. 84	4-(trans-4-pentylcyclohexyl)-4'-(1-hexyl)tolan
	No. 85	4-(trans-4-pentylcyclohexyl)-4'-(1-heptyl)tolan
	No. 86	4-(trans-4-pentylcyclohexyl)-4'-(1-octyl)tolan
	No. 87	4-(trans-4-pentylcyclohexyl)-4'-(1-nonyl)tolan
	No. 88	4-(trans-4-pentylcyclohexyl)-4'-(1-decyl)tolan
20	No. 89	4-(trans-4-hexylcyclohexyl)-4'-(1-propyl)tolan
	No. 90	4-(trans-4-hexylcyclohexyl)-4'-(1-butyl)tolan
	No. 91	4-(trans-4-hexylcyclohexyl)-4'-(1-pentyl)tolan
	No. 92	4-(trans-4-hexylcyclohexyl)-4'-(1-hexyl)tolan
	No. 93	4-(trans-4-hexylcyclohexyl)-4'-(1-heptyl)tolan
25	No. 94	4-(trans-4-hexylcyclohexyl)-4'-(1-octyl)tolan
	No. 95	4-(trans-4-hexylcyclohexyl)-4'-(1-nonyl)tolan
	No. 96	4-(trans-4-hexylcyclohexyl)-4'-(1-decyl)tolan
	No. 97	4-(trans-4-heptylcyclohexyl)-4'-(1-propyl)tolan
	No. 98	4-(trans-4-heptylcyclohexyl)-4'-(1-butyl)tolan
30	No. 99	4-(trans-4-heptylcyclohexyl)-4'-(1-pentyl)tolan
	No. 100	4-(trans-4-heptylcyclohexyl)-4'-(1-hexyl)tolan
	No. 101	4-(trans-4-heptylcyclohexyl)-4'-(1-heptyl)tolan
	No. 102	4-(trans-4-heptylcyclohexyl)-4'-(1-octyl)tolan
	No. 103	4-(trans-4-heptylcyclohexyl)-4'-(1-nonyl)tolan
35	No. 104	4-(trans-4-heptylcyclohexyl)-4'-(1-decyl)tolan
	No. 105	4-(trans-4-octylcyclohexyl)-4'-(1-propyl)tolan
	No. 106	4-(trans-4-octylcyclohexyl)-4'-(1-butyl)tolan
	No. 107	4-(trans-4-octylcyclohexyl)-4'-(1-pentyl)tolan
	No. 108	4-(trans-4-octylcyclohexyl)-4'-(1-hexyl)tolan
40	No. 109	4-(trans-4-octylcyclohexyl)-4'-(1-heptyl)tolan
	No. 110	4-(trans-4-octylcyclohexyl)-4'-(1-octyl)tolan
	No. 111	4-(trans-4-octylcyclohexyl)-4'-(1-nonyl)tolan
	No. 112	4-(trans-4-octylcyclohexyl)-4'-(1-decyl)tolan
	No. 113	2-fluoro-4-(trans-4-propylcyclohexyl)-4'-(1-propyl)tolan
45	No. 114	2-fluoro-4-(trans-4-propylcyclohexyl)-4'-(1-butyl)tolan
	No. 115	2-fluoro-4-(trans-4-propylcyclohexyl)-4'-(1-pentyl)tolan
	No. 116	2-fluoro-4-(trans-4-butylcyclohexyl)-4'-(1-propyl)tolan
	No. 117	2-fluoro-4-(trans-4-butylcyclohexyl)-4'-(1-butyl)tolan
	No. 118	2-fluoro-4-(trans-4-butylcyclohexyl)-4'-(1-pentyl)tolan
50	No. 119	2-fluoro-4-(trans-4-pentylcyclohexyl)-4'-(1-propyl)tolan
	No. 120	2-fluoro-4-(trans-4-pentylcyclohexyl)-4'-(1-butyl)tolan
	No. 121	2-fluoro-4-(trans-4-pentylcyclohexyl)-4'-(1-pentyl)tolan
	No. 121-2	2-fluoro-4-(trans-4-pentylcyclohexyl)-4'-(1-hexyl)tolan (CS point: 51.3°C, SN point: 102.2°C, and NI point: 201.3°C)

55

Example 3

Preparation of 4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-propyl)tolan

4-[2-(Trans-4-propylcyclohexyl)ethyl]phenylacetylene (2.54 g, 0.01 mol) and 4-(1-propyl)iodobenzene

(2.4 g, 0.01 mol) were dissolved in diethylamine (20 ml), and then added copper iodide (0.11 g, 0.15 mmol) and dichlorobis(triphenylphosphine)palladium dichloride (0.21 g, 0.3 mmol). The resulting mixture was subjected to reaction and purification operations in the same manner as in Example 1, to obtain the objective 4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-propynyl)tolan (compound No. 122) (1.6 g).

The following compounds are prepared in the same manner as above:

No. 123	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
No. 124	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 125	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
10 No. 126	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 127	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 128	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
No. 129	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 130	4-[2-(trans-4-ethylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
15 No. 131	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 132	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
No. 133	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 134	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 135	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
20 No. 136	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 137	4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
No. 138	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
No. 139	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 140	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
25 No. 141	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 142	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
No. 143	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 144	4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
No. 145	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
30 No. 146	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 147	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
No. 148	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 149	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 150	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
35 No. 151	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 152	4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
No. 153	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
No. 154	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 155	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
40 No. 156	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 157	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 158	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
No. 159	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 160	4-[2-(trans-4-hexylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
45 No. 161	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
No. 162	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
No. 163	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
No. 164	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 165	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
50 No. 166	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
No. 167	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan
No. 168	4-[2-(trans-4-heptylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
No. 169	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
No. 170	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
55 No. 171	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
No. 172	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-hexynyl)tolan
No. 173	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-heptynyl)tolan
No. 174	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-octynyl)tolan
No. 175	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-nonynyl)tolan

	No. 176	4-[2-(trans-4-octylcyclohexyl)ethyl]-4'-(1-decynyl)tolan
	No. 177	2-fluoro-4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
	No. 178	2-fluoro-4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
5	No. 179	2-fluoro-4-[2-(trans-4-propylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
	No. 180	2-fluoro-4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
	No. 181	2-fluoro-4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
	No. 182	2-fluoro-4-[2-(trans-4-butylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan
	No. 183	2-fluoro-4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-propynyl)tolan
10	No. 184	2-fluoro-4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-butynyl)tolan
	No. 185	2-fluoro-4-[2-(trans-4-pentylcyclohexyl)ethyl]-4'-(1-pentynyl)tolan

Example 4

15 Preparation of 4-(4-propylphenyl)-4'-(1-propynyl)tolan

4-Ethynyl-4'-propylbiphenyl (prepared according to the method disclosed in Japanese patent application laid-open No. Sho 58-110527/1983) (2.2 g, 0.01 mol) and 4-(1-propynyl)iodobenzene (2.4 g, 0.01 mol) were dissolved in diethylamine (20 ml), and then added copper iodide (0.11 g, 0.15 mmol) and dichlorobis(triphenylphosphine)palladium dichloride (0.21 g, 0.3 mmol). The resulting mixture was subjected to reaction and purification operation in the same manner as in Example 1, to obtain the objective 4-(4-propylphenyl)-4'-(1-propynyl)tolan (compound No. 186) (1.7 g).

The following compounds are prepared in the same manner as above:

	Compound No. 187	4-(4-ethylphenyl)-4'-(1-propynyl)tolan
	No. 188	4-(4-ethylphenyl)-4'-(1-butynyl)tolan
25	No. 189	4-(4-ethylphenyl)-4'-(1-pentynyl)tolan
	No. 190	4-(4-ethylphenyl)-4'-(1-hexynyl)tolan
	No. 191	4-(4-propylphenyl)-4'-(1-butynyl)tolan
	No. 192	4-(4-propylphenyl)-4'-(1-pentynyl)tolan
	No. 193	4-(4-propylphenyl)-4'-(1-hexynyl)tolan
30	No. 194	4-(4-butylphenyl)-4'-(1-propynyl)tolan
	No. 195	4-(4-butylphenyl)-4'-(1-butynyl)tolan
	No. 196	4-(4-butylphenyl)-4'-(1-pentynyl)tolan
	No. 197	4-(4-butylphenyl)-4'-(1-hexynyl)tolan
	No. 198	4-(4-pentylphenyl)-4'-(1-propynyl)tolan
35	No. 199	4-(4-pentylphenyl)-4'-(1-butynyl)tolan
	No. 200	4-(4-pentylphenyl)-4'-(1-pentynyl)tolan
	No. 201	4-(4-pentylphenyl)-4'-(1-hexynyl)tolan
	No. 202	4-(4-hexylphenyl)-4'-(1-propynyl)tolan
	No. 203	4-(4-hexylphenyl)-4'-(1-butynyl)tolan
40	No. 204	4-(4-hexylphenyl)-4'-(1-pentynyl)tolan
	No. 205	4-(4-hexylphenyl)-4'-(1-hexynyl)tolan
	No. 206	4-(4-heptylphenyl)-4'-(1-propynyl)tolan
	No. 207	4-(4-heptylphenyl)-4'-(1-butynyl)tolan
	No. 208	4-(4-heptylphenyl)-4'-(1-pentynyl)tolan
45	No. 209	4-(4-heptylphenyl)-4'-(1-hexynyl)tolan
	No. 210	4-(4-octylphenyl)-4'-(1-propynyl)tolan
	No. 211	4-(4-octylphenyl)-4'-(1-butynyl)tolan
	No. 212	4-(4-octylphenyl)-4'-(1-pentynyl)tolan
	No. 213	4-(4-octylphenyl)-4'-(1-hexynyl)tolan
50	No. 214	2-fluoro-4-(4-propylphenyl)-4'-(1-propynyl)tolan
	No. 215	2-fluoro-4-(4-propylphenyl)-4'-(1-butynyl)tolan
	No. 216	2-fluoro-4-(4-propylphenyl)-4'-(1-pentynyl)tolan
	No. 217	2-fluoro-4-(4-butylphenyl)-4'-(1-propynyl)tolan
	No. 218	2-fluoro-4-(4-butylphenyl)-4'-(1-butynyl)tolan
55	No. 219	2-fluoro-4-(4-butylphenyl)-4'-(1-pentynyl)tolan
	No. 220	2-fluoro-4-(4-pentylphenyl)-4'-(1-propynyl)tolan
	No. 221	2-fluoro-4-(4-pentylphenyl)-4'-(1-butynyl)tolan
	No. 222	2-fluoro-4-(4-pentylphenyl)-4'-(1-pentynyl)tolan

Example 5**Preparation of 4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan**

5 Trans-4-propylcyclohexanecarboxylic acid-p-ethylphenyl ester (which can be obtained by subjecting 4-hydroxyphenylacetylene obtained from 4-hydroxyacetophenone as a raw material and trans-4-propylcyclohexanecarboxylic acid to esterification reaction in a conventional manner) (2.7 g, 0.01 mol) and 4-(1-propynyl)iodobenzene (2.4 g, 0.01 mol) were dissolved in diethylamine (20 ml), and then added copper iodide (0.11 g, 0.15 mmol) and dichlorobis(triphenylphosphine)palladium dichloride (0.21 g, 0.3 mmol). The resulting mixture was subjected to reaction and purification operation in the same manner as in Example 1 to obtain the objective 4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan (compound No. 223) (1.3 g).

The following compounds are obtained in the same manner as above:

No. 224	4-(trans-4-ethylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 225	4-(trans-4-ethylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
15 No. 226	4-(trans-4-ethylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 227	4-(trans-4-ethylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
No. 228	4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 229	4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 230	4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
20 No. 231	4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 232	4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 233	4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 234	4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
No. 235	4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
25 No. 236	4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 237	4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 238	4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
No. 239	4-(trans-4-hexylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 240	4-(trans-4-hexylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
30 No. 241	4-(trans-4-hexylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 242	4-(trans-4-hexylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
No. 243	4-(trans-4-heptylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 244	4-(trans-4-heptylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 245	4-(trans-4-heptylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
35 No. 246	4-(trans-4-heptylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
No. 247	4-(trans-4-octylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 248	4-(trans-4-octylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 249	4-(trans-4-octylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 250	4-(trans-4-octylcyclohexylcarbonyloxy)-4'-(1-hexynyl)tolan
40 No. 251	2-fluoro-4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 252	2-fluoro-4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 253	2-fluoro-4-(trans-4-propylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 254	2-fluoro-4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 255	2-fluoro-4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
45 No. 256	2-fluoro-4-(trans-4-butylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 257	2-fluoro-4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-propynyl)tolan
No. 258	2-fluoro-4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-butynyl)tolan
No. 259	2-fluoro-4-(trans-4-pentylcyclohexylcarbonyloxy)-4'-(1-pentynyl)tolan
No. 260	4-(4-ethylbenzoyloxy)-4'-(1-propynyl)tolan
50 No. 261	4-(4-ethylbenzoyloxy)-4'-(1-butynyl)tolan
No. 262	4-(4-ethylbenzoyloxy)-4'-(1-pentynyl)tolan
No. 263	4-(4-ethylbenzoyloxy)-4'-(1-hexynyl)tolan
No. 264	4-(4-propylbenzoyloxy)-4'-(1-propynyl)tolan
No. 265	4-(4-propylbenzoyloxy)-4'-(1-butynyl)tolan
55 No. 266	4-(4-propylbenzoyloxy)-4'-(1-pentynyl)tolan
No. 267	4-(4-propylbenzoyloxy)-4'-(1-hexynyl)tolan
No. 268	4-(4-butylbenzoyloxy)-4'-(1-propynyl)tolan
No. 269	4-(4-butylbenzoyloxy)-4'-(1-butynyl)tolan
No. 270	4-(4-butylbenzoyloxy)-4'-(1-pentynyl)tolan

	No. 271	4-(4-butylbenzoyloxy)-4'-(1-hexynyl)tolan
	No. 272	4-(4-pentylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 273	4-(4-pentylbenzoyloxy)-4'-(1-butynyl)tolan
5	No. 274	4-(4-pentylbenzoyloxy)-4'-(1-pentynyl)tolan
	No. 275	4-(4-pentylbenzoyloxy)-4'-(1-hexynyl)tolan
	No. 276	4-(4-hexylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 277	4-(4-hexylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 278	4-(4-hexylbenzoyloxy)-4'-(1-pentynyl)tolan
10	No. 279	4-(4-hexylbenzoyloxy)-4'-(1-hexynyl)tolan
	No. 280	4-(4-heptylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 281	4-(4-heptylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 282	4-(4-heptylbenzoyloxy)-4'-(1-pentynyl)tolan
	No. 283	4-(4-heptylbenzoyloxy)-4'-(1-hexynyl)tolan
15	No. 284	4-(4-octylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 285	4-(4-octylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 286	4-(4-octylbenzoyloxy)-4'-(1-pentynyl)tolan
	No. 287	4-(4-octylbenzoyloxy)-4'-(1-hexynyl)tolan
	No. 288	2-fluoro-4-(4-propylbenzoyloxy)-4'-(1-propynyl)tolan
20	No. 289	2-fluoro-4-(4-propylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 290	2-fluoro-4-(4-propylbenzoyloxy)-4'-(1-pentynyl)tolan
	No. 291	2-fluoro-4-(4-butylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 292	2-fluoro-4-(4-butylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 293	2-fluoro-4-(4-butylbenzoyloxy)-4'-(1-pentynyl)tolan
25	No. 294	2-fluoro-4-(4-pentylbenzoyloxy)-4'-(1-propynyl)tolan
	No. 295	2-fluoro-4-(4-pentylbenzoyloxy)-4'-(1-butynyl)tolan
	No. 296	2-fluoro-4-(4-pentylbenzoyloxy)-4'-(1-pentynyl)tolan

Example 6

30

Preparation of 4-methoxy-4'-(1-propynyl)tolan

4-Methoxyphenyl acetylene (2.65 g, 0.02 mol) and 4-(1-propynyl)iodobenzene (5.0 g, 0.02 mol) were dissolved in diethylamine (20 ml), and then added copper iodide (0.06 g) and dichlorobis(triphenylphosphine)ladium dichloride (0.21 g). The resulting mixture was subjected to reaction and purification operations in the same manners as in Example 1, to obtain the objective 4-methoxy-4'-(1-propynyl)tolan (No. 297) (1.35 g).

35

The following compounds are prepared in the same manner as above:

	No. 298	4-methoxy-4'-(1-butynyl)tolan
	No. 299	4-methoxy-4'-(1-pentynyl)tolan
	No. 300	4-methoxy-4'-(1-hexynyl)tolan
40	No. 301	4-methoxy-4'-(1-heptynyl)tolan
	No. 302	4-methoxy-4'-(1-octynyl)tolan
	No. 303	4-methoxy-4'-(1-nonynyl)tolan
	No. 304	4-methoxy-4'-(1-decynyl)tolan
	No. 305	4-ethoxy-4'-(1-propynyl)tolan
45	No. 306	4-ethoxy-4'-(1-butynyl)tolan
	No. 307	4-ethoxy-4'-(1-pentynyl)tolan
	No. 308	4-ethoxy-4'-(1-hexynyl)tolan
	No. 309	4-ethoxy-4'-(1-heptynyl)tolan
	No. 310	4-ethoxy-4'-(1-octynyl)tolan
50	No. 311	4-ethoxy-4'-(1-nonynyl)tolan
	No. 312	4-ethoxy-4'-(1-decynyl)tolan
	No. 313	4-propoxy-4'-(1-butynyl)tolan
	No. 314	4-propoxy-4'-(1-pentynyl)tolan
	No. 315	4-propoxy-4'-(1-hexynyl)tolan
55	No. 316	4-propoxy-4'-(1-heptynyl)tolan
	No. 317	4-propoxy-4'-(1-octynyl)tolan
	No. 318	4-propoxy-4'-(1-nonynyl)tolan
	No. 319	4-propoxy-4'-(1-decynyl)tolan
	No. 320	4-butoxy-4'-(1-propynyl)tolan

	No. 321	4-butoxy-4'-(1-butylnyl)tolan
	No. 322	4-butoxy-4'-(1-pentylnyl)tolan
	No. 323	4-butoxy-4'-(1-hexylnyl)tolan
5	No. 324	4-butoxy-4'-(1-heptylnyl)tolan
	No. 325	4-butoxy-4'-(1-octylnyl)tolan
	No. 326	4-butoxy-4'-(1-nonylnyl)tolan
	No. 327	4-butoxy-4'-(1-decylnyl)tolan
	No. 328	4-pentyloxy-4'-(1-propylnyl)tolan
10	No. 329	4-pentyloxy-4'-(1-butylnyl)tolan
	No. 330	4-pentyloxy-4'-(1-pentylnyl)tolan
	No. 331	4-pentyloxy-4'-(1-hexylnyl)tolan
	No. 332	4-pentyloxy-4'-(1-heptylnyl)tolan
	No. 333	4-pentyloxy-4'-(1-octylnyl)tolan
15	No. 334	4-pentyloxy-4'-(1-nonylnyl)tolan
	No. 335	4-pentyloxy-4'-(1-decylnyl)tolan
	No. 336	4-hexyloxy-4'-(1-propylnyl)tolan
	No. 337	4-hexyloxy-4'-(1-butylnyl)tolan
	No. 338	4-hexyloxy-4'-(1-pentylnyl)tolan
20	No. 339	4-hexyloxy-4'-(1-hexylnyl)tolan
	No. 340	4-hexyloxy-4'-(1-heptylnyl)tolan
	No. 341	4-hexyloxy-4'-(1-octylnyl)tolan
	No. 342	4-hexyloxy-4'-(1-nonylnyl)tolan
	No. 343	4-hexyloxy-4'-(1-decylnyl)tolan
25	No. 344	4-heptyloxy-4'-(1-propylnyl)tolan
	No. 345	4-heptyloxy-4'-(1-butylnyl)tolan
	No. 346	4-heptyloxy-4'-(1-pentylnyl)tolan
	No. 347	4-heptyloxy-4'-(1-hexylnyl)tolan
	No. 348	4-heptyloxy-4'-(1-heptylnyl)tolan
30	No. 349	4-heptyloxy-4'-(1-octylnyl)tolan
	No. 350	4-heptyloxy-4'-(1-nonylnyl)tolan
	No. 351	4-heptyloxy-4'-(1-decylnyl)tolan
	No. 352	4-octyloxy-4'-(1-propylnyl)tolan
	No. 353	4-octyloxy-4'-(1-butylnyl)tolan
35	No. 354	4-octyloxy-4'-(1-pentylnyl)tolan
	No. 355	4-octyloxy-4'-(1-hexylnyl)tolan
	No. 356	4-octyloxy-4'-(1-heptyl)tolan
	No. 357	4-octyloxy-4'-(1-octylnyl)tolan
	No. 358	4-octyloxy-4'-(1-nonylnyl)tolan
40	No. 359	4-octyloxy-4'-(1-decylnyl)tolan

Example 7 (Use example 1)

A liquid crystal composition A consisting of

45

50

55

A	C_3H_7		C_4H_9	27.6 wt.parts
	C_4H_9		C_2H_5	20.7 "
	C_5H_{11}		CH_3	20.7 "
	C_3H_7		C_2H_5	17.2 "
	C_5H_{11}		C_2H_5	13.8 "

has an NI point of 72.4°C, a viscosity at 20°C η_{20} of 20.1 cp and a Δn of 0.087. A liquid crystal composition B obtained by adding 15 parts by weight of 4-propyl-4'-(1-propynyl)tolan shown in Example 1 of the present invention to 85 parts by weight of the composition A had an NI point of 72.0°C and a η_{20} of 20.0 cp, that is, these values were almost unchanged, but the Δn value rose up to 0.126.

Example 8 (Use example 2)

A liquid crystal composition C consisting of

C	C_3H_7		CN	30 wt.parts
	C_5H_{11}		CN	40 "
	C_9H_{15}		CN	30 "

has an NI point of 52.3°C, a viscosity at 20°C η_{20} of 21.7 cp and a Δn of 0.119. A liquid crystal composition D obtained by adding 15 parts by weight of 4-propyl-4'-(1-pentynyl)tolan (compound No. 11 of the present invention shown above) to 85 parts by weight of the liquid crystal composition C had an NI point of 49.6°C (that is, slightly lowered) and a η_{20} of 21.7 (that is, unchanged), but the Δn rose up to 0.137.


As seen from these Use examples, the compound of the present invention has a very large effect of making reduction in the NI point of the liquid crystal composition obtained by using the compound as small as possible, without raising the viscosity, but raising the optical anisotropy value Δn .

According to the present invention, it is possible to obtain a liquid crystal compound and a liquid crystal composition having a large optical anisotropy Δn value and yet a low viscosity, and besides, having well-balanced characteristics as liquid crystal materials for display.



Claims


1. 4-Substituted-4'-(1-alkynyl)tolans of the formula:



wherein R¹ and R² each represent a C₁-C₈ alkyl group in which one CH₂ group or two non-adjacent CH₂ groups may be replaced by an O atom, -CO- group, -CO-O-group, -O-CO- group or -CH=CH- group; -A- represents an unsubstituted 1,4-phenylene group, a 1,4-phenylene having one or two F, Cl or Br atoms or CN groups as substituents, a 1,4-cyclohexylene group, a pyrimidine-2,5-diyl group or a 1,3-dioxane-2,5-diyl group; X represents a group -COO-, -OCO-, -CH₂CH₂-, -OCH₂-, -CH₂O- or -CH=CH- or a single bond; n is 0 or 1 (and when n is 0, X represents a single bond); and Y is H or F.

2. A tolan compound according to claim 1 wherein n is 0 and X represents a single bond.

3. A tolan compound according to claim 1, wherein n is 1, -A- represents



and X represents a single bond.

4. A tolan compound according to claim 1, wherein n is 1, -A- represents



and X represents a single bond.

5. A tolan compound according to claim 1, wherein n is 1, -A- represents




and X represents a group -COO-.

6. A tolan compound according to claim 1, wherein n is 1, -A- represents



and X represents a group -COO-.

7. A tolan compound according to claim 1, wherein n is 1, -A- represents



and X represents a group -CH₂-CH₂.




8. A liquid crystal composition comprising at least two components, at least one of which is a tolan compound as claimed in any one of the preceding claims.

9. A liquid crystal element, wherein a nematic liquid crystal having a positive dielectric anisotropy value, together with an added rotatory polarization substance, is sealed between a pair of opposed upper and lower electrode substrates; liquid crystal molecules form a 160-170° - twisted, helical structure in the thickness direction thereof; the polarization axis of polarizing plates provided placing the helical structure therebetween deviates within 20 to 70° from the direction of liquid crystal molecule arrangement in the electrode substrates; the product of the thickness of the liquid crystal layer (d) times the optical anisotropy value of the liquid crystal layer ($\Delta n \times d$) is from 0.7 to 1.2 μm ; a liquid crystal composition containing 0.1 to 40% by weight of a tolan compound as claimed in claim 1, being provided in the liquid crystal element.

Patentansprüche

1. In 4-Position substituiertes 4'-(1-Alkynyl)-tolan der Formel:



worin R^1 und R^2 jeweils eine C_1 - C_8 -Alkylgruppe repräsentieren, in welcher eine CH_2 -Gruppe oder zwei nicht-benachbarte CH_2 -Gruppen durch ein Sauerstoffatom, eine -CO-Gruppe, eine -CO-O-Gruppe, eine -O-CO-Gruppe oder eine -CH=CH-Gruppe ersetzt sein können;

worin -A- eine unsubstituierte 1,4-Phenylengruppe, eine 1,4-Phenylengruppe mit einem oder zwei Fluor-, Chlor- oder Bromatomen oder CN-Gruppen als Substituenten, eine 1,4-Cyclohexylengruppe, eine Pyrimidin-2,5-diylgruppe oder eine 1,3-Dioxan-2,5-diylgruppe repräsentiert;

worin X eine -COO-, -OCO-, - CH_2CH_2 -, - OCH_2 -, - CH_2O - oder -CH=CH-Gruppe oder eine Einfachbindung repräsentiert;

worin n gleich 0 oder 1 ist (und wenn n gleich 0 ist, X eine Einfachbindung repräsentiert); und worin Y gleich H oder F ist.

2. Tolanverbindung nach Anspruch 1, worin n gleich 0 ist und X eine Einfachbindung repräsentiert.

3. Tolanverbindung nach Anspruch 1, worin n gleich 1 ist, -A- für



steht und X eine Einfachbindung repräsentiert.

4. Tolanverbindung nach Anspruch 1, worin n gleich 1 ist, -A- für



steht und X eine Einfachbindung repräsentiert.

5. Tolanverbindung nach Anspruch 1, worin n gleich 1 ist, -A- für





steht und X eine -COO-Gruppe repräsentiert.

6. Tolanverbindung nach Anspruch 1, worin n gleich 1 ist, - $\textcircled{A}$ - für



steht und X eine -COO-Gruppe repräsentiert.

7. Tolanverbindung nach Anspruch 1, worin n gleich 1 ist, - $\textcircled{A}$ - für




steht und X eine -CH₂CH₂-Gruppe repräsentiert.

8. Flüssigkristallzusammensetzung mit mindestens zwei Komponenten, von denen mindestens eine eine Tolanverbindung nach einem der voranstehenden Ansprüche ist.

9. Flüssigkristallelement, worin ein nematisches Flüssigkristall, welches einen positiven dielektrischen Anisotropiewert aufweist, zusammen mit einer zugegebenen Rotationspolarisationsverbindung zwischen einem Paar sich gegenüberliegenden oberen und unteren Elektrodensubstraten eingesiegelt ist; wobei die Flüssigkristallmoleküle eine um 160 bis 170° verdrehte Helixstruktur in Richtung des Abstandes (der Dicke) bilden; wobei die Polarisations-Achse von vorgesehenen Polarisationsplatten, welche die Helixstruktur zwischen sich aufnehmen, innerhalb des Bereichs von 20 bis 70° von der Richtung der Flüssigkristallmolekülanordnung in den Elektrodensubstraten abweicht; wobei das Produkt der Dicke der Flüssigkristallschicht (d) und des optischen Anisotropiewerts der Flüssigkristallschicht ($\Delta n \times d$) von 0,7 bis 1,2 μm beträgt; wobei eine Flüssigkristallzusammensetzung 0,1 bis 40 Gew. % einer Tolanverbindung gemäß Anspruch 1 enthält, in der Flüssigkristallelement enthalten ist.

Revendications

1. 4'-(1-alcynyl)tolane-4-substitué de la formule:



dans lequel R¹ et R² représentent chacun un groupement alkyle en C₁-C₈ dans lequel un groupement CH₂ ou deux groupements CH₂ non adjacents peuvent être remplacés par un atome O, un groupement -CO-, un groupement -CO-O-, un groupement -O-CO- ou un groupement -CH=CH-; - $\textcircled{A}$ - représente un groupement 1,4-phénylène non substitué, un 1,4-phénylène ayant un ou deux atomes de F, Cl ou Br ou groupements CN comme substituants, un groupement 1,4-cyclohexylène, un groupement pyrimidine-2,5-diyle ou un groupement 1,3-dioxane-2,5-diyle; X représente un groupement -COO-, -OCO-, -CH₂CH₂-, OCH₂-, -CH₂O- ou -CH=CH- ou une liaison simple; n est 0 ou 1 (et, lorsque n est 0, X représente une liaison simple); et Y est H ou F.

2. Composé du tolane selon la revendication 1, dans lequel n est 0 et X représente une liaison simple.
3. Composé du tolane selon la revendication 1, dans lequel n est 1, - $\textcircled{A}$ - représente



5

et X représente une liaison simple.

4. Composé du tolane selon la revendication 1, dans lequel n est 1, - A - représente

10



et X représente une liaison simple.

15

5. Composé du tolane selon la revendication 1, dans lequel n est 1, - A - représente



20

et X représente un groupement $-\text{COO}-$.

6. Composé du tolane selon la revendication 1, dans lequel n est 1, - A - représente

25



et X représente un groupement $-\text{COO}-$.

30

7. Composé du tolane selon la revendication 1, dans lequel n est 1, - A - représente



35

et X représente un groupement $-\text{CH}_2\text{CH}_2-$.

8. Composition liquide cristalline comprenant au moins deux composants dont un au moins est un composé du tolane tel que revendiqué dans l'une quelconque des revendications précédentes.

40

9. Élément liquide cristallin dans lequel un liquide cristallin nématique ayant une valeur d'anisotropie diélectrique positive en même temps qu'avec une substance avec polarisation rotatoire ajoutée est scellée entre une paire d'électrodes supérieure et inférieure opposées; les molécules liquides cristallines forment une structure hélicoïdale avec un angle de torsion de $160-170^\circ$ dans la direction de son épaisseur; l'axe de polarisation des plaques de polarisation disposées de manière à placer entre elles la structure hélicoïdale dévie de 20 à 70° par rapport à la direction de l'arrangement moléculaire du liquide cristallin dans les substrats des électrodes; le produit de l'épaisseur de la couche de liquide cristallin (d) par la valeur de l'anisotropie optique de la couche de liquide cristallin ($\Delta n \times d$) est compris entre 0.7 et $1.2 \mu\text{m}$; la composition liquide cristalline contenant de 0.1 à 40% en poids d'un composé du tolane tel que revendiqué dans la revendication 1 étant fourni dans l'élément liquide cristallin.

45

50

55