CLAIMS

1. Use of an adhesive composition in an immunosensor, said composition comprising:

an adhesive;

water;

a poloxamer; and

an anticoagulant.

2. An adhesive composition for use in an immunosensor, said composition comprising:

an adhesive;

water;

a poloxamer; and

an anticoagulant,

wherein

the composition is disposed on a sheet;

the concentration of the poloxamer with respect to the adhesive is approximately in the range of about 0.05 to about 0.5 percent;

the anticoagulant is selected from the group consisting of: citrate and oxalate; or

the adhesive is a sulfopolyster.

3. The use of claim 1 or adhesive composition of claim 2, wherein the anticoagulant is selected from the group consisting of: heparin, citrate, ethylenediaminetetraacetic acid, and oxalate.

4. The use of claim 1 or adhesive composition of claim 2, wherein the poloxamer comprises units derived from ethylene oxide and propylene oxide.

5. The use of claim 1 or adhesive composition of claim 4, wherein ethylene oxide and propylene oxide serve as the monomers in block copolymers.

6. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is pressure-sensitive.

7. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is heat-activated.

8. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is water soluble.

9. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is a sulfopolyester.

10. The use of claim 1 or adhesive composition of claim 2, wherein a concentration of the poloxamer with respect to the adhesive is approximately in the range of about 0.05 to about 0.5 percent.

11. The use of claim 3 or adhesive composition of claim 3, wherein a concentration of the heparin with respect to the adhesive is approximately in the range of about 0.1 to about 10 milligrams per milliliter.

12. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive and the water are combined to form a mixture prior to being included with the poloxamer and the anticoagulant.

CLAIMS

1. Use of an adhesive composition in an immunosensor, said composition comprising:

   an adhesive;

   water;

   a poloxamer; and

   an anticoagulant.

2. An adhesive composition for use in an immunosensor, said composition comprising:

   an adhesive;

   water;

   a poloxamer; and

   an anticoagulant,

   wherein the composition is disposed on a sheet.

3. The use of claim 1 or adhesive composition of claim 2, wherein the anticoagulant is selected from the group consisting of: heparin, citrate, ethylenediaminetetraacetic acid, and oxalate.

4. The use of claim 1 or adhesive composition of claim 2, wherein the poloxamer comprises units derived from ethylene oxide and propylene oxide.

5. The use of claim 1 or adhesive composition of claim 4, wherein ethylene oxide and propylene oxide serve as the monomers in block copolymers.

6. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is pressure-sensitive.

7. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is heat-activated.

8. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is water soluble.

9. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive is a sulfopolyester.

10. The use of claim 1 or adhesive composition of claim 2, wherein a concentration of the poloxamer with respect to the adhesive is approximately in the range of about 0.05 to about 0.5 percent.

11. The use of claim 3 or adhesive composition of claim 3, wherein a concentration of the heparin with respect to the adhesive is approximately in the range of about 0.1 to about 10 milligrams per milliliter.

12. The use of claim 1 or adhesive composition of claim 2, wherein the adhesive and the water are combined to form a mixture prior to being included with the poloxamer and the anticoagulant.