

**A GRINDING TOOL FOR TRAPEZOID
GRINDING OF A WAFER**

FIELD

[0001] This disclosure relates to semiconductor and solar wafers such as silicon on insulator (SOI) bonded structures, and more particularly to a grinding tool for grinding a bonded SOI wafer.

BACKGROUND

[0002] Semiconductor wafers are generally prepared from a single crystal ingot (e.g., a silicon ingot) which is sliced into individual wafers. While reference will be made herein to semiconductor wafers constructed from silicon, other materials may be used as well, such as germanium, gallium arsenide or other materials described below. One type of wafer is a silicon-on-insulator (SOI) wafer. An SOI wafer includes a thin layer of silicon (an active layer) atop an insulating layer (i.e., an oxide layer) which is in turn disposed on a silicon substrate. A bonded SOI semiconductor wafer is a type of SOI structure.

[0003] Due to device width shrink, power conservation, super-high speed performance, and/or special applications in electronic industry, the demands on SOI (silicon on insulator) wafers are increasing. One challenge is to effectively remove the unbonded outer peripheral portion of an active layer wafer bonded to the support substrate in order to avoid delamination. Delamination can result in particle contamination in the process and/or device lines of the wafer.

[0004] When manufacturing an SOI wafer, outer peripheral portions of the two wafers to be bonded are subjected to R or T chamfering, or edge profiling (as further described below), in order to prevent wafer breakage, cracks and/or particle generation. Also, outer peripheral portions of a bonded substrate have uneven thickness due to wafering steps. Because of this uneven thickness, during the bonding process, the outer peripheral portion is either not bonded at all and/or weakly bonded. When an active wafer thickness is reduced with processes such as grinding, etching, polishing, etc., this unbonded portion is partially delaminated from the bonded substrate during the film thickness reducing processes. The delaminated parts cause problems for film thickness reduction, cleaning, and measurement processes. Furthermore, in device processes, the remaining unbonded portions are delaminated, which causes particle generation and severely impacts device yields.

[0005] There have been several prior art attempts to solve delamination. For example, Figures 1A-1D show a progression of steps for bonding a substrate wafer S and an active layer wafer A to each other and then chamfering the edge peripheral portion of the bonded wafer W. Figure 1A shows the substrate below the active layer wafer, and Figure 1B shows the bonded wafers. Figure 1C shows a grinder G grinding the outer peripheral edges of the wafers, and Figure 1D shows the complete SOI wafer W (note that the complete wafer is further processed). This method is believed to be substantively similar to that shown in Japanese Patent Application No. 1986-256621. Among other drawbacks of this example, the diameter of the wafer W is smaller than the standard wafer diameter, which

causes problems for the downstream handling facilities and jigs.

[0006] In another prior art example shown in Figures 2A-2D, a bonded SOI wafer W is formed as described above from an active layer wafer A and a substrate wafer S. The wafer edges are ground as shown in Figures 2B-2C such that the entire outer edge of the active wafer A is ground off, but only a portion of substrate is ground off. This method is believed to be substantively similar to that shown in Japanese Patent Application No. 1989-227441. This method suffers from poor efficiency.

[0007] In the prior art example shown in Figure 3A, the active wafer A is ground at its edges to form a ledge L (wafer A is thus a pre-ground wafer). The wafer A is bonded to substrate wafer S in Figure 3B. In figure 3C, the top surface of the bonded SOI wafer W is ground to remove the ledge L, and the complete wafer is shown in Figure 3D. The unbonded portion of the active layer wafer can thereafter be ground down. This method is believed to be substantively similar to that shown in Japanese Patent Application No. 1992-85827.

[0008] In prior art Figure 4A, a bonded SOI wafer W is formed as described above from an active layer wafer A and a substrate wafer S. In Figure 4B, the active wafer A is ground at its upper peripheral edge E to form the ledge L shown in Figure 4C. To complete the wafer processing of Figure 4D, selective etching, polishing and/or PAC (plasma assisted chemical etching) processes are used to remove the unbonded parts from the outer peripheral edge of the active layer wafer A. This method is believed to be substantively similar to that shown in

US Patent 6,534,384 B2, which is incorporated herein by reference. As can be seen, many steps are required to form the complete wafer.

[0009] In prior art Figure 5A, the active layer wafer A includes a groove R formed in its lower surface prior to bonding. The active wafer A is bonded to the substrate wafer S in Figure 5B. This method is believed to be substantively similar to that shown in US Patent Application 2009/0203167 A1, which is incorporated herein by reference. In Figure 5C, grinding is performed on wafer A on the opposite side from the groove R. The unbonded portion of the outer peripheral portion of the wafer A can be removed after grinding the wafer to predetermined thickness, as shown in the complete wafer W of Figure 5D.

[0010] There remains an unfulfilled need for a wafer surface treatment method and a wafer that addresses the disadvantages of current methods of preventing delamination of the outer peripheral portion of an active layer of a bonded structure.

BRIEF SUMMARY

[0011] In one aspect, a grinding tool for trapezoid grinding of a wafer on a profiling machine comprises an annular wheel including a central hole adapted for mounting the wheel on a spindle. The wheel includes at least two grooves disposed at an outer edge of the wheel and the grooves are sized for receiving an outer edge of the wafer. At least one of the grooves is adapted for rough grinding of the wafer. At least one other of the grooves is adapted for fine grinding of the wafer.

[0012] In another aspect, the wheel of the grinding tool includes three or more grooves disposed at an outer edge of the wheel and the grooves are sized for receiving an outer edge of the wafer. At least one of the grooves is adapted for rough grinding of the wafer and at least one other of the grooves is adapted for fine grinding of the wafer. Each groove is sized and shaped so that only the upper peripheral edge of the wafer is ground.

[0013] In still another aspect, a grinding tool for grinding of a wafer on a profiling machine comprises an annular wheel including a central hole adapted for mounting the wheel on a spindle. The wheel includes three or more grooves disposed at an outer edge of the wheel and the grooves are sized for receiving an outer edge of the wafer. One groove is for rough grinding of the wafer and at least two grooves are for fine grinding of the wafer. Each groove has a V-shape in cross-section and is sized relative to the wafer so that only the upper peripheral edge of the wafer is ground.

[0014] Various refinements exist of the features noted in relation to the above-mentioned aspects. Further features may also be incorporated in the above-mentioned aspects as well. These refinements and additional features may exist individually or in any combination. For instance, various features discussed below in relation to any of the illustrated embodiments may be incorporated into any of the above-described aspects, alone or in any combination.

BRIEF DESCRIPTION OF THE DRAWINGS

[0015] Figures 1A-5D are side views showing prior art methods of making an SOI wafer.

[0016] Figure 6 is a flowchart showing a method of manufacturing an SOI wafer according to one embodiment.

[0017] Figures 7A-7E are a progression of side views showing aspects of the method of manufacturing of Figure 6.

[0018] Figure 8 is a flowchart showing a method of manufacturing an SOI wafer according to another embodiment.

[0019] Figures 9A-9D are a progression of side views showing aspects of the method of manufacturing of Figure 8.

[0020] Figures 10 and 11 show a grinding wheel of one embodiment for performing a trapezoid grinding step.

[0021] Figure 12 is a side view of an SOI wafer aligned with a groove of the grinding wheel of Figure 10.

[0022] Figure 13 is an enlarged view of an SOI wafer after trapezoid grinding.

[0023] The figures are not to scale, and portions are enlarged for illustrative purposes. Corresponding reference characters indicate corresponding parts throughout the figures.

DETAILED DESCRIPTION

[0024] Referring now to Figure 6 and to 7A-7E, a method 100 of manufacturing or processing a bonded wafer (alternatively, a silicon-on-insulator structure or SOI wafer) is shown. An active wafer 101 and a substrate wafer 103, such as those shown in Fig 7A, are conventional wafers. Both have mirror-polished front surfaces 101F, 103F and are relatively defect-free.

[0025] Active wafer 101 and substrate wafer 103 may be any single crystal semiconductor material suitable for use in an SOI structure. In general, the wafers may be composed of a material selected from the group consisting of silicon, germanium, gallium arsenide, silicon germanium, gallium nitride, aluminum nitride, phosphorous, sapphire and combinations thereof. In one embodiment, the wafers 101, 103 are made of silicon.

[0026] A layer of oxide is deposited 102 on the front surface of the active wafer. Oxidation is typically performed in a vertical furnace, e.g. commercially available AMS400. The front surface of the wafer is then bonded 104 to the front surface of the substrate wafer to form a bonded wafer 105 as shown in Fig 7B. Bonding can be performed in a conventional hydrophilic bonding process using a tool such as Model EVG® 850 from EV Group of Austria. Heat treatment 106 is suitably performed in an electric oven (such as model Blue M from TPS of Pennsylvania) to strengthen the bond. The next step, trapezoid grinding 108 is further described below with reference to Fig. 7C. Surface grinding 110, shown in Fig. 7D is suitably performed using a single side grinder, such as in model DFG-830 from Disco Corporation

of Japan. The surface grinding 110 suitably includes a rough grinding step and a fine grinding step. Rough grinding is suitably performed using a 600 mesh with 20-30 microns grit size, and fine grinding is 3000 mesh and grit size of 2-6 microns.

[0027] Referring again to Fig. 6, etching 112 is next performed on the bonded wafer 105, and is suitably performed in a conventional etching apparatus using an alkali etchant, though an acid etchant may also be used. Polishing 114 is then performed and is suitably a single-side polishing on front surface 105F using a Strasbaugh Mark 9-K. Alternatively, the polishing 114 may be a double-side polishing of both the front surface 105F and back surface 105B. Finishing 116 of the bonded wafer 105 includes inspecting the wafer for all required parameters, such as flatness and particle count, and then packaging the wafer for shipment to customers.

[0028] As can be seen from Figures 7E and 13, the finished or bonded wafer 105 has an upper portion having a trapezoid shape. More specifically, the upper portion including the remainder of the active layer wafer 101 and a relatively small portion of the substrate wafer is angled at the outer peripheral edge portion so that the wafer is said to have a trapezoid shape or a trapezoid shape in cross-section. Note the lower portion of the bonded wafer 105 (which corresponds substantially to the substrate wafer 103 in this embodiment) has a conventional bevel or rounded shape (broadly, a curved shape) at its outer peripheral edge and thus does not have a trapezoid shape. The upper portion of the bonded wafer 105 is

substantially coincident with the active wafer 101 in this embodiment.

[0029] Referring again to Fig. 7C, an outer peripheral edge of the active wafer 101 is brought into contact with the grinding wheel and is ground at an angle relative to the front surface 105F of the bonded wafer 105. The angle is suitably between about 3° and 10°, and in this embodiment the angle is about 7°. The edge grinding is performed until the entire outer peripheral edge is ground as shown in Figure 7D. The grinding eliminates any notch in the outer peripheral edge. The grinding may suitably be done such that the length of the angled or sloped portion is between about 1 mm and 1.5 mm, e.g. about 1.25 mm. Note that the angle and depth of grind is such that a small portion of the top bevel 119 of the substrate wafer 103 is removed during the trapezoid grinding.

[0030] In Figure 7C, the surface of the active wafer 101 is ground until it has a thickness of 40-50 microns, as shown in Figure 7D. Note the trapezoid shape of the active wafer 101 in Figure 7D. Also, the edge grind is performed such that a portion of the substrate wafer 103 is ground.

[0031] Referring to Figures 8 and 9A-9D, the grinding steps are reversed as compared to that of Figures 6 and 7A-7D. In other words, the surface of the active wafer 101 is ground first, before the trapezoid grinding. This order of steps is shown in Figure 8. Again, the surface grinding step may include a rough grinding step and a fine grinding step. Rough grinding is suitably performed using a 600 mesh and grit size of 20 to 30

microns, and fine grinding is 3000 mesh and grit size of 2 to 6 microns. The surface is ground as shown in Figure 9B, and then the edge of the active wafer 101 is next ground in Figure 9C until the edges have the trapezoid shape shown in Figure 9D.

[0032] Referring to Figures 10 and 11, a grinding wheel 151 (broadly, a trapezoid grinding tool) of one embodiment is designed for the performance of the trapezoid grinding 108. The wheel 151 is adapted to be mounted on a conventional edge profiling machine 152 that performs the trapezoid grinding. In this embodiment, the profiling machine is an STC EP-5800RHO machine adapted for 200 mm diameter wafers. The wheel 151 is mounted on a spindle 153 of the profiling machine 152.

[0033] The wheel 151 of this embodiment is ring-shaped or annular and has a central hole 154 adapted for mounting the wheel on the on the spindle 151 of the profiling machine 152. The wheel 151 has a diameter D of 202 mm with a central hole diameter HD of 30 mm and thickness of 20 mm. The wheel 151 of this embodiment has an upper groove 155, a central groove 157 and a lower groove 159 disposed at an outer edge of the wheel. The grooves 155, 157, 159 are generally V-shaped in this embodiment. Note that the wheel 151 may alternatively have just one groove, or practically any other number of grooves, within the scope of this disclosure.

[0034] In this embodiment, the upper and central grooves 155, 157 are adapted for fine grinding, and the lower groove 159 is adapted for rough grinding. Each groove suitably includes diamond grits. For fine grinding, diamond grit size of 2000 or 3000 mesh is

suitable. For rough grinding, 600 mesh or 800 mesh is suitable. The wheel 151 is suitably made of metal alloy, aluminum alloy, or stainless steel, though other materials are contemplated.

[0035] Each groove wall of this embodiment slopes from a bottom of the groove to a top of the groove and has a flat bottom. In this embodiment, the slope is at about a 7° angle. The width of the bottom of the groove is about 1.8 mm for use with a bonded wafer having a total thickness of about 200 mm, so that the substrate wafer or back surface of the wafer is not in contact with the groove during trapezoid grinding. The width of each groove at its widest portion (the top of the groove) is about 3.5 mm. The wall of the groove curves into the bottom of the groove at a radius of about 0.2 mm. The groove depth GD is about 6.0 mm and the groove root depth RD is about 8.0 mm.

[0036] The wheel 151 is installed on the edge profiling machine 152, such as on a spindle of the STC EP-5800 RHO. After wheel installation, spindle height (vertical direction) and distance (horizontal direction) are fine adjusted, so that groove 155 of the wheel 151 and the bonded wafer 105 are aligned as shown in Figure 12. Note that the outermost portion of substrate wafer edge and the bottom surface are not in contact with the grinding groove 155. Then, trapezoid grinding is performed as described above. Trapezoid grinding can be performed with either rough grit groove or fine grit groove or both grit grooves (first rough grit groove, then fine grit groove). The grinding may be performed as a

single pass or multiple pass process, depending, for example, on edge quality requirements.

[0037] The above example methods are applied to remove the unbonded outer peripheral parts of an active layer wafer bonded on a substrate wafer. This results in a bonded wafer having a more securely bonded outer peripheral portion. In a suitable method, after bonding of an active layer wafer onto a support substrate and post-bond heat treat of the bonded pairs, trapezoid grinding is applied to remove the unbonded outer peripheral portion of the active layer wafer. An edge grinding wheel such as wheel 151 may be used to perform the trapezoid grinding step. Among other advantages, the bonded wafer according to embodiments of this disclosure is less likely to suffer delamination. Additionally, the bonded wafer inhibits or prevents particle contamination that might otherwise occur due to delaminated unbonded portions on the process/device lines of the wafer.

[0038] When introducing elements of the present invention or the embodiment(s) thereof, the articles "a", "an", "the" and "said" are intended to mean that there are one or more of the elements. The terms "comprising", "including" and "having" are intended to be inclusive and mean that there may be additional elements other than the listed elements.

[0039] As various changes could be made in the above constructions without departing from the scope of the invention, it is intended that all matter contained in the above description and shown in the accompanying drawing[s] shall be interpreted as illustrative and not in a limiting sense.

WHAT IS CLAIMED IS:

1. A grinding tool for trapezoid grinding of a wafer on a profiling machine, the tool comprising:

an annular wheel including a central hole adapted for mounting the wheel on a spindle,

the wheel including at least two grooves disposed at an outer edge of the wheel, the grooves sized for receiving an outer edge of the wafer,

at least one of the grooves adapted for rough grinding of the wafer,

at least one other of the grooves adapted for fine grinding of the wafer.

2. The grinding tool of claim 1 wherein each groove is angled such that an upper peripheral edge of the wafer is ground and so that a lower peripheral edge of the wafer is not ground.

3. The grinding tool of claim 2 wherein the groove has an angle between about 3° and 10° and wherein the groove has a flat bottom so that only the upper peripheral edge of the wafer is ground.

4. The grinding tool of claim 2 wherein each groove has a V-shape in cross-section sized so that only the upper peripheral edge of the wafer is ground.

5. The grinding tool of claim 1 wherein the at least two grooves are disposed adjacent one another so that the wafer can be readily moved from groove to groove.

6. The grinding tool of claim 1 wherein the groove for rough grinding has a diamond grit size of about 600 to about 800 mesh, and the groove for fine grinding has a diamond grit size of about 2000 to about 3000 mesh.

7. The grinding tool of claim 1 wherein the wheel includes two grooves for fine grinding and one groove for rough grinding.

8. A grinding tool for grinding of a wafer on a profiling machine, the tool comprising:

an annular wheel including a central hole adapted for mounting the wheel on a spindle,

the wheel including three or more grooves disposed at an outer edge of the wheel, the grooves sized for receiving an outer edge of the wafer,

at least one of the grooves adapted for rough grinding of the wafer,

at least one other of the grooves adapted for fine grinding of the wafer, and

each groove sized and shaped so that only the upper peripheral edge of the wafer is ground.

9. The grinding tool of claim 8 wherein each groove is angled such that an upper peripheral edge of the wafer is ground and so that a lower peripheral edge of the wafer is not ground.

10. The grinding tool of claim 9 wherein the groove has an angle of about 7° and wherein the groove has a flat

bottom so that only the upper peripheral edge of the wafer is ground.

11. The grinding tool of claim 10 wherein each groove has a V-shape in cross-section.

12. The grinding tool of claim 11 wherein the grooves are disposed adjacent one another so that the wafer can be quickly moved from groove to groove.

13. The grinding tool of claim 1 wherein the groove for rough grinding has a diamond grit size of about 600 to about 800 mesh, and the groove for fine grinding has a diamond grit size of about 2000 to about 3000 mesh.

14. The grinding tool of claim 13 wherein the wheel includes two grooves for fine grinding and one groove for rough grinding.

15. A grinding tool for grinding of a wafer on a profiling machine, the tool comprising:

an annular wheel including a central hole adapted for mounting the wheel on a spindle,

the wheel including three or more grooves disposed at an outer edge of the wheel, the grooves sized for receiving an outer edge of the wafer,

one groove for rough grinding of the wafer,

at least two grooves for fine grinding of the wafer,
and

each groove having a V-shape in cross-section and sized relative to the wafer so that only the upper peripheral edge of the wafer is ground.

16. The grinding tool of claim 15 wherein the groove has an angle of about 7° and wherein the groove is a flat bottomed V-shape so that only the upper peripheral edge of the wafer is ground.

17. The grinding tool of claim 16 wherein the grooves are disposed adjacent one another so that the wafer can be quickly moved from groove to groove.

18. The grinding tool of claim 17 wherein the groove for rough grinding has a diamond grit size of about 600 to about 800 mesh, and the groove for fine grinding has a diamond grit size of about 2000 to about 3000 mesh.