

DESCRIPTION

KEYPAD MADE FROM THERMOPLASTIC POLYURETHANE RESIN AND METHOD FOR FORMING THEREOF

5

TECHNICAL FIELD

The present invention relates to a keypad of thermoplastic polyurethane resin and it's forming method.
10 More particularly, the present invention relates to a keypad of thermoplastic polyurethane resin excelling in secondary formability, oleic acid resistance, discoloration resistance, clarity, and printability, and it's forming method.

15

BACKGROUND ART

Thermoplastic polyurethane resin (TPU for short hereinafter) has long been used in a variety of applications including paint, adhesive, roll, tube, and binder for magnetic recoding medium. It also finds use as synthetic
20 leather, film, and molding sheet because of its better low-temperature properties, flexibility, and durability than other resins.

Among others, hot-molded TPU sheets are used as skin for automotive steering wheels and automotive instrument
25 panels, bust cups for brassieres and swimsuits, keypads for electronic machines and equipment, trays for electronic parts, air mats, water beds, and various protective cases.

Those hot-molded TPU sheets mentioned above are usually used in direct contact with the human body or in the
30 direct sunlight. Therefore, TPU for hot-molded sheets is required to have good secondary formability as well as oleic acid resistance and discoloration resistance. (Oleic acid resistance is a measure of resistance to human sweat.) It is also required to have good clarity and printability because
35 formed products often need a good appearance.

Patent Document 1 discloses a TPU sheet excelling in dry touch properties and oleic acid resistance. Also, Patent

Document 2 discloses a TPU powder for slush molding which is composed of adipate polyester and polycarbonate diol (PCD for short hereinafter).

Being produced from aromatic diisocyanate and organic solvent, the TPU disclosed in Patent Document 1 lacks discoloration resistance and poses a problem with environmental pollution with waste liquid and solvent vapor. In addition, slush molding is not suitable for precision molding.

Patent Document 1:

Japanese Patent Laid-Open No. 2001-187811

Patent Document 2:

Japanese Patent Laid-Open No. Hei 6-206973

The present invention was completed in view of the foregoing. It is an object of the present invention to provide a keypad of thermoplastic polyurethane resin excelling in secondary formability, oleic acid resistance, discoloration resistance, clarity, and printability.

DISCLOSURE OF INVENTION

The present invention covers a keypad of thermoplastic polyurethane resin excelling in secondary formability, oleic acid resistance, discoloration resistance, clarity, and printability. This object is achieved by using a TPU of specific composition.

The TPU disclosed in the present invention will find use not only as keypad but also as skin for automotive steering wheels and automotive instrument panels, bust cups for brassieres and swimsuits, keypads for electronic machines and equipment, trays for electronic parts, air mats, water beds, and various protective cases.

BRIEF DESCRIPTION OF DRAWINGS

Fig. 1 is a diagram showing the results of measurement of the viscoelastic properties of PU-2.

Legend of symbols:

○: Storage modulus (E')

□: Loss modulus (E'')

△: Loss modules (E'')/Storage modules (E') ($\tan \delta$)

5

BEST MODE FOR CARRYING OUT THE INVENTION

The present invention is directed to any one of the following.

(1) A keypad of TPU obtained from a TPU sheet by
10 thermoforming, wherein the TPU sheet is a melt-formed product of resin pellets resulting from reaction between an organic diisocyanate (A) composed mainly of hexamethylenediisocyanate (A1), a high-molecular weight polyol (B) composed mainly of polycarbonate diol (B1), and a chain extender (C) composed
15 mainly of an aliphatic diol (C1) having 2 to 10 carbons.

(2) A method for thermoforming a keypad which includes vacuum forming the TPU sheet defined in (1) above.

(3) A method for thermoforming a keypad which includes stamping the TPU sheet defined in (1) above.

20 A detailed description of the present invention will be given below.

The terms used in the present invention are defined as follows.

"Thermoformable sheet" is defined as a sheet of
25 synthetic resin which is to undergo thermoforming which includes vacuum forming, stamping, compressed-air forming, etc. "Primary forming" is defined as a step of forming a sheet from pellets. "Secondary forming" is defined as a step of forming a keypad from the sheet just mentioned above.

30 "Composed mainly of" means that each component, for example (A), contains its subcomponent, for example (A1) accounting for no less than 50 wt%.

The raw materials used in the present invention are described in the following.

35 The organic diisocyanate (A) used in the present invention is one which is composed mainly of hexamethylenediisocyanate (A1) (abbreviated as HDI

hereinafter). If the major component of the organic diisocyanate (A) is any other isocyanate than HDI (A1), the resulting TPU pellets will be poor in discoloration resistance and secondary formability. Incidentally, good secondary formability implies the capability of precision forming. The sheet of TPU pellets according to the present invention is applicable to the cover of small (palm-size) electronic instruments (e.g., the cover with key switches for card-type calculator and remote control for TV set and video deck).

In the present invention, the HDI (A1) may be used in combination with other organic diisocyanates exemplified below. 2,4-tolylenediisocyanate, 2,6-tolylenediisocyanate, xylene-1,4-diisocyanate, xylene-1,3-diisocyanate, tetramethylxylenediisocyanate, 4,4'-diphenylmethanediisocyanate, 2,4'-diphenylmethanediisocyanate, 2,2'-diphenylmethanediisocyanate, 4,4'-diphenyletherdiisocyanate, 2-nitrophenyl-4,4'-diisocyanate, 2,2'-diphenylpropane-4,4'-diisocyanate, 3,3'-dimethyldiphenylmethane-4,4'-diisocyanate, 4,4'-diphenylpropanediisocyanate, m-phenylenediisocyanate, p-phenylenediisocyanate, naphthylene-1,4-diisocyanate, naphthylene-1,5-diisocyanate, 3,3'-dimethoxydiphenyl-4,4'-diisocyanate, and other aromatic diisocyanates; tetramethylenediisocyanate, decamethylenediisocyanate, lysinediisocyanate, and other aliphatic diisocyanates; and isophoronediisocyanate, hydrogenated tolylenediisocyanate, hydrogenated xylenediisocyanate, hydrogenated diphenylmethanediisocyanate, hydrogenated tetramethylxylenediisocyanate, and other alicyclic diisocyanates.

The content of the subcomponent (A1) in the component (A) should be no less than 70 wt%, preferably no less than 80 wt%, so that the resulting TPU has good weather resistance, flexibility, and hand.

According to the present invention, the high-molecular weight polyol (B) is composed mainly of PCD (B1), which is

usually obtained from a low-molecular weight diol and a low-molecular weight carbonate by condensation reaction.

The low-molecular weight diol includes, for example, ethylene glycol, 1,3-proylene glycol, 1,2-propylene glycol, 5 1,2-butanediol, 1,3-butanediol, 1,4-butanediol (1,4-BD for short hereinafter), 2-methyl-1,3-propanediol, 1,5-pentanediol, 1,6-hexandiol (1,6-HD for short hereinafter), 3-methyl-1,5-pentanediol (MPD for short hereinafter), neopentylglycol, 1,8-octanediol, 1,9-nonanediol, 10 3,3-dimethylolheptane, diethylene glycol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, 2-ethyl-1,3-propanediol, 2-n-propyl-1,3-propanediol, 2-isopropyl-1,3-propanediol, 2-n-butyl-1,3-propanediol, 2-isobutyl-1,3-propanediol, 2-tert-butyl-1,3-propanediol, 2-methyl-2-ethyl-1,3-propanediol, 15 2,2-diethyl-1,3-propanediol, 2-ethyl-2-n-propyl-1,3-propanediol, 2-ethyl-2-n-butyl-1,3-propanediol, 2-ethyl-3-ethyl-1,4-butanediol, 2-methyl-3-ethyl-1,4-butanediol, 2,3-diethyl-1,5-pentanediol, 2,4-diethyl-1,5-pentanediol, 2,3,4-triethyl-1,5-pentanediol, 20 dimethylolpropionic acid, dimethylolbutanoic acid, dimer acid diol, and alkylene oxide adduct of bisphenol A. The low-molecular weight polyol constituting PCD should preferably be aliphatic low-molecular weight diols with 2 to 10 carbons so that the resulting TPU sheet has good clarity and printability. Of the low-molecular weight diols, MPD is 25 most desirable because the resulting TPU sheet exhibits good clarity and printability with very little bleeding.

The low-molecular weight carbonate includes dialkyl carbonate (such as dimethyl carbonate and diethyl carbonate), 30 diaryl carbonate (such as diphenyl carbonate), and alkylene carbonate (such as ethylene carbonate and propylene carbonate).

The high-molecular weight polyol (B) should have a number-average molecular weight of 500 to 5,000, preferably 35 1,000 to 3,000. With a number-average molecular weight smaller than 500 or larger than 5,000, the resulting TPU will be poor in flexibility or mechanical strength, respectively.

If the high-molecular weight polyol (B) has its major constituent replaced with any other high-molecular weight polyol than (B1), such as polyether polyol or polyester polyol, the resulting TPU will be poor in heat resistance or water resistance, respectively.

Any other high-molecular weight polyol than PCD (B1) that can be used in combination without decrease in durability includes, for example, polyester polyol, polyether polyol, polyether-ester polyol, and polyolefin polyol.

The chain extender (C) used in the present invention is composed mainly of aliphatic diol (C1) having 2 to 10 carbons. Examples of (C1) include ethylene glycol, 1,3-proylene glycol, 1,2-propylene glycol, 1,2-butanediol, 1,3-butanediol, 1,4-BD, 2-methyl-1,3-propanediol, 1,5-pentanediol, 1,6-HD, MPD, neopentylglycol, 1,8-octanediol, 1,9-nonanediol, 3,3-dimethylolheptane, diethylene glycol, 1,4-cyclohexanediol, 1,4-cyclohexanedimethanol, 2-ethyl-1,3-propanediol, 2-n-propyl-1,3-propanediol, 2-isopropyl-1,3-propanediol, 2-n-butyl-1,3-propanediol, 2-isobutyl-1,3-propanediol, 2-tert-butyl-1,3-propanediol, 2-methyl-2-ethyl-1,3-propanediol, 2,2-diethyl-1,3-propanediol, 2-ethyl-2-n-propyl-1,3-propanediol, 2-ethyl-2-n-butyl-1,3-propanediol, 2-ethyl-3-ethyl-1,4-butanediol, 2-methyl-3-ethyl-1,4-butanediol, 2,3-diethyl-1,5-pentanediol, and 2,4-diethyl-1,5-pentanediol. Of the above-mentioned examples, aliphatic diols having 2 to 6 carbons are preferable and 1,4-BD is most desirable, from the standpoint of the mechanical strength of the resulting TPU. If the chain extender (C) has its major component (C1) replaced with a low-molecular weight compound containing active hydrogen groups, the resulting TPU will be poor in formability (including secondary formability), clarity, and mechanical strength. Those chain extenders which can be used in addition to (C1) are low-molecular weight polyamines having a number-average molecular weight smaller than 500, such as ethylenediamine, hexamethylenediamine, xylylenediamine, isophoronediamine, and ethylenetriamine, and

low-molecular weight aminoalcohols having a number-average molecular weight smaller than 500, such as monoethanolamine, diethanolamine, and monopropanolamine.

TPU pellets for the keypad of the present invention
5 may be produced in any way without specific restrictions so long as they rely on the above-mentioned raw materials (A) to (C). They may be produced by any one of the following process which consists of: mixing the high-molecular weight polyol (B) and the chain extender (C) and then mixing the
10 resulting mixture with the organic diisocyanate (A); metering and vigorously mixing the above-mentioned raw materials, and pouring the resulting mixture into a vat for reaction therein at 50 to 200°C, preferably 60 to 160°C; kneading and polymerizing the above-mentioned raw materials in an extruder
15 at 80 to 250°C, preferably 120 to 250°C, and extruding the resulting TPU through a die; or supplying the above-mentioned raw materials all at once to a kneader for reaction therein at 80 to 250°C, preferably 120 to 230°C. The product obtained by the foregoing process is made into strand cut
20 pellets of TPU. If necessary, the processed materials may be recycled or aged for complete reaction. Extrusion is desirable for continuous production. TPU in pellet form gives off (1) no dust unlike powder, (2) facilitates storage and transportation unlike solvent solutions, and (3) permits
25 easy molding into various shapes.

A urethane-forming catalyst is not essential in the production of TPU pellets; however it should preferably be used to reduce reaction time and to ensure complete reaction. It is possible to use any common catalyst, such as organic
30 compounds or inorganic compounds of bismuth, lead, tin, iron, antimony, uranium, cadmium, cobalt, thorium, aluminum, mercury, zinc, nickel, cerium, molybdenum, vanadium, copper, manganese, zirconium, or calcium. Preferred catalysts are organometal compounds, particularly dialkyltin compounds.
35 Typical organotin catalysts include, for example, stannous octoate, stannous oleate, dibutyltin diacetate, dibutyltin dilaurate, dibutyltin maleate, dibutyltin mercaptopropionate,

and dibutyltin dodecylmercaptide. The amount of the catalyst may vary without restrictions, depending on the properties of raw materials, the reaction condition, and the reaction time. It is usually 0.0001 to 5 wt%, preferably about 0.001 to 2 wt%, of the total amount of the reaction mixture.

The polyol (B) and the chain extender (C) should be fed in a molar ratio (C)/(B) of from 0.5 to 5, particularly from 1 to 3. With an excessively small or large value of (C)/(B), the resulting TPU will be poor in mechanical strength or formability (including secondary formability), respectively.

The raw materials should be fed in such a way that the molar ratio of active hydrogen groups to isocyanate groups is equal to or larger than 0.8/1 and smaller than 1/1, preferably equal to or larger than 0.85/1 and equal to or smaller than 0.99/1. If the molar ratio is smaller than the lower limit, the resulting TPU will be poor in mechanical strength because of its small molecular weight. If the molar ratio is larger than the upper limit, the resulting TPU will be poor in appearance due to fish-eyes.

The thus obtained TPU should have a weight-average molecular weight of 5,000 to 1,000,000, preferably 10,000 to 500,000. It will be poor in strength or formability if its molecular weight is smaller or larger than these limits, respectively. Incidentally, the weight-average molecular weight is expressed in terms of that of polystyrene measured by gel permeation chromatography (GPC).

The TPU should have a hardness "A" of 70 to 98, preferably 80 to 95, as prescribed in JIS-K7311. Because of this hardness, TPU feels hard if it is in solid form but feels elastic if it is in thin form.

Incidentally, the TPU according to the present invention is exempt from fire protection law for its storage because it is produced without organic solvents. In addition, it does not cause environmental pollution during its fabrication.

The TPU of the present invention may be incorporated with a variety of additives such as slip agent, hydrolysis preventing agent, antioxidant, UV light absorber, UV light stabilizer, filler, and reinforcing fibers, if necessary.

5 The keypad of the present invention is produced by making the TPU pellets mentioned above into a film or sheet, 0.03 to 5 mm thick, and then forming the film or sheet into a desired shape by vacuum forming or stamping. In this way it is possible to easily obtain precision thin formings such as
10 keypad for electronic instruments.

Vacuum forming may be accomplished as follows. First, the sheet which has been made from the TPU as mentioned above is heated and softened. The softened sheet is brought into close contact with the mold under vacuum. After cooling, the
15 formed sheet is demolded and trimmed (if necessary). Stamping may be accomplished as follows. First, the sheet which has been made from the TPU as mentioned above is heated and softened. The softened sheet is clamped between female and male molds under vacuum. After cooling, the formed sheet
20 is demolded and trimmed (if necessary). In either case, the heating temperature of the sheet should preferably be 60 to 250° C.

EXAMPLES

25 The invention will be described in more detail with reference to the following examples and comparative examples, which are not intended to restrict the scope thereof. In Examples and Comparative Examples, "%" means "wt%".

30 [Preparation of thermoplastic polyurethane resin] Synthesis Example 1

A mixing tank (capable of temperature control) was charged with 932.3 kg of polyol A and 67.7 kg of 1,4-BD. After thorough mixing, the mixture liquid was heated to 60°C.
35 The mixture liquid was transferred to a head tank, in which it was heated to 75°C. The mixture liquid was continuously fed, together with HDI, to a twin-screw extruder having its

temperature adjusted as follows. A vicinity of hopper: 160°C, a middle part: 190°C, and a forward end: 225°C. The feeding rate of the mixture liquid was 2447 g/min, and the feeding rate of the HDI was 553 g/min. The molten resin was
 5 discharge through a strand die and the resulting strand was cut into pellets after cooling. After ageing at 25°C for 3 days, there was obtained a sample of thermoplastic polyurethane resin pellets which is designated as PU-1. The resin feed amount was 180 kg/h.

10

Synthesis Examples 2 to 5 and Synthesis Comparative Examples 1 to 3

The same procedure as in Synthesis Example 1 was repeated to give samples (PU-2 to PU-8) of thermoplastic
 15 polyurethane resin except that the formulation was changed as shown in Tables 1 and 2.

Table 1

		Synthesis Example				
		1	2	3	4	5
Mixing tank	High-molecular weight polyol (kg)					
	Polyol A	932.3	914.4			932.3
	Polyol B			857.3		
	Polyol C				857.3	
	Chain extender (kg)					
	1,4-BD	67.7	85.6	142.7	142.7	67.7
Feed rate of mixture fluid (g/min)		2,447	2,387	2,139	2,139	2,430
Feed rate of organic diisocyanate (g/min)						
HDI		553	613	861	861	570
NCO/OH molar ratio		0.98	0.98	0.98	0.98	1.02
Sample designation of TPU		PU-1	PU-2	PU-3	PU-4	PU-5
Result						
Weight-average M. W.		87,000	92,000	82,000	83,000	150,000
Melt viscosity (Pa·s)		1,200	2,000	1,000	1,100	9,000

Table 2

		Synthesis Comparative Example		
		1	2	3
Mixing tank	High-molecular weight polyol (kg)			
	Polyol B			857.3
	Polyol C	857.3		
	Polyol D		857.3	
	Chain extender (kg)			
	1,4-BD	142.7	142.7	142.7
Feed rate of mixture fluid (g/min)		1,877	1,877	1,843
Feed rate of organic diisocyanate (g/min)				
	MDI	1,123	1,123	
	H ₁₂ MDI			1,204
NCO/OH molar ratio		0.98	0.98	0.98
Sample designation of TPU		PU-6	PU-7	PU-8
Result				
	Weight-average M. W.	105,000	106,000	121,000
	Melt viscosity (Pa·s)	2,200	2,500	4,800

Description of components and properties in
 5 Application Examples 1 to 5 and Application Comparative
 Examples 1 to 3 and Tables 1 and 2.

Polyol A:

10 Polycarbonate diol obtained from 3-methyl-1,5-pentanediol
 and diethyl carbonate

Number-average molecular weight = 1,500

Polyol B:

15 Polycarbonate diol obtained from 3-methyl-1,5-pentanediol
 and diethyl carbonate

Number-average molecular weight = 1,000

Polyol C:

Polycarbonate diol obtained from 1,6-hexanediol and diethyl carbonate

Number-average molecular weight = 1,000

5 Polyol D:

Polyester diol obtained from 1,4-butanediol and adipic acid

Number-average molecular weight = 1,000

1,4-BD: 1,4-butanediol

10 HDI: Hexamethylene diisocyanate

MDI: 4,4'-diphenylmethanediisocyanate

H₁₂MDI: Hydrogenated diphenylmethanediisocyanate

TPU: Thermoplastic polyurethane resin

15 Number-average molecular weight

Measured by using a GPC apparatus: Model HLC-8020, from TOSOH CORPORATION

Solution: DMF solution (1%)

Analytical curve: polystyrene analytical curve

20

Melt viscosity

Measuring instrument: flow tester, Model CFT 500C (from SHIMADZU CORPORATION)

Measuring temperature: 180°C

25 Die: 1 mm in diameter

1 mm long

Preheating: 240 seconds

Load: 98 N

Amount of sample: 2 g

[Evaluation of polyurethane resin]

Reference Examples 1 to 5 and Reference Comparative Examples 1 to 3

Each of the samples, PU-1 to PU-8, was made into a sheet (0.2 mm thick) by extrusion and the resulting sheet was evaluated. The stock temperature was 180°C and the T-die temperature was 170°C. The results of evaluation are shown in Tables 3 and 4. The sample PU-2 was tested for dynamic viscoelasticity. The results of the test are shown in Fig. 1.

10

Table 3

	Reference Example				
	1	2	3	4	5
TPU	PU-1	PU-2	PU-3	PU-4	PU-5
Film appearance	○	○	○	○	○
Weather resistance	○	○	○	○	○
Hydrolysis resistance	○	○	○	○	○
Oleic acid resistance	○	○	○	○	○
JIS-A hardness	85	90	96	95	86
Strength at rupture (MPa)	49	57	56	55	51
Elongation at rupture (%)	770	610	650	630	760
Printability					
Vacuum forming	○	○	○	○	○
Stamping	○	○	○	○	○
Secondary formability					
Vacuum forming	○	○	○	○	○
Stamping	○	○	○	○	○

Table 4

	Reference Comparative Example		
	1	2	3
TPU	PU-6	PU-7	PU-8
Film appearance	○	○	○
Weather resistance	×	×	○
Hydrolysis resistance	○	×	○
Oleic acid resistance	○	○	×
JIS-A hardness	85	86	85
Strength at rupture (MPa)	49	50	57
Elongation at rupture (%)	560	680	430
Printability			
Vacuum forming	○	○	○
Stamping	○	○	○
Secondary formability			
Vacuum forming	○	○	×
Stamping	○	○	×

Appearance:

5 Resin samples were visually observed and rated according to the following criterion.

 ○: clear with no fish-eyes.

 △: clear with some fish-eyes.

 ×: cloudy with bleeding and fish-eyes.

10

Weather resistance:

 Measured according to JIS K7350

 Irradiate with light from a xenon lamp for 2000 hours.

 ○: $\Delta YI < 10$

15

 ×: $\Delta YI \geq 10$

Oleic acid resistance:

Evaluated in terms of decrease in the strength at rupture which was measured after the sample sheet had been immersed in oleic acid at 70°C for 24 hours.

5 Rated according to the following criterion.

○: decrease less than 50%

X: decrease no less than 50%

Hydrolysis resistance:

10 Evaluated in terms of the strength at rupture which was measured according to JIS K7311 after the sample had been allowed to stand in an atmosphere at 85°C and 95 %RH for 30 days.

Hardness, strength at rupture, and elongation at rupture:

Measured according to JIS K7311

15 Secondary formability and printability:

Printing was performed on that side of the sheet sample which became concave after forming. After coating, the sheet sample underwent vacuum forming and stamping. The resulting product was visually examined for printing and drawing.

20

Printability:

○: no deformation in printing

X: deformation in printing

Secondary formability:

25

○: with sharp edges

X: without sharp edges

Conditions of vacuum forming:

Sheet heating temperature: 140°C

Vacuum pressure: 1.3 kPa

30

Forming time: 20 seconds

Conditions of stamping:

Sheet heating temperature: 140°C

Press pressure: 10 MPa

Pressing time: 10 seconds

Dynamic viscoelasticity

Measuring instrument: Rheovibron DDV-01FP (A&D Co., LTD)

Under the following conditions

5 Starting temperature: -100°C
Rate of temperature rise: 2°C/min

Specimen

Wide: 4 mm
Long: 25 mm
10 Thick: 200 μm

Dynamic displacement: 16 μm

Frequency: 11 Hz

Automatic load: 6.1×10^{-2} N

15 TPU in Reference Examples 1 to 5 gave good results in all the tests. In Reference Comparative Examples, however, the samples PU-6 and PU-7 prepared from MDI as an organic diisocyanate were poor in weather resistance, the sample PU-7 prepared from polyester polyol was poor in hydrolysis
20 resistance, and the sample PU-8 prepared from H₁₂MDI was poor in secondary formability.

[Evaluation of polyurethane resin keypad]

25 Examples 1 to 5

The polyurethane resin film was formed into keypad by vacuum forming or stamping under the conditions mentioned above, and the resulting keypad was evaluated. The results of evaluation are shown in Table 5.

Table 5

	Example				
	1	2	3	4	5
TPU	PU-1	PU-2	PU-3	PU-4	PU-5
Vacuum forming					
Depressability	○	○	○	○	○
Key interference	○	○	○	○	○
Stamping					
Depressability	○	○	○	○	○
Key interference	○	○	○	○	○

Depressability:

5 Evaluated by visually observing whether the keypad is broken or damaged when strongly depressed straight with a fingernail, and rated according to the following criterion.

 ○: break and damage are not observed.

10 X: break and damage are observed.

Key interference:

 Evaluated by observing whether depressing one key affects its adjacent key.

15 ○: adjacent key is moved very little.

 X: adjacent key is moved greatly.

 It is noted from Table 5 that the polyurethane resin keypad of the present invention exhibits good performance.

CLAIMS:

1. A keypad of polyurethane resin obtained from a thermoplastic polyurethane resin sheet by thermoforming,
5 wherein said thermoplastic polyurethane sheet is a melt-formed product of resin pellets resulting from reaction between an organic diisocyanate (A) composed mainly of hexamethylenediisocyanate (A1), a high-molecular weight polyol (B) composed mainly of polycarbonate diol (B1), and a
10 chain extender (C) composed mainly of an aliphatic diol (C1) having 2 to 10 carbons.
2. The method for thermoforming the keypad which comprises vacuum forming the thermoplastic polyurethane resin
15 sheet defined in claim 1.
3. The method for thermoforming the keypad which comprises stamping the thermoplastic polyurethane resin sheet defined in claim 1.