

11 JAN 2000

**CLEANING GAS AND METHOD FOR CLEANING VACUUM
TREATMENT APPARATUS BY FLOWING THE CLEANING GAS**

BACKGROUND OF THE INVENTION

5 The present invention relates to a cleaning gas
for removing an unnecessary deposit deposited on an
inner wall and tools of a thin film producing
apparatus by means of CVD method, and relates to a
method for cleaning a vacuum treatment apparatus by
the cleaning gas.

10 In various production processes for producing
thin-film devices, optical devices and super steel
materials, various films, powders and whiskers are
produced by means of CVD method, sputtering method,
sol-gel method and vapor deposition method. By the
15 execution of the above-mentioned methods,
unnecessary depositions are deposited on an inner
wall and tools of the producing apparatus. In order
to prevent such unnecessary deposit from affecting
objective products, it is necessary to properly
20 remove such unnecessary deposit. A cleaning gas
employed to remove such unnecessary deposit is
required to have several performances. For example,
such a cleaning gas has to perform so as not to
damage the objective products, not to increase the
25 amount of particles in a reactor of the apparatus,
to be easily varied into innocent gas and to
tenderly affect the earth.

Presently, a plasma cleaning employing a
cleaning gas of at least one of C_2F_6 , CF_4 , C_4F_8 , NF_3
30 and ClF_3 and a plasma-less cleaning employing a
cleaning gas of at least one of F_2 , Cl_2 and ClF_3 have
practically been executed to remove unnecessary

deposits. However, these methods have several problems such that when the cleaning is executed by using the above-mentioned fluorine series gas, heat-resisting Ni-alloy, stainless steel and AlN are
5 corroded by the gas and particles are increased in the apparatus, and that if the temperature for cleaning is lowered to suppress such corrosion, an idling time thereof is increased to lower the throughput of the apparatus, and that if the
10 temperature for the cleaning is lowered to prevent the corrosion of the material of the apparatus, the cleaning speed is lowered.

A Japanese Patent Provisional Publication No. 8-295600 discloses a method for cleaning a nickel
15 base plate employed to produce whiskers of TiC, TiCO and TiCN by means of diluted nitric acid. However, this method requires executing a wet cleaning in an in-site cleaning, and therefore it becomes difficult to improve the throughput of the apparatus.

20 SUMMARY OF THE INVENTION

It is therefore an object of the present invention to provide an improved cleaning gas which effectively removes unnecessary deposit deposited in a vacuum treatment apparatus while satisfying
25 performances required to such a cleaning gas.

A aspect of the present invention resides in a cleaning gas for removing a deposited material generated in a vacuum treatment apparatus for forming a thin film of at least one of Ti, W, Ta, Ru,
30 Ir, a compound including one of Ti, W, Ta, Ru and Ir and an alloy including one of Ti, W, Ta, Ru and Ir, the cleaning gas comprises HF gas and oxygen containing gas.

Another aspect of the present invention resides in a method which functions to remove a deposited material generated in a vacuum treatment apparatus for forming a thin film of at least one of Ti, W, Ta, Ru and Ir, a compound including one of Ti, W, Ta, Ru and Ir and an alloy including one of Ti, W, Ta, Ru and Ir. The method comprises a step of flowing a cleaning gas in the vacuum treatment apparatus.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a plan view showing a thin film producing apparatus of a cluster tool type, to which a cleaning method according to the present invention is adapted; and

Fig. 2 is a schematic view showing one of the thin film producing apparatus.

DETAILED DESCRIPTION OF THE INVENTION

As a result of intensive studies, the present inventors have found a composition of a cleaning gas by which unnecessary deposit deposited on an inner wall and tools of a film producing apparatus is efficiently and safely removed. More specifically, the cleaning gas according to the present invention functions to effectively remove unnecessary deposit deposited in a vacuum treatment apparatus for producing thin films of one of Ti, W, Ta, Ru and Ir, and of a compound of one of Ti, W, Ta, Ru and Ir, and alloy of one of Ti, W, Ta, Ru and Ir. The cleaning gas is a mixed gas containing a HF gas and an oxygen-containing gas. The concentration of the HF gas is greater than or equal to 1 vol%, and the concentration of the oxygen containing gas ranges from 0.5 to 99 vol%.

The oxygen containing gas employed in the

cleaning gas according to the present invention comprises at least one of O₂ gas, O₃ gas, N₂O gas, NO gas, CO gas and CO₂ gas.

The cleaning gas according to the present invention is applicable to the apparatus made of Ti, W and Ta, a compound of one of Ti, W and Ta and an alloy of one of Ti, W and Ta. More specifically, Ti, W, Ta, an oxide of one of Ti, W and Ta, a nitride of one of Ti, W and Ta and an alloy of one of Ti, W and Ta. Furthermore, the cleaning gas is applicable to the apparatus made of Ti, TiN, TiW, TiON, W, WN, TaN, Ru, Ir, compound thereof and alloy thereof. The cleaning gas simultaneously removes CVD reaction by-product produced at piping with by-product produced in the chamber of the apparatus.

It is preferable that the concentration of the HF gas of the cleaning gas is greater than or equal to 1 vol% and the concentration of the oxygen containing gas of the cleaning gas is within a range from 0.5 to 99 vol%. More preferably, the concentration of HF gas is greater than or equal to 10 vol% and the concentration of the oxygen containing gas is within a range from 1 to 90 vol%. If the concentration of HF gas is smaller than 1 vol% and the concentration of oxygen containing gas is smaller than 0.5 vol%, it is difficult to ensure a preferable etching speed. Specifically, when the concentration of oxygen containing gas is smaller than 0.5 vol%, the material of the apparatus is damaged by the cleaning gas in relatively large degree. Further, when the concentration of oxygen containing gas is greater than 1 vol%, an etching speed of the cleaning gas is accelerated. When the

concentration of oxygen containing gas is greater than a range from 75 to 85 vol%, the etching speed tends to decrease in inverse proportion to the increase of the oxygen concentration. If the
5 concentration of the oxygen containing gas is greater than 90 vol%, the etching speed is radically decreased.

In addition to the above-mentioned gases, inert gas such as N_2 , Ar, He may be employed. Further, the
10 other gas having an oxidation property may be employed.

Next, as to the pressure during the cleaning operation employing the cleaning gas according to the present invention, it is necessary that the
15 whole pressure, which is the sum of the HF gas partial pressure and the oxygen containing gas partial pressure, is smaller than or equal to 500 Torr. Preferably, the whole pressure should be smaller than or equal to 100 Torr, and it is further
20 preferable that the pressure is within a range 0.1 to 10 Torr.

If the whole pressure becomes greater than 500 Torr, the evaluating time necessary for evacuating the cleaning gas becomes large. Further, even if a
25 mixture ratio of the mixed gas is within an allowable range and if the partial pressure of the oxygen containing gas is smaller than or equal to 0.005 Torr, it is difficult to ensure a preferable etching speed, and the amount of particles in the
30 reactor is increased without improving the corrosion resistance of the material of the apparatus.

As a result of further intensive studies, the inventors of the present invention have found that

the corrosion resistance of the material employed in the apparatus is remarkably improved by adding oxygen containing gas to HF gas. More specifically, the cleaning gas according to the present invention
5 is applicable to (1) Al and Al-alloy such as Al5052 and Al6061 (JIS mark) at a temperature range not larger than 600 °C, (2) heat-resisting Ni-alloy at a temperature range not larger than 450 °C, (3) austenitic stainless steels at a temperature range
10 of 450 °C, (4) ferritic stainless steels at a temperature range of 460 °C, (5) aluminum nitride at a temperature range not larger than 700 °C, (6) aluminum oxide at a temperature range not larger than 920 °C, (7) quartz at a temperature range not
15 larger than 700 °C, (8) silicon nitride at a temperature range of 760 °C and (9) silicon carbide at a temperature range of 680 °C. That is, the cleaning temperature may be determined according to the employed material.

20 The present invention will be explained in detail with reference to the following examples. It will be understood that the present invention is not limited to these examples.

Examples 1 to 14, Comparative examples 1 and 2

25 As to a sample produced by forming a Ti film of 1 µm thick on a silicon wafer, measurements of etching speed thereto under conditions shown in Table 1 were executed. The results thereof are also shown in Table 1. As is clearly shown in Table 1,
30 the etching speed was remarkably improved by adding a trace quantity of O₂ gas. Also, when the O₂ gas had been changed to one of O₃, N₂O, NO, CO and CO₂, the etching speed was similarly improved.

[Table 1]

	Temperature (°C)	Gas flow amount (SCCM)	Gas concentration (vol%)	Pressure (Torr)	Etching speed (Å/min)
Comparative Example 1	500	HF:1000	HF:100	5	103
Example 1	500	HF:1000 O2:5	HF:99.5 O2:0.5	5	298
Example 2	500	HF:1000 O2:10	HF:99 O2:1	5	1660
Example 3	500	HF:1000 O2:100	HF:90.9 O2:9.1	5	8710
Example 4	500	HF:300 O2:50	HF:85.7 O2:14.3	5	2490
Example 5	500	HF:1000 O2:1000	HF:50 O2:50	5	10340
Example 6	500	HF:1000 O2:1500	HF:40 O2:60	5	10305
Example 7	500	HF:1000 O2:2000	HF:33.3 O2:66.7	5	10426
Example 8	500	HF:1000 O2:3000	HF:25 O2:75	5	10319
Example 9	500	HF:1000 O2:4000	HF:20 O2:80	5	10229
Example 10	500	HF:1000 O2:7000	HF:12.5 O2:87.5	5	9875
Example 11	500	HF:500 O2:4500	HF:10 O2:90	5	8136
Example 12	500	HF:10 O2:990	HF:1 O2:99	5	238
Comparative Example 2	500	HF:5 O2:995	HF:0.5 O2:99.5	5	99.4
Example 13	600	HF:1000 O2:100	HF:90.9 O2:9.1	5	11900
Example 14	700	HF:1000 O2:100	HF:90.9 O2:9.1	5	13810

Examples 15 to 22, Comparative examples 3 and 4

5 As to a sample produced by forming a TiN film
of 1μm thick on a silicon wafer, measurements of
etching speed thereto under conditions shown in
Table 2 were executed. The results thereof are also
shown in Table 2. As is clearly shown in Table 2,
10 the etching speed was remarkably improved by adding

a trace quantity of O₂ gas. Also, when the O₂ gas had been changed to one of O₃, N₂O, NO, CO and CO₂, the etching speed was similarly improved.

5 [Table 2]

	Temperature (°C)	Gas flow rate (SCCM)	Gas concentration (vol%)	Pressure (Torr)	Etching speed (Å/min)
Comparative Example 3	500	HF:1000	HF:100	5	8.5
Example 15	500	HF:1000	HF:99.5	5	926
		O ₂ :5	O ₂ :0.5		
Example 16	500	HF:1000	HF:99	5	1400
		O ₂ :10	O ₂ :1		
Example 17	500	HF:1000	HF:90.9	5	1760
		O ₂ :100	O ₂ :9.1		
Example 18	500	HF:1000	HF:50	5	2500
		O ₂ :1000	O ₂ :50		
Example 19	500	HF:500	HF:10	5	1120
		O ₂ :4500	O ₂ :90		
Example 20	500	HF:10	HF:1	5	238
		O ₂ :990	O ₂ :99		
Comparative Example 4	500	HF:5	HF:0.5	5	140
		O ₂ :995	O ₂ :99.5		
Example 21	600	HF:1000	HF:90.9	5	4300
		O ₂ :100	O ₂ :9.1		
Example 22	700	HF:1000	HF:90.9	5	8200
		O ₂ :100	O ₂ :9.1		

Examples 23 to 24, Comparative example 5

As to a sample produced by forming a W film of 1μm thick on a silicon wafer, measurements of etching speed thereto under conditions shown in Table 3 were executed. The results thereof are also shown in Table 3. As is clearly shown in Table 3, the etching speed was remarkably improved by adding a trace quantity of O₂ gas. Also, when the O₂ gas had been changed to one of O₃, N₂O, NO, CO and CO₂, the etching speed was similarly improved.

[Table 3]

	Temperature (°C)	Gas flow rate (SCCM)	Gas concentration (vol%)	Pressure (Torr)	Etching speed (Å/min)
Comparative Example 5	500	HF:1000	HF:100	5	≤ 1
Example 23	500	HF:1000 O ₂ :10	HF:99 O ₂ :1	5	1800
Example 24	500	HF:1000 O ₂ :10	HF:90.9 O ₂ :9.1	5	2870

Examples 25

5 As to a sample produced by forming a WN film of 1μm thick on a silicon wafer, measurements of etching speed thereto under a condition that a temperature is 500 °C, HF gas flow rate is 900 SCCM (90%), O₂ gas flow rate is 100 SCCM (10%). As a result, the
10 etching speed was 3045 Å/min which is very high in etching speed. When O₂ gas had not been added, the etching speed was smaller than or equal to a measurement lower limit (≤ 1 Å/min).

15 It has not been confirmed of the damages of the apparatus due to the operations for examples 1 to 25. Examples 26 to 36, Comparative examples 6 to 16

As to Al, Al-alloy 5052 (JIS mark), Al-alloy 6061 (JIS mark), heat-resisting Ni-alloy (trade name: Hastelloy C-22), ferroalloy SUS316L (JIS mark),
20 SUS304 (JIS mark), SUS430L (JIS mark), AlN, Al₂O₃, Si₃N₄, SiO₂, corrosion characteristics by gas were observed. More specifically, HF gas (flow rate: 1000 SCCM) and a mixed gas of HF gas (flow rate: 1000SCCM) and N₂O gas (flow rate: 10SCCM) were used.
25 The examples were exposed to the gas under a pressure of 500 Torr for 5 hours. After the exposure, the surface of each example was observed

by an electron microscope, and the change of weights of each sample before and after the exposure was measured. As a result, it was found that damages to the material were remarkably decreased by adding N₂O
5 gas. Further, the etching speed of each of the examples 26 to 36 was very high as same as those of the examples 1 to 25. Comparative examples 6 to 16 show the results obtained by the experiments using only HF gas. Also when the gas N₂O had been changed
10 to one of O₂, O₃, NO, CO and CO₂, the etching speed of this example was high as is similar to those of the examples 1 to 25.

[Table 4]

	Material (JIS mark)	Temperature (°C)	Observation result
Comparative Example 6	Al	400	White thick film was deposited and the film was cracked (Comparative example 6 to 8)
Comparative Example 7	Al5052	400	
Comparative Example 8	Al6061	400	
Comparative Example 9	Heat-resisting Ni alloy	400	Surface of each comparative examples 9 to 12 was turned to yellow or black and was cracked.
Comparative Example 10	SUS316	400	
Comparative Example 11	SUS304	400	
Comparative Example 12	SUS430	450	
Comparative Example 13	AlN	700	Corrosive particulates were generated on the surface of each comparative examples 13-14.
Comparative Example 14	Al2O3	900	
Comparative Example 15	SiO2	700	The surface of each comparative example was etched to lose transparency, and the weight thereof was decreased by the etching.
Comparative Example 16	Si3N4	700	
Example 26	Al	600	Semitransparent film was produced on the surface of each comparative example 26-32 and was in a passive state. Therefore, no corrosion was occurred.
Example 27	Al5052	600	
Example 28	Al6061	600	
Example 29	Heat-resisting Ni alloy	450	
Example 30	SUS316	450	
Example 31	SUS304	450	
Example 32	SUS430	460	
Example 33	AlN	700	The weight and surface condition of each example 33 to 35 were not substantially changed as compared with those of each example before treatment.
Example 34	Al2O3	900	
Example 35	SiO2	700	
Example 36	Si3N4	760	A semitransparent film was formed on the surface of the example 36. The surface was smooth and had no corrosion. Si-O bonding was observed as a result of the analysis of ESCA. It is thought that an oxide film superior in corrosion was formed on the surface.

Comparative Example 17

The heat-resisting Ni-alloy (trade name: Hastelloy C-22) was exposed to the mixed gas of HF gas (flow rate: 1000SCCM) and O₂ gas (flow rate: 5 1000SCCM) at temperature 450 °C and under pressure 760 Torr for 5 hours. As a result, the surface of the comparative example 17 was turned to yellow, and corrosive particles were generated.

Example 37

10 The heat-resisting Ni-alloy (trade name: Hastelloy C-22) was exposed to the mixed gas of HF gas (flow rate: 1000 SCCM) and O₂ gas (flow rate: 1000 SCCM) at a temperature of 450 °C and under a pressure of 500 Torr for 40 hours. As a result, a 15 transparent passive film was formed on the surface of the example 37. The film was extremely thin and smooth. No corrosion was found on the surface.

Comparative Example 18

The heat-resisting Ni-alloy (trade name: 20 Hastelloy C-22) was exposed to the mixed gas of HF gas (flow rate: 990 SCCM) and O₂ gas (flow rate: 10 SCCM) at a temperature of 450 °C and under a pressure of 0.05 Torr for 40 hours. As a result, the surface of the comparative example 17 was turned to yellow 25 and corroded. By an electron microscope, it was found that projecting substance and particulate material are generated on the surface of the comparative example 18. As a result of XMA observation, it was found that the particles 30 produced on the surface of the comparative example 18 was a metal such as Fe and Ni and F.

Comparative Example 19

An example obtained by forming TiW film of 1μm

thick on a silicon wafer was heated at 500 °C, and HF gas (100%, flow rate: 1000SCCM) was flowed in the reactor for 1 hour. Thereafter, the example was analyzed as to Ti and W by means of an X-ray
5 fluorescence analyzer. As a result, Ti and W were remained on the wafer surface.

Example 38

An example obtained by forming TiW film of 1 μ m thick on a silicon wafer was heated at 500 °C, and
10 the mixed gas of HF gas (flow rate: 1000 SCCM) and O₂ gas (flow rate: 1000 SCCM) was flowed in the reactor for 1 hour. Thereafter, the example was analyzed as to Ti and W by means of an X-ray fluorescence analyzer. As a result, Ti and W were not detected
15 on the wafer surface.

Examples 39 to 52, Comparative Examples 20 to 21

As to a sample produced by forming a Ta film of 1 μ m thick on a silicon wafer, measurements of etching speed thereto under conditions shown in Table 5 were
20 executed. The results thereof are also shown in Table 5. As is clearly shown in Table 5, the etching speed was remarkably improved by adding a trace quantity of O₂ gas. Also, when the O₂ gas had been changed to one of O₃, N₂O, NO, CO and CO₂, the
25 etching speed was similarly improved.

[Table 5]

	Temperature (°C)	Gas flow rate (SCCM)	Gas concentration (vol%)	Pressure (Torr)	Etching speed (Å/min)
Comparative Example 21	500	HF:1000	HF:100	5	29
Example 39	500	HF:1000 O2:5	HF:99.5 O2:0.5	5	128
Example 40	500	HF:1000 O2:10	HF:99 O2:1	5	460
Example 41	500	HF:1000 O2:100	HF:90.9 O2:9.1	5	960
Example 42	500	HF:300 O2:50	HF:85.7 O2:14.3	5	1340
Example 43	500	HF:1000 O2:1000	HF:50 O2:50	5	6960
Example 44	500	HF:1000 O2:1500	HF:40 O2:60	5	7342
Example 45	500	HF:1000 O2:2000	HF:33.3 O2:66.7	5	7132
Example 46	500	HF:1000 O2:3000	HF:25 O2:75	5	7369
Example 47	500	HF:1000 O2:4000	HF:20 O2:80	5	7089
Example 48	500	HF:1000 O2:7000	HF:12.5 O2:87.5	5	4958
Example 49	500	HF:500 O2:4500	HF:10 O2:90	5	2685
Example 50	500	HF:10 O2:990	HF:1 O2:99	5	265
Comparative Example 22	500	HF:5 O2:995	HF:0.5 O2:99.5	5	32.2
Example 51	600	HF:1000 O2:100	HF:90.9 O2:9.1	5	8872
Example 52	700	HF:1000 O2:100	HF:90.9 O2:9.1	5	9810

Examples 53 to 60, Comparative Examples 22 and 23

5 As to a sample produced by forming a TaN film
of 1μm thick on a silicon wafer, measurements of
etching speed thereto under conditions shown in
Table 6 were executed. The results thereof are also
shown in Table 6. As is clearly shown in Table 6,
10 the etching speed was remarkably improved by adding

a trace quantity of O₂ gas. Also, when the O₂ gas had been changed to one of O₃, N₂O, NO, CO and CO₂, the etching speed was similarly improved.

5 [Table 6]

	Tempera- ture (°C)	Gas flow rate (SCCM)	Gas concentration (vol%)	Pressure (Torr)	Etching speed (Å /min)
Comparative Example 23	500	HF:1000	HF:100	5	0.5
Example 53	500	HF:1000	HF:99.5	5	54
		O ₂ :5	O ₂ :0.5		
Example 54	500	HF:1000	HF:99	5	258
		O ₂ :10	O ₂ :1		
Example 55	500	HF:1000	HF:90.9	5	1692
		O ₂ :100	O ₂ :9.1		
Example 56	500	HF:1000	HF:50	5	1870
		O ₂ :1000	O ₂ :50		
Example 57	500	HF:500	HF:10	5	380
		O ₂ :4500	O ₂ :90		
Example 58	500	HF:10	HF:1	5	93
		O ₂ :990	O ₂ :99		
Comparative Example 24	500	HF:5	HF:0.5	5	28
		O ₂ :995	O ₂ :99.5		
Example 59	600	HF:1000	HF:90.9	5	2396
		O ₂ :100	O ₂ :9.1		
Example 60	700	HF:1000	HF:90.9	5	3986
		O ₂ :100	O ₂ :9.1		

Next, a cleaning method for practically applying the above-mentioned gas to a vacuum
 10 treatment apparatus such as a thin film producing apparatus will be discussed.

Figs. 1 and 2 show a thin film producing apparatus 2 of a cluster-tool type. The thin film producing apparatus 2 comprises a common conveying
 15 chamber 4 which has the form of octagon and is made of aluminum alloy. An articulated conveying arm 6 made of aluminum alloy is provided in the common conveying chamber 4 so as to be rotatable and

expandable therein. A supporting portion for supporting a semiconductor wafer 50 to be treated is installed to a tip end of the articulated conveying arm 6. Four thin-film producing apparatuses 8A to 8D are connected to the common conveying chamber 4 through gate valves G1 to G4, respectively. A chamber 20 of each of the thin-film producing apparatuses 8A to 8D is made of aluminum alloy and includes a table 10 for setting the wafer 50 thereon, a clamp ring 28 for fixing the wafer 50 on the table 10, a shower head 24 for flowing gas and an attachment ring therein. The table 10 is made of aluminum alloy. Spare chambers 12A and 12B are connected to the common conveying chamber 4 through gate valves G5 and G6, respectively. The spare chambers 12A and 12B function as cooling chambers for cooling the treated wafer 50. Cassette chambers 14A and 14B for storing a plurality of the wafers 50 are connected to the common conveying chamber 4 through gate valves G7 and G8. It will be understood that a preheating chamber for preheating the wafer 50 before treatment may be provided as a spare chamber.

The thin-film producing apparatuses 8A to 8D, the common conveying chamber 4, the spare chambers 12A and 12B, and the cassette chambers 14A and 14B are independently connected to a gas supply line 16 for supplying treatment gas, inert gas such as N₂ gas and the cleaning gas according to the present invention and to a gas evacuating line 18 for evacuating an inner ambient thereof.

In the thin-film producing apparatuses 8A to 8D, thin films of Ti, W, Ta, Ru, Ir, the compound

thereof and the alloy thereof are produced by the thermal CVD method. Further, the plasma CVD method is executed by the provision of a high-frequency electric source for generating plasma, if necessary.

5 A representative thermal CVD method executed by using the thin-film producing apparatuses 8A to 8D will be discussed with reference to Fig. 2.

10 The thin-film producing apparatus 8A comprises the aluminum-alloy chamber 20 in which the table 10 providing a heater 22 therein is installed. The shower head portion 24 made of aluminum alloy is installed to a ceiling portion oppositely facing with the table 10. A gas supply port 24a of the shower head portion 24 is connected to the gas
15 supply line 16. A plurality of gas outlet ports 26 are provided at a bottom portion of the chamber 20 and are connected to the gas evacuating line 18. The clamp ring 28 made of AlN (aluminum nitride) is provided around the table 10 so as to fix a wafer 50
20 on the table 10. A ring-shaped attachment ring 30 is provided around the clamp ring 28, as shown in Fig. 2.

25 When a thin film of Ti or W is produced on the wafer 50 by using the above-mentioned thin-film producing apparatus 8A, the thin film is also produced on the inner wall of the chamber 20, exposed portions of the table 10, the clamp ring 28, the attachment ring 30 as an unnecessary film causing particles. The exposed portions of the
30 table 10 are exposed to the cleaning gas. Therefore, it is necessary to execute a cleaning treatment for removing the unnecessary film attached on various portions at regular intervals or irregular intervals.

The examples 1 to 36 are employed in this cleaning method as a cleaning gas. If the examples 26 to 36 shown in Table 4 are employed as a cleaning gas, a mixed gas of HF gas (flow rate: 1000 SCCM) and N₂O gas (flow rate: 10 SCCM) is used and the pressure is set at about 500 Torr. The cleaning temperature is set at about 500 °C within a range of 450 to 600 °C.

In this condition, the etching speed of the cleaning gas with respect to TiN is about 4000 Å/min although this high speed is not shown in Table 4. This speed is generally the same as that in a case that the cleaning executed by means of ClF₃ gas at the temperature ranging from 200 to 300 °C. Further, if ClF₃ gas is used at the high temperature 500 °C, the table 10, the shower head 24, the clamp ring 28 and the attachment ring 30 will be corroded. In contrast, by using the cleaning gas according to the present invention, even at the temperature of 500 °C, the corrosion of the various portions in the chamber 20 is prevented. That is, the film producing process is generally executed at the temperature ranging from 600 to 700 °C, and the conventional cleaning process was generally executed at a temperature ranging from 200 to 300 °C. In contrast, the cleaning process using the cleaning gas according to the present invention can be executed at the temperature ranging from 450 to 600 °C. Therefore, the difference between the temperature in the film producing process and the temperature in the cleaning process is largely decreased by employing the cleaning gas according to the present invention. This enables the idling time for varying

the temperature to be largely decreased.
Consequently, this improves a throughput of the
apparatus 2. Further, it will be understood that
cleaning an inner surface of the piping of the gas
5 evacuating line is simultaneously executed with this
cleaning of the chamber 20.

Herein, the cleaning gas may be diluted by
mixing inert gas such as Ar, N₂ and He. Further, the
cleaning may be executed at predetermined intervals.
10 More specifically, it may be executed at each time
when a predetermined number of the wafers were
processed, or at each time when an accumulated time
period for producing film reached a predetermined
time period, or at regular intervals.

15 Furthermore, an after-treatment of the cleaning
process may be executed by evacuating the cleaning
gas from the chamber 20 and repeatedly supplying and
stopping supplying inert gas such as N₂ gas to the
chamber 20, under a condition that the supply of the
20 cleaning gas is stopped. If the repeated supply and
stop of the inert gas are executed several times
while evacuating gases from the chamber 20, the
cleaning gas will be rapidly discharged from the
chamber 20.

25 Additionally, the gas supply port 24a of the
shower head portion 24 may be divided into two ports
which are connected to a cleaning gas supply line
and a film-producing gas supply line, respectively.
If such an arrangement of the plural supply ports
30 24a is employed, inert gas such as N₂ gas is flowed
in the film-producing gas supply line during the
cleaning process. This prevents the cleaning gas
from inversely flowing to and remaining in the

film-producing gas supply line. Accordingly, the affect of the remaining cleaning gas to the next film producing process is prevented.

Furthermore, although the explanation of the
5 cleaning process is discussed as to the film
producing apparatus 8A, it will be understood that
the other film producing apparatuses 8B to 8D may
execute the normal film forming process during the
cleaning process of the film producing apparatus 8A
10 or may independently execute the cleaning process.

Although the embodiment of the cleaning method
has been shown and described such that only the film
producing apparatus 8A executes the cleaning process,
it will be understood that several or all of the
15 film producing apparatuses 8A to 8D may
simultaneously execute the cleaning process together
with the common conveying chamber 4. In this case,
the pressures of the respective chambers are
equalized at the same pressure by supplying inert
20 gas before the cleaning. Thereafter, the
corresponding gate valves are opened, and the
cleaning gas is supplied to the respective gas
supply line 16. Furthermore, simultaneously with
this supply, the evacuation through the respective
25 gas evacuating lines 18 is executed. This enables
the several chambers to be simultaneously cleaned by
the cleaning process.

Furthermore, in such a situation, the spare
chambers 12A and 12B and the cassette chambers 14A
30 and 14B may be simultaneously cleaned by this
cleaning process.

Although the cleaning gas and method according
to the present invention has been shown and

described such that the cleaning gas is independently supplied to the film producing apparatus, the common conveying chamber, the spare chamber and the cassette chamber, it will be
5 understood that the present invention is not limited to this embodied method and may be supplied to each of several blocks constituted by several chambers. This enables the number of the gas supply lines to be decreased. Furthermore, if it is arranged such
10 that all of the chambers are simultaneously executed, it is possible to decrease the number of the gas supply lines to one.

Although the embodied cleaning gas and method according to the present invention has been mainly
15 shown and described as to the removal of the thin film of Ti, W, compound thereof and alloy thereof, it will be understood that the invention is not limited to these and may be applicable to the removal of the thin film of Ta, Ru, Ir, the compound
20 thereof and the alloy thereof.

Further, although the embodied cleaning gas and method according to the present invention has been shown and described to employ the CVD method, the invention is not limited to this and may be applied
25 to a vacuum treatment apparatus which generates the above mentioned compound and alloy in a treatment chamber due to a main treatment. Furthermore, although the embodied cleaning method according to the present invention has been shown and described
30 as to the apparatus for treating a semiconductor wafer, the invention is not limited to this and may be applied to an apparatus treating a LCD substrate or glass substrate.

With the cleaning gas and the cleaning method of a vacuum treatment apparatus in accordance with the present invention, it becomes possible to ensure superior advantages. More specifically, by
5 employing the cleaning gas according to the present invention to clean the vacuum treatment apparatus, it becomes possible to remove an unnecessary film deposited in the vacuum treatment apparatus, which produces a thin film of Ti, W, Ta, Ru, Ir, the
10 compound thereof and the alloy thereof, at a relatively high temperature near the film producing temperature and at high etching speed and to prevent the apparatus from being damaged by corrosion. Therefore, it is possible to decrease a difference
15 between the temperatures in film producing process and in cleaning process. This enables the idling time for varying the temperature to be decreased. Consequently, it is possible to remarkably improve an yield factor of products and a throughput of the
20 producing apparatus employing the cleaning gas and the method using the gas according to the present invention.

The entire disclosure of Japanese Patent Application No. 11-302715 filed on November 24, 1999
25 including specification, claims, drawings and summary are incorporated herein by reference in its entirety.

WHAT IS CLAIMED IS:

- 1 1. A cleaning gas for removing a deposited
2 material generated in a vacuum treatment apparatus,
3 the vacuum treatment apparatus producing a thin film
4 of at least one of Ti, W, Ta, Ru, Ir, a compound
5 including one of Ti, W, Ta, Ru and Ir and an alloy
6 including one of Ti, W, Ta, Ru and Ir, said cleaning
7 gas comprising:
8 HF gas; and
9 oxygen containing gas.
- 1 2. A cleaning gas as claimed in claim 1, wherein a
2 concentration of said HF is greater than or equal to
3 1 vol%, and a concentration of said oxygen
4 containing gas ranges from 0.5 to 99 vol%.
- 1 3. A cleaning gas as claimed in claim 1, wherein
2 said oxygen containing gas includes at least one of
3 O₂ gas, O₃ gas, N₂O gas, NO gas, CO gas and CO₂ gas.
- 1 4. A cleaning gas as claimed in claim 1, wherein
2 the compound including one of Ti, W, Ta, Ru and Ir
3 includes TiN, TiW, TiON, WN and TaN.
- 1 5. A method for removing a deposited material
2 generated in a vacuum treatment apparatus for
3 forming a thin film of one of Ti, W, Ta, Ru and Ir,
4 a compound including one of Ti, W, Ta, Ru and Ir and
5 an alloy including one of Ti, W, Ta, Ru and Ir, said
6 method comprising the steps of;
7 flowing a cleaning gas in the vacuum treatment
8 apparatus.



- 1 6. A method as claimed in claim 5 further
2 comprising the step of evacuating the cleaning gas
3 flowed in the vacuum treatment apparatus.
- 1 7. A method as claimed in claim 5, wherein the
2 cleaning gas comprises HF gas and oxygen containing
3 gas.
- 1 8. A method as claimed in claim 7, wherein a
2 concentration of the HF gas is greater than or equal
3 to 1 vol%, and a concentration of said oxygen
4 containing gas ranges from 0.5 to 99 vol%.
- 1 9. A method as claimed in claim 7, wherein said
2 oxygen containing gas includes at least one of O₂ gas,
3 O₃ gas, N₂O gas, NO gas, CO gas and CO₂ gas.
- 1 10. A method as claimed in claim 5, wherein a
2 temperature in the vacuum treatment apparatus is
3 kept within a range of 450 to 600 °C when the
4 cleaning is executed.
- 1 11. A method as claimed in claim 5, wherein the
2 vacuum treatment apparatus includes a plurality of
3 vacuum treatment apparatuses which are connected to
4 a common conveying chamber, the plurality of the
5 vacuum treatment apparatuses and the common
6 conveying chamber are selectively cleaned by flowing
7 the cleaning gas.
- 1 12. A method as claimed in claim 5, wherein the
2 vacuum treatment apparatus includes a plurality of
3 vacuum treatment apparatuses which are connected to
4 a common conveying chamber, the plurality of the



5 vacuum treatment apparatuses and the common
6 conveying chamber are simultaneously cleaned by
7 flowing the cleaning gas.

