

Description

This invention relates to highly durable, dye light-polarizing film having neutral gray and high polarizing coefficient, which comprises a polymer film having at least three dichroism dyes adsorbed and orientated therein.

Hitherto, a light-polarizing film has generally been prepared by adsorbing such polarizing elements as iodine or dichroism dye in a stretch-orientated base film. The base film is made from polyvinyl alcohol or derivatives thereof. Alternatively, the film is made from polyene prepared by dehydrochlorination of polyvinyl chloride or dehydration of polyvinyl alcohol.

Light-polarizing film in which a polarizing element of iodine is used is excellent in initial polarization quality, but is not satisfactory in durability, particularly when employed for a long period of time under high temperature and high humidity conditions, since resistances against water and heat are small. A few proposals have been made, in order to improve durability, e.g., a fast treatment with aqueous formalin or boric acid solution or application of protective film made from polymer film having small water vapor transmission. However, these treatments are not enough yet to improve resistance under high temperature and humidity conditions.

Light-polarizing film in which a polarizing element of dichroism dye is used is superior to that in which iodine is used in place of the dichroism dye, with respect to durability against water and heat. However, there are still difficulties of (1) no definite light transmission or not neutral gray, (2) no definite polarizing coefficient and (3) considerably inferior polarizing coefficient to that of a light-polarizing film in which iodine is used.

DE-A-31 48 787 discloses the use of more than one dichroism dye in a light-polarizing film in order to achieve good heat and humidity resistance.

According to the invention there is provided a light-polarizing film comprising an oriented polymer film and, as a polarizing element, a dichroism dye, characterized in that the oriented polymer film is made from polyvinyl alcohol or a derivative thereof and the polarizing element comprises at least three adsorbed dichroism dyes selected from:

(A) yellow dichroism dyes having a major absorption wavelength region in the range of 400—500 nm,

(B) black dichroism dyes having a major absorption wavelength region in the range of 450—650 nm,

(C) blue dichroism dyes having a major absorption wavelength region in the range of 570—700 nm,

(D) orange or red dichroism dyes having a major adsorption wavelength region in the range of 450—570 nm, and

(E) green dichroism dyes having a major absorption wavelength region in the range of 600—700 nm or 400—450 nm,

said light polarizing film having, over the visible light region of 400—700 nm, a polarizing coefficient of at least 70%, and a difference between the minimum and the maximum light transmittances of at most 20%.

In the accompanying drawings, Figures 1—10 show the relationship between wavelength and the light transmittance of a single polarizer or the polarizing coefficient of light-polarizing films obtained in Examples 1—10, and Figures 11—12 show the same relationship with respect to light-polarizing films obtained in Comparison Examples 1 and 2.

The light-polarizing film of the present invention is highly durable, of high quality and has a neutral gray and high polarizing coefficient. Preferably, over the visible light wavelength region of 400—700nm, the minimum light transmittance is at least 20%.

A first embodiment of light-polarizing film of the invention comprises at least one dye each from (A), (B) and (C).

A second embodiment is one which contains at least one dye each from (A), (B) and (C).

A third embodiment is one which contains at least one dye each from (A), (C) and (D).

A fourth embodiment is one which contains at least one dye each from (C), (D) and (E).

Any organic direct dye as defined under (A) to (E) may be employed in the present invention, as long as the dichroism ratio is large. The dyes generally are azo dyes. Examples thereof are as follows, referring to C.I. Generic Names and trade names:

Organic direct dyes:

(A): yellow dichroism dyes having major absorption wavelength region in the range of 400—500 nm (class A),

(B): black dichroism dyes having major absorption wavelength region in the range of 450—650 nm (class B),

(C): blue dichroism dyes having major absorption wavelength region in the range of 570—700 nm (class C),

(D): orange or red dichroism dyes having major absorption wavelength region in the range of 450—570 nm (class D), and

(E): green dichroism dyes having major absorption wavelength in the range of 600—700 nm or 400—450 nm (class E).

C.I. Generic names and trade names:

Class A:
C.I. Direct Yellow 12 [example of trade name (hereinafter the same): "Chrysophenine"]

C.I. Direct Yellow 44 ["Direct Fast Yellow GC"]

C.I. Direct Yellow 28 ["Sumilight Supra Yellow BC Conc"]

C.I. Direct Yellow 142 ["Sumilight Yellow GR"]

Class B:
C.I. Direct Black 17 ["Japanol Fast Black D Conc"]

This Sheet Has Been Replaced



C.I. Direct Black 19 ["Sumilight Black G Conc"]
 C.I. Direct Black 51 ["Direct Fast Black Conc"]
 C.I. Direct Black 154 ["Direct Deep Black XA"]
 C.I. Direct Black 32 ["Direct Fast Black AB"]
 C.I. Direct Black 22 ["Direct Fast Black B"]
 C.I. Direct Black 112 ["Sumilight Supra Grey
 Conc"]
 C.I. Direct Black 113 ["Sumilight Supra Grey
 NGL Conc"]

Class C:

C.I. Direct Blue 202 ["Sumilight Supra Blue
 3GS"]
 C.I. Direct Blue ["Direct Sky Blue 6B"]
 C.I. Direct Blue 168 ["Direct Copper Blue 2B"]
 C.I. Direct Blue 71 ["Sumilight Blue BRR Conc"]
 C.I. Direct Blue 78 ["Sumilight Supra Blue G
 Conc"]

Class D:

C.I. Direct Orange 26 ["Direct Fast Orange S"]
 C.I. Direct Orange 107 ["Sumilight Supra
 Orange GD Extra Conc"]
 C.I. Direct Red 31 ["Nippon Fast Red BB Conc"]
 C.I. Direct Red 2 ["Benzopurpurine 4B"]
 C.I. Direct Red 81 ["Sumilight Red 4B"]
 C.I. Direct Red 79 ["Sumilight Supra Red 4BL
 170%"]
 C.I. Direct Red 247 ["Japanol Fast Red FA"]

Class E:

C.I. Direct Green 85 ["Direct Dark Green BA"]

A dye combination which is desirable for the present invention is one which satisfies the following requirements, over the whole visible light region of 400—700 nm; (1) the minimum polarizing coefficient is at least 70%, preferably at least 80%, (2) difference between the maximum and minimum polarizing coefficients is at most 20%, and (3) difference between the minimum and maximum light transmittances is at most 20%, preferably at most 15%. No polarization performances as above have ever been expected. The dye combination is obtained by selecting at least one dye each from at least three of the respective five classes above, for instance, (1) a group consisting of classes A, B and C, (2) a group consisting of classes A, B, C and D, (3) a group consisting of classes A, C and D or (4) a group consisting of classes C, D and E.

Dyes listed in examples above have large dichroism ratio, in particular, among organic direct dyes.

Groups mentioned above (1)—(4) are standard ones. Dyes belonging to the other classes may be incorporated thereinto.

Mixing various dyes is necessary, which respectively have different absorption and polarization characteristics at different wavelength regions within the range of 400—700 nm. Only one dye is hardly able to provide a polarizing film, over the whole visible light region of 400—700 nm, showing the same absorption characteristic, i.e., neutral gray, and having high polarizing

coefficient. No dye polarizing film is obtained without blending various dyes, which, over the whole wavelength region of visible light ranging from 400 to 700 nm, shows neutral gray and has high polarizing coefficient.

One of combinations of dyes in more concrete manner suitable for the present invention is one comprising three dyes, i.e., C.I. Direct Yellow 12, C.I. Direct Black 19 and C.I. Direct Blue 202. Another example is a combination of four dyes, i.e., C.I. Direct Yellow 12, C.I. Direct Black 17, C.I. Direct Blue 202 and C.I. Direct Orange 26. Further example is a combination of five dyes, i.e., C.I. Direct Yellow 44, C.I. Direct Black 17, C.I. Direct Blue 202, C.I. Direct Orange 26 and C.I. Direct Red 2. The other example is a combination of four dyes, i.e., C.I. Direct Blue 1, C.I. Direct Red 81, C.I. Direct Orange 107 and C.I. Direct Green 85.

Further addition of dichroism dyes mentioned below is more favorable:

C.I. Direct Violet 9 [trade name (hereinafter the same) "Nippon Brilliant Violet BK Conc"]

C.I. Direct Violet 51 ["Sumilight Violet BB"]

C.I. Direct Brown 106 ["Sumilight Supra Brown G Conc"]

C.I. Direct Brown 223 ["Direct Brown MA"]

Polymer film used in the present invention is made from polyvinyl alcohol or derivatives thereof. Alternatively, these compounds may be modified by olefins such as ethylene, propylene, etc., crotonic acid, acrylic acid, methacrylic acid, maleic acid, etc. Polyvinyl alcohol or derivatives thereof are preferred, since a dye is easily adsorbed and orientated in the film.

One of processes to have organic direct dyes adsorbed and orientated in polymer film is usually to dissolve the organic direct dyes in water and then to dye the polymer film therewith. Orientation of dichroism dye adsorbed in the polymer film is effected by orientating the polymer film before or after the adsorption. Stretch of film made from polyvinyl alcohol or derivatives thereof is carried out by a wet stretching method or by a dry stretching method under rolling. The latter method is preferable from the viewpoints of stability in working and uniformity in stretching.

Dry stretching under rolling of film made of polyvinyl alcohol or derivatives thereof is carried out in such a manner that percentage of water content of film is controlled to 8% or less, back tension of at least 50 Kg/cm² is applied and then rolling is effected under at least 100 Kg/cm of line pressure by means of at least one pair of rolls held at a temperature of 20°C or higher, preferably 55°C—130°C. Then, orientated film made from polyvinyl alcohol or derivatives thereof is obtained with high stretching ratio and without unevenness in stretching.

After organic direct dye is adsorbed and orientated in polymer film, the film is, if necessary, subjected to an after-treatment with, for example, aqueous boric acid solution. Light transmittance of a light-polarizing film as well as polarizing coefficient thereof are improved thereby. The



after-treatment with aqueous boric acid solution varies depending on polymer film employed and organic direct dye employed. It is usually conducted under the conditions wherein concentration of boric acid is 1—15%, preferably 5—10%, and a temperature is 30°—80°C, preferably 50—80°C. When concentration of boric acid is less than 1% and temperature is lower than 30°C, an improvement desired is hardly obtained. On the other hand, when concentration of boric acid is greater than 15% and temperature is higher than 80°C, a light-polarizing film obtained is brittle. Addition of surface active agents with or without inorganic salts to the boric acid solution is preferred. Any of nonionic, cationic or anionic surface active agents may be employed, preferably nonionic ones. Nonionic surface active agent is, for example, ethylene oxide-addition polymerization products of higher alcohol or ethylene oxide-addition polymerization products of nonyl phenol. An amount of the surface active agent to be added is 0.005—0.5 wt.%, preferably 0.02—0.2 wt.% based on water. Anhydrous sodium sulfate is usually employed as the inorganic salts. Alternatively, sodium or potassium salt of sulfuric acid, hydrochloric acid or nitric acid may be used. These inorganic salts may be used in an amount of 0.1—5 wt.%, preferably 0.3—3 wt.%. If desired, a fixation treatment may be effected together with aqueous cationic high molecular compound solution.

Either one or both surfaces of the present dye light-polarizing film this obtained may be coated with a protector film uniaxially stretch-orientated. The protector film is made from a material superior in optical transparency and mechanical strength. The material is, for example, tetrafluoroethylene-hexafluoroethylene copolymer and other fluorocarbon resin, polyester resin, polyolefin resin, polyamide resin, etc., in addition to conventional cellulose acetate and polyacrylic resin.

The present dye light-polarizing film has extremely smaller difference between the maximum and minimum light transmittances over the whole visible light region of 400—700 nm than that of any conventional ones. The present film has neutral gray. Furthermore, the present film has small difference between the maximum and minimum polarizing coefficients over the whole visible light region. Polarization quality of the present film is excellent and on the same level as that of a light-polarizing film wherein a light polarizing element is iodine.

The present light-polarizing film is usable for display by liquid crystal, particularly for such applications as instruments mounted in vehicles and displays in various industrial instruments, which require high durability.

The present invention is explained in more detail by examples.

Polarizing coefficient referred to in the present invention is defined as follows. Two sample sheets of polarizing film or polarizing plate are piled one on the other and subjected to

measurement of a light transmission curve. The Spectrophotometer UV210 by Shimadzu Seisakusho was used. Polarizing coefficient is given by the formula

$$\sqrt{\frac{H_{||} - H_{\perp}}{H_{||} + H_{\perp}}} \times 100 (\%)$$

wherein $H_{||}$ denotes the light transmission in placing two identical polarizers in parallel which is measured when two samples sheets are piled so that the directions of stretch-orientation of light polarizing film are in parallel each other, and $H_{\perp}$ denotes the light transmission in placing two identical polarizers on cross axis (0° and 90°) which is measured when two sample sheets are piled so that the directions of stretch-orientation of light-polarizing film are cross each other.

Example 1


Polyvinyl alcohol film (Kuraray Vynlon® 7500) of 75 microns thick was stretched four times at 105°C by means of pressure rolls uniaxially in the longitudinal direction, to prepare a light-polarizing base film. The film was dipped at 60°C for ten minutes, under tension, in a solution containing three dyes defined below and 7.0 wt.% of anhydrous sodium sulfate: 0.08 wt.%, 0.06 wt.% and 2.5 wt.% of "Japanol Fast Black D conc" of C.I. Direct Black 17 in C.I. Generic Name (same hereinafter), "Chrysophenine" of C.I. Direct Yellow 12 and "Sumilight Supra Blue 3 GS" of C.I. Direct Blue 202, respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for 30 minutes with water of 20°C to obtain a light-polarizing film which had neutral gray. Fig. 1 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 2

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in a solution containing four dyes defined below and 7 wt.% of anhydrous sodium sulfate: 0.06 wt.%, 0.10 wt.%, 0.08 wt.% and 2.5 wt.% of "Chrysophenine", "Direct Fast Orange S" of C.I. Direct Orange 26, "Japanol Fast Black D conc" and "Sumilight Supra Blue 3 GS", respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was further dipped at 65°C for five minutes in aqueous solution of 7.5 wt.% boric acid, and washed for 30 minutes with water of 20°C. A light-polarizing film thus obtained had neutral gray. Fig. 2 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 3

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in a solution containing five dyes defined below and



7.0 wt.% of anhydrous sodium sulfate: 0.06 wt.%, 0.08 wt.%, 0.10 wt.%, 0.10 wt.% and 2.0 wt.% of "Chrysophenine", "Japanol Fast Black D conc", "Direct Fast Orange S", "Benzopurpurine 4 B" of C.I. Direct Red 2 and "Sumilight Supra Blue 3 GS" respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was further dipped at 65°C for five minutes in aqueous solution containing 7.5 wt. of boric acid and washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Figure 3 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 4

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in aqueous solution containing four dyes defined below and 7.0 wt.% of anhydrous sodium sulfate: 0.08 wt.%, 0.10 wt.%, 0.08 wt.% and 0.15 wt.% of "Direct Fast Yellow GC" of C.I. Direct Yellow 44, "Sumilight Supra Orange GD extra conc" of C.I. Direct Orange 107, "Sumilight Black G conc" of C.I. Direct Black 19 and "Direct Sky Blue 6 B" of C.I. Direct Blue 1, respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was dipped at 65°C for five minutes in aqueous solution containing 7.5 wt.% of boric acid and washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Fig. 4 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 5

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in aqueous solution containing three dyes defined below and 7.0 wt.% of anhydrous sodium sulfate: 0.06 wt.%, 0.10 wt.% and 2.0 wt.% of "Chrysophenine", "Sumilight Black G conc" and "Sumilight Supra Blue 3 GS", respectively, all being manufactured by Sumitomo Chemical Company, Limited.

Then, the film was dipped at 65°C for five minutes in aqueous solution of 7.5 wt.% of boric acid and washed for 30 minutes with water of 20°C. A light-polarizing film obtained neutral gray. Fig. 5 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 6

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in aqueous solution containing three dyes defined below and 7.0 wt.% of anhydrous sodium sulfate: 0.04 wt.%, 0.13 wt.% and 0.09 wt.% of "Direct Sky Blue 6 B", "Sumilight Red 4 B" of C.I. Direct Red 81 and "Direct Dark Green BA" of C.I. Direct Green 85", respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was dipped at 65°C for five minutes in aqueous solution of 7.5 wt.% of boric acid and

washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Fig. 6 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 7

The similar base film to that in Example 1 was dipped at 60°C for 20 minutes, under tension, in aqueous solution containing six dyes defined below and 7.5 wt.% of anhydrous sodium sulfate: 0.08 wt.%, 0.06 wt.%, 2.0 wt.%, 0.04 wt.%, 0.04 wt.% and 0.04 wt.% of "Japanol Fast Black D conc", "Chrysophenine", "Sumilight Supra Blue 3GS", "Nippon Fast Red BB conc" of C.I. Direct Red 31, "Nippon Brilliant Violet BK conc" of C.I. Direct Violet 9 and "Benzopurpurine 4 B", respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was dipped at 65°C for five minutes in aqueous solution of 7.5 wt.% of boric acid and washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Fig. 7 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 8

The similar base film to that in Example 1 was dipped at 60°C for ten minutes, under tension, in a solution containing three dyes defined below and 7.0 wt.% of anhydrous sodium sulfate: 0.04 wt.%, 0.08 wt.% and 2.5 wt.% of "Chrysophenine", "Benzopurpurine 4 B" and "Sumilight Supra Blue 3GS", respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was further dipped at 65°C for five minutes in aqueous solution of 7.5 wt.% boric acid and dipped for 30 seconds in water. A light-polarizing film thus obtained had neutral gray. Fig. 8 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 9

Unstretched polyvinyl alcohol film (Kuraray Vynolon® 7500) of 75 μ thick was dipped at 40°C for 30 seconds, under tension, in aqueous solution containing three dyes defined below and 0.8 wt.% of anhydrous sodium sulfate: 0.03 wt.%, 0.02 wt.% and 0.09 wt.% of "Japanol Fast Black D conc", "Chrysophenine" and "Sumilite Supra Blue 3 GS", respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for ten minutes with water of 20°C. The film was uniaxially stretched four times in the longitudinal direction at room temperature. A light-polarizing film obtained had neutral gray. Fig. 9 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 10

Unstretched polyvinyl alcohol film (Kuraray Vynolon® 7500) of 75 μ thick was dipped at 40°C for



30 seconds, under tension, in aqueous solution containing four dyes defined below and 0.8 wt.% of anhydrous sodium sulfate: 0.02 wt.%, 0.04 wt.%, 0.03 wt.% and 0.09 wt.% of "Chrysophenine", "Direct Fast Orange S", "Japanol Fast Black D conc" and "Sumilite Supra Blue 3 GS" respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was uniaxially stretched four times in the longitudinal direction. Then, the film was dipped at 50°C for five minutes in aqueous solution of 7.5 wt.% of boric acid, and washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Fig. 10 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 11

Cellulose triacetate film commercially available and manufactured by Fuji Photo Film corporation of 80 μ thick was coated on both sides of the light-polarizing films prepared by Examples 1—10, respectively, by use of urethane adhesive.

Initial polarization qualities of light-polarizing plates obtained were observed. Polarization qualities of the light-polarizing plates were again observed after they had been left to stand for 500 hours in a thermo-hygrostat held at 85°C and under 90% RH. There were no change in polarization qualities from the initial ones.

Example 12

The same light-polarizing plates as in Example 11 were left to stand for 200 hours in a hot air oven held at 100°C, after initial polarization qualities had been observed. There were no change in polarization qualities from the initial ones.

Comparison example 1

The similar base film to that in Example 1 was dipped at 50°C for 40 minutes, under tension, in aqueous solution containing 0.03 wt.% of only one dye of "Japanol Fast Black D conc" and 0.3 wt.% of anhydrous sodium sulfate, said dye being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for 30 minutes with water of 20°C. Fig. 11 shows light transmittance of single polarizer and polarizing coefficient of a light-polarizing film obtained, in dotted and solid lines, respectively. The light-polarizing film had no neutral gray and inferior light polarization quality.

Comparison example 2

The similar base film to that in Example 1 was dipped at 50°C for 40 minutes, under tension, in aqueous solution containing 0.03 wt.% of only one dye of "Chrysophenine" and 0.3 wt.% of anhydrous sodium sulfate, said dye being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for 30 minutes with water of 20°C. Fig. 12 shows light transmittance of single polarizer and polarizing coefficient of a light-polarizing film obtained, in

dotted and solid lines, respectively. The film had no neutral gray and inferior light polarization quality.

Claims

1. A light-polarizing film comprising an oriented polymer film and, as a polarizing element, a dichroism dye, characterized in that the oriented polymer film is made from polyvinyl alcohol or a derivative thereof and the polarizing element comprises at least three adsorbed dichroism dyes selected from:

(A) yellow dichroism dyes having a major absorption wavelength region in the range of 400—500 nm,

(B) black dichroism dyes having a major absorption wavelength region in the range of 450—650 nm,

(C) blue dichroism dyes having a major absorption wavelength region in the range of 570—700 nm,

(D) orange or red dichroism dyes having a major adsorption wavelength region in the range of 450—570 nm, and

(E) green dichroism dyes having a major absorption wavelength region in the range of 600—700 nm or 400—450 nm, said light polarizing film having, over the visible light region of 400—700 nm, a polarizing coefficient of at least 70%, and a difference between the minimum and the maximum light transmittances of at least 20%.

2. A light-polarizing film according to claim 1, wherein, over the visible light region of 400—700 nm, the difference between the minimum and the maximum polarizing coefficients is at most 20% and the minimum light transmittance is at least 20%.

3. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one dye each from (A), (B) and (C) as defined in claim 1.

4. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one dye each from (A), (B), (C) and (D) as defined in claim 1.

5. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one each from (A), (C) and (D) as defined in claim 1.

6. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one each from (C), (D) and (E) as defined in claim 1.

7. A light-polarizing film according to any one of the claims 3 to 6, wherein the dichroism dyes in the various classes (A) to (E), as and when present, are selected from:

- (A) C.I. Direct Yellow 12
C.I. Direct Yellow 44;
- (B) C.I. Direct Black 17
C.I. Direct Black 19;
- (C) C.I. Direct Blue 202
C.I. Direct Blue 1;



30 seconds, under tension, in aqueous solution containing four dyes defined below and 0.8 wt.% of anhydrous sodium sulfate: 0.02 wt.%, 0.04 wt.%, 0.03 wt.% and 0.09 wt.% of "Chrysophenine", "Direct Fast Orange S", "Japanol Fast Black D conc" and "Sumilite Supra Blue 3 GS" respectively, all being manufactured by Sumitomo Chemical Company, Limited. Then, the film was uniaxially stretched four times in the longitudinal direction. Then, the film was dipped at 50°C for five minutes in aqueous solution of 7.5 wt.% of boric acid, and washed for 30 minutes with water of 20°C. A light-polarizing film obtained had neutral gray. Fig. 10 shows light transmittance of single polarizer and polarizing coefficient thereof in dotted and solid lines, respectively.

Example 11

Cellulose triacetate film commercially available and manufactured by Fuji Photo Film corporation of 80 μ thick was coated on both sides of the light-polarizing films prepared by Examples 1—10, respectively, by use of urethane adhesive.

Initial polarization qualities of light-polarizing plates obtained were observed. Polarization qualities of the light-polarizing plates were again observed after they had been left to stand for 500 hours in a thermo-hygrostat held at 85°C and under 90% RH. There were no change in polarization qualities from the initial ones.

Example 12

The same light-polarizing plates as in Example 11 were left to stand for 200 hours in a hot air oven held at 100°C, after initial polarization qualities had been observed. There were no change in polarization qualities from the initial ones.

Comparison example 1

The similar base film to that in Example 1 was dipped at 50°C for 40 minutes, under tension, in aqueous solution containing 0.03 wt.% of only one dye of "Japanol Fast Black D conc" and 0.3 wt.% of anhydrous sodium sulfate, said dye being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for 30 minutes with water of 20°C. Fig. 11 shows light transmittance of single polarizer and polarizing coefficient of a light-polarizing film obtained, in dotted and solid lines, respectively. The light-polarizing film had no neutral gray and inferior light polarization quality.

Comparison example 2

The similar base film to that in Example 1 was dipped at 50°C for 40 minutes, under tension, in aqueous solution containing 0.03 wt.% of only one dye of "Chrysophenine" and 0.3 wt.% of anhydrous sodium sulfate, said dye being manufactured by Sumitomo Chemical Company, Limited. Then, the film was washed for 30 minutes with water of 20°C. Fig. 12 shows light transmittance of single polarizer and polarizing coefficient of a light-polarizing film obtained, in

dotted and solid lines, respectively. The film had no neutral gray and inferior light polarization quality.

Claims

1. A light-polarizing film comprising an oriented polymer film and, as a polarizing element, a dichroism dye, characterized in that the oriented polymer film is made from polyvinyl alcohol or a derivative thereof and the polarizing element comprises at least three adsorbed dichroism dyes selected from:

(A) yellow dichroism dyes having a major absorption wavelength region in the range of 400—500 nm,

(B) black dichroism dyes having a major absorption wavelength region in the range of 450—650 nm,

(C) blue dichroism dyes having a major absorption wavelength region in the range of 570—700 nm,

(D) orange or red dichroism dyes having a major adsorption wavelength region in the range of 450—570 nm, and

(E) green dichroism dyes having a major absorption wavelength region in the range of 600—700 nm or 400—450 nm, said light polarizing film having, over the visible light region of 400—700 nm, a polarizing coefficient of at least 70%, and a difference between the minimum and the maximum light transmittances of at least 20%.

2. A light-polarizing film according to claim 1, wherein, over the visible light region of 400—700 nm, the difference between the minimum and the maximum polarizing coefficients is at most 20% and the minimum light transmittance is at least 20%.

3. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one dye each from (A), (B) and (C) as defined in claim 1.

4. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one dye each from (A), (B), (C) and (D) as defined in claim 1.

5. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one each from (A), (C) and (D) as defined in claim 1.

6. A light-polarizing film according to claim 1 or 2, wherein the dichroism dyes comprise at least one each from (C), (D) and (E) as defined in claim 1.

7. A light-polarizing film according to any one of the claims 3 to 6, wherein the dichroism dyes in the various classes (A) to (E), as and when present, are selected from:

(A) C.I. Direct Yellow 12

C.I. Direct Yellow 44;

(B) C.I. Direct Black 17

C.I. Direct Black 19;

(C) C.I. Direct Blue 202

C.I. Direct Blue 1;



- (D) C.I. Direct Orange 26
C.I. Direct Orange 107
C.I. Direct Red 31
C.I. Direct Red 81
C.I. Direct Red 2; and
(E) C.I. Direct Green 85.

8. Light-polarizing film according to any one of the preceding claims, wherein the polymer film has been uniaxially press-stretched under at least one pair of pressure rolls held at a temperature of 55—130°C.

9. A light-polarizing film according to any one of the preceding claims, which has been treated with aqueous boric acid solution held at a temperature of 50—80°C.

Patentansprüche

1. Lichtpolarisationsfolie, umfassend eine orientierte Polymerfolie und als Polarisationsselement einen Dichroismusfarbstoff, dadurch gekennzeichnet, daß die orientierte polymere Folie gebildet ist aus einem Polyvinylalkohol oder einem Derivat davon, und das Polarisationsselement wenigstens drei absorbierte Dichroismusfarbstoffe enthält, die ausgewählt sind aus:

(A) gelben Dichroismusfarbstoffen mit einem Hauptabsorptionswellenlängenbereich von 400 bis 500 nm,

(B) schwarzen Dichroismusfarbstoffen mit einem Hauptabsorptionswellenlängenbereich von 450 bis 650 nm,

(C) blauen Dichroismusfarbstoffen mit einem Hauptabsorptionswellenlängenbereich von 570 bis 700 nm,

(D) orangenen oder roten Dichroismusfarbstoffen mit einem Hauptabsorptionswellenlängenbereich von 450 bis 570 nm, und

(E) grünen Dichroismusfarbstoffen mit einem Hauptabsorptionswellenlängenbereich von 600 bis 700 nm oder 400 bis 450 nm, wobei die Lichtpolarisationsfolie über den Bereich des sichtbaren Lichtes von 400 bis 700 nm einen Polarisationskoeffizienten von wenigstens 70% hat und der Unterschied zwischen der minimalen und der maximalen Lichttransmittanz höchstens 20% beträgt.

2. Lichtpolarisationsfolie nach Anspruch 1, wobei über den Bereich des sichtbaren Lichtes von 400 bis 700 nm der Unterschied zwischen dem minimalen und dem maximalen Polarisationskoeffizient höchstens 20%, und die minimale Lichttransmittanz wenigstens 20% beträgt.

3. Lichtpolarisationsfolie nach Anspruch 1 oder 2, wobei die dichroismusfarbstoff wenigstens einen Farbstoff aus jeder Gruppe (A), (B), und (C) gemäß Anspruch 1 umfassen.

4. Lichtpolarisationsfolie nach Anspruch 1 oder 2, wobei die Dichroismusfarbstoffe wenigstens einen Farbstoff aus jeder der Gruppen (A), (B), (C) und (D) gemäß Anspruch 1 umfassen.

5. Lichtpolarisationsfolie nach Anspruch 1 oder 2, wobei die Dichroismusfarbstoffe wenigstens eine aus jeder der Gruppen (A), (C) und (D) gemäß Anspruch 1 umfassen.

6. Lichtpolarisationsfolie nach Anspruch 1 oder 2, wobei die Dichroismusfarbstoffe wenigstens einen aus jeder der Gruppen (C), (D) und (E) gemäß Anspruch 1 umfassen.

7. Lichtpolarisationsfolie nach irgendeinem der Ansprüche 3 bis 6, wobei die Dichroismusfarbstoffe in den verschiedenen Gruppen (A) bis (E), wenn sie vorhanden sind, wie folgt ausgewählt sind:

- (A) C.I. Direct Yellow 12
C.I. Direct Yellow 44;
(B) C.I. Direct Black 17
C.I. Direct Black 19;
(C) C.I. Direct Blue 202
C.I. Direct Blue 1;
(D) C.I. Direct Orange 26
C.I. Direct Orange 107
C.I. Direct Red 31
C.I. Direct Red 81
C.I. Direct Red 2; und
(E) C.I. Direct Green 85.

8. Lichtpolarisationsfolie nach irgendeinem der vorhergehenden Ansprüche, wobei die Polymerfolie einachsrig druckgestreckt ist unter wenigstens einem Paar von Druckwalzen, die auf einer Temperatur von 55 bis 130°C gehalten sind.

9. Lichtpolarisationsfolie nach irgendeinem der vorhergehenden Ansprüche, die mit wässriger Borsäurelösung behandelt worden ist, die auf einer Temperatur von 50 bis 80°C gehalten worden ist.

Revendications

1. Pellicule polarisant la lumière, comprenant une pellicule orientée en polymère et, comme élément polarisant, un colorant dichroïque, caractérisée en ce que la pellicule orientée en polymère est en alcool polyvinylique ou en l'un de ses dérivés, et l'élément polarisant comprend au moins trois colorants dichroïques adsorbés choisis parmi:

(A) des colorants dichroïques jaunes ayant un domaine principal de longueurs d'onde d'absorption compris entre 400 et 500 nm,

(B) des colorants dichroïques noirs ayant un domaine principal de longueurs d'onde d'absorption compris entre 450 et 650 nm,

(C) des colorants dichroïques bleus ayant un domaine principal de longueurs d'onde d'absorption compris entre 570 et 700 nm,

(D) des colorants dichroïques oranges ou rouges ayant un domaine principal de longueurs d'onde d'absorption compris entre 450 et 570 nm,

(E) des colorants dichroïques verts ayant un domaine principal de longueurs d'onde d'absorption compris entre 600 et 700 nm ou entre 400 et 450 nm,

la pellicule polrisant la lumière ayant, dans tout le domaine de la lumière visible, de 400 à 700 nm, un coefficient de polarisation d'au moins 70% et une différence entre le facteur minimum de transmission de la lumière et le facteur maximum de transmission de la lumière d'au plus 20%.

2. Pellicule polarisant la lumière suivant la



revendication 1, dans laquelle, dans tout le domaine de la lumière visible de 400 à 700 nm, la différence entre les coefficients de polarisation minimum et maximum est d'au plus 20%, et le facteur minimum de transmission de la lumière est d'au moins 20%.

3. Pellicule polarisant la lumière suivant la revendication 1 ou 2, dans lesquelles les colorants dichroïques comprennent au moins des colorants choisis, chacun, dans (A), (B) et (C), tels que définis à la revendication 1.

4. Pellicule polarisant la lumière suivant la revendication 1 ou 2, dans lesquelles les colorants dichroïques comprennent au moins des colorants choisis, chacun dans (A), (B), (C) et (D), tels que définis à la revendication 1.

5. Pellicule polarisant la lumière suivant la revendication 1 ou 2, dans lesquelles les colorants dichroïques comprennent au moins des colorants choisis, chacun, dans (A), (C) et (D), tels que définis à la revendication 1.

6. Pellicule polarisant la lumière suivant la revendication 1 ou 2, dans lesquelles les colorants dichroïques comprennent au moins des colorants choisis, chacun, dans (C), (D) et (E), tels que définis à la revendication 1.

7. Pellicule polarisant la lumière suivant l'une

quelconque des revendications 3 à 6, dans laquelle les colorants dichroïques des diverses classes (A) à (E) sont, quand ils sont présents, choisis parmi:

- 5 (A) C.I. Jaune substantif 12
C.I. Jaune substantif 44;
- (B) C.I. Noir substantif 17
C.I. Noir substantif 19;
- 10 (C) C.I. Bleu substantif 202
C.I. Bleu substantif 1;
- (D) C.I. Orange substantif 26
C.I. Orange substantif 107
C.I. Rouge substantif 31
15 C.I. Rouge substantif 81
C.I. Rouge substantif 2; et
- (E) C.I. Vert substantif 85.

8. Pellicule polarisant la lumière suivant l'une quelconque des revendications précédentes, dans laquelle la pellicule en polymère a été étirée à la presse uniaxialement sous au moins une paire de cylindres de pression maintenus à une température de 55 à 130°C.

9. Pellicule polarisant la lumière suivant l'une quelconque des revendications précédentes, qui a été traitée par une solution aqueuse d'acide borique maintenue à une température de 50 à 80°C.



This Sheet Has Been Replaced



8



* C L M S *