

WHAT IS CLAIMED IS:

1. A method for decomposing polypropylene (PP) waste, comprising:
 - a. adding PP waste to a reaction vessel;
 - b. adding at least one oxidizing agent to the reaction vessel to give a mixture;and
 - c. subjecting the mixture obtained in b. to conditions effective to decompose the PP waste to produce decomposition products, wherein the decomposition products comprise at least one dicarboxylic acid optionally substituted by a nitro group; or the salts or esters or anhydrides thereof.
2. The method of claim 1, wherein the decomposition products further comprise at least one carboxylic acid, optionally substituted by a nitro group.
3. The method of claim 1 or 2, wherein the PP waste further comprises at least one plastic material; and at least one non-plastic material.
4. The method of claim 3, wherein the plastic material comprises at least one selected from the group consisting of plastic film, plastic foam, plastic packaging, plastic bags, plastic wrap, and combinations thereof.
5. The method of claim 3, wherein the non-plastic material comprises at least one selected from the group consisting of non-plastic organic material, inorganic material, fluid, and combinations thereof.
6. The method of any one of claims 1-5, wherein the at least one oxidizing agent is oxygen (O_2), nitric oxide (NO), nitrous oxide (N_2O), nitrogen dioxide (NO_2), nitric acid (HNO_3), aqueous nitric acid (HNO_3), or combinations thereof.
7. The method of claim 6, wherein the at least one oxidizing agent is aqueous nitric acid (HNO_3).

8. The method of claim 7, wherein the nitric acid has a concentration of 10-100 wt%.
9. The method of claim 8, wherein the nitric acid has a concentration of about 67 to about 70 wt%.
10. The method of any one of claims 7-9, wherein the weight ratio of nitric acid to PP is at least 3:1.
11. The method of any one of claims 7-9, wherein the weight ratio of nitric acid to PP is at least 10:1.
12. The method of any one of claims 7-9, wherein the weight ratio of nitric acid to PP is 10-100:1.
13. The method of claim 1, wherein the conditions comprise a temperature range from 60 °C to 200 °C.
14. The method of any one of claims 1-13, wherein the conditions comprise an initial pressure range of 0 psi to 1000 psi.
15. The method of any one of claims 14, wherein the conditions comprise the presence of a gas that is at least one selected comprising air, nitrogen (N₂), oxygen (O₂), or combinations thereof.
16. The method of any one of claims 1-15, wherein the conditions comprise a residence time in the reaction vessel of 30 minutes to 30 hours.
17. The method of any one of claims 1-16, wherein the dicarboxylic acid or dicarboxylic acid substituted with at least one nitro group is substituted with one or more methyl groups.

18. The method of any one of claims 1-17, wherein the decomposition products comprise at least one C₄-C₁₅ dicarboxylic acid.
19. The method of any one of claims 1-17, wherein the decomposition products comprise at least one C₄-C₉ dicarboxylic acid.
20. The method of claim 18 or 19, wherein when the dicarboxylic acid comprises a carbon chain of an even number n between the two carboxy groups, it is substituted by (n/2)-1 methyl groups.
21. The method of any one of claims 18-20, when the dicarboxylic acid comprises a carbon chain of an odd number n between the two carboxy groups, it is substituted by (n/2)-1 or (n/2)-2 methyl groups.
22. The method of any one of claims 1-21, wherein the decomposition products comprise at least one of 2-methylsuccinic acid, 3-methylglutaric acid, 2,4-dimethylglutaric acid, 2,4-dimethyladipic acid, 3,5-dimethylpimelic acid, 2,4,6-trimethylpimelic acid, 2,4,6-trimethylsebacic acid, and 2,4,6,8-tetramethyl-azelaic acid.
23. The method of any one of claims 1-22, wherein the decomposition products comprise at least one of Butanedioic acid, methyl-, dimethyl ester; Butanedioic acid, methyl-, dimethyl ester; Butanedioic acid, methyl-, dimethyl ester; Pentanedioic acid, 2,4-dimethyl-, dimethyl ester; 1,4-Benzenedicarbonitrile, 2-formyl-1H-; Pentanedioic acid, 2,4-dimethyl-, dimethyl ester; 5-Acetoxy-3-methyl-hexanoic acid, methyl ester; 9-Decenoic acid, 2,4-dimethyl-, methyl ester, (R,R)-(-)-; Heptanedioic acid, 2-methyl-, dimethyl ester; Heptanedioic acid, 3,5-dimethyl-, dimethyl ester; Quinoline, 2-butyl; Cyclohexanecarboxylic acid, ethyl ester; 3-Cyclobut-1-enyl-hydroxy-2-methyl-propionic acid, methyl ester; Adipic acid, methyl propyl ester; Methyl 2-methyl-3-cyclopropylpropanoate; 2-Propanone, 1-cyclopentyl-3-ethoxy-; Cyclohexane, 1,2-diethyl-, cis-; Cyclohexane, 1,2-diethyl-3-methyl-; Octanedioic acid, 2,2,7,7-tetramethyl-; 9-Decenoic acid, 2,4-dimethyl-, methyl ester, (2S, 4R)-(+)-; O-Fluoroacetophenone oxime; Dibenzo[b,f]oxepin-3-ylamine; Carbamic acid, (4-ethoxyphenyl)-, ethyl ester; Quinoline,

2-(1-methyl-1H-imidazol-4-yl); 2,8-Bis(1,5,5-trimethylpyrrolidin-2,4-dion-3-ylidene)-3,7-diazanonan; 2-Amino-3,5,7,8-tetrahydro-4,6-pteridinedione; or 1,2-Dimethoxy-4-(1,2-dimethoxyethyl)benzene.

24. The method of any one of claims 1-23, wherein the carboxylic acid or dicarboxylic acid is substituted with at least one nitro group.
25. The method of any one of claims 1-24, wherein the carboxylic acid or dicarboxylic acid is substituted in the 2-position with the nitro group.
26. The method of any one of claims 1-24, wherein the carboxylic acid or dicarboxylic acid is substituted in the 3-position with the nitro group.
27. The method of any one of claims 1-24, wherein the carboxylic acid or dicarboxylic acid is substituted at an internal position with the nitro group.
28. The method of any one of claims 1-27, further comprising adding at least one solid state catalyst to the reaction vessel.
29. The method of claim 28, wherein the at least one solid state catalyst is zeolite, alumina, silico-alumino-phosphate, sulfated zirconia, zinc oxide, titanium oxide, zirconium oxide, niobium oxide, iron carbonate, calcium carbide, or combinations thereof.
30. The method of any one of claims 1-29, further comprising separating the decomposition products into a solid phase and a liquid phase.
31. The method of claim 30, wherein the solid phase comprises at least one of oligomer, polymer, or combinations thereof.
32. The method of claim 30, wherein the solid phase further comprises at least one solid state catalyst.

33. The method of claim 30, wherein the liquid phase comprises a carboxylic acid, dicarboxylic acid, carboxylic acid substituted with a nitro group, or dicarboxylic acid substituted with a nitro group, or the salt, or ester or anhydride thereof.
34. The method of any one of claims 1-33, further comprising converting the carboxylic acid optionally substituted with a nitro group and/or the dicarboxylic acid optionally substituted with a nitro group into an ester.
35. The method of any one of claims 30-34 further comprising separating the carboxylic acid optionally substituted with a nitro group and/or the dicarboxylic acid optionally substituted with a nitro group, or the salts, or esters or anhydrides thereof.
36. The method of claim 34, further comprising separating the at least one corresponding ester.
37. The method of claim 36, wherein the ester is at least one of 2-methylsuccinic acid, dimethyl ester; 3-methylglutaric acid, dimethyl ester; 2,4-dimethylglutaric acid, dimethyl ester; 2,4-dimethyladipic acid, dimethyl ester; 3,5-diethylpimelic acid, dimethyl ester; 2,4,6-trimethylpimelic acid, dimethyl ester; 4,6-trimethylsebacic acid, dimethyl ester; 2,4,6,8-tetramethyl-azelaic acid; or a combination thereof.
38. The method of claim 31, further comprising feeding the oligomer, the polymer, and combinations thereof back into the reaction vessel.
39. The method of claim 30, wherein the liquid phase further comprises the at least one oxidizing agent.
40. The method of claim 39, further comprising collecting and regenerating the at least one oxidizing agent.

41. A composition, comprising 2-methylsuccinic acid, 3-methylglutaric acid, 2,4-dimethylglutaric acid, 2,4-dimethyladipic acid, 3,5-dimethylpimelic acid, 2,4,6-trimethylpimelic acid, 2,4,6-trimethylsebacic acid, and 2,4,6,8-tetramethyl-azelaic acid, or the salts, or esters or anhydrides thereof.
42. The composition of claim 41, further comprising at least one of Butanedioic acid, methyl-, dimethyl ester; Butanedioic acid, methyl-, dimethyl ester ; Butanedioic acid, methyl-, dimethyl ester; Pentanedioic acid, 2,4-dimethyl-, dimethyl ester; 1,4-Benzenedicarbonitrile, 2-formyl-1H-; Pentanedioic acid, 2,4-dimethyl-, dimethyl ester; 5-Acetoxy-3-methyl-hexanoic acid, methyl ester; 9-Decenoic acid, 2,4-dimethyl-, methyl ester, (R,R)-(-); Heptanedioic acid, 2-methyl-, dimethyl ester; Heptanedioic acid, 3,5-dimethyl-, dimethyl ester; Quinoline, 2-butyl; Cyclohexanecarboxylic acid, ethyl ester; 3-Cyclobut-1-enyl-hydroxy-2-methyl-propionic acid, methyl ester; Adipic acid, methyl propyl ester; Methyl 2-methyl-3-cyclopropylpropanoate; 2-Propanone, 1-cyclopentyl-3-ethoxy-; Cyclohexane, 1,2-diethyl-, cis-; Cyclohexane, 1,2-diethyl-3-methyl-; Octanedioic acid, 2,2,7,7-tetramethyl-; 9-Decenoic acid, 2,4-dimethyl-, methyl ester, (2S, 4R)-(+)-; O-Fluoroacetophenone oxime; Cyclohexanone, 2-(1-mercapto-1-methylethyl)-5-methyl-, trans-; Dibenzo[b,f]oxepin-3-ylamine; Carbamic acid, (4-ethoxyphenyl)-, ethyl ester; Quinoline, 2-(1-methyl-1H-imidazol-4-yl)-; 2,8-Bis(1,5,5-trimethylpyrrolidin-2,4-dion-3-ylidene)-3,7-diazanonan; 2-Amino-3,5,7,8-tetrahydro-4,6-pteridinedione; or 1,2-Dimethoxy-4-(1,2-dimethoxyethyl)benzene, or the salts or the esters or the anhydrides thereof.