

DEFECT-RICH CRYSTALLINE (METALLO)SILICATES AND
PROCESS FOR PREPARING SUCH (METALLO)SILICATES

The present invention relates to defect-rich crystalline (metallo)silicates, a process for preparing such (metallo)-silicates and to the use of these crystalline (metallo)silicates as catalysts or catalyst carriers.

In general, crystalline (metallo)silicates in both natural and synthetic forms are of particular interest since they find wide and promising application in industry as, for instance, catalyst carriers or catalysts in various types of (hydro)conversion processes.

At the present moment a large number of suitable methods for preparing the various crystalline (metallo)silicates have become available. The use of a template, in particular an organic nitrogen containing compound, in a reaction mixture wherein the various forming components are present in defined molar ratios is among the best known techniques in the synthesis of crystalline(metallo)silicates.

Crystalline (metallo)silicates obtained from such a reaction mixture generally contain in the as-synthesized form substantial amounts of template. In order to activate the crystalline products obtained the template is normally removed substantially. This is usually achieved by subjecting the crystalline products to a calcination treatment.

In the calcination treatment the template and/or degradation products thereof will substantially be removed from the crystalline products. Thus, active substantially template-free crystalline (metallo)-

silicates may be obtained which can suitably be used in the various processes.

It should be noted, however, that it is well known that not all crystalline (metallo)silicates in the as-synthesized form can suitably be subjected to a calcination treatment normally necessary to remove the template and/or degradation products thereof. Some crystalline (metallo)silicates apparently have such a poor intrinsic stability that during a calcination treatment their crystalline structures will collapse.

Crystalline (metallo)silicates can generally be defined as built up of three-dimensional frameworks of tetrahedral SiO_4 and MO_4 units (the so-called TO_4 units, T=tetrahedral) which are corner-linked via oxygen atoms. In this respect each Si site should theoretically have four oxygen corner-linked T-neighbours. These Si sites are so-called Q^4 sites. It will be understood that the Si sites which terminate the framework will have at most three oxygen corner-linked T-neighbours, which is normally the case. Such Si sites are referred to as Q^3 sites and form a relatively low percentage of the total number of Si sites (typically less than 1% for particles of 1 micron). Recently it has been recognized in silica-rich molecular sieves that Si sites having only three oxygen-linked T-neighbours (internal Q^3 sites) also exist in the internal framework. It is known that direct information about the presence of these internal Q^3 sites can very conveniently be obtained from magic-angle-spinning (MAS) solid-state ^{29}Si -NMR spectroscopy. In the context of the present specification these internal Q^3 sites are hereinafter to be referred to as defects.

It is known to those skilled in the art that after substantial removal of the template from the zeolite by a standard calcination procedure (550 °C in air for a period of four hours) defects are hardly present anymore.

Reference is made in this respect also to Zeolites, 1986, Vol 6, pp 14-16, wherein it is concluded that in some calcined ZSM-5 samples the ion-exchange capacity in excess of the framework aluminium content observed is due to a small amount of internal silanol defect sites.

It has now been found that substantially template-free crystalline microporous (metallo)silicates can be provided in which a substantial amount of the internal defects initially present in the as-synthesized form is retained.

Such crystalline (metallo)silicates are of particular interest since they may suitably be used to incorporate catalytically active species into the framework in an amount that substantially exceeds the normal metal ion exchange value.

Object of the present invention is to provide substantially template-free crystalline microporous (metallo)silicates which comprise a substantial number of internal framework defects.

The present invention thus relates to crystalline microporous (metallo)silicates having a maximum M/Si molar ratio of 0.03, wherein M represents at least one of Al, Fe, B, Ga or Ti, containing less than 1%wt of organic template (originated) material and having a Relative Defect Retention (RDR)-value of 0.1-1, wherein the RDR-value is defined as $(C - C^*) / (i - C^*)$, wherein C represents the percentage of defects present, C* represents the percentage of defects retained when subjecting the corresponding at least 1%wt of organic template (originated) material containing crystalline (metallo)silicate to a standard calcination treatment in air at a temperature of 550 °C for a period of 4 hours, wherein i represents the percentage of defects initially present in the uncalcined corresponding organic template containing crystalline (metallo)silicate, and wherein

$i > C^*$.

It should be noted that the RDR-value is a measure of the extent to which initially present defects in a template containing crystalline (metallo)silicate can be retained, relative to the extent to which defects would be retained if the material were to be subjected to a standard calcination treatment in air at a temperature of 550 °C for a period of 4 hours.

This means that the crystalline (metallo)silicates according to the present invention contain a percentage of defects (C) which is larger than would be retained (expressed as C^*) when subjecting the uncalcined corresponding template containing crystalline (metallo)silicate to a standard calcination in air at a temperature of 550 °C for a period of 4 hours.

This excess of defects, expressed as $(C - C^*)$, is referred to as the Absolute Defect Retention (ADR).

Suitably, the crystalline microporous (metallo)silicates according to the present invention have a ADR of at least 2%, preferably at least 4%.

The uncalcined organic template containing crystalline (metallo)silicates suitably contain a percentage of defects (i), such that $(i - C^*)$ is at least 4%, preferably at least 10%.

The crystalline microporous (metallo)silicates according to the present invention preferably have a RDR value of 0.20-0.90, more preferably 0.30-0.90.

Preferably, the crystalline microporous (metallo)silicates according to present invention have a maximum M/Si molar ratio of 0.015. In particular, the present invention relates to crystalline microporous (metallo)silicates as described hereinabove wherein M represents aluminium.

The crystalline microporous (metallo)silicates according to the present invention comprise various

structures, provided that they fulfil the requirements as defined hereinbefore. For instance, defect-rich forms of ZSM-type (metallo)silicates, SCS-type (metallo)silicates, ferrierite, mordenite, zeolite β and other types of zeolitic (metallo)silicates are examples in accordance with the present invention.

Suitably one or more catalytically active species are incorporated in the crystalline microporous (metallo)silicates according to the present invention. Preferably, the catalytically active species comprise one or more salts of metals of Group IVB, VB, VIB, VIIB, or VIII as well as ammonium ions and/or protons. They can be incorporated by well-known techniques such as, for example, impregnation and ion-exchange. It will be clear to those skilled in the art that the crystalline microporous (metallo)silicates according to the present invention can suitably be applied as catalyst or catalyst carrier in a variety of processes, and can also be exposed to any suitable regeneration method known in the art.

The present invention further relates to a process for the preparation of crystalline microporous (metallo)silicates as defined hereinabove, which comprises subjecting a crystalline (metallo)silicate having a maximum M/Si molar ratio of 0.03, wherein M represents at least one of Al, Fe, B, Ga or Ti, and containing at least 1%wt of template to a heat treatment which is carried out in the presence of oxygen at a temperature of 400-600 °C and a pressure of at most 100 mbar for at least 1 hour.

Preferably, the heat treatment in the process according to the present invention is carried out at a temperature of 450-500 °C. The heat treatment is preferably carried out at a pressure of less than 20 mbar, and for a period of time of at least 2 hours.

The heat treatment in the present process is suitably carried out in air. Other oxygen-containing gases can also suitably be used.

The crystalline (metallo)silicate to be subjected to the present process contains at least 1%wt of template. The template comprises in principle all templates which can suitably be used in the preparation of crystalline (metallo)silicates. Suitable examples are organic templates as (un)substituted secondary or tertiary amines such as di- and tri-alkanolamines, dioxane, trioxane morpholine, and templates which comprise a quaternary ammonium cation. Templates comprising a quaternary ammonium cation are preferred. Preferably, the crystalline (metallo)silicates to be subjected to the present process have a maximum M/Si molar ratio of 0.015. Preferably, crystalline aluminosilicates are subjected to the heat treatment according to the present invention.

The invention will now be illustrated by the following Examples.

Example 1

A crystalline microporous (metallo)silicate according to the present invention was prepared as follows: Waterglass (ex PQ) was added to a solution containing 96 %wt H₂SO₄, octane-1,8-diamine (OD) and water to give a starting mixture of the following molar composition: 25 SiO₂:7.4 Na₂O:8.4 H₂SO₄:7.5 OD:1000 H₂O. The product obtained was subsequently kept at 160 °C for a period of 72 hours in a stirred autoclave. The crystalline product thus obtained (ZSM-48) was separated by filtration, water washed and dried at 120 °C. Two samples of the product obtained were exposed to respectively a heat treatment according to the present invention which was carried out in the presence of oxygen at a temperature of 470 °C, a pressure of 5 mbar for a period of 16 hours and a calcination treatment in air at a temperature of 550 °C

for a period of 4 hours.

Example 2

An experiment was carried out in substantially the same manner as described in Example 1, except that the starting mixture contained 96 %wt H_2SO_4 , tetramethylammonium bromide (TMABr), NaAlO_2 , NaOH, octane-1,8-diamine (OD), silica and water, and that the heat treatment according to the present invention was carried out at 460 °C. The molar composition of the starting mixture was as follows:

25 SiO_2 :0.1 Al_2O_3 :7.4 Na_2O :7.4 H_2SO_4 :7.5 OD:0.75
TMABr:1000 H_2O . The crystalline product obtained was of the ZSM-48 type.

Example 3

An experiment was carried out in substantially the same manner as described in Example 1, except that the starting mixture contained silica, sodium aluminate, sodium hydroxide, tetramethylammonium hydroxide (TMAOH), tetramethylammonium chloride (TMACl) and water, that the product obtained was kept at 190 °C for a period of 64 hours in a stirred autoclave, and that the heat treatment was carried out at 20 mbar. The molar composition of the starting mixture was as follows:

25 SiO_2 :0.025 Al_2O_3 :0.5 Na_2O :5 TMA_2O :8 TMACl:400 H_2O .
The crystalline product obtained was of the SCS-5 type.

Example 4

An experiment was carried out in substantially the same manner as described in Example 1, except that the starting mixture contained silica, sodium aluminate, sodium hydroxide, tetrapropylammonium hydroxide (TPAOH) and water, that the product obtained was kept at 170 °C for a period of 32 hours in a stirred autoclave, and that the heat treatment was carried out at 10 mbar. The molar composition of the starting mixture was as follows:

25 SiO₂:0.025 Al₂O₃:Na₂O:4.5 TPA₂O:450 H₂O. The crystalline product obtained was of the ZSM-5 type.

Example 5

An experiment was carried out in substantially the same manner as described in Example 3, except that the starting mixture contained ammonia instead of sodium aluminate, and that the heat treatment was carried out at 460 °C and 20 mbar. The molar composition of the starting mixture was as follows:

25 SiO₂:NH₃:0.5 Na₂O:2.5 TPA₂O:450 H₂O. The crystalline product obtained was of the ZSM-5 type.

The values of C, C*, ADR, and i, expressed as percentages, and RDR as determined with solid-state ²⁹Si-NMR-spectroscopy in the experiments described, and having the meanings as defined hereinbefore, are together with the Si/Al molar ratios of the untreated materials summarized in Table 1.

Table 1.

	Si/Al	i	C*	C	RDR	ADR
Example 1	770	8	3	7	0.8	4
2	110	8	0	5	0.6	5
3	80	35	5	12	0.2	7
4	220	16	1	6	0.3	5
5	>800	24	10	15	0.4	5

It will be clear from the results presented in Table 1 that the crystalline (metallo)silicates according to the present invention contain substantially larger amounts of defect sites than the corresponding crystalline (metallo)silicates which have been exposed to a calcination treatment in air at 550 °C for a period of 4 hours.



C L A I M S

1. Crystalline microporous (metallo)silicates having a maximum M/Si molar ratio of 0.03, wherein M represents at least one of Al, Fe, B, Ga or Ti, containing less than 1 %wt of organic template (originated) material and having a Relative Defect Retention (RDR)-value of 0.1-1, wherein the RDR-value is defined as $(C - C^*) / (i - C^*)$, wherein C represents the percentage of defects present, C* represents the percentage of defects retained when subjecting the corresponding at least 1%wt of organic template (originated) material containing crystalline (metallo)silicate to a standard calcination treatment in air at a temperature of 550 °C for a period of 4 hours, wherein i represents the percentage of defects initially present in the uncalcined corresponding organic template containing crystalline (metallo)silicate, and wherein $i > C^*$.
2. Crystalline microporous (metallo)silicates according to claim 1 having a RDR-value of 0.20-0.90, more preferably 0.30-0.90.
3. Crystalline microporous (metallo)silicates according to claim 1 or 2 having an Absolute Defect Retention (ARD)-value of at least 2%, more preferably at least 4%, wherein the ADR-value is defined as $(C - C^*)$, and C and C* have the meanings as described hereinbefore.
4. Crystalline microporous (metallo)silicates according to any one of claims 1-3 having a maximum M/Si molar ratio of 0.015.
5. Crystalline microporous (metallo)silicates according to any one of claims 1-4 wherein M represents Al.
6. Crystalline microporous (metallo)silicates according to any one of claims 1-5, wherein one or more



catalytically active species have been incorporated.

7. Crystalline micro-porous (metallo)silicates according to any one of claims 1-6, wherein the catalytically active compounds comprise one or more salts of metals of Group IVB, VB, VIB, VIIB or VIII.

8. Process for the preparation of crystalline microporous (metallo)silicates as defined in any one of claims 1-7, which comprises subjecting a crystalline (metallo)silicate having a maximum M/Si molar ratio of 0.03, wherein M represents at least one of Al, Fe, B, Ga or Ti, and containing at least 1 %wt of template to a heat treatment which is carried out in the presence of oxygen at a temperature of 400-600 °C and a pressure of at most 100 mbar for at least 1 hour.

9. Process according to claim 8, in which the calcination treatment is carried out at a temperature of 450-500 °C.

10. Process according to claim 8 or 9, in which the calcination treatment is carried out at a pressure of less than 20 mbar.

11. Process according to any one of claims 8-10, in which the calcination treatment is carried out for at least 2 hours.

12. Process according to any one of claims 8-11, in which the calcination treatment is carried out in air.

13. Process according to any one of claims 8-12, in which the template comprises an organic cation or a precursor thereof.

14. Process according to any one of claims 8-13, in which the template comprises a quaternary ammonium cation.

15. Process according to any one of claims 8-14, in which the crystalline (metallo)silicate has a maximum M/Si molar ratio of at least 0.015.

16. Process according to any one of claims 8-15, substantially as described hereinbefore with particular



- 11 -

reference to the Examples.

17. Process for carrying out catalytic reactions in which use is made of a crystalline microporous (metallo)-silicate as claimed in any one of claims 1-7.

CS6/T5230FF