

We claim:

1. A method for processing a substrate within a process chamber, comprising:
 - applying a direct current to an electrode disposed within a pedestal on which the substrate is disposed within the process chamber;
 - flowing one or more process gases into the process chamber subsequent to applying the direct current to the electrode;
 - applying radio frequency (RF) power to a showerhead within the process chamber, subsequent to flowing one or more process gases into the process chamber;
 - processing the substrate subsequent to applying RF power;
 - stopping the application of the RF power subsequent to processing the substrate;
 - removing the one or more process gases from the process chamber subsequent to stopping the application of RF power; and
 - stopping the application of the DC power subsequent to removing the one or more process gases.
2. The method of claim 1, wherein applying the direct current to the electrode further comprises applying a DC voltage of about 300 volts to about 500 volts and applying the RF power to the showerhead further comprises applying power of about 100 watts to about 6000 watts.
3. The method of claim 2, wherein the one or more process gases include helium.
4. The method of claim 2, wherein during the processing the substrate the pressure within the process chamber is about 5 Torr to about 15 Torr and the spacing between the showerhead and the pedestal is about 450 mils to about 750 mils.
5. A method for processing a substrate, comprising sequential operations of:

- (a) positioning the substrate on a surface of a pedestal within a process chamber, wherein the pedestal is at a first spacing from a showerhead;
- (b) applying a DC voltage at a first DC voltage level to an electrode disposed within the pedestal to chuck the substrate;
- (c) flowing one or more process gases into the process chamber through the showerhead;
- (d) applying an RF power at a first RF power level to the showerhead within the process chamber;
- (e) increasing the DC voltage and the RF power to a second DC voltage level and a second RF power level either prior to, during, or both prior to and during processing of the substrate;
- (f) decreasing the DC voltage and the RF power to a third DC voltage level and a third RF power level after processing of the substrate;
- (g) moving the pedestal within the process chamber to a second spacing from the showerhead;
- (h) stopping the application of RF power to the showerhead;
- (i) removing the one or more process gases from the process chamber; and
- (j) stopping the application of the DC voltage to the electrode.

6. The method of claim 5, wherein the first spacing is about 450 mils to about 750 mils and the second spacing is about 200 mils to about 400 mils.

7. The method of claim 5, wherein the first DC voltage level is about 300 volts to about 500 volts.

8. The method of claim 5, wherein the one or more process gases include helium.

9. The method of claim 5, wherein the first RF power level is greater than about 100.

10. The method of claim 5, wherein the second DC voltage level is about 800 volts to about 1100 volts and the second RF power level is greater than about 1000 watts.

11. The method of claim 5, wherein the pressure within the process chamber during the substrate processing is about 5 Torr to about 15 Torr and the third DC voltage level is about 300 volts to about 500 volts.

12. A method for processing a substrate, comprising:
 positioning the substrate on a surface of a pedestal, wherein the pedestal is at a first spacing from a showerhead within a process chamber;
 applying a DC voltage at a first DC voltage to an electrode disposed within the pedestal;
 flowing a first process gas into the process chamber through the showerhead after the application of the DC voltage at a first DC voltage level;
 applying radio frequency (RF) power to the showerhead within the process chamber at a first RF power level;
 moving the pedestal to a second spacing from the showerhead, wherein the second spacing is closer to the showerhead than the first spacing;
 flowing a second process gas mixture into the process chamber through the showerhead;
 increasing the DC voltage and the RF power to a second DC voltage level and a second RF power level to either prior to, during, or both prior to and during the performance of a process on the substrate;
 decreasing the DC voltage and the RF power after performing the process on the substrate to a third DC voltage level and a third RF power level;
 flowing the first process gas into the process chamber through the showerhead while removing the second process gas mixture from the process chamber after performing the process on the substrate;
 moving the pedestal within the process chamber to a third spacing from the showerhead;
 stopping the application of the RF power;

removing the first process gas from the process chamber after stopping the application of the RF power; and

stopping the application of the DC power after removing the first process gas from the process chamber.

13. The method of claim 12, wherein the pedestal is spaced apart from the showerhead between about 450 and about 750 mils at the first spacing.

14. The method of claim 13, wherein the first DC voltage level is about 300 volts to about 500 volts and the first process gas is helium.

15. The method of claim 14, wherein the second DC voltage level is about 800 volts to about 1100 volts, the second process gas comprises either argon, propene, or both argon and propene, and a pressure within the process chamber during the substrate processing is about 5 Torr to about 15 Torr subsequent to flowing the first process gas into the process chamber.