

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification⁶:

B29C 47/12, D01D 4/02

A1

(11) International Publication Number:

WO 95/24303

(43) International Publication Date: 14 September 1995 (14.09.95)

(21) International Application Number:

PCT/US95/03015

(22) International Filing Date:

13 March 1995 (13.03.95)

(30) Priority Data:

08/212,080

11 March 1994 (11.03.94)

US

(71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY
[US/US]; 1007 Market Street, Wilmington, DE 19898 (US).(72) Inventors: RAKESTRAW, Julie, Anderson; 8 Spring Hill
Lane, Newark, DE 19711-2826 (US). WAGGONER,
Marion, Glen; 36 Sageway Road, R.D. 3, Hockessin, DE
19707 (US).(74) Agents: KONKOL, Chris, P. et al.; E.I. du Pont de Nemours
and Company, Legal/Patent Records Center, 1007 Market
Street, Wilmington, DE 19898 (US).(81) Designated States: AM, AU, BB, BG, BR, BY, CA, CN, CZ,
EE, FI, GE, HU, JP, KG, KP, KR, KZ, LK, LR, LT, LV,
MD, MG, MN, MX, NO, NZ, PL, RO, RU, SG, SI, SK,
TJ, TT, UA, UZ, VN, European patent (AT, BE, CH, DE,
DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI
patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE,
SN, TD, TG), ARIPO patent (KE, MW, SD, SZ, UG).

Published

With international search report.


Before the expiration of the time limit for amending the
claims and to be republished in the event of the receipt of
amendments.

SG 9611430-1

RTMA

+ PER + Annexes

(54) Title: POLYMER EXTRUSION DIE



(57) Abstract

An improved die, containing one or more orifices, for the extrusion of polymers is disclosed wherein the orifices are flared at the polymer discharge end, and the orifices have certain relative dimensions and configurations. The dies are useful for producing items such as films, shaped profiles, sheets, fibers, strands, etc. Also disclosed are a process for using the die, and an extrusion apparatus containing such a die.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

96 11430-1

TITLE

POLYMER EXTRUSION DIE

FIELD OF THE INVENTION

This invention concerns an improved die for the
5 extrusion of polymers, wherein the exit of the die
orifice(s) is flared, and the flared and unflared
sections have specified relative dimensions and shapes.

TECHNICAL BACKGROUND

Extrusion of polymers through a die to form shaped
10 extrudates is a well known process, and is extensively
used commercially, see for instance H. Mark, et al.,
Ed., Encyclopedia of Polymer Science and Engineering,
2nd Ed., vol. 6, John Wiley & Sons, New York, 1986,
p. 571-631 and p. 802-824 (fibers), which is hereby
15 included by reference. Items that can be made by
polymer extrusion include films, fibers, sheet, strands
(including those strands to be cut into pellets for
further processing), and shaped profiles. The
extrudates are usually essentially continuous, and are
20 often cut into useable lengths.

The extrusion process is one in which the molten
polymer is forced through a shaped orifice, and the
extrudate is then cooled, usually until solid. The
cross section of the extrudate (perpendicular to the
25 flow direction) usually has the same shape as the
orifice. Due to the importance of extrusion
commercially, improved dies are constantly being sought,
so that the process runs more cheaply, and/or with less
off-quality production, etc. A particular problem in
30 this process is "die drips", which are small portions of
(usually) molten polymer which collect around the die
orifice, and which can cause problems of product defects
and downtime.

U.S. Patent 4,822,546 describes a polymer extrusion
35 die which is advantageous for use with high flow

polymers and wherein the die is part of an underwater pelletizer. There is no mention of the use of this die in other extrusion processes.

SUMMARY OF THE INVENTION

- 5 This invention concerns a die having flared orifices for the extrusion of polymers, comprising, a die body having one or more flared orifices having the following components:
- 10 a first zone having surface S_1 ;
a second zone having surface S_2 ;
a third zone having surface S_3 ;
a length L_1 which is the total length of said first, second and third zones;
a length L_3 which is the length of said third
15 zone;
a polymer flow axis A; and
said die has a surface S_5 on a discharge side of said die; and
wherein:
- 20 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;
A and S_3 are perpendicular to S_5 ;
- 25 if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;
- if said second zone has more than one step area change, an analogous angle of each step
30 corresponding to said angle T is 45° to 90° ;
- an area of the orifice in said third zone is about 1.1 to 1.7 about times an area of the orifice at said first zone; and
a shape of said first zone and a shape of said
35 third zone are geometrically similar.

This Sheet Has Been Replaced



This invention also includes a polymer extrusion apparatus comprising a die and a means for pumping a polymer through said die, wherein the improvement comprises, a die for the extrusion of polymers having one or more flared orifices having the following components:

- a first zone having surface S_1 ;
- a second zone having surface S_2 ;
- a third zone having surface S_3 ;
- a length L_1 which is the total length of said first, second and third zones;
- a length L_3 which is the length of said third zone;
- a polymer flow axis A; and

said die has a surface S_5 on a discharge side of said die; and

wherein:

- L_1/L_3 is about 2 or more;
- L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;
- A and S_3 are perpendicular to S_5 ;
- if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;
- if said second zone has more than one step area change, an analogous angle of each step corresponding to said angle T is 45° to 90° ;
- an area of the orifice in said third zone is about 1.1 to 1.7 about times an area of the orifice at said first zone;
- a shape of said first zone and a shape of said third zone are geometrically similar;
- and providing that surface S_5 of said die is not in contact with a liquid cooling medium.

This invention further concerns a process for the extrusion of polymer, comprising extruding a polymer through a die having one or more flared orifices having the following components:

- 5 a first zone having surface S_1 ;
 a second zone having surface S_2 ;
 a third zone having surface S_3 ;
 a length L_1 which is the total length of said first, second and third zones;
- 10 a length L_3 which is the length of said third zone;
- a polymer flow axis A; and
 said die has a surface S_5 on a discharge side of said die; and
- 15 wherein:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;
- 20 A and S_3 are perpendicular to S_5 ;
 if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;
- if said second zone has more than one step area change, an analogous angle of each step corresponding to said angle T is 45° to 90° ;
- 25 an area of the orifice in said third zone is about 1.1 to about 1.7 times an area of the orifice at said first zone;
- 30 a shape of said first zone and a shape of said third zone are geometrically similar;
 and providing that surface S_5 of said die is not in contact with a liquid cooling medium.

DETAILS OF THE INVENTION

The disclosure concerning the die and its orifices herein applies to the die itself, the die when included in an extrusion apparatus, and the die when used in the
5 process of extruding polymer.

DESCRIPTION OF THE DRAWINGS

The Figures herein are not to scale.

A cross section of a flared die orifice, with one step in Z_2 (see below), of this invention is shown in
10 Figure 1. This cross section is perpendicular to surface S_5 (see below). Only a part of the die body having one orifice is shown. The die may contain more than one orifice, and also may have other functional parts that extrusion dies may normally have, such as a
15 means for attaching the die to the extrusion apparatus, a means for measuring the temperature of the die, a means for heating the die, a means for sealing the contact surfaces between the die and the remainder of the extrusion apparatus (so molten polymer will not leak),
20 etc.

Through the length of the orifice, the orifice can be considered to have three zones, a first zone Z_1 having surface S_1 , a third (flared) zone Z_3 having surface S_3 , and a second or transition zone Z_2 having
25 surface S_2 . S_4 of Figure 1 is the surface on the inlet side of the die, while S_5 is the surface on the outlet or discharge side of the die. S_4 need not be flat, and S_5 must be flat and perpendicular to A only in proximity to the orifice (close enough for extrudate to touch S_5).
30 It is preferred if S_1 is approximately parallel to polymer flow axis A (by approximately parallel is meant plus or minus 5°), and more preferred if it is S_1 is parallel to A. S_3 , the orifice surface of Z_3 , is parallel to the polymer flow axis A and perpendicular to
35 surface S_5 .

Cross sections AA and BB of the die in Figure 1 are perpendicular to flow axis A. L_1 is the total length of the orifice, while L_3 is the length of zone Z_3 . The cross sections at AA and BB go through the (complete) orifice shown in Figure 1. The cross section BB is taken at a spot near where zones Z_1 and Z_2 meet, but it is in Z_1 . The area of the orifice at the cross section AA is about 1.1 to 1.7 times the area of the same orifice at cross section BB, preferably about 1.3 to 1.45 (or the area after each step in Z_2 is at least 1.1 times the area of Z_1 or the previous step). L_1/L_3 is about two or more, preferably about 2 to about 20, and more preferably about 3 or more or about 3 to about 10.

The cross sections of the orifice at AA and BB are substantially geometrically similar to each other. By geometrically similar is meant "Two geometric figures are similar if one can be made congruent to the other by using a transformation of similitude, i.e., if one is a magnification or reduction of the other.", definition of "similar" from James and James Mathematics Dictionary, 3rd Ed., D. Van Nostrand Co., Inc., Princeton, NJ, 1968, p. 331. In other words the orifice cross section at BB is a reduction in size of the cross section at AA, so that the area of the orifice cross section at AA is 1.1 to 1.7 times that at cross section AA.

The angle T is the angle formed by S_2 and A or approximately at which the orifice transitions from S_1 to S_2 , if Z_2 contains one step. This transition may be in one step or a series of steps. The transition zone step(s) may also be in the form of a curve. The line R is then taken as a tangent to the curve at the point at which the curve meets the surface of Z_1 . In a preferred die, angle T (or angles analogous to T in which Z_2 has more than one step) is about 60° to 90° .

Figure 2 is an outline of the orifice used in the Examples herein. It is described in those Examples.

As the polymer flows into Z_1 it of course assumes the cross sectional shape of Z_1 (cross section at BB).
5 As the polymer flows through the transition zone, and then into Z_3 , it expands to have a cross section such as that at AA, i.e., it eventually matches the shape and size of the orifice at Z_3 . The polymer exiting the die will therefore have the shape and approximate size of
10 the cross section at AA if L_3 is long enough (the cross section of the polymer exiting the die may be somewhat larger than the orifice cross section at AA due to the well known phenomenon of "die swell"). While Z_1 is necessary for the die orifice herein, the die may also
15 include an "extension" of Z_1 (but not part of L_1 or Z_1) which is not necessarily the same size and/or shape as Z_1 , which extension conducts melted polymer to Z_1 .

Within Z_2 , there may be one, or more than one, change in the area of orifice. Each change is herein
20 termed a step. If there is a single step, the only requirement for Z_2 is the angle T be about 45° to 90° . Z_3 , immediately adjacent to the step, has S_3 as its surface. If there is more than one step, each step has an angle which corresponds or is analogous to angle T
25 when there is only one step. Each of these angles must also be about 45° about 90° . Only the orifice surface downstream (as the polymer flows) of the last step is S_3 . All of the other surfaces in Z_2 which correspond to S_3 (herein collectively S_{2A}) in each of the other steps
30 is in Z_2 , and each of these surfaces is parallel to A. It is preferred that each of these surfaces parallel to A are long enough so that before the next step the polymer is substantially in contact with the periphery of each surface S_{2A} .

It is believed that the minimum value of L_3 is desirable because it allows the polymer to substantially achieve the final shape and size desired for the extrudate. By "substantially in contact with" is meant
5 the polymer is either in contact with, or within 0.13 mm of the surface (S_3 and/or S_{2A}).

It is believed that S_3 and S_{2A} should not extend too much longer than the length required for the polymer to substantially contact the full periphery of S_3 or S_{2A} .
10 The length needed (of S_3 or S_{2A}) for any particular process, which includes the variables of extrudate shape and size, polymer used, polymer temperature, extrusion rate, etc., can be readily determined by simple routine experimentation, by varying L_3 in a series of die
15 inserts, as inserts were used in the Examples herein.

The die may be made out of any material that polymer extrusion dies are usually made out of, such as tool steel. Care should be taken to avoid nicks and other blemishes on the orifice surfaces, especially at
20 angled surfaces. The surface finish of the die should be that normally given to extrusion dies. All measurements herein are construed to have the usual machining and other fabrication errors normal in die manufacture.

25 The extrusion die may contain one or more orifices. Many dies have only one orifice, particularly if the cross section of the orifice is large. Other dies such as those for forming fibers (often called spinnerets) usually have many orifices. It is preferred if the
30 cross sections at AA (Z_1) and BB (Z_2) (and hence the orifice) are both circular, both square or rectangular.

The extrusion may be carried out in any apparatus in which extrusions are normally done. Such an apparatus usually includes a means for melting the
35 polymer (except if molten polymer is supplied to the

apparatus), and a means to pump or force the molten polymer through the die orifices at an appropriate rate. Useful devices for pumping or melting and pumping are gear pumps, single and twin screw extruders, pistons (as
5 in a ram extruder), or a pressurized vessel (as by gas pressure) containing molten polymer. Extrusion conditions, such as polymer temperature, may be those normally used in extrusions of that polymer.

After exiting the extrusion die the polymer is
10 usually solidified (or in the case of elastomers may be crosslinked). Thermoplastics are normally solidified by cooling. The cooling medium may be air or a liquid such as water. If the cooling medium is a liquid, the liquid is not in contact with surface S_5 of the die. If the
15 extrudate is to be cut into pieces, such as pellets, it is preferred if the cutter (blade) is not in direct contact with the die, particularly surface S_5 .

The polymers useful with the extrusion die described herein include thermoplastics, elastomers
20 before crosslinking, and thermosets before crosslinking. Thermoplastics include polyesters, polyamides, polyethers, polyolefins, halogenated polyolefins, fluorinated polyolefins, thermoplastic polyimides, poly(imide-ethers) and polycarbonates, and the like.
25 Polymers which are extruded may contain the usual additives such as fillers, reinforcing agents, antioxidants, colorants, pigments, etc. Exemplary of these are carbon black, glass fiber, clay, mica, graphite fiber, titanium dioxide, carbon fibers and
30 natural fibers.

In all of the Examples herein the orifices had a circular cross section (AA and BB).

EXPERIMENTAL APPARATUS FOR EXAMPLES 1-3

A 57 mm twin-screw Werner & Pfleiderer (W&P)
35 extruder was used to melt the polymer and develop

sufficient pressure to force the resin through the die. With the exception of the test die, all operating conditions, in terms of barrel temperatures, screw rpm, feed rates, etc. used were normal processing conditions for the polymer tested.

Rynite® and Zytel® resins are commercially available from E. I. du Pont de Nemours and Company.

EXAMPLE 1

The die plate used had holes for two die inserts.

10 The inserts were placed into the die plate from the rear and secured with a retainer ring. The first insert, which was the control, had a standard configuration with a 4.5 mm diameter die land and an aspect ratio of 3/1. The second insert, the test orifice, had a flared

15 section at the end of the die, as shown in Figure 2. The inner diameter in the first section of the die land (shown as 1 in Figure 2) was 4.5 mm, as with the control die. The inner diameter of the flared section (indicated by 2 in Figure 2) was 5.4 mm, giving a

20 diameter ratio of 1.2. The ratio of the area in the expanded section to the unexpanded section was 1.44. The depth of the flare from the face into the die (shown as 3 in Figure 2) was 6 mm, or 1.33 times the original diameter.

25 The total throughput of resin was 68 kg/hr, or 34 kg/hr/orifice. The resin tested was Zytel® 70G33, nylon 6,6 reinforced with 33% chopped glass fiber. Within 30 seconds after startup, accumulation of drips was evident at the exit of the strand from the standard

30 die. The strand exiting from the flared die showed improved strand quality and no drips. Five minutes after startup, the exit face of the die surrounding the flared die was still clean. The exit face surrounding the standard die was surrounded with die drips which

were approximately 1/8-1/4" long and beginning to turn brown due to thermal degradation.

EXAMPLE 2

The extruder and die plate were identical to those described in Example 1. The resin tested was Rynite® 530, a blend containing primarily of poly(ethylene terephthalate) resin and 30% chopped glass fiber. The test was run with a throughput of 68 kg/hr through 2 orifices. An extremely rapid buildup of drips was observed on the standard die, with significant accumulation in less than 2 minutes. Small droplets of molten resin were observed surrounding the flared die exit shortly after startup. After 5 minutes, the die face surrounding the standard die was coated with a mixture of resin and fiberglass, and substantial degradation was evident. The die face surrounding the flared die showed the original droplets but no growth had occurred. After 10 minutes, large accumulations of drips were evident at the standard die, and the drips were beginning to interfere with the flow of the strand. The flared die still showed no growth of the initial droplets.

EXAMPLE 3

The extruder and die plate were identical to those described above. The resin tested was Zytel® 103, an unreinforced nylon-6,6 resin. Approximately 20 minutes after startup, the standard die showed growth of drips surrounding the exit of the strand from the die. The die face surrounding the flared die remained clear. Sixty minutes after startup, growth of the accumulations around the standard die had continued and the flared die remained clear. Although the rate of accumulation of die drips on the standard straight through die was slower for unreinforced resins than for the two reinforced resins cited in Examples 1 and 2, the flared

die provided an operating improvement vs. the standard straight through die.

EXAMPLE 4

5 A 40 mm W&P twin-screw extruder was used to melt the resin and develop pressure sufficient to force the melt through the die plate. The die plate used was the same as described in Example 1 above. The resin tested was Rynite® 530 at 68 kg/hr. The diameter of the original land (1 in Figure 2) was 4.5 mm. The diameter
10 of the flared section (2 in Figure 2) was 5.4 mm. The flared section extended 6.0 mm back from the face of the die. The second orifice tested had two expansions, from 4.5 mm to 4.8 mm and from 4.8 mm to 5.4 mm (diameter ratios of 1.067 and 1.125). Each flared section had a
15 length of 4 mm. Both of these configurations were effective in reducing the accumulation of die drips at the die face exit when compared to the standard, straight-through die design.

EXAMPLE 5

20 A 40 mm W&P twin-screw extruder was used to melt the resin and develop pressure sufficient to force the melt through the die plate. The die plate used was the same as described above. The resin tested was Rynite® 530 at 68 kg/hr. The extruder was operated at
25 normal processing conditions. The first orifice tested was the flared orifice with 1.2x ratio of diameters described above in Example 4. The second die tested had three expansions, from 4.5 mm to 4.8 mm, from 4.8 mm to 5.05 mm and from 5.05 to 5.4 mm. Each flared section
30 had a length of 3 mm. Both of these configurations were effective in reducing the accumulation of die drips at the die face exit when compared to the standard, straight-through die design.



13

THIS SHEET HAS BEEN
REPLACEDCLAIMS

What is claimed is:

1. A die having flared orifices for the extrusion of polymers, comprising, a die body having one or more
5 flared orifices having the following components:
 a first zone having surface S_1 ;
 a second zone having surface S_2 ;
 a third zone having surface S_3 ;
 a length L_1 which is the total length of said
10 first, second and third zones;
 a length L_3 which is the length of said third zone;
 a polymer flow axis A; and
 said die has a surface S_5 on a discharge side
15 of said die; and
 wherein:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going through said orifice is in substantial contact with the
20 periphery of S_3 before exiting said orifice;
 A and S_3 are perpendicular to S_5 ;
 if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;
25 if said second zone has more than one step area change, an analogous angle of each step corresponding to said angle T is 45° to 90° ;
 an area of the orifice in said third zone is about 1.1 to about 1.7 times an area of the orifice at
30 said first zone; and
 a shape of said first zone and a shape of said third zone are geometrically similar.
2. The die as recited in Claim 1 wherein L_1/L_3 is about 3 to about 10.





3. The die as recited in Claim 1 wherein S_1 is approximately parallel to A.

4. The die as recited in Claim 1 wherein the angle T or analogous angles are about 60° to about 90° .

5 5. The die as recited Claim 1 wherein the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

10 6. The die as recited in Claim 1 wherein L_1/L_3 is about 3 to about 10, S_1 is approximately parallel to A, the angle T or analogous angles are about 60° to about 90° , and the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

15 7. A polymer extrusion apparatus comprising a die and a means for pumping a polymer through said die, wherein the improvement comprises, a die for the extrusion of polymers having one or more flared orifices having the following components:

20 a first zone having surface S_1 ;
a second zone having surface S_2 ;
a third zone having surface S_3 ;
a length L_1 which is the total length of said first, second and third zones;



25 a length L_3 which is the length of said third zone;

a polymer flow axis A; and
said die has a surface S_5 on a discharge side of said die; and

30 wherein:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;

A and S_3 are perpendicular to S_5 ;





if said second zone has a one step area change, an angle T , which is an angle formed by of S_2 and A , is about 45° to about 90° ;

5 if said second zone has more than one step area change, an analogous angle of each step corresponding to said angle T is 45° to 90° ;

an area of the orifice in said third zone is about 1.1 to 1.7 about times an area of the orifice at said first zone;

10 a shape of said first zone and a shape of said third zone are geometrically similar;

and providing that surface S_2 of said parallel flared die is not in contact with a liquid cooling medium.

15 8. The apparatus as recited in Claim 7 wherein L_1/L_3 is about 3 to about 10.

9. The apparatus as recited in Claim 7 wherein S_1 is approximately parallel to A .

20 10. The apparatus as recited in Claim 7 wherein the angle T or analogous angles are about 60° to about 90° .

25 11. The apparatus as recited Claim 7 wherein the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

30 12. The apparatus as recited in Claim 7 wherein L_1/L_3 is about 3 to about 10, S_1 is approximately parallel to A , the angle T or analogous angles are about 60° to about 90° , and the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

13. A process for the extrusion of polymer, comprising extruding a polymer through a die having one or more flared orifices having the following components:



- a first zone having surface S_1 ;
a second zone having surface S_2 ;
a third zone having surface S_3 ;
a length L_1 which is the total length of said
5 first, second and third zones;
a length L_3 which is the length of said third
zone;
a polymer flow axis A; and
said die has a surface S_5 on a discharge side
10 of said die; and
wherein:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going
through said orifice is in substantial contact with the
15 periphery of S_3 before exiting said orifice;
A and S_3 are perpendicular to S_5 ;
if said second zone has a one step area
change, an angle T, which is by S_2 and A, is about 45°
to about 90° ;
20 if said second zone has more than one step
area change, an analogous angle of each step
corresponding to said angle T is 45° to 90° ;
an area of the orifice in said third zone is
about 1.1 to 1.7 about times an area of the orifice at
25 said first zone;
a shape of said first zone and a shape of said
third zone are geometrically similar;
and providing that surface S_5 of said die is
not in contact with a liquid cooling medium.
30 14. The process as recited in Claim 13 wherein
 L_1/L_3 is about 3 to about 10.
15. The process as recited in Claim 13 wherein S_1
is approximately parallel to A.
16. The process as recited in Claim 13 wherein the
35 angle T or analogous angles are about 60° to about 90° .



* C L M S *

17. The process recited Claim 13 wherein the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

18. The process as recited in Claim 13 wherein
5 L_1/L_3 is about 3 to about 10, S_1 is approximately parallel to A, the angle T or analogous angles are about 60° to about 90° , and the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

10






FIG. 1

2/2




FIG.2

polymers and wherein the die is part of an underwater pelletizer. There is no mention of the use of this die
5 in other extrusion processes.

European Patent Application 0 566 276 A1 discloses an improved plastics extruder die, wherein molten plastic enters the die through an opening of a smaller diameter and exits the die through an extrusion orifice
10 of a larger diameter. In particular, the ratio of the diameter of the extrusion orifice to that of the channel in the die plate through which molten polymer enters the extrusion orifice is 1.1-2.0.

SUMMARY OF THE INVENTION

15 This invention concerns a die having flared orifices for the extrusion of polymers, comprising, a die body having one or more flared orifices having the following components:

- a first zone having surface S_1 ;
- 20 a second zone having surface S_2 ;
- a third zone having surface S_3 ;
- a length L_1 which is the total length of said first, second and third zones;
- a length L_3 which is the length of said third
25 zone;
- a polymer flow axis A; and
- said die has a surface S_5 on a discharge side of said die; and
- wherein:
- 30 L_1/L_3 is about 2 or more;
- L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;
- A and S_3 are perpendicular to S_5 ;
- 35 if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;

AMENDED SHEET

This is the replacement sheet

Date: 19 SEP 1996

if said second zone has more than one step
area change, an analogous angle of each step
5 corresponding to said angle T is 45° to 90° ;

an area of the orifice in said third zone is
about 1.1 to 1.7 about times an area of the orifice at
said first zone; and

a shape of said first zone and a shape of said
10 third zone are geometrically similar.

AMENDED SHEET

This is the replacement sheet

Date: 19 SEP 1961

What is claimed is:

1. A die having flared orifices for the extrusion
5 of polymers, comprising, a die body having one or more
flared orifices having the following components:
a first zone having surface S_1 ;
a second zone having surface S_2 ;
a third zone having surface S_3 ;
10 a length L_1 which is the total length of said
first, second and third zones;
a length L_3 which is the length of said third
zone;
a polymer flow axis A; and
15 said die has a surface S_5 on a discharge side
of said die, wherein
A and S_3 are perpendicular to S_5 ;
the shape of said first zone and the shape of
said third zone being geometrically similar.
20 said die being characterized by that:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going
through said orifice is in substantial contact with the
periphery of S_3 before exiting said orifice;
25 if said second zone has a one step area
change, an angle T, which is an angle formed by S_2 and
A, is about 45° to about 90° ;
if said second zone has more than one step
area change, an analogous angle of each step
30 corresponding to said angle T is 45° to 90° ;
the area of the orifice in said third zone is
about 1.1 to about 1.7 times the area of the orifice at
said first zone.
2. The die as recited in Claim 1 wherein L_1/L_3 is
35 about 3 to about 10.



* C L M S *

AMENDED SHEET

This is the replacement sheet

Date: 19 SEP 1996

3. The die as recited in Claim 1 wherein S_1 is approximately parallel to A.

5 4. The die as recited in Claim 1 wherein the angle T or analogous angles are about 60° to about 90° .

5. The die as recited Claim 1 wherein the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

10 6. The die as recited in Claim 1 wherein L_1/L_3 is about 3 to about 10, S_1 is approximately parallel to A, the angle T or analogous angles are about 60° to about 90° , and the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice
15 in said third zone.

7. A polymer extrusion apparatus comprising a die and a means for pumping a polymer through said die, wherein the improvement comprises, a die for the extrusion of polymers having one or more flared orifices
20 having the following components:

a first zone having surface S_1 ;
a second zone having surface S_2 ;
a third zone having surface S_3 ;
a length L_1 which is the total length of said
25 first, second and third zones;
a length L_3 which is the length of said third zone;
a polymer flow axis A; and
said die has a surface S_5 on a discharge side
30 of said die, wherein
A and S_3 are perpendicular to S_5 ;
the shape of said first zone and the shape of said third zone being geometrically similar.
said die in said apparatus being characterized
35 by that:
 L_1/L_3 is about 2 or more;
 L_3 is long enough so that a polymer going through said orifice is in substantial contact with the periphery of S_3 before exiting said orifice;

This is the replacement sheet

AMENDED SHEET

Date: 19 SEP 1996



if said second zone has a one step area change, an angle T, which is an angle formed by S_2 and A, is about 45° to about 90° ;

if said second zone has more than one step area change, an analogous angle of each step corresponding to said angle T is 45° to 90° ;

the area of the orifice in said third zone is about 1.1 to about 1.7 times the area of the orifice at said first zone.

8. The apparatus as recited in Claim 7 wherein L_1/L_3 is about 3 to about 10.

9. The apparatus as recited in Claim 7 wherein S_1 is approximately parallel to A.

10. The apparatus as recited in Claim 7 wherein the angle T or analogous angles are about 60° to about 90° .

11. The apparatus as recited Claim 7 wherein the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

12. The apparatus as recited in Claim 7 wherein L_1/L_3 is about 3 to about 10, S_1 is approximately parallel to A, the angle T or analogous angles are about 60° to about 90° , and the area of the orifice in said first zone is about 1.30 to about 1.45 times the area of the orifice in said third zone.

13. A process for the extrusion of polymer, comprising extruding a polymer through a die having one or more flared orifices having the following components:



AMENDED SHEET

This is the replacement sheet

Date: 19 SEP 1996