

METHOD OF PROVIDING CONSISTENT QUALITY OF TARGET MATERIAL REMOVAL BY LASERS HAVING DIFFERENT OUTPUT PERFORMANCE CHARACTERISTICS

Technical Field

[0001] This invention relates to use of a laser to drill vias in or otherwise process portions of material of electronic materials products and, in particular, to techniques of achieving with consistent high quality vias drilled or regions formed after material processing by laser-based systems exhibiting different operating output parameters.

Background Information

[0002] Lasers are used to drill vias in and ablate material from electronic materials products, such as homogenous films, particulate filled resins, polyimides, and fiber reinforced polymers, either with or without metal cladding. The state of the art for solid state UV laser via drilling, for example, is to set and control or monitor the laser pulse energy by setting and controlling the laser pulse power and repetition rate for a desired process. Gaussian and imaged beam optics configurations are used in this manner. Other laser output performance characteristics vary among different lasers but remain within the specifications of the laser. Variation in laser output performance characteristics within the specified limits can result in differences in drilled via quality among multiple lasers, multiple beam positioning heads, and multiple laser systems, even when the same process is performed and same material is used on all systems. Specifically, variation in parameters within the specifications of the laser can cause, especially for blind via drilling applications, bottom copper cladding residue formation or nonhomogeneous melting, which results in differences in drilled via quality. In these applications, the pulse energy used during the drilling process can also affect via taper (ratio of bottom diameter to top diameter of via) as well as the quality of bottom copper cladding. A high quality blind via is one that has a desired bottom diameter and all thin film resin material removed from the bottom to exhibit a shiny copper cladding spot.

[0003] In general, the quality of a laser-processed material refers to a standard of excellence specified by a customer of laser processing equipment. Quality metrics differ for different laser processing operations. In addition to the quality metrics discussed above for via drilling, there are quality metrics for electrically conductive link severing, resistive material trimming, thick or thin film passive component thermal annealing, and substrate material scribing by laser outputs.

[0004] The quality metric for link severing governs the extent of operational damage to materials surrounding and underlying a link resulting from laser output interaction with the materials during severing of the link. The quality metric for laser trimming governs the minimization of an electro-optic response contributed by laser interaction during resistive material removal so as not to materially influence electrical measurements performed to determine when a specified resistance value has been achieved during resistive material trimming. The quality metric for laser annealing governs the degree of uniformity of distribution of heat applied to a component to change one of its characteristic parameters. The quality metric for laser scribing governs the minimization of microcrack formation in scribe line trench edges resulting from debris generated during cutting. This is a measure of the difference between laser pulse energy and the ablation energy threshold of the scribed material.

[0005] Moreover, the control of pulse energy is imperfect and is subject to short-term transients that may not be normalized by energy control devices present in the optical system. Such deviations in pulse energy can cause undesirable variations in via quality metrics.

[0006] What is desired, therefore, are techniques for achieving laser drilling of vias or other removal of material with consistent high quality from multiple lasers, multiple beam positioning heads, and multiple laser-based systems. It is also desired to achieve consistent removal of material by a laser, the output performance characteristics of which vary within specified limits over time.

Summary of the Invention

[0007] This invention entails adjusting laser pulse energy to account for the effects of laser pulse width variations among different lasers. Laser pulse energy adjustments are motivated by an understanding of the effect of laser pulse width variations among different lasers on satisfying a quality metric associated with a laser-processed target. In a preferred embodiment, the adjustments normalize the

effect of pulse width variations among different lasers drilling vias in a target specimen. In addition, the number of laser pulses delivered to the target specimen to form each via can be modified, based on the pulse energy applied to the via location, to control different via quality metrics.

[0008] The conventional method of controlling a via drilling process entails controlling the pulse energy for the given process. The pulse energy, E_p , for use in performing a given process is determined by the fluence, F , desired for the process. The fluence, in J/cm^2 , is calculated as

$$F = \frac{E_p}{\frac{\pi}{4} D^2},$$

where E_p is the pulse energy in J and D is the via diameter in cm. Applicants have found that drilling the same material at the same fluence level with lasers having different pulse widths results in different quality for the bottom copper cladding layer of a target specimen. Applicants have determined that a more appropriate parameter for predicting the bottom copper cladding quality for blind vias is

$$\frac{F}{\sqrt{\tau}},$$

where F is the pulse fluence in J/cm^2 and τ is the laser pulse width in ns. Taking steps to keep $F/\sqrt{\tau}$ constant among lasers in a group of different lasers provides more consistent laser processing. This is true for laser processing operations other than via drilling and targets other than those having copper cladding.

[0009] Additional aspects and advantages will be apparent from the following detailed description of preferred embodiments, which proceeds with reference to the accompanying drawings.

Brief Description of the Drawings

[0010] Fig. 1 is a set of four light microscope images showing differences in quality of 58 μm diameter blind vias drilled in the same copper-clad target material with different lasers emitting pulsed laser beams at the same fluence but with different pulse widths.

[0011] Figs. 2 and 3 are each a set of four light microscope images showing similarities in quality of 58 μm diameter blind vias drilled in the same copper-clad

target material with different lasers emitting pulsed laser beams at the same $F/\sqrt{\tau}$ but with different pulse widths.

[0012] Fig. 4 is a graph showing a curve that represents, for different lasers, as a function of $F/\sqrt{\tau}$ the number of laser pulses ablating bulk Model ABF dielectric target material to form a 58 μm blind via having a taper of 75%.

[0013] Fig. 5 is a graph showing via taper as a function of a number of laser pulses drilling a 58 μm diameter blind via in Model ABF dielectric target material at a 60 kHz repetition rate and 0.73 J/cm² fluence.

Detailed Description of Preferred Embodiments

[0014] Preferred embodiments of this invention entail the use of a solid state UV laser to perform via drilling and ablation of electronic circuit materials such as homogenous films, particulate filled resins, polyimides, and fiber-reinforced polymers, either with or without metal cladding. The Model ABF circuit board dielectric material manufactured by Ajinomoto Fine-Techno Co., Inc., Kawasaki, Japan is the target material on which the following descriptions are based. The following descriptions are directed to via drilling, but the invention is also applicable to other methods of material removal, such as link severing, material trimming, annealing, and scribing.

[0015] Fig. 1 is a set of four photographs of microscope images that illustrate the problem solved by the invention. Fig. 1 shows light microscope pictures of two 58 μm diameter vias drilled to depths of 35 μm -40 μm at approximately the same fluence level with 355 nm UV lasers having different pulse widths. The top two photographs represent images of blind vias focused at the upper surfaces of the target materials, and the bottom two photographs represent images of blind vias focused at a lower copper cladding layers at the bottoms of the vias. (The parameter P_{ws} represents laser power at the work surface.) Comparison of the left-hand and right-hand side pairs of photographs shown in Fig. 1 reveals that, at the same fluence level, a shorter pulse width Laser A slightly melted the bottom copper layer and a longer pulse width Laser B barely cleaned the dielectric material off the bottom copper layer. Laser A and Laser B each emit 355 nm light beams. The brightness of the bottom copper layer is significantly different for the same fluence level with two different laser pulse widths.

[0016] Applicants' study of pulse width effects on via quality suggests that $F/\sqrt{\tau}$ is a more appropriate parameter for predicting the quality of the bottom copper cladding for blind vias, where F is the pulse fluence in J/cm^2 and τ is the laser pulse width in ns.

[0017] Figs. 2 and 3 are each a set of four photographs of microscope images that illustrate the effect of the invention on laser drilled via quality. The top two and bottom two photographs of each of Figs. 2 and 3 represent the same depths of focus used in the corresponding photographs of Fig. 1. Figs. 2 and 3 show light microscope images of blind vias drilled in the same material with lasers having different pulse widths, but the ratio $F/\sqrt{\tau}$ is kept approximately equal instead of F . The bottom photographs show that the surface quality of the bottom copper layer is similar for lasers emitting pulses of different pulse widths as long as the ratio $F/\sqrt{\tau}$ remains constant.

[0018] Recognizing that the parameter $F/\sqrt{\tau}$ affects bottom copper layer quality, a system operator can take steps to keep this parameter constant for different ones in the group of lasers to provide more consistent laser processing. For a laser with a pulse width specification having a nominal value, a minimum value, and a maximum value, different lasers in a group can be normalized to one another by normalizing the ratio $F/\sqrt{\tau}$ for each laser in the group. One method of achieving normalization entails normalizing all lasers relative to the nominal pulse width specification so that all of the lasers drill as though each of them is a nominal pulse width laser at any given set of process parameters. The equation to normalize the lasers for this pulse width effect is

$$F_{\text{Drill}} = F_{\text{nom}} \frac{\sqrt{\tau_{\text{Laser}}}}{\sqrt{\tau_{\text{nom}}}},$$

where F_{Drill} is the fluence to be used during drilling, F_{nom} is the nominal fluence programmed into the laser system for the given process, τ_{Laser} is the actual pulse width of the laser being used, and τ_{nom} is the nominal pulse width specification of the laser.

[0019] In one typical procedure, an operator sets in a system input device a fluence value specified for a given processing operation. The system has in memory stores previously entered laser parameter data. Laser system software can

automatically take the parameters entered for a given process and recalculate a different pulse energy to satisfy the $F/\sqrt{\tau}$ parameter consistent with the quality metric needed for use during drilling, i.e., the pulse energy based on the pulse width of the actual laser being used. This same methodology may also be used for correcting pulse width variations as the laser pulse repetition rate is changed, thereby resulting in consistent via quality for vias drilled at the same programmed fluence and different repetition rates. The pulse width information for the individual laser being used could be either entered into a calibration file based on previous measurements or measured in real time using a pulse detector.

[0020] The basis for normalization of pulse energy effects is illustrated by Figs. 4 and 5, which show the dependence of via taper on the number of pulses for a given pulse energy. Specifically, Fig. 4 shows the minimum number of pulses incident on a target location to achieve a 75% via taper. As Fig. 4 illustrates, a drop in average pulse energy (resulting in a corresponding drop in $F/\sqrt{\tau}$) for a particular via can result in a need to use a greater number of pulses to create a desired taper ratio. Fig. 5 shows that use of fewer than the necessary number of taper pulses results in a via taper lower than that which is desired. To compensate for this pulse energy reduction, the machine control system can detect the pulse energy for a given via in real time and adjust the number of pulses applied to that via in real time to maintain the desired taper. As Fig. 5 illustrates for the example given, the use of 58 pulses achieves a 75% via taper. Additional pulses would be used to achieve better via bottom surface quality. The number of pulses could be either increased or decreased to create the desired taper for the given via, depending on whether the average pulse energy for that via was higher or lower than the programmed pulse energy.

[0021] It will be obvious to those having skill in the art that many changes may be made to the details of the above-described embodiments without departing from the underlying principles of the invention. The scope of the present invention should, therefore, be determined only by the following claims.

Claims

1. A method of meeting consistently a quality metric specified for regions of target specimen material processed by laser output pulses emitted by different ones of a group of lasers, the laser output pulses before processing of target specimen material characterized by nominal pulse energy values determined by pulse width and peak power values, comprising:

specifying a quality metric for laser-processed regions of target specimen material; and

adjusting the nominal pulse energy values of the laser output pulses to establish, for each laser in the group, adjusted energy values that cause the regions of target specimen material processed by the laser output pulses to meet consistently the quality metric specified, the adjusting of the nominal pulse energy values including determining for the lasers in the group a ratio representing the specified quality metric and expressed as

$$\frac{F}{\sqrt{\tau}},$$

where F and τ are, respectively, the fluence and pulse width of the laser pulses.

2. The method of claim 1, in which each of the lasers in the group emits a series of the laser output pulses, and further comprising changing the number of laser output pulses in the series of one or more of the lasers to process associated regions of the target specimen material in response to detection of a deviation from the adjusted energy values.

3. The method of claim 1, in which the laser processing of target specimen material forms a via in one of the regions of the target specimen material.

4. The method of claim 3, in which the target specimen material includes an ablatable target material having a major surface covered by a metal cladding, and in which the quality metric includes the condition of the metal cladding upon removal of the ablatable target material to form the via.

5. A method of meeting consistently a quality metric specified for regions of target specimen material processed by laser output pulses emitted by a laser operating within an output performance specification range, the laser emitting a series of output pulses each of which characterized by a nominal energy value and an actual pulse width, comprising:

specifying a quality metric to be met by regions of the target specimen material upon completion of laser processing of them; and

scaling by multiplying by a parameter the nominal energy values of the laser output pulses to provide a series of output pulses with scaled energy values for processing the regions of target specimen material, the parameter being a function of the actual pulse widths of the laser output pulses.

6. The method of claim 5, in which the laser pulses with scaled energy values each cover a target area and the parameter is expressed as

$$\frac{F}{\sqrt{\tau}},$$

where F and τ are, respectively, the fluence and pulse width of the laser pulses.

7. The method of claim 5, in which the laser processing of target specimen material forms vias in the regions.

8. The method of claim 7, in which the target specimen material includes an ablatable material having a major surface covered by a metal cladding, and in which the quality metric includes the condition of the metal cladding upon removal of the ablatable material to form the vias.

9. A method of meeting consistently a quality metric specified for a laser emitting a target specimen processing pulsed laser beam for processing a target specimen material, comprising:

determining nominal pulse energy values of a nominal pulsed beam emitted by the laser, the nominal pulse energy values derived from pulse width and peak power values of the nominal pulsed beam; and

scaling the nominal pulse energy values by a parameter to produce a target specimen processing pulsed laser beam having scaled laser pulse energy values corresponding to the quality metric, the parameter expressed as $F/\sqrt{\tau}$, where F is the fluence computed from the peak power values of the laser pulses of the nominal pulsed beam incident on a target area and τ is the pulse width of the pulses of the nominal pulsed beam.