CLAIMS

1. A production method for producing a particle mixture in which two or more types of particles are mixed, the production method comprising:

a step of adding a first additive to first particles and mixing the first additive with the first particles using a first mixer; and

a step of introducing the two or more types of particles including the first particles mixed with the first additive and second particles into a blender container of a gravity blender, and mixing the two or more types of particles inside the blender container,

wherein the gravity blender comprises a conveyance route that is connected to a downstream portion of the blender container and extending to an upper opening of the blender container,

wherein the step of introducing and mixing the two or more types of particles includes make the two or more types of particles circulate in the blender container and the conveyance route,

wherein the number N of circulation time of the two or more types of particles satisfies $1.5<N<2.5$, N is calculated by dividing a value obtained by multiplying the flow rate of the two or more types of particles that pass through the conveyance route by a circulation period by total amount of the two or more types of particles.

2. The production method according to claim 1, further comprising a step of adding a second additive to the second particles and mixing the second additive with the second particles using a second mixer,

wherein the step of introducing and mixing the two or more types of particles includes introducing the two or more types of particles including the first particles mixed with the first additive and the second particles mixed with the second additive

into the blender container and mixing the two or more types of particles inside the blender container.

3. The production method according to claim 1 or 2,

wherein the first particles and the second particles are made of the same material and have different average particle diameters.

4. The production method according to claim 1 or 2,

wherein the first particles and the second particles are of the same type, and

the step of introducing and mixing the two or more types of particles includes introducing the two or more types of particles including the first particles mixed with the first additive and the second particles mixed with no first additive into the blender container and mixing the two or more types of particles inside the blender container.

5. The production method according to any one of claims 1 to 4,

wherein the blender container is provided with an inlet in an upper portion and an outlet in a lower portion, and

the step of mixing the two or more types of particles inside the blender container includes

a step of mixing the two or more types of particles while allowing the two or more types of particles to fall from the inlet to the outlet with the force of gravity, and then conveying the two or more types of particles from the outlet to the inlet in order to mix the two or more types of particles again while allowing the two or more particles to fall from the inlet to the outlet with the force of gravity.

6. The production method according to any one of claims 1 to 5,

wherein the first particles and the second particles are water-absorbent resin

particles.

7. The production method according to any one of claims 1 to 6,

wherein the step of introducing and mixing the two or more types of particles includes

a step of introducing the first particles mixed with the first additive and the second particles into the blender container alternately and repeatedly.