

SURFACE-TREATMENT SOLUTION FOR ZINC OR ZINC ALLOY
COATED STEEL SHEET, METHOD OF PRODUCING ZINC OR ZINC
ALLOY COATED STEEL SHEET WITH SURFACE-COATING LAYER, AND
ZINC OR ZINC ALLOY COATED STEEL SHEET WITH
5 SURFACE-COATING LAYER

TECHNICAL FIELD

[0001] This disclosure relates to a surface-treatment solution for a zinc or
zinc alloy coated steel sheet, a method of producing a zinc or zinc alloy
10 coated steel sheet with a surface-coating layer, and a zinc or zinc alloy coated
steel sheet with a surface-coating layer.

BACKGROUND

[0002] Zinc or zinc alloy coated steel sheets that are surface-treated by
15 chromating using a treatment solution mainly composed of chromic acid,
dichromic acid, or salts thereof to improve the corrosion resistance
(anti-white rust property, anti-red rust property) have conventionally been in
wide use. Recent global environmental issues, however, have increased the
demand for use of non-polluting steel sheets surface-treated not by
20 chromating, namely, chromium-free treated steel sheets.

[0003] Such a zinc or zinc alloy coated steel sheet with a surface-coating
layer (hereinafter also referred to as a "coated steel sheet") is used for
automobiles, household electrical appliances, office automation equipment,
construction materials, and the like. When used in these applications, they
25 are often exposed to the atmosphere without coating as outer plates and the
like, and users are requesting products with aesthetic surface appearance. In
particular, if remarkable alteration or discoloration on the surface appearance
is observed over time from the production until the user's use, the product
value is lowered. On the other hand, zinc or zinc alloy coated steel sheets
30 undergo a phenomenon of "blackening" that changes color from gray to black
as a result of oxidation of the surface due to aging, and the blackening
becomes more pronounced particularly when zinc or zinc alloy coated steel
sheets have a coated layer containing elements such as Mg and Al, which are
more easily oxidized than Zn. Although blackening phenomenon is

suppressed to some extent by applying a surface-coating layer, especially when steel sheets are transported and stored under the condition that they are overlapped in coils over a long period of time under a high-temperature and high-humidity environment, which is a very severe environment in which oxygen supply is insufficient and water supply is abundant, formation of oxygen-deficient zinc oxide, which is the main factor of blackening, is markedly promoted, and the steel sheets are more prone to blackening. In addition, there is a tradeoff between the planar part anti-corrosion property required for coated steel sheets and the blackening resistance, and none of the conventional techniques achieve both planar part anti-corrosion property and blackening resistance at the same time under harsh environments.

[0004] Therefore, there is a need for a coated steel sheet that is excellent in blackening resistance and planar part anti-corrosion property, and that suppresses the above phenomenon. Further, considering that coated steel sheets are used for various purposes, it is also required for a coated steel sheet to have excellent corrosion resistance after alkali degreasing, anti-water stain property, solvent resistance, perspiration resistance, coating adhesion property, and storage stability. In the case of further welding, it is also required for a coated steel sheet to have excellent heat discoloration resistance and heat cracking resistance.

[0005] JP2015175003A (PTL 1) and JP201637620A (PTL 2) describe techniques for imparting excellent planar part anti-corrosion property and blackening resistance by applying a surface-treatment solution to a zinc or zinc alloy coated steel sheet and drying it to form a surface-coating layer, wherein the surface-treatment solution contains: a hydrolyzable group-containing silane compound obtained from a glycidyl group-containing silane coupling agent, a tetraalkoxysilane, and a phosphonic acid; a zirconium carbonate compound; and a vanadic acid compound. However, since the surface-coating layer has a polysiloxane bond as a main skeleton by a condensation reaction of a silane compound, visually-observable cracks easily occur due to thermal decomposition of the polysiloxane bond upon heating at a high temperature exceeding 500 °C. Furthermore, due to the existence of many hard components derived from the zirconium carbonate compound, coating adhesion can not be sufficiently secured. In addition, corrosion

resistance, coating adhesion property, and lubricity are not sufficient.

[0006] JP2011117070A (PTL 3) describes a technique for imparting planar part anti-corrosion property, coating adhesion property, conductivity, lubricity, and storage stability by forming a first layer and a second layer on a zinc or
5 zinc alloy coated steel sheet, wherein the first layer contains a metal compound containing at least one selected from the group consisting of vanadic acid, Ti, Al, and Zn, in addition to a water-soluble zirconium compound, a tetraalkoxysilane, an epoxy group-containing compound, a chelating agent, and a silane coupling agent, and the second layer contains an
10 organic resin and is over-coated on the surface of the first layer. However, although an organic resin is used in the upper layer for ensuring planar part anti-corrosion property, the upper layer contains a large amount of a metal compound containing at least one selected from the group consisting of a vanadic acid compound, Ti, Al, and Zn, which are components in the lower
15 layer. Such metal compounds promote oxidation of the coating surface as an eluting component under severe conditions in a high-temperature and high-humidity environment. Thus, it is not possible to secure adequate blackening resistance.

[0007] JP2008291350A (PTL 4) describes a technique for imparting planar
20 part anti-corrosion property and blackening resistance by forming a surface-coating layer containing a specific titanium-containing aqueous liquid, a nickel compound, and/or a cobalt compound, and a fluorine-containing compound. However, since the fluorine-containing compound, as an eluting component, promotes the oxidation of the coating surface under severe
25 conditions in a high-temperature and high-humidity environment, sufficient blackening resistance can not be ensured. Furthermore, PTL 4 does not consider, for example, anti-water stain property, perspiration resistance, heat discoloration resistance, and heat cracking resistance, and is not sufficient.

[0008] JP201360646A (PTL 5) and PTL 6 (JP2014101562A) describe
30 techniques for imparting planar part anti-corrosion property, blackening resistance, and anti-water stain property by forming a surface-coating layer containing a specific titanium-containing aqueous liquid, a nickel compound, a fluorine-containing compound, an organic phosphoric acid compound, and a vanadic acid compound. Furthermore, JP2010156020A (PTL 7) describes a

technique for imparting corrosion resistance and coating adhesion property by forming a surface-coating layer containing a titanium-containing aqueous solution, a fluorine-containing compound, an anionic urethane resin and/or an anionic epoxy resin, an organic phosphoric acid compound, a vanadic acid
5 compound, a zirconium carbonate compound, and a glycidyl group-containing silane coupling agent. However, when containing a fluorine-containing compound or an organic phosphoric acid compound, the yellow discoloration of the layer tends to become conspicuous upon heating at a high temperature exceeding 500 °C, and the appearance is impaired. PTL 7 does not consider,
10 for example, perspiration resistance, solvent resistance, and heat cracking resistance, and is not sufficient.

CITATION LIST

Patent Literature

15 **[0009]** PTL 1: JP2015175003A
PTL 2: JP201637620A
PTL 3: JP2011117070A
PTL 4: JP2008291350A
PTL 5: JP201360646A
20 PTL 6: JP2014101562A
PTL 7: JP2010156020A

SUMMARY

(Technical Problem)

25 **[0010]** As described above, none of the conventional coated steel sheets are capable of satisfying both planar part anti-corrosion property and blackening resistance in a severe environment and satisfying all other characteristics in a well-balanced manner. In particular, blackening resistance tends to be problematic when steel sheets are transported and stored under the condition
30 that they are overlapped in coils over a long period of time under a high-temperature and high-humidity environment, which is a more severe environment in which oxygen supply is insufficient and water supply is abundant. As used herein, the blackening resistance to be evaluated in a high-temperature and high-humidity environment in a state where the steel

sheets are overlapped is referred to as "stack blackening resistance". There are no steel sheets capable of providing good stack blackening resistance while satisfying all the above-mentioned characteristics in a well-balanced manner.

5 **[0011]** It would thus be helpful to provide a zinc or zinc alloy coated steel sheet with a surface-coating layer that does not contain a chromium compound in the surface-coating layer and that is excellent in all of heat discoloration resistance, heat cracking resistance, planar part anti-corrosion property, corrosion resistance after alkali degreasing, blackening resistance, stack
10 blackening resistance, anti-water stain property, solvent resistance, perspiration resistance, coating adhesion property, and storage stability, as well as a surface-treatment solution and a method for producing the same.

(Solution to Problem)

15 **[0012]** As a result of extensive studies, the inventors found that the above problems can be solved by forming a surface-coating layer on a zinc or zinc alloy coated steel sheet using a surface-treatment solution containing a glycidyl group-containing silane coupling agent (A), a tetraalkoxysilane (B), a zirconium carbonate compound (C), an anionic polyurethane resin (D) having
20 a glass transition temperature (T_g) of 80 °C to 130 °C, a vanadium compound (E), a molybdic acid compound (F), and water, the surface-treatment solution having a pH of 8.0 to 10.0, and the amount of each component satisfying a predetermined relationship. In particular, in order to improve stack blackening resistance, it is effective to add the zirconium carbonate compound
25 (C) to the surface-treatment solution, and it is important to set the amount thereof to 45 mass% or more with respect to the total mass (X_S) of the components (A) to (C).

[0013] The present disclosure is based on the aforementioned discoveries and the primary features thereof are as follows.

30 **[1]** A surface-treatment solution for a zinc or zinc alloy coated steel sheet containing a glycidyl group-containing silane coupling agent (A), a tetraalkoxysilane (B), a zirconium carbonate compound (C), and an anionic polyurethane resin (D) having a glass transition temperature (T_g) of 80 °C to 130 °C, a vanadium compound (E), a molybdic acid compound (F), and water,

the surface-treatment solution having a pH of 8.0 to 10.0, and the amount of each component satisfying: (1) a mass ratio (X_S/D_S) of a total mass (X_S) of a solid content mass (A_S) of the glycidyl group-containing silane coupling agent (A), a solid content mass (B_S) of the tetraalkoxysilane (B), and a ZrO₂ equivalent mass (C_Z) in the zirconium carbonate compound (C) to a solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.05 to 0.35; (2) a mass ratio (A_S/X_S) of the solid content mass (A_S) of the glycidyl group-containing silane coupling agent (A) to the total mass (X_S) is from 0.20 to 0.40; (3) a mass ratio (B_S/X_S) of the solid content mass (B_S) of the tetraalkoxysilane (B) to the total mass (X_S) is from 0.010 to 0.30; (4) a mass ratio (C_Z/X_S) of the ZrO₂ equivalent mass (C_Z) in the zirconium carbonate compound (C) to the total mass (X_S) is from 0.45 to 0.70; (5) a mass ratio ($E_V/(X_S + D_S)$) of a V equivalent mass (E_V) in the vanadium compound (E) to a total mass ($X_S + D_S$) of the total mass (X_S) and the solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.0010 to 0.015; and (6) a mass ratio ($F_M/(X_S + D_S)$) of a Mo equivalent mass (F_M) in the molybdic acid compound (F) to the total mass ($X_S + D_S$) of the total mass (X_S) and the solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.0010 to 0.015.

[0014] [2] The surface-treatment solution for a zinc or zinc alloy coated steel sheet according to [1], further containing a sodium silicate (G), wherein the amount thereof satisfies: (7) a mass ratio ($G_S/(X_S + G_S)$) of a solid content mass (G_S) of the sodium silicate (G) to the total mass ($X_S + G_S$) of the total mass (X_S) and the solid content mass (G_S) of the sodium silicate (G) is less than 0.05, inclusive of 0.00.

[0015] [3] The surface-treatment solution for a zinc or zinc alloy coated steel sheet according to [1] or [2], further containing a wax (H), wherein the amount thereof satisfies: (8) a mass ratio ($H_S/(X_S + D_S)$) of a solid content mass (H_S) of the wax (H) to the total mass ($X_S + D_S$) of the total mass (X_S) and the solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.002 to 0.10.

[0016] [4] A method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer, comprising: a first step of applying the surface-treatment solution as recited in any one of [1] to [3] to a surface of a

zinc or zinc alloy coated steel sheet; and a second step of subsequently drying the applied surface-treatment solution to form a surface-coating layer having a coating weight of 50 mg/m^2 to $2,000 \text{ mg/m}^2$.

[0017] [5] The method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer according to [4], wherein T_S is 15°C to 55°C , T_L is 10°C to 40°C , and ΔT is 5°C to 40°C , where T_S and T_L represent a temperature of the zinc or zinc alloy coated steel sheet and a temperature of the surface-treatment solution in the first step, respectively, and ΔT represents $T_S - T_L$, and the second step includes a preliminary drying step of drying the applied surface-treatment solution in the atmosphere for a time t seconds, and a heating and drying step of subsequently heating and drying the applied surface-treatment solution in a drying furnace, wherein $\Delta T/t$ is 1°C/s to 60°C/s .

[0018] [6] A zinc or zinc alloy coated steel sheet with a surface-coating layer, comprising: a zinc or zinc alloy coated steel sheet; and a surface-coating layer having a coating weight of 50 mg/m^2 to $2,000 \text{ mg/m}^2$ obtained by applying the surface-treatment solution as recited in any one of [1] to [3] to a surface of the zinc or zinc alloy coated steel sheet, and drying the applied surface-treatment solution.

[0019] [7] The zinc or zinc alloy coated steel sheet with a surface-coating layer according to [6], wherein the surface-coating layer is formed by a Zr-containing phase and a Zr-free phase, and the Zr-containing phase has a volume fraction of 5 % to 40 %.

[0020] [8] The zinc or zinc alloy coated steel sheet with a surface-coating layer according to [6] or [7], wherein the zinc or zinc alloy coated steel sheet is a hot-dip Zn-Al alloy coated steel sheet comprising a hot-dip Zn-Al alloy coated layer formed on at least one surface of a base steel sheet, the hot-dip Zn-Al alloy coated layer containing (consisting of), by mass%, Al: 3.0 % to 6.0 %, Mg: 0.2 % to 1.0 %, and Ni: 0.01 % to 0.10 %, with the balance being Zn and inevitable impurities.

(Advantageous Effect)

[0021] The zinc or zinc alloy coated steel sheet with a surface-coating layer according to the present disclosure does not contain a chromium compound in

the surface-coating layer and is excellent in all of heat discoloration resistance, heat cracking resistance, planar part anti-corrosion property, corrosion resistance after alkali degreasing, blackening resistance, stack blackening resistance, anti-water stain property, solvent resistance, perspiration resistance, coating adhesion property, and storage stability. Further, the surface-treatment solution and the production method according to the disclosure can produce a zinc or zinc alloy coated steel sheet with a surface-coating layer having the above-mentioned excellent characteristics.

BRIEF DESCRIPTION OF THE DRAWING

[0022] FIG. 1 is an SEM image of a surface of a surface-coating layer in Example No. 164.

DETAILED DESCRIPTION

[0023] <Zinc or zinc alloy coated steel sheet>

Examples of the zinc or zinc alloy coated steel sheet used in the disclosure include: an electrogalvanized steel sheet, a hot-dip galvanized steel sheet, a Zn-Al alloy coated steel sheet, a Zn-Fe alloy coated steel sheet, a Zn-Mg alloy coated steel sheet, a Zn-Al-Mg alloy coated steel sheet, and the like.

[0024] More preferably, the zinc or zinc-alloy coated steel sheet may be a hot-dip Zn-Al alloy coated steel sheet comprising a hot-dip Zn-Al alloy coated layer formed on at least one surface of a base steel sheet, the hot-dip Zn-Al alloy coated layer containing, by mass%, Al: 3.0 % to 6.0 %, Mg: 0.2 % to 1.0 %, and Ni: 0.01 % to 0.10 %, with the balance being Zn and inevitable impurities. This steel sheet has an advantage that it exhibits better red rust resistance than other coated steel sheets configured otherwise. It is thus advantageous when used in a more severe corrosive environment such as outdoor. More preferably, the hot-dip Zn-Al alloy coated steel sheet contains a Zn-Al-Mg eutectic alloy in the hot-dip Zn-Al alloy coated layer. The Zn-Al-Mg eutectic alloy is preferably contained in an area ratio of 1 % to 50 % on the surface of the coated layer.

[0025] The zinc or zinc alloy coated steel sheet with a surface-coating layer according to the disclosure comprises: a zinc or zinc alloy coated steel sheet; and a surface-coating layer (hereinafter also simply referred to as a "layer")

having a coating weight per side of 50 mg/m² to 2,000 mg/m² obtained by applying a surface-treatment solution described later to a surface of the zinc or zinc alloy coated steel sheet, and drying the applied surface-treatment solution. The zinc or zinc alloy coated steel sheet disclosed herein is
5 excellent in all of heat discoloration resistance, heat cracking resistance, planar part anti-corrosion property, corrosion resistance after alkali degreasing, blackening resistance, stack blackening resistance, anti-water stain property, solvent resistance, perspiration resistance, coating adhesion property, and storage stability.

10 **[0026]** <Surface-treatment solution for zinc or zinc alloy coated steel sheet>
The surface-treatment solution for a zinc or zinc alloy coated steel sheet according to the disclosure (hereinafter simply referred to as a "surface-treatment solution") may contain a glycidyl group-containing silane coupling agent (A), a tetraalkoxysilane (B), a zirconium carbonate compound
15 (C), an anionic polyurethane resin (D) having a glass transition temperature (T_g) of 80 °C to 130 °C, a vanadium compound (E), a molybdic acid compound (F), and water, and may optionally contain a sodium silicate (G) and a wax (H).

[0027] <Glycidyl group-containing silane coupling agent (A)>

20 To the surface-treatment solution according to the disclosure, a glycidyl group-containing silane coupling agent (A) is added. The silane coupling agent (A) is not particularly limited as long as it contains a glycidyl group and a lower alkoxy group having 1 to 5, preferably 1 to 3 carbon atoms as hydrolyzable groups directly bonded to Si element. Examples thereof
25 include, but are not limited to, 3-glycidoxypropyltrimethoxysilane, 3-glycidoxypropyltriethoxysilane, 3-glycidoxypropylmethyldimethoxy- silane, and 2-(3,4-epoxycyclohexyl)ethyltriethoxysilane. Of these, 3-glycidoxypropyltrimethoxysilane and 3-glycidoxypropyltriethoxysilane are preferable from the perspectives of capability of generating more
30 condensation points between the glycidyl group-containing silane coupling agents (A) and more condensation points with a tetraalkoxysilane (B) and a zirconium carbonate compound (C) described later, and of providing good barrier property after the layer formation.

[0028] In the glycidyl group-containing silane coupling agent (A), an alkoxy

group is directly bonded to Si element in the compound, and it reacts with water in an aqueous solution to form a silanol group. This silanol group reacts with the surface of the zinc or zinc alloy coated steel sheet or undergoes a condensation reaction in a complex manner with components (B) and (C) described later.

[0029] It is necessary that a mass ratio (A_S/X_S) of the solid content mass (A_S) of the glycidyl group-containing silane coupling agent (A) to the total mass (X_S) be from 0.20 to 0.40, preferably from 0.24 to 0.37, and more preferably from 0.27 to 0.34. When the mass ratio is less than 0.20, the planar part anti-corrosion property and the corrosion resistance after alkali degreasing are inferior. When the mass ratio exceeds 0.40, the heat cracking resistance is inferior.

[0030] <Tetraalkoxysilane (B)>

When the component (A) is used alone, the heat cracking resistance is inferior.

Thus, tetraalkoxysilane (B) is added to the surface-treatment solution disclosed herein. In the absence of the component (B), the organic functional group of the component (A) undergoes thermal oxidative decomposition in a heating atmosphere at 500 °C or higher, causing large cracks. On the other hand, when the component (B) is added in an appropriate amount, a dense layer with good barrier property can be obtained while suppressing the amount of the component (A) to such an extent that the heat cracking resistance is acceptable. Since the layer obtained from the component (A) and the component (B) is dense, cracks upon heating can also be refined, no cracks are visually observed, and excellent heat cracking resistance is obtained.

[0031] The tetraalkoxysilane (B) contains four lower alkoxyl groups as hydrolyzable groups directly bonded to Si element, and is not particularly limited as long as it can be represented by a general expression $Si(OR)_4$ (in the expression, R represents the same or different alkyl groups having carbon atoms of 1 to 5). Examples thereof may include: tetramethoxysilane; tetraethoxysilane; and tetrapropoxysilane, and at least one or more of these compounds may be used. Among these, tetraethoxysilane and tetramethoxysilane are preferable from the viewpoint of capability of generating more condensation points between tetraalkoxysilanes (B) and more

condensation points with the component (A) or the below-described component (C), thereby providing good barrier property after the layer formation.

[0032] In the tetraalkoxysilane (B), an alkoxy group directly bonded to Si element in the compound, and the alkoxy group reacts with water in an aqueous solution to form a silanol group. This silanol group reacts with the surface of the zinc or zinc alloy coated steel sheet and undergoes a condensation reaction in a complex manner with the component (A) and the below-described component (C).

[0033] The mass ratio (B_S/X_S) of the solid content mass (B_S) of the tetraalkoxysilane (B) to the total mass (X_S) needs to be from 0.010 to 0.30, and is preferably from 0.03 to 0.23, and more preferably from 0.06 to 0.15. When the mass ratio is less than 0.010, the heat cracking resistance is lowered. When the mass ratio exceeds 0.30, the planar part anti-corrosion property and the corrosion resistance after alkali degreasing deteriorate.

[0034] The component (A) and the component (B) may be used alone, but it is preferable to add them to the surface-treatment solution after a condensation reaction of the component (A) with the component (B) to give a low condensate, in which case a even better barrier property can be obtained after the layer formation. This low condensate has a polysiloxane bond formed by a condensation reaction between the silanol groups of the components (A) and (B) as a main skeleton, and may be the one in which all of the terminal groups bonded to Si element are alkoxy groups or may be the one in which some of the groups directly bonded to Si element are alkoxy groups.

[0035] The condensation degree of the low condensate obtained by the condensation reaction of the component (A) with the component (B) is preferably 2 to 30, and more preferably 2 to 10. When the condensation degree is 30 or less, it is possible to stably use the component (A) and the component (B) without causing a white precipitate in the aqueous solution. The low condensate may be obtained by reacting the component (A), the component (B), and a chelating agent described later at a reaction temperature of 1 °C to 70 °C for about 10 minutes to 20 hours to perform autoclave treatment. Examples of the chelating agent include: hydroxycarboxylic acids such as malic acid, acetic acid, and tartaric acid; monocarboxylic acids;

dicarboxylic acid such as oxalic acid, malonic acid, succinic acid, citric acid, and adipic acid or polycarboxylic acids such as tricarboxylic acid; and aminocarboxylic acids such as glycine, and at least one of these may be used.

5 **[0036]** The condensation state of the low condensate can be measured using gel permeation chromatography (GPC), NMR, and FT-IR described in JIS-K7252-4.

10 **[0037]** The chelating agent acting to stabilize this low condensate acts when the alkoxy group of the component (A) and the alkoxy group of the component (B) undergo hydrolysis reaction with water and a chelating agent. Although the reason for the stabilizing effect by the chelating agent is uncertain, this effect is considered as being obtained by the chelating agent properly coordinating to the silanol groups derived from the components (A) and (B) caused by the hydrolysis reaction. That is, a proper coordination action of the chelating agent to the silanol group suppresses excessive condensation of
15 the components (A) and (B), and a surface-treatment solution excellent in storage stability can be obtained. Furthermore, stable layer quality can be obtained even after long-term storage of the surface-treatment solution.

20 **[0038]** The chelating agent is effective for securing corrosion resistance in addition to storage stability. Although the reason is uncertain, the chelating agent is considered to coordinate also with the vanadium compound (E) described later, and when the layer is exposed to a corrosive environment, the chelating agent coordinated to the vanadium compound (E) elutes with a vanadium compound (E), whereby the condensation of the components (A) and (B) losing the ligand in the layer progresses, thereby improving the
25 barrier property of the layer and contributing to the corrosion resistance.

[0039] <Zirconium carbonate compound (C)>

A zirconium carbonate compound (C) is added to the surface-treatment solution disclosed herein. By using the components (A) and (B) in combination with the zirconium carbonate compound (C), it is possible to
30 provide a dense layer that has good barrier property and that is excellent in heat cracking resistance, planar part anti-corrosion property, corrosion resistance after alkali degreasing, anti-water stain property, perspiration resistance, blackening resistance, and stack blackening resistance. The reason why the barrier property is enhanced is that the zirconium carbonate

compound (C) has a hydroxyl group which is a condensation point with a silanol group. Further, since the zirconium carbonate compound (C) produces zirconium oxide and zirconium hydroxide when dried, the resulting layer is excellent in planar part anti-corrosion property, corrosion resistance
5 after alkali degreasing, anti-water stain property, perspiration resistance, blackening resistance, and stack blackening resistance. The reason why the heat cracking resistance is high is considered to be that the volume shrinkage of zirconium oxide is low even when it is exposed to a heating atmosphere at 500 °C, and furthermore, due to the thermal expansion of the coated layer,
10 visually-unobservable micro cracks form in the zirconium oxide layer and disperse the stress such that no visually-observable cracks are formed, whereby excellent heat cracking resistance is obtained. Examples of the zirconium carbonate compound (C) include salts such as sodium, potassium, lithium, and ammonium of zirconium carbonate compounds, and at least one
15 of these may be used. Among these, ammonium zirconium carbonate is preferable from the viewpoints of layer formability, anti-water stain property, and the like.

[0040] The mass ratio (C_Z/X_S) of the ZrO_2 equivalent mass (C_Z) in the zirconium carbonate compound (C) to the total mass (X_S) needs to be from
20 0.45 to 0.70, and is preferably from 0.48 to 0.67, and more preferably from 0.50 to 0.63. When the mass ratio is less than 0.45, the barrier property derived from the zirconium carbonate compound (D) is insufficient, and the planar part anti-corrosion property, the corrosion resistance after alkali degreasing, and the stack blackening resistance are lowered. Note that the
25 blackening resistance is maintained. On the other hand, when the mass ratio exceeds 0.70, many hard components derived from the zirconium carbonate compound are contained, and good coating adhesion property can not be obtained.

[0041] The layer containing the above-described components (A) to (C) is
30 usually hard and is excellent in barrier property, planar part anti-corrosion property, and corrosion resistance after alkali degreasing. This layer does not cause visually-observable cracks even upon heating above 500 °C due to the existence of the dense layer obtained from the tetraalkoxysilane (B) and the zirconium carbonate compound (C), and is excellent in heat cracking

resistance.

[0042] <Anionic polyurethane resin (D)>

An anionic polyurethane resin (D) having a glass transition temperature (T_g) of 80 °C to 130 °C is added to the surface-treatment solution disclosed herein
5 in order to suppress cracks derived from inorganic components. As a result, it is possible to obtain a layer excellent in heat discoloration resistance, heat cracking resistance, planar part anti-corrosion property, blackening resistance, stack blackening resistance, anti-water stain property, solvent resistance, perspiration resistance, and coating adhesion property. The polyurethane
10 resin has a high molecular weight and a urethane bond with high intermolecular cohesive force, and is thus dense and has good barrier property. Although the polyurethane resin itself has adhesion to the substrate, it exhibits even better barrier property when used in combination with the components (A) to (C). Accordingly, a layer having excellent performance
15 as described above can be obtained.

[0043] Examples of a polyol which is the basic skeleton affecting the properties of the urethane resin include polyether-based polyols, polyester-based polyols, and polycarbonate-based polyols. Polyester-based polyols and polycarbonate-based polyols have polar groups, and can provide a
20 tough layer by intermolecular interaction. Although polycarbonate-based polyols are expensive, they are excellent in mechanical strength. Since polyether-based polyols have no polar group, it is somewhat inferior in mechanical strength, yet is chemically stable in terms of, for example, hydrolysis resistance. The polyol of the component (D) used in the present
25 disclosure is not particularly limited, yet from the viewpoints of the target properties of the present disclosure such as corrosion resistance after alkali degreasing and anti-water stain property, it is preferable to use a polyether-based polyol.

[0044] The weight average molecular weight of the component (D) is
30 preferably about 10,000 to 500,000, and more preferably 50,000 to 300,000, when measured by the gel permeation chromatography as prescribed in JIS-K7252-4. Increasing the weight average molecular weight may improve the T_g and mechanical properties of the urethane resin, and hence the barrier property of the layer is improved, making it possible to improve the planar

part anti-corrosion property, the corrosion resistance after alkali degreasing, the anti-water stain property, the solvent resistance, and the perspiration resistance.

[0045] The anionic polyurethane resin (D) is obtained by a general synthesis method using a polyether polyol (particularly diol) and polyisocyanate (particularly diisocyanate) as raw materials. Optionally, a polyamine (particularly diamine), a carboxylic acid having two or more (particularly preferably two) hydroxyl groups, and a reactive derivative of the carboxylic acid may be added as raw materials. Without limitation, a more specific synthesis may prepare a urethane prepolymer having isocyanate groups at both ends from a polyether diol and a diisocyanate and add a carboxylic acid having two hydroxyl groups or to obtain an anionic polyurethane resin by reacting the reactive derivative in the solvent to give a derivative having an isocyanate group at each end, then adding triethanolamine or the like as a counter cation, and subsequently adding to water to obtain an emulsion. Thereafter, chain extension may be carried out by further adding diamine, if necessary.

[0046] As the polyisocyanate used for producing the component (D), aliphatic, alicyclic, and aromatic polyisocyanates can be used, and any of these may be used. Specific examples thereof include tetramethylene diisocyanate, hexamethylene diisocyanate, lysine diisocyanate, hydrogenated xylylene diisocyanate, 1,4-cyclohexylene diisocyanate, 4,4'-dicyclohexyl methane diisocyanate, 2,4'-dicyclohexyl methane diisocyanate, isophorone diisocyanate, 3,3'-dimethoxy-4,4'-biphenylene diisocyanate, 1,5-naphthalene diisocyanate, 1,5-tetrahydronaphthalene diisocyanate, 2,4-tolylene diisocyanate, 2,6-tolylene diisocyanate, 4,4'-diphenylmethane diisocyanate, 2,4'-diphenylmethane diisocyanate, phenylene diisocyanate, xylylene diisocyanate, and tetramethylxylylene diisocyanate. Among these, an aliphatic or alicyclic polyisocyanate, such as tetramethylene diisocyanate, hexamethylene diisocyanate, lysine diisocyanate, hydrogenated xylene diisocyanate, 1,4-cyclohexylene diisocyanate, 4,4'-dicyclohexyl methane diisocyanate, 2,4'-dicyclohexyl methane diisocyanate, and isophorone diisocyanate, is preferably used since a layer excellent not only in solvent resistance, planar part anti-corrosion property, corrosion resistance after

alkali degreasing, and the like, but also in heat discoloration resistance can be obtained.

[0047] Examples of the polyether polyols used for producing the component (D) include, in addition to the above-mentioned low molecular weight polyols
5 such as 1,2-propanediol, 1,3-propanediol, trimethylolpropane, glycerin, polyglycerin, and pentaerythritol, bisphenol A, ethylene oxide and/or propylene oxide adducts to amine compounds such as ethylenediamine and the like, polytetramethylene ether glycol, and the like.

[0048] The carboxylic acid having two or more hydroxyl groups, preferably
10 two hydroxyl groups, or a reactive derivative thereof used in the production of the component (D) is used for introducing an acidic group into the component (D) and for making the component (D) water dispersible. Examples of the carboxylic acid include dimethylol alkanoic acids such as dimethylolpropionic acid, dimethylolbutanoic acid, dimethylolpentanoic acid, and
15 dimethylolhexanoic acid. Examples of the reactive derivative include an acid anhydride. In this way, by making the component (D) self-water dispersible and not using or minimizing the use of an emulsifying agent, it is possible to obtain a layer excellent in anti-water stain property.

[0049] In producing the component (D), polyamine, water, and the like are
20 used. The polyamine, water, and the like are used to extend the chain of the prepared prepolymer. Examples of the polyamine to be used include hydrazine, ethylenediamine, propylenediamine, 1,6-hexanediamine, tetramethylenediamine, isophoronediamine, xylylenediamine, piperazine, 1,1'-bicyclohexane-4,4'-diamine, diphenylmethanediamine,
25 ethyltolylenediamine, diethylenetriamine, dipropylenetriamine, triethylenetetramine, and tetraethylenepentamine, and these can be used alone or in combination of two or more.

[0050] In order to improve the stability of the resin at the time of synthesizing the component (D) and further enhance the layer formability
30 when the ambient environment at the time of layer formation is in a low-temperature drying condition, it is preferable to incorporate a layer-forming aid at synthesis. Examples of the layer-forming aid include butyl cellosolve, N-methyl-2-pyrrolidone, butyl carbitol, and texanol; among these preferred is N-methyl-2-pyrrolidone.

[0051] The glass transition temperature (T_g) of the component (D) needs to be 80 °C to 130 °C, and is preferably 85 °C to 125 °C, and more preferably 90 °C to 120 °C. The glass transition temperature is adjusted according to the molecular weight of the polyol to be used and the like. When the glass transition temperature (T_g) is lower than 80 °C, the solvent resistance is inferior. This is because the cohesiveness among the components (D) when formed into a layer or the cohesiveness with the components (A) to (C) is insufficient and the barrier property of the layer deteriorates. On the other hand, when the glass transition temperature (T_g) exceeds 130 °C, the layer becomes excessively hard, and excellent coating adhesion property can not be obtained. The glass transition temperature (T_g) of the component (E) can be measured by using a dynamic viscoelasticity measuring device (RSAG2 available from TA Instruments) to measure the dynamic viscoelasticity of a layer prepared as a measurement sample by drying at room temperature for 24 hours, then at 80 °C for 6 hours, and subsequently at 120 °C for 20 minutes, and to obtain the local maximum value of $\tan \delta$.

[0052] The mass ratio (X_S/D_S) of the total mass (X_S) of the components (A) to (C) to the solid content mass (D_S) of the anionic polyurethane resin (D) needs to be from 0.05 to 0.35, preferably from 0.10 to 0.32, and more preferably from 0.19 to 0.28. When the mass ratio is less than 0.05, the amount of the anionic polyurethane resin is large and the barrier property is insufficient. Accordingly, the planar part anti-corrosion property, the corrosion resistance after alkali degreasing, and the solvent resistance are lowered. On the other hand, when the mass ratio exceeds 0.35, the amount of the anionic polyurethane resin is small, and the heat discoloration resistance, heat cracking resistance, blackening resistance, stack blackening resistance, anti-water stain property, perspiration resistance, and coating adhesion property are inferior.

[0053] <Vanadium compound (E)>

The vanadium compound (E) is added to the surface-treatment solution disclosed herein. The vanadium compound (E) exists in a uniformly-dispersed manner in the layer, yet it elutes appropriately in a corrosive environment and bonds with zinc ions eluted similarly in the corrosive environment to form a dense passive layer, thereby improving the

planar part anti-corrosion property and the corrosion resistance after alkali degreasing. Examples of the vanadium compound (E) include ammonium metavanadate, sodium metavanadate, and vanadium acetylacetonate, and at least one of these may be used.

5 **[0054]** The mass ratio ($E_V/(X_S + D_S)$) of the V equivalent mass (E_V) in the vanadium compound (E) to the total mass ($X_S + D_S$) of the total mass (X_S) of the components (A) to (C) and the solid content mass (D_S) of the component (D) needs to be from 0.0010 to 0.015, preferably from 0.0017 to 0.011, and more preferably from 0.0023 to 0.007. When the mass ratio is less than
10 0.0010, the effect of forming a passive layer with zinc ions is insufficient, and the planar part anti-corrosion property and the corrosion resistance after alkali degreasing are lowered. On the other hand, when the mass ratio exceeds 0.015, it is not possible to obtain good blackening resistance, stack blackening resistance, anti-water stain property, perspiration resistance, and coating
15 adhesion property. Further, since oxidative discoloration of vanadium appears during heating above 500 °C, the heat discoloration resistance and heat cracking resistance are also lowered.

[0055] <Molybdic acid compound (F)>

A molybdic acid compound (F) is added to the surface-treatment solution
20 disclosed herein in order to obtain excellent blackening resistance and stack blackening resistance. Examples of the molybdic acid compound include molybdic acid, ammonium molybdate, sodium molybdate, potassium molybdate, magnesium molybdate, and zinc molybdate, and it is preferable to use at least one selected from these in the present disclosure.

25 **[0056]** The black patina (blackening) phenomenon of a zinc or zinc alloy coated layer is believed to be caused by the formation of oxygen-deficient zinc oxide when the zinc or zinc alloy coated layer is exposed to a high-temperature and high-humidity atmosphere. Molybdenum is a second transition metal having various valences, and it is present as MoO_2 or MoO_3 in
30 chemical combination with oxygen in the air. In the present disclosure, a molybdate such as MoO_4^{2-} is used. It is considered that this molybdate is uniformly added to the layer and then reduced to a molybdenum oxide such as MoO_3 under a high-temperature and high-humidity atmosphere. It is considered that through this action, oxygen is appropriately supplied to the

zinc on the surface of the zinc or zinc alloy coated layer, and formation of oxygen-deficient zinc oxide is suppressed. On the other hand, excessive addition of molybdate causes deterioration of the planar part anti-corrosion property and corrosion resistance after alkali degreasing.

5 **[0057]** The mass ratio ($F_M/(X_S + D_S)$) of the Mo equivalent mass (F_M) in the molybdic acid compound (F) to the total mass ($X_S + D_S$) of the total mass (X_S) of the components (A) to (C) and the solid content mass (D_S) of the component (D) needs to be from 0.0010 to 0.015, preferably from 0.0027 to 0.012, and more preferably from 0.0043 to 0.009. When the mass ratio is
10 less than 0.0010, excellent blackening resistance and stack blackening resistance can not be obtained. When the mass ratio exceeds 0.015, good planar part anti-corrosion property and corrosion resistance after alkali degreasing can not be obtained.

[0058] <Sodium silicate (G)>

15 In the surface-treatment solution disclosed herein, sodium silicate (G) may be added in place of some of the zirconium carbonates (C) in order to obtain even better heat cracking resistance. The amount of zirconium carbonates (C) can be reduced by increasing the amount of the sodium silicate (G). The sodium contained in the sodium silicate (G) bonds with an oxygen atom of a SiO_4
20 tetrahedron separated from the SiO_4 bonding network by heat. Therefore, recombination of the SiO_4 bonding network is prevented. By this action, the component (G) imparts fluidity to the silicate glass, and the softening temperature of the silicate glass is lowered from at or above 1,700 °C to 500 °C to 700 °C. In the present disclosure, it is considered that by utilizing
25 this effect, when a layer including the components (A) to (C) that is hard and has a low thermal expansion coefficient is heated to 500 °C or higher, flowability is imparted to the layer, and excellent heat resistant cracking resistance is obtained.

[0059] The sodium silicate (G) used in the present disclosure includes SiO_2
30 and Na_2O , and the molar ratio thereof is not particularly limited as long as $\text{SiO}_2/\text{Na}_2\text{O}$ is from 4 to 1. Examples thereof include No. 2 sodium silicate and No. 3 sodium silicate, and one or more of these may be used. A more preferable molar ratio is $\text{SiO}_2/\text{Na}_2\text{O}$ of from 4 to 2. When $\text{SiO}_2/\text{Na}_2\text{O}$ exceeds 4, the effect for heat cracking resistance is insufficient. When

SiO₂/Na₂O is less than 1, although the effect on heat cracking resistance is saturated, immobilization of the sodium silicate (G) into the layer becomes difficult, and the blackening resistance can be maintained. However, the stack blackening resistance, which is evaluated in a more severe environment, is inferior.

[0060] From the viewpoint of not lowering the stack blackening resistance, with regard to the amount of the sodium silicate (G), the mass ratio ($G_S/(X_S + G_S)$) of the solid content mass (G_S) of the sodium silicate (G) to the total mass ($X_S + G_S$) of the total mass (X_S) of components (A) to (C) and the solid mass (G_S) of the sodium silicate (G) is less than 0.05 (inclusive of 0.00, i.e., including the case where it is not added). It is more preferably 0.047 or less, and still more preferably 0.042 or less. When the mass ratio is 0.05 or more, the stack blackening resistance is inferior. On the other hand, the lower limit is preferably set to 0.00, yet it may be 0.001 or more, and more preferably 0.005 or more, in expectation of further improving heat cracking resistance.

[0061] <Wax (H)>

A wax (H) may be added to the surface-treatment solution disclosed herein in order to improve lubricity. The wax (H) is not particularly limited as long as it is compatible with the solution. Examples thereof include polyolefin wax such as polyethylene, montan wax, paraffin wax, microcrystalline wax, carnauba wax, lanolin-based wax, silicon-based wax, and fluorine-based wax, and at least one of these may be suitably used. Examples of the polyolefin wax include polyethylene wax, oxidized polyethylene wax, and polypropylene wax, and at least one of these may be used.

[0062] The mass ratio ($H_S/(X_S + D_S)$) of the solid content mass (H_S) of the wax (H) to the total mass ($X_S + D_S$) is preferably from 0.002 to 0.10, and more preferably from 0.01 to 0.08. When the mass ratio is 0.002 or more, a sufficient lubricity-improving effect can be obtained. On the other hand, when the mass ratio is 0.10 or less, there is no concern for excessively high lubricity leading to coil collapse in the coiling process during coil production. Also, there is no concern that the planar part anti-corrosion property, the corrosion resistance after alkali degreasing, or the coating adhesion property may deteriorate.

[0063] <pH: 8.0 to 10.0>

The surface-treatment solution disclosed herein is obtained by mixing the above-mentioned components in water such as deionized water or distilled water. The solid content ratio of the surface-treatment solution may be appropriately selected, yet it is preferably 10 % to 20 %. The pH of the surface-treatment solution needs to be adjusted to 8.0 to 10.0, and preferably 8.5 to 9.5. When the pH is less than 8.0 or more than 10.0, the storage stability of the surface-treatment solution decreases. Further, when the pH exceeds 10.0, the etching of the zinc or zinc alloy coated layer becomes excessive and the planar part anti-corrosion property and the corrosion resistance after alkali degreasing are lowered. When pH is adjusted, ammonia or a salt thereof and any one or more of the above-mentioned chelating agents may be appropriately used.

[0064] Further, if required, an additive may be added to the surface-treatment solution, such as an alcohol, a ketone, a cellosolve, an amine-based water-soluble solvent, a defoamer, a fungicidal/antifungal agent, a coloring agent, a wettability improving agent for uniform coating, a resin, a surfactant, or the like. However, it is important that these additives are added only to such an extent that the addition will not adversely affect the quality achievable by the present disclosure. The maximum amount is preferably less than 5 mass% with respect to the total solid content of the surface-treatment solution.

[0065] <Method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer>

The method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer according to the present disclosure comprises: applying the above-described surface-treatment solution to a surface of a zinc or zinc alloy coated steel sheet; and subsequently drying the applied surface-treatment solution to form a surface-coating layer having a coating weight of 50 mg/m² to 2,000 mg/m². The conditions and methods for forming the layer will be described in detail below.

[0066] The coating weight of the surface-coating layer after heating and drying is 50 mg/m² to 2,000 mg/m² per side, and preferably 500 mg/m² to 1,500 mg/m² per side. When the coating weight is less than 50 mg/m², the barrier property becomes insufficient, and the planar part anti-corrosion

property, corrosion resistance after alkali degreasing, blackening resistance, anti-water stain property, and perspiration resistance can not be ensured. On the other hand, when the coating weight exceeds $2,000 \text{ mg/m}^2$, the layer is thick, and the heat discoloration resistance and heat cracking resistance are inferior.

[0067] Before applying the surface-treatment solution to the zinc or zinc alloy coated steel sheet, the zinc or zinc alloy coated steel sheet may optionally be subjected to a pre-treatment for removing oil and stains on its surface. Zinc or zinc alloy coated steel sheets are often coated with anti-rust oil to prevent them from rusting. Even when not coated with anti-rust oil, such steel sheets still have oil or stains which have adhered during operation. Through the above-mentioned pre-treatment, the surface of the zinc or zinc alloy coated layer is cleaned and becomes easy to be wetted uniformly. In the case where the surface of the zinc or zinc alloy coated steel sheet is free of oil and stains and can be uniformly wetted with the surface-treatment solution, such pre-treatment is not necessary. The method of pretreatment is not particularly limited, and examples thereof include hot water rinsing, organic solvent washing, and alkali degreasing washing.

[0068] As a method of applying the surface-treatment solution to a surface of a zinc or zinc alloy coated steel sheet, an optimum method may be selected as appropriate depending on the shape of the zinc or zinc alloy coated steel sheet to be processed. Examples thereof include roll coating, bar coating, dip coating, and spray coating. After the application, an air knife or squeezing rolls may be used to adjust the coating weight or to ensure the uniformity of appearance or layer thickness.

[0069] As a means for heating and drying the zinc or zinc alloy coated steel sheet after the application of the surface-treatment solution, a dryer, a hot air oven, a high frequency induction heater, or a drying furnace such as an infrared oven may be used.

[0070] Preferably, T_S is 15°C to 55°C , T_L is 10°C to 40°C , and ΔT is 5°C to 40°C , where T_S and T_L represent a temperature of the zinc or zinc alloy coated steel sheet and a temperature of the surface-treatment solution in the applying of the surface-treatment solution, respectively, and ΔT represents $T_S - T_L$. It is also preferable that the drying is performed in two steps including

a preliminary drying step of drying the applied surface-treatment solution in the atmosphere for a time t seconds, and a heating and drying step of subsequently heating and drying the applied surface-treatment solution in a drying furnace, wherein $\Delta T/t$ is $1\text{ }^{\circ}\text{C/s}$ to $60\text{ }^{\circ}\text{C/s}$.

5 **[0071]** T_L is preferably around room temperature, that is, from $10\text{ }^{\circ}\text{C}$ to $40\text{ }^{\circ}\text{C}$. When the T_L is less than $10\text{ }^{\circ}\text{C}$, the fluidity of the surface-treatment solution decreases, and when it exceeds $40\text{ }^{\circ}\text{C}$, the storage stability of the surface-treatment solution deteriorates. T_S is preferably set to $15\text{ }^{\circ}\text{C}$ to $55\text{ }^{\circ}\text{C}$ in order to ensure ΔT for obtaining a two-phase separation layer in
10 which a Zr-containing phase described later has a desired volume fraction.

[0072] In this embodiment, firstly, it is important to provide a temperature difference ΔT between T_S and T_L by at least a predetermined temperature, and secondly, to determine a time t (sec) in the preliminary drying step in relation to the temperature difference ΔT . In this way, moisture in the
15 surface-treatment solution layer formed on the surface of the steel sheet can be gradually vaporized. That is, in the surface-treatment solution layer formed on the surface of the steel sheet, before the water vaporizes, Si begins a condensation reaction with moisture together with Zr, and a desired surface-coating layer can be obtained. When ΔT is less than $5\text{ }^{\circ}\text{C}$, moisture
20 in the surface-treatment solution layer does not vaporize, making it impossible to obtain a two-phase separation layer having a Zr-containing phase described later in a desired volume fraction. When ΔT is over $40\text{ }^{\circ}\text{C}$, moisture in the surface-treatment solution layer begins to vaporize before the above condensation reaction starts, making it impossible to secure a
25 predetermined amount of a phase (a Zr-free phase described later) made of a resin component constituting the skeleton of the layer. When $\Delta T/t$ is less than $1\text{ }^{\circ}\text{C/s}$, the above condensation reaction becomes excessive and a two-phase separation layer having a volume fraction as described below can not be obtained. In the case of $\Delta T/t$ exceeding $60\text{ }^{\circ}\text{C/s}$, the condensation
30 reaction becomes insufficient, and it is impossible to secure a predetermined amount of a phase (a Zr-free phase described later) made of a resin component constituting the skeleton of the layer.

[0073] The subsequent heating and drying step can be carried out according to the conventional method, and is not particularly limited, yet the peak metal

temperature (PMT) is preferably 60 °C to 200 °C, and more preferably 80 °C to 180 °C. When the PMT is 200 °C or lower, the layer is less prone to cracks and the layer components hardly undergo thermal decomposition, and various performances required by the present disclosure are not deteriorated.

5 On the other hand, if the PMT is 60 °C or higher, the bonding between the components of the surface-coating layer is sufficiently obtained, various performances required by the present disclosure do not deteriorate. Regarding the heating time, it is preferably 0.1 seconds to 60 seconds, and particularly preferably 1 second to 30 seconds from the viewpoint of
10 productivity and the like, while optimal conditions are selected as appropriate depending on the conditions such as the composition of the zinc or zinc alloy coated steel sheet to be used, the process and configuration of the production line, and so on.

[0074] <Form of surface-coating layer>

15 The surface-coating layer thus formed on the surface of the zinc or zinc alloy coated steel sheet is separated into a Zr-containing phase and a Zr-free phase by Si undergoing a condensation reaction with Zr during the heating and drying. As used herein, "Zr-free phase" means a phase having a Zr content of less than 3 mass% with respect to the entire constituent elements.

20 **[0075]** The Zr-containing phase refers to a phase that is composed mainly of inorganic materials such as oxides of Si, Zr, and V. The Zr-free phase refers to a phase that constitutes a basic skeleton for forming the surface-coating layer, that is composed mainly of C and O, and that further contains resin components including Si. Since Si is concentrated in the Zr-containing
25 phase, the Si concentration of the Zr-containing phase is higher than that of the Zr-free phase.

[0076] Si in the surface-coating layer may enhance the bondability between Si, the bondability between the Zr-containing phase and the Zr-free phase, and the bondability between the layer and the surface of the coated layer, thereby
30 improving the corrosion resistance.

[0077] Zr in the surface-coating layer is an important element for forming a phase made of an inorganic material including Zr. By distributing the Zr-containing phase in the surface-coating layer, it is possible to enhance the bondability between the Zr-containing phase and the Zr-free phase and to

form a dense layer with good barrier property. To obtain this effect, the Zr-containing phase has a volume fraction of preferably 5 % to 40 %, and more preferably 5 % to 30%, with respect to the entire surface-coating layer. When the volume fraction of the Zr-containing phase is less than 5 %, elution of V becomes insufficient, and the corrosion resistance is no longer improved. When the volume fraction of the Zr-containing phase exceeds 40 %, the barrier property of the layer imparted by organic components is deteriorated, and the corrosion resistance is no longer improved.

[0078] When the ratio between the concentrations of Zr and Si in the Zr-containing phase is expressed as $Zr/(Si + Zr)$ in terms of mass ratio, the ratio is preferably 0.50 or more and 0.95 or less.

[0079] When coexisting with the Zr-containing phase, V in the surface-coating layer adequately elutes under a corrosive environment and bonds with zinc ions eluted from the coating surface to form a dense passive layer, thereby improving corrosion resistance. To obtain this effect, the V content in the Zr-containing phase is preferably 0.003 to 0.1 when expressed as $V/(Si + Zr)$ in terms of mass ratio.

[0080] The volume fraction of the Zr-containing phase can be evaluated by observing a surface or a cross section of the layer with an electron microscope. A scanning electron microscope (SEM) can be used for the observation. In recent SEMs, there are various types of secondary electron detector and backscattered electron detector depending on manufacturer and model, and it is reported that different information can be obtained depending on viewing conditions. Therefore, to observe the layer surface, appropriate observation conditions may be selected depending on the apparatus to be used every time. However, when the accelerating voltage varies greatly, the information depth varies and the evaluation results may vary accordingly. It is thus preferable to evaluate the acceleration voltage in the range of 0.5 kV to 3 kV. For observation of the cross section of the layer, it is suitable to observe a cross section of the layer processed with the focused ion beam (FIB) under an SEM, or to observe a sample processed to flakes with FIB under a transmission electron microscope (TEM) or a scanning transmission electron microscope (STEM). The Zr-containing phase and the Zr-free phase can be clearly distinguished by the contrast difference in electron microscope images. In

particular, when evaluating by SEM observation of a surface of the layer, a secondary electron image observation is carried out using an Everhart-Thornley type detector as a general secondary electron detector with a low accelerating voltage of about 0.5 kV to 3 kV, where a phase made of an inorganic material (a Zr-containing phase) appears bright, while a phase made of a resin component (a Zr-free phase) dark.

[0081] Accordingly, it is possible to set the observation condition in which the contrast difference appears clearly, binarize the observed electron microscope image, calculate the area ratio of the Zr-containing phase, and consider the result as the volume fraction. Since there are various methods of binarization and numerical values may vary with the selected threshold, it is important to determine the threshold so as not to largely deviate from the distinction between the bright part and the dark part discriminated from the original image. For example, when a secondary electron image is established using an Everhart-Thornley type detector at an accelerating voltage of 1 kV to 2 kV, it is effective to binarize the image using a maximum entropy method. At this time, the observation magnification is preferably about 10,000 time to 30,000 times. In addition, at this time, it is conceivable that there are variations depending on the observation location, it is preferable to acquire images of at least 5 fields of view or more for each sample and use the average as the evaluation value. As for the observation image, by performing smoothing to remove noise, more accurate evaluation can be made. However, if the smoothing is excessive, the resolution of the image deteriorates, which may affect the evaluation results. It is thus preferable to set the operator size to about 10 nm at the maximum. In addition, in the microscope observation, in order to discriminate between a Zr-containing phase and a Zr-free phase for each target region, element analysis by energy dispersive spectroscopy (EDS) can be used for the cross-sectional observation under TEM or STEM. By elemental analysis in each phase, it can be determined whether Zr is contained or not in each phase.

[0082] Advantageous effects of the present disclosure will now be described with reference to examples and comparative examples. The disclosed examples are provided by way of illustration only and not intended to be limiting of the present disclosure.

EXAMPLES

[0083] [Example 1]

(1) Sample sheet

- 5 The below-described zinc or zinc alloy coated steel sheets were used as sample sheets. Note that a zinc or zinc alloy coated layer was formed on both surfaces of each steel sheet and the coating weight in Table 1 indicates the coating weight per side of a zinc or zinc alloy coated layer. The surface area ratio of the Zn-Al-Mg-based eutectic alloy determined by the
- 10 below-described method is also listed in Table 1. SEM observation is performed at random sites on the surface of the coated layer at 100 times magnification. Then, Mg mapping is carried out by EDS in the same field of view. The result is analyzed to make binarization. From this binary image, the area ratio of the Zn-Al-Mg-based eutectic alloy is calculated. Similar
- 15 evaluation is carried out in arbitrary 8 fields of view, and finally the result of arithmetically averaging the area ratios of all fields of view is taken as the surface area ratio of the Zn-Al-Mg-based eutectic alloy.

[0084]

Table 1

ID	Zinc or zinc alloy coated steel sheet	Thickness	Coating weight per side	Surface area ratio of Zn-Al-Mg-based eutectic alloy
(I)	hot-dip galvanized steel sheet	0.8 mm	60 g/m ²	-
(II)	hot-dip Zn-5 mass% Al-0.6 mass% Mg alloy coated steel sheet	0.8 mm	90 g/m ²	22
(III)	hot-dip Zn-5 mass% Al-0.6 mass% Mg-0.04 mass% Ni alloy coated steel sheet	0.8 mm	90 g/m ²	22
(IV)	hot-dip Zn-4.8 mass% Al-0.9 mass% Mg-0.03 mass% Ni alloy coated steel sheet	0.8 mm	80 g/m ²	18
(V)	hot-dip Zn-5 mass% Al-0.7 mass% Mg-0.04 mass% Ni alloy coated steel sheet	0.8 mm	90 g/m ²	23

[0085] (2) Pre-treatment (cleaning)

The surface of each sample sheet was treated using PALCLEAN N364 S manufactured by Nihon Parkerizing Co., Ltd., to remove oil and stains from the surface. The surface of the sample sheet was then washed with tap water
5 to make sure that the surface was 100 % wettable with water, and pure water (deionized water) was poured over the surface. The sample sheet was dried in an oven of 100 °C atmosphere to remove moisture.

[0086] (3) Preparation of surface-treatment solution

The components (A) to (H) listed in Table 2 were mixed in water at the mass
10 ratios in Table 2 to obtain surface-treatment solutions having a solid content of 15 mass%.

[0087] The compounds in Table 2 are as follows.

[0088] <Glycidyl group-containing silane coupling agent (A)>

A1: 3-glycidoxypropyltriethoxysilane

15 A2: 3-glycidoxypropyltrimethoxysilane

[0089] <Tetraalkoxysilane (B)>

B1: tetramethoxysilane

B2: tetraethoxysilane

[0090] <Zirconium carbonate compound (C)>

20 C1: Potassium zirconium carbonate (ZrO_2 : 20.0 mass%)

C2: Zirconium ammonium carbonate (ZrO_2 : 20.0 mass%)

[0091] <Anionic polyurethane resin (D)>

Production Method 1 (anionic polyurethane resin D1)

To a reactor were added 100 parts by mass of a polyether polyol having a
25 number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 5 parts by mass of 2,2-dimethyl-1,3-propanediol, 100 parts by mass of 4,4-dicyclohexylmethane diisocyanate, 20 parts by mass of 2,2-dimethylolpropionic acid, and 120 parts by mass of N-methyl-2-pyrrolidone to obtain a urethane prepolymer having a free
30 isocyanate group content of 5 % with respect to the nonvolatile content. Then, 16 parts by mass of tetramethylene diamine and 10 parts by mass of triethylamine were added to 500 parts by mass of deionized water, and while stirring with a homomixer, and the urethane prepolymer was added and emulsified and dispersed. Finally, deionized water was added to obtain a

water-dispersible polyurethane resin having a solid content of 25 mass%. The glass transition temperature (T_g) of the obtained polyurethane resin (D1) was measured using a dynamic viscoelasticity measuring device and was found to be 40 °C.

5 **[0092]** Production Method 2 (anionic polyurethane resin D2)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol,
10 100 parts by mass of a polyester polyol having a number average molecular weight of 2,220 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D2) was measured using the dynamic viscoelasticity measuring device and was found to be 70 °C.

15 **[0093]** Production Method 3 (anionic polyurethane resin D3)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol,
20 100 parts by mass of a polyester polyol having a number average molecular weight of 2,060 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D3) was measured using the dynamic viscoelasticity measuring device and was found to be 80 °C.

25 **[0094]** Production Method 4 (anionic polyurethane resin D4)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that instead of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol,
30 100 parts by mass of a polyether polyol having a number average molecular weight of 1,900 obtained from polyethylene glycol and polypropylene glycol was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D4) was measured using the dynamic viscoelasticity measuring device and was found to be 85 °C.

[0095] Production Method 5 (anionic polyurethane resin D5)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyether polyol having a number average molecular weight of 1,740 obtained from polyethylene glycol and polypropylene glycol was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D5) was measured using the dynamic viscoelasticity measuring device and was found to be 90 °C.

[0096] Production Method 6 (anionic polyurethane resin D6)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyether polyol having a number average molecular weight of 1,560 obtained from polyethylene glycol and polypropylene glycol was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D6) was measured using the dynamic viscoelasticity measuring device and was found to be 105 °C.

[0097] Production Method 7 (anionic polyurethane resin D7)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyester polyol having a number average molecular weight of 1,320 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D7) was measured using the dynamic viscoelasticity measuring device and was found to be 120 °C.

[0098] Production Method 8 (anionic polyurethane resin D8)

A water dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular

weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyester polyol having a number average molecular weight of 1,240 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D8) was measured using the dynamic viscoelasticity measuring device and was found to be 125 °C.

[0099] Production Method 9 (anionic polyurethane resin D9)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyester polyol having a number average molecular weight of 1,160 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D9) was measured using the dynamic viscoelasticity measuring device and was found to be 130 °C.

[0100] Production Method 10 (anionic polyurethane resin D10)

A water-dispersible urethane resin having a solid content of 25 mass% was obtained in the same manner as in Production Method 1, except that in place of 100 parts by mass of a polyether polyol having a number average molecular weight of 5,000 obtained from polyethylene glycol and polypropylene glycol, 100 parts by mass of a polyester polyol having a number average molecular weight of 1,000 obtained from 1,6-hexanediol and adipic acid was used in the reactor. The glass transition temperature (T_g) of the obtained polyurethane resin (D10) was measured using the dynamic viscoelasticity measuring device and was found to be 140 °C.

[0101] <Vanadium compound (E)>

E1: ammonium metavanadate (V: 43.5 mass%)

E2: metavanadyl acetylacetonate (V: 19.2 mass%)

[0102] <Molybdic acid compound (F)>

F1: ammonium molybdate (Mo: 54.4 mass%)

F2: sodium molybdate (Mo: 43.8 mass%)

[0103] <Sodium silicate (G)>

G1: No. 3 sodium silicate (solid content: 38.5 mass%)

G2: No. 2 sodium silicate (solid content: 40.6 mass%)

[0104] <Wax (H)>

H1: polyethylene wax (Chemipearl® W900 manufactured by Mitsui Chemicals, Inc., solid content: 40.0 mass%; Chemipearl is a registered
5 trademark in Japan, other countries, or both)

H2: microcrystalline wax (Nopco® 1245-M-SN manufactured by San Nopco Limited, solid content: 46.0 mass%; Nopco is a registered trademark in Japan, other countries, or both)

[0105] (4) Treatment method

10 Each surface-treatment solution listed in Table 2 was applied to the corresponding sample sheet after pretreatment listed in the "Steel Sheet" column in Table 3 with a bar coater, then directly placed in an oven without being washed with water, and dried at a peak metal temperature (PMT) in the "PMT" column to form a surface-coating layer having a coating weight (per
15 side) in Table 3 on one side of the sample sheet. The coating weight was determined by quantitatively determining the Zr of the compounded zirconium carbonate compound (C) by a fluorescent X-ray analyzer and converting it from the Zr coating weight to the layer coating weight.

[0106] (5) Evaluation test method

20 The results of evaluations of the following (5-1) to (5-12) on each obtained zinc or zinc alloy coated steel sheet with a surface-coating layer (hereinafter simply referred to as a "sample") are also listed in Table 3. Evaluation criteria C and D are not preferable due to insufficient performance.

[0107] (5-1) Heat discoloration resistance

25 Evaluation was made for each sample by: heating the sample in an IR image furnace to a sheet temperature of 500 °C in 30 seconds; retaining the sample at 500 °C for 5 minutes; taking the sample out of the IR image furnace and leaving the sample to allow it to be naturally cooled to the room temperature; and visually observing the surface appearance of the sample when it was
30 cooled. The evaluation criteria are as follows.

(Evaluation criteria)

A: no color change

B: very slightly yellowish

B-: slightly yellowish

- B=: very slightly brownish
- B≡: slightly brownish
- C: discolored to brown
- D: discolored to dark brown

5 **[0108] (5-2) Heat cracking resistance**

Evaluation was made for each sample by: heating the sample in an IR image furnace to a sheet temperature of 500 °C in 30 seconds; retaining the sample at 500 °C for 5 minutes; taking the sample out of the IR image furnace and leaving the sample to allow it to be naturally cooled to the room temperature;
10 and visually observing the surface appearance of the sample when it was cooled. Visually-unobservable cracks were observed with an optical microscope at 1,000 times magnification. The evaluation criteria are as follows.

(Evaluation criteria)

- 15 A: no cracks occurred
- B: few visually-unobservable cracks occurred
- B=: no visually-observable cracks, but visually-unobservable cracks occurred
- B=: very few cracks occurred
- 20 B≡: few cracks occurred
- C: narrow cracks occurred on the entire surface
- D: narrow and broad cracks spread across the entire surface

[0109] (5-3) Planar part anti-corrosion property

Each sample was subjected to a salt spray test (SST) according to
25 JIS-Z-2371-2000, in a planar state without being pressed. The planar part anti-corrosion property was evaluated based on the white rust area ratio after 240 hours. The evaluation criteria are as follows.

(Evaluation criteria)

- A: white rust area ratio being less than 5 %
- 30 B: white rust area ratio being 5 % or more and less than 10 %
- B=: white rust area ratio being 10 % or more and less than 25 %
- C: white rust area ratio being 25 % or more and less than 50 %
- D: white rust area ratio being 50 % or more and 100 % or less

[0110] (5-4) Corrosion resistance after alkali degreasing

Evaluation was made for each sample by: dissolving an alkali degreasing agent FC-E6406 (manufactured by Nihon Parkerizing Co., Ltd.) in pure water at concentration of 20 g/L and heating the solution to 60°C; immersing the sample in the alkali solution thus prepared for two minutes, then taking the sample out of the solution, washing with water, and drying the sample; and
5 subjecting the sample to a salt spray test (JIS-Z-2371-2000) to determine a white rust generation state 120 hours after the spray according to the white rust area ratio. The evaluation criteria are the same as in (5-3) above.

[0111] (5-5) Blackening resistance

10 Evaluation was made for each sample by: measuring the brightness (L-value) of the sample before the test; leaving the sample for 24 hours in a thermo-hygrostat controlled in an atmosphere at a temperature of 80 °C and a relative humidity of 98 %; then measuring the brightness (L-value) of the sample; and calculating the change in brightness (L-value): ΔL = (the L-value
15 after the test) – (the L-value before the test). The evaluation criteria are as follows. The L value was measured by SCI mode (specularly reflected light included) using SR 2000 manufactured by Nippon Denshoku Industries Co., Ltd.

(Evaluation criteria)

- 20 A: $-6 < \Delta L$, and with uniform appearance without unevenness
 B: $-10 < \Delta L \leq -6$, and with uniform appearance without unevenness
 B-: $-14 < \Delta L \leq -10$, and with uniform appearance without unevenness
 C: $-14 < \Delta L \leq -10$, and with fine black spots
 D: $\Delta L \leq -14$, or with uneven appearance

25 **[0112] (5-6) Stack blackening resistance**

Target surfaces of two samples having the same layer were overlapped with each other and tighten together at a torque of 20 kgf, and left standing for 4 weeks in a thermo-hygrostat controlled in an atmosphere at a temperature of 50 °C and a relative humidity of 98 %, and its surface appearance was visually
30 observed. The evaluation criteria are as follows.

(Evaluation criteria)

- A: no discoloration, and with uniform appearance without unevenness
B: very slightly discolored to black, and with uniform appearance without unevenness

B-: slightly discolored to black, and with uniform appearance without unevenness

B=: very slightly discolored to black, and with fine black spots

B≡: slightly discolored to black, and with fine black spots

5 C: discolored to black, and with fine black spots

D: discolored to black, and with uneven appearance

[0113] (5-7) Anti-water stain property

The anti-water stain property was evaluated for each sample by: dropping 100 μ L deionized water onto the sample surface in a planar state without being pressed; placing the sample in a hot-air oven at a furnace temperature of 100 °C for 10 minutes; and visually observing the water drop trace after removing the sample from the oven. The evaluation criteria are as follows.

(Evaluation criteria)

A: no water drop boundary being observed from any angle

15 B: water drop boundary being slightly observed depending on angle

B⁻: water drop boundary being slightly observed from any angle

C: water drop boundary being clearly observed from any angle

D: water drop boundary being clearly observed beyond dropping range

[0114] (5-8) Solvent resistance

20 Evaluation was made for each sample by: pressing a piece of gauze soaked with ethanol against the sample surface at a load of 4.90 N (500 gf); rubbing the sample surface with the gauze ten times reciprocally at the same load; and visually evaluating the scars resulted from the rubbing. The evaluation criteria are as follows.

25 (Evaluation criteria)

A: no scars

B: scars not observed when viewed from the top, but clearly observed when viewed diagonally

B-: scars slightly observed when viewed from the top

30 C: scars clearly observed when viewed from the top

D: layer peeled off

[0115] (5-9) Perspiration resistance

For each sample, 10 μ L of artificial perspiration conforming to JIS-B7001-1995 was dropped on the sample surface, and a silicone rubber

stopper was pressed against the dropping portion to prepare a site contaminated to a certain area with artificial perspiration. Each test piece thus prepared was allowed to stand for 4 hours in a thermo-hygrostat controlled in an atmosphere at a temperature of 40 °C and a relative humidity of 80 %, and the appearance change of the contaminated site was evaluated.

The evaluation criteria are as follows.

(Evaluation criteria)

A: no color change

B: very slight discoloration

10 B-: slight discoloration

C: slightly discolored to black

D: clearly discolored to black

[0116] (5-10) Coating adhesion property

Delicon® #700 (manufactured by Dai Nippon Toryo Co., Ltd.; Delicon is a registered trademark in Japan, other countries, or both), which is a melamine alkyd-based paint, was applied to each sample and baked at 130 °C for 30 minutes to form a coating layer having a thickness of 30 µm. Subsequently, it was immersed in boiling water for 2 hours, and immediately cuts were made to reach the steel substrate in a grid form (10 by 10, 1 mm interval). Further, an Erichsen extruder was used to apply extrusion processing of 5 mm such that the cuts were on the outer (front) side, and the peeling area of the coating layer was measured by applying and peeling an adhesive tape. The evaluation criteria are as follows. Note that the Erichsen extrusion conditions were in accordance with JIS Z-2247-2006, with a punch diameter of 20 mm, a die diameter of 27 mm, and a drawing width of 27 mm.

(Evaluation criteria)

A: no peeling

B: peeled area ratio being less than 3 %

B-: peeled area ratio being 3 % or more and less than 10%

30 C: peeled area ratio being 10 % or more and less than 30 %

D: peeled area ratio being 30 % or more

[0117] (5-11) Lubricity

Evaluation was made for each sample by: cutting a disc-shaped test piece with a diameter of 100 mm out of the sample; molding the test piece into a cup-like

- shape under a set of conditions including a punch diameter of 50 mm, a die diameter of 51.91 mm, and a blank holding force of 1t; visually analyzing the appearance of the drawing-processed surface of the test piece thus molded (i.e., the appearance of the external surface of the side of the cup); and
- 5 evaluating the severity of scars and the degree of blackening of the surface. The evaluation criteria are as follows.

(Evaluation criteria)

- A: substantially no change over the entire surface, with uniform appearance
- 10 B: minor scars and blackening, with clearly non-uniform appearance
- B–: local scars and blackening, with clearly non-uniform appearance
- C: severe scars and blackening mainly at corners
- D: molding failed due to cracking

[0118] (5-12) Storage stability

- 15 Each of the surface-treatment solutions listed in Table 2 was stored in a constant temperature bath at 40 °C for 30 days. Then, each surface-treatment solution was removed from the bath and its appearance was visually examined and evaluated. The evaluation criteria are as follows.

(Evaluation criteria)

- 20 A: no change
- B: very small amount of precipitation observed
- B–: small amount of precipitation observed
- C: small amount of precipitation observed and viscosity slightly increased
- D: large amount of precipitation observed or gelling occurred

[0119]

Table 2

Surface-treatment solution																		Category
No.	Component							Mass ratio							pH			
	(A)	(B)	(C)	(D)	(E)	(F)	(G)	(H)	A ₃ X ₅	B ₃ X ₅	C ₇ /X ₅	X ₃ D ₅	E _v /(X ₅ +D ₅)	F _w /(X ₅ +D ₅)		G ₃ /(X ₅ +G ₃)	H ₃ /(X ₅ +D ₅)	
1	A1	B1	C2	D4	E1	F1	-	-	0.22	0.178	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
2	A1	B1	C2	D4	E1	F1	-	-	0.26	0.138	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
3	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
4	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.0	Example
5	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.5	Example
6	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.5	Example
7	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	10.0	Example
8	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
9	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
10	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
11	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
12	A1	B1	C2	D4	E1	F1	-	-	0.36	0.086	0.56	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
13	A1	B1	C2	D4	E1	F1	-	-	0.39	0.086	0.52	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
14	A1	B1	C2	D4	E1	F1	G1	-	0.39	0.086	0.52	0.24	0.0033	0.0067	0.001	0.000	9.0	Example
15	A1	B1	C2	D4	E1	F1	G1	-	0.39	0.086	0.52	0.24	0.0033	0.0067	0.006	0.000	9.0	Example
16	A1	B1	C2	D4	E1	F1	G1	-	0.38	0.085	0.51	0.24	0.0033	0.0067	0.017	0.000	9.0	Example
17	A1	B1	C2	D4	E1	F1	-	-	0.31	0.023	0.67	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
18	A1	B1	C2	D4	E1	F1	-	-	0.32	0.054	0.63	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
19	A2	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.0	Example
20	A2	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.5	Example
21	A2	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.5	Example
22	A2	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	10.0	Example
23	A1	B2	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
24	A1	B1	C2	D4	E1	F1	-	-	0.28	0.212	0.51	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
25	A1	B1	C2	D4	E1	F1	-	-	0.25	0.260	0.49	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
26	A1	B1	C2	D4	E1	F1	-	-	0.33	0.188	0.48	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
27	A1	B1	C2	D4	E1	F1	-	-	0.34	0.173	0.49	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
28	A1	B1	C1	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
29	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.0	Example
30	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	8.5	Example
31	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
32	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.5	Example
33	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	10.0	Example
34	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
35	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
36	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
37	A1	B1	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
38	A1	B1	C2	D4	E1	F1	-	-	0.27	0.076	0.65	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
39	A1	B1	C2	D4	E1	F1	-	-	0.27	0.054	0.67	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
40	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.08	0.0033	0.0067	0.000	0.000	9.0	Example

Table 2 (cont'd)

Surface-treatment solution																	Category	
No.	Component							Mass ratio							pH			
	(A)	(B)	(C)	(D)	(E)	(F)	(G)	(H)	A ₅ /X ₅	B ₅ /X ₅	C ₂ /X ₅	X ₃ /D ₅	E _v /(X ₅ +D ₃)	F _N /(X ₅ +D ₃)		G ₅ /(X ₅ +G ₃)		H ₅ /(X ₅ +D ₃)
41	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.15	0.0033	0.0067	0.000	0.000	9.0	Example
42	A2	B2	C2	D3	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
43	A2	B2	C2	D5	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
44	A2	B2	C2	D6	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
45	A2	B2	C2	D7	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
46	A2	B2	C2	D8	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
47	A2	B2	C2	D9	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
48	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.30	0.0033	0.0067	0.000	0.000	9.0	Example
49	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.34	0.0033	0.0067	0.000	0.000	9.0	Example
50	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.086	0.60	0.34	0.0033	0.0067	0.001	0.000	9.0	Example
51	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.086	0.60	0.34	0.0033	0.0067	0.005	0.000	9.0	Example
52	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.085	0.59	0.35	0.0033	0.0067	0.015	0.000	9.0	Example
53	A1	B1	C2	D4	E1	F1	G1	-	0.30	0.084	0.59	0.35	0.0033	0.0066	0.028	0.000	9.0	Example
54	A1	B1	C2	D4	E1	F1	G1	-	0.30	0.083	0.58	0.35	0.0033	0.0065	0.043	0.000	9.0	Example
55	A1	B1	C2	D4	E1	F1	G1	-	0.30	0.082	0.57	0.35	0.0032	0.0064	0.049	0.000	9.0	Example
56	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0013	0.0067	0.000	0.000	9.0	Example
57	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0020	0.0067	0.000	0.000	9.0	Example
58	A2	B2	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
59	A1	B1	C2	D4	E2	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
60	A1	B1	C2	D4	E1	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
61	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0089	0.0067	0.000	0.000	9.0	Example
62	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0122	0.0067	0.000	0.000	9.0	Example
63	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.086	0.60	0.24	0.0122	0.0067	0.003	0.000	9.0	Example
64	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.086	0.60	0.24	0.0122	0.0067	0.006	0.000	9.0	Example
65	A1	B1	C2	D4	E1	F1	G1	-	0.31	0.085	0.59	0.24	0.0122	0.0067	0.017	0.000	9.0	Example
66	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0013	0.000	0.000	9.0	Example
67	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0033	0.000	0.000	9.0	Example
68	A2	B2	C2	D4	E2	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
69	A2	B2	C2	D4	E2	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
70	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0100	0.000	0.000	9.0	Example
71	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0134	0.000	0.000	9.0	Example
72	A1	B1	C2	D4	E1	F1	G1	-	0.29	0.082	0.57	0.25	0.0033	0.0066	0.054	0.000	9.0	Example
73	A1	B1	C2	D4	E1	F1	G1	-	0.28	0.077	0.54	0.27	0.0033	0.0065	0.103	0.000	9.0	Example
74	A2	B2	C2	D4	E2	F1	G1	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example
75	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	8.0	Example
76	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	8.5	Example
77	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example
78	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.5	Example
79	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	10.0	Example
80	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example
81	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example

Table 2 (cont'd)

Surface-treatment solution																			Category
No.	Component								Mass ratio										
	(A)	(B)	(C)	(D)	(E)	(F)	(G)	(H)	A ₅ /X ₅	B ₅ /X ₅	C ₂ /X ₅	X ₃ /D ₅	E ₄ /(X ₅ +D ₅)	F ₄ /(X ₅ +D ₅)	G ₅ /(X ₅ +G ₅)	H ₅ /(X ₅ +D ₅)	pH		
82	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example	
83	A1	B1	C2	D4	E1	F1	G2	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	9.0	Example	
84	A1	B1	C2	D4	E1	F1	G1	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	8.0	Example	
85	A1	B1	C2	D4	E1	F1	G1	-	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.000	10.0	Example	
86	A1	B1	C2	D4	E1	F1	G1	-	0.25	0.069	0.49	0.30	0.0032	0.0064	0.194	0.000	9.0	Example	
87	A2	B2	C2	D4	E2	F1	G2	-	0.25	0.069	0.49	0.30	0.0032	0.0064	0.194	0.000	9.0	Example	
88	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.011	9.0	Example	
89	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
90	A1	B1	C2	D4	E1	F1	-	H2	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
91	A2	B2	C2	D4	E2	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	8.0	Example	
92	A2	B2	C2	D4	E2	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	8.5	Example	
93	A2	B2	C2	D4	E2	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
94	A2	B2	C2	D4	E2	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.5	Example	
95	A2	B2	C2	D4	E2	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	10.0	Example	
96	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	8.0	Example	
97	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	8.5	Example	
98	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
99	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.5	Example	
100	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	10.0	Example	
101	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
102	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
103	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
104	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.033	9.0	Example	
105	A1	B1	C2	D4	E1	F1	-	H1	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.042	9.0	Example	
106	A2	B2	C2	D4	E2	F1	-	H2	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.067	9.0	Example	
107	A1	B1	C2	D4	E1	F1	G1	H1	0.29	0.082	0.57	0.25	0.0033	0.0066	0.054	0.011	9.0	Example	
108	A1	B1	C2	D4	E1	F1	G1	H1	0.28	0.077	0.54	0.27	0.0033	0.0065	0.103	0.033	9.0	Example	
109	A1	B1	C2	D4	E1	F1	G2	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
110	A2	B2	C2	D4	E2	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
111	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	8.0	Example	
112	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	8.5	Example	
113	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
114	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.5	Example	
115	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	10.0	Example	
116	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
117	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
118	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
119	A1	B1	C2	D4	E1	F1	G1	H1	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
120	A1	B1	C2	D4	E1	F1	G2	H2	0.26	0.072	0.50	0.29	0.0032	0.0064	0.167	0.032	9.0	Example	
121	A2	B2	C2	D4	E2	F1	G1	H2	0.25	0.069	0.49	0.30	0.0032	0.0064	0.194	0.064	9.0	Example	

Table 2 (cont'd)

No.	Surface-treatment solution										Category							
	Component					Mass ratio												
	(A)	(B)	(C)	(D)	(E)	(F)	(G)	(H)	A ₀ /X ₀	B ₀ /X ₀		C ₂ /X ₀	X ₀ /D ₀	E _v /(X ₀ +D ₀)	F _M /(X ₀ +D ₀)	G ₀ /(X ₀ +G ₀)	H ₀ /(X ₀ +D ₀)	pH
122	A2	B2	C2	D4	E2	F1	G1	H2	0.25	0.069	0.49	0.30	0.0032	0.0064	0.194	0.096	9.0	Example
123	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
124	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
125	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
126	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
127	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
128	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
129	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
130	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
131	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
132	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
133	A1	B2	C2	D4	E1	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
134	A1	B2	C2	D4	E1	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
135	A1	B2	C2	D4	E1	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
136	A1	B2	C2	D4	E1	F2	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Example
137	-	B1	C2	D4	E1	F1	-	-	0.00	0.300	0.70	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
138	A1	-	C2	D4	E1	F1	-	-	0.34	0.000	0.66	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
139	A1	B1	-	D4	E1	F1	-	-	0.60	0.400	0.00	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
140	A1	B1	C2	-	E1	F1	-	-	0.31	0.086	0.60	-	0.0029	0.0069	0.000	0.000	9.0	Comparative Example
141	A1	B1	C2	D4	-	F1	-	-	0.31	0.086	0.60	0.24	0.0000	0.0067	0.000	0.000	9.0	Comparative Example
142	A1	B1	C2	D4	E1	-	-	-	0.31	0.086	0.60	0.24	0.0033	0.0000	0.000	0.000	9.0	Comparative Example
143	A1	B1	C2	D4	E1	F1	-	-	0.18	0.213	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
144	A1	B1	C2	D4	E1	F1	-	-	0.42	0.084	0.50	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
145	A1	B1	C2	D4	E1	F1	-	-	0.34	0.006	0.65	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
146	A1	B1	C2	D4	E1	F1	-	-	0.24	0.308	0.45	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
147	A1	B1	C2	D4	E1	F1	-	-	0.35	0.226	0.43	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
148	A1	B1	C2	D4	E1	F1	-	-	0.24	0.037	0.72	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
149	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.04	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
150	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.36	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
151	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0008	0.0067	0.000	0.000	9.0	Comparative Example
152	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0156	0.0067	0.000	0.000	9.0	Comparative Example
153	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0200	0.0067	0.000	0.000	9.0	Comparative Example
154	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0008	0.000	0.000	9.0	Comparative Example
155	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0156	0.000	0.000	9.0	Comparative Example
156	A1	B1	C2	D4	E1	F1	G1	-	0.24	0.066	0.46	0.31	0.0032	0.0063	0.237	0.000	9.0	Example
157	A1	B1	C2	D4	E1	F1	G1	H1	0.24	0.066	0.46	0.31	0.0032	0.0063	0.237	0.032	9.0	Example
158	A1	B1	C2	D1	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
159	A1	B1	C2	D2	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
160	A1	B1	C2	D10	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	9.0	Comparative Example
161	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	7.5	Comparative Example
162	A1	B1	C2	D4	E1	F1	-	-	0.31	0.086	0.60	0.24	0.0033	0.0067	0.000	0.000	12.0	Comparative Example

[0120]

Table 3

No.	Process condition			Performance evaluation											Category	
	Steel sheet	Coating weight (mg/m ²)	PMT (°C)	Heat discoloration resistance	Heat cracking resistance	Planar part anti-corrosion property	Corrosion resistance after degreasing	Blackening resistance	Stack blackening resistance	Anti-water stain property	Solvent resistance	Perspersion resistance	Coating adhesion property	Lubricity		Storage stability
1	III	900	110	B-	B	B-	B-	A	A	A	A	A	A	B	A	Example
2	III	900	110	B-	B-	B	B	A	A	A	A	A	A	B	A	Example
3	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
4	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
5	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
6	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
7	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
8	I	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
9	II	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
10	IV	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
11	V	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
12	III	900	110	B-	B=	A	A	A	A	A	A	A	A	B	A	Example
13	III	900	110	B-	B=	A	A	A	A	A	A	A	A	B	A	Example
14	III	900	110	B	B=	A	A	A	A	A	A	A	A	B	A	Example
15	III	900	110	B	B-	A	A	A	A	A	A	A	A	B	A	Example
16	III	900	110	B	B	A	A	A	A	A	A	A	A	B	A	Example
17	III	900	110	B-	B=	A	A	A	A	A	A	A	B-	B	A	Example
18	III	900	110	B-	B=	A	A	A	A	A	A	A	A	B	A	Example
19	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
20	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
21	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
22	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
23	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
24	III	900	110	B-	B	B	B	A	A	A	A	A	A	B	A	Example
25	III	900	110	B-	B	B-	B-	A	A	A	A	A	A	B	A	Example
26	III	900	110	B-	B	B	B	A	A	A	A	A	A	B	A	Example
27	III	900	110	B-	B	B	B	A	A	A	A	A	A	B	A	Example
28	III	900	110	B-	B-	B	B	A	A	A	B	A	A	B	A	Example
29	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
30	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
31	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
32	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
33	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	B	Example
34	I	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
35	II	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
36	IV	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
37	V	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
38	III	900	110	B-	B=	B	B	A	A	A	A	A	A	B	A	Example
39	III	900	110	B-	B=	B-	B-	A	A	A	A	A	B-	B	A	Example
40	III	900	110	B	B	B-	B-	A	A	A	B-	A	A	B	A	Example

Table 3 (cont'd)

No.	Process condition			Performance evaluation											Category	
	Steel sheet	Coating weight (mg/m ²)	PMT (°C)	Heat discoloration resistance	Heat cracking resistance	Planar part anti-corrosion property	Corrosion resistance after degreasing	Blackening resistance	Stack blackening resistance	Anti-water stain property	Solvent resistance	Perspiration resistance	Coating adhesion property	Lubricity		Storage stability
41	III	900	110	B	B	B	B	A	A	A	B	A	A	B	A	Example
42	III	900	110	B-	B-	A	A	A	A	A	B-	A	A	B	A	Example
43	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
44	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
45	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
46	III	900	110	B-	B-	A	A	A	A	A	A	A	B	B	A	Example
47	III	900	110	B-	B-	A	A	A	A	A	A	A	B-	B	A	Example
48	III	900	110	B=	B=	A	A	B	B	B	A	B	B	B	A	Example
49	III	900	110	B=	B=	A	A	B-	B-	B-	A	B-	B-	B	A	Example
50	III	900	110	B=	B=	A	A	B-	B-	B-	A	B-	B-	B	A	Example
51	III	900	110	B-	B-	A	A	B-	B-	B-	A	B-	B-	B	A	Example
52	III	900	110	B	B	A	A	B-	B-	B-	A	B-	B-	B	A	Example
53	III	900	110	B	B	A	A	B-	B=	B=	A	B-	B-	B	A	Example
54	III	900	110	B	B	A	A	B-	B=	B=	A	B-	B-	B	A	Example
55	III	900	110	B	B	A	A	B-	B-	B-	A	B-	B-	B	A	Example
56	III	900	110	B	B	B-	A	A	A	A	A	A	A	B	A	Example
57	III	900	110	B	B	B	A	A	A	A	A	A	A	B	A	Example
58	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
59	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
60	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
61	III	900	110	B=	B=	A	A	B	B	B	A	B	B	B	A	Example
62	III	900	110	B=	B=	A	A	B-	B-	B-	A	B-	B-	B	A	Example
63	III	900	110	B=	B=	A	A	B-	B-	B-	A	B-	B-	B	A	Example
64	III	900	110	B-	B-	A	A	B-	B-	B-	A	B-	B-	B	A	Example
65	III	900	110	B	B	A	A	B-	B-	B-	A	B-	B-	B	A	Example
66	III	900	110	B-	B-	A	A	B-	B-	A	A	A	A	B	A	Example
67	III	900	110	B-	B-	A	A	B	B	A	A	A	A	B	A	Example
68	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
69	III	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
70	III	900	110	B-	B-	B	B	A	A	A	A	A	A	B	A	Example
71	III	900	110	B-	B-	B-	B-	A	A	A	A	A	A	B	A	Example
72	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
73	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
74	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
75	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	B	Example
76	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
77	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
78	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
79	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	B	Example
80	I	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
81	II	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example

Table 3 (cont'd)

No.	Process condition			Performance evaluation												Category
	Steel sheet	Coating weight (mg/m ²)	PMT (°C)	Heat discoloration resistance	Heat cracking resistance	Planar part anti-corrosion property	Corrosion resistance after degreasing	Blackening resistance	Stack blackening resistance	Anti-water stain property	Solvent resistance	Perspiration resistance	Coating adhesion property	Lubricity	Storage stability	
82	IV	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
83	V	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
84	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	B	Example
85	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	B	Example
86	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
87	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
88	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
89	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
90	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
91	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	B	Example
92	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
93	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
94	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
95	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	B	Example
96	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	B	Example
97	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
98	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
99	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
100	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	B	Example
101	I	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
102	II	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
103	IV	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
104	V	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
105	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
106	III	900	110	B-	B-	A	A	A	A	A	A	A	A	A	A	Example
107	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
108	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
109	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
110	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
111	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	B	Example
112	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
113	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
114	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
115	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	B	Example
116	I	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
117	II	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
118	IV	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
119	V	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
120	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
121	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example

Table 3 (cont'd)

No.	Process condition			Performance evaluation												Category
	Steel sheet	Coating weight (mg/m ²)	PMT (°C)	Heat discoloration resistance	Heat cracking resistance	Planar part anti-corrosion property	Corrosion resistance after degreasing	Blackening resistance	Stack blackening resistance	Anti-water stain property	Solvent resistance	Perspiration resistance	Coating adhesion property	Lubricity	Storage stability	
122	III	900	110	B	B	B	B	A	B=	A	A	A	B	A	A	Example
123	III	50	110	B-	B-	B-	B-	B-	B-	B-	B-	B-	B-	B	A	Example
124	III	300	110	B-	B-	B-	B	B	B	B	B	B	B	B	A	Example
125	III	600	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
126	III	1200	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
127	III	1600	110	B=	B=	A	A	A	A	A	A	A	A	B	A	Example
128	III	2000	110	B=	B=	A	A	A	A	A	A	A	A	A	A	Example
129	III	900	60	B-	B-	B-	B-	B-	B-	B-	B-	B-	A	B	A	Example
130	III	900	80	B-	B-	B	B	B	B	B	B	B	A	B	A	Example
131	III	900	180	B-	B-	B	B	B	B	B	B	B	B	B	A	Example
132	III	900	200	B-	B-	B-	B-	B-	B-	B-	B-	B-	B-	B	A	Example
133	I	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
134	II	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
135	IV	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
136	V	900	110	B-	B-	A	A	A	A	A	A	A	A	B	A	Example
137	III	900	110	B-	B	D	D	A	A	A	A	A	A	B	A	Comparative Example
138	III	900	110	B-	D	A	A	A	A	A	A	A	A	B	A	Comparative Example
139	III	900	110	C	C	D	D	B-	D	D	A	D	A	B	A	Comparative Example
140	III	900	110	D	D	A	A	C	D	C	A	C	C	B-	A	Comparative Example
141	III	900	110	B	B	D	D	A	A	A	A	A	A	B	A	Comparative Example
142	III	900	110	B-	B-	A	A	D	D	A	A	A	A	B	A	Comparative Example
143	III	900	110	B-	B-	C	C	A	A	A	A	A	A	B	A	Comparative Example
144	III	900	110	B-	C	A	A	A	A	A	A	A	A	B	A	Comparative Example
145	III	900	110	B-	C	A	A	A	A	A	A	A	A	B	A	Comparative Example
146	III	900	110	B-	B-	D	D	A	B-	B-	A	B-	A	B	A	Comparative Example
147	III	900	110	B=	B=	C	C	A	C	B	A	B	A	B	A	Comparative Example
148	III	900	110	B-	B-	A	A	A	A	A	A	A	C	B	B-	Comparative Example
149	III	900	110	B-	B-	C	C	A	A	A	C	A	A	B	A	Comparative Example
150	III	900	110	C	C	A	A	C	C	C	A	C	B	B-	A	Comparative Example
151	III	900	110	B-	B-	C	C	A	A	A	A	A	A	B	A	Comparative Example
152	III	900	110	C	C	A	A	C	C	C	A	C	C	B	B	Comparative Example
153	III	900	110	D	D	A	A	D	D	D	A	D	D	B	B-	Comparative Example
154	III	900	110	B-	B-	A	A	C	C	A	A	A	A	B	A	Comparative Example
155	III	900	110	B-	B-	C	C	A	A	A	A	A	A	B	B-	Comparative Example
156	III	900	110	B	B	A	A	A	B=	A	A	A	A	B	A	Example
157	III	900	110	B	B	A	A	A	B=	A	A	A	A	A	A	Example
158	III	900	110	B-	B-	A	A	A	A	A	D	A	A	B	A	Comparative Example
159	III	900	110	B-	B-	A	A	A	A	A	C	A	A	B	A	Comparative Example
160	III	900	110	B-	B-	A	A	A	A	A	A	A	C	B	A	Comparative Example
161	III	900	110			Test canceled because preparation of a surface-treatment solution failed.										Comparative Example
162	III	900	110	B-	B-	D	D	A	A	A	A	A	A	B	C	Comparative Example

[0121] As listed in Tables 2 and 3, our examples are excellent in all of heat discoloration resistance, heat cracking resistance, planar part anti-corrosion property, corrosion resistance after alkali degreasing, blackening resistance, anti-water stain property, solvent resistance, perspiration resistance, coating
5 adhesion property, and storage stability, and even in stack blackening resistance evaluated in a more severe environment. In contrast, the comparative examples outside the appropriate ranges required by the present disclosure in terms of any of the requirements disclosed herein were insufficient in any of the above-mentioned properties. In addition, in
10 Comparative Example No. 161, due to a low pH, a surface-treatment solution could not be prepared and sample sheet evaluation could not be made.

[0122] [Example 2]

The same operations were performed as described above in the (1) Sample sheet, (2) Pre-treatment (cleaning), and (3) Surface-treatment solution
15 sections in Example 1.

[0123] (4) Treatment method

On each sample sheet after the pre-treatment listed in the "Steel sheet" column in Table 4, a surface-treatment solution No. 93 in Table 2 was applied with a bar coater, and the sample sheet was then placed in an oven without being
20 washed with water to form a surface-coating layer having a coating weight (per side) of 900 mg/m^2 on one surface thereof. At this time, the temperature of the sample sheet and the temperature of the surface-treatment solution in applying the surface-treatment solution are represented by T_S and T_L , respectively, and $T_S - T_L$ is represented by ΔT , as seen in Table 4. Regarding
25 the drying of the surface-treatment solution, the preliminary drying time t (sec) before the sample sheet is placed in the oven and the peak metal temperature PMT in the subsequent heat drying in the oven are also listed in Table 4. The coating weight was determined by quantitatively determining the Zr of the compounded zirconium carbonate compound (C) by a fluorescent
30 X-ray analyzer and converting it from the Zr coating weight to the layer coating weight.

[0124] (5) Evaluation test method

In addition to the evaluations in (5-1) to (5-12) in Example 1, each obtained zinc or zinc alloy coated steel sheet with a surface-coating layer (hereinafter

referred to simply as a "sample") was subjected to evaluations of (5-13) and (5-14), and the results are listed in Table 4. Evaluation criteria C and D are not preferable due to insufficient performance.

[0125] (5-13) High planar part anti-corrosion property

- 5 Each sample was subjected to a salt spray test (SST) according to JIS-Z-2371-2000, in a planar state without being pressed. The planar part anti-corrosion property was evaluated based on the white rust area ratio after 480 hours. The evaluation criteria are as follows.

(Evaluation criteria)

- 10 A: white rust area ratio being less than 5 %
B: white rust area ratio being 5 % or more and less than 10 %
B-: white rust area ratio being 10 % or more and less than 25 %
C: white rust area ratio being 25 % or more and less than 50 %
D: white rust area ratio being 50 % or more and 100 % or less

15 **[0126]** (5-14) Layer phase analysis

- SEM observation was carried out to examine the surface of the surface-coating layer of each sample. Using an Everhart-Thornley type detector with an accelerating voltage of 1 kV, secondary electron images were observed. At 20,000 times observation magnification (about $6\ \mu\text{m} \times 4\ \mu\text{m}$ as an observation area), each image was captured as a digital image of 1024×700 pixels in gray scale of 256 gradations. In each observed image, a phase made of a Zr-containing inorganic material appears bright and a phase made of a Zr-free resin component dark. Accordingly, as the proportion of a Zr-containing phase, the area ratio of a region observed to be bright was
20 determined and considered as the volume fraction according to the following
25 procedure.

- (A): To remove noise, apply smoothing processing to the acquired SEM image with a Gaussian filter with an operator size of 1 pixel.
(B): Binarize the image of (A) by the maximum entropy method.
30 (C): Determine the ratio of the bright area of the binarized image.

Table 4

[illegible]

[0128] As can be seen from Table 4, some of our examples were also excellent in high planar part anti-corrosion property, where the volume fraction of a Zr-containing phase was adjusted in the range of 5 % to 40 % by controlling the temperature condition at the time of application and the preliminary drying condition before heating and drying within the predetermined ranges.

[0129] For instance, FIG. 1 presents an SEM image of a surface of a surface-coating layer. A secondary electron image was observed using an Everhart-Thornley secondary electron detector with an accelerating voltage of 1 kV. It can be seen that Zr-containing regions of bright contrast are dispersed in Zr-free regions of dark contrast. For this field of view, binarization was performed by the maximum entropy method, and the area ratio of the Zr-containing phase (bright regions) was found to be 19 %.

INDUSTRIAL APPLICABILITY

[0130] The zinc or zinc alloy coated steel sheet with a surface-coating layer produced by using the surface-treatment solution according to the disclosure is suitable for various applications such as for use as a member to be subjected to arc welding, but also for steel sheets for household electrical appliances, steel sheets for building materials, and steel sheets for automobiles.

CLAIMS

1. A surface-treatment solution for a zinc or zinc alloy coated steel sheet containing a glycidyl group-containing silane coupling agent (A), a
5 tetraalkoxysilane (B), a zirconium carbonate compound (C), and an anionic polyurethane resin (D) having a glass transition temperature (T_g) of 80 °C to 130 °C, a vanadium compound (E), a molybdic acid compound (F), and water, the surface-treatment solution having a pH of 8.0 to 10.0, and the amount of each component satisfying:

10 (1) a mass ratio (X_S/D_S) of a total mass (X_S) of a solid content mass (A_S) of the glycidyl group-containing silane coupling agent (A), a solid content mass (B_S) of the tetraalkoxysilane (B), and a ZrO_2 equivalent mass (C_Z) in the zirconium carbonate compound (C) to a solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.05 to 0.35;

15 (2) a mass ratio (A_S/X_S) of the solid content mass (A_S) of the glycidyl group-containing silane coupling agent (A) to the total mass (X_S) is from 0.20 to 0.40;

(3) a mass ratio (B_S/X_S) of the solid content mass (B_S) of the tetraalkoxysilane (B) to the total mass (X_S) is from 0.010 to 0.30;

20 (4) a mass ratio (C_Z/X_S) of the ZrO_2 equivalent mass (C_Z) in the zirconium carbonate compound (C) to the total mass (X_S) is from 0.45 to 0.70;

(5) a mass ratio ($E_V/(X_S + D_S)$) of a V equivalent mass (E_V) in the vanadium compound (E) to a total mass ($X_S + D_S$) of the total mass (X_S) and the solid content mass (D_S) of the anionic polyurethane resin (D) is from
25 0.0010 to 0.015; and

(6) a mass ratio ($F_M/(X_S + D_S)$) of a Mo equivalent mass (F_M) in the molybdic acid compound (F) to the total mass ($X_S + D_S$) of the total mass (X_S) and the solid content mass (D_S) of the anionic polyurethane resin (D) is from 0.0010 to 0.015.

30

2. The surface-treatment solution for a zinc or zinc alloy coated steel sheet according to claim 1, further containing a sodium silicate (G), wherein the amount thereof satisfies:

(7) a mass ratio ($G_S/(X_S + G_S)$) of a solid content mass (G_S) of the

sodium silicate (G) to the total mass ($X_S + G_S$) of the total mass (X_S) and the solid content mass (G_S) of the sodium silicate (G) is less than 0.05, inclusive of 0.00.

5 3. The surface-treatment solution for a zinc or zinc alloy coated steel sheet according to claim 1 or 2, further containing a wax (H), wherein the amount thereof satisfies:

 (8) a mass ratio ($H_S/(X_S + D_S)$) of a solid content mass (H_S) of the wax (H) to the total mass ($X_S + D_S$) of the total mass (X_S) and the solid
10 content mass (D_S) of the anionic polyurethane resin (D) is from 0.002 to 0.10.

 4. A method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer, comprising:

 a first step of applying the surface-treatment solution as recited in any
15 one of claims 1 to 3 to a surface of a zinc or zinc alloy coated steel sheet; and

 a second step of subsequently drying the applied surface-treatment solution to form a surface-coating layer having a coating weight of 50 mg/m² to 2,000 mg/m².

20 5. The method of producing a zinc or zinc alloy coated steel sheet with a surface-coating layer according to claim 4, wherein T_S is 15 °C to 55 °C, T_L is 10 °C to 40 °C, and ΔT is 5 °C to 40 °C, where T_S and T_L represent a temperature of the zinc or zinc alloy coated steel sheet and a temperature of the surface-treatment solution in the first step, respectively,
25 and ΔT represents $T_S - T_L$, and

 the second step includes a preliminary drying step of drying the applied surface-treatment solution in the atmosphere for a time t seconds, and a heating and drying step of subsequently heating and drying the applied surface-treatment solution in a drying furnace, wherein $\Delta T/t$ is 1 °C/s to
30 60 °C/s.

 6. A zinc or zinc alloy coated steel sheet with a surface-coating layer, comprising:

 a zinc or zinc alloy coated steel sheet; and

a surface-coating layer having a coating weight of 50 mg/m² to 2,000 mg/m² obtained by applying the surface-treatment solution as recited in any one of claims 1 to 3 to a surface of the zinc or zinc alloy coated steel sheet, and drying the applied surface-treatment solution.

5

7. The zinc or zinc alloy coated steel sheet with a surface-coating layer according to claim 6, wherein the surface-coating layer is formed by a Zr-containing phase and a Zr-free phase, and the Zr-containing phase has a volume fraction of 5 % to 40 %.

10

8. The zinc or zinc alloy coated steel sheet with a surface-coating layer according to claim 6 or 7, wherein the zinc or zinc alloy coated steel sheet is a hot-dip Zn-Al alloy coated steel sheet comprising a hot-dip Zn-Al alloy coated layer formed on at least one surface of a base steel sheet, the
15 hot-dip Zn-Al alloy coated layer containing, by mass%, Al: 3.0 % to 6.0 %, Mg: 0.2 % to 1.0 %, and Ni: 0.01 % to 0.10 %, with the balance being Zn and inevitable impurities.