

## GEAR OIL HAVING LOW COPPER CORROSION PROPERTIES

The present invention relates to a gear oil additive composition and a gear oil composition containing the same. In particular, the present invention relates to a gear oil additive composition used to reduce corrosion of yellow metal components which are present in axles and transmissions. Further, the present invention relates to a method of reducing yellow metal corrosion in axles and transmissions.

### BACKGROUND OF THE INVENTION

In gear oil applications, sulfurized olefins are typically used to protect gears from scoring. However, these sulfur compounds are extremely corrosive towards yellow metals, such as copper and copper alloys. The sulfur components in combination with phosphorus components produce a composition that degrades the copper. Gear oil specifications have minimum requirements for copper corrosion. For example, the API GL-5 category requires a maximum rating of 3 in the ASTM D-130 Test. However, this test does not provide a quantitative measurement of copper corrosion. It is a visual rating based on the discoloration of a copper strip. To obtain a quantitative measurement, we use the copper catalyst weight loss measurement from the ASTM D-5704 Test. The copper catalyst weight loss also reveals the copper corrosiveness of the oxidized oil.

Sulfurized isobutylenes are widely used in formulating gear lubricants intended for API GL-5 service. However, this type of sulfur-containing extreme pressure component causes large copper catalyst weight loss in the ASTM D-5704 test.

European Patent Application No. 678 569 B1 discloses a lubricating composition comprising a major amount of an oil of lubricating viscosity with an iodine number less than 4, (A) one or more ashless antioxidants selected from

amine antioxidants, dithiophosphoric esters, phenol antioxidants, dithiocarbamates and aromatic phosphates, (B) from 0.01 to 3% by weight of at least one boron-containing dispersant or detergent, and optionally, (C) at least one additive selected from (i) a sulfur containing antiwear or extreme  
5 pressure agent, (ii) a phosphorus or boron antiwear or extreme pressure agent, and (iii) mixtures thereof, provided that (C) is different from (A), and wherein the total amount of antioxidant is from 2 to 10% by weight. The additives are useful for controlling oxidation of lubricants. Further, these lubricants have reduced viscosity increase caused by oxidation, while maintaining favorable  
10 carbon/varnish ratings.

U.S. Patent No. 6,362,136 discloses compositions containing a sulfur-containing antiwear/extreme pressure agent, basic nitrogen compound or a mixture thereof together with a hydrocarbyl mercaptan. The composition may  
15 additionally contain a phosphorus or boron antiwear or extreme pressure agent, a dispersant or an overbased metal salt. This patent also relates to lubricants, functional fluids, and concentrates containing the same. Seals, e.g. nitrile, polyacrylate, and fluoroelastomer seals, in contact with these compositions have reduced deterioration. This patent teaches that with the use  
20 of these compositions, lubricants, and functional fluids, the seals useful life is extended.

U.S. Patent No. 6,262,000 discloses that the antiwear performance of power transmitting fluids, particularly continuously variable transmission fluids, is  
25 improved by incorporating an additive combination of amine phosphates, organic polysulfides, zinc salts of phosphorothioic acid esters and optionally a friction modifier.

U.S. Patent No. 5,254,272 discloses lubricant compositions especially useful  
30 as hydraulic fluids contain a metal-free anti-wear or load-carrying additive containing sulfur and/or phosphorus and an amino succinate ester as corrosion inhibitor. This patent teaches that such compositions are free from heavy metal

and have improved environmental acceptability where heavy metals are to be avoided, e.g. in agriculture.

5 U.S. Patent No. 5,342,531 discloses a lubricant composition comprising a major proportion of polyalkylene glycol of lubricating viscosity and a minor proportion dissolved therein of (a) at least one sulfur-containing antiwear or extreme pressure agent, (b) at least one amine salt of at least one partially esterified monothiophosphoric acid, and (c) at least one amine salt of at least one partially esterified phosphoric acid. This patent teaches that such  
10 compositions have improved resistance to wear, oxidative degradation and metallic corrosion.

U.S. Patent No. 5,942,470 discloses gear oils and gear oil additive concentrates of enhanced positraction performance comprising: (i) at least one  
15 oil-soluble sulfur-containing extreme pressure or antiwear agent; (ii) at least one oil-soluble amine salt of a partial ester of an acid of phosphorus; and (iii) at least one oil-soluble succinimide compound. These compositions preferably contain one, more preferably two, and most preferably all three of the following additional components: (iv) at least one amine salt of a carboxylic acid; (v) at  
20 least one nitrogen-containing ashless dispersant; and (vi) at least one trihydrocarbyl ester of a pentavalent acid of phosphorus.

Japanese Patent No. JP 2000-328084 discloses a gear oil composition comprising a specified dialkyltrisulfide, a specified dithiophosphoric ester, and  
25 one or more of acidic phosphoric and phosphorus esters and alkylamine salts of the esters in a base oil of a kinematic viscosity at 100°C. The composition has high oxidation stability and corrosion resistance to copper at temperatures of 150°C or higher.

30 U.S. Patent No. 4,609,480 discloses a lubricant composition effective in extending the fatigue life and increasing the corrosion resistance of the

machine parts lubricated therewith. The lubricant composition comprises two types of essential additives, namely (a) a dithiocarbamic acid ester and/or an alkyl thiocarbamoyl compound and (b) a 1,3,4-thiadiazole compound admixed with the lubricant base material each in a limited amount. In addition to the above mentioned advantages, the resistance against scoring can further be increased by the admixture of the lubricant composition with a third additive (c) such as sulfurized olefins, sulfurized oils, sulfurized oxymolybdenum dithiocarbamates, sulfurized oxymolybdenum organophosphordithioates, phosphoric acid esters and phosphorus esters.

### SUMMARY OF THE INVENTION

Disclosed herein is a gear oil additive composition having low corrosion of yellow metal components of axles and transmissions, particularly copper and copper alloys.

In a first aspect, there is provided a gear oil additive composition comprises:

- a) an organic polysulfide containing greater than 30 wt% of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 12 carbon atoms and  $x$  is 4 or greater;


- b) a thiadiazole; and
- c) at least one ashless phosphorus-containing wear inhibitor compound.

In a second aspect, there is provided a gear oil composition comprising:

- a) a major amount of a base oil of lubricating viscosity; and

b) a minor amount of a gear oil additive composition comprising:

- (i) an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of

4 to 12 carbon atoms and  $x$  is 4 or greater;

- (ii) a thiadiazole; and


- (iii) at least one ashless phosphorus-containing wear inhibitor compound.

In a third aspect, there is provided a method of reducing yellow metal corrosion in axles and transmissions, said method comprising contacting the metal components of the axle and transmission with a gear oil composition comprising:

a) a major amount of a base oil of lubricating viscosity; and

b) a minor amount of a gear oil additive composition comprising:

- (i) an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 12 carbon atoms and  $x$  is about 4 or greater;

- (ii) a thiadiazole; and

- (iii) at least one ashless phosphorus-containing wear inhibitor compound.

Preferably, the gear oil additive composition will contain about 40 to 75 wt % of the organic polysulfide, about 0.5 to 15 wt % of the thiadiazole and about 5.0 to 40 wt % of the ashless phosphorus-containing wear inhibitor compound.

Disclosed herein is a gear oil composition comprising a major amount of a base oil of lubricating viscosity and a minor amount of the disclosed gear oil additive composition.

Disclosed herein is a method of reducing the yellow metal corrosion of axles and transmission by contacting the metal components of the axle and transmission with the gear oil composition.

Among other factors, the disclosure is based on the surprising discovery that a gear oil additive composition and gear oil composition having low odor and low chlorine significantly reduces corrosion of yellow metal components of axles and transmissions, particularly copper and copper alloys. The disclosed compositions have an advantageously lower odor than comparable compositions currently available in the marketplace. Moreover, in view of the increasingly stringent requirements regarding the chlorine content of additives for petroleum products, the low levels of chlorine associated with the disclosed composition is advantageous since any chlorine discharged into the environment accidentally or as waste is environmentally undesirable. Preferably, the disclosed additive compositions will not contain compounds containing zinc. The disclosed compositions can advantageously have a lower sulfur treat rate (organic polysulfide) than comparable compositions utilizing sulfurized isobutylene, while providing comparable or improved gear scoring resistance and improved performance in reducing yellow metal corrosion.


#### **DETAILED DESCRIPTION OF THE INVENTION**

The gear oil additive composition and gear oil composition will now be described more thoroughly below.

### Gear Oil Additive Composition

The present invention provides a gear oil additive composition comprising:

- 5           a)     an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of about 4 to 12 carbon atoms and  $x$  is about 4 or greater;

- b)     a thiadiazole; and
- 10          c)     at least one ashless phosphorus-containing wear inhibitor compound.

Preferably, the gear oil additive composition will contain the organic polysulfide in the range from about 45 to 70 wt % and, more preferably from about 50 to 65 wt %.

- 15       Preferably, the organic polysulfide will contain at least 40 wt % and, more preferably at least 50 wt %, and most preferably at least 55 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.

Preferably,  $R_1$  and  $R_2$  are independently an alkyl group of about 4 to 10 carbon atoms and more preferably, about 4 to 6 carbon atoms. Most preferably,  $R_1$  and  $R_2$  are each a tertiary-butyl group.

20

Preferably,  $x$  is about 4 to 8 and more preferably,  $x$  is about 4 to 7.

Preferably, the organic polysulfide is predominantly a di-tertiary-butyl tetra-sulfide. More preferably, the organic polysulfide is a mixture of di-tertiary-butyl tri-, tetra- and penta-sulfide having greater than 50 wt % di-tertiary-butyl-tetra-sulfide such as the di-tertiary-butyl polysulfide known as TBPS 454, which is  
5 commercially available from Chevron Phillips Chemical Company.

The gear oil additive composition will also contain thiadiazole. Preferably, the thiadiazole comprises at least one of 2,5-dimercapto-1,3,4-thiadiazole; 2-mercapto-5-hydrocarbylthio-1,3,4-thiadiazoles; 2-mercapto-5-hydrocarbyldithio-1,3,4-thiadiazoles; 2,5-bis(hydrocarbylthio)- and 2,5-bis(hydrocarbyldithio)-  
10 1,3,4-thiadiazoles. The more preferred compounds are the 1,3,4-thiadiazoles, especially the 2-hydrocarbyldithio-5-mercapto-1,3,4-dithiadiazoles and the 2,5-bis(hydrocarbyldithio)-1,3,4-thiadiazoles, a number of which are available as articles of commerce from either Ethyl Corporation as Hitec® 4313 or from Lubrizol Corporation as Lubrizol®5955A. Typically, the thiadiazole will be  
15 present in the gear oil additive composition in amounts ranging from about 0.5 to 15 wt %, and will preferably be present in the gear oil additive composition in amounts from about 0.7 to 12 wt % and more preferably from about 1.0 to 10 wt %.

The gear oil additive composition of the present invention will further contain at  
20 least one ashless phosphorus-containing wear inhibitor compound preferably selected from the group consisting of an amino phosphorus compound and a trialkyl phosphite.

The amino phosphorus compound may be a phosphorus compound as described in accordance with Salentine, U.S. Patent No. 4,575,431, the  
25 disclosure of which is herein incorporated by reference. Preferably, the amino phosphorus compound is an amine dithiophosphate. Typical dithiophosphates useful in the lubricant of the present invention are well known in the art. These dithiophosphates are those containing two hydrocarbyl groups and one

hydrogen functionality, and are therefore acidic. The hydrocarbyl groups useful herein are preferably aliphatic alkyl groups of about 3 to 8 carbon atoms.

Trialkyl phosphites useful in the present invention include  $(RO)_3 P$  where R is a hydrocarbyl of about 4 to 24 carbon atoms, more preferably about 8 to 18 carbon atoms, and most preferably about 10 to 14 carbon atoms. The hydrocarbyl may be saturated or unsaturated. Preferably, the trialkyl phosphite contains at least 75 wt % of the structure  $(RO)_3 P$  wherein R is as defined above. Representative trialkyl phosphites include, but are not limited to, tributyl phosphite, trihexyl phosphite, trioctyl phosphite, tridecyl phosphite, trilauryl phosphite and trioleyl phosphite. A particularly preferred trialkyl phosphite is trilauryl phosphite, such as commercially available Duraphos TLP by Rhodia Incorporated Phosphorus & Performance Derivatives. Preferred are mixtures of phosphites containing hydrocarbyl groups having about 10 to 14 carbon atoms. These mixtures are usually derived from animal or natural vegetable sources. Representative hydrocarbyl mixtures are commonly known as coco, tallow, tall oil, and soya.

Typically, the gear oil additive composition will contain about 5.0 to 40 wt % of the ashless phosphorus-containing wear inhibitor compound. Preferably, the ashless phosphorus-containing wear inhibitor compound will be present from about 7.0 to 35 wt % and more preferably from about 10 to 35 wt %.

The gear oil additive composition will optionally contain sufficient organic liquid diluent to make it easy to handle during shipping and storage. Typically, the gear oil additive composition will contain from about 0 to 20 wt % of the organic liquid diluent and preferably about 3 to 15 wt %.

Suitable organic diluents which can be used include, for example, solvent refined 100N, i.e., Cit-Con 100N, and hydrotreated 100N, i.e., Chevron 100N,

and the like. The organic diluent preferably has a viscosity of from about 1.0 to 20 cSt at 100°C.

The gear oil additive composition may also further contain a dispersant compound in a range from about 3.0 to 45 wt %.

- 5 The components of the gear oil additive composition can be blended in any order and can be blended as combinations of components. The gear oil additive composition produced by blending the above components might be a slightly different composition than the initial mixture because the components may interact.
- 10 If desired, an additional sulfur-containing compound or mixture of compounds, such as sulfurized olefins, for example, sulfurized isobutylene, sulfurized fatty esters, sulfurized oils, sulfurized fatty acids, and alkenyl monosulfides, may be added as an additional component of the gear oil additive composition or to lubricating oils containing the gear oil additive composition.

15

#### Gear Oil Composition


- The organic polysulfide, thiadiazole, and ashless phosphorus-containing wear inhibitor are generally added to a base oil that is sufficient to lubricate gears which are present in axles and transmissions. Typically, the gear oil composition will contain a major amount of a base oil of lubricating viscosity and a minor amount of the gear oil additive composition described above.
- 20

The base oil of lubricating viscosity used in such compositions may be mineral oils or synthetic oils of viscosity suitable for use in gears. The base oils may be derived from synthetic or natural sources. Mineral oils for use as the base oil in this invention include, for example, paraffinic, naphthenic and other oils that

are ordinarily used in lubricating oil compositions. Synthetic oils include, for example, both hydrocarbon synthetic oils and synthetic esters and mixtures thereof having desired viscosity. Hydrocarbon synthetic oils may include, for example, oils prepared from the polymerization of ethylene, i.e., polyalphaolefin or PAO, or from hydrocarbon synthesis procedures using carbon monoxide and hydrogen gases such as in a Fisher-Tropsch process. Useful synthetic hydrocarbon oils include liquid polymers of alpha olefins having the proper viscosity. Especially useful are the hydrogenated liquid oligomers of C<sub>6</sub> to C<sub>12</sub> alpha olefins such as 1-decene trimer. Likewise, alkyl benzenes of proper viscosity, such as didodecyl benzene, can be used. Useful synthetic esters include the esters of monocarboxylic acids and polycarboxylic acids, as well as mono-hydroxy alkanols and polyols. Typical examples are didodecyl adipate, pentaerythritol tetracaproate, di-2-ethylhexyl adipate, dilaurylsebacate, and the like. Complex esters prepared from mixtures of mono and dicarboxylic acids and mono and dihydroxy alkanols can also be used. Blends of mineral oils with synthetic oils are also useful. Group I base oil is preferred.

In its broadest aspect, the gear oil composition of the present invention will comprise:

- a) a major amount of a base oil of lubricating viscosity; and
- b) a minor amount of a gear oil additive composition comprising:
  - (i) a organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein R<sub>1</sub> and R<sub>2</sub> are independently an alkyl group of about 4 to 12 carbon atoms and x is about 4 or greater;

- (ii) a thiadiazole; and
- (iii) at least one ashless phosphorus-containing wear inhibitor.

Typically, the gear oil composition will comprise about 0.1 to 3.6 wt %, preferably from about 0.6 to 2.5 wt % and more preferably from about 1.5 to 2.2 wt % of the organic polysulfide. The gear oil composition will also comprise about 0.01 to 0.6 wt %, preferably from about 0.05 to 0.4 wt % and more preferably from about 0.1 to 0.3 wt % of the thiadiazole. The gear oil composition will further comprise about 0.1 to 2.5 wt %, preferably from about 0.2 to 1.7 wt % and more preferably from about 0.4 to 1.2 wt % of the ashless phosphorus-containing wear inhibitor compound.

The gear oil composition may also further contain a dispersant compound in the range from about 0.1 to 2.7 wt %.

In another aspect the gear oil composition of the present invention will have chlorine levels typically below 50 ppm and more preferably below 25 ppm.

#### Other Additives

The following additive components are examples of some of the components that can be favorably employed in the present invention. These examples of additives are provided to illustrate the present invention, but they are not intended to limit it:

##### 1. Metal Detergents

Sulfurized or unsulfurized alkyl or alkenyl phenates, alkyl or alkenyl aromatic sulfonates, sulfurized or unsulfurized metal salts of multi-hydroxy alkyl or alkenyl aromatic compounds, alkyl or alkenyl

hydroxy aromatic sulfonates, sulfurized or unsulfurized alkyl or alkenyl naphthenates, metal salts of alkanolic acids, metal salts of an alkyl or alkenyl multiacid, borated overbased metal salts, and chemical and physical mixtures thereof.

5    2.    Dispersants

Alkenyl succinimides, alkenyl succinimides modified with other organic compounds, alkenyl succinimides modified by post-treatment with ethylene carbonate or boric acid, pentaerythritol alkenyl succinates, phenate-salicylates and their post-treated analogs, alkali metal or mixed  
10    alkali metal, alkaline earth metal borates, dispersions of hydrated alkali metal borates, dispersions of alkaline-earth metal borates, polyamide ashless dispersants, or mixtures of such dispersants.

3.    Anti-Oxidants

Anti-oxidants reduce the tendency of mineral oils to deteriorate in  
15    service which deterioration is evidenced by the products of oxidation such as sludge and varnish-like deposits on the metal surfaces and by an increase in viscosity. Examples of anti-oxidants useful in the present invention include, but are not limited to, phenol type (phenolic) oxidation inhibitors, such as 4,4'-methylene-bis(2,6-di-tert-butylphenol),  
20    4,4'-bis(2,6-di-tert-butylphenol), 4,4'-bis(2-methyl-6-tert-butylphenol), 2,2'-methylene-bis(4-methyl-6-tert-butylphenol), 4,4'-butylidene-bis(3-methyl-6-tert-butylphenol), 4,4'-isopropylidene-bis(2,6-di-tert-butylphenol), 2,2'-methylene-bis(4-methyl-6-nonylphenol), 2,2'-isobutylidene-bis(4,6-dimethylphenol), 2,2'-  
25    methylene-bis(4-methyl-6-cyclohexylphenol), 2,6-di-tert-butyl-4-methylphenol, 2,6-di-tert-butyl-4-ethylphenol, 2,4-dimethyl-6-tert-butylphenol, 2,6-di-tert-l-dimethylamino-p-cresol, 2,6-di-tert-4-(N,N'-dimethylaminomethylphenol), 4,4'-thiobis(2-methyl-6-tert-butylphenol), 2,2'-thiobis(4-methyl-6-tert-butylphenol), bis(3-methyl-4-hydroxy-5-tert-

butylbenzyl)-sulfide, and bis(3,5-di-tert-butyl-4-hydroxybenzyl).

Diphenylamine-type oxidation inhibitors include, but are not limited to, alkylated diphenylamine, phenyl- $\alpha$ -naphthylamine, and alkylated- $\alpha$ -naphthylamine. Other types of oxidation inhibitors include metal dithiocarbamate (e.g., zinc dithiocarbamate), and methylenebis(dibutyldithiocarbamate).

#### 4. Anti-Wear Agents

As their name implies, these agents reduce wear of moving metallic parts. Examples of such agents include, but are not limited to, phosphates, carbonates, esters, and molybdenum complexes.

#### 5. Rust Inhibitors (Anti-Rust Agents)

a) Nonionic polyoxyethylene surface active agents: polyoxyethylene lauryl ether, polyoxyethylene higher alcohol ether, polyoxyethylene nonyl phenyl ether, polyoxyethylene octyl phenyl ether, polyoxyethylene octyl stearyl ether, polyoxyethylene oleyl ether, polyoxyethylene sorbitol monostearate, polyoxyethylene sorbitol mono-oleate, and polyethylene glycol mono-oleate.

b) Other compounds: stearic acid and other fatty acids, dicarboxylic acids, metal soaps, fatty acid amine salts, metal salts of heavy sulfonic acid, partial carboxylic acid ester of polyhydric alcohol, and phosphoric ester.

#### 6. Demulsifiers

Addition product of alkylphenol and ethylene oxide, polyoxyethylene alkyl ether, and polyoxyethylene sorbitan ester.

#### 7. Extreme Pressure Anti-Wear Agents (EP/AW Agents)

Diphenyl sulfide, methyl trichlorostearate, chlorinated naphthalene, fluoroalkylpolysiloxane, lead naphthenate, neutralized phosphates,

neutralized or partially neutralized thiophosphates or dithiophosphates, and sulfur-free phosphates.

8. Friction Modifiers

5 Fatty alcohol, fatty acid, amine, borated ester, and other esters, and dihydrocarbyl hydrogen phosphonates.

9. Multifunctional Additives

10 Sulfurized oxymolybdenum dithiocarbamate, sulfurized oxymolybdenum organo phosphorodithioate, oxymolybdenum monoglyceride, oxymolybdenum diethylate amide, amine-molybdenum complex compound, and sulfur-containing molybdenum complex compound.

10. Viscosity Index Improvers

15 Polymethacrylate type polymers, ethylene-propylene copolymers, styrene-isoprene copolymers, hydrated styrene-isoprene copolymers, polyisobutylene, and dispersant type viscosity index improvers.

11. Pour Point Depressants

Polymethyl methacrylate.

12. Foam Inhibitors

Alkyl methacrylate polymers and dimethyl silicone polymers.

20 13. Metal Deactivators

Disalicylidene propylenediamine, triazole derivatives, mercaptobenzothiazoles, and mercaptobenzimidazoles.

## EXAMPLES

25 The invention will be further illustrated by the following examples, which set forth particularly advantageous method embodiments. While the Examples are

provided to illustrate the present invention, they are not intended to limit it. This application is intended to cover those various changes and substitutions that may be made by those skilled in the art without departing from the spirit and scope of the appended claims.

5

#### Comparative Example A

2.4 wt % (194.0 grams) of an organic polysulfide containing a mixture of di-  
tertiary-butyl tri-, tetra-, and penta-sulfide having greater than 50 wt % di-  
tertiary-butyl tetra-sulfide (available as TBPS 454 from Chevron Phillips  
Chemical Company), 12.4 wt % (990.0 grams) of solvent refined bright stock  
10 base oil (Citgo 150), and 85.2 wt % (6,817.0 grams) of hydro-processed 600  
neutral base oil (Chevron 600N) were mixed until the mixture was  
homogenous.

#### Comparative Example B

2.4 wt % (247.0 grams) of an organic polysulfide containing a mixture of di-  
15 tertiary-butyl tri-, tetra-, and penta-sulfide having greater than 50 wt % di-  
tertiary-butyl tetra-sulfide (available as TBPS 454 from Chevron Phillips  
Chemical Company), 1.1 wt % (110.0 grams) of amine dithiophosphate (as  
described in Salentine, U.S. Patent No. 4,575,431), 12.2 wt % (1,248.0 grams)  
of Citgo 150 bright stock (base oil), and 84.3 wt % (8,595.0 grams) of hydro-  
20 processed 600 neutral base oil (Chevron 600N) were mixed until the mixture  
was homogenous.

#### Comparative Example C

2.4 wt % (12.1 grams) of an organic polysulfide containing a mixture of di-  
tertiary-butyl tri-, tetra-, and penta-sulfide having greater than 50 wt % di-  
25 tertiary-butyl tetra-sulfide (available as TBPS 454 from Chevron Phillips  
Chemical Company), 0.3 wt % (1.5 grams) of thiadiazole (available as Hitec  
4313 from Ethyl Corporation), 12.3 wt % (61.7 grams) of solvent refined bright  
stock base oil (Citgo 150), and 85.0 wt % (424.7 grams) of hydro-processed  
600 neutral base oil (Chevron 600N) were mixed until the mixture was  
30 homogenous.

#### Comparative Example D

4.0 wt % (320.0 grams) of sulfurized isobutylene having 47 wt % sulfur (available as Mobilad C-100 from ExxonMobil Chemical Company), 12.2 wt % (974.0 grams) of solvent refined bright stock base oil (Citgo 150), and 83.8 wt % (6,706.0 grams) of hydro-processed 600 neutral base oil (Chevron 600N) were mixed until the mixture was homogenous.

#### Comparative Example E

3.6 wt % (18.0 grams) of sulfurized isobutylene having 47 wt % sulfur (available as Mobilad C-100 from ExxonMobil Chemical Company), 1.1 wt % (5.4 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 12.1 wt % (60.4 grams) of solvent refined bright stock base oil (Citgo 150), and 83.2 wt % (416.2 grams) of hydro-processed 600 neutral base oil (Chevron 600N) were mixed until the mixture was homogenous.

#### Comparative Example F

3.6 wt % (18.0 grams) of sulfurized isobutylene having 47 wt % sulfur (available as Mobilad C-100 from ExxonMobil Chemical Company), 0.3 wt % (1.5 grams) of thiadiazole (available as Hitec® 4313 from Ethyl Corporation), 12.2 wt % (60.9 grams) of solvent refined bright stock base oil (Citgo 150), and 83.9 wt % (419.6 grams) of hydro-processed 600 neutral base oil (Chevron 600N) were mixed until the mixture was homogenous.

#### Comparative Example G

Base additive package K:

Base additive package K was prepared as follows: 69.2 wt % (346.1 grams) of sulfurized isobutylene having 47 wt % sulfur (available as Mobilad C-100 from ExxonMobil Chemical Company), 20.2 wt % (101.0 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 5.8 wt % (28.9 grams) of thiadiazole (available as Hitec® 4313 from Ethyl Corporation), and 4.81 wt % (24.0 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was homogenous.

#### Comparative Example H

- 5.2 wt % (26.0 grams) of the base package K, 12.5 wt % (62.7 grams) of solvent refined bright stock base oil (Citgo 150), and 82.3 wt % (411.3 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example I

- 5.2 wt % (26.0 grams) of the base package K, 1.2 wt % (6.2 grams) of 1300 molecular weight succinimide ethylene carbonate post-treated dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 78.6 wt % (392.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example J

- 5.2 wt % (26.0 grams) of the base package K, 1.2 wt % (6.2 grams) of 2300 molecular weight succinimide ethylene carbonate post-treated dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 78.6 wt % (392.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example K

- 5.2 wt % (26.0 grams) of the base package K, 1.2 wt % (6.2 grams) of 1000 molecular weight succinimide dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 78.6 wt % (392.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example L

- 5.2 wt % (26.0 grams) of the base package K, 1.2 wt % (6.2 grams) of pentaerythritol and polyisobutenyl succinic anhydride (molecular weight 1000) ester dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil

(Citgo 150), and 78.6 wt % (392.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example M

5 A gear oil additive composition was prepared as follows: 67.9 wt % (679.3 grams) of sulfurized isobutylene having 47 wt % sulfur (available as Mobilad C-100 from ExxonMobil Chemical Company), 9.4 wt % (94.3 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 12.3 wt % (122.6 grams) of trilauryl phosphate (available as Duraphos TLP from Rhodia Inc. Phosphorus & Performance Derivatives), 5.7 wt % (56.6 grams) of  
10 thiadiazole (available as Lubrizol® 5955A from Lubrizol Corporation), and 4.7 wt % (47.2 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was homogenous.

5.3 wt % (901.0 grams) of the additive package above described, 18.9 wt % (3,220.0 grams) of solvent refined bright stock base oil (Citgo 150), and 75.8 wt  
15 % (12,879.0 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example N

3.0 wt % (108.0 grams) of a di-t-butyl polysulfide containing at least 80 wt % of di-t-butyl tri-sulfide (available as TBPS 344 from Chevron Phillips Chemical  
20 Company), 12.3 wt % (442.8 grams) of solvent refined bright stock base oil (Citgo 150), and 84.7 wt % (3,049.2 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Comparative Example O

L42 test evaluation:

25 As mentioned in the background of this application, sulfur containing compounds are typically used in gear oil formulations to protect the gears from scoring. The API GL-5 category specifies the L42 test method as the procedure for determining the load carrying capacity of the lubricant under conditions of high-speed and shock loads.

The L42 test procedure is described in ASTM Technical Publication STP512A "Laboratory Performance Test for Automotive Gear Lubricants Intended for API GL-5 Service" available from ASTM International at 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959 and is incorporated herein for  
5 all purposes.

Comparative Example A (having an organic polysulfide containing a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide, and having greater than 50 wt % of a di-tertiary-butyl tetra-sulfide) and Comparative Example N (having an organic polysulfide containing a di-t-butyl polysulfide containing at least 80 wt  
10 % of di-t-butyl tri-sulfide) were evaluated in the L42 test.

Comparative Example A passed the L42 test and Example N failed the L42 test.

#### Example 1

A gear oil additive composition was prepared as follows: 63.7 wt % (318.4  
15 grams) of an organic polysulfide containing a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide and having greater than 50 wt % di-tertiary-butyl tetra-sulfide (available as TBPS 454 from Chevron Phillips Chemical Company), 28.4 wt % (142.1 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 7.9 wt % (39.5 grams) of thiadiazole (available as  
20 Hitec® 4313 from Ethyl Corporation), were mixed until the mixture was homogenous.

3.8 wt % (456.0 grams) of the gear oil additive composition described above, 12.2 wt % (1,464.0 grams) of solvent refined bright stock base oil (Citgo 150), and 84.0 wt % (10,080.0 grams) of hydro-processed 600 neutral base oil  
25 (Chevron 600N) were mixed at 130 °F until the mixture was homogenous.

#### Example 2

A gear oil additive composition was prepared as follows: 52.9 wt % (264.7 grams) of an organic polysulfide containing a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide and having greater than 50 wt % di-tertiary-butyl tetra-sulfide (available as TBPS 454 from Chevron Phillips Chemical Company),  
30

30.9 wt % (154.4 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 8.8 wt % (44.1 grams) of thiadiazole (available as Hitec® 4313 from Ethyl Corporation), and 7.4 wt % (36.8 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was  
5 homogenous.

3.4 wt % (255.0 grams) of the gear oil additive composition described above, 15.0 wt % (1,125.0 grams) of solvent refined bright stock base oil (Citgo 150), and 81.6 wt % (6,120.0 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

10

### Example 3

Base additive package J:

Base additive package J was prepared as follows: 52.9 wt % (529.4 grams) of an organic polysulfide containing a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide and having greater than 50 wt % di-tertiary-butyl tetra-sulfide  
15 (available as TBPS 454 from Chevron Phillips Chemical Company), 30.9 wt % (308.8 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 8.8 wt % (88.2 grams) of thiadiazole (available as Hitec® 4313 from Ethyl Corporation), and 7.4 wt % (73.6 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was  
20 homogenous.

### Example 4

3.4 wt % (17.0 grams) of the base package J, 1.2 wt % (6.2 grams) of 1300 molecular weight succinimide ethylene carbonate post-treated dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 80.4  
25 wt % (401.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

### Example 5

3.4 wt % (17.0 grams) of the base package J, 1.2 wt % (6.2 grams) of pentaerythritol and polyisobutenyl succinic anhydride (molecular weight 1000)

ester dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 80.4 wt % (401.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Example 6

- 5 3.4 wt % (17.0 grams) of the base package J, 1.2 wt % (6.2 grams) of a highly over-based mixture of phenate and salicylate, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 80.4 wt % (401.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

10

#### Example 7

- 3.4 wt % (17.0 grams) of the base package J, 2.5 wt % (12.5 grams) of a polyisobutenyl succinic anhydride (molecular weight 2300), 14.8 wt % (74.0 grams) of solvent refined bright stock base oil (Citgo 150), and 79.3 wt % (396.5 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed  
15 until the mixture was homogenous.

#### Example 8

- 3.4 wt % (17.0 grams) of the base package J, 1.2 wt % (6.2 grams) of 2300 molecular weight succinimide ethylene carbonate post-treated dispersant, 15.0 wt % (75.0 grams) of solvent refined bright stock base oil (Citgo 150), and 80.4 wt % (401.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were  
20 mixed until the mixture was homogenous.

#### Example 9

- 3.4 wt % (17.0 grams) of the base package J, 1.2 wt % (6.2 grams) of 1000 molecular weight succinimide dispersant, 15.0 wt % (75.0 grams) of solvent  
25 refined bright stock base oil (Citgo 150), and 80.4 wt % (401.8 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Example 10

A gear oil additive composition was prepared as follows: 51.4 wt % (514.3 grams) of an organic polysulfide containing a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide and having greater than 50 wt % di-tertiary-butyl tetra-  
5 sulfide (available as TBPS 454 from Chevron Phillips Chemical Company), 14.3 wt % (142.9 grams) of amine dithiophosphate (as described in Salentine, U.S. Patent No. 4,575,431), 18.6 wt % (185.7 grams) of triauryl phosphite (available as Duraphos TLP from Rhodia Inc. Phosphorus & Performance Derivatives), 8.57 wt % (85.7 grams) of thiadiazole (available as Lubrizol®  
10 5955A from Lubrizol Corporation) and 7.1 wt % (71.4 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was homogenous.

3.5 wt % (630.0 grams) of the gear oil additive composition described above, 19.3 wt % (3,474.0 grams) of solvent refined bright stock base oil (Citgo 150),  
15 and 77.2 wt % (13,896.0 grams) of solvent refined 100 neutral base oil (Exxon 100N) were mixed until the mixture was homogenous.

#### Example 11

3.4 wt % (17.0 grams) of the base package J, 0.5 wt % (2.5 grams) of a dispersed hydrated alkali metal borate (available as OLOA 9750 from Chevron  
20 Oronite Company), 15.1 wt % (75.6 grams) of solvent refined bright stock base oil (Citgo 150), and 81.0 wt % (404.9 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

#### Example 12

3.4 wt % (17.0 grams) of the base package J, 2.5 wt % (12.5 grams) of a polyamide ashless dispersant (available as OLOA 340D from Chevron Oronite  
25 Company), 14.8 wt % (74.0 grams) of solvent refined bright stock base oil (Citgo 150), and 79.3 wt % (396.5 grams) of solvent refined 600 neutral base oil (Exxon 600N) were mixed until the mixture was homogenous.

### Example 13

#### Performance evaluation:

Comparative Examples A–M and Examples 1–12 were evaluated following the ASTM D-5704 test procedure. In this test, a sample of the lubricant was placed in a heated gear case containing two spur gears, a test bearing, and a copper catalyst. The lubricant was heated to 325 °F and the gears were operated for 50 hours at predetermined load and speed conditions. Air was bubbled through the lubricant at a specified rate and the bulk oil temperature of the lubricant was controlled throughout the test. Parameters used for evaluating oil degradation after testing were viscosity increase, insolubles in the used oil, and gear cleanliness. Also, as part of the test report, the copper catalyst percent weight loss based upon the original weight of the copper strip was reported. The copper weight loss result indicates the copper activity of the test lubricants.

A copy of this test method can be obtained from ASTM International at 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959 and is herein incorporated for all purposes.

The performance results are presented in Table 1.

Table 1

|                       | ASTM D-5704 Copper Catalyst Weight Loss (%) |
|-----------------------|---------------------------------------------|
| Comparative Example A | 17.4                                        |
| Comparative Example B | 16.8                                        |
| Comparative Example C | 19.2                                        |
| Comparative Example D | 16.8                                        |
| Comparative Example E | 15.4                                        |
| Comparative Example F | 16.6                                        |
| Comparative Example H | 13.2                                        |

|                       |      |
|-----------------------|------|
| Comparative Example I | 13.3 |
| Comparative Example J | 14.3 |
| Comparative Example K | 13.7 |
| Comparative Example L | 13.9 |
| Comparative Example M | 14.0 |
| Example 1             | 11.0 |
| Example 2             | 8.8  |
| Example 4             | 6.0  |
| Example 5             | 5.5  |
| Example 6             | 6.0  |
| Example 7             | 6.0  |
| Example 8             | 5.3  |
| Example 9             | 6.5  |
| Example 10            | 5.9  |
| Example 11            | 4.5  |
| Example 12            | 4.7  |

The results presented in Table 1 demonstrate that the compositions of the present invention (Examples 1-12) provide low copper corrosion as evidenced by the significantly lower percent copper weight loss when compared to the Comparative Examples A-M.

Claims:

1. A gear oil additive composition comprising:

- a) an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 12 carbon atoms and  $x$  is 4 or greater;

- b) a thiadiazole; and  
c) at least one ashless phosphorus-containing wear inhibitor compound.

2. The gear oil composition according to claim 1, wherein the composition comprises from 35 to 75 wt % of the organic polysulfide, 0.5 to 15 wt % of the thiadiazole, and 5.0 to 40 wt % of the ashless phosphorus-containing wear inhibitor compound.

3. A gear oil additive composition according to claim 1 or 2, further comprising a dispersant additive selected from the group consisting of alkenyl succinimides, alkenyl succinimides modified with other organic compounds, alkenyl succinimides modified by post-treatment with ethylene carbonate or boric acid, pentaerythritol alkenyl succinates, phenate-salicylates and their post-treated analogs, alkali metal or mixed alkali metal, alkaline earth metal borates, dispersions of hydrated alkali metal borates, dispersions of alkaline-earth metal borates, polyamide

ashless dispersants, or mixtures of such dispersants.

4. A gear oil additive composition according to claim 3, wherein the dispersant additive is present in a range from 3.0 to 45 wt %.
5. The gear oil additive composition according to any one of the preceding claims, wherein the organic polysulfide is present from 45 to 70 wt %.
6. The gear oil additive composition according to any one of claims 1 to 4, wherein the organic polysulfide is present from 50 to 65 wt %.
7. The gear oil additive composition according to any one of the preceding claims, wherein the organic polysulfide contains at least 40 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
8. The gear oil additive composition according to any one of claims 1 to 6, wherein the organic polysulfide contains at least 50 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
9. The gear oil additive composition according to any one of claims 1 to 6, wherein the organic polysulfide contains at least 55 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
10. The gear oil additive composition according to any one of the preceding claims, wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 10 carbon atoms.
11. The gear oil additive composition according to any one of claims 1 to 9, wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 6 carbon atoms.

12. The gear oil additive composition according to claim 10 or 11, wherein  $R_1$  and  $R_2$  are each a tertiary-butyl group.
13. The gear oil additive composition according to any one of the preceding claims, wherein  $x$  is 4 to 8.
14. The gear oil additive composition according to any one of claims 1 to 12, wherein  $x$  is 4 to 7.
15. The gear oil additive composition according to any one of the preceding claims, wherein the organic polysulfide is di-tertiary-butyl polysulfide.
16. The gear oil additive composition according to any one of claims 1 to 14, wherein the organic polysulfide is a mixture of di-tertiary-butyl-tri-, tetra-, and penta-sulfide.
17. The gear oil additive composition according to any one of the preceding claims, wherein the thiadiazole is present from 0.7 to 12 wt %.
18. The gear oil additive composition according to any one of claims 1 to 16, wherein the thiadiazole is present from 1.0 to 10 wt %.
19. The gear oil additive composition according to any one of the preceding claims, wherein the thiadiazole comprises at least one of 2,5-dimercapto-1,3,4-thiadiazole; 2-mercapto-5-hydrocarbylthio-1,3,4-thiadiazoles; 2-mercapto-5-hydrocarbyldithio-1,3,4-thiadiazoles; 2,5-bis(hydrocarbylthio)- and 2,5-bis(hydrocarbyldithio)-1,3,4-thiadiazoles.
20. The gear oil additive composition according to any one of the preceding claims, wherein the ashless phosphorus-containing wear inhibitor compound is present from 7.0 to 35 wt %.

21. The gear oil additive composition according to any one of claims 1 to 19, wherein the ashless phosphorus-containing wear inhibitor compound is present from 10 to 35 wt %.

22. The gear oil additive composition according to any one of the preceding claims, wherein the ashless phosphorus-containing wear inhibitor compound is at least one compound selected from the group consisting of an amino phosphorus compound and a trialkyl phosphite.


23. The gear oil additive composition according to claim 22, wherein the amino phosphorus compound is amine dithiophosphate.

24. The gear oil additive composition according to claim 22, wherein the trialkyl phosphate is trilauryl phosphite.

25. The gear oil additive composition according to claim 24, wherein the trilauryl phosphite contains at least 75 wt % of the structure  $(RO)_3 P$ , wherein R is a hydrocarbyl of 4 to 24 carbon atoms.

26. A gear oil composition comprising:

- a) a major amount of a base oil of lubricating viscosity; and
- b) a minor amount of a gear oil additive composition comprising:
  - (i) an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of

4 to 12 carbon atoms and x is 4 or greater;

(ii) a thiadiazole; and

(iii) at least one ashless phosphorus-containing wear inhibitor compound.

27. The gear oil composition according to claim 26, wherein the composition comprises from 0.1 to 3.6 wt % of the organic polysulfide, 0.01 to 0.6 wt % of the thiadiazole, and 0.1 to 2.5 wt % of the ashless phosphorus-containing wear inhibitor compound.

28. The gear oil composition according to claim 26 or 27, further comprising a dispersant additive selected from the group consisting of alkenyl succinimides, alkenyl succinimides modified with other organic compounds, alkenyl succinimides modified by post-treatment with ethylene carbonate or boric acid, pentaerythritol alkenyl succinates, phenate-salicylates and their post-treated analogs, alkali metal or mixed alkali metal, alkaline earth metal borates, dispersion of hydrated alkali metal borates, dispersion of alkaline-earth metal borates, polyamide ashless dispersants, or mixtures of such dispersants.

29. The gear oil composition according to claim 28, wherein the dispersant additive is present in a range from 0.1 to 2.7 wt %.

30. The gear oil composition according to any one of claims 26 to 29, wherein the organic polysulfide is present from 0.6 to 2.5 wt %.

31. The gear oil composition according to any one of claims 26 to 29, wherein the organic polysulfide is present from 1.5 to 2.2 wt %.

32. The gear oil composition according to any one of claims 26 to 31,

- wherein the organic polysulfide contains at least 40 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
33. The gear oil composition according to any one of claims 26 to 31, wherein the organic polysulfide contains at least 50 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
34. The gear oil composition according to any one of claims 26 to 31, wherein the organic polysulfide contains at least 55 wt % of the dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds.
35. The gear oil composition according to any one of claims 26 to 34, wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 10 carbon atoms.
36. The gear oil composition according to any one of claims 26 to 34, wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 6 carbon atoms.
37. The gear oil composition according to any one of claims 26 to 36, wherein  $R_1$  and  $R_2$  are each a tertiary-butyl group.
38. The gear oil composition according to any one of claims 26 to 37, wherein  $x$  is 4 to 8.
39. The gear oil composition according to any one of claims 26 to 37, wherein  $x$  is 4 to 7.
40. The gear oil composition according to any one of claims 26 to 39, wherein the organic polysulfide is a di-tertiary-butyl polysulfide.
41. The gear oil composition according to any one of claims 26 to 39,

wherein the organic polysulfide is a mixture of di-tertiary-butyl tri-, tetra-, and penta-sulfide.

42. The gear oil composition according to any one of claims 26 to 41, wherein the thiadiazole is present from 0.05 to 0.4 wt %.

43. The gear oil composition according to any one of claims 26 to 41, wherein the thiadiazole is present from 0.1 to 0.3 wt %.

44. The gear oil composition according to any one of claims 26 to 43, wherein the thiadiazole comprises at least one of 2,5-dimercapto-1,3,4-thiadiazole; 2-mercapto-5-hydrocarbylthio-1,3,4-thiadiazoles; 2-mercapto-5-hydrocarbyldithio-1,3,4-thiadiazoles; 2,5-bis(hydrocarbylthio)- and 2,5-bis(hydrocarbyldithio)-1,3,4-thiadiazoles.

45. The gear oil composition according to any one of claims 26 to 44, wherein the ashless phosphorus-containing wear inhibitor compound is present from 0.2 to 1.7 wt %.

46. The gear oil composition according to any one of claims 26 to 44, wherein the ashless phosphorus-containing wear inhibitor compound is present from 0.5 to 1.2 wt %.

47. The gear oil composition according to any one of claims 26 to 46, wherein the ashless phosphorus-containing wear inhibitor compound is at least one compound selected from the group consisting of an amino phosphorus compound and a trialkyl phosphite.

48. The gear oil composition according to claim 47, wherein the amino phosphorus compound is amine dithiophosphate.

49. The gear oil composition according to claim 47, wherein the trialkyl


phosphite is trilauryl phosphite.

50. The gear oil composition according to claim 49, wherein the trilauryl phosphite contains at least 75 wt % of the structure  $(RO)_3 P$ , wherein R is a hydrocarbyl of 4 to 24 carbon atoms.

51. The gear oil composition according to any one of claims 26 to 50, having chlorine levels below 50 ppm.

52. A method of reducing yellow metal corrosion in axles and transmissions, said method comprising contacting the metal components of the axle and transmission with a gear oil composition comprising:

- a) a major amount of a base oil of lubricating viscosity; and
- b) a minor amount of a gear oil additive composition comprising:
  - (i) an organic polysulfide containing greater than 30 wt % of a dialkyl polysulfide compound or mixture of dialkyl polysulfide compounds of the formula:



wherein  $R_1$  and  $R_2$  are independently an alkyl group of 4 to 12 carbon atoms and x is about 4 or greater;

- (ii) a thiadiazole; and
- (iii) at least one ashless phosphorus-containing wear inhibitor compound.

## **GEAR OIL HAVING LOW COPPER CORROSION PROPERTIES**

### **ABSTRACT OF THE DISCLOSURE**

A gear oil additive composition and gear oil composition comprising a organic polysulfide having at least 30 wt % of a dialkyl polysulfide compound or mixture  
5 of dialkyl polysulfide compounds, a thiadiazole; and at least one ashless phosphorus-containing wear inhibitor compound is disclosed as having low yellow corrosion in axles and transmissions.