

A B S T R A C T

SINTERED REFRACTORY PRODUCT EXHIBITING
ENHANCED THERMAL SHOCK RESISTANCE

5

The invention concerns a sintered refractory product having the following average chemical composition, in weight percentages based on oxides: $20\% < \text{Al}_2\text{O}_3 < 90\%$; $6\% \leq \text{SiO}_2 < 30\%$; $3\% < \text{ZrO}_2 < 50\%$; $0\% \leq \text{Cr}_2\text{O}_3 < 50\%$. The inventive product is characterized in that it comprises 17 to 85 wt.% of mullite-zirconium grains.

15

20

25

Translation of the title and the abstract as published by the PCT Authorities, possibly after making changes, ex officio, e.g. under PCT Rules 37.2, 38.2, and/or 48.3.



162162



G00002