



STRUCTURE AND PROCESS FOR ELECTRO/MECHANICAL  
JOINT FORMATION

BACKGROUND OF THE INVENTION

5 The present invention pertains to methods and  
means for simultaneously joining together electrical  
and other components through the application of  
directed energy, such as ultrasonic energy. More  
particularly, the present invention is directed to  
electro/mechanical joint formation by the application  
10 of directed energy, typically ultrasonic energy, in  
order to simultaneously bond together polymer  
substrates and metal circuit patterns which are present  
as conductive coatings on separate substrates.

15 Ultrasonic bonding methods are used to permanently  
bond two or more parts made of a polymer material,  
particularly when or where it is undesirable to use  
adhesives. The use of adhesives can adversely effect  
the strength of the mechanical joint in instances  
where the joint is exposed to certain chemicals,  
20 solvents, pressures and temperatures. In addition,  
ultrasonic bonding requires little or no surface  
preparation, is very fast, can be readily automated,  
and no fixture or cure time is required for the  
parts after the process is complete.

25 Ultrasonic bonding of metals is also known.  
Permanent bonding obviates the need for mechanical  
fasteners such as screws, bolts or rivets as well as  
eliminating the need for other bonding methods such as  
brazing or soldering. Ultrasonic bonding of metals  
30 generally creates an improved electrical joint in that

PO9-93-010



the interface between the two mating parts is essentially eliminated.

5 In certain applications, it is necessary or  
desired to provide a joint with both mechanically  
robust and electrically conductive characteristics. It  
would be desirable to take advantage of the unique  
features that ultrasonic bonding can provide, however,  
to date, it is not known how to achieve this on a  
conductively coated plastic part. Each bonding  
0 operation can be done separately, as described above;  
however, simultaneous bonding is difficult. One of the  
reasons for this is that for polymer to polymer  
ultrasonic bonding, the ultrasonic energy is applied to  
each part so that the movement of one part relative to  
5 the other is a direct impact motion (hammer type  
movement). However, with metal to metal ultrasonic  
bonding, the movement of one part relative to the other  
is sheer (one part sliding against the other).  
Accordingly, the desired direction of motion for  
10 bonding polymers and metals is different and seemingly  
incompatible.

Bonding of conductively coated polymer surfaces  
together is useful in many applications among which  
are, to name but a few: (1) the sealing of housings  
15 for the control of electromagnetic interference (EMI);  
(2) the protection of electronic packages from  
electrostatic discharge (ESD) events; and (3) the  
affixation of surface mount components to thermoplastic  
circuit cards.

#### 30 OTHER PATENTS DISCUSSING ULTRASONIC BONDING METHODS

U.S. Patent 4,546,409 appears to teach that  
ultrasonic energy can be applied in order to create a



PO9-93-010

metal to metal bond between a multitude of surfaces.  
However, the method discussed in this patent is  
specific to semiconductor devices.

5 Likewise, the teachings of U.S. Patent 4,468,731  
appear to disclose only the ultrasonic bonding of  
polymers to polymers exclusively. There are apparently  
no discussions of bonding metal surfaces or  
conductively coated polymer surfaces.

10 U.S. Patent 4,589,584 seems to apply to ultrasonic  
bonding of a filled polymer to another filled polymer  
with simultaneous bonding of an unfilled polymer to  
another unfilled polymer. An electrical connection is  
achieved by using a conductive filler in the filled  
15 polymer. An example of this is the use of silver  
particles in a thermoplastic matrix. A number of other  
disclosed fillers which can be used includes glass,  
mica and minerals. However these fillers would not  
provide distinct electrical connections and would in  
fact destroy the desired insulative properties of  
20 polymeric substrates or circuit boards.

#### OBJECTS OF THE INVENTION

Accordingly, it is an object of the present  
invention to provide a method for bonding a plurality  
of conductively coated polymer substrates to each other  
25 in a single operation by applying directed energy to  
the objects to be bonded.

Another object of the present invention is to  
achieve a structurally strong mechanical bond and a low  
resistance electrical connection by selecting proper  
30 joint geometry, metallurgical structure and metal  
location. Various joint configurations are shown



PO9-93-010

including butt joints, tongue and groove joint, and step joints among others, depending upon the mechanical and electrical characteristics required of the bond.

5 A further object of the present invention is to provide a non-chemical, non-solvent reaction or cure of an interposer adhesive disposed between a component and substrate, while simultaneously forming an electrical connection for certain circuit devices including, but not limited to, surface mount technology devices.

10 Yet another object of the present invention is to provide a structure that does not require special bonding methods and is readily adaptable to conventional bonding equipment like that utilized in ultrasonic bonding.

15 SUMMARY OF THE INVENTION

This invention relates to a method for joining at least two conductively coated polymer substrates, especially where the conductive coating has been selectively patterned. A conductive layer is present  
20 on those substrate regions where an electrical bond is to be formed. The conductive coating is absent from those areas where a mechanical bond is to be formed. The substrates are then placed in a configuration where the locations at which a mechanical bond is to be  
25 formed are in contact and in which the locations where an electrical bond is to be formed are also in contact. The directed energy is then applied to the substrates so as to simultaneously fuse together the conductive coatings and the polymer substrates respectively.

30 Once the energy source is applied to the surfaces to be bonded, the metal to metal and polymer to polymer



PO9-93-010

joints are created in the same operation. The parts to be joined are provided with a special geometry, which insures that energy transfer occurs in a favorable detection to simultaneously assure end-to-end contact of polymeric materials and side-by-side contact of metal portions.

#### GLOSSARY OF TERMS

As used herein and in the appended claims, the following terminology is used:

- 10 A polymer is any non electrically conductive material used in two or more surfaces to be joined which will melt and fuse together; nonconductive material includes but is not limited to plastics, polymers, and thermoplastics.
- 15 "Bonding" refers to any method for joining a plurality of surfaces including, but not limited to, use of a directional high energy source. A joint is any permanent junction of a plurality of surfaces.
- 20 "Conductive coating" refers to any conductive material suitable for use as a coating on polymeric materials. "Metallized" refers to having a surface permanently covered with an electrically conductive material. "Metal" refers to any electrically conductive material suitable for use as a coating on other materials.
- 25 A mechanical bond is a joint which responds to tensile and sheer forces so as to assure the structural integrity of the device; and an electrical bond provides a low resistance electrical path.



PO9-93-010

"Flash" refers to the extrusion of molten polymer over the metal portions which generally adversely affects electrical conductivity. Directed energy is any high energy source, including but not limited to, ultrasonic energy.

#### BRIEF DESCRIPTION OF THE DRAWINGS

The subject matter which is regarded as the invention is particularly pointed out and distinctly claimed in the concluding portion of the specification. The invention, however, both as to organization and method of practice, together with further objects and advantages thereof, may best be understood by reference to the following description taken in connection with the accompanying drawings in which:

FIGURE 1 is a side view illustrating the plating geometry for a tongue and groove joint design in accordance with the present invention;

FIGURE 2 is a side view similar to Figure 1 but more particularly showing the application of a directed energy source to two mating surfaces as the two surfaces are brought together;

FIGURE 3 is a side view similar to Figure 2, except that it illustrates the resultant geometry after the two mating metal and polymer surfaces are fused together to form a single, unitary structure;

FIGURE 4 is a side view similar to Figure 1 but more particularly illustrating a different embodiment with a step joint geometry, in further accordance with the present invention; and

PO9-93-010



FIGURE 5 is a side view similar to Figure 1, illustrating an alternate geometry.

#### A DETAILED DESCRIPTION OF THE INVENTION

According to the principles of this invention, Figure 1 is an illustration of a plating geometry employing a tongue-in-groove joint design. To obtain an electro-mechanical joint, first a conductive coating is applied to selected areas where an electrical bond is to be formed. Metal coating is not applied to areas where a mechanical bond is to be formed. The presence of the metal coating in some areas and its absence in other areas allow a polymer to polymer bond to be achieved while at the same time forming the metal to metal bond. Clearly, the method is also applicable to parts in which appropriate metal patterns have already been disposed. Metal coating can be easily removed from any area through selective etching, mechanical abrasion or other methods.

The method of joint configuration of Figure 1 illustrates two mating portions 10 and 20 to be joined. Each mating portion includes conductively coating 30. Tongue feature 50 includes energy director 40 which is not coated with metal, or from which the metal has been removed prior to bonding. Metal 60 is however left on side walls of tongue 50. Mating part 10 of portion 20 possesses groove structure 70. Groove 70 is dimensioned to accept tongue 50. Groove 70 is not coated with conductive material in the area at the base of the groove, or metal is removed from this area prior to bonding. Metal 100 is left on the side walls of groove 70.

PO9-93-010



The metallurgical structure in a preferred embodiment comprises a number of conductive layers deposited on a polymer substrate. The metallurgical structure preferably comprises layers of electroless/electroplated copper 110, electroplated nickel 120, and electroplated gold 130 respectively. The thicknesses of the copper, nickel, and gold coatings are approximately 1000 microinches, 85 microinches and 30 microinches, respectively.

To achieve a robust electro-mechanical joint, the two mating halves, as shown in Figure 2 are loaded into a jig or a fixture 250 and ultrasonically bonded using standard ultrasonic bonding methods.

Figures 2 and 3 is a further illustration of the application of an ultrasonic energy source 150 to two portions 200 and 300 to be joined and the resultant geometry in a tongue-in-groove joint configuration, respectively. Figure 3 in particular illustrates the general shape of the completed polymeric bond 210 and the completed metal bond 350. The clamping pressure, bonding time, and energy delivered are all variables which can be changed in dependence on the desired characteristics of the bond. In one embodiment the ultrasonic energy used ranged between 40 and 300 Ws (Watt-seconds), the clamping pressure ranged between 10 and 30 psi and energy pulse was applied for a time ranging between 0.1 and 0.5 seconds.

The joint configuration described above is utilized in a number of different applications in which two or more parts are to be joined to form a mechanically robust structure and at the same time to achieve a low resistance electrical connection between




PO9-93-010

5       conductive patterns on the mating portions. Some applications include, but are not limited to housings (connectors, sub-assemblies), thermoplastic printed circuit boards (both two and three dimensional ), and the attachment of devices to printed circuit boards and other substrates.

10       In addition, although a tongue-in-groove joint configuration is described above, other configurations can be used. Figure 4 shows another geometry that can be utilized. Figure 4 illustrates the two mating portions 400 and 410 to be joined. Each mating portion 400 and 410 includes conductively coated regions 440 and 450, respectively. One mating portion 400 includes energy director 430 which is not coated with metal (or  
15       from which the metal has been removed prior to bonding). To prevent flashing, the geometry is designed so that when mating halves 440 and 450 are joined, the two sides 460 and 470 of each mating portion 400 and 410 are not joined and a space or gap  
20       remains between the two sides 460 and 470.

25       Similarly, Figure 5 shows yet another possible joint design. Figure 5 also illustrates two mating portions 500 and 510 to be joined with one mating portion including energy director 530 which is not coated with metal (or from which the metal has been removed prior to bonding). Conductive material 540 and 550 is present on mating portions 500 and 510 respectively. One side of one of the mating portions (here 510) possesses a set-back 560 from its top  
30       surface to reduce or eliminate the flashing problem.

While the invention has been described in detail herein in accordance with certain preferred embodiments thereof, many modifications and changes therein may be



P09-93-010

effected by those skilled in the art. Accordingly, it is intended by the appended claims to cover all such modifications and changes as fall within the true spirit and scope of the invention.

CLAIMS

What is claimed is:



1. A method for joining substrates, said method comprising:

5 applying a conductive layer on each one of said substrates at a first location where an electrical bond is to be formed and providing a second location, on each one of said substrates, which is free of conductive material where a mechanical bond is to be formed;

10 placing said substrates in a configuration wherein said first locations, where a mechanical bond is to be formed, are in contact and in which said second locations, where an electrical bond is to be formed, are in contact;

15 applying directed energy to said substrates so as to fuse said conductive layers and said polymer substrates.

- 20 2. The method of claim 1, wherein said conductive layer is applied on each one of said substrates; and

said conductive layer is then removed from said second locations where a mechanical bond is to be formed.

- 25 3. The method of claim 1, wherein the directed energy is ultrasonic.

PO9-93-010



4. The method of claim 1, in which the substrates to be joined further comprise a butt joint configuration.
5. The method of claim 1, in which the surfaces to be joined further include a step joint configuration with tapered ends and a pocket to prevent molten polymeric substrate material from flashing to substrate surfaces.
6. The method of claim 1, in which the surfaces to be joined further include a butt joint configuration with tapered ends and a pocket to prevent molten polymer from flashing to substrate surfaces.
7. The method of claim 1, in which the conductive layer comprises a metal suitable for diffusion bonding.
8. The method of claim 1, in which said conductive layer includes layers of nickel, copper and gold.
9. The method of claim 1 in which said conductive layers on their respective polymer substrates are configured in a side-by-side relationship.
10. The method of claim 1 in which said polymer substrates are configured in an end-to-end relationship.
11. The joined substrates made in accordance with claim 1.

PO9-93-010



11. The joined substrates made in accordance with  
claim 1.

12. A combination of polymeric substrates each  
having a conductive layer thereon wherein said  
polymeric substrates have been fused together and  
in which said conductive layers thereon have also  
been fused together.

13. A method for joining at least two  
conductively coated polymer substrates, said  
method comprising:

placing said substrates in a configuration in  
which locations where a polymeric bond is to be  
formed are placed in contact and locations where  
an electrical bond is to be formed are placed in  
side-to-side contact;

applying directed energy to said substrates  
so as to fuse said conductive coatings and said  
polymer substrates.

