

POLYMERIZATION CATALYST AND PROCESS

BACKGROUND OF THE INVENTION

This invention relates to modified supported chromium oxide olefin polymerization catalyst systems.

5 It further relates to a method of making ethylene polymers and copolymers.

Supported chromium oxide catalyst systems have been used for many years in the polymerization of olefins. Ethylene can be polymerized by contacting the monomer with silica-supported chromium oxide catalyst systems, the reaction
10 being carried out in an inert liquid at temperatures below 110°C for producing solid polymer suspended in the liquid or at temperatures above 110°C for solution polymerization. The properties of the resulting polymer depend upon a number of factors, including the type of catalyst system employed and its activation temperature, the reaction pressure, and the reaction temperature. It is generally
15 known that titanium can be added to the supported chromium oxide catalyst systems to produce a polymer having an increased melt index and a broader molecular weight distribution. It is also generally known that certain substances called promoters or adjuvants can be used in combination with chromium oxide catalyst systems to modify the properties of the polymer.

20 The use of chromium catalyst systems with certain organoboron promoters generally is known to broaden the polymer molecular weight distribution. Use of titanium in the catalyst system support or boron adjuvants in the reactor can result in improvements in the environmental stress crack resistance (ESCR) of the resultant polymers, as well as increased catalyst system productivity. Unfortunately,
25 these modifications can increase the amount of low molecular weight polymer and oligomers that are formed. Low molecular weight polymers and oligomers can contribute smoke and odor during the processing of the polymer, or resin, as it is molded into bottles and other articles of manufacture.

Another important characteristic of a blow molding resin is the swell
30 properties of the resin. Two kinds of swell are critical during blow molding. These are "weight swell" and "diameter swell"; the later also is referred to herein as "die swell". As polymer, or resin, is extruded under pressure through a die opening and

- 2 -

into a mold, a polymer has a tendency to swell as it exits the die. This is known as weight swell and can be determinative of the thickness of bottle wall, as well as the overall weight of the resultant blow molded product. For example, a resin which is extruded through a 0.508 mm (0.02 inch) die gap might yield a bottle wall thickness of 1.52 mm (0.06 inches), in which case the weight swell is said to be 300%. A resin that swells too much can produce a bottle with too thick of a wall. To compensate, the die opening, or gap, can be narrowed by manual adjustment. However, any decrease in die gap can increase the resistance to the flow of the resin through the die. Narrower die gaps can result in higher shear rates during extrusion which also can increase melt fracture leading to a rough bottle surface. Thus, a resin which can be described as easily processable must exhibit low weight swell, which allows a wide die gap.

Diameter, or die, swell refers to how much a parison flares out as it is extruded from the die. For example, a resin extruded through a circular die of 2.54 cms (one (1) inch) diameter can yield a parison tube of 3.81 cms (1.5 inches) in diameter; the die swell is said to be 50%. Die swell is significant because molds usually are designed for a certain amount of flare; too much die swell can interfere with molding of a bottle handle. A high degree of weight swell often causes high die swell because of the narrow die gap. Unfortunately, a narrow gap also increases the resistance to polymer flow. Thus, as used herein, a polymer which is considered easily processable also should exhibit low die swell.

Attempts have been made to obtain ethylene polymers having a broader molecular weight distribution (MWD) and consequent improved environmental stress crack resistance imparted by organoboron promoters and titania-containing catalyst systems. One of the most prevalent problems associated with such attempts is an increase of the amount of swell exhibited by the resin as it exits the die. Swell can be decreased by raising the activation temperature of the catalyst system, however, this also can reduce the polymer ESCR. Swell also can be decreased by lowering the melt index (MI), but this generally makes the resin more difficult to process, as measured by output rate and melt fracture. Swell also can be decreased by adding more chromium to the catalyst system, but this tends to impart a dirty color to the final polymer product. Thus, it has been difficult to

- 3 -

produce a resin that maintains good swell and processing characteristics, high ESCR, and a low volatiles content.

SUMMARY OF THE INVENTION

It is desirable to provide a process by which high density ethylene polymers and copolymers can be manufactured having a high stress crack resistance and are prepared in high yield.

Again it is desirable to minimize the production of oligomers and low molecular weight polymer during the polymerization process.

Once again it is desirable to minimize the amount of die swell and weight swell exhibited by the resin during molding.

Yet again it is desirable to provide a blow molding polymer which processes well in the blow molding machine.

In accordance with one embodiment of the invention, a polymerization catalyst system is provided which comprises chromium oxide on a silica-titania, wherein said support comprises less than about 3 weight percent titanium, in combination with an organoboron promoter. Further according to the invention, an ethylene polymer or copolymer is produced by contacting an ethylene monomer, and an optional comonomer, with an activated catalyst system comprising chromium oxide on a silica-titania, wherein said support comprises less than about 3 weight percent titanium, in the presence of an organoboron promoter. The resulting polymer is produced in high yield and has a combination of improved properties, including high shear response, good environmental stress crack resistance, and high density.

DETAILED DESCRIPTION OF THE INVENTION

The silica containing substrates, or supports, used in the invention catalyst systems are silica or silica-alumina gels. Such gels conventionally are prepared by mixing an acid such as sulfuric acid with an aqueous solution of an alkali metal silicate such as sodium silicate to produce an aqueous gel, or hydrogel. The silicate preferably is added to the acid, and the reaction mixture is strongly agitated. The mixing temperature can range from about 1°C to about 43°C. The resulting hydrogel is approximately 3 to about 12 weight percent SiO₂ and has a pH in a range of about 3 to about 9. The hydrogel is aged at a temperature of about

- 4 -

18°C to 98°C for a suitable time, generally more than one hour. Silica gels often have a minor portion, generally not exceeding 20 weight percent, of alumina or other metal oxides, and the support of the invention includes composite silica gels comprising silica and alumina, thoria, zirconia and like substances.

5 As used in this disclosure, the term "support" refers to a carrier for another catalytic component. However, by no means, is a support necessarily an inert material; it is possible that a support can contribute to catalytic activity and selectivity.

10 The hydrogel then is washed with water and either an ammonium salt solution or a dilute acid to reduce the alkali metal content of the hydrogel to less than about 0.1 weight percent. The ammonium salt solution is preferably one such as ammonium nitrate or an ammonium salt of an organic acid which volatilizes upon subsequent calcination.

15 Water in the hydrogel can be removed by any conventional method, such as, for example, by spray drying, vacuum oven drying, or air oven drying at temperatures above 100°C. If the hydrogel is dried by heating, it is not necessary to add an agent to the gel to prevent shrinkage of the pores.

20 The support must comprise titanium. Titanation of the silica can be effected using a variety of methods. The titanated catalyst systems must comprise no more than about 3 weight percent titanium, based on the weight of the catalyst system (not including the organoboron component), after calcining. All or part of the titanium can be supplied by coprecipitation of silica and titania. In the coprecipitation method, a titanium compound, such as, for example, a titanium
25 halide, nitrate, sulfate, oxalate, or alkyl titanate, can be incorporated with the acid or the silicate in an amount such that the amount of titanium present as titanium dioxide in the final calcined catalyst system is less than about 3 weight percent. The amount of titanium in the calcined catalyst system generally will be about 0.5 weight percent to about 3.0 weight percent, preferably within a range of about 0.5 to about 2.6 weight percent. Most preferably, the amount of titanium in the catalyst
30 system support is within a range of 0.8 to 1.5 weight percent. The coprecipitation of titania with silica is disclosed in U.S. Pat. No. 3,887,494, the disclosure of which is hereby incorporated by reference.

- 5 -

Titanation of the catalyst system support alternatively can be effected by impregnation of the hydrogel or xerogel before or after incorporation of the chromium component of the catalyst system. For example, an aqueous solution of a hydrolysis-resistant titanium compound can be incorporated into a silica hydrogel and dried by conventional techniques.

Titanation of the silica support also can be accomplished by adding a titanium compound to the silica xerogel, usually with heat to vaporize the solvent and cause titanium to be deposited on the support.

Particularly advantageous catalyst systems useful in this invention are silica-titanias created by twice aging, as disclosed in U.S. Patent No. 4,981,831, the disclosure of which is hereby incorporated by reference.

The chromium component of the catalyst system comprises about 0.5% to about 4% weight percent chromium, preferably about 0.8 to about 2.0 weight percent, based on the weight of the calcined catalyst system and most preferably between 0.8 and 1.5% weight percent. The chromium component can be coprecipitated with the silica or the silica-titania or added by means of an nonaqueous solution of a chromium compound such as tertiary butyl chromate to the xerogel, but preferably it is introduced by incorporating an aqueous solution of a water soluble chromium compound into the hydrogel after washing the hydrogel to remove alkali metal ions. Suitable chromium compounds include chromium acetate, chromium nitrate, chromium sulfate, chromium trioxide, ammonium chromate or any other chromium compound which can be converted to chromium oxide by calcination with at least part of the chromium being converted to the hexavalent state. As used herein, the term "chromium oxide", as used to describe the chromium compound present in the catalyst system after calcining, includes fixed surface chromates formed by the reaction of chromium oxide and silica, as discussed in Hogan, J. Poly. Sci. A-1, 8, 2637-2652 (1970). The chromium compound can be employed in any amount so as to provide the desired weight percent chromium in the final catalyst system.

The catalyst system can be activated by calcining at a temperature within the range of about 530°C to about 650°C in a dry atmosphere containing oxygen, usually dry air, for a time of about 10 minutes to 20 hours or longer.

- 6 -

Activation can follow titanation of the catalyst system in the activator, as described above, by heating the fluidized catalyst system sample to about 316°C, substituting dry air for the nitrogen atmosphere present during titanation, raising the temperature to at least about 400°C, and calcining the fluidized catalyst system at this elevated
5 temperature for any appropriate activation time. Following activation, the catalyst system must be stored in a dry, inert atmosphere until used.

Catalyst systems of this invention do not require a reduction step using carbon monoxide or other reducing treatments. In fact, such reduction treatments can be detrimental to this invention because they can narrow the
10 molecular weight distribution and lower the density of the resin beyond that which is desirable for blow molding.

The resultant chromium on silica-titania catalyst system must be of a certain porosity. The pore volume of the resultant catalyst system preferably is within a range of about 0.6 to about 1.4 milliliters per gram and preferably within a
15 range of about 0.7 to about 1.3 milliliters per gram. Most preferably, for best catalyst system activity and most improved polymer product properties, the pore volume of the catalyst system is within a range of 0.8 to 1.1 milliliters per gram. Higher pore volumes tend to give higher swell in the resin, and lower pore volumes destroy the activity of the catalyst system.

20 The surface area of the catalyst system must be within a range of about 100 m²/gram to about 500 m²/gram, preferably within a range of about 200 m²/gram to about 400 m²/gram. Most preferably, the surface area of the catalyst system, for best catalyst system productivity and best resultant polymer processing properties is within a range of 300 m²/gram to 400 m²/gram.

25 The resultant pore diameter is important because it can affect the amount of swell in the resin. As used here, the pore diameter is calculated by the equation: Pore diameter = 4(Pore Volume)/(Surface Area). The pore diameter must be from about 50 angstroms (Å) to about 150 Å, preferably between 60 Å and 140 Å, and most preferably between 70 Å and 120 Å.

30 Organoboron compounds used as promoters with the silica-titania chromium oxide catalyst systems of the invention can be expressed as BR₃, wherein each R is selected independently from hydrogen, alkyl, cycloalkyl and aryl, at least

- 7 -

one R in each compound being a hydrocarbon radical having from 1 to 12 carbon atoms, with the total number of carbon atoms not exceeding 30 in each compound. Examples of suitable boron promoters include trimethylborane, triethylborane, tri-n-dodecyl-borane, tricyclohexylborane, tri(2-methylcyclopentyl)borane,

5 triphenylborane, tribenzylborane, tri(2-ethylphenyl)borane, methyldiethylborane, and like compounds. Boron compounds such as diborane which can form an organoboron compound in-situ, on contact with the olefin monomer(s), also are suitable. Trialkylboranes presently are preferred because of their availability.

The amount of boron compound used is generally within a range of
10 about 0.1 to about 10 weight percent, based on the weight of the calcined catalyst system fed to the polymerization reactor. In a continuous particle form process using a loop reactor, for example, it is convenient to introduce the organoboron compound as a separate stream into the reactor, either continuously or in pulses, as a dilute solution in an inert hydrocarbon, e.g., 0.1 weight percent in isobutane. The
15 concentration of the organoboron compound also can be expressed in parts per million (ppm) based on the diluent used in the polymerization reactor. Weight percent ranges of organoboron compounds should be from about 0.1ppm to about 2 ppm organoboron compound, based on the amount of diluent charged in a continuous particle form process using a loop reactor. Preferably it should be from
20 0.3ppm to 1.5ppm, and most preferably it should be from 0.8ppm to 1.3ppm. Higher levels of the boron compound can generate more volatile components, and lower amounts do not give sufficiently high ESCR.

Reactants

Polymers produced in accordance with the process of this invention
25 are homopolymers of ethylene and copolymers of ethylene and higher alpha-olefin comonomers. Preferably, the ethylene concentration in the polymerization reactor is within a range of from about 2 weight percent to about 20 weight percent, based on the total liquid content of the reactor. Most preferably, the ethylene concentration in the polymerization reactor is within a range of from about 4 to about 15 weight
30 percent. Measured in another manner, ethylene concentration in the polymerization reactor flash gas is within a range of from about 2 weight percent to about 12 weight percent. Most preferably, the ethylene concentration in the polymerization

- 8 -

reactor flash gas is within a range of from about 3 to about 8 weight percent. Ethylene concentration in the reactor can significantly affect the molecular weight of the resultant polymer and also catalyst system activity.

Alpha-olefin comonomers used in the present invention can have
5 from 3 to 8 carbon atoms and are preferably selected from the group consisting of 1-butene, 1-hexene, and mixtures thereof in order to produce a copolymer with desirable properties as well as ease of use in a loop/slurry polymerization reaction process. The most preferred comonomer is 1-hexene to produce a copolymer with the best product properties. If a comonomer is present during polymerization, the
10 comonomer concentration in the polymerization reactor is within a range of from about 0.1 to about 10 weight percent. Most preferably, comonomer is present within a range of about 0.2 to about 2 weight percent.

Polymerization Process

Polymerization of the olefin monomer(s) must be carried out under
15 loop/slurry polymerization conditions wherein the temperature is kept below the temperature at which polymer swells. Such polymerization techniques are well known in the art and are disclosed, for instance, in Norwood, U.S. Patent No. 3,248,179, the disclosure of which is herein incorporated by reference. A light diluent, loop polymerization process is much more preferred than a stirred tank
20 reactor because a stirred tank cannot contain isobutane, which is necessary to produce other commercially popular high density polyethylene polymer product grades. A loop reactor also has an advantage in that isobutane diluent can be flashed off during polymer recovery, eliminating the necessity of separating polymer product from solvent. Additionally, the greater heat transfer surface of a loop
25 reactor offers much more versatility for plant operation, and often less polymer swelling during polymerization.

Polymerization reaction temperature in the reactor, or reaction zone, according to this invention, is critical and is dependant on the type of catalyst system employed. Polymerization reaction temperatures usually must be within a
30 range of about 200°F to about 230°F (93°C to 110°C), preferably within a range of about 210°F to about 225°F (99°C to 107°C). Most preferably, the reaction zone temperature is within a range of 210°F to 220°F (99°C to 104°C). Too high of a

- 9 -

reactor temperature can produce a polymer with too low of a molecular weight; or even to a fouled reactor. Too low of a reactor temperature can make the polymerization process inoperable because a lower reactor temperature can be difficult to maintain due to the exothermic polymerization reaction, flashing off reactor diluent can be difficult, and can produce a polymer with a commercially unacceptable high molecular weight.

Products

Polymers produced in accordance with this invention are homopolymers of ethylene and copolymers of ethylene and higher alpha-olefin comonomers. Polymers produced according to this invention are much more easily processed than polymers produced in accordance with different polymerization processes. The high load melt index (HLMI) usually is within a range of about 5g/10mins to about 25g/10mins, preferably within a range of about 8g/10mins to about 20g/10 minutes. Most preferably, the HLMI of the polymer product is within a range of 10g/10mins to 16g/10 mins. The HLMI/MI ratio of polymers produced in accordance with this invention is relatively high and usually is within a range of about 100 to about 250, preferably within a range of about 140 to about 230; most preferably the HLMI/MI ratio is within a range of 160 to 200.

These polymers also have a broad molecular weight distribution as evidenced by M_w/M_n . Usually the M_w/M_n ratio is within a range of about 15 to about 30, preferably within a range of about 15 to about 26. Most preferably the M_w/M_n ratio is within a range of 18 to 23. These polymers also have a very narrow density range, usually within a range of about 0.950 g/cc to about 0.960 g/cc. Preferably the density is within a range of about 0.952 g/cc to about 0.958 g/cc and most preferably the density is within a range of 0.953 g/cc to 0.957 g/cc.

Polymers produced in accordance with this invention also have a very high environmental stress crack resistance (ESCR). Generally, under Condition A, the ESCR is greater than about 400 hours, preferably greater than about 500 hours and most preferably the ESCR, condition A is greater than 600 hours. The modified Condition B ESCR usually is greater than about 50 hours, preferably greater than about 65 hours, and most preferably greater than 80 hours.

Polymers of this invention also have excellent processing

- 10 -

characteristics, as indicated by a high shear rate at the onset of melt fracture. The shear rate at onset of melt fracture is at least about 2000 sec^{-1} , preferably greater than about 2100 sec^{-1} , and most preferably greater than 2200 sec^{-1} . Polymers of this invention also have high output rates from a blow molding machine, at least 1200
5 grams per minute (g/min), preferably greater than 1300 g/min, and most preferably greater than 1350 g/min.

Polymers of this invention are characterized as having low swell characteristics, too. They usually exhibit less than about 42% diameter swell, preferably less than about 39%, and most preferably less than 35%. The weight
10 swell of polymers of this invention usually is less than about 380%, preferably less than about 350%, and most preferably less than 330%.

Polymers of this invention also are characterized as having a low volatile content, or smoke content. This means that they should contain less than 2% of their weight as oligomeric components having less than 1000 molecular
15 weight. Preferably, these polymers comprise less than about 1.6 weight % below 1000 MW, and most preferably these polymers comprise less than 1.4% material below 1000 in molecular weight. These polymers should also contain less than about 0.7% xylene solubles, preferably less than about 0.65%, and most preferably less than 0.6% xylene solubles.

20 The following examples are provided to further assist a person skilled in the art with understanding the invention. The particular reactants, conditions, and other variables are intended to be generally illustrative of these inventions and are not meant to be construed to the unduly limiting the reasonable scope of the invention.

25 EXAMPLES

Catalyst systems used for the production of the inventive resins, Runs
17 - 22, was a low porosity Cr/silica-titania commercially available from W.R. Grace Company as 965 Sylopore®. It contained 2.5 weight percent titanium as titania and originally 1.0 weight percent chromium. Sylopore® has a pore volume
30 of about 1.0 cc/g and a surface area of usually about $380 \text{ m}^2/\text{g}$. Specific measurements may be shown in the Tables that follow. In some Runs, both inventive Runs and control Runs, extra chromium was added through impregnation

- 11 -

of a 0.5% methanol solution of chromium nitrate, as indicated in the Tables.

Control resins were made from several other types of commercial catalyst systems commercially available from W.R. Grace. The catalyst 969MS (sometimes also referred to as 1%Cr on Grade 952 silica), used for Runs 1 - 10, had a pore volume of about 1.6 cc/g and a surface area around 300 m²/g.

Run 11 was made using a HA30 support, from W.R. Grace, having the properties listed in the Tables.

Runs 12 - 14, were made by a catalyst system described as chromium on HPVSA silica. This silica also was made by W.R. Grace and had a surface area of about 580 m²/g and a pore volume of about 2.2 cc/g.

Another silica support used in Runs 15 and 16, labeled HPV, had a pore volume of 2.5 cc/g and a surface area of 300 m²/g.

Some polymers, or resins, were made from 964 Magnapore®, Runs 23 - 34, and 963 Magnapore®, Runs 35 - 48, and which contained 1.0, 2.0 or 3.0 weight percent chromium on a high porosity silica-titania and either 2.5 or 5.0 weight percent titanium, as indicated. 964 Magnapore® has a pore volume of 2.3 cc/g and a surface area of 540 m²/g. 963 Magnapore® has a pore volume of 2.6 cc/g and a surface area of 520 m²/g.

The catalyst system used in Runs 49 - 61 was similar to 963 Magnapore®, but had only one (1) weight percent titania in the support.

Another catalyst system was used in Runs 62 - 64 and was prepared by W.R. Grace by depositing aluminophosphate (P/Al molar ratio of 0.6) into the pores of silica. This material had a pore volume of 1.3 cc/g and a surface area of 250 m²/g.

Ethylene polymers were prepared using these catalyst systems in a continuous particle form process (also known as a slurry loop process) by contacting a catalyst system with a ethylene and 1-hexene. The medium (diluent) and temperature thus were selected such that the copolymer was produced as solid particles and is recovered in that form. Ethylene that had been dried over activated alumina was used as the monomer.

The reactor was a liquid full 15.2 cm diameter pipe loop having a volume of 23 gallons (87 liters). Liquid isobutane, degassed by fractionation and

- 12 -

dried over alumina, was used as the diluent, and occasionally some hydrogen was added to regulate the molecular weight of the polymer product. The reactor pressure was about 3.8 MPa (about 580 psi). The reactor temperature was varied over the range of 180°F to 230°F (82°C to 110°C), as indicated in the Tables

5 below. The reactor was operated to have a residence time of 1.25 hours. Catalyst system was added through a 0.35 cc circulating ball-check feeder. At steady state conditions, the isobutane feed rate was about 46 liters per hour, the ethylene feed rate was about 30 lbs/hr, and the 1-hexene feed rate was varied to control the density of the polymer product. Catalyst system concentrations in the reactor can be

10 such that the catalyst system content ranges from 0.001 to about 1 weight percent, based on the weight of the reactor contents. Polymer was removed from the reactor at a rate of about 25 lbs per hour and recovered in a flash chamber. A Vulcan dryer was used to dry the polymer under nitrogen at about 60°C to about 80°C.

Cocatalysts triethylaluminum (TEA) and triethylboron (TEB) some-

15 times were added, as indicated in the Table below. To prevent static buildup in the reactor, a small amount (<5 ppm of diluent) of a commercial antistatic agent sold as Stadis 450 was usually added.

Density (g/ml): ASTM D 1505-68 and ASTM D 1928, Condition C. Determined on a compression molded sample, cooled at about 15 C per minute, and

20 conditioned at room temperature for about 40 hours.

High Load Melt Index (HLMI)(g/10 min): ASTM D1238, condition E. Determined at 190 C with a 21,600 gram weight.

Molecular Weight Distribution M_w/M_n : Molecular weights and molecular weight distributions were obtained using a Waters 150 CV gel permeation

25 chromatograph with trichlorobenzene (TCB) as the solvent, with a flow rate of 1 mL/minute at a temperature of 140 C. BHT (2,6-di-tert-butyl-4-methylphenol) at a concentration of 1.0 g/L was used as a stabilizer in the TCB. An injection volume of 220 L was used with a nominal polymer concentration of 0.3 g/l (at room temperature). Dissolution of the sample in stabilized TCB was carried out by

30 heating at 160-170 C for 20 hours with occasional, gentle agitation. The column was two Waters HT-6E columns (7.8x300mm). The columns were calibrated with a broad linear polyethylene standard (Phillips Marlex® BHB 5003) for which the

- 13 -

molecular weight had been determined. As a measure of volatile oligomeric components, or smoke, the amount of material found in the range of molecular weights from 100 to 1000 are listed in the table below.

5 Xylene solubles (%): ASTM D5494-94. A measurement of the amount of low molecular weight oligomers and thus, of the potential of the resin to smoke during processing.

A "Quantachrome Autosorb-6 Nitrogen Pore Size Distribution Instrument" was used to determined the surface area and pore volume of the supports. This instrument was acquired from the Quantachrome Corporation,
10 Syosset, N.Y.

Polymer resins obtained by this invention are useful for blow molding applications. In these examples blow molding evaluations were conducted by blowing a one gallon (105.0 + 0.5 gm) bottle on a Uniloy 2016 single head blow molding machine using a 2.5 inch diameter die, 20 degree diverging die, 32%
15 accumulator position, 8.5 second blow time, 0.10 second blow delay, 0.75 second pre-blow delay and a 45°F mold temperature. A reciprocating screw speed of 45 rpm was used, providing parison extrusion at shear rates greater than 10,000/sec⁻¹ through the die.

Three measurements of polymer processability during blow molding
20 were determined in the following three tests:

1-Minute Output. Describes the speed at which one part of the blow molding operation was accomplished. For this test, the extruder on the blow molding machine was set at 45 rpm and it was allowed to extrude resin for one full minute at the same die gap used to make the desired bottles. After 1 minute, the
25 test was stopped and extruded polymer was weighed to determine the 1-minute output value. This value provides an indication of the rate of extrusion of the polymer during the blow molding operation.

Processing Rating. A subjective rating given by the machine operator based on their unbiased observations during the test. Each resin was given a rating
30 of from 1 to 5, with 5 being the worst and 1 being the best. The operator considered such factors as head pressure, temperature, cycle time, pinch-off, and difficulties trimming.

- 14 -

Shear Rate at Melt Fracture. The onset of melt fracture of each resin was evaluated on the same Uniloy machine used in the previous two tests, by opening the die gap and extruding the resin. Shear rate was increased steadily by increasing the screw rpm. Onset of melt fracture was the rpm at which the parison showed visible signs of melt fracture, such as a shark skin appearance or a distorted rippled surface.

Percent Weight Swell. Measures the amount the molten resin expands immediately as the resin exits the die. Percent weight swell is a measure of the "memory" of polymer chains as the chains seek to relax and reform the original polymer shape. Weight swell is important because it measures how tightly the die gap must be adjusted to provide a constant bottle weight. If a resin has high weight swell, the die gap required will be tighter to make the proper part weight. In so doing, higher stress will be required to push the resin through the die than a lower weight swell resin. Weight swell is defined as the ratio of the die gap to the final bottle wall thickness.

Diameter Swell (Die Swell). The ratio of the parison diameter to the die diameter.

EXAMPLE 1

A total of 64 polymers were produced for this test in accordance with the above procedures. Information about the catalyst system, the polymerization reaction, and evaluation of the polymers are listed in Table 1 below.

Only the unique combination of catalyst system properties (pore diameter, activation temperature, Ti and Cr level) and reactor properties (TEB level) yields a polymer that is especially well suited to the desired blow molding operations. This is evidenced by the high level of ESCR, good processing characteristics (as indicated by the 1-minute output test, operator evaluations, and the shear at onset of melt fracture), and low volatile or smoke content (as indicated by the xylene solubles test, the amount of material found in the GPC molecular weight decade of 10^2 - 10^3 , i.e., less than 1000 molecular weight, and by the subjective odor rating given by the machine operator (5=worst, 1=best).

TABLE 1

Catalyst Characteristics						
Run Number	Support	Weight Percent Chromium	Weight Percent Titanium	Pore Volume cc/g	Surface Area m ² /g	Pore Radius Å
1	Silica	0.6	0.0	1.6	300	213
2	Silica	0.6	0.0	1.6	300	213
3	Silica	1.0	0.0	1.6	300	213
4	Silica	1.0	0.0	1.6	300	213
5	Silica	1.0	0.0	1.6	300	213
6	Silica	1.0	0.0	1.6	300	213
7	Silica	1.0	0.0	1.6	300	213
8	Silica	1.0	0.0	1.6	300	213
9	Silica	1.0	0.0	1.6	300	213
10	Silica	1.0	0.0	1.6	300	213
11	Silica	1.0	0.0	1.6	500	128
12	Silica	1.0	0.0	2.2	577	153
13	Silica	1.0	0.0	2.2	577	153
14	Silica	1.0	0.0	2.2	577	153
15	Silica	1.0	0.0	2.5	300	333
16	Silica	1.0	0.0	2.5	300	333
17	Silica-Titania	1.0	2.5	1.0	380	105
18	Silica-Titania	1.0	2.5	1.0	380	105

Catalyst Characteristics						
Run	Support	Weight Percent	Weight Percent	Pore	Surface	Pore
Number		Chromium	Titanium	Volume	Area	Radius
				cc/g	m ² /g	Å
19	Silica-Titania	1.0	2.5	1.0	380	105
20	Silica-Titania	1.0	2.5	1.0	380	105
21	Silica-Titania	1.0	2.5	1.0	380	105
22	Silica-Titania	2.0	2.5	1.0	380	105
23	Silica-Titania	1.0	5.0	2.3	540	170
24	Silica-Titania	1.0	5.0	2.3	540	170
25	Silica-Titania	2.0	5.0	2.3	540	170
26	Silica-Titania	2.0	5.0	2.3	540	170
27	Silica-Titania	2.0	5.0	2.3	540	170
28	Silica-Titania	2.0	5.0	2.3	540	170
29	Silica-Titania	2.0	5.0	2.3	540	170
30	Silica-Titania	2.0	5.0	2.3	540	170
31	Silica-Titania	2.0	5.0	2.3	540	170
32	Silica-Titania	3.0	5.0	2.3	540	170
33	Silica-Titania	3.0	5.0	2.3	540	170
34	Silica-Titania	3.0	5.0	2.3	540	170
35	Silica-Titania	2.0	2.5	2.6	520	200
36	Silica-Titania	2.0	2.5	2.6	520	200
37	Silica-Titania	2.0	2.5	2.6	520	200

Catalyst Characteristics						
Run Number	Support	Weight Percent Chromium	Weight Percent Titanium	Pore Volume cc/g	Surface Area m ² /g	Pore Radius Å
38	Silica-Titania	2.0	2.5	2.6	520	200
39	Silica-Titania	2.0	2.5	2.6	520	200
40	Silica-Titania	2.0	2.5	2.6	520	200
41	Silica-Titania	2.0	2.5	2.6	520	200
42	Silica-Titania	2.0	2.5	2.6	520	200
43	Silica-Titania	2.0	2.5	2.6	520	200
44	Silica-Titania	2.0	2.5	2.6	520	200
45	Silica-Titania	2.0	2.5	2.6	520	200
46	Silica-Titania	2.0	2.5	2.6	520	200
47	Silica-Titania	2.0	2.5	2.6	520	200
48	Silica-Titania	2.0	2.5	2.6	520	200
49	Silica-Titania	2.0	1.0	2.6	535	194
50	Silica-Titania	2.0	1.0	2.6	535	194
51	Silica-Titania	2.0	1.0	2.6	535	194
52	Silica-Titania	2.0	1.0	2.6	535	194
53	Silica-Titania	2.0	1.0	2.6	535	194
54	Silica-Titania	2.0	1.0	2.6	535	194
55	Silica-Titania	2.0	1.0	2.6	535	194
56	Silica-Titania	2.0	1.0	2.6	535	194

<i>Catalyst Characteristics</i>							
Run Number	Support	Weight Percent Chromium	Weight Percent Titanium	Pore Volume cc/g	Surface Area m ² /g	Pore Radius Å	
57	Silica-Titania	2.0	1.0	2.6	535	194	
58	Silica-Titania	2.0	1.0	2.6	535	194	
59	Silica-Titania	2.0	1.0	2.6	535	194	
60	Silica-Titania	2.0	1.0	2.6	535	194	
61	Silica-Titania	2.0	1.0	2.6	535	194	
62	Silica-AlPO ₄	1.0	0.0	1.3	250	208	
63	Silica-AlPO ₄	1.0	0.0	1.3	250	208	
64	Silica-AlPO ₄	1.0	0.0	1.3	250	208	

TABLE 2

Run Number	Reaction Conditions					Polymer Properties				
	Calcining Temp.	Reactor Temp.	Cocat. Type	Conc ppm	MI g/10 min	HLMI g/10 min	HLMI/MI	density g/mL	M _w /M _n	
	°F	°F								
1	1300	220	TBB	2.23	0.01	7.9	794	0.9526	16.8	
2	1300	221	TBB	1.77	0.02	9.0	452	0.9547	13.1	
3	1450	214	None	ND	0.30	30.0	100	0.9533	8.4	
4	1450	217	None	ND	0.41	37.6	91.6	0.9540	10.4	
5	1450	218	None	ND	0.31	31.5	102	0.9551	7.9	
6	1200	217	TBB	2.0	0.06	8.9	148	0.9545	16.4	
7	1200	220	TBB	2.0	0.05	11.8	236	0.9544	14.9	
8	1200	220	TBB	2.0	0.06	13.6	220	0.9546	14.4	
9	1300	222	TBB	1.0	0.07	11.4	1637	0.9536	8.4	
10	1300	222	TBB	1.0	0.09	14.3	159	0.9537	8.4	
11	1300	218	TBB	2.08	0.01	10.2	1040	0.9524	11.4	
12	1000	218	TBB	2.0	0.15	20.7	138	0.9539	17.5	
13	1000	217	TBB	2.0	0.14	19.3	138	0.9541	14.4	
14	1000	220	TBB	2.13	0.02	10.7	536	0.9539	20.0	
15	1200	217	TBB	2.0	0.06	12.4	207	0.9546	15.2	
16	1200	218	TBB	2.0	0.10	15.7	157	0.9544	14.2	
17	1100	211	TBB	1.0	0.14	19.8	141	0.9512	23.5	
18	1100	213	TBB	1.0	0.06	11.1	184	0.9532	19.4	

- 20 -

Run Number	Reaction Conditions					Polymer Properties				
	Calcining Temp.	Reactor Temp.	Cocat.	Conc	MI	HLMI	HLMI/MI	density	M _w /M _n	
	°F	°F	Type	ppm	g/10 min	g/10 min	g/10 min	g/mL	g/mL	
19	1100	214	TEB	1.0	0.07	12.8	182	0.9545	21.5	
20	1100	216	TEB	1.0	0.07	12.5	178	0.9530	17.2	
21	1100	218	TEB	1.0	0.05	11.5	230	0.9540	23.0	
22	1100	216	TEB	2.0	0.09	19.4	216	0.9552	24.1	
23	1000	210	TEB	2.0	0.17	28.7	169	0.9562	32.2	
24	1000	204	TEB	2.0	0.09	17.2	191	0.9567	38.8	
25	1100	216	TEA	2.0	0.12	16.7	139	0.9545	30.2	
26	1100	195	TEB	2.0	0.06	14.9	248	0.9545	41.9	
27	1100	203	TEB	2.0	0.18	32.5	180	0.9560	ND	
28	1100	203	TEB	2.0	0.15	27.4	183	0.9565	29.0	
29	1100	193	TEB	2.0	0.05	13.1	263	0.9544	35.1	
30	1000	203	TEB	2.0	0.11	21.0	191	0.9554	38.1	
31	1000	203	TEB	2.0	0.04	12.8	320	0.9581	37.2	
32	1000	199	TEB	2.0	0.08	17.8	222	0.9552	37.2	
33	1000	205	TEB	4.0	0.13	27.1	208	0.9561	35.6	
34	1000	197	TEB	4.0	0.06	17.4	291	0.9564	43.9	
35	1000	211	TEB	2.0	0.13	21.7	167	0.9544	25.6	
36	1000	210	TEB	2.0	0.11	19.2	174	0.9545	24.7	
37	1100	219	None	ND	0.23	20.1	87.2	0.9586	12.6	

Run Number	Reaction Conditions				Polymer Properties				
	Calcining Temp.	Reactor Temp.	Cocat. Type	Conc ppm	MI g/10 min	HLMI g/10 min	HLMI/MI	density	M _w /M _n
	°F	°F						g/mL	
38	1100	219	None	ND	0.32	23.6	73.8	0.9587	13.2
39	1100	219	TBA	ND	0.34	26.7	78.5	0.957	14.0
40	1100	218	TBA	2.0	0.11	12.5	113	0.9530	22.8
41	1100	219	TBA	2.0	0.15	17.0	113	0.9533	24.0
42	1100	208	TBB	2.0	0.09	17.2	191	0.9559	21.4
43	1100	219	TBB/A	2.0/0.5	0.19	25.4	134	0.9587	21.2
44	1100	219	TBB/A	1.4/0.3	0.21	26.4	126	0.9585	21.0
45	1100	219	TBB/A	1.9/0.5	0.22	24.8	113	0.9549	21.6
46	1100	219	TBB/A	2.3/2.3	0.15	21.8	146	0.9547	22.7
47	1100	219	TBB/A	2.0/2.0	0.35	33.5	95.7	0.9492	21.2
48	1200	206	TBB	2.05	0.05	12.5	250	0.9537	23.4
49	1100	220	TBB	1.83	0.04	11.9	299	0.9577	23.7
50	1100	219	TBB	1.94	0.07	15.2	217	0.9557	19.8
51	1100	219	TBB	1.89	0.06	13.7	228	0.9545	18.8
52	1200	220	TBB	2	0.12	19.7	164	0.956	22.8
53	1200	220	TBB	2.1	0.15	22.6	151	0.9569	20.8
54	1200	220	TBB	1.9	0.2	24.2	121	0.9562	17.5
55	1200	220	TBB	1.9	0.21	26.9	128	0.9569	18.5
56	1200	220	TBB	1.9	0.2	25.7	129	0.9568	18.1

- 22 -

Reaction Conditions					Polymer Properties				
Run	Calcining	Reactor	Cocat.	Conc	MI	HLMI	HLMI/MI	density	M _w /M _n
Number	Temp.	Temp.	Type	ppm	g/10 min	g/10 min	g/10 min	g/mL	
	°F	°F							
57	1200	220	TEB	2.1	0.19	24.9	131	0.9586	18.5
58	1200	220	TEB	2.1	0.16	22.8	142	0.9586	18.7
59	1200	218	TEB	2.02	0.07	14.3	204	0.9526	20.3
60	1200	220	TEB	1.96	0.02	10.8	540	0.9533	20.4
61	1200	213	TEB	2.01	0.02	10.3	514	0.9545	22.9
62	1300	212	TEB	1.94	0.08	18.2	228	0.9574	17.9
63	1300	214	TEB	2.15	0.04	13.7	342	0.9567	21.7
64	1300	219	TEB	1.84	0.1	21.9	219	0.9552	15.1

Note: TEB is Triethylboron; TEA is triethyl aluminum; and TEB/A is a combination of triethylboron and triethyl aluminum.

TABLE 3

Run Number	ESCR		Swell		Processing Character			Volatiles		
	Cond.	Cond.	Die	Weight	Process	Melt Fract.	1 min	Odor	Xylene	Wt. % MW Decade
	A	mod B	Swell	Swell	Rating	Shear	output	Rating	Solubles	10^2-10^3
	hours	hours	%	%	1 to 5	Rate	@ 7% g	1 to 5	%	(<1000MW)
1	104	48	30.4	246	3	1240	743	3	0.08	0.73
2	90	48	31.7	247	3	1250	752	3	0.12	0.61
3	115	115	42.9	399	2	1930	ND	3	0.22	0.00
4	42	<24	44.6	445	2	2440	1465	3	0.80	0.35
5	64	<24	46.7	405	2	2420	1454	2	0.12	0.33
6	361	82	32.4	312	2	2290	1378	2	ND	0.69
7	196	56	34.2	314	2	2350	1412	2	ND	0.81
8	234	44	38.0	314	2	2270	1364	2	ND	0.45
9	71	39	29.9	259	2	1440	865	2	0.20	0.01
10	60	37	30.4	263	2	1920	1154	2	0.08	0.01
11	408	139	36.7	293	2	1260	756	3	0.20	0.44
12	395	90	42.3	401	2	2460	1476	2	ND	0.94
13	395	73	45.4	375	2	2240	1348	2	ND	0.62
14	>1000	185	41.8	316	3	735	442	2	0.58	0.55
15	316	54	35.0	334	2	2370	1424	2	ND	0.65
16	248	61	41.3	349	2	2440	1465	2	ND	0.51
17	>1000	411	42.3	368	3	2350	1412	2	0.56	1.54

Run Number	ESCR		Swell		Processing Character			Volatiles		
	Cond.	Cond.	Die	Weight	Process	Melt Fract.	1 min	Odor	Xylene	Wt. % MW Decade
	A	mod B	Swell	Swell	Rating	Shear	output	Rating	Solubles	10^2-10^3
	hours	hours	%	%	1 to 5	Rate	@ 7% g	1 to 5	%	(<1000MW)
18	>1000	127	36.7	321	2	2300	1382	2	0.56	1.29
19	594	104	37.3	328	2	2310	1391	2	0.64	1.04
20	726	87	36.5	327	2	2350	1413	2	0.52	1.19
21	428	87	39.0	313	2	2230	1339	2	0.48	1.61
22	283	115	34.5	290	3	2360	ND	5	1.29	1.27
23	>1000	233	43.9	399	4	2290	ND	4	0.99	2.05
24	>1000	429	42.6	395	4	2200	ND	4	1.07	2.44
25	304	102	44.1	330	3	1620	976	3	0.75	2.83
26	>1000	170	43.9	434	4	2200	1321	3	1.12	3.73
27	>1000	86	39.3	450	3	2260	1359	3	1.59	ND
28	414	75	39.0	402	4	2320	1393	3	0.99	2.14
29	>1000	226	37.3	485	5	2170	1304	3	1.28	2.67
30	>1000	317	40.1	392	5	2160	ND	5	0.80	2.34
31	>1000	257	40.1	397	5	2210	ND	5	1.21	2.60
32	>1000	300	38.0	410	5	2190	ND	5	1.20	2.42
33	>1000	139	40.6	475	5	2180	ND	5	1.37	2.40
34	>1000	261	40.1	457	5	2170	ND	5	1.10	2.92
35	>1000	329	42.3	455	2	2260	1362	2	0.92	1.46

Run Number	BSCR		Swell		Processing Character			Volatiles		
	Cond.	Cond.	Die	Weight	Process	Melt Fract.	1 min	Odor	Xylene	Wt. % MW
	A	mod B	Swell	%	Rating	Shear	output	Rating	Solubles	Decade
	hours	hours	%	%	1 to 5	Rate	@ 7% g	1 to 5	%	(<1000MW)
36	>1000	241	46.4	436	3	2230	1339	3	0.96	1.97
37	209	45	51.0	353	3	1010	428	3	0.28	0.00
38	202	45	52.0	379	3	N/A	493	3	0.32	0.14
39	271	45	53.0	403	3	N/A	570	3	0.24	0.29
40	534	125	43.4	321	2	1110	669	2	0.56	1.53
41	400	85	45.1	325	2	1030	620	2	0.60	1.22
42	>1000	144	44.9	414	3	2230	1343	3	0.80	1.43
43	485	69	47.0	459	3	1870	1378	2	1.04	0.37
44	417	61	48.0	489	3	1890	1442	2	0.64	0.44
45	637	90	47.0	407	3	1660	973	2	0.40	0.73
46	500	110	46.0	409	3	1500	915	3	0.20	0.85
47	>1000	500	49.0	474	4	1640	1402	3	0.60	0.81
48	>1000	180	40.3	386	2	2090	1257	3	0.92	1.58
49	258	120	43.1	332	2	848	510	3	0.68	1.38
50	441	120	42.9	338	2	1180	711	3	0.56	0.91
51	564	139	41.3	330	2	496	599	3	0.52	0.74
52	321	76	45.0	404	3	1560	1125	3	0.52	0.66
53	329	78	44.0	392	3	1680	1009	3	0.48	0.44

Run Number	ESCR		Swell		Processing Character			Volatiles		
	Cond.	Cond.	Die	Weight	Process	Melt Fract.	1 min	Odor	Xylene	Wt. % MW
	A	mod B	Swell	Swell	Rating	Shear	output	Rating	Solubles	Decade
	hours	hours	%	%	1 to 5	Rate	@ 7% g	1 to 5	%	10 ² -10 ³ (<1000MW)
54	251	71	45.0	400	3	1910	991	3	0.60	0.33
55	373	56	45.0	429	3	1430	1182	3	0.76	0.49
56	378	69	46.0	412	3	1650	996	3	0.68	0.30
57	368	58	45.0	384	3	1640	948	3	0.64	0.31
58	346	56	46.0	389	3	1580	871	3	0.92	0.31
59	912	139	40.8	358	2	1820	1096	2	0.72	1.03
60	672	139	42.3	369	3	1490	898	2	0.40	1.08
61	>1000	146	40.8	317	3	777	467	2	0.64	1.22
62	131	48	35.2	332	2	2370	1425	2	0.52	1.09
63	131	48	35.2	322	2	2340	1410	2	0.66	1.38
64	112	48	36.7	326	2	2410	1451	3	0.68	0.89

- 27 -

By studying the data in Tables 1-3, it can be seen that ESCR is improved by high levels of TEB and Ti, which unfortunately also yields high volatiles or smoke. Swell is decreased by lowering the HLMI, which also makes processing more difficult, as indicated by lower values from the melt fracture and output tests. Swell is also decreased by increasing the activation temperature, but this also hurts ESCR. Notice also that the output test drops significantly if TEB is omitted, and the ESCR drops significantly if Ti is omitted. However, if TEB rises too much volatiles became a problem. Finally, notice also that swell becomes too high if the pore diameter increases much.

Thus the many opposing variables are uniquely balanced by the precise combination of conditions taught in this invention.

While this invention has been described in detail for the purpose of illustration, it is not to be construed as limited thereby but is intended to cover all changes and modifications within the spirit and scope thereof.

CLAIMS

1. A polymerization process comprising contacting under slurry polymerization conditions in an isobutane diluent at a temperature of from about 93.3°C to about 110°C (about 200°F to 230°F)
 - 5 a) ethylene monomer;
 - b) at least 1 mono-1-olefin comonomer having about three to eight carbon atoms per molecule;
 - c) a catalyst system comprising chromium supported on a silica-titania support, wherein said support comprises from about 0.5 to about 3 weight
10 percent titanium, based on the weight on the support, wherein said catalyst system has a average pore diameter from 50 to about 150 angstroms, and said catalyst system has been activated at a temperature within a range of about 1000°F to about 1200°F (about 538°C to about 649°C);
 - d) about 0.1 to about 2.0 mg/kg, based on the reactor diluent, of an
15 organoboron compound; and
 - e) recovering an ethylene/mono-1-olefin copolymer.
2. A process according to claim 1, wherein said organoboron compound is a trialkylboron compound.
3. A process according to claim 1, wherein said comonomer is selected
20 from the group consisting of propylene, 1-butene, 1-pentene, 1-hexene, 1-octene, and mixtures thereof.
4. A process according to claim 3, wherein said comonomer is 1-hexene.
5. A process according to claim 1, wherein said reactor temperature is
25 within a range of about 98.9°C to about 104.4°C (about 210°F to 220°F).
6. A process according to claim 1, wherein said titania of the silica-titania support is coprecipitated with the silica.
7. A process according to claim 1, wherein said catalyst system is aged twice and wherein the first aging is at a substantially neutral pH and wherein the
30 second aging is at an alkaline pH.
8. A process according to claim 2, wherein said trialkylboron cocatalyst is present in the reactor in an amount within a range of 0.3 to 1.3 mg/kg of diluent.



9. A composition comprising ethylene and a 1-hexene, wherein said copolymer has a high load melt index (HLMI) within a range of about 5 to about 25 g/10 minutes, a density within a range of about 0.95 to 0.96 g/cc, a shear response (HLMI/MI) is within a range of about 140 to about 230, a weight swell of less than about 350%, and a die swell within a range of about 30% to about 40%, an ESCR (Condition A) of greater than about 400 hours, a M_w/M_n of between about 15 and about 26, the onset of melt fracture of greater than about 2200 sec⁻¹, and 1-minute output test value of greater than 1300 grams per minute, xylene solubles of less than 0.65%, and less than 2.0% material of molecular weight less than 1000.

10. A composition according to claim 9, wherein the density is within the range of 0.952 to 0.958 g/cc.

11. A composition according to claim 10, wherein said high-load melt index is within a range of 10 to 16 grams/10 minutes.

12. A composition according to claim 10, wherein said shear response (HLMI/MI) is within a range of 160 to 200.

13. A composition prepared from a polymerization process comprising contacting under slurry polymerization conditions in an isobutane diluent at a temperature of from 98.8°C to 104.4°C (210°F to 220°F).

a) ethylene monomer;

b) 1-hexene;

c) a catalyst system comprising chromium supported on a silica-titania support, wherein said support comprises from about 0.5 to about 3 weight percent titanium, based on the weight on the support, wherein said catalyst system has a average pore diameter from 70 to about 120 angstroms, and said catalyst system has been activated at a temperature within a range of about 1000°F to about 1200°F (about 538°C to about 649°C);

d) about 0.3 to about 1.5 mg/kg, based on the reactor diluent, of a trialkylboron compound; and

e) recovering an ethylene/mono-1-olefin copolymer, and,

wherein said composition has a high load melt index (HLMI) within a range of about 5 to about 25 g/10 minutes, a density within a range of about 0.95 to 0.96 g/cc, a shear response (HLMI/MI) is within a range of about 140 to about



- 30 -

230, a weight swell of less than about 350%, and a die swell within a range of about 30% to about 40%, an ESCR (Condition A) of greater than about 400 hours, a M_w/M_n of between about 15 and about 26, the onset of melt fracture of greater than about 2200 sec-1, and 1-minute output test value of greater than 1300 grams
5 per minute, xylene solubles of less than 0.65%, and less than 2.0% material of molecular weight less than 1000.

