

(51) International Patent Classification:
C08F 4/6592 (2006.01)(21) International Application Number:
PCT/US2015/015130(22) International Filing Date:
10 February 2015 (10.02.2015)

(25) Filing Language: English

(26) Publication Language: English


(30) Priority Data:

61/938,466	11 February 2014 (11.02.2014)	US
61/938,472	11 February 2014 (11.02.2014)	US
61/981,291	18 April 2014 (18.04.2014)	US
61/985,151	28 April 2014 (28.04.2014)	US
62/032,383	1 August 2014 (01.08.2014)	US
61/087,911	5 December 2014 (05.12.2014)	US
62/087,914	5 December 2014 (05.12.2014)	US
62/088,196	5 December 2014 (05.12.2014)	US
62/087,905	5 December 2014 (05.12.2014)	US

(71) Applicant: **UNIVATION TECHNOLOGIES, LLC**
[US/US]; 5555 San Felipe, Suite 1950, Houston, TX
77056 (US).(72) Inventors: **RIX, Francis, C.**; 4015 Rusting Woods Court,
League City, TX 77059 (US). **TODD, Alexander, D.**; 203W. 39th Street, Austin, TX 78751 (US). **HARLAN, Jeff,**
C.; 15810 Dunmoor Dr., Houston, TX 77059 (US).(74) Agents: **LEAVITT, Kristina** et al.; Univation Technolo-
gies, LLC, 5555 San Felipe, Suite 1950, Houston, TX
77056 (US).(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY,
BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM,
DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT,
HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR,
KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG,
MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM,
PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC,
SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ,
TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU,
TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE,
DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU,
LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK,
SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, KM, ML, MR, NE, SN, TD, TG).

[Continued on next page]

(54) Title: PRODUCING POLYOLEFIN PRODUCTS

100
FIG. 1

(57) Abstract: Catalyst systems and methods for making and using the same. A method of methylating a catalyst composition while substantially normalizing the enantiomeric distribution is provided. The method includes slurrying the organometallic compound in dimethoxyethane (DME), and adding a solution of RMgBr in DME, wherein R is a methyl group or a benzyl group, and wherein the RMgBr is greater than about 2.3 equivalents relative to the organometallic compound. After the addition of the RMgBr, the slurry is mixed for at least about four hours. An alkylated organometallic is isolated, wherein the methylated species has a meso / rac ratio that is between about 0.9 and about 1.2.

Published:

- *without international search report and to be republished
upon receipt of that report (Rule 48.2(g))*