

Description**1. Field of the Invention:**

5 This invention relates to the use of a lubricant and surface conditioner for formed metal surfaces, and more particularly to the use of a lubricant and surface conditioner which improves the mobility of aluminum cans without adversely affecting the adhesion of paints or lacquers applied thereto.

2. Discussion of Related Art:

10 Aluminum cans are commonly used as containers for a wide variety of products. After their manufacture, the aluminum cans are typically washed with acidic cleaners to remove aluminum fines and other contaminants therefrom. Recently, environmental considerations and the possibility that residues remaining on the cans following acidic cleaning could influence the flavor of beverages packaged in the cans has led
15 to an interest in alkaline cleaning to remove such fines and contaminants. However, the treatment of aluminum cans generally results in differential rates of metal surface etch on the outside versus on the inside of the cans. For example, optimum conditions required to attain an aluminum fine-free surface on the inside of the cans usually leads to can mobility problems on conveyors because of the increased roughness on the outside can surface.

20 These aluminum can mobility problems are particularly apparent when it is attempted to convey the cans through single filers and to printers. Thus, a need has arisen in the aluminum can manufacturing industry to modify the coefficient of static friction on the outside surface of the cans to improve their mobility without adversely affecting the adhesion of paints or lacquers applied thereto. The reason for improving the mobility of aluminum cans is the general trend in this manufacturing industry to increase
25 production without additional capital investments in building new plants. The increased production demand is requiring can manufacturers to increase their line and printer speeds to produce 20 to 40 percent more cans per unit of time. For example, the maximum speed at which aluminum cans may be passed through a printing station typically is on the average of about 1150 cans per minute, whereas it is desired that such rate be increased to about 1400 to 1500 cans per minute or even higher.

30 However, thoroughly cleaned aluminum cans by either acid or alkaline cleaner are, in general, characterized by high surface roughness and thus have a high coefficient of static friction. This property hinders the flow of cans through single filers and printers when attempting to increase their line speed. As a result, printer misfeeding problems, frequent jammings, down time, and loss of production occur in addition to high rates of can spoilage.

35 Another consideration in modifying the surface properties of aluminum cans is the concern that such may interfere with or adversely affect the ability of the can to be printed when passed to a printing or labeling station. For example, after cleaning the cans, labels may be printed on their outside surface as well as lacquers may be sprayed on their inside surface. In such case, the adhesion of the paints and lacquers is of major concern.

40 Thus, it would be desirable to provide a means of improving the mobility of aluminum cans through filers and printers to increase production, reduce line jammings, minimize down time, and reduce can spoilage. Accordingly, it is an object of this invention to provide such means of improving the mobility of aluminum cans and to overcome the afore-noted problems.

3. Description of the Invention

45 The invention relates to the use of a composition consisting essentially of a solution of water and water-soluble ethoxylated organic material selected from the group consisting of ethoxylated fatty acids, salts of ethoxylated fatty acids, ethoxylated alcohols having at least 4 carbon atoms and containing up to 50 moles
50 of condensed ethylene oxide per mole of alcohol, ethoxylated alkyl alcohol phosphate esters, and mixtures thereof, said liquid lubricant and surface conditioner composition having a pH of between 1 and 6.5 as surface conditioner for aluminum cans.

The invention further relates to an aluminum can, at least one exterior surface of which is coated with a film formed from water-soluble ethoxylated organic material selected from the group consisting of ethoxylated fatty acids, salts of ethoxylated fatty acids, ethoxylated alcohols having at least 4 carbon atoms and
55 containing up to 50 moles of condensed ethylene oxide per mole of alcohol, ethoxylated alkyl alcohol phosphate esters, and mixtures thereof, the amount of film on said surface being sufficient to reduce the coefficient of static friction thereof.

In addition, the invention relates to a process of reducing the coefficient of static friction on at least one exterior surface of a cleaned aluminum can when conveyed comprising applying to said surface a liquid lubricant and surface conditioner composition according to claims 1 to 4 and drying said surface to form thereon a film and a process comprising the steps of cleaning an aluminum can with an aqueous acidic or alkaline cleaning solution, drying the cleaned can, and subsequently conveying the cleaned and dried can via automatic conveying equipment to a location where it is lacquered or decorated by printing or both, characterized in contacting at least one exterior surface of said aluminum can, prior to the last drying of said exterior surface before automatic conveying, with a lubricant and surface conditioner composition according to claims 1 to 4, thereby forming a film on the can surface to provide the surface of the can after drying with a coefficient of static friction that is not more than 1.5 and that is less than would be obtained on a can surface of the same type without such film coating.

Other than in the operating examples, or where otherwise indicated, all numbers expressing quantities of ingredients or reaction conditions used herein are to be understood as modified in all instances by the term "about".

In accordance with this invention, it has been found that a lubricant and surface conditioner applied to aluminum cans after washing enhances their mobility. The lubricant and surface conditioner reduces the coefficient of static friction on the outside surface of the cans, and enables a substantial increase in production line speeds.

More particularly, in accordance with this invention, it has been found that application of a thin organic film to the outside surface of aluminum cans serves as a lubricant inducing thereto a lower coefficient of static friction, and consequently providing an improved mobility to the cans. It has also been found that the improved mobility of the cans depends on the thickness or amount of the organic film, and on the chemical nature of the material applied to the cans.

The lubricant and surface conditioner for aluminum cans in accordance with this invention may be selected from water-soluble organic phosphate esters; alcohols; fatty acids including mono-, di-, tri-, and poly-acids; fatty acid derivatives such as salts, hydroxy acids, amides, esters, ethers and derivatives thereof; and mixtures thereof.

The lubricant and surface conditioner for aluminum cans in accordance with this invention preferably comprises a water-soluble derivative of a saturated fatty acid such as an ethoxylated stearic acid or an ethoxylated isostearic acid, or alkali metal salts thereof such as polyoxyethylated stearate and polyoxyethylated isostearate. In addition, the lubricant and surface conditioner for aluminum cans may comprise a water-soluble alcohol having at least about 4 carbon atoms reacted with up to about 50 moles of ethylene oxide. Excellent results have been obtained when the alcohol comprises polyoxyethylated oleyl alcohol containing an average of about 20 moles of ethylene oxide per mole of alcohol.

Further, the lubricant and surface conditioner for aluminum cans in accordance with this invention may preferably comprise a phosphate acid ester or an ethoxylated alkyl alcohol phosphate ester. Such phosphate esters are commercially available under the tradename Gafac® PE 510 from GAF Corporation, Wayne, New Jersey, and as Ethfac® 136 and Ethfac® 161 from Ethox Chemicals, Inc., Greenville, S.C. In general, the organic phosphate esters may comprise alkyl and aryl phosphate esters with and without ethoxylation.

The lubricant and surface conditioner for aluminum cans may be applied to the cans during their wash cycle, during one of their treatment cycles, during one of their water rinse cycles, or more preferably, during their final water rinse cycle. In addition, the lubricant and surface conditioner may be applied to the cans after their final water rinse cycle, i.e., prior to oven drying, or after oven drying, by fine mist application from water or volatile non-inflammable solvent solution. It has been found that the lubricant and surface conditioner is capable of depositing on the aluminum surface of the cans to provide them with the desired characteristics. The lubricant and surface conditioner may be applied by spraying and reacts with the aluminum surface through chemisorption or physisorption to provide it with the desired film.

Generally, in the cleaning process of the cans, after the cans have been washed, they are typically exposed to an acidic water rinse. In accordance with this invention the cans may thereafter be treated with a lubricant and surface conditioner comprising an anionic surfactant such as a phosphate acid ester. In such case, the pH of the treatment system is important and generally should be acidic, that is between about 1 and about 6.5, preferably between about 2.5 and about 5. If the cans are not treated with the lubricant and surface conditioner of this invention after the acidic water rinse, the cans are exposed to a tap water rinse and then to a deionized water rinse. In such event, the deionized water rinse solution is prepared to contain the lubricant and surface conditioner of this invention which may comprise a nonionic surfactant selected from the afore-mentioned polyoxyethylated alcohols or polyoxylated fatty acids. After such treatment, the cans may be passed to an oven for drying prior to further processing.

The amount of lubricant and surface conditioner to be applied to the cans should be sufficient to reduce the coefficient of static friction on the outside surface of the cans to a value of about 1.5 or lower, and preferably to a value of about 1 or lower. Generally speaking, such amount should be of the order of from about 3 mg/m² to about 60 mg/m² of lubricant and surface conditioner on the outside surface of the cans.

For a fuller understanding of the invention, reference should be made to the following examples which are intended to be merely descriptive, illustrative, and not limiting as to the scope of the invention.

EXAMPLE I

This example illustrates the amount of aluminum can lubricant and surface conditioner necessary to improve their free mobility through the tracks and printing stations of an industrial can manufacturing facility, and also shows that the lubricant and surface conditioner does not have an adverse effect on the adhesion of labels printed on the outside surface as well as of lacquers sprayed on the inside surface of the cans.

Uncleaned aluminum cans obtained from an industrial can manufacturer were washed clean with an alkaline cleaner available from the Amchem Products Division, Henkel Corporation, Ambler, PA employing that company's Ridoline® 3060/306 process. The cans were washed in a laboratory miniwasher processing 14 cans at a time. The cans were treated with different amounts of lubricant and surface conditioner in the final rinse stage of the washer and then dried in an oven. The lubricant and surface conditioner comprised about a 10% active concentrate of polyoxyethylated isostearate, an ethoxylated nonionic surfactant, available under the tradename Ethox MI-14 from Ethox Chemicals, Inc., Greenville, S.C. The treated cans were returned to the can manufacturer for line speed and printing quality evaluations. The printed cans were divided into two groups, each consisting of 4 to 6 cans. All were subjected for 20 minutes to one of the following adhesion test solutions:

Test Solution A; 1% Joy® (a commercial liquid dishwashing detergent, Proctor and Gamble Co.) solution in 3:1 deionized water: tap water at a temperature of 82 °C (180 °F).

Test Solution B; 1% Joy® detergent solution in deionized water at a temperature of 100 °C (212 °F).

After removing the printed cans from the adhesion test solution, each can was cross-hatched using a sharp metal object to expose lines of aluminum which showed through the paint or lacquer, and tested for paint adhesion. This test included applying Scotch (Scotch is a registered trademark of the 3M Company) transparent tape No. 610 firmly over the cross-hatched area and then drawing the tape back against itself with a rapid pulling motion such that the tape was pulled away from the cross-hatched area. The results of the test were rated as follows: 10, perfect, when the tape did not peel any paint from the surface; 8, acceptable; and 0, total failure. The cans were visually examined for any print or lacquer pick-off signs.

In addition, the cans were evaluated for their coefficient of static friction using a laboratory static friction tester. This device measures the static friction associated with the surface characteristics of aluminum cans. This is done by using a ramp which is raised through an arc of 90 ° by using a constant speed motor, a spool and a cable attached to the free swinging end of the ramp. A cradle attached to the bottom of the ramp is used to hold 2 cans in horizontal position approximately 0.5 inches apart with the domes facing the fixed end of the ramp. A third can is laid upon the 2 cans with the dome facing the free swinging end of the ramp, and the edges of all 3 cans are aligned so that they are even with each other.

As the ramp begins to move through its arc a timer is automatically actuated. When the ramp reaches the angle at which the third can slides freely from the 2 lower cans, a photoelectric switch shuts off the timer. It is this time, recorded in seconds, which is commonly referred to as "slip time". The coefficient of static friction is equal to the tangent of the angle swept by the ramp at the time the can begins to move.

The average values for the adhesion test and coefficient of static friction evaluation results are summarized in Table 1 which follows:

Table 1

Test No.	Lubricant and Surface Conditioner Concentrate (%/vol.)	Adhesion Evaluation				Coefficient of Static Friction
		Test Solution	OSW	ISW	ID	
1	Control(no treatment)	-	-	-	-	1.422
2	0.1	B	10	10	10	0.941
3	0.25	A	10	10	10	-
4	0.5	B	9.5*	10	10	0.801
5	0.75	A	10	10	10	0.630
6	1.0	B	10	10	10	0.643
7	2.0	A	10	10	10	0.566
8	5.0	B	10	10	10	0.547
9	10.0	A	9.8*	10	10	0.560

* Little pick-off was visually noticed on the outside walls, mainly at the contact marks. In Table 1, OSW stands for outside sidewall, ISW stands for inside sidewall, and ID stands for inside dome.

In brief, it was found that the lubricant and surface conditioner concentrate as applied to the cleaned aluminum cans provided improved free mobility to the cans even at very low use concentrations, and it had no adverse effect on either adhesion of label print or internal lacquer tested even at 20 to 100 times the required use concentration to reduce the coefficient of static friction of the cans.

EXAMPLE II

This example illustrates the use of the aluminum can lubricant and surface conditioner of Example I in an industrial can manufacturing facility when passing cans through a printing station at the rate of 1260 cans per minute.

Aluminum can production was washed with an acidic cleaner (Ridoline® 125 CO, available from Amchem Products, Inc., Ambler, PA), and then treated with a non-chromate conversion coating (Alodine® 404). The aluminum can production was then tested for "slip" and the exterior of the cans were found to have a static coefficient of friction of about 1.63. During processing of these cans through a printer station, the cans could be run through the printer station at the rate of 1150 to 1200 cans per minute without excessive "trips", i.e., improperly loaded can events. In such case, the cans are not properly loaded on the mandrel where they are printed. Each "trip" causes a loss of cans which have to be discarded because they are not acceptable for final stage processing.

About 1 ml/liter of aluminum can lubricant and surface conditioner was added to the deionized rinse water system of the can washer which provided a reduction of the static coefficient of friction on the exterior of the cans to a value of 1.46 or a reduction of about 11 percent from their original value. After passing the cans through the printer, it was found that the adhesion of both the interior and exterior coatings were unaffected by the lubricant and surface conditioner. In addition, the printer speed could be increased to its mechanical limit of 1250 to 1260 cans per minute without new problems.

In similar fashion, by increasing the concentration of the aluminum can lubricant and surface conditioner to the deionized rinse water system, it was possible to reduce the coefficient of static friction of the cans by 20 percent without adversely affecting the adhesion of the interior and exterior coatings of the cans. Further, it was possible to maintain the printer speed continuously at 1250 cans per minute for a 24 hour test period.

EXAMPLE III

This example illustrates the use of other materials as the basic component for the aluminum can lubricant and surface conditioner.

Aluminum cans were cleaned with an alkaline cleaner solution having a pH of about 12 at about 41 °C (105 °F) for about 35 seconds. The cans were rinsed, and then treated with three different lubricant and surface conditioners comprising various phosphate ester solutions. Phosphate ester solution 1 comprised a phosphate acid ester (available under the tradename Gafac® PE 510 from GAF Corporation, Wayne, New Jersey) at a concentration of 0.5 g/l. Phosphate ester solution 2 comprised an ethoxylated alkyl alcohol

phosphate ester (available under the tradename Ethfac® 161 from Ethox Chemicals, Inc., Greenville, S.C.) at a concentration of 0.5 g/l. Phosphate ester solution 3 comprised an ethoxylated alkyl alcohol phosphate ester (available under the tradename Ethfac® 136 from Ethox Chemicals, Inc., Greenville, S.C.) at a concentration of 1.5 g/l.

The mobility of the cans in terms of coefficient of static friction was evaluated and found to be as follows:

Phosphate ester solution	pH	Coefficient of static friction
1	3.6	0.476
2	3.3	0.630
3	2.6	0.770

The aforementioned phosphate ester solutions all provided an acceptable mobility to aluminum cans, but the cans were completely covered with "water-break". It is desired that the cans be free of water-breaks, i.e., have a thin, continuous film of water thereon, because otherwise they contain large water droplets, and the water film is non-uniform and discontinuous. To determine whether such is detrimental to printing of the cans, they were evaluated for adhesion. That is, the decorated cans were cut open and boiled in a 1% liquid dishwashing detergent solution (Joy®) comprising 3:1 deionized water: tap water for ten minutes. The cans were then rinsed in deionized water and dried. As in Example I, eight cross-hatched scribe lines were cut into the coating of the cans on the inside and outside sidewalls and the inside dome. The scribe lines were taped over, and then the tape was snapped off. The cans were rated for adhesion values. The average value results are summarized in Table 2.

Table 2

Adhesion Rating			
Phosphate ester Solution	OSW	ISW	ID
control	10	10	10
1	9.8	6.8	1.0
2	9.8	10	10
3	10	10	10

In Table 2, OSW stands for outside sidewall, ISW stands for inside sidewall, and ID stands for inside dome.

For the control, it was observed that there was no pick-off (loss of coating adhesion) on either the outside sidewall, the inside sidewall or the inside dome of the cans.

For phosphate ester solution 1, it was observed that there was almost no pick-off on the outside sidewall, substantial pick-off on the inside sidewall, and complete failure on the inside dome of the cans.

For phosphate ester solution 2, it was observed that there was almost no pick-off on the outside sidewall, and no pick-off on the inside sidewall and no pick-off on the inside dome of the cans.

For phosphate ester solution 3, it was observed that there was no pick-off on the outside sidewall, the inside sidewall, and the inside dome of the cans.

Claims

1. Use of a composition consisting essentially of a solution of water and water-soluble ethoxylated organic material selected from the group consisting of ethoxylated fatty acids, salts of ethoxylated fatty acids, ethoxylated alcohols having at least 4 carbon atoms and containing up to 50 moles of condensed ethylene oxide per mole of alcohol, ethoxylated alkyl alcohol phosphate esters, and mixtures thereof, said liquid lubricant and surface conditioner composition having a pH of between 1 and 6.5 as surface conditioner for aluminum cans.
2. Use according to claim 1 wherein the pH is between 2.5 and 5.



phosphate ester (available under the tradename Ethfac® 161 from Ethox Chemicals, Inc., Greenville, S.C.) at a concentration of 0.5 g/l. Phosphate ester solution 3 comprised an ethoxylated alkyl alcohol phosphate ester (available under the tradename Ethfac® 136 from Ethox Chemicals, Inc., Greenville, S.C.) at a concentration of 1.5 g/l.

The mobility of the cans in terms of coefficient of static friction was evaluated and found to be as follows:

Phosphate ester solution	pH	Coefficient of static friction
1	3.6	0.476
2	3.3	0.630
3	2.6	0.770

The aforementioned phosphate ester solutions all provided an acceptable mobility to aluminum cans, but the cans were completely covered with "water-break". It is desired that the cans be free of water-breaks, i.e., have a thin, continuous film of water thereon, because otherwise they contain large water droplets, and the water film is non-uniform and discontinuous. To determine whether such is detrimental to printing of the cans, they were evaluated for adhesion. That is, the decorated cans were cut open and boiled in a 1% liquid diswashing detergent solution (Joy®) comprising 3:1 deionized water: tap water for ten minutes. The cans were then rinsed in deionized water and dried. As in Example 1, eight cross-hatched scribe lines were cut into the coating of the cans on the inside and outside sidewalls and the inside dome. The scribe lines were taped over, and then the tape was snapped off. The cans were rated for adhesion values. The average value results are summarized in Table 2.

Table 2

Adhesion Rating			
Phosphate ester Solution	OSW	ISW	ID
control	10	10	10
1	9.8	6.8	1.0
2	9.8	10	10
3	10	10	10

In Table 2, OSW stands for outside sidewall, ISW stands for inside sidewall, and ID stands for inside dome.

For the control, it was observed that there was no pick-off (loss of coating adhesion) on either the outside sidewall, the inside sidewall or the inside dome of the cans.

For phosphate ester solution 1, it was observed that there was almost no pick-off on the outside sidewall, substantial pick-off on the inside sidewall, and complete failure on the inside dome of the cans.

For phosphate ester solution 2, it was observed that there was almost no pick-off on the outside sidewall, and no pick-off on the inside sidewall and no pick-off on the inside dome of the cans.

For phosphate ester solution 3, it was observed that there was no pick-off on the outside sidewall, the inside sidewall, and the inside dome of the cans.

Claims

1. Use of a composition consisting essentially of a solution of water and water-soluble ethoxylated organic material selected from the group consisting of ethoxylated fatty acids, salts of ethoxylated fatty acids, ethoxylated alcohols having at least 4 carbon atoms and containing up to 50 moles of condensed ethylene oxide per mole of alcohol, ethoxylated alkyl alcohol phosphate esters, and mixtures thereof, said liquid lubricant and surface conditioner composition having a pH of between 1 and 6.5 as surface conditioner for aluminum cans.
2. Use according to claim 1 wherein the pH is between 2.5 and 5.



3. Use according to claim 1 wherein the ethoxylated fatty acid is stearic acid or isostearic acid.
4. Use according to claims 1 to 3 wherein said water is deionized water.
5. An aluminum can, at least one exterior surface of which is coated with a film formed from water-soluble ethoxylated organic material selected from the group consisting of ethoxylated fatty acids, salts of ethoxylated fatty acids, ethoxylated alcohols having at least 4 carbon atoms and containing up to 50 moles of condensed ethylene oxide per mole of alcohol, ethoxylated alkyl alcohol phosphate esters, and mixtures thereof, the amount of film on said surface being sufficient to reduce the coefficient of static friction thereof.
6. An aluminum can according to claim 5 wherein the coated surface has a coefficient of static friction of 1.5 or below.
7. An aluminum can according to claim 6 wherein the surface is coated with from 3 to 60 mg/m² of said film.
8. A process of reducing the coefficient of static friction on at least one exterior surface of a cleaned aluminum can when conveyed comprising applying to said surface a liquid lubricant and surface conditioner composition according to claims 1 to 4 and drying said surface to form thereon a film.
9. A process according to claim 8 wherein the film coated surface of the can is subsequently printed, lacquered, or both without a substantial reduction in the adherence of the printing or lacquer to the surface.
10. A process comprising the steps of cleaning an aluminum can with an aqueous acidic or alkaline cleaning solution, drying the cleaned can, and subsequently conveying the cleaned and dried can via automatic conveying equipment to a location where it is lacquered or decorated by printing or both, characterized in contacting at least one exterior surface of said aluminum can, prior to the last drying of said exterior surface before automatic conveying, with a lubricant and surface conditioner composition according to claims 1 to 4, thereby forming a film on the can surface to provide the surface of the can after drying with a coefficient of static friction that is not more than 1.5 and that is less than would be obtained on a can surface of the same type without such film coating.
11. A process according to claim 10 comprising at least one additional step selected from the group consisting of:
 - (A) decorating by printing at least a part of the coated surface so as to obtain a dried printing having an adhesion to the can not significantly less than obtained on the same, but uncoated, surface;
 - (B) lacquering at least a part of the coated surface so as to obtain a dried lacquer coat having an adhesion to the can not significantly less than obtained on the same, but uncoated, surface; and
 - (C) a combination of steps (A) and (B) being applied to separate portions of the coated surface.

Patentansprüche

1. Verwendung einer Zusammensetzung, bestehend im wesentlichen aus einer Lösung aus Wasser und wasserlöslichem ethoxylierten organischen Material, ausgewählt aus der Gruppe bestehend aus ethoxylierten Fettsäuren, Salzen ethoxylierter Fettsäuren, ethoxylierten Alkoholen mit wenigstens 4 Kohlenstoff-Atomen und enthaltend bis zu 50 mol kondensiertes Ethylenoxid pro Mol Alkohol, ethoxylierten Alkylalkolphosphatestern und Mischungen derselben, wobei die flüssige Gleitmittel- und Oberflächenvorbehandlungsmittelzusammensetzung einen pH zwischen 1 und 6,5 aufweist, als oberflächenvorbehandlungsmittel für Aluminium Dosen.
2. Verwendung nach Anspruch 1, wobei der pH zwischen 2,5 und 5 ist.
3. Verwendung nach Anspruch 1, wobei die ethoxylierte Fettsäure Stearinsäure oder Isostearinsäure ist.
4. Verwendung nach den Ansprüchen 1 bis 3, wobei das Wasser deionisiertes Wasser ist.



5. Aluminiumdose, bei der wenigstens eine äußere Oberfläche mit einem Film beschichtet ist, gebildet aus wasserlöslichem ethoxylierten organischen Material, ausgewählt aus der Gruppe bestehend aus ethoxylierten Fettsäuren, Salzen ethoxylierter Fettsäuren, ethoxylierten Alkoholen mit wenigstens 4 Kohlenstoff-Atomen und enthaltend bis zu 50 mol kondensiertes Ethylenoxid pro Mol Alkohol, ethoxylierten Alkylalkoholphosphatestern und Mischungen derselben, wobei die Menge an Film auf der Oberfläche ausreicht, um deren statischen Reibungskoeffizienten herabzusetzen.
6. Aluminiumdose nach Anspruch 5, wobei die beschichtete Oberfläche einen statischen Reibungskoeffizienten von 1,5 oder darunter aufweist.
7. Aluminiumdose nach Anspruch 6, wobei die Oberfläche mit 3 bis 60 mg/m² des Films beschichtet ist.
8. Verfahren zur Verminderung des statischen Reibungskoeffizienten wenigstens einer äußeren Oberfläche einer gereinigten Aluminiumdose beim Transport, umfassend das Aufbringen einer flüssigen Gleitmittel- und Oberflächenvorbehandlungsmittelzusammensetzung nach den Ansprüchen 1 bis 4 auf die Oberfläche und Trocknen der Oberfläche, um darauf einen Film zu bilden.
9. Verfahren nach Anspruch 8, wobei die filmbeschichtete Oberfläche der Dose anschließend bedruckt, lackiert wird oder beides ohne wesentliche Minderung der Haftung des Drucks oder des Lacks an der Oberfläche.
10. Verfahren, umfassend die Schritte der Reinigung einer Aluminiumdose mit einer sauren oder alkalischen wässrigen Reinigungslösung, Trocknen der gereinigten Dose, und anschließend Transportieren der gereinigten und getrockneten Dose über eine automatische Fördereinrichtung an einen Ort, wo sie lackiert oder durch Drucken dekoriert wird oder beides, gekennzeichnet durch Zusammenbringen wenigstens einer äußeren Oberfläche der Aluminiumdose vor dem letzten Trocknen der äußeren Oberfläche vor dem automatischen Transport mit einer Gleitmittel- und Oberflächenvorbehandlungsmittelzusammensetzung nach den Ansprüchen 1 bis 4, wodurch sich ein Film auf der Dosenoberfläche bildet, um die Oberfläche der Dose nach dem Trocknen mit einem statischen Reibungskoeffizienten zu versehen, der nicht höher als 1,5 ist, und der niedriger ist als der, der auf einer Dosenoberfläche des gleichen Typs ohne derartige Filmbeschichtung erhalten werden würde.
11. Verfahren nach Anspruch 10, umfassend wenigstens einen zusätzlichen schritt, ausgewählt aus der Gruppe bestehend aus:
 - (A) Dekorieren wenigstens eines Teils der beschichteten Oberfläche durch Bedrucken, um einen getrockneten Druck zu erhalten, der eine Haftung an der Dose aufweist, die nicht merklich geringer ist als die auf der gleichen, aber unbeschichteten Oberfläche erzielte;
 - (B) Lackieren wenigstens eines Teils der beschichteten Oberfläche, um einen getrockneten Lacküberzug zu erhalten, der eine Haftung an der Dose aufweist, die nicht merklich geringer ist als die auf der gleichen, aber unbeschichteten Oberfläche erzielte,
 - (C) eine Kombination der Schritte (A) und (B), angewandt auf verschiedene Stellen der beschichteten Oberfläche.

Revendications

1. Utilisation d'une composition comprenant essentiellement une solution d'eau et d'une matière organique éthoxylée soluble dans l'eau, choisie dans le groupe formé d'acides gras éthoxylés, de sels d'acides gras éthoxylés, d'alcools éthoxylés ayant au moins 4 atomes de carbone et contenant jusqu'à 50 moles d'oxyde d'éthylène condensé par mole d'alcool, d'esters phosphates d'alcool alkylique éthoxylés, et de mélanges de ceux-ci, ladite composition liquide, lubrifiante et de conditionnement de surface, ayant un pH entre 1 et 6,5, comme conditionneur de surface pour boîtes d'aluminium.
2. Utilisation selon la revendication 1, dans laquelle le pH se situe entre 2,5 et 5.
3. Utilisation selon la revendication 1, dans laquelle l'acide gras éthoxylé est l'acide stéarique ou l'acide isostéarique.
4. Utilisation selon les revendications 1 à 3, dans laquelle l'eau est de l'eau désionisée.



5. Boîte d'aluminium, dont au moins une surface externe est revêtue d'une pellicule formée d'une matière organique éthoxylée soluble dans l'eau, choisie dans le groupe formé d'acides gras éthoxylés, de sels d'acides gras éthoxylés, d'alcools éthoxylés ayant au moins 4 atomes de carbone et contenant jusqu'à 50 modes d'oxyde d'éthylène condensé par mode d'alcool, d'esters phosphates d'alcool alkylique éthoxylés et des mélanges de ceux-ci, la quantité de la pellicule sur la surface étant suffisante pour réduire son coefficient de frottement statique.
6. Boîte d'aluminium selon la revendication 5, dans laquelle la surface revêtue a un coefficient de frottement statique de 1,5 ou moins.
7. Boîte d'aluminium selon la revendication 6, dans laquelle la surface est revêtue de 3 à 60 mg/m² de la pellicule.
8. Procédé pour réduire le coefficient de frottement statique sur au moins une surface externe d'une boîte d'aluminium nettoyée, alors qu'elle est transportée, comprenant l'application sur la surface d'une composition liquide, lubrifiante et de conditionnement de surface selon des revendications 1 à 4, et à sécher la surface pour y former une pellicule.
9. Procédé selon la revendication 8, dans lequel la surface de la boîte revêtue de la pellicule est ensuite imprimée, vernie ou des deux, sans réduction substantielle de l'adhérence de l'impression ou du vernis sur la surface.
10. Procédé comprenant des étapes consistant à nettoyer une boîte d'aluminium avec une solution de nettoyage aqueuse acide ou alcaline, à sécher la boîte nettoyée, et ensuite à transporter la boîte nettoyée et séchée via une installation de transport automatique, jusqu'à un endroit où elle est vernie ou décorée par impression, ou les deux, caractérisé en ce qu'il consiste à mettre en contact au moins une surface externe de la boîte d'aluminium, avant le dernier séchage de la surface externe avant le transport automatique, avec une composition lubrifiante et de conditionnement de surface selon les revendications 1 à 4, formant ainsi une pellicule sur la surface de la boîte, pour donner à la surface de la boîte après séchage un coefficient de frottement statique n'excédant pas 1,5 et inférieur à ce qui serait obtenu sur une surface de boîte du même type, sans cette pellicule de revêtement.
11. Procédé selon la revendication 10, comprenant au moins une étape supplémentaire choisie dans le groupe de:
- (A) décoration par impression d'au moins une partie de la surface revêtue de façon à obtenir une impression séchée ayant vis-a-vis de la boîte une adhérence pas significativement inférieure à celle obtenue sur la même surface, non revêtue;
 - (B) vernissage d'au moins une partie de la surface revêtue de façon à obtenir un vernis séché présentant vis-a-vis de la boîte une adhérence pas significativement inférieure à celle obtenue sur la même surface non revêtue; et
 - (C) une combinaison des étapes (A) et (B) appliquées à des parties différentes de la surface revêtue.