REPLACED SHEETS SG
☑ Description : paged 1 to paged 15
☑ Claim(s) : paged 16 to paged 22
☑ Drawing(s) : paged 14 to paged 14
☐ Abstract : paged 23 to paged .....

EN991-111

DESIGN OF HIGH DENSITY STRUCTURES WITH LASER ETCH STOP

Field of the Invention

The present invention relates to multi-layer circuit packages having laser drilled blind vias between internal circuitization planes for the purpose of electrical interconnection.

Background of the Invention

In the fabrication of multi-layer circuit boards and cards, it is necessary to form passages such as vias and through holes from one layer of the structure to a deeper layer. Such passages may be formed mechanically, chemically or by using lasers of various wavelengths to vaporize or burn away the circuit board material. Blind vias are passages that do not pass completely through a board or card. After formation of a blind via, material, such as a metal, may be deposited on the surface of the via to provide an electrical, power, or ground connection between the two layers connected to the via. In other words, the blind vias may be formed for plating of joining metallurgy which provides the inter-electrical connections within the multi-layer structure.

Lasers are commonly used to drill blind vias through the

This Sheet Has Been Replaced

insulating polymeric dielectric of multi-layer structures to metal lands to establish interplanar electrical interconnection. These multi-layer structures usually include multiple layers of the same polymeric dielectric material laminated to both sides of the structure; the vias may be formed on either side. In drilling such blind vias, it is critical to the operability of the multi-layer structure that registration between the laser and the internal metal land be achieved. Occurrence of misregistration may result in removal of dielectric material adjacent to the land and continuing to the internal metal planes leading to electrical shorts upon subsequent plating.

Complicating the successful formation of such blind vias and multi-layer structures described above is the fact that successive dielectric layers such as the core and joining level dielectric layer, are often formed of the same dielectric material. While employing the same dielectric material provides certain processing advantages, e.g., being able to use the same hole making techniques for both layers, for example excimer laser drilling, it introduces a problem if misregistration occurs. If misregistration occurs during drilling of blind vias to the underlying lands, this undesirable attack of the inner, core-level dielectric may result. If there is significant misregistration, the laser drilled blind via will not stop at the circuitization layer within the package,

This Sheet Has Been Replaced

but rather, the laser will continue to drill through the structure to the underlying metal layer. Misregistration can be potentially deleterious to the integrity of the package since it can lead to electrical shorts between joining metallurgy and the power plane upon subsequent plating.

Summary of the Invention

The present invention solves the problems existing in the prior art by providing a design incorporating material and methods for fabricating high density structures, eliminating misregistration concerns without sacrificing the electrical and mechanical integrity of the structure.

Accordingly, the present invention provides a multi-layer electronic circuit package including at least one electrically conductive plane, a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light, and a second organic polymeric dielectric material having a second optical absorbency to the ablating wavelength of laser light, the first and second optical absorbencies being different from each other. A first layer of one of the organic polymeric materials overlays at least one surface of at least one electrically conductive plane and a second layer of a different

This Sheet Has Been Replaced



organic polymeric material with a different optical absorbency to the material in the first layer overlays the first layer.

Brief Description of the Drawings

Figure 1a represents a cross-sectional view of a typical prior art multi-layer card assembly for fabrication of high speed, high density packages.

Figure 1b represents a cross sectional view of the multi-layer assembly of Figure 1a including additional layers of dielectric material laminated onto the structure to which a hole forming and subsequent plating procedure have been performed with good alignment.

Figure 2a represents a cross sectional view of a multi-layer structure of Figure 1a to which a hole forming and subsequent plating procedure have been performed with poor alignment.

Figure 2b represents a multi-layer card assembly of Figure 1a incorporating aspects of the present invention to which a subsequent hole forming and subsequent plating procedure have been performed with poor alignment.

This Sheet Has Been Replaced

Figure 3a represents a simplified cross sectional view of one embodiment of the present invention.

Figure 3b represents a simplified cross sectional view of one embodiment of the present invention for which layer 7 and 8 are subsequently laminated onto both sides of a metal layer.

Figures 4a and 4b represent photographs of 2 different materials, which may be used in embodiments of the present invention, after undergoing a hole formation process.

Figures 5a, 5b, and 5c represent cross sectional scanning electron micrographs of materials, which may be used in embodiments of the present invention, after being subjected to a hole formation process.

Detailed Description of Various and Preferred Embodiments

A typical multi-layer high density structure as seen in Figure 1a may include a metallic layer 1 surrounded by a dielectric material applied, e.g., by lamination, to both sides of the metallic layer. The metal layers may conduct electricity throughout the card to various components attached thereto. The dielectric also serves to insulate the various components attached

This Sheet Has Been Replaced

thereto. The dielectric serves to insulate the various conductive layers. After formation of a via (hole) in layer 2, another metallic layer 3 may be plated through that hole in the dielectric material.

Figure 1b represents the structure of Figure 1a with additional layers of dielectric material laminated to both sides of the original structures. In Figure 1b, acceptable alignment of drilled blind vias in layer 4 and the previously formed hole in layer 2 is shown.

In the typical multi-layer high density structure as seen in Figure 1b, the two dielectric layers 2 and 4 are typically formed of the same material. Use of the same dielectric material to form adjacent layers has certain advantages, e.g., structural and mechanical, but can cause problems when similar hole making techniques are practiced on the assembly. The problems are particularly pronounced if lasers are used to form the holes. Without very precise, constant monitoring, there is no way to know at what point to shut off the laser when it approaches the boundary between the two dielectric layers.

Due to the fact that the layers are formed from the same dielectric material, the hole forming process can result in the

This Sheet Has Been Replaced

removal of material from both layers. In other words, if the dielectric material is uniform in the lead direction it may be treated as a single ply of a single material. If misregistration occurs, common during the drilling of blind vias to the underlying lands, undesirable attack of the inner, core-level dielectric layer can result.

As seen in Figure 2a, this misregistration can lead to the removal of the layer 2. The entire area is then plated with another layer of metal resulting in metal being deposited in contact with the underlying core of metal as in the area 6 indicated by the arrow in Figure 2a. The subsequent plating over the blind via and contact between the metal layers can result in an electrical short.

The present invention, rather than using two layers of the same dielectric polymeric material, incorporates layered dielectric polymers of different optical absorbencies. According to the present invention, it is essential only that the two polymers used have different optical properties. In fact, the polymers may be essentially identical in all other physical characteristics as long as they are suitable for use in the present invention as dielectric components of an electronic package.

This Sheet Has Been Replaced

Shown very simply in Figure 3, the present invention includes two adjacent dielectric layers 7 and 8 with absorbencies $\alpha(n_1, \lambda)$ for the layer 7 and $\alpha(n_2, \lambda)$ for the layer 8, where n is the chromosphore concentration and λ is the wavelength of the incident radiation (e.g., laser). For the present invention to work, $\alpha(n_1,$) $\alpha(n_2,$) as seen in Figure 3b. Layer 8 may directly abut both sides of a metal layer, with layer 7 abutting layer 8 on the outside. A laser or other method used to form holes in the dielectric layers impacts upon layer 7 as shown by the arrow in Figure 3b.

In the example shown in Figure 3b, a UV excimer laser is used to form the blind vias. Due to the dielectric's absorbency of a predetermined wave length of light, upon the impact of the laser the layer 7 is ablated or vaporized by the laser. Given the structure of the present invention, the depth of holes drilled in the dielectric material may be easily and precisely controlled. The layer 7, being sensitive to a particular wave length of light, will be removed upon the impingement of that light on the layer. Yet, upon removal of the layer 7 in the area impacted on by the laser and the exposure of the layer 8, the removal of material will cease since the material forming layer 8 is relatively insensitive to that particular wavelength.

This Sheet Has Been Replaced

Table I includes examples from two categories of materials which may be used to form alternating dielectric layers according to preferred aspect of the present invention when using an excimer laser operating at a wavelength of 308 nm. The list is only illustrative; any number of dielectric materials with different optical absorbencies may be used according to the present invention. Type A and Type B refer to dielectrics A and B as shown in Figure 3b.

TABLE I

Type A	Type B
1a. PTFE(polytetrafluoroethylene) or FEP (fluorinated ethylene propylene copolymer) or PFA (polytetrafluoroethylene-perfluorovinylether) copolymer or others of a variety of TEFLON-type polymers	1b. PTFE filled with an absorbing dopant such as polyimide
2a. PTFE filled with amorphous silica particles	2b. PTFE filled with a variety of absorbing particles 2b'. PTFE filled with a variety of absorbing and nonabsorbing particles
3a. PMMA (polymethylmethacrylate)	3b. PTFE filled with any of a variety of particles and polyimide

Using materials with differing non-absorbing optical properties provides differing laser/material interaction. For

This Sheet Has Been Replaced

instance, the core-level dielectric may be selected from a group of materials listed as Type A in Table I. These materials are examples of materials which do not absorb and therefore cannot be drilled at excimer laser wavelengths such as, for example, 308nm. The materials listed as Type A in Table I are suitable for use as the core-level or other layers of dielectric according to the present invention if excimer laser drilling is selected to form the holes in the dielectric laid down over top of the layer formed over the material of Type A.

Absorbing particles which may be used with the present invention include, among others, polymers having suitable chromophores, e.g., those with conjugated bonding, and, therefore, absorb well in the ultraviolet. Glass particles that are non-absorbing at 308 nm include, e.g., Min-u-sil (U.S. Silica) or equivalent.

An alternate process or method such as the utilization of a CO_2 laser or a mechanical punch or drill may then be used to form holes in the material of Type A. The list of Type A and B materials is meant to be illustrative and not exhaustive; any material having an absorbency property different to that of the material laid over top of it may be used. It is necessarily only for the two materials to have different absorbency properties.

This Sheet Has Been Replaced

If the inner layer 8 as seen in Figure 3 is formed of a material labelled Type A in Table I, the outer layer 7 may be formed of a material listed as Type B in Table I. Such material is ablated at excimer laser wavelengths. By using this construction, if less than acceptable alignment occurs during excimer laser drilling of blind vias through layer 7, no adverse electrical impact on the structure will result.

The result of the use of such materials having differing absorbency properties may be seen in Figure 2b. Unlike in Figure 2a, with the two dielectric layers formed of a similar material, in Figure 2b, the removal of the layer 7 does not result in the removal of the inner layer 8. Therefore, the electrical shorting which can occur in the embodiment shown Figure 2b is precluded from occurring.

Preferably, the materials used to form the two layers, although not similar in absorbency of similar wavelengths of light, have similar mechanical, thermal, chemical, electrical and other such properties. For example, PTFE (layer 8) and polyimide-doped PTFE (layer 7) or quartz-filled PTFE (layer 8) and polyimide-doped quartz-filled PTFE (layer 7) and polyimide-doped glass-filled PTFE (layer 7) may be used, where concentrations of the dopant polyimide are low enough not to effect the above mentioned properties. Such

This Sheet Has Been Replaced

concentrations of dopant are on the order of about 5% polyimide by weight or less. In addition to alleviating alignment concerns during drilling of the outer dielectric layer, the use of materials labeled as Type A in Table I for core fabrication will facilitate the deletion of metal using excimer lasers for repair of short circuits at the surface of the core level shown in Figure 1a.

Table II presents the different drilling rates for the various Type A and Type B materials from Table I using an excimer laser operating at 308nm at an energy per unit area per pulse (fluence) at the surface of the dielectric of 12 Joules per square centimeter (J/cm^2).

TABLE II

Material	Drilling Rate (microns/pulse)
Type A	
PTFE	0
PTFE filled with silica particles	<0.5
Type B	
0.5 wt% polyimide in PTFE	5.0
5.0 wt% polyimide in PTFE	3.5
PTFE filled with a variety of absorbing particles with or without addition of polyimide	3.0 - 4.0

Figure 4a represents photographs of the dielectric 2a in Table I, PTFE filled with silica particles, after attempting to drill

This Sheet Has Been Replaced

through two mils of the material with 100 pulses using an excimer laser (308nm) at a fluence of 12 J/cm^2. As can be seen from the photograph in Figure 4a, the material has only been only slightly ablated, i.e., very shallow holes. Figure 4b shows a sample of material 2b in Table I, PTFE filled with a variety of absorbing glass particles, after being drilled with only 16 pulses. As is evident from Figure 4b, relatively complete and clean holes have been formed all the way through the material. Thus, Figures 4a and 4b demonstrate how these two materials could be used in one embodiment of the present invention.

Further evidence of the differential effect of various wave lengths of light on the various materials is shown in Figure 5a which represents a SEM micrograph of material 2b from Table I drilled under nominal excimer laser processing conditions. Figure 5b represents a photograph of a similarly treated sample of material 3b from Table I. Figure 5c shows a SEM micrograph of material 2A of Table I drilled using a CO2 laser. The photographs in Figure 5 represent further evidence of the usefulness of the present invention.

The present invention also includes a method of forming a multi-layer electronic circuit package. Preferably, at least one layer of the multi-layer electronic circuit package includes an

This Sheet Has Been Replaced

electrically conductive plane. Over one, two, or all surfaces of the conductive layer is deposited a first organic, polymeric dielectric material. The first layer may be chosen, for example, from the materials listed as Type A in Table I. The first organic polymeric material preferably has a first absorbency to an ablating wavelength of laser light.

After the first layer of dielectric is laid down, circuitization, including lands, may be deposited on the first layer. Upon the first dielectric layer and any circuitization may be deposited a second layer of a second organic, polymeric dielectric material. The second organic polymeric material preferably has a second optical absorbency different than the first optical absorbency of the first dielectric layer at the same laser ablating wavelength. Using a laser, a via may be formed through the second dielectric layer to the circuitization by ablating the material forming the second layer at the laser ablating wavelength. Conductive material may then be deposited on the surfaces of the via.

The dielectric materials may be deposited on the conductive layer in any order, depending upon the process used to form vias or other passages in the various layers. Means other than a laser may be used to form passages through the dielectric layers, such as a

This Sheet Has Been Replaced

mechanical punch. Further, the process is not limited to any specific wavelengths of laser light.

This Sheet Has Been Replaced

* C L M S *

Claims

1. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light; and

a second organic polymeric dielectric material having a second optical absorbency to said ablating wavelength of laser light, said first and second optical absorbencies differing from each other;

wherein a first layer of one of said organic polymeric materials overlays at least one surface of said at least one electrically conductive plane and a second layer of a different organic polymeric material with a different optical absorbency to the material in said first layer overlays said first layer.

2. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with quartz particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

This Sheet Has Been Replaced

* C L M S *

3. The multi-layer electronic circuit package according to claim 2, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

4. The multi-layer electronic circuit package according to claim 2, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

5. The multi-layer electronic circuit package according to claim 2, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (from U.S. Silica) or equivalent.

6. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

7. The multi-layer electronic circuit package according to

This Sheet Has Been Replaced

* C L M S *

claim 1, wherein a second electrically conductive plane at least partially overlays said second layer of said organic polymeric dielectric material.

8. The multi-layer electronic circuit package according to claim 1, wherein a layer of circuitization overlays said first layer of organic polymeric dielectric material and said second layer of organic polymeric dielectric material overlays said first layer and said circuitization layer.

9. A method of forming a multi-layer electronic circuit package, wherein at least one layer of the multi-layer package includes an electrically conductive plane with an organic, polymeric dielectric deposited on major surfaces thereof, said method comprising the steps of:

a) depositing a first layer of a first organic polymeric dielectric material on a major surface of the conductive plane, said first organic polymeric material having a first optical absorbency to an ablating wavelength of laser light;

b) forming circuitization, including lands, on said first layer of organic, dielectric material;

c) depositing a second layer of a second organic, polymeric dielectric material atop said circuitized first layer, said second organic polymeric material having a second optical absorbency

This Sheet Has Been Replaced

* C L M S *

different than said first optical absorbency of said first layer at a laser ablating wavelength; and

d) laser ablating a via through said second layer to said circuitization at said laser ablating wavelength.

10. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with silica particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

11. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

12. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

This Sheet Has Been Replaced

* C L M S *

13. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (U.S. Silica) or equivalent.

14. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

15. The method of forming a multi-layer electronic circuit package according to claim 9, wherein a second electrically conductive plane is deposited at least partially over said second layer of organic polymeric dielectric material.

16. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a layer of a first organic polymeric based dielectric material overlaying at least one surface of said at least one electrically conductive plane, said first dielectric material exhibiting low optical absorbency at a laser ablating wavelength; and

This Sheet Has Been Replaced

a layer of a second organic polymeric based dielectric material overlaying said first layer, said second polymeric material exhibiting high optical absorbency at said wavelength.

17. The multi-layer electronic circuit package according to claim 16, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with quartz particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

18. The multi-layer electronic circuit package according to claim 17, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

19. The multi-layer electronic circuit package according to claim 17, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

This Sheet Has Been Replaced



20. The multi-layer electronic circuit package according to claim 17, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (U.S. Silica) or equivalent.

21. The multi-layer electronic circuit package according to claim 16, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

22. The multi-layer electronic circuit package according to claim 16, wherein a second electrically conductive plane at least partially overlays said second layer of said organic polymeric based dielectric material.

23. The multi-layer electronic circuit package according to claim 16, wherein a layer of circuitization overlays said first layer of organic based polymeric dielectric material and said second layer of organic polymeric based dielectric material overlays said first layer and said circuitization layer.

This Sheet Has Been Replaced

Abstract of the Disclosure

A multi-layer electronic circuit package including at least one electrically conductive plane, a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light, and a second organic polymeric dielectric material having a second optical absorbency to the ablating wavelength of laser light. The first and second optical absorbencies being different from each other. A first layer of one of the organic polymeric materials overlays at least one surface of the at least one electrically conductive plane and a second layer of a different organic polymeric material with a different optical absorbency to the material in the first layer overlays the first layer.

This Sheet Has Been Replaced





FIG. 1(a)



FIG. 1(b)



FIG. 2(a)



FIG. 2(b)



FIG. 3(a)



FIG. 3(b)



FIG. 4(a)



FIG. 4(b)

500X

FIG. 5(a)

350X

FIG. 5(b)



500X

FIG. 5(c)

REPLACEMENT SHEETS SG
Description : paged 1 to paged 15
Claim(s) : paged 16 to paged 22
Drawing(s) : paged 1/4 to paged 4/4
Abstract : paged 23 to paged —
DATE OF RECEIPT 15/10/97

DESIGN OF HIGH DENSITY STRUCTURES WITH LASER ETCH STOP

This is the replacement sheet
Date: 15/10/97

Field of the Invention

The present invention relates to multi-layer circuit packages having laser drilled blind vias between internal circuitization planes for the purpose of electrical interconnection.

Background of the Invention

In the fabrication of multi-layer circuit boards and cards, it is necessary to form passages such as vias and through holes from one layer of the structure to a deeper layer. Such passages may be formed mechanically, chemically or by using lasers of various wavelengths to vaporize or burn away the circuit board material. Blind vias are passages that do not pass completely through a board or card. After formation of a blind via, material, such as a metal, may be deposited on the surface of the via to provide an electrical, power, or ground connection between the two layers connected to the via. In other words, the blind vias may be formed for plating of joining metallurgy which provides the inter-electrical connections within the multi-layer structure.

Lasers are commonly used to drill blind vias through the

insulating polymeric dielectric of multi-layer structures to metal lands to establish interplanar electrical interconnection. These multi-layer structures usually include multiple layers of the same polymeric dielectric material laminated to both sides of the structure; the vias may be formed on either side. In drilling such blind vias, it is critical to the operability of the multi-layer structure that registration between the laser and the internal metal land be achieved. Occurrence of misregistration may result in removal of dielectric material adjacent to the land and continuing to the internal metal planes leading to electrical shorts upon subsequent plating.

Complicating the successful formation of such blind vias and multi-layer structures described above is the fact that successive dielectric layers such as the core and joining level dielectric layer, are often formed of the same dielectric material. While employing the same dielectric material provides certain processing advantages, e.g., being able to use the same hole making techniques for both layers, for example excimer laser drilling, it introduces a problem if misregistration occurs. If misregistration occurs during drilling of blind vias to the underlying lands, this undesirable attack of the inner, core-level dielectric may result. If there is significant misregistration, the laser drilled blind via will not stop at the circuitization layer within the package,

but rather, the laser will continue to drill through the structure to the underlying metal layer. Misregistration can be potentially deleterious to the integrity of the package since it can lead to electrical shorts between joining metallurgy and the power plane upon subsequent plating.

Summary of the Invention

The present invention solves the problems existing in the prior art by providing a design incorporating material and methods for fabricating high density structures, eliminating misregistration concerns without sacrificing the electrical and mechanical integrity of the structure.

Accordingly, the present invention provides a multi-layer electronic circuit package including at least one electrically conductive plane, a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light, and a second organic polymeric dielectric material having a second optical absorbency to the ablating wavelength of laser light, the first and second optical absorbencies being different from each other. A first layer of one of the organic polymeric materials overlays at least one surface of at least one electrically conductive plane and a second layer of a different

organic polymeric material with a different optical absorbency to the material in the first layer overlays the first layer.

Brief Description of the Drawings

Figure 1a represents a cross-sectional view of a typical prior art multi-layer card assembly for fabrication of high speed, high density packages.

Figure 1b represents a cross sectional view of the multi-layer assembly of Figure 1a including additional layers of dielectric material laminated onto the structure to which a hole forming and subsequent plating procedure have been performed with good alignment.

Figure 2a represents a cross sectional view of a multi-layer structure of Figure 1a to which a hole forming and subsequent plating procedure have been performed with poor alignment.

Figure 2b represents a multi-layer card assembly of Figure 1a incorporating aspects of the present invention to which a subsequent hole forming and subsequent plating procedure have been performed with poor alignment.

This is the replacement sheet

Date: 15/10/97

Figure 3a represents a simplified cross sectional view of one embodiment of the present invention.

Figure 3b represents a simplified cross sectional view of one embodiment of the present invention for which layer 7 and 8 are subsequently laminated onto both sides of a metal layer.

Figures 4a and 4b represent photographs of 2 different materials, which may be used in embodiments of the present invention, after undergoing a hole formation process.

Figures 5a, 5b, and 5c represent cross sectional scanning electron micrographs of materials, which may be used in embodiments of the present invention, after being subjected to a hole formation process.

Detailed Description of Various and Preferred Embodiments

A typical multi-layer high density structure as seen in Figure 1a may include a metallic layer 1 surrounded by a dielectric material applied, e.g., by lamination, to both sides of the metallic layer. The metal layers may conduct electricity throughout the card to various components attached thereto. The dielectric also serves to insulate the various components attached

thereto. The dielectric serves to insulate the various conductive layers. After formation of a via (hole) in layer 2, another metallic layer 3 may be plated through that hole in the dielectric material.

Figure 1b represents the structure of Figure 1a with additional layers of dielectric material laminated to both sides of the original structures. In Figure 1b, acceptable alignment of drilled blind vias in layer 4 and the previously formed hole in layer 2 is shown.

In the typical multi-layer high density structure as seen in Figure 1b, the two dielectric layers 2 and 4 are typically formed of the same material. Use of the same dielectric material to form adjacent layers has certain advantages, e.g., structural and mechanical, but can cause problems when similar hole making techniques are practiced on the assembly. The problems are particularly pronounced if lasers are used to form the holes. Without very precise, constant monitoring, there is no way to know at what point to shut off the laser when it approaches the boundary between the two dielectric layers.

Due to the fact that the layers are formed from the same dielectric material, the hole forming process can result in the

removal of material from both layers. In other words, if the dielectric material is uniform in the lead direction it may be treated as a single ply of a single material. If misregistration occurs, common during the drilling of blind vias to the underlying lands, undesirable attack of the inner, core-level dielectric layer can result.

As seen in Figure 2a, this misregistration can lead to the removal of the layer 2. The entire area is then plated with another layer of metal resulting in metal being deposited in contact with the underlying core of metal as in the area 6 indicated by the arrow in Figure 2a. The subsequent plating over the blind via and contact between the metal layers can result in an electrical short.

The present invention, rather than using two layers of the same dielectric polymeric material, incorporates layered dielectric polymers of different optical absorbencies. According to the present invention, it is essential only that the two polymers used have different optical properties. In fact, the polymers may be essentially identical in all other physical characteristics as long as they are suitable for use in the present invention as dielectric components of an electronic package.

Shown very simply in Figure 3, the present invention includes two adjacent dielectric layers 7 and 8 with absorbencies $\alpha(n_1, \lambda)$ for the layer 7 and $\alpha(n_2, \lambda)$ for the layer 8, where n is the chromosphore concentration and λ is the wavelength of the incident radiation (e.g., laser). For the present invention to work, $\alpha(n_1,$) $\alpha(n_2,$) as seen in Figure 3b. Layer 8 may directly abut both sides of a metal layer, with layer 7 abutting layer 8 on the outside. A laser or other method used to form holes in the dielectric layers impacts upon layer 7 as shown by the arrow in Figure 3b.

In the example shown in Figure 3b, a UV excimer laser is used to form the blind vias. Due to the dielectric's absorbency of a predetermined wave length of light, upon the impact of the laser the layer 7 is ablated or vaporized by the laser. Given the structure of the present invention, the depth of holes drilled in the dielectric material may be easily and precisely controlled. The layer 7, being sensitive to a particular wave length of light, will be removed upon the impingement of that light on the layer. Yet, upon removal of the layer 7 in the area impacted on by the laser and the exposure of the layer 8, the removal of material will cease since the material forming layer 8 is relatively insensitive to that particular wavelength.

THIS SHEET HAS BEEN REPLACED

Table I includes examples from two categories of materials which may be used to form alternating dielectric layers according to preferred aspect of the present invention when using an excimer laser operating at a wavelength of 308 nm. The list is only illustrative; any number of dielectric materials with different optical absorbencies may be used according to the present invention. Type A and Type B refer to dielectrics A and B as shown in Figure 3b.

TABLE I

Type A	Type B
1a. PTFE(polytetrafluoroethylene) or FEP (fluorinated ethylene propylene copolymer) or PFA (polytetrafluoroethylene-perfluorovinylether) copolymer or others of a variety of TEFLON-type polymers	1b. PTFE filled with an absorbing dopant such as polyimide
2a. PTFE filled with amorphous silica particles	2b. PTFE filled with a variety of absorbing particles 2b'. PTFE filled with a variety of absorbing and nonabsorbing particles
3a. PMMA (polymethylmethacrylate)	3b. PTFE filled with any of a variety of particles and polyimide

Using materials with differing non-absorbing optical properties provides differing laser/material interaction. For

This Sheet Has Been Replaced

This is the replacement sheet

Date: 15/10/97

instance, the core-level dielectric may be selected from a group of materials listed as Type A in Table I. These materials are examples of materials which do not absorb and therefore cannot be drilled at excimer laser wavelengths such as, for example, 308nm. The materials listed as Type A in Table I are suitable for use as the core-level or other layers of dielectric according to the present invention if excimer laser drilling is selected to form the holes in the dielectric laid down over top of the layer formed over the material of Type A.

Absorbing particles which may be used with the present invention include, among others, polymers having suitable chromophores, e.g., those with conjugated bonding, and, therefore, absorb well in the ultraviolet. Glass particles that are non-absorbing at 308 nm include, e.g., Min-u-sil (U.S. Silica) or equivalent.

An alternate process or method such as the utilization of a CO_2 laser or a mechanical punch or drill may then be used to form holes in the material of Type A. The list of Type A and B materials is meant to be illustrative and not exhaustive; any material having an absorbency property different to that of the material laid over top of it may be used. It is necessarily only for the two materials to have different absorbency properties.

This is the replacement sheet

Date: 15/10/97

If the inner layer 8 as seen in Figure 3 is formed of a material labelled Type A in Table I, the outer layer 7 may be formed of a material listed as Type B in Table I. Such material is ablated at excimer laser wavelengths. By using this construction, if less than acceptable alignment occurs during excimer laser drilling of blind vias through layer 7, no adverse electrical impact on the structure will result.

The result of the use of such materials having differing absorbency properties may be seen in Figure 2b. Unlike in Figure 2a, with the two dielectric layers formed of a similar material, in Figure 2b, the removal of the layer 7 does not result in the removal of the inner layer 8. Therefore, the electrical shorting which can occur in the embodiment shown Figure 2b is precluded from occurring.

Preferably, the materials used to form the two layers, although not similar in absorbency of similar wavelengths of light, have similar mechanical, thermal, chemical, electrical and other such properties. For example, PTFE (layer 8) and polyimide-doped PTFE (layer 7) or quartz-filled PTFE (layer 8) and polyimide-doped quartz-filled PTFE (layer 7) and polyimide-doped glass-filled PTFE (layer 7) may be used, where concentrations of the dopant polyimide are low enough not to effect the above mentioned properties. Such

This is the replacement sheet.
Date: 15/10/97

concentrations of dopant are on the order of about 5% polyimide by weight or less. In addition to alleviating alignment concerns during drilling of the outer dielectric layer, the use of materials labeled as Type A in Table I for core fabrication will facilitate the deletion of metal using excimer lasers for repair of short circuits at the surface of the core level shown in Figure 1a.

Table II presents the different drilling rates for the various Type A and Type B materials from Table I using an excimer laser operating at 308nm at an energy per unit area per pulse (fluence) at the surface of the dielectric of 12 Joules per square centimeter (J/cm^2).

TABLE II

Material	Drilling Rate (microns/pulse)
Type A	
PTFE	0
PTFE filled with silica particles	<0.5
Type B	
0.5 wt% polyimide in PTFE	5.0
5.0 wt% polyimide in PTFE	3.5
PTFE filled with a variety of absorbing particles with or without addition of polyimide	3.0 - 4.0

Figure 4a represents photographs of the dielectric 2a in Table I, PTFE filled with silica particles, after attempting to drill

This is the replacement sheet

Date: 15/10/97

through two mils of the material with 100 pulses using an excimer laser (308nm) at a fluence of 12 J/cm^2. As can be seen from the photograph in Figure 4a, the material has only been only slightly ablated, i.e., very shallow holes. Figure 4b shows a sample of material 2b in Table I, PTFE filled with a variety of absorbing glass particles, after being drilled with only 16 pulses. As is evident from Figure 4b, relatively complete and clean holes have been formed all the way through the material. Thus, Figures 4a and 4b demonstrate how these two materials could be used in one embodiment of the present invention.

Further evidence of the differential effect of various wave lengths of light on the various materials is shown in Figure 5a which represents a SEM micrograph of material 2b from Table I drilled under nominal excimer laser processing conditions. Figure 5b represents a photograph of a similarly treated sample of material 3b from Table I. Figure 5c shows a SEM micrograph of material 2A of Table I drilled using a CO2 laser. The photographs in Figure 5 represent further evidence of the usefulness of the present invention.

The present invention also includes a method of forming a multi-layer electronic circuit package. Preferably, at least one layer of the multi-layer electronic circuit package includes an

This is the replacement sheet

Date: 15/10/97

electrically conductive plane. Over one, two, or all surfaces of the conductive layer is deposited a first organic, polymeric dielectric material. The first layer may be chosen, for example, from the materials listed as Type A in Table I. The first organic polymeric material preferably has a first absorbency to an ablating wavelength of laser light.

After the first layer of dielectric is laid down, circuitization, including lands, may be deposited on the first layer. Upon the first dielectric layer and any circuitization may be deposited a second layer of a second organic, polymeric dielectric material. The second organic polymeric material preferably has a second optical absorbency different than the first optical absorbency of the first dielectric layer at the same laser ablating wavelength. Using a laser, a via may be formed through the second dielectric layer to the circuitization by ablating the material forming the second layer at the laser ablating wavelength. Conductive material may then be deposited on the surfaces of the via.

The dielectric materials may be deposited on the conductive layer in any order, depending upon the process used to form vias or other passages in the various layers. Means other than a laser may be used to form passages through the dielectric layers, such as a

This is the replacement sheet

Date: 15/10/97

mechanical punch. Further, the process is not limited to any specific wavelengths of laser light.



Claims

1. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light; and

a second organic polymeric dielectric material having a second optical absorbency to said ablating wavelength of laser light, said first and second optical absorbencies differing from each other;

wherein a first layer of one of said organic polymeric materials overlays at least one surface of said at least one electrically conductive plane and a second layer of a different organic polymeric material with a different optical absorbency to the material in said first layer overlays said first layer.

2. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with quartz particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

This Sheet Has Been Replaced



3. The multi-layer electronic circuit package according to claim 2, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

4. The multi-layer electronic circuit package according to claim 2, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

5. The multi-layer electronic circuit package according to claim 2, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (from U.S. Silica) or equivalent.

6. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

7. The multi-layer electronic circuit package according to

This Sheet Has Been Replaced

claim 1, wherein a second electrically conductive plane at least partially overlays said second layer of said organic polymeric dielectric material.

8. The multi-layer electronic circuit package according to claim 1, wherein a layer of circuitization overlays said first layer of organic polymeric dielectric material and said second layer of organic polymeric dielectric material overlays said first layer and said circuitization layer.

9. A method of forming a multi-layer electronic circuit package, wherein at least one layer of the multi-layer package includes an electrically conductive plane with an organic, polymeric dielectric deposited on major surfaces thereof, said method comprising the steps of:

a) depositing a first layer of a first organic polymeric dielectric material on a major surface of the conductive plane, said first organic polymeric material having a first optical absorbency to an ablating wavelength of laser light;

b) forming circuitization, including lands, on said first layer of organic, dielectric material;

c) depositing a second layer of a second organic, polymeric dielectric material atop said circuitized first layer, said second organic polymeric material having a second optical absorbency

This Sheet Has Been Replaced



different than said first optical absorbency of said first layer at a laser ablating wavelength; and

d) laser ablating a via through said second layer to said circuitization at said laser ablating wavelength.

10. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with silica particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

11. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

12. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

This Sheet Has Been Replaced



* C L M S *

13. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (U.S. Silica) or equivalent.

14. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

15. The method of forming a multi-layer electronic circuit package according to claim 9, wherein a second electrically conductive plane is deposited at least partially over said second layer of organic polymeric dielectric material.

16. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a layer of a first organic polymeric based dielectric material overlaying at least one surface of said at least one electrically conductive plane, said first dielectric material exhibiting low optical absorbency at a laser ablating wavelength; and

This Sheet Has Been Replaced

* C L M S *

a layer of a second organic polymeric based dielectric material overlaying said first layer, said second polymeric material exhibiting high optical absorbency at said wavelength.

17. The multi-layer electronic circuit package according to claim 16, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with quartz particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

18. The multi-layer electronic circuit package according to claim 17, wherein said dopant is polyimide in polytetrafluoroethylene, TINUVIN in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

19. The multi-layer electronic circuit package according to claim 17, wherein said absorbing particles are selected from the group consisting of polymers having suitable chromophore groups, e.g., conjugated bonding.

This Sheet Has Been Replaced

20. The multi-layer electronic circuit package according to claim 17, wherein said glass particles are selected from the group consisting of silicas, e.g., Min-U-sil (U.S. Silica) or equivalent.

21. The multi-layer electronic circuit package according to claim 16, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

22. The multi-layer electronic circuit package according to claim 16, wherein a second electrically conductive plane at least partially overlays said second layer of said organic polymeric based dielectric material.

23. The multi-layer electronic circuit package according to claim 16, wherein a layer of circuitization overlays said first layer of organic based polymeric dielectric material and said second layer of organic polymeric based dielectric material overlays said first layer and said circuitization layer.

This Sheet Has Been Replaced

This is the replacement sheet
15
Date: 19/10/97

DESIGN OF HIGH DENSITY STRUCTURES WITH LASER ETCH STOP

Abstract of the Disclosure

A multi-layer electronic circuit package including at least one electrically conductive plane, a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light, and a second organic polymeric dielectric material having a second optical absorbency to the ablating wavelength of laser light. The first and second optical absorbencies being different from each other. A first layer of one of the organic polymeric materials overlays at least one surface of the at least one electrically conductive plane and a second layer of a different organic polymeric material with a different optical absorbency to the material in the first layer overlays the first layer.

Figure 1



FIG. 1(a)



FIG. 1(b)



FIG. 2(a)



FIG. 2(b)



FIG. 3(a)



FIG. 3(b)



FIG. 4(a)



FIG. 4(b)



500X

FIG. 5(a)

350X

FIG. 5(b)



500X

FIG. 5(c)

This is the replacement sheet

Date: 6/8/98

REPLACEMENT SHEETS SG
☑ Description : paged 9 to paged —
☑ Claim(s) : paged 16 to paged 19
☐ Drawing(s) : paged — to paged —
☐ Abstract : paged — to paged —

DATE OF RECEIPT 6/8/98

Table I includes examples from two categories of materials which may be used to form alternating dielectric layers according to preferred aspect of the present invention when using an excimer laser operating at a wavelength of 308 nm. The list is only illustrative; any number of dielectric materials with different optical absorbencies may be used according to the present invention. Type A and Type B refer to dielectrics A and B as shown in Figure 3b.

TABLE I

Type A	Type B
1a. PTFE(polytetrafluoroethylene) or FEP (fluorinated ethylene propylene copolymer) or PFA (polytetrafluoroethylene-perfluorovinylether) copolymer or others of a variety of TEFLON-type polymers	1b. PTFE filled with an absorbing dopant such as polyimide TINUVIN, or pyrene
2a. PTFE filled with amorphous silica particles	2b. PTFE filled with a variety of absorbing particles 2b'. PTFE filled with a variety of absorbing and nonabsorbing particles
3a. PMMA (polymethylmethacrylate)	3b. PTFE filled with any of a variety of particles and polyimide

'TINUVIN being a substituted hydroxyphenyl benzotriazole (i.e. a UV absorber). By Hawley's Condensed Chemical Dictionary, 11th edition published by Van Nostrand Reinhold.

Using materials with differing non-absorbing optical roperties provides differing laser/material interaction. For

This is the replacement sheet

Date: 6/8/98

WHAT IS CLAIMED IS:

1. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a first organic polymeric dielectric material having a first optical absorbency to an ablating wavelength of laser light; and

a second organic polymeric dielectric material having a second optical absorbency to said ablating wavelength of laser light, whereby said first material dielectric material absorbs wavelengths of light that are not the same as wavelengths of light that are absorbed by said second dielectric material;

wherein a first layer of said first or said second organic polymeric materials overlays at least one surface of said at least one electrically conductive plane and a second layer of the other of said first and second organic polymeric materials overlays said first layer.

2. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with quartz particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

3. The multi-layer electronic circuit package according to claim 2, wherein said dopant is polyimide in polytetrafluoroethylene, a substituted hydroxyphenyl benzotriazole in polymethylmethacrylate, or pyrene in polymethlymethacrylate.

4. The multi-layer electronic circuit package according to claim 2, wherein said absorbing particles are polymers having suitable chromophore groups.

5. The multi-layer electronic circuit package according to claim 2, wherein said glass particles are silicas.

6. The multi-layer electronic circuit package according to claim 1, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

7. The multi-layer electronic circuit package according to claim 1, wherein a second electrically conductive plane at least partially overlays said second layer of said organic polymeric dielectric material.

8. The multi-layer electronic circuit package according to claim 1, wherein a layer of circuitization overlays said first layer of organic polymeric dielectric material and said second layer of organic polymeric dielectric material overlays said first layer and said circuitization layer.

9. A method of forming a multi-layer electronic circuit package, wherein at least one layer of the multi-layer package includes an electrically conductive plane with an organic, polymeric dielectric deposited on major surfaces thereof, said method comprising the steps of:

a) depositing a first layer of a first organic polymeric dielectric material on a major surface of the conductive plane, said first organic polymeric material having a first optical absorbency to an ablating wavelength of laser light;

b) forming circuitization, including lands, on said first layer of organic, dielectric material;

c) depositing a second layer of a second organic, polymeric dielectric material atop said circuitized first layer, said second organic polymeric material having a second optical absorbency

different than said first optical absorbency of said first layer at a laser ablating wavelength; and

d) laser ablating a via through said second layer to said circuitization at said laser ablating wavelength.

10. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene and polytetrafluoroethylene filled with silica particles and said second organic polymeric dielectric material is selected from the group consisting of polytetrafluoroethylene filled with an absorbing dopant, polytetrafluoroethylene filled with absorbing particles, and polytetrafluoroethylene filled with glass particles and polyimide.

11. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said dopant is polyimide in polytetrafluoroethylene, a substituted hydroxyphenyl benzotriazole in polymethylmethacrylate, or pyrene in polymethylmethacrylate.

12. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said absorbing particles are polymers having suitable chromophore groups.

13. The method of forming a multi-layer electronic circuit package according to claim 10, wherein said glass particles are silicas.

14. The method of forming a multi-layer electronic circuit package according to claim 9, wherein said first organic polymeric dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

15. The method of forming a multi-layer electronic circuit package

according to claim 9, wherein a second electrically conductive plane is deposited at least partially over said second layer of
organic polymeric dielectric material.

16. A multi-layer electronic circuit package, comprising:

at least one electrically conductive plane;

a first layer of a first organic polymeric based dielectric material overlaying at least one surface of said at least one electrically conductive plane, said first dielectric material exhibiting low optical absorbency at a laser ablating wavelength; and

a second layer of a second organic polymeric based dielectric material overlaying said first layer, said second polymeric
material exhibiting high optical absorbency at said wavelength; and

wherein said first organic polymeric based dielectric material is polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 10,600 nm and said second organic polymeric dielectric material is polyimide-doped polytetrafluoroethylene having an optical absorbency to an ablating wavelength of laser light of 308 nm.

17. A multi-layer electronic circuit package, comprising:

a first electrically conductive plane;

a first layer of a first organic polymeric based dielectric material overlaying at least one surface of said first electrically conductive plane, said first dielectric material exhibiting low optical absorbency at a laser ablating wavelength;

a second layer of a second organic polymeric based dielectric material overlaying said first layer, said second polymeric material exhibiting high optical absorbency at said wavelength; and

a second electrically conductive plane is deposited at least partially over said second layer of organic polymeric dielectric material.