

CLAIMS**WHAT IS CLAIMED IS:**

1. A repaired flange bolt hole comprising:
a flange defining a flange bolt hole having a surface, the flange comprising a base material,
a coating system disposed over the surface of the flange bolt hole,
wherein the coating system comprises a corrosion resistant layer, wherein the corrosion resistant layer comprises a different material than the base material.
2. The repaired flange bolt hole according to claim 1, wherein the corrosion resistant layer comprises a nickel super alloy, super austenitic stainless steel, or combinations thereof.
3. The repaired flange bolt hole according to claim 1, wherein the corrosion resistant layer comprises a ceramic material.
4. The repaired flange bolt hole according to claim 1, wherein the corrosion resistant layer comprises titania, chromia, alumina, or combinations thereof.
5. The repaired flange bolt hole according to claim 4, wherein the coating system further comprises an aluminum layer disposed beneath the corrosion resistant layer.
6. The repaired flange bolt hole according to claim 2, wherein the coating system has a thickness of about 100 to about 400 microns.
7. The repaired flange bolt hole according to claim 5, wherein the coating system has a thickness of about 10 to about 100 microns.
8. The repaired flange bolt hole according to claim 1, wherein the base material comprises stainless steel.
9. The repaired flange bolt hole according to claim 1, wherein the coating system has a porosity of less than about 5%.
10. The repaired flange bolt hole according to claim 1, wherein the flange bolt hole comprises a circular opening with a depth and a diameter and is disposed along a high pressure compressor in a gas turbine engine.
11. A method of repairing a flange bolt hole, the flange bolt hole having a surface and comprising a base material, the method comprising:
reaming the flange bolt hole to remove corroded material in the flange bolt hole, and
applying a coating system to the surface of the flange bolt hole,

wherein the coating system comprises a corrosion resistant layer that comprises a different material than the base material.

12. The method according to claim 11, wherein the corrosion resistant layer comprises a nickel super alloy, super austenitic stainless steel, or combinations thereof.

13. The method according to claim 11, wherein the corrosion resistant layer comprises a ceramic material.

14. The method according to claim 11, wherein the corrosion resistant layer comprises titania, chromia, alumina, or combinations thereof.

15. The method according to claim 14, wherein applying a coating system to the surface of the flange bolt hole comprises applying an aluminum slurry to the surface of the flange bolt hole.

16. The method according to claim 11, wherein the coating system is applied to a thickness of about 100 to about 400 microns.

17. The method according to claim 14, wherein the coating system is applied to a thickness of about 10 to about 100 microns.

18. The method according to claim 11, wherein the base material comprises stainless steel.

19. The method according to claim 11, wherein applying the coating system to the flange bolt hole comprises resistance welding a plug comprising a corrosion resistant material to the surface of the flange bolt hole and drilling a hole in the plug to reform the flange bolt hole with the corrosion resistant layer disposed on the surface.

20. The method according to claim 11, wherein applying the coating system to the flange bolt hole comprises applying the coating system as a slurry, by a sol-gel process, by thermal spray, by cold spray, or combinations thereof.