

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization

International Bureau

(43) International Publication Date
15 June 2023 (15.06.2023)



(10) International Publication Number
WO 2023/102763 A1

(51) International Patent Classification:

C08L 23/12 (2006.01) *C08L 23/08* (2006.01)
C08L 23/20 (2006.01) *C08K 3/04* (2006.01)
C08L 23/16 (2006.01) *C08K 3/22* (2006.01)

(21) International Application Number:

PCT/CN2021/136322

(22) International Filing Date:

08 December 2021 (08.12.2021)

(25) Filing Language: English

(26) Publication Language: English

(71) Applicant: **DOW GLOBAL TECHNOLOGIES LLC**
[US/US]; 2211 H.H. Dow Way, Midland, Michigan 48674
(US).

(72) Inventor; and

(71) Applicant (*for SC only*): **LIU, Andong** [CN/CN]; No. 936,
Zhangheng Road, Shanghai Pilot Free Trade Zone, Shang-
hai 201203 (CN).

(72) Inventors: **GENG, Xiang**; No. 936, Zhangheng Road,
Shanghai Pilot Free Trade Zone, Shanghai 201203 (CN).
MUNRO, Jeffrey C.; 230 Abner Jackson Parkway, Lake
Jackson, Texas 77566 (US). **BARRY, Russell P.**; Riet-
strasse 14, 8717 Schais (CH). **MING, Ming**; No. 936,
Zhangheng Road, Shanghai Pilot Free Trade Zone, Shang-
hai 201203 (CN). **OHMURA, Takahiko**; Shibusawa ABC
Bldg. #1, 5F Ebisu-cho 1, Kanagawa-Ku, Yokohama-shi
221-0024 (JP).

(74) Agent: **WU, FENG & ZHANG**; 3 FL, Building 2, Yard 3,
FengXiuZhongLu Road, Haidian District, Beijing 100094
(CN).

(81) Designated States (*unless otherwise indicated, for every
kind of national protection available*): AE, AG, AL, AM,
AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ,
CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO,
DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN,
HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN,
KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD,
ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO,
NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW,

SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every
kind of regional protection available*): ARIPO (BW, GH,
GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ,
UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ,
TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK,
EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV,
MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

WO 2023/102763 A1

(54) Title: THERMOPLASTIC POLYOLEFIN AND MOLDED ARTICLE THEREFROM

(57) Abstract: The present disclosure is directed to an article. In an embodiment, a molded article is provided and includes a crosslink-free polymeric composition. The crosslink-free polymeric composition includes from 65 wt% to 75 wt% of a propylene homopolymer, from 20 wt% to 35 wt% of an impact modifier, and from 0.5 wt% to 5 wt% of a pigment (and optional additive), the propylene homopolymer, the impact modifier, and the pigment (and optional additive) amounting to 100 wt% of the crosslink-free polymeric composition. The impact modifier includes at least two members selected from the group consisting of (i) a random ethylene/C₄-C₈ α -olefin copolymer having a density from 0.85 g/cc to 0.89 g/cc, and a melting point from 45°C to 65°C, and a melt index from 0.1 g/10min to 6.0 g/10 min, (ii) an ethylene/octene multi-block copolymer having a density from 0.86 g/cc to 0.89 g/cc, a melting point from 115°C to 125°C and (iii) an ethylene/propylene/diene terpolymer (EPDM) having an ethylene content from 65 wt% to 87 wt% and a Mooney viscosity (1+4 at 125°C) from 16 to 68, and (iv) combinations thereof.