

ABSTRACT

5 A film-shaped adhesive is disclosed, which contains an epoxy resin, a phenolic resin, and an elastomer, and may further contain an inorganic filler. A content of the inorganic filler is from 0 to 10% by mass, based on a total amount of the film-shaped adhesive. A content of the elastomer is from 20 to 50% by mass, based on the total amount of the film-shaped adhesive. The content of the elastomer is from 40 to 60 parts by mass with respect to 100 parts by mass of a total amount of the epoxy resin and the phenolic resin.

Fig. 1