

Description

This invention relates to compositions useful in encapsulating signal transmission devices.

Signal transmission devices, such as electrical and optical cables, typically contain a plurality of individual conductors, each of which conduct an electrical or optical signal. A grease-like composition, such as FLEXGEL, (commercially available from AT&T) is typically used around the individual conductors. Other filling compositions include petroleum jelly (PJ) and polyethylene modified petroleum jelly (PEPJ). For a general discussion of cable filling compositions, and particularly FLEXGEL type compositions, see U.S. Patent No. 4,259,540.

When cable is spliced it is often the practice to clean the grease-like composition from the individual conductors so that the encapsulant will adhere to the conductor upon curing, preventing water or other contaminants from seeping between the conductor and the encapsulant. Therefore, an encapsulant which will adhere directly to a conductor coated with a grease-like composition is highly desirable.

Many of the connecting devices (hereinafter connectors) used to splice individual conductors of a cable are made from polycarbonate. A significant portion of prior art encapsulants are not compatible with polycarbonate, and thus, stress or crack polycarbonate connectors over time. Therefore, it is desirable to provide an encapsulant which is compatible with, that is will not stress or crack, a polycarbonate connector.

It is often necessary that signal transmission devices, particularly splices, be re-entered for repairs, inspection or the like. Therefore, it is desirable to provide a re-enterable encapsulant. Further, it is desirable to provide a encapsulant which is transparent to facilitate inspection.

Many of the prior art encapsulants, which have addressed the above problems with varying degrees of success, are based on two-part polyurethane gels which include isocyanate and crosslinking portions. However, all of the two-part polyurethane gels share at least two common problems. First, the high water reactivity of isocyanates necessitates involved and expensive packaging to prevent reactions with water prior to cure with the crosslinking agent. Second, it is well known in the art that isocyanate compounds are hypo-allergenic, and thus, can induce allergic reactions in certain persons, particularly when a two part system which requires on-site mixing of the components is used.

Therefore, it is highly desirable to provide an encapsulant which serves as a water-impervious barrier, which has good adhesion to grease-coated conductors, which is compatible with polycarbonate splice connectors, which is re-enterable, which is transparent, and which does not require the use of an isocyanate compound.

Encapsulants used in signal transmission devices may be exposed for prolonged periods to high humidity and heat during use. This may cause the encapsulants to disintegrate, noticeably swell or revert to a liquid. It is generally known that polyesters can be degraded under such hydrolytic conditions. Therefore, it is further desirable to provide a polyester gel encapsulant composition which is hydrolytically stable.

EP-A-0282184 describes an encapsulant composition which overcomes many of the disadvantages of the prior art. The composition of the copending application serves as a water-impervious barrier, is compatible with polycarbonate, splice connectors, may be transparent and re-enterable, and does not require the use of an isocyanate compound. The encapsulant comprises an extended reaction product of an admixture of

- 1) an effective amount of an anhydride functionalized compound
- 2) an effective amount of a crosslinking agent, and
- 3) at least one plasticizer to extend the reaction product.

It now has been discovered that the hydrolytic stability of the compositions disclosed in that application can be improved by the incorporation of an oxirane containing material.

The use of oxirane containing materials in various compositions is of course known. For example, Canadian Pat. No. 1,224,595 discloses a two-part, low viscosity, epoxy resin potting composition which cures to semi-flexible thermoset state comprised of liquid polyglycidyl ether, liquid carboxyl-terminated polyester, and cyclic dicarboxylic acid anhydride. This composition is not extended with a plasticizer and lacks grease and polycarbonate compatibility. Such a composition would be brittle, hard, and opaque, and would not be easily re-enterable.

EP-A-049098 discloses compositions suitable for forming surface coatings, laminates or composite materials formed by bringing together:

- (a) a first polymer containing carboxylic acid, anhydride or acid chloride groups,
- (b) an amine or alcohol or a derivative thereof which is a tertiary amine, a ketimine, an acetal or an oxazolidine and
- (c) a second polymer capable of cross-linking with the first polymer in the presence of the amine or alcohol, e.g. an epoxy resin. Other components may be present including pine oil. The compositions disclosed do not have the necessary properties for use as an encapsulant.

Epoxy resins have also long been used as electrical potting compounds and for electric circuit boards.

Typically, epoxy resins are tightly cross-linked when cured and form a brittle polymer with little flexibility and elongation, high tensile strength and a dielectric constant in the range of 3.8 to 5.5. Even flexibilized epoxy resins typically have tensile strengths well above 21.1 Newtons/cm² (N/cm²) (normally in the 1000 range), a percent elongation of 10% to 20%, and dielectric constants at 25°C and 1MHz of greater than 3.0. Such epoxies fail to meet industry specifications for reenterable encapsulant materials. Generally, it has not been possible to formulate epoxies with enough softness or flexibility for use in encapsulating wire assemblies, for potting cable connectors or for other application where a soft, very flexible rubbery insulating material is needed.

In addition, epoxy resins typically have a temperature rise or exotherm of from 20°C to as much as 260°C with room temperature curing systems. Numerous detrimental effects can be experienced by high exotherms, including damaging effects on wire insulation, connecting devices and closure components.

Surprisingly, it has now been found that epoxy resins can be used in an encapsulant material to provide hydrolytic stability without adversely affecting the other outstanding properties, (e.g. adhesion to conductors, compatibility with polycarbonate, re-enterability, low dielectric constants) and without high exotherms.

According to the present invention there is provided a grease compatible, hydrolytically stable dielectric encapsulant capable of being used to encapsulate a splice of a signal conducting device comprising:

an extended reaction product of an admixture of:

- (a) from 3 to 60 weight percent of an anhydride functionalized compound having reactive anhydride sites;
- (b) from 1.0 to 30 weight percent of a crosslinking agent capable of reacting with said anhydride functionalized composition to form a cured cross-linked material, said crosslinking agent being selected from polyols, polyamines and polythiols; and

(c) from 1.5 to 20 weight percent of an oxirane containing material to provide hydrolytic stability, said oxirane containing material being selected from aliphatic glycidyl ethers, aliphatic glycidyl esters, epoxidized dienes, epoxidized polyesters, epoxidized alpha olefins, epoxidized polyolefins, epoxidized natural rubber, and epoxidized oils;

the admixture having a ratio of equivalents of anhydride functionalized compound to epoxy equivalent which is no greater than 1.25

wherein the reaction product is extended with at least one plasticizer, present in the range of between 35 and 85 percent by weight of the encapsulant, and the said at least one plasticizer is essentially inert with the reaction product and is substantially nonexuding therefrom; the encapsulant having a C-H adhesion value of at least 4, the value being obtained by measuring the maximum pull out force in Newtons at a speed of 0.8 mm/sec of a 0.046 cm diameter and 15 cm long conductor from a test vessel filled with said encapsulant, the reaction product also having a solubility parameter of from 7.9 to 8.6.

The present invention provides a hydrolytically stable encapsulant composition particularly useful as an encapsulant for signal transmission devices, such as electrical or optical cables. It is to be understood that the invention has utility as an encapsulant for signal transmission devices which are not cables, for example, electrical or electronic components and devices, such as sprinkler systems, junction box fillings, to name a few. It is further contemplated that the encapsulant may have utility as an encapsulant or sealant for non-signal transmitting devices.

"Essentially inert" as used herein means that the plasticizer does not become cross-linked into the reaction between the anhydride functionalized composition and the cross-linking agent.

"Non-exuding" as used herein means that the plasticizer has the ability to become and remain blended with the reaction product of the anhydride functionalized compound, the cross-linking agent and oxirane material at ambient temperatures. Many excellent plasticizers experience some blooming, or a slight separation from the solid, especially at higher temperatures, and over lengthy storage times. These plasticizers are still considered to be "substantially non-exuding".

"Hydrolytic stability" as used herein is defined as a maximum percent weight change of from -10% to +5% as measured by test method 6.01 described in Bellcore Specification TA-TSY-000354 on Re-Enterable Encapsulants and a small change in hardness of less than 50, preferably less than 20, as measured with a quarter cone penetrometer.

"Anhydride functionalized compound" as used herein is defined as a polymer, oligomer, or monomer, which has been reacted to form a compound which has anhydride reactive sites thereon.

"Epoxy equivalent weight" as used herein is defined as the weight of resin which contains one gram equivalent of epoxy.

The invention also contemplates a method for filling an enclosure containing a signal transmission device comprising mixing the components of the encapsulant together to form a liquid encapsulant, pouring the liquid encapsulant composition into an enclosure at ambient temperature, the liquid encapsulant curing to form a cross-linked encapsulant which fills the enclosure including voids between the individual conductors of the transmission device. The liquid encapsulant composition of the invention may also be forced into a contamin-

ated component under pressure to force the contaminant from the component, the encapsulant subsequently curing to protect the component from recontamination. The liquid encapsulant composition may also be poured into a component so that the encapsulant forms a plug or dam upon curing.

The encapsulant of the invention is suited for use as an encapsulant for signal transmission devices and other uses in which a hydrolytically stable, water-impervious, preferably re-enterable, barrier is desired. Encapsulant materials according to the invention are hydrolytically stable with a tensile strength of less than 21.1 N/cm² and percent elongation of greater than 50% but less than 250% and dielectric constant at 1MHz and 25°C less than 3.0. The temperature rise or exotherm is very low, on the order of less than 5°C and, typically, less than 1°C. Further, they are compatible with cable filling compounds and with polycarbonate splice connectors.

The encapsulant may be used in a signal transmission device, for example, in a cable splice which comprises: 1) an enclosure member; 2) a signal transmission device which includes at least one signal conductor; and 3) at least one connecting device joining the at least one conductor to at least one other conductor in the enclosure member. The signal conductor is capable of transmitting a signal, for example, an electrical or optical signal.

The encapsulant is formed by reacting an anhydride functionalized compound with a suitable crosslinking agent and an oxirane containing material in the presence of an organic plasticizer which extends the reaction product. The oxirane containing material provides the encapsulant with hydrolytic stability. The plasticizer is essentially inert to the reaction product and substantially non-exuding. The plasticizer system chosen contributes to the desired properties of the encapsulant, such as, the degree of adhesion to grease-coated conductors, the degree of compatibility with polycarbonate connectors, and the softness or hardness of the encapsulant.

Polymers, oligomers, or monomers which have been reacted to form a compound having reactive anhydride sites thereon are useful as the anhydride functionalized compound of the invention.

Examples of anhydride functionalized compounds which are suitable for use in the encapsulant of the invention include maleinized polybutadiene-styrene polymers (such as Ricon 184/MA), maleinized polybutadiene (such as Ricon 131/MA or Lithene LX 16-10MA), maleic anhydride modified vegetable oils (such as maleinized linseed oil, dehydrated castor oil, soybean oil or tung oil, and the like), maleinized hydrogenated polybutadiene, maleinized polyisoprene, maleinized ethylene/propylene/1,4-hexadiene terpolymers, maleinized polypropylene, maleinized piperylene/2-methyl-1-butene copolymers, maleinized polyterpene resins, maleinized cyclopentadiene, maleinized gum or tall oil resins, maleinized petroleum resins, copolymers of dienes and maleic anhydride or mixtures thereof.

The anhydride functionalized compound may be present in an amount ranging from 3 to 60 percent by weight based on total solids of the reaction product.

Suitable cross-linking agents for use in the invention are compounds which will react with anhydride reactive sites of the anhydride functionalized compound to form a cross-linked polymer structure. Cross-linking agents for use in the present invention are selected from polythiols, polyamines and polyols.

Suitable polythiol and polyamine cross-linking agents may vary widely within the scope of the invention and include (1) mercaptans and (2) amines which are polyfunctional. These compounds are often hydrocarbyl substituted but may contain other substituents either as pendant or catenary (in the backbone) units such as cyano, halo, ester, ether, keto, nitro, sulfide or silyl groups. Examples of compounds useful in the present invention included the polymercapto-functional compounds such as 1,4-butanedithiol, 1,3,5-pentanetrithiol, 1,12-dodecanedithiol; polythiol derivatives of polybutadienes and the mercapto-functional compounds such as the di- and tri-mercaptopropionate esters of the poly(oxypropylene) diols and triols. Suitable organic diamines include the aromatic, aliphatic and cycloaliphatic diamines. Illustrative examples include: amine terminated polybutadiene, the polyoxyalkylene polyamines, such as those available for Texaco Chemical Co., Inc., under the tradename Jeffamine, the D, ED, DU, BuD and T series.

Suitable polyol cross-linking agents include, for example, polyalkadiene polyols (such as Poly bd R-45HT), polyether polyols based on ethylene oxide and/or propylene oxide and/or butylene oxide, ricinoleic acid derivatives (such as castor oil), polyester polyols, fatty polyols, ethoxylated fatty amides or amines or ethoxylated amines, hydroxyl bearing copolymers of dienes or mixtures thereof. Hydroxyl terminated polybutadiene such as Poly bd R-45HT is presently preferred.

The castor oil which may be used is primarily comprised of a mixture of about 70% glyceryl triricinoleate and about 30% glyceryl diricinoleate-monooleate or monolinoleate and is available from the York Castor Oil Company as York USP Castor Oil. Ricinoleate based polyols are also available from Caschem and Spencer-Kellogg. Suitable interesterification products may also be prepared from castor oil and substantially non-hydroxyl-containing naturally occurring triglyceride oils as disclosed in U.S. Patent 4,603,188.

Suitable polyether polyol cross-linking agents include, for example, aliphatic alkylene glycol polymers hav-

ing an alkylene unit composed of at least two carbon atoms. These aliphatic alkylene glycol polymers are exemplified by polyoxypropylene glycol and polytetramethylene ether glycol. Also, trifunctional compounds exemplified by the reaction product of trimethylol propane and propylene oxide may be employed. A typical polyether polyol is available from Union Carbide under the designation Niox PPG-425. Specifically, Niox PPG-425, a copolymer of a conventional polyol and a vinyl monomer, represented to have an average hydroxyl number of 263, an acid number of 0.5, and a viscosity of 80 centistokes at 25°C.

The general term polyether polyols also includes polymers which are often referred to as amine based polyols or polymeric polyols. Typical amine based polyols include sucrose-amine polyol such as Niox BDE-400 or FAF-529 or amine polyols such as Niox LA-475 or LA-700, all of which are available from Union Carbide.

Suitable polyalkadiene polyol cross-linking agents can be prepared from dienes which include unsubstituted, 2-substituted or 2,3-disubstituted 1,3-dienes of up to 12 carbon atoms. Preferably, the diene has up to 6 carbon atoms and the substituents in the 2- and/or 3-position may be hydrogen, alkyl groups having about 1 to 4 carbon atoms, substituted aryl, unsubstituted aryl, halogen and the like. Typical of such dienes are 1,3-butadiene, isoprene, chloroprene, 2-cyano-1,3-butadiene and 2,3-dimethyl-1,2-butadiene. A hydroxyl terminated polybutadiene is available from ARCO Chemicals under the designation Poly-bd R-45HT.

Poly-bd R-45HT is represented to have a molecular weight of about 2800, a degree of polymerization of about 50, a hydroxyl functionality of about 2.4 to 2.6 and a hydroxyl number of 46.6. Further, hydrogenated derivatives of the polyalkadiene polymers may also be useful.

Besides the above polyols, there can also be employed lower molecular weight, reactive, chain-extending or crosslinking compounds having molecular weights typically of 300 or less, and containing therein about 2 to 4 hydroxyl groups. Materials containing aromatic groups therein, such as N, N-bis (2-hydroxypropyl) aniline may be used to thereby produce useful gels.

To insure sufficient crosslinking of the cured gels the polyol based component preferably contain polyols having hydroxyl functionality of at least 2. Examples of such polyols include polyoxypropylene glycol, polyoxyethylene glycol, polyoxytetramethylene glycol, and small amounts of polycaprolactone glycol. An example of a suitable polyol is Quadrol, N,N,N',N'-tetrakis-(2-hydroxypropyl)-ethylene diamine, available from BASF Wyandotte Corp.

The cross-linking agent may be present in an amount ranging from 1.0 to 30 percent by weight based on total solids of the reaction product.

Oxirane containing materials that are useful in the encapsulant composition are epoxy compounds having aliphatic or cycloaliphatic backbones and at least one terminal or pendant oxirane group. Suitable oxirane containing materials would be aliphatic alkyl, alkenyl, alkadiene and cycloalkyl oxiranes. These may be substituted with any group, e.g., ester, alkoxy, ether and thioether, that does not react with the anhydride reactive sites of the anhydride functionalized compound. Monoepoxy, diepoxy and polyepoxy compounds and mixtures thereof may be used.

Examples of suitable oxirane materials are aliphatic glycidyl esters or ethers (such as Ciba-Geigy's Araldite RD-2, Wilmington's WC-68 or WC-97), triglycidyl ether or castor oil (such as Wilmington's WC-85), polypropylene oxide diglycidyl ethers (such as Grilonit's F 704), cycloaliphatic epoxides (such as Union Carbide's ERL4221 or Wilmington's MK-107), bicyclopentadiene ether epoxy resins, epoxidized polyunsaturated vegetable oil acid esters (such as Viking's Vikoflex 9080), epoxidized polyunsaturated triglycerides (such as Viking's Vikoflex 7190 and C.P. Hall's Paraplex G-62), epoxidized polyesters, epoxidized diene polymers (such as B F 1000 Resin from Nippon Soda), epoxidized polybutadiene polyols (such as Viking's polybutadiene oxides), epoxidized alpha olefins (such as Viking's Vikolox 16), terpene oxides (such as Viking's alpha pinene oxide), polybutene oxides (such as Viking's polybutene (L-14) oxide), Diel-Alder oxide (such as Viking's Dicyclopentadiene Diepoxide), or epoxidized natural rubber.

The oxirane containing material should be present in an amount sufficient to provide hydrolytic stability. The amount depends upon epoxy equivalent weight (EEW) which may vary over a wide range and is a function of the ratio of equivalents of anhydride functionalized compound (A) to oxirane (E), A/E ratio. The A/E ratio should be no greater than 1-25, preferably between 0.25 and 1.25, and most preferably between 0.25 and 0.55. The higher the equivalent weight of the oxirane containing material (also referred to herein as epoxy equivalent weight) the greater the amount required to provide hydrolytic stability. Typically, the oxirane containing material is present in an amount ranging from 1.5 to 50 percent by weight based on the total solids of the reaction product.

The reaction product of an anhydride functionalized compound, a suitable cross-linking agent and an oxirane containing material is typically in the range of between 5 and 95 weight percent and preferably between 20 and 70 weight percent of the encapsulant. The admixture should contain between 0.9 to 1.1 reactive groups from the crosslinking agent for each anhydride reactive site.

The plasticizing system, which extends the reaction product of the anhydride functionalized compound,

the cross-linking agent and oxirane containing material contributes to many of the functional characteristics of the encapsulant of the present invention. Plasticizing system refers to the one or more plasticizer compounds which may be used together to achieve the desired properties for the encapsulant. The plasticizing system is selected so as to be essentially inert with the reaction product of the anhydride functionalized compound, the cross-linking agent and the oxirane containing material, and substantially non-exuding. The plasticizing system selected also preferably provides an encapsulant which has excellent adhesion to grease-coated conductors and which is compatible with polycarbonate connectors.

Plasticizer compounds which may be used to achieve a suitable plasticizing system include aliphatic, naphthenic, and aromatic petroleum based hydrocarbon oils; cyclic olefins (such as polycyclopentadiene,) vegetable oils (such as linseed oil, soybean oil, sunflower oil); saturated or unsaturated synthetic oils; polyalphaolefins (such as hydrogenated polymerized decene-1), hydrogenated terphenyls, propoxylated fatty alcohols (such as PPG-11 stearyl alcohol); polypropylene oxide mono- and di- esters, pine oil-derivatives (such as alpha-terpineol), polyterpenes, cyclopentadiene copolymers with fatty acid esters, phosphate esters and mono-, di-, and poly-esters, (such as trimellitates, phthalates, benzoates, fatty acid ester derivatives, castor oil derivatives, fatty acid ester alcohols, dimer acid esters, glutarates, adipates, sebacates) and mixtures thereof. Particularly preferred are a mixture of hydrocarbon oils with esters.

Examples of polyalphaolefins which may be used as plasticizers in the present invention are disclosed in U.S. Patent No. 4,355,130.

Examples of vegetable oils useful as plasticizers in the present invention are disclosed in U.S. Patent No. 4,375,521.

The plasticizer compounds used to extend the reaction product may be present in the range of between 35 and 85 percent by weight of the encapsulant, and preferably between 50 and 70 percent.

Previously it has been difficult to provide an encapsulant which has excellent adhesion to grease-coated wires and which also does not stress or crack a polycarbonate splice module. It has been discovered that by using a plasticizing system, in conjunction with a crosslinked anhydride functionalized compound, to provide an encapsulant having a particular total solubility parameter, both of these objectives can be achieved.

It has been discovered that the total solubility parameter of an encapsulant of the present invention can be an indication of an encapsulant's ability to adhere to grease-coated conductors and of its compatibility with polycarbonate connectors. The solubility parameter value (represented by δ) is a measure of the total forces holding the molecules of a solid or liquid together and is normally given without units although its units are properly (Cal/per cc)^{1/2}. Every compound or system is characterized by a specific value of solubility parameter and materials having similar solubility parameters tend to be miscible. See, for example, A.F.M. Barton "CRC Handbook of Solubility Parameters and Other Cohesion Parameters", 1983, CRC Press, Inc.

Solubility parameters may be obtained from literature values or may be estimated by summation of the effects contributed by all the groups in a molecular structure using available group molar attraction constants developed by Hoy, utilizing the following equation:

$$\delta = \frac{\Sigma F_T + 135.1}{V_M}$$

and using the group molar attraction constants in K.L. Hoy, "Tables of Solubility Parameters", Union Carbide Corp. 1975; J. Paint Technol 42, 76 (1970), where ΣF_T is the sum of all the group molar attraction constants (F_T), V_M is the molar volume (MW/d), MW is the molecular weight and d is the density of the material or system in question.

This method can be used to determine the solubility parameters of the cross-linked polymer and the individual value of each component if the chemical structure is known.

To determine the solubility parameter for hydrocarbon solvents, the following equation was utilized:

$$\delta = 6.9 + 0.02 \text{ Kauri - butanol value}$$

The Kauri-butanol value was calculated using the following equation:

$$KB = 21.5 + 0.206 (\% \text{ wt. naphthenes}) + 0.723 (\% \text{ wt. aromatics})$$

See, W.W. Reynolds and E.C. Larson, Off., Dig., Fed. Soc. Paint Technol. 34, 311 (1962); and Shell Chemicals, "Solvent Power", Tech. Bull ICS (x)/79/2, 1979.

The approximate compositions for the hydrocarbon oil can be obtained from the product brochures under the carbon type analysis for naphthenic and aromatic carbon atoms.

Cross-linked polymers may swell by absorbing solvent but do not dissolve completely. The swollen macromolecules are called gels.

For a plasticized crosslinked polymer system, the total solubility parameter would be the weighted arithmetic mean of the value of each component.

$$\delta_T = \delta_a \phi_a + \delta_b \phi_b + \delta_c \phi_c \dots$$

Where ϕ_a , ϕ_b , and ϕ_c are the fractions of A, B, and C in the system and δ_a , δ_b , and δ_c are the solubility parameter of the individual components.

A plasticized crosslinked polymer system with a total solubility parameter of between 7.9 and 9.5 would be substantially compatible with the major constituents in the PJ, PEPJ, or FLEXGEL compositions. In order to achieve maximum compatibility with the grease compositions and also be compatible with polycarbonate, the total solubility of the encapsulant is between 7.9 and 8.6, and more preferably, between 8.0 and 8.3.

The reaction between the anhydride functionalized compound, the cross-linking agent and the oxirane containing material may be catalyzed to achieve an increased curing rate. The type of catalyst useful for this reaction will depend upon the nature of the anhydride functionalized compound, the crosslinking agent and the oxirane containing material. Many tertiary amine catalysts have been found to be particularly useful ("tertiary amine", as used herein, is meant to include amidines and guanidines as well as simple tri-substituted amines). These tertiary amine catalysts include 1,8-diazabicyclo[5.4.0]undec-7-ene (DBU), 1,5-diazabicyclo[4.3.0]non-5-ene (DBN), and salts thereof, tetradecyldimethylamine, octyldimethylamine, octyldecylmethylamine, octadecyldimethylamine, 1,4-diazabicyclo[2.2.2]octane, tetramethylguanidine, 4-dimethylaminopyridine, and 1,8-bis(dimethylamino)-naphthalene, with DBU and DBN being especially preferred on the basis of the more rapid reaction rates provided.

Although the use of a catalyst is generally not necessary when the crosslinking agent is amine functional, addition of catalysts such as DBU and DBN may have an accelerating effect upon the reaction rate. When a catalyst is used, it should be present in an amount ranging from 0.1 to 5 percent by weight based on total solids of the reaction product to be effective, and preferably between 0.5 to 3.0 percent by weight.

Although the crosslinking reactions to prepare the encapsulant compositions of the present invention are preferably conducted at or near ambient temperature, it should be obvious to one skilled in the art that the reaction rate may be accelerated, if desired, by the application of elevated temperatures.

It is also possible to add other additives, such as fillers, fungicides, oxidation preventatives or any other additive as necessary. As oxidation preventatives, there can be used hindered phenols, for example, Irganox 1010, Tetrakis methylene (3,5-di-tert-butyl-4-hydroxyhydrocinnamate)methane, and Irganox 1076, Octadecyl B(3,5-tert-butyl-4-hydroxyphenol) propionate, (made by the Ciba-Geigy Company).

As stated above, the most common grease-like substance which is used to fill cables is FLEXGEL, an oil extended thermoplastic rubber, commercially available from AT&T. Other filling compositions include petroleum jelly (PJ) and polyethylene modified petroleum jelly (PEPJ). All such cable filling compositions are herein collectively referred to as grease.

To quantify the adhesion of an encapsulant to grease-coated conductors a test to determine an encapsulant's C-H Adhesion Value will be used. In general, this test measures the amount of force it takes to pull a grease-coated conductor from a vessel containing a cured encapsulant. The greater the force which is required, the greater the adhesion.

To determine the C-H Adhesion Value of an encapsulant the following test was conducted. Six, 0.046 cm diameter (22 gauge) polyethylene insulated conductors (PIC), taken from a length of FLEXGEL filled telephone cable purchased from General Cable Co. were cut into 15 cm lengths. The test vessels were filled almost flush with the top edge with the test encapsulant. A lid having several holes in it was placed thereon and a coated conductor was inserted into each hole such that 4 cm of the conductor protrude above the lid. A tape flag was placed at the 4 cm mark to support the conductors while the encapsulant cured. After four days at room temperature the lid was removed and the vessel mounted in a Instron tensile testing machine. Each conductor was pulled out of the encapsulant at a crosshead speed of about 0.8 mm/sec. The maximum pull-out force was measured in Newtons/conductor for each of the conductors. The average of the six values in Newtons/conductor was assigned as the C-H Adhesion Value. Similar tests were also run to determine the C-H Adhesion Value for conductors coated with a PEPJ grease and are included in the examples below. A C-H Adhesion Value of at least 4 is an acceptable value (4 Newtons/conductor maximum pull-out force), with a C-H Adhesion Value of at least 13 preferred.

As noted, a further concern in formulating an encapsulant for use in splice enclosures is the compatibility of the encapsulant with polycarbonate connectors. Compatibility is evidenced by a lack of stressing or cracking of a polycarbonate connector over time. An encapsulant's compatibility with polycarbonate will be quantified by assigning a Polycarbonate Compatibility Value (PCV). This will be measured by means of a stress test conducted on polycarbonate modules which have been encapsulated in a particular encapsulant at an elevated temperature for an extended period of time. The percentage of the original flexure test control value after four or nine weeks at 60°C will be designated as the Polycarbonate Compatibility Value. The original flexure test control value is the breaking force in Newtons of three polycarbonate modules following flexure test ASTM D790 using an Instron tensile machine at a crosshead speed of about 0.2 mm/sec. An acceptable Polycarbonate Compatibility Value is 80 (80% of the average of the three control modules), with a value of 90 being preferred.

Polycarbonate Compatibility Values were determined as follows: Three control modules were crimped with the recommended maximum wire gauge, the wires had solid polyethylene insulation. This produced maximum stress on each module. The breaking force of the three modules was measured in Newtons, using the flexure test outlined in ASTM D790 on an Instron tensile machine, at a cross head speed of about 0.2 mm/sec. The average of these three values was used as the control value. Three crimped modules were placed in a tray and submerged in encapsulant. The tray was placed in an air pressure pot under 1.41 Kg/cm² pressure for 24 hours, while the encapsulant gelled and cured. After 24 hours, the tray with the encapsulated modules was placed in an air circulating oven at 60°C for 4 weeks.

After 4 weeks, the samples were removed and allowed to cool to room temperature. The encapsulant was peeled from the modules. The breaking force of the three modules was measured following the ASTM D790 flexure test. The average of these three values, divided by that of the control, multiplied by 100, is assigned as the Polycarbonate Compatibility Value.

Hydrolytic stability was measured based on test method 6.01 described in Bellcore Specification TA-TSY-000354 on Re-Enterable Encapsulants and measures percent weight change. The hydrolytic stability of the cured gels were determined by measuring weight loss and hardness change on three 2.54 by 5.08 by 0.95 cm samples of each composition tested. The hardness of each sample was determined by a one-quarter cone penetrometer according to ASTM D-1403. All samples were then weighed and placed in boiling water (100°C) with deionized water adjusted to pH 11.5 for 7 days. After turning off the heat the samples remained in the water for two hours, then were allowed to equilibrate to room temperature for two hours, weighed and their final hardness measured. The failure criteria for this test is a maximum percent weight change of from -10% to +5%. The encapsulant samples should retain sufficient hardness to maintain their original shape. The change in hardness can be measured with a quarter cone penetrometer. The smaller the change in hardness the greater the resistance to hydrolytic degradation.

The following lists of commercially available components were used in the examples which follow. Preparation A was prepared as described. The function of each component is also listed. Function is indicated as follows: Anhydride Functionalized Compound - "AFC"; Cross-linking Agent - "CA"; oxirane containing material - "O"; plasticizer compound - "P"; and catalyst - "C".

COMPONENT TABLE

<u>MATERIALS</u>	<u>DESCRIPTION</u>	<u>SOURCE</u>	<u>FUNCTION</u>
Ricon 131/MA	Polybutadiene (80 $\pm$ 5 % Trans and Cis 1.4 vinyl. 20 $\pm$ 5 % 1.2 vinyl) - Maleic anhydride adduct with average molecular weight of about 6000 and equivalent weight of about 1745	Colorado Chemical Specialities. Inc.	AFC
Lithene LX16-10MA	Polybutadiene (50-60 % 1.4-Trans, 25-35 % 1.4 Cis, 10-15 % 1.2 vinyl) - Maleic anhydride adduct with average molecular weight of about 8800 and equivalent weight of about 1100	Revertex Ltd.	AFC
Nisso BN 1015	Polybutadiene (> 85 % 1.2 vinyl) - maleic anhydride adduct with average molecular weight of about 1207 and equivalent weight of about 750	Nippon Soda Co., Ltd.	AFC
Ricon 184/MA	Butadiene-styrene random copolymer - maleic anhydride adduct with average molecular weight of about 10.000 and equivalent weight of about 1730	Colorado Chemicals Specialities. Inc.	AFC
PA-18	Copolymer of octadecene-1 and maleic anhydride with average molecular weight of about 50.000	Gulf Oil	AFC
Poly bd R-45 HT	Hydroxyl terminated polybutadiene (about 60 % Trans-1.4. 20 % Cis. 1.4 and 20 % 1.2 vinyl) with average molecular weight of about 3000 and hydroxyl functionality of about 2.5	Arco Chemical Co.	CA
Nisso G-3000	Hydroxyl terminated polybutadiene (> 90 % 1.2 vinyl) with average molecular weight of about 3000 and hydroxyl functionality of > 1.6	Nippon Soda Co., Ltd.	CA
York USP Caster Oil	Vegetable oil of about 70 % glyceryl triricinolein and about 30 % glyceryl diricinolein mono-oleate or monolinoleate and hydroxyl functionality about 2.7	York Caster Oil Co.	CA
Ethoduomeen T/13	Ethoxylated fatty diamines with average molecular weight of about 470 and three primary hydroxyls	Armak	CA.C
Polycat DBU	1.8 diaza-bicyclo (5.4.0) undecene-7	Air Products	C
Flexon 650	Naphthenic Oil. Aniline pt 190	Exxon Co.	P

<u>MATERIALS</u>	<u>DESCRIPTION</u>	<u>SOURCE</u>	<u>FUNCTION</u>
Sunthane 450	Naphthenic Oil, Aniline pt 175	Sun Oil Co.	P
ADMA 14	Tetradecyldimethylamine	Ethyl Chemicals	C
DAMA 810	Octyldecylmethylamine	Ethyl Chemicals	C
Paol 40	Polyalphaolefin	Burmah-Castrol Inc.	P
Soybean Oil	Supreme Soybean Oil	Spencer Kellogg	P
Alpha-Terpincol	---	Hercules Inc.	P
Trixylenol Phosphate	---	FMC Inc.	P
Tricresyl Phosphate	---	FMC Inc.	P
Wiconol APS	PPG-11 Stearyl Ether	Witco Chemical	P
Yarmor 302	Pine Oil	Hercules Inc.	P
Emory 2900	Dioctyl dimerate	Emery	P
Escopol R-020	Polycyclopentadiene	Exxon Chemical	P
Sunthene 480	Naphthenic Oil, aniline pt 178	Sun Oil Co.	P
Plasthall 100	Isooctyl Tallate	C.P. Hall Co.	P
Flextricin P-8	Glyceryl tri (acetyl ricinoleate)	CasChem. Inc.	P
Indopol H-100	Polybutene	Amoco Chemical Corp.	P
Linseed Oil	Supreme Linseed Oil	Cargill	P
Nuoplaz 6959	Tri-octyl Trimellitate	Nuodex. Inc.	P
1,6-Hexanedithiol	---	Aldrich Chem. Co.	CA
Jeffamine T-403	Polyether triamine with amine equivalent weight of about 150	Texaco Chem. Inc.	CA

55	50	45	40	35	30	25	20	15	10	5
<u>MATERIALS</u>		<u>DESCRIPTION</u>	<u>SOURCE</u>	<u>FUNCTION</u>						
1.9-Nonanedithiol	---		Aldrich Chem. Co.	CA						
CasChem 126		Polyurethane Encapsulant	CasChem. Inc.							
D-1000		Polyurethane Encapsulant	AT&T							
Araldite RD-2		1,4-butanedioldiglycidyl ether, epoxy equivalent weight of about 136.	Ciba-Geigy	0						
ERL-4421		3,4-epoxycyclohexyl-methyl-3,4-epoxy cyclohexane carboxylate, epoxy equivalent weight of about 137.	Union Carbide	0						
ERL-4234		2-(3,4-epoxycyclohexyl-5,5-spiro-3,4-epoxy) cyclohexane-meta-dioxane, epoxy equivalent weight of about 143.5.	Union Carbide	0						
Vikolox 12		1,2-epoxydodecane, about 7.8 percent oxirane oxygen.	Viking Chem.	0						
Vikoflex 7190		Epoxidized linseed oil, about 9.0 percent oxirane oxygen.	Viking Chem.	0						
Polybutadiene Oxide		Epoxidized Sartamer Poly bd R-45 HT (hydroxylterminated polybutadiene), about 7.15 percent oxirane oxygen.	Viking Chem.	0						
BF-1000 Resin		Epoxidized polybutadiene, about 7.4 percent oxirane oxygen.	Nisso Nippon Soda	0						
Vikoflex 9080		Octyl epoxy linseedate, about 7.0 percent oxirane oxygen.	Viking Chem.	0						
Vikolox 16		1,2-hexadecane oxide, about 6.1 percent oxirane oxygen.	Viking Chem.	0						
Vikolox 20-24		Alpha olefin oxide, about 4.4 percent oxirane oxygen.	Viking Chem.	0						
Vikolox 24-28		Alpha olefin oxide, about 3.7 percent oxirane oxygen.	Viking Chem.	0						
Fuelsaver		Fungicide	Angus							

The epoxy equivalent weights of the oxirane containing materials used in the examples of Tables II and III as determined by wet analysis are summarized here in Table I.

TABLE I. Oxirane Containing Materials

<u>Material</u>	<u>Percent Oxirane Oxygen</u>	<u>Epoxy Equivalent Weight</u>	<u>Source-Structure</u>
Araldite-RD-2	----	136	Ciba-Geigy - 1,4-butanedioldiglycidyl ether
ERL-4221	11.7	137	Union Carbide - 3,4-epoxy cyclohexyl-methyl - 3,4-epoxy cyclohexane carboxylate
ERL-4234	----	143.5	Union Carbide - 2 (3,4-epoxycyclohexyl-5,5-spiro-3,4-epoxy) cyclohexane-meta-dioxane
Vikoflex 7190	9.0	117.8	Viking - Epoxidized Linseed Oil
Vikolox 12	7.8	205	Viking - 1,2-epoxy-dodecane
Polybutadiene Oxide	7.15	215	Viking - Epoxidized Sartamer Poly bd R-45HT (hydroxyl-terminated polybutadiene)
Vikoflex 9080	7.0	228.5	Viking - octyl epoxy linseedate
Vikolox 16	6.1	262.3	Viking - 1,2-hexadecane oxide
Vikolox 18	5.4	296.3	Viking - 1,2-octadecane oxide
Vikolox 20-24	4.4	344.8	Viking
Vikolox 24-28	3.7	438.4	Viking

The invention is further described in the following examples wherein all parts are by weight. Where a particular test was not run in a particular example it is indicated by "-".

Preparation A - Amine Compound C

The following amine compound was prepared by charging to a reaction vessel 25 gram of Jeffamine T-403 (polyether triamine from Texaco Chemicals, Inc.), 0.309 equivalents and 170 gm isoctyl acrylate, 0.923 equivalents. The vessel was mixed and heated slightly for 3 days to produce the Michael adduct. Spectral analysis confirmed that the addition had taken place.

Example 1

An encapsulant of the present invention was prepared by mixing the following materials using an air-driven stirrer until the mixture appeared homogeneous.

22.2 parts of Ricon 131/MA, and 34.7 parts of soybean oil were added to a breaker and mixed using an air-driven stirrer until the mixture appeared homogeneous. To another beaker, 14.8 parts of Poly BD 45 HT, 1.26 parts of ADMA-14, 3.4 parts of Araldite RD-2, 0.2 parts Fuelsaver, 1.56 parts soybean oil and 21.88 parts Flexon 650 were added and likewise mixed. The beakers containing the mixtures were added to a third breaker and were mixed by hand for 2 minutes. Once mixed, the gel time was measured by determining the amount of time required for a 200g sample to reach a viscosity of 1,000 poise using a Sunshine Gel Time Meter, available from Sunshine Scientific Instrument. Clarity was measured visually. Clarity is either transparent (T) or opaque (O).

Tear strength was tested by the procedure of ASTM D-624, tensile strength and elongation were measured by the procedure of ASTM D-412; adhesion of the encapsulant to a grease coated wire was measured as described above (C-H adhesion value); and the encapsulants compatibility with polycarbonate (Polycarbonate Compatibility Value, PCV), was also measured as described above. The approximate Total Solubility Parameter for some of the encapsulants was also calculated as described above.

Examples 2-47, and Comparative Examples

Encapsulants of the invention were prepared and tested as described in Example 1. The formulation test results are set forth in Tables II through V below.

TABLE II

Example	1	2	3	4	5
Ricon 131 MA	22.2	21.21	20.76	21.48	20.78
Poly bd R45HT	14.8	14.29	13.84	14.32	14.32
ADMA-14	1.26	0.89	1.38	1.32	1.32
Vikoflex 9080	----	11.09	6.4	5.91	5.74
FuelSaver	0.2	0.2	0.2	0.6	0.2
Flexon 650	21.88	23.07	22.72	21.57	21.74
Soybean Oil	36.26	29.08	34.70	35.2	34.7
Araldite RD-2	3.4	----	----	----	----
A/E Ratio	0.51	0.25	0.43	0.48	0.5
Tear Strength N/cm	7.4	4.9	6.8	6.7	7.5
Tensile Strength N/cm ²	13.6	10.3	14.1	11.5	13.2
Elongation %	90	134	129.5	121	119.5
Geltime (minutes)	57.9	187.1	64.9	69.1	64.8
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days 100°C, water pH 11.5)					
Hardness (quarter cone)	25.0	15.7	28.8	29.0	31.7
Change in quarter cone	15.0	3.9	14.6	14.1	18.7
% Weight Change	+2.3	-0.81	-0.3	+1.4	-1.79
C-H Adhesion Value, N Flexgel	16.9	----	21.4	----	22.7
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	553
3 weeks	522	----	----	537	527
4 weeks	521	----	----	507	513
PCV Value	97	----	----	94	95
(note: control 538)					
Total Solubility Parameter (TSP)	8.2	----	----	8.2	8.1

TABLE II (con't)

5	Example	6	7	8	9	10
	Ricon 131 MA	21.96	22.2	23.23	21.39	21.84
	Poly bd R45HT	14.64	14.8	15.65	14.41	14.56
	ADMA-14	1.27	1.3	0.97	1.26	1.26
10	Vikoflex 9080	4.8	4.0	2.43	-----	-----
	Vikoflex 7190	-----	-----	-----	4.36	4.0
	FuelSaver	0.2	0.2	0.39	0.2	0.2
	Flexon 650	22.43	22.8	25.27	19.83	19.8
	Soybean Oil	34.70	34.7	32.07	38.55	38.34
15	A/E Ratio	0.6	0.73	1.25	0.51	0.56
	Tear Strength N/cm	7.2	8.4	7.9	6.1	7.2
	Tensile Strength N/cm ²	13.1	14.3	15.4	13.1	13.8
	Elongation %	123.5	109	127	137	134
	Geltime (minutes)	63.8	63.8	86.1	82.5	73.0
20	Gel-Clarity	T	T	T	T	T
	Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
	Hardness (quarter cone)	34.0	44.6	64.0	25.5	35.2
25	Change in quarter cone	20.7	29	53.1	11.2	20.7
	% Weight change	+1.66	+1.5	+2.64	+1.9	-----
	C-H Adhesion Value, N					
	Flexgel	22.2	23.1	-----	20.9	29.4
30	Polycarbonate Compatibility 60°C (Breaking Force, N)					
	1 week	544	-----	-----	-----	-----
	3 weeks	524	-----	-----	-----	-----
	4 weeks	514	-----	-----	-----	-----
	PCV Value	95	-----	-----	-----	-----
35	Total Solubility Parameter (TSP)	8.2	-----	-----	-----	-----

TABLE II (con't)

Example	11	12	13	14	15
Ricon 131MA	22.2	23.9	23.9	36.0	22.2
Poly bd R45HT	14.8	16.1	16.1	24.0	14.8
ADMA-14	1.26	1.0	1.0	0.9	1.3
Vikoflex 7190	3.0	----	----	----	----
Vikolox 12	----	7.33	3.13	----	----
Vikolox 16	----	----	----	14.1	6.8
FuelSaver	0.2	----	----	0.2	0.2
Flexon 650	19.9	26.0	26.0	21.9	20.0
Soybean Oil	38.14	25.67	29.87	6.8	34.7
A/E Ratio	0.75	0.38	0.9	0.38	0.49
Tear Strength N/cm	9.1	7.4	7.7	12.3	8.9
Tensile Strength N/cm ²	15.1	16.9	17.4	25.8	14.3
Elongation %	142	123	122	88	125
Geltime (minutes)	67.3	71.2	61.4	73.7	66.2
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	43.0	16.5	46.5	10.5	55.6
Change in quarter cone	28.2	3.3	33.8	3	38.6
% Weight Change	----	+0.03	+0.3	+0.3	+3.99
C-H Adhesion Value, N Flexgel	21.4	24.0	----	----	26.2
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	----
3 weeks	----	----	----	----	----
4 weeks	----	----	----	----	----
PCV Value	----	----	----	----	----
Total Solubility Parameter (TSP)	----	----	----	----	----

TABLE II (con't)

Example	16	17	18	19	20
Ricon 131MA	23.9	23.9	23.43	22.2	21.6
Poly bd R45HT	11.1	13.1	15.78	14.8	14.4
ADMA-14	1.0	1.0	0.98	1.26	----
Polybutadiene Oxide	5.0	3.0	----	----	----
ERL 4234	----	----	1.96	----	----
ERL 4221	----	----	----	3.4	----
BF-1000	----	----	----	----	5.94
Fuelsaver	0.4	0.3	----	0.2	0.2
Flexon 650	25.6	25.7	25.5	21.88	19.66
Soybean Oil	33.0	33.0	32.35	36.26	35.3
DAMA-810	----	----	----	----	2.9
A/E Ratio	0.61	1.0	1.0	0.51	0.45
Tear Strength N/cm	8.6	8.9	6.7	8.6	6.8
Tensile Strength N/cm ²	16.1	14.2	17.1	14.1	13.1
Elongation %	142	95	125	109	126
Geltime (minutes)	87.4	----	67.2	61.7	61.5
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	18	31.7	30.5	22.5	----
Change in quarter cone	8	19.9	21.5	11.0	----
% Weight Change	+1.2	+5.0	-4.6	-0.76	----
C-H Adhesion Value, N Flexgel	----	----	----	----	----
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	----
3 weeks	----	----	----	548	----
4 weeks	----	----	----	521	----
PCV Value	----	----	----	97	----
Total Solubility Parameter (TSP)	----	----	----	8.2	----

TABLE II (con't)

Example	21	22	23	24
5 Ricon 131MA	23.9	23.9	23.9	21.48
Poly bd R45HT	16.1	16.1	16.1	14.32
DAMA-810	----	----	----	3.0
ADMA-14	1.0	1.0	1.0	----
10 Vikoflex 9080	----	----	----	5.91
Vikolox 16	9.4	----	----	----
Vikolox 20-24	----	12.7	----	----
Vikolox 24-28	----	----	16.1	----
Flexon 650	16.6	13.3	9.9	19.67
Soybean Oil	33.0	33.0	33.0	35.42
15 A/E Ratio	0.38	0.37	0.37	0.48
Tear Strength N/cm	10.8	8.8	12.2	5.1
Tensile Strength N/cm ²	14.5	19.5	20.0	11.5
Elongation %	116	139	96	100
20 Geltime (minutes)	60	35.3	40.8	62
Gel-Clarity	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)				
25 Hardness (quarter cone)	21.2	23.3	9.8	26.3
Change in quarter cone	8.9	10.6	0.6	13.1
% Weight Change	+0.2	-0.3	+2.3	+0.8
30 C-H Adhesion Value, N Flexgel	----	----	----	26.2
Polycarbonate Compatibility 60°C (breaking force, N)				
35 1 week	----	----	----	----
3 weeks	----	----	----	528
4 weeks	----	----	----	530
PCV Value	----	----	----	98
40 Total Solubility Parameter (TSP)	----	----	----	8.2

TABLE II (con't)

Example	25	26	27	28	29
Ricon 131MA	59.45	27.8	17.06	30.49	34.52
Castor Oil	10.55	----	----	----	----
Ethoduomeen T-13	----	1.0	----	----	----
Nisso GI 3000	----	----	18.94	----	----
Amine Compound C	----	----	----	5.5	----
1,6-hexandithiol	----	----	----	----	1.49
DAMA-810	2.5	----	3.0	----	----
ADMA-14	----	----	----	1.5	1.5
Flexon 650	----	23.3	15.22	20.0	19.0
Soybean Oil	11.2	29.1	39.84	33.73	34.0
Vikoflex 9080	16.3	7.6	5.94	8.78	9.49
Poly bd R45HT	----	11.2	----	----	----
A/E Ratio	0.49	0.48	0.38	0.45	0.48
Tear Strength N/cm	6.5	2.2	4.7	5.3	3.2
Tensile Strength N/cm ²	14.4	6.7	10.4	12.2	7.9
Elongation %	130	101	116	103	104
Geltime (minutes)	----	10.5	341.4	373.1	30.2
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	8.9	----	24.7	17.0	----
Change in quarter cone	0.0	----	8.7	0.2	----
% Weight Change	+3.7	----	----	+4.8	----
C-H Adhesion Value, N Flexgel	----	----	23.6	12.9	14.2
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	----
3 weeks	----	----	----	----	----
4 weeks	----	----	----	----	----
PCV Value	----	----	----	----	----
Total Solubility Parameter (TSP)	----	----	----	----	----

TABLE II (con't)

Example	30	31	32	33	34
Ricon 131MA	21.6	21.6	21.6	21.69	11.32
Poly bd R45HT	14.4	14.4	14.4	14.4	7.55
DAMA 810	2.9	2.9	2.9	2.9	4.0
Nuoplaz 6959	55.16	-----	-----	-----	-----
Flexricin P-8	-----	-----	55.16	-----	-----
Emory 2900	-----	55.16	-----	-----	-----
Soybean Oil	-----	-----	-----	54.96	45.57
Vikoflex 9080	5.94	5.94	5.94	5.94	3.12
Fuelsaver	-----	-----	-----	0.2	0.2
Flexon 650	-----	-----	-----	-----	28.23
A/E Ratio	0.48	0.48	0.48	0.48	0.48
Tear Strength N/cm	6.5	5.6	9.1	6.5	1.9
Tensile Strength N/cm ²	15.9	14.3	14.5	11.7	3.4
Elongation %	108	107	131	105	208
Geltime (minutes)	81.8	135.1	81.8	-----	203.6
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	25.2	22.5	32.2	30.0	-----
Change in quarter cone	15.0	9.3	21.2	15.5	-----
% Weight Change	+5.5	-----	-----	-----	-----
C-H Adhesion Value, N					
Flexgel	34.7	23.1	-----	-----	-----
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	-----	-----	-----	-----	-----
3 weeks	-----	-----	-----	-----	-----
4 weeks	-----	-----	-----	-----	-----
PCV Value	-----	-----	-----	-----	-----
Total Solubility Parameter (TSP)	-----	8.1	-----	8.3	-----

TABLE II (con't)

Example	35	36	37	38	39
Lithene LX16-10MA	17.84	----	----	----	----
Ricon 184MA	----	44.26	28.43	----	----
Nisso BN 1015	----	----	----	----	14.8
PA-18	----	----	----	4.92	----
Poly bd R45HT	18.16	25.74	13.24	16.34	22.1
ADMA-14	1.5	1.0	1.3	----	----
DBU	----	----	----	0.38	0.34
Flexon 650	22.0	8.82	28.43	67.69	20.66
Soybean Oil	35.05	8.83	28.43	----	32.6
Vikoflex 9080	5.45	11.35	5.84	10.68	9.5
A/E Ratio	0.68	0.52	0.64	----	0.48
Tear Strength N/cm	7.2	10.7	4.0	2.3	1.8
Tensile Strength N/cm ²	17.0	17.0	6.0	3.4	4.0
Elongation %	92	286	279	195	195
Geltime (minutes)	28.9	143.3	285	----	----
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	17	11.7	37.8		
Change in quarter cone	-4.8	0.0	0.0		
% Weight Change	----	+4.1	----		
C-H Adhesion Value, N					
Flexgel	20.5	40.9	11.1	----	----
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	----
3 weeks	----	----	----	----	----
4 weeks	----	----	----	----	----
PCV Value	----	----	----	----	----
Total Solubility Parameter (TSP)	----	----	----	----	----

TABLE II (con't)

Example	40	41	42	43	44
Ricon 131MA	21.6	21.6	21.6	21.6	21.6
Poly bd R45HT	14.4	14.4	14.4	14.4	14.4
DAMA-810	2.9	2.9	2.9	2.9	2.9
Vikoflex 9080	5.94	5.94	5.94	5.94	5.94
Sunthene 450	35.3	35.3	35.3	35.3	35.3
Alpha-Terpinol	19.86	----	----	----	----
Yarmor 302	----	19.86	----	----	----
Witconol APM	----	----	19.86	----	----
Escopol R020	----	----	----	19.86	----
Trixylenyl Phosphate	----	----	----	----	19.86
A/E Ratio	0.48	0.48	0.48	0.48	0.48
Tear Strength N/cm	2.5	3.5	4.2	6.3	5.1
Tensile Strength N/cm ²	4.1	9.2	6.4	16.8	11.9
Elongation %	271	125	197	107	90
Geltime (minutes)	116.8	71.8	89.4	38.1	89.9
Gel-Clarity	T	T	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)					
Hardness (quarter cone)	46.7	29.7	39		
Change in quarter cone	5.2	15.4	13.7		
% Weight Change	+0.6	-1.3	+3.7		
C-H Adhesion Value, N					
Flexgel	13.8	27.6	18.7	24.5	28.9
Polycarbonate Compatibility 60°C (breaking force, N)					
1 week	----	----	----	----	----
3 weeks	----	----	----	----	----
4 weeks	----	----	----	----	----
PCV Value	----	----	----	----	----
Total Solubility Parameter (TSP)	----	----	----	----	----

TABLE II (con't)

Example	45	46	47
5 Ricon 131MA	34.12	21.6	21.6
Poly bd R45HT	----	14.4	14.4
DAMA-810	----	2.9	2.9
Flexon 650	19.0	----	----
10 Soybean Oil	32.16	----	----
DBU	0.34	----	----
1,9-nonanedithiol	1.88	----	----
Vikoflex 9080	12.5	5.94	5.94
Linseed Oil	----	35.3	35.3
Paol 40	----	19.86	----
15 Indopol H-100	----	----	19.86
A/E Ratio	0.36	0.48	0.48
Tear Strength N/cm	1.2	5.6	6.3
Tensile Strength N/cm ²	4.9	10.5	12.9
20 Elongation %	60	122	143
Geltime (minutes)	----	89.3	67.6
Gel-Clarity	T	T	T
Hydrolytic Stability			
25 (7 days, 100°C, water pH 11.5)			
Hardness (quarter cone)			
Change in quarter cone			
% Weight Change			
30 C-H Adhesion Value, N			
Flexgel	----	20.0	----
Polycarbonate Compatibility			
35 60°C (breaking force, N)			
1 week	----	----	----
3 weeks	----	----	----
4 weeks	----	----	----
PCV Value	----	----	----
40 Total Solubility			
Parameter (TSP)	----	----	----

TABLE III

COMPARATIVE EXAMPLES

Comparative Example	A	B	C	D	E
10 Ricon 131MA	22.2	21.0	22.2	22.2	22.2
Poly bd R45HT	14.8	14.0	14.8	14.8	14.8
ADMA-14	1.3	1.4	1.26	1.26	1.26
Fuelsaver	0.2	0.2	0.2	0.2	0.2
Flexon 650	25.6	25.5	20.6	20.6	19.9
15 Soybean Oil	34.7	35.9	39.94	39.94	38
Vikoflex 9080	1.2	2.0	----	----	----
Vikolox 12	----	----	1.0	----	----
Vikoflex 7190	----	----	----	1.0	0.5
A/E Ratio	2.4	1.4	2.6	2.3	4.5
20 Tear Strength N/cm	8.1	8.1	10.0	7.9	7.7
Tensile Strength N/cm ²	15.4	15.0	15.0	12.4	13.8
Elongation %	112	117	117	153	144
Geltime (minutes)	53.4	54.7	52.1	70.0	62.0
Gel-Clarity	T	T	T	T	T
25 Hydrolytic Stability	very	very			
(7 days, 100°C,	soft	soft	disin-	disin-	disin-
water pH 11.5)	did	did	tegrated	tegrated	tegrated
Hardness (quarter cone)	not	not			
Change in quarter cone	hold	hold			
30 % Weight Change	shape	shape			

TABLE III (con't)

COMPARATIVE EXAMPLES

Comparative Example	F	G	H
Ricon 131MA	23.66	20.44	24.36
Poly bd R45HT	15.94	14.56	15.64
ADMA-14	0.99	----	----
DBU	----	0.3	0.34
Flexon 650	25.74	----	27.66
Soybean Oil	32.68	----	32.0
Polybutadiene Oxide	0.99	----	----
Sunthane 480	----	36.0	----
Plasthall 100	----	28.7	----
A/E Ratio	2.9	----	----
Tear Strength N/cm	9.3	4.6	6.6
Tensile Strength N/cm ²	14.8	9.2	13.4
Elongation %	146	103	110
Geltime (minutes)	68.1	----	----
Gel-Clarity	T	T	T
Hydrolytic Stability (7 days, 100°C, water pH 11.5)	very soft, did	disin- tegrated	disin- tegrated
Hardness (quarter cone)	not		
Change in quarter cone	hold		
% Weight Change	shape		

TABLE IV

COMPARATIVE EXAMPLES

Comparative Example	I	J	K	L
	Control	Heated Control	D1000	Cas Chem 126
Polycarbonate Compatibility 50°C (breaking force, newtons)	538.4			
1 week		570	507	498
3 weeks		574	476	449
4 weeks		552	405	369
PCV Value			75	69

The data presented in Tables II - IV indicates that encapsulant compositions according to the invention are hydrolytically stable. The data further confirms that adhesion to conductors and polycarbonate compatibility are not adversely affected by use of oxirane materials in encapsulants of the invention. Without the oxirane material present, the resulting gel disintegrates as shown by comparative examples G and H in the hydrolytic stability test. Comparative examples A through F provide evidence that an inadequate amount of ox-

irane material leads to poor hydrolytic stability with very soft materials or disintegration resulting from this test. An important characteristic of encapsulants are their insulating properties which help prevent line losses or other transmission efficiencies in electrical cables or devices.

TABLE V

<u>Example</u>	<u>Dielectric Constant at 1 MHz</u>
1	2.93
3	2.88
19	2.91
26	2.83

In Table V the dielectric constants of Examples 1, 3, 19 and 26 are present. The table indicates that encapsulants according to the invention exhibit excellent electrical properties as a result of low dielectric constants of about or less than 3 at 1 MHz (as determined by ASTM D-150).

Claims

1. A grease compatible, hydrolytically stable dielectric encapsulant capable of being used to encapsulate a splice of a signal conducting device comprising:
an extended reaction product of an admixture of:
 - (a) from 3 to 60 weight percent of an anhydride functionalized compound having reactive anhydride sites;
 - (b) from 1.0 to 30 weight percent of a crosslinking agent capable of reacting with said anhydride functionalized composition to form a cured cross-linked material, said crosslinking agent being selected from polyols, polyamines and polythiols; and
 - (c) from 1.5 to 20 weight percent of an oxirane containing material to provide hydrolytic stability, said oxirane containing material being selected from aliphatic glycidyl ethers, aliphatic glycidyl esters, epoxidized dienes, epoxidized polyesters, epoxidized alpha olefins, epoxidized polyolefins, epoxidized natural rubber, and epoxidized oils;
 the admixture having a ratio of equivalents of anhydride functionalized compound to epoxy equivalent which is no greater than 1.25
 wherein the reaction product is extended with at least one plasticizer, present in the range of between 35 and 85 percent by weight of the encapsulant, and the said at least one plasticizer is essentially inert with the reaction product and is substantially nonexuding therefrom; the encapsulant having a C-H adhesion value of at least 4, the value being obtained by measuring the maximum pull out force in Newtons at a speed of 0.8 mm/sec of a 0.046 cm diameter and 15 cm long conductor from a test vessel filled with said encapsulant, the reaction product also having a solubility parameter of from 7.9 to 8.6.
2. An encapsulant as claimed in Claim 1 in which the oxirane containing material has at least one oxirane group.
3. An encapsulant as claimed in Claim 1 or Claim 2 in which the admixture has a ratio of equivalents of anhydride functionalized compound to epoxy equivalent of between 0.25 and 1.25.
4. An encapsulant as claimed in Claim 3 in which the ratio is between 0.25 and 0.55.
5. An encapsulant as claimed in any preceding Claim in which the oxirane containing material is an epoxidized oil.



irane material leads to poor hydrolytic stability with very soft materials or disintegration resulting from this test. An important characteristic of encapsulants are their insulating properties which help prevent line losses or other transmission efficiencies in electrical cables or devices.

TABLE V

<u>Example</u>	<u>Dielectric Constant at 1 MHz</u>
1	2.93
3	2.88
19	2.91
26	2.83

In Table V the dielectric constants of Examples 1, 3, 19 and 26 are present. The table indicates that encapsulants according to the invention exhibit excellent electrical properties as a result of low dielectric constants of about or less than 3 at 1 MHz (as determined by ASTM D-150).

Claims

1. A grease compatible, hydrolytically stable dielectric encapsulant capable of being used to encapsulate a splice of a signal conducting device comprising:
an extended reaction product of an admixture of:
 - (a) from 3 to 60 weight percent of an anhydride functionalized compound having reactive anhydride sites;
 - (b) from 1.0 to 30 weight percent of a crosslinking agent capable of reacting with said anhydride functionalized composition to form a cured cross-linked material, said crosslinking agent being selected from polyols, polyamines and polythiols; and
 - (c) from 1.5 to 20 weight percent of an oxirane containing material to provide hydrolytic stability, said oxirane containing material being selected from aliphatic glycidyl ethers, aliphatic glycidyl esters, epoxidized dienes, epoxidized polyesters, epoxidized alpha olefins, epoxidized polyolefins, epoxidized natural rubber, and epoxidized oils;
 the admixture having a ratio of equivalents of anhydride functionalized compound to epoxy equivalent which is no greater than 1.25
 wherein the reaction product is extended with at least one plasticizer, present in the range of between 35 and 85 percent by weight of the encapsulant, and the said at least one plasticizer is essentially inert with the reaction product and is substantially nonexuding therefrom; the encapsulant having a C-H adhesion value of at least 4, the value being obtained by measuring the maximum pull out force in Newtons at a speed of 0.8 mm/sec of a 0.046 cm diameter and 15 cm long conductor from a test vessel filled with said encapsulant, the reaction product also having a solubility parameter of from 7.9 to 8.6.
2. An encapsulant as claimed in Claim 1 in which the oxirane containing material has at least one oxirane group.
3. An encapsulant as claimed in Claim 1 or Claim 2 in which the admixture has a ratio of equivalents of anhydride functionalized compound to epoxy equivalent of between 0.25 and 1.25.
4. An encapsulant as claimed in Claim 3 in which the ratio is between 0.25 and 0.55.
5. An encapsulant as claimed in any preceding Claim in which the oxirane containing material is an epoxidized oil.



6. An encapsulant as claimed in Claim 5 in which the epoxidized oil is an epoxidized polyunsaturated vegetable oil.
7. An encapsulant as claimed in Claim 2 in which the oxirane containing material is selected from monoepoxy, diepoxy and polyepoxy compounds and combinations thereof.
8. An encapsulant as claimed in any preceding Claim further comprising a catalyst present in an amount between 0.1 and 5 percent by weight based on total solids of the reaction product.
9. An encapsulant as claimed in any preceding Claim having a tensile strength of less than 21.1 N/cm² and between 50 to 250 percent elongation.
10. An encapsulant as claimed in any preceding Claim having a total solubility parameter of between 8.0 to 8.3.
11. An encapsulant as claimed in any preceding Claim having a polycarbonate compatibility value of at least 80.
12. A signal transmission component comprising (a) a signal transmission device and (b) an encapsulant as claimed in any preceding Claim.
13. A process for filling an enclosure comprising pouring into said enclosure at ambient temperature a liquid encapsulant composition as claimed in any preceding Claim and allowing the composition to cure.

Patentansprüche

1. Schmiermittelverträgliche, hydrolytisch stabile dielektrische Einbettung, die zur Verwendung als Einbettung eines Spleißes einer Signalübertragungsvorrichtung fähig ist, umfassend:
ein gestrecktes Reaktionsprodukt eines Gemisches von:
 - (a) 3 bis 60 Gew.-% einer mit einem Anhydrid funktionalisierten Verbindung mit reaktiven Anhydridstellen,
 - (b) 1.0 bis 30 Gew.-% eines Vernetzungsmittels, das zur Reaktion mit der mit dem Anhydrid funktionalisierten Zusammensetzung fähig ist, wobei ein gehärtetes vernetztes Material gebildet wird, wobei das Vernetzungsmittel ausgewählt ist aus Polyolen, Polyaminen und Polythiolen; und
 - (c) 1.5 bis 20 Gew.-% einer Oxiran enthaltenden Substanz, um hydrolytische Stabilität zu verleihen, wobei die Oxiran enthaltende Substanz ausgewählt ist aus aliphatischen Glycidylethern, aliphatischen Glycidylestern, epoxidierten Dienen, epoxidierten Polyestern, epoxidierten Alphaolefinen, epoxidierten Polyolefinen, epoxidiertem natürlichem Kautschuk und epoxidierten Ölen,
 wobei das Gemisch ein Verhältnis von Äquivalenten von mit einem Anhydrid funktionalisierter Verbindung zu Epoxyäquivalenten aufweist, das nicht größer als 1.25 ist, wobei das Reaktionsprodukt mit mindestens einem Weichmacher gestreckt ist, der in einem Bereich zwischen 35 und 85 Gew.-% der Einbettung vorhanden ist, wobei dieser mindestens eine Weichmacher im wesentlichen inert zum Reaktionsprodukt ist und nicht wesentlich daraus ausschwitzt; die Einbettung einen C-H-Adhäsionswert von mindestens 4 aufweist, wobei der Wert durch Messen der maximalen Herausziehkraft in Newton bei einer Geschwindigkeit von 0,8 mm/Sek. eines Leiters mit 0,046 cm Durchmesser und 15 cm Länge aus einem Testgefäß, das mit der Einbettung gefüllt ist, erhalten wird, wobei das Reaktionsprodukt auch einen Löslichkeitsparameter von 7,9 bis 8,6 aufweist.
2. Einbettung nach Anspruch 1, in der die Oxiran enthaltende Substanz mindestens eine Oxirangruppe aufweist.
3. Einbettung nach Anspruch 1 oder 2, in der das Gemisch ein Verhältnis von Äquivalenten der mit einem Anhydrid funktionalisierten Verbindung zu Epoxy-äquivalenten zwischen 0,25 und 1,25 aufweist.
4. Einbettung nach Anspruch 3, wobei das Verhältnis zwischen 0,25 und 0,55 ist.
5. Einbettung nach einem der vorstehenden Ansprüche, in der die Oxiran enthaltende Substanz ein epoxi-



diertes Öl ist.

6. Einbettung nach Anspruch 5, in der das epoxidierte Öl ein epoxidiertes polyungesättigtes pflanzliches Öl ist.
7. Einbettung nach Anspruch 2, in der die Oxiran enthaltende Substanz ausgewählt ist aus Monoepoxy-, Diepoxy- und Polyepoxyverbindungen und Gemischen davon.
8. Einbettung nach einem der vorstehenden Ansprüche, die weiter einen Katalysator umfaßt, der in einer Menge zwischen 0,1 und 5 Gew.-%, bezogen auf die gesamten Feststoffe des Reaktionsprodukts, vorhanden ist.
9. Einbettung nach einem der vorstehenden Ansprüche, mit einer Zugfestigkeit von weniger als 21,1 N/cm² und 50 bis 250 % Dehnung.
10. Einbettung nach einem der vorstehenden Ansprüche mit einem Gesamtlöslichkeitsparameter zwischen 8,0 und 8,3.
11. Einbettung nach einem der vorstehenden Ansprüche mit einem Polycarbonatverträglichkeitswert von mindestens 80.
12. Signalübertragungsbauteil, umfassend (a) eine Signalübertragungsvorrichtung und (b) ein Einbettungsmittel nach einem der vorstehenden Ansprüche.
13. Verfahren zum Füllen eines Einschlusses, umfassend das Eingießen einer flüssigen Einbettungszusammensetzung nach einem der vorstehenden Ansprüche bei Umgebungstemperatur in den Einschluß und Härtenlassen der Zusammensetzung.

Revendications

1. Composition d'encapsulation diélectrique, stable à l'hydrolyse, compatible avec les graisses, pouvant être utilisée pour encapsuler une épissure d'un dispositif conduisant des signaux, comprenant :
un produit de réaction plastifié d'un mélange :
 - (a) de 3 à 60 % en poids d'un composé à fonctionnalité anhydride comportant deux sites anhydride réactifs ;
 - (b) de 1,0 à 30 % en poids d'un agent de réticulation à même de réagir avec ladite composition à fonctionnalité anhydride pour former un matériau réticulé durci, l'agent de réticulation étant choisi parmi les polyols, les polyamides et les polythiols ; et
 - (c) de 1,5 à 20 % en poids d'un matériau contenant de l'oxiranne, destiné à conférer une stabilité à l'hydrolyse, le matériau contenant de l'oxiranne étant choisi parmi les éthers glycidyliques aliphatiques, les esters glycidyliques aliphatiques, les diènes époxydés, les polyesters époxydés, les alpha-oléfines époxydées, les polyoléfines époxydées, le caoutchouc naturel époxydé et les huiles époxydées ;
le mélange présentant un rapport entre équivalents du composé à fonctionnalité anhydride et du composé époxydique, non supérieur à 1,25,
où le produit de la réaction est plastifié par au moins un plastifiant, présent en une quantité de 35 à 85 % en poids par rapport à la composition d'encapsulation, ledit au moins un plastifiant étant essentiellement inerte vis-à-vis du produit de la réaction et ne pouvant pour ainsi dire pas s'en échapper par exsudation, la composition d'encapsulation ayant un indice d'adhérence C-H d'au moins 4, cet indice étant obtenu par la mesure de la force maximale, en newtons, pour tirer, à une vitesse de 0,8 mm/s, un conducteur de 0,046 cm de diamètre et de 15 cm de longueur à partir d'un récipient d'essai rempli de la composition d'encapsulation, le produit de la réaction ayant aussi un paramètre de solubilité de 7,9 à 8,6.
2. Composition d'encapsulation selon la revendication 1, dans laquelle le matériau contenant l'oxiranne possède au moins un groupe oxiranne.
3. Composition d'encapsulation selon la revendication 1 ou 2, dans laquelle le mélange présente un rapport



entre équivalents du composé à fonctionnalité anhydride et des groupes époxy compris entre 0,25 et 1,25.

4. Composition d'encapsulation selon la revendication 3, dans lequel le rapport est compris entre 0,25 et 0,55.
5. Composition d'encapsulation selon l'une quelconque des revendications précédentes, dans laquelle le matériau contenant de l'oxiranne est une huile époxydée.
6. Composition d'encapsulation selon la revendication 5, dans laquelle l'huile époxydée est une huile végétale polyinsaturée époxydée.
7. Composition d'encapsulation selon la revendication 2, dans laquelle le matériau contenant de l'oxiranne est choisi parmi l'ensemble comprenant les composés monoépoxydiques, diépoxydiques et polyépoxydiques et leurs combinaisons.
8. Composition d'encapsulation selon l'une quelconque des revendications précédentes, qui comprend en outre un catalyseur présent en une quantité de 0,1 à 5 % en poids par rapport à l'extrait sec total du produit de la réaction.
9. Composition d'encapsulation selon l'une quelconque des revendications précédentes, qui a une résistance à la traction inférieure à 21,1 N/cm² et un allongement de 50 à 250 %.
10. Composition d'encapsulation selon l'une quelconque des revendications précédentes, qui présente un paramètre de solubilité totale de 8,0 à 8,3.
11. Composition d'encapsulation selon l'une quelconque des revendications précédentes, qui présente un indice de compatibilité avec les polycarbonates d'au moins 80.
12. Composant de transmission de signaux comprenant
 - (a) un dispositif de transmission de signaux et
 - (b) une composition d'encapsulation selon l'une quelconque des revendications précédentes.
13. Procédé pour remplir une enceinte, qui consiste à verser dans cette enceinte et à la température ambiante une composition d'encapsulation liquide selon l'une quelconque des revendications précédentes, et à permettre à la composition de durcir.