



9900169-5

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : B01J 31/26, 31/32	A1	(11) International Publication Number: WO 98/02247 (43) International Publication Date: 22 January 1998 (22.01.98)
(21) International Application Number: PCT/US97/11095 (22) International Filing Date: 25 June 1997 (25.06.97) (30) Priority Data: 08/680,419 15 July 1996 (15.07.96) US (71) Applicant: MOBIL OIL CORPORATION [US/US]; 3225 Gallows Road, Fairfax, VA 22037 (US). (72) Inventors: HSIEH, John, Tai-Tung; 9 Ellsworth Drive, Warren, NJ 07060 (US). SCHREGENBERGER, Sandra, Denise; 5 Hope Court, Neshanic, NJ 08853 (US). (74) Agents: SCHNELLER, Marina, V. et al.; Mobil Oil Corporation, 3225 Gallows Road, Fairfax, VA 22037 (US).	(81) Designated States: AU, CA, JP, KR, SG, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>	
(54) Title: COMONOMER PRETREATED BIMETALLIC CATALYST FOR BLOW MOLDING AND FILM APPLICATIONS		
(57) Abstract The invention relates to a catalyst component which is a contact product of reagents comprising: silica which has a pore volume which exceeds 2.9 cc/gram and an average pore diameter which exceed 400 Angstroms; a metallocene of a first transition metal, activated by an alumoxane; a contact product of dialkylmagnesium and trialkylsilanol; a second transition metal source which exhibits a hydrogen response which is different from that of the metallocene; and an olefin of 4 to 20 carbon atoms. This catalyst component is activated by an aluminum alkyl activator.		