



159159

Process for rendering an ash inert, artificial
pozzolana obtained by means of the said process

5 The invention relates to a process for rendering inert ash originating from the incineration of municipal waste.

The incinerators used to destroy municipal waste
10 (domestic waste and hospital waste) produce generally large volumes of ash, both in the form of clinker in the incineration furnaces and of fly ash entrained in the flue gases. The mineralogical composition of this ash does not vary by very much, whatever its origin,
15 and the following are generally encountered therein, although in proportions which can vary by as much as 100%, indeed even more: alkali metal chlorides (NaCl and KCl), calcium (usually in the form of calcium carbonate, calcium sulphate, calcium hydroxide or
20 calcium hydroxychloride, in particular calcium hydroxide and calcium sulphate), quartz, vitrified aluminosilicates, heavy metals in the metallic or combined form (in particular tin, zinc, lead, cadmium, mercury, copper and chromium), chlorinated organic
25 derivatives and nonincinerated materials. The nonincinerated materials usually include aluminium metal.

International Application WO 00/29095 discloses a
30 process for rendering inert waste originating from incinerator flue gases, according to which this waste is dispersed with a hydraulic binder in water and then filtered off.

35 The process was improved by using, for the filtration stage, a belt filter, which makes it possible to subject the filtration cake to efficient washing. This washing of the cake improves the mechanical properties



G00002

and the resistance to leaching of the inerted waste resulting from the process.

European Patent EP-883 585 [Solvay (Société Anonyme)]
5 provides a process for rendering inert ash comprising heavy metals. According to this known process, the ash is first washed and filtered, in order to remove the water-soluble materials present therein, and the aqueous cake collected from the filtration is treated
10 with phosphoric acid or an alkali metal phosphate. The phosphate-comprising residue thus obtained is subsequently calcined and then a hydraulic binder and water are added to form a hydraulic mortar. On conclusion of this known process, a solid inorganic
15 mass is obtained which is substantially inert with respect to atmospheric agents and which conforms to the standards for toxicity by leaching, in particular the TCLP (Toxicity Characteristic Leaching Procedure, USA) standard.

20 These known processes apply to all types of ash, in particular to fly ash originating from the incineration of domestic or hospital waste. They involve a hydraulic binder.

25 In the case of ash originating from the incineration of municipal waste, an improvement to these known processes has now been found which makes it possible to dispense with the hydraulic mortar without harming the
30 inert nature of the treated ash.

Consequently, the invention relates to a process for rendering inert an ash originating from the incineration of municipal waste, according to which the
35 ash is subjected successively to treatment with a water-soluble phosphate in the presence of water and to calcination; according to the invention, the treatment with the phosphate is carried out under conditions

adjusted to crystallize hydroxylapatite [sic] and/or whitlockite.

5 In the process according to the invention, the ash comprises a clinker from a furnace for the incineration of municipal waste and/or a fly ash which was separated from the flue gas originating from such an incineration furnace.

10 The term "municipal waste" is intended to denote domestic waste and hospital waste. This waste normally comprises metals (including heavy metals and aluminium), calcium-comprising compounds (generally calcium hydroxide and calcium sulphate), sodium-
15 comprising compounds (in particular sodium chloride) and organic compounds (in particular chlorinated organic compounds and items made of plastic, especially made of poly(vinyl chloride)).

20 The term "heavy metals" is intended to denote metals with a density at least equal to 5 g/cm^3 , and beryllium, arsenic, selenium and antimony, in accordance with the generally accepted definition (Heavy Metals in Wastewater and Sludge Treatment
25 Processes, Vol. I, CRC Press Inc., 1987, page 2).

The amount of heavy metals in the ash subjected to the process according to the invention depends on the origin of the municipal waste. It is usually between
30 0.5 and 15 parts by weight per 100 parts by weight of dry matter of the ash, more generally between 3.0 and 10 parts by weight per 100 parts by weight of the ash.

Aluminium is generally present in the ash in an amount
35 of 2.0 to 8.0 parts by weight per 100 parts by weight of the ash, more generally in an amount of 3.0 to 5.0 parts by weight per 100 parts by weight of the ash.

In the process according to the invention, the water-soluble phosphate reacts with the calcium of the ash, forming calcium phosphate. The water-soluble phosphate is generally phosphoric acid or an alkali metal phosphate, for example sodium phosphate. Orthophosphoric acid is preferred.

In accordance with the invention, the treatment with the phosphate is carried out under conditions adjusted in order for the calcium phosphate which is formed to be in the form of crystals of hydroxylapatite [sic] and/or of whitlockite.

Hydroxylapatite [sic] is a mineral of general formula $\text{Ca}_5(\text{PO}_4)_3(\text{OH})$. Whitlockite is a mineral of general formula $\text{Ca}_9\text{Fe}_x\text{Mg}_{1-x}\text{H}(\text{PO}_4)_7$, where x is an integer or fractional number between 0 and 1.

The crystals of hydroxylapatite [sic] and of whitlockite have the property of allowing, by isomorphism, substitution of a portion of their calcium atoms by atoms of heavy metals. The amount of hydroxylapatite [sic] and/or of whitlockite crystallized must consequently be sufficient for these minerals to absorb the heavy metals of the ash in their respective crystal lattices. The optimum amount of hydroxylapatite [sic] and/or of whitlockite to be crystallized will consequently depend on the amount of heavy metals present in the ash and it must consequently be determined in each specific case by a routine operation in the laboratory. The amount of hydroxylapatite [sic] and/or of whitlockite to be crystallized will itself condition the amount of water-soluble phosphate which has to be added to the ash. Depending on the origin of the latter, the amount by weight of water-soluble phosphate employed (expressed in the H_3PO_4 form) can vary, for example, from 10 to 20% of the weight of dry matter of the ash. Furthermore, the formation of hydroxylapatite [sic] and of

whitlockite requires the presence of calcium in the ash. Depending on the amount of hydroxylapatite [sic] and/or whitlockite to be crystallized, the amount by weight of calcium (expressed in the CaO form) can vary, 5 for example, from 10 to 35% of the weight of dry matter of the ash. In an alternative form, if required, additional calcium (in the metallic or combined form) has to be added to the ash before or during the addition of the water-soluble phosphate in order to 10 obtain the required amount of crystals of hydroxylapatite [sic] and/or of whitlockite. Use is advantageously made of calcium carbonate, preferably avoiding basic calcium compounds, in particular calcium hydroxide.

15 In the process according to the invention, the water-soluble phosphate is added to the ash in the presence of water. The water must be present in an amount at least sufficient to crystallize the hydroxylapatite 20 [sic] and/or the whitlockite. In practice, it is present in an amount of greater than 10% (preferably at least equal to 25%) of the weight of dry matter of the ash. In practice, it is not advantageous for the amount of water employed to exceed 100% of the dry matter of 25 the ash. The values from 30 to 75% are generally highly suitable.

In the process according to the invention, the calcination has a twofold function. First, it serves to 30 destroy the organic compounds of the ash. Secondly, it brings about a recrystallization of the hydroxylapatite [sic] and/or of the whitlockite. The calcination is normally carried out at a temperature of greater than 400°C, preferably at least equal to 600°C. It is not 35 advantageous to exceed a temperature of 1 000°C. The temperatures from 600 to 950°C are especially advantageous. The calcination can be carried out in an inert atmosphere (for example, under a nitrogen atmosphere). It is preferable to carry out the

calcination in the presence of air, so as to bring about the combustion of the organic compounds, in particular halogenated organic compounds.

- 5 The recrystallization of the hydroxylapatite [sic] and/or of the whitlockite has the advantageous result of strengthening the insoluble nature of these compounds in water.
- 10 In an advantageous embodiment of the process according to the invention, before the treatment of the ash with the phosphate, the ash is subjected to alkaline aqueous washing at a pH of greater than 8.5, for example from 9 to 14, preferably from 9.5 to 13. In this embodiment,
- 15 the pH is measured on the aqueous solution collected from the washing. This embodiment of the process is targeted at removing the water-soluble compounds of the ash. It exhibits the additional advantage that the ash collected from the washing is found under the optimum
- 20 conditions for obtaining the crystallization of hydroxylapatite [sic] and/or of whitlockite during the treatment with the water-soluble phosphate.

- In another specific embodiment of the process according to the invention, which is especially suited to the case of an ash comprising chromium in the hexavalent state, a reducing agent is added to the ash collected from the treatment with the phosphate. In this embodiment of the process, the function of the reducing
- 30 agent is to reduce the hexavalent chromium in order to bring it to a lower valency state. Iron metal (for example iron filings) and carbon (for example active carbon) constitute preferred reducing agents. The reducing agent is advantageously employed in an amount
- 35 by weight substantially of between 0.3 and 1% by weight of the ash.

The ash collected from the process according to the invention exists in the form of a pulverulent or

granular inorganic mass which is inert with respect to the environment and atmospheric agents and which conforms to the standards for toxicity by leaching, particularly the TLCP standard defined above. This
5 inorganic mass exhibits the noteworthy and unexpected property of having a pozzolanic capability which marks it out for forming hydraulic binders.

In the case where the ash subjected to the process
10 according to the invention comprises calcium sulphate, it may prove to be desirable to decompose the latter. This is because it has been observed that if, on conclusion of the calcination, the ash comprises calcium sulphate, the latter has a detrimental effect
15 on the hydraulic properties of the ash.

To this end, in a specific embodiment of the process according to the invention, the ash is subjected, before or after the calcination, to washing with a
20 solution of sodium carbonate or of sodium hydroxide (for example, at pH 13), so as to dissolve the aluminium by oxidation of the latter. The washing can be carried out at ambient temperature or at a higher temperature, for example from 40 to 75°C.

25 In an especially advantageous embodiment of the process according to the invention, the ash is washed with an aqueous alkali metal carbonate solution at a pH of greater than 10 to decompose the calcium sulphate. The
30 washing is advantageously carried out at a pH of 12 to 13. In this embodiment of the invention, the pH is measured on the aqueous solution collected from the washing. In the embodiment which has just been described, the washing of the ash with the sodium
35 carbonate solution can be carried out on the ash downstream of the calcination. However, it is preferable, according to an advantageous alternative form of the invention, for the washing with the aqueous sodium carbonate solution to be carried out at the same

time as the washing of the ash, upstream of the treatment with the water-soluble phosphate.

It has been observed that in the case where the ash
5 recovered from the calcination comprising aluminium metal, the latter has a detrimental effect on the pozzolanic properties of the ash, resulting in uncontrollable swelling of the mortars.

10 To this end, in a preferred embodiment of the process according to the invention, the ash is subjected to oxidizing heating in order to oxidize the aluminium metal to alumina. For the implementation of this
15 embodiment of the invention, the oxidizing heating is advantageously carried out at the same time as the calcination, the latter then being carried out in an oxidizing atmosphere (for example, air) at a temperature of greater than 800°C, preferably of 900 to 1 000°C.

20 The ash collected on conclusion of the process according to the invention can be stored in a landfill site without risk to the environment (in particular to ground water and surface water). It can also be
25 recovered in value, such as in civil engineering works, for example in road metals or as filling material in bitumen road surfaces. Because of its pozzolanic properties, the ash collected on conclusion of the process according to the invention finds an especially
30 advantageous use in the manufacture of hydraulic cements.

Consequently, the invention also relates to an
artificial pozzolana, obtained by subjecting an ash
35 originating from the incineration of municipal waste to an inerting process in accordance with the invention, and to hydraulic binders comprising this artificial pozzolana.

The invention is illustrated by the following description of the single figure of the appended drawing, which represents the diagram of a plant employing a specific embodiment of the process
5 according to the invention.

The plant represented in the figure comprises a furnace 1 in which municipal waste 2 is incinerated. A clinker 3, on the one hand, and a flue gas 4, on the
10 other hand, are collected from the furnace 1. The flue gas 4 is laden with fly ash and in addition is contaminated by toxic gaseous compounds, particularly hydrogen chloride and volatile heavy metals. It is first treated in a dust separator 5 (for example, an
15 electrostatic precipitator), where the fly ash 6 is separated therefrom. The dedusted flue gas 7 is subsequently treated in a purification device 8, known per se, in order to extract therefrom the acidic gaseous compounds, and then it is discharged to the
20 chimney 9.

The clinker 3 and the fly ash 6 are mainly composed of inorganic compounds and of chlorinated organic compounds, in particular dioxins and furans.
25

The clinker is treated in a mill 10 and the milled clinker 11 is subsequently introduced with the fly ash 6 into a mixing chamber 23. An ash 24 is collected from the chamber 23 and is sent to a washing chamber
30 12. The ash 24 is dispersed, in the washing chamber 12, in an amount of water 13 sufficient to dissolve substantially all the water-soluble compounds present in the ash. In addition, sodium carbonate 14, intended to react with the calcium sulphate of the ash to form
35 insoluble calcium carbonate and sodium sulphate, which passes into solution, is introduced into the chamber 12. The pH in the washing medium of the chamber 12 settles at approximately 12.5. An aqueous suspension 15 is collected from the washing chamber and is treated

immediately on a filter 16. An aqueous solution 17, on the one hand, and an aqueous cake 18, on the other hand, are separated from the filter 16.

5 The cake 18 comprises most of the heavy metals, in addition to the dioxins and the furans, of the ash 24. In addition, it comprises calcium (mainly in the form of calcium hydroxide and calcium carbonate) and is impregnated with water. In accordance with the
10 invention, it is introduced into a reaction chamber 19, where orthophosphoric acid 20, extra water 25 and iron filings 26 are added thereto. The phosphoric acid 20 reacts with the calcium compounds and with the water to crystallize hydroxylapatite [sic] and/or whitlockite.
15 The function of the iron filings 26 is to reduce the hexavalent chromium. An ash 21 comprising crystals of hydroxylapatite [sic] and/or of whitlockite is collected from the reaction chamber 19. It is transferred to a calcination chamber 22, where it is
20 heated at a temperature of approximately 950°C in the presence of air for a time sufficient to decompose the dioxins and furans, to oxidize the aluminium metal to the form of alumina and to recrystallize the hydroxylapatite [sic] and/or the whitlockite. A dry
25 pulverulent mass 27 which is inert and which exhibits the properties of an artificial pozzolana is collected from the calcination chamber 22. The artificial pozzolana 27 can advantageously be used in the manufacture of hydraulic binders.

30

The examples described below will reveal the advantage of the invention.

In these examples, a fly ash from the incineration of
35 domestic waste was treated, this fly ash having the composition which appears in Table 1 below (analysis carried out by X-ray fluorescence).

Table 1

Constituent	Content (mg/kg)
Al	27 209
Ba	2 864
Br	913
Ca	131 055
Cd	494
Cl	170 814
Cr	636
Cu	1 430
Fe	12 688
K	90 251
Mg	10 447
Mn	701
Mo	576
Na	11 894
Nb	10
Ni	101
P	3 246
Pb	11 226
Rb	121
S	50 698
Sb	1 020
Si	44 950
Sn	1 502
Sr	516
Ti	8 224
V	107
Zn	18 123

Example 1

5 100 g of ash were withdrawn and were subjected to a washing operation. To this end, the ash was dispersed in an aqueous solution composed of 1 l of demineralized water comprising 50 g of sodium carbonate and the aqueous suspension thus obtained was subjected to
10 moderate stirring for 2 hours at ambient temperature.

The aqueous suspension was subsequently filtered, the filtration cake was dried and the dry cake was weighed: 78.2 g.

- 5 70 g of the dry cake were withdrawn and were subjected to the inerting process. To this end, 70 g of water and 7 g of phosphoric acid (which corresponds to 0.1 kg of phosphoric acid per kg of dry cake) were successively added to it and the resulting mixture was calcined at
- 10 750°C for 1 hour. The dry powder collected on conclusion of the calcination was subjected to a standardized test of toxicity by leaching. To carry out this test, 30 g of the powder were withdrawn and were subjected to three successive leachings with 300 ml of
- 15 demineralized water. The three leaching solutions were collected and mixed and the composition of the mixture of the leaching solutions which is thus obtained was analysed. The result of the analysis appears in Table 2 below.

Table 2

Constituents	Contents (mg/kg of solution)
Al	9.5
As	0.024
Ba	0.2
Ca	5.6
Cd	<0.01
Co	<0.04
Cr	0.42
Cr(VI)	<0.2
Cu	0.01
Fe	<0.02
Hg	0.03
Mg	0.3
Mn	<0.01
Mo	0.84
Ni	<0.03
Pb	<0.3
Sb	0.17
Sn	<0.02
Sr	0.2
Ti	<0.01
Tl	0.3
V	<0.03
Zn	0.05

Example 2

- 5 The test of Example 1 is repeated under the following conditions:

Washing solution: 1 l of demineralized water, as such, without sodium carbonate,

Phosphoric acid: 4.5 g (which corresponds to 0.1 kg/kg of dry cake),

Calcination: 750°C for 1 hour.

The results of the test of toxicity by leaching are recorded in Table 3 below.

Table 3

Constituents	Contents (mg/kg of solution)
Al	16
As	<0.01
Ba	0.2
Ca	778
Cd	<0.01
Co	<0.03
Cr	2.4
Cr (VI)	0.65
Cu	0.02
Fe	<0.01
Hg	0.005
Mg	2.5
Mn	<0.001
Mo	2.8
Ni	<0.03
Pb	<0.50
Sb	0.01
Sn	<0.05
Sr	3.9
Ti	<0.02
Tl	<0.50
V	<0.03
Zn	

5

Example 3

10 In order to demonstrate the pozzolanic nature of the treated ash, the following comparative test was carried out. 75 g of road hydraulic binder "ARC 3" (composed of 78% slag, 11% quicklime and 5% clinker) were mixed with 25 g of ash treated according to the invention. The resulting mixture was mixed with water and subjected to

setting and curing. The mechanical properties of the mortar obtained were measured according to the EN 196-1 standard and were compared with the properties of a mortar obtained starting from 100% of road hydraulic binder "ARC 3".

	Term (days)	Flexural strength (MPa)	Compressive strength (MPa)
100% Road binder "ARC 3"	60 d	7.4	32.0
75% Road binder "ARC 3" + 25% treated ash	60 d	7.3	33.2

The substitution of 25% of binder by treated ash does not reduce the mechanical properties of the mortar, which shows the pozzolanic nature of the treated ash.

The preceding examples show the good ability of the process according to the invention to render inert the heavy metals of fly ash.

15

Comparison of the results of Example 1 with those of Example 2 reveals in addition the advantage of incorporating sodium carbonate in the water used to wash the fly ash, as regards rendering inert toxic metals, in particular chromium (especially chromium(VI)), aluminium, molybdenum and strontium.

20

CLAIMS

1. Process for rendering inert an ash originating from the incineration of municipal waste, according to
5 which the ash is subjected successively to treatment with a water-soluble phosphate in the presence of water and to calcination, characterized in that the treatment with the phosphate is carried out under conditions adjusted to crystallize hydroxylapatite [sic] and/or
10 whitlockite.
2. Process according to Claim 1, characterized in that, before the treatment with the phosphate, the ash is subjected to alkaline washing at a pH of greater
15 than 8.5.
3. Process according to Claim 2, characterized in that the washing is carried out at a pH of 9.5 to 13.
- 20 4. Process according to any one of Claims 1 to 3, characterized in that a reducing agent is added to the ash.
5. Process according to any one of Claims 1 to 4,
25 characterized in that, in the case where the ash comprises calcium sulphate, it is washed with an aqueous alkali metal carbonate solution at a pH of greater than 10.
- 30 6. Process according to Claim 5, characterized in that the washing of the ash with the alkali metal carbonate solution is carried out at a pH of 12 to 13.
7. Process according to any one of Claims 1 to 6,
35 characterized in that, in the case where the ash comprises aluminium metal, it is subjected to a treatment for oxidation of the said aluminium metal.

8. Process according to Claim 7, characterized in that the treatment for oxidation of the aluminium metal comprises an oxidizing heating of the ash.
- 5 9. Process according to Claim 8, characterized in that, to carry out the oxidizing heating of the ash, the calcination is carried out at a temperature of 900 to 1 000°C.
- 10 10. Artificial pozzolana, obtained by subjecting an ash originating from the incineration of municipal waste to an inerting process in accordance with any one of Claims 1 to 9.