Claims

[Claim 1]

An optical pressure-sensitive adhesive sheet comprising a pressure-sensitive adhesive layer, wherein

the optical pressure-sensitive adhesive sheet does not comprise a foam layer, and

the pressure-sensitive adhesive layer has a compressibility of the pressure-sensitive adhesive layer after 300 seconds from pressure release in the following compression test of 3.5% or less:

<Compression test>

A disk-shaped pressure-sensitive adhesive layer having a thickness of 1 mm and a diameter of 8 mm is pressurized at 0.35 MPa from above and below at 50°C for 10 seconds, and left to still stand for 300 seconds after pressure release.

[Claim 2]

The optical pressure-sensitive adhesive sheet according to claim 1, wherein a compressibility immediately after pressurizing for 10 seconds in the compression test is 20% or more.

[Claim 3]

The optical pressure-sensitive adhesive sheet according to claim 1 or 2, wherein a gel fraction of the pressure-sensitive adhesive layer is 73% or more.

[Claim 4]

An optical member laminate comprising the optical pressure-sensitive adhesive sheet according to any one of claims 1 to 3.

[Claim 5]

The optical member laminate according to claim 4, wherein the optical member laminate is an image display apparatus.