OPTICAL SYSTEMS FABRICATED BY PRINTING-BASED ASSEMBLY

CROSS-REFERENCE TO RELATED APPLICATIONS

[001] This application claims the benefit of priority to U.S. Provisional Patent Applications 60/885,306 filed January 17, 2007 and 60/944,611 filed June 18, 2007, both of which are hereby incorporated by reference in their entirety to the extent not inconsistent with the disclosure herein.

STATEMENT REGARDING FEDERALLY SPONSORED RESEARCH OR DEVELOPMENT

[002] This invention was made, at least in part, with United States governmental support under DEFG02-91-ER45439 awarded by U.S. Department of Energy. The United States Government has certain rights in this invention.

BACKGROUND OF INVENTION

[003] Since the first demonstration of a printed, all polymer transistor in 1994, a great deal of interest has been directed at development of a new class of electronic systems comprising flexible integrated electronic devices on plastic substrates. [Garnier, F., Hajlaoui, R., Yassar, A. and Srivastava, P., Science, Vol. 265, pgs 1684 – 1686] Substantial research has been directed over the last decade toward developing new solution processable materials for conductors, dielectrics and semiconductors elements for flexible polymer-based electronic devices. Progress in the field of flexible electronics is not only driven by the development of new solution processable materials but also by new device geometries, techniques for high resolution, dense patterning of large substrate areas, and high throughput processing strategies compatible with plastic substrates. It is expected that the continued development of new materials, device configurations and fabrication methods will play an essential role in the rapidly emerging new class of flexible integrated electronic devices, systems and circuits.

[004] Interest in the field of flexible electronics arises out of several important advantages provided by this technology. First, the mechanical ruggedness of plastic substrates provides a platform for electronic devices less susceptible to damage and/or electronic performance degradation caused by mechanical stress. Second, the inherent

flexibility and deformability of plastic substrate materials allows these materials to be integrated into useful shapes, form factors and configurations not possible with conventional brittle silicon based electronic devices. For example, device fabrication on flexible, shapeable and/or bendable plastic substrates has potential to enable a class of functional devices having revolutionary functional capabilities, such as electronic paper, wearable computers, large-area sensors and high resolution displays, that are not feasible using established silicon-based technologies. Finally, electronic device assembly on flexible plastic substrates has potential for low cost commercial implementation via high speed processing techniques, such as printing, capable of assembling electronic devices over large substrate areas.

[005] Despite considerable motivation to develop a commercially feasible platform for flexible electronics, the design and fabrication of flexible electronic devices exhibiting good electronic performance continues to present a number of significant technical challenges. First, conventional well-developed methods of making single crystalline silicon based electronic devices are incompatible with most plastic materials. For example, traditional high quality inorganic semiconductor components, such as single crystalline silicon or germanium semiconductors, are typically processed by growing thin films at temperatures (> 1000 degrees Celsius) that significantly exceed the melting or decomposition temperatures of most or all plastic substrates. In addition, many inorganic semiconductors are not intrinsically soluble in convenient solvents that would allow for solution based processing and delivery. Second, although amorphous silicon, organic or hybrid organic-inorganic semiconductors have been developed that are compatible with low temperature processing and integration into plastic substrates, these materials do not exhibit electronic properties comparable to conventional single crystalline semiconductor based systems. Accordingly, the performance of electronic devices made from these alternative semiconductor materials is less than current state of the art high performance semiconductor devices. As a result of these limitations, flexible electronic systems are presently limited to specific applications not requiring high performance, such as use in switching elements for active matrix flat panel displays with non-emissive pixels and in light emitting diodes.

[006] Macroelectronics is a rapidly expanding area of technology which has generated considerable interest in developing commercially feasible flexible electronic systems and processing strategies. The field of macroelectronics relates to microelectronic systems wherein microelectronic devices and device arrays are

distributed and integrated on large area substrates significantly exceeding the physical dimensions of conventional semiconductor wafers. A number of macroelectronic products have been successfully commercialized including large area macroelectronic flat panel display products. The majority of these display systems comprise amorphous or polycrystalline silicon thin film transistor arrays patterned onto rigid glass substrates. Macroelectronic display devices having substrate dimensions as large as 100's of meters squared have been achieved. Other macroelectronic products in development include photovoltaic device arrays, large area sensors and RFID technology.

[007] Despite considerable progress in this field, there is continued motivation to integrate flexible substrates and device structures into macroelectronic systems so as to impart new device functionality, such as enhanced ruggedness, mechanical flexibility and bendability. To address this need, a number material strategies for flexible macroelectronic systems are currently being pursued including organic semiconductor thin film transistor technology, nano-wire and nanoparticle based flexible electronics and organic/inorganic semiconductor hybrid technology. In addition, substantial research is currently directed at developing new fabrication processes for accessing high throughput and low cost manufacturing of macroelectronic systems.

[008] U.S. Patents 11/145,574 and 11/145,542, both filed on June 2, 2005, disclose a high yield fabrication platform using printable semiconductor elements for making electronic devices, optoelectronic devices and other functional electronic assemblies by versatile, low cost and high area printing techniques. The disclosed methods and compositions provide for the transfer, assembly and/or and integration of microsized and/or nanosized semiconductor elements using dry transfer contact printing and/or solution printing techniques providing good placement accuracy, registration and pattern fidelity over large substrate areas. The disclosed methods provide important processing advantages enabling the integration of high quality semiconductor materials fabricated using conventional high temperature processing methods onto substrates by printing techniques which may be independently carried out at relatively low temperatures (< about 400 degrees Celsius) compatible with a range of useful substrate materials, including flexible plastic substrates. Flexible thin film transistors fabricated using printable semiconductor materials exhibit good electronic performance characteristics, such as device field effect mobilities greater than 300 $cm^2 V^{-1} s^{-1}$ and on/off ratios greater than 10^3, when in flexed and non-flexed conformations.

[009] It will be appreciated from the foregoing that a need exists for methods of making large area integrated electronics, including macroelectronic systems. In particularly, fabrication methods for these systems are needed that are capable of high-throughput and low cost implementation. Further, there is currently a need for macroelectronic systems combining good electronic device performance and enhanced mechanical functionality such as flexibility, shapeability, bendability and/or stretchability.

SUMMARY OF THE INVENTION

[010] The present invention provides optical devices and systems fabricated, at least in part, via printing-based assembly and integration of printable functional materials and/or semiconductor-based devices and device components. In specific embodiments the present invention provides light emitting systems, light collecting systems, light sensing systems and photovoltaic systems comprising printable semiconductor elements, including large area, high performance macroelectronic devices. Optical systems of the present invention comprise printable semiconductor containing structures (e.g., printable semiconductor elements) assembled, organized and/or integrated with other device components via printing techniques that exhibit performance characteristics and functionality comparable to single crystalline semiconductor based devices fabricated using conventional high temperature processing methods. Optical systems of the present invention have device geometries and configurations, such as form factors, component densities, and component positions, accessed by printing that provide a range of useful device functionalities. Optical systems of the present invention include devices and device arrays exhibiting a range of useful physical and mechanical properties including flexibility, shapeability, conformability and/or stretchablity. Optical systems of the present invention include, however, devices and device arrays provided on conventional rigid or semi-rigid substrates, in addition to devices and device arrays provided on flexible, shapeable and/or stretchable substrates.

[011] This invention also provides device fabrication and processing steps, methods and materials strategies for making optical systems at least in part via printing techniques, including contact printing, for example using a conformable transfer devices, such as an elastomeric transfer device (e.g., elastomer layer or stamp). In specific embodiments, methods of the present invention provide a high-throughput, low cost fabrication platform for making a range of high performance optical systems, including light emitting systems, light collecting systems, light sensing systems and photovoltaic

systems. Processing provided by the present methods is compatible with large area substrates, such as device substrates for microelectronic devices, arrays and systems, and is useful for fabrication applications requiring patterning of layered materials, such as patterning printable structures and/or thin film layers for electronic and electro-optic devices. Methods of the present invention are complementary to conventional microfabrication and nanofabrication platforms, and can be effectively integrated into existing photolithographic, etching and thin film deposition device patterning strategies, systems and infrastructure. The present device fabrication methods provide a number of advantages over conventional fabrication platforms including the ability to integrate very high quality semiconductor materials, such as single crystalline semiconductors and semiconductor-based electronic devices/device components, into optical systems provided on large area substrates, polymer device substrates, and substrates having contoured a conformation.

[012] In an aspect, the present invention provides processing methods using high quality bulk semiconductor wafer starting materials that are processed to provide large yields of printable semiconductor elements with preselected physical dimensions and shapes that may be subsequently transferred, assembled and integrated into optical systems via printing. An advantage provided by the present printing-based device fabrication methods is that the printable semiconductor elements retain desirable electronic properties, optical properties and compositions of the high quality bulk wafer starting material (e.g., mobility, purity and doping etc.) while having different mechanical properties (e.g., flexibility, stretchability etc.) that are useful for target applications such as flexible electronics. In addition, use of printing-based assembly and integration, for example via contact printing or solution printing, is compatible with device fabrication over large areas, including areas greatly exceeding the dimensions of the bulk wafer starting material. This aspect of the present invention is particularly attractive for applications in macroelectronics. Further, the present semiconductor processing and device assembly methods provide for very efficient use of virtually the entire starting semiconductor material for making printable semiconductor elements that can be assembled and integrated into a large number of devices or device components. This aspect of the present invention is advantageous because very little of the high quality semiconductor wafer starting material is wasted or discarded during processing, thereby providing a processing platform capable of low cost fabrication of optical systems.

[013] In one aspect, the present invention provides optical systems comprising printable semiconductor elements, including printable semiconductor-based electronic devices/device components, assembled, organized and/or integrated using contact printing. In an embodiment of this aspect, the invention provides a semiconductor-based optical system made by a method comprising the steps of: (i) providing a device substrate having a receiving surface; and (ii) assembling one or more plurality of printable semiconductor elements on the receiving surface of the substrate via contact printing. In an embodiment, the optical system of this aspect of the present invention comprises an array of semiconductor-based devices or device components assembled on the receiving surface of the substrate via contact printing. In specific embodiments, each of the printable semiconductor elements of the optical system comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters. In an embodiment of this aspect, printable semiconductor elements comprise on or more semiconductor devices selected from the group consisting of LED, solar cell, diode, p-n junctions, photovoltaic systems, semiconductor-based sensor, laser, transistor and photodiode, having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[014] In an embodiment, the printable semiconductor element(s) is/are an electronic device or a component of an electronic device. In an embodiment, the printable semiconductor element(s) is/are selected from the group consisting of: an LED, a laser, a solar cell, a sensor, a diode, a transistor, and a photodiode. In an embodiment, the printable semiconductor element(s) comprises the semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure. In an embodiment, the printable semiconductor element comprises the semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel. In an embodiment, the system further comprises an electrically conducting grid or mesh provided in electrical contact with at least a portion of said printable semiconductor elements, wherein the electrically conducting grid or mesh providing at least one electrode for said system.

[015] Useful contact printing methods for assembling, organizing and/or integrating printable semiconductor elements of this aspect include dry transfer contact printing, microcontact or nanocontact printing, microtransfer or nanotransfer printing and self assembly assisted printing. Use of contact printing is beneficial in the present optical systems because it allows assembly and integration of a plurality of printable semiconductor in selected orientations and positions relative to each other. Contact printing in the present invention also enables effective transfer, assembly and integration of diverse classes of materials and structures, including semiconductors (e.g., inorganic semiconductors, single crystalline semiconductors, organic semiconductors, carbon nanomaterials etc.), dielectrics, and conductors. Contact printing methods of the present invention optionally provide high precision registered transfer and assembly of printable semiconductor elements in preselected positions and spatial orientations relative to one or more device components prepatterned on a device substrate. Contact printing is also compatible with a wide range of substrate types, including conventional rigid or semi-rigid substrates such as glasses, ceramics and metals, and substrates having physical and mechanical properties attractive for specific applications, such as flexible substrates, bendable substrates, shapeable substrates, conformable substrates and/or stretchable substrates. Contact printing assembly of printable semiconductor structures is compatible, for example, with low temperature processing (e.g., less than or equal to 298K). This attribute allows the present optical

systems to be implemented using a range of substrate materials including those that decompose or degrade at high temperatures, such as polymer and plastic substrates. Contact printing transfer, assembly and integration of device elements is also beneficial because it can be implemented via low cost and high-throughput printing techniques and systems, such as roll-to-roll printing and flexographic printing methods and systems. The present invention include methods wherein contact printing is carried out using a conformable transfer device, such as an elastomeric transfer device capable of establishing conformal contact with external surfaces of printable semiconductor elements. In embodiments useful for some device fabrication applications contact printing is carried out using an elastomeric stamp.

[016] In an embodiment, the step of contact printing-based assembly of printable semiconductor comprises the steps of: (i) providing a conformable transfer device having one or more contact surfaces; (ii) establishing conformal contact between an external surface of the printable semiconductor element and the contact surface of the conformable transfer device, wherein the conformal contact bonds the printable semiconductor element to the contact surface; (iii) contacting the printable semiconductor element bonded to the contact surface and the receiving surface of the device substrate; and (iv) separating the printable semiconductor element and the contact surface of the conformable transfer device, thereby assembling the printable semiconductor element on the receiving surface of the device substrate. In some embodiments, the step of contacting the printable semiconductor element bonded to the contact surface and the receiving surface of the device substrate comprises establishing conformal contact between the contact surface of the transfer device having the printable semiconductor element(s) and the receiving surface. In some embodiments, the printable semiconductor element(s) on the contact surface are brought into contact with an adhesive and/or planarizing layer provided on the receiving surface to facilitate release and assembly on the device substrate. Use of elastomeric transfer devices, such as elastomer layers or stamps including PDMS stamps and layers, is useful in some methods given the ability of these devices to establish conformal contact with printable semiconductor elements, and the receiving surfaces, external surface and internal surfaces of device substrates and optical components.

[017] Use of printable semiconductor materials and printable semiconductor-based electronic devices/device components in embodiments of this aspect provides the capable of integrating a range of high quality semiconductor materials for fabricating

optical systems exhibiting excellent device performance and functionality. Useful printable semiconductor elements include, semiconductor elements derived from high quality semiconductor wafer sources, including single crystalline semiconductors, polycrystalline semiconductors, and doped semiconductors. In a system of the present invention, the printable semiconductor element comprises a unitary inorganic semiconductor structure. In a system of the present invention, the printable semiconductor element comprises a single crystalline semiconductor material. In addition, use of printable semiconductor structures provides the capability of integrating printable structures comprising semiconductor electronic, optical and opto-electronic devices, device components and/or semiconductor heterostructures, such as hybrid materials made via high temperature processing and subsequently assembled on a substrate via printing. In certain embodiment, printable semiconductor elements of the present invention comprise functional electronic devices or device components, such as p-n junctions, semiconductor diodes, light emitting diodes, semiconductor lasers (e.g., Vertical-Cavity Surface-Emitting Lasers (VCSEL)), and/or photovoltaic cells.

[018] In an embodiment, the printable semiconductor elements are assembled on said device substrate such that they generate a multilayer structure on said receiving surface. In an embodiment, for example, the multilayer structure comprises mechanically-stacked solar cells. In an embodiment, for example, the printable semiconductor elements are solar cells having different band-gaps.

[019] Optical systems of this aspect of the present invention may optionally comprise a variety of additional device elements including, but not limited to, optical components, dielectric structures, conductive structures, adhesive layers or structures, connecting structures, encapsulating structures, planarizing structures, electro-optic elements and/or thin film structures and arrays of these structures. In an embodiment, for example, an optical system of the present invention further comprises one or more passive or active optical components selected from the group consisting of: collecting optics, concentrating optics, diffusing optics, dispersive optics, optical fibers and arrays thereof, lenses and arrays thereof, diffusers, reflectors, Bragg reflectors, waveguides ("light-pipes"), and optical coatings (e.g., reflective coatings or antireflective coatings). In some embodiments, active and/or passive optical components are spatially aligned with respect to at least one of the printable semiconductor elements provided on the device substrate. Optical systems of this aspect of the present invention may optionally comprise a variety of additional device components including, but not limited to,

electrical interconnects, electrodes, insulators and electro-optical elements. Printed-based assembly may be used to assembly and integrate additional device elements and additional device components, in addition to assembly and integration of these additional elements by variety of techniques well known in the field of microelectronics, including but not limited to, optical photolithography, deposition techniques (e.g., chemical vapor deposition, physical vapor deposition, atomic layer deposition, sputtering deposition etc.), soft lithography, spin coating and laser ablation patterning.

[020] Printing-based assembly provides a very high degree of control over the physical dimensions, geometry, relative spatial orientation and organization, doping levels and materials purity of the printable semiconductor elements assembled and integrated into the present optical systems. In an embodiment, printable semiconductor elements of the optical system are provided on the receiving surface of the substrate with a density equal to or greater than 5 semiconductor elements mm^{-1}, preferably for some embodiments a density equal to or greater than 50 semiconductor elements mm^{-1}, and preferably for some applications a density equal to or greater than 100 semiconductor elements mm^{-1}. In another embodiment, the printable semiconductor elements of the optical system have at least one longitudinal physical dimension (e.g., length, width etc.), optionally two longitudinal physical dimensions, less than or equal to 2000 nanometers, and in some embodiments less than or equal to 500 nanometers. In another embodiment, each printable semiconductor element of the optical system has at least one cross-sectional physical dimension (e.g. thickness) less than or equal to 100 microns, preferably for some applications less than or equal to 10 microns, and preferably for some applications less than or equal to 1 microns. In another embodiment, the positions of the printable semiconductor elements in the optical system relative to each other are selected to within 10,000 nanometers.

[021] Printable semiconductor elements may be assembled in selected orientations with respect to each other or other device elements of optical systems of the present invention. In an embodiment, printable semiconductor elements of the optical system are longitudinal aligned with respect to each other. The present invention includes, for example, optical systems wherein printable semiconductor elements extend lengths that are parallel to within 3 degrees of each other. In another embodiment, the optical system further comprising first and second electrodes provided on the receiving surface, wherein the printable semiconductor elements are in electrical contact with at least one of the electrodes, and wherein the printable semiconductor elements provide a fill factor

between the first and second electrodes greater than or equal to 10 %, preferably for some embodiments equal to or larger than 50%.

[022] The present invention also includes optical systems comprising printable semiconductor elements arranged in a low density (or sparse) configuration. Use of a low density configuration has benefits for some applications, as the amount of semiconductor incorporated in the device is low, thus, accessing lower costs. In these configurations, semiconductor elements may be arrange on a substrate so that the density of semiconductor elements is low enough such that the system is optically transparent, preferably for some embodiments more than 50% optical transparent at selected wavelength. In an embodiment, printable semiconductor elements of the optical system are provided on the receiving surface of the substrate with a density equal to or less than 1000 semiconductor elements mm^{-1}, preferably for some embodiments a density equal to or less than 500 semiconductor elements mm^{-1}, and more preferably for some embodiments a density equal to or less than 50 semiconductor elements mm^{-1}. In an embodiment of the present methods and systems capable of accessing sparse configurations, the semiconductor elements cover less than or equal to 10% of the receiving surface of the target substrate; in another embodiment less than or equal to 1%; and in another embodiment less than or equal to 0.1%. In another embodiment, the optical system further comprising first and second electrodes provided on the receiving surface, wherein the printable semiconductor elements are in electrical contact with at least one of the electrodes, and wherein the printable semiconductor elements provide a fill factor between the first and second electrodes less than or equal to 10 %, preferably for some embodiments less than or equal to 5%.

[023] The present invention includes optical systems comprising printable semiconductor elements assembled and integrated onto a range of useful substrate materials, including glass substrates, polymer substrate, plastic substrates, metal substrates, ceramic substrates, wafer substrates, and composite substrates. Substrates useful in the present optical systems include those having useful mechanical and/or physical properties such as flexibility, shapeability, stretchability, mechanical ruggedness and optical transparency at selected wavelengths. In some embodiments, optical systems of the present invention comprise printable semiconductor elements assembled and integrated onto a device substrate prepatterned with device components. In some embodiment, optical systems of the present invention comprise

printable semiconductor elements assembled and integrated onto a device substrate having a selected optically functionality, such as a device substrate comprising a lens, lens array, optical window, reflector, optical coating, series of optical coatings, or optically transparent substrate optionally having one or more optical coatings such as reflective coatings or antireflective coatings. In some embodiments, optical systems of the present invention comprise printable semiconductor elements assembled and integrated onto a device substrate having a contoured receiving surface, such as a concave receiving surface, convex receiving surface, a spherical surface, an elliptical surface or receiving surface having a complex contour with both concave regions and convex regions.

[024] Optical systems of the present invention may further comprise one or more encapsulating layers, planarizing layers, laminating layers, cover layers and/or bonding layers. Encapsulating layers, laminating layers, planarizing layers, covering layers or bonding layers may be provided on top of printable semiconductor elements or other device components to provide enhanced mechanical stability and ruggedness. Encapsulating layers, laminating layers, planarizing layers, covering layers or bonding layers may be provided in a configuration so as to mechanically, optically and/or electrically interconnect device components and structures of the present optical systems. Encapsulating layers, laminating layers, covering layers, planarizing layers, or bonding layers may comprise layers of deposited material, spin coated layers and/or molded layers. Encapsulating layers, laminating layers, covering layers, planarizing layers, or bonding layers are preferably at least partially optically transparent for some optical systems and applications of the present invention. Useful encapsulating layers, laminating layers, planarizing layers, covering layers and/or bonding layers may comprise one or more polymers, composite polymers, metals, dielectric materials, epoxy materials or prepolymer materials. In an embodiment, printable semiconductor elements are bonded or otherwise integrated to the receiving surface via one or more of the following: (i) cold welding the semiconductor elements to the receiving surface via a metal layer provided between the printable semiconductor elements and the receiving layer; (ii) provided via an adhesive layer provided between the printable semiconductor elements and the receiving layer; or (iii) provided by a lamination, encapsulation or planarizing layer provided on top of the printable semiconductor elements and the receiving layer. If the adhesive layer is metal, this layer can also serve to establish

electrical contact to the printable semiconductor element during printing-based assembly and integration.

[025] In some embodiments, the composition and thickness of an encapsulating, laminating or planarizing layer is selected such that the printable semiconductor elements, such as printed semiconductor devices and/or device components, assembled on a device substrate are placed near or on the neutral mechanical plane. In an embodiment, for example an encapsulating or laminating layer is provided on top of assembled printable semiconductor elements, wherein the encapsulating or laminating layer has a composition and thickness similar to that of the device substrate. In these embodiments, matching the encapsulating and/or laminating layer composition and thickness dimension with that of the device substrate results in the printable semiconductor elements residing near the neutral mechanical plane. Alternatively, the thickness and Young's modulus of the encapsulating and/or laminating layer may be selected to result in the printable semiconductor elements residing near the neutral mechanical plane. An advantage of processing methods and device geometries wherein printable semiconductor elements reside near the neutral mechanical plane of the device is that strain on these elements are minimized during bending or deformation. This strategy for managing strains generated during bending has benefits for minimizing delamination or other degradation of the device result from bending induced strain.

[026] In some embodiments, optical systems of the present invention provide light emitting optical systems, including, but not limited to, advanced lighting systems, arrays of light emitting diodes, arrays of semiconductor lasers (e.g., VCSELs), passive matrix LED (light emitting diode) displays, active matrix LED displays, ILED (inorganic light emitting diode) displays, macroelectronic display devices, and flat panel displays. In some embodiments, optical systems of the present invention provide light sensing optical systems including, optical sensors and sensor arrays, flexible sensors, stretchable sensors, conformal sensors and sensor skins. In some embodiments, optical systems of the present invention provide optical systems providing both light emitting and light sensing functionality such as sheet scanners. Optical systems of the present invention include energy conversion and storage systems including photovoltaic devices, device arrays and systems including solar cell arrays. In some embodiments, optical systems of the present invention comprise a plurality of one or more LEDs, photovoltaic cells, semiconductor lasers, photodiodes, and electro-optical elements having at least two physical dimensions (e.g., length, width, diameter or thickness) less

than 200 microns. In an embodiment, for example, the present invention provides an optical system comprising an array of solar cells, wherein each cell in the array has at least two physical dimensions (e.g., length, width, diameter or thickness) less than 200 microns. In another embodiment, for example, the present invention provides an optical system comprising an array of LEDs, wherein each LED in the array has a thickness less than 3 microns, and preferably for some applications less than 1 micron.

[027] In another aspect, the present invention provides a method for making an optical system comprising the steps: (i) providing a device substrate having a receiving surface; and (ii) assembling one or more printable semiconductor elements on the receiving surface of the substrate via contact printing; wherein each of the printable semiconductor elements comprise a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[028] Useful contact printing methods useful in this aspect of the present invention include dry transfer contact printing, microcontact or nanocontact printing, microtransfer or nanotransfer printing and self assembly assisted printing. Optionally, methods of the present invention employ contact printing as implemented using a conformable transfer device, such as an elastomeric transfer device (e.g., elastomeric stamp, composite stamp or layer). Optionally, a plurality of printable semiconductor elements are

assembled on the receiving surface of the substrate, for example in a dense or spares configuration. Optionally, methods of this aspect of the present invention further comprise the step of prepatterning the device substrate with one or more device components. Optionally, methods of this aspect of the present invention further comprise the step of providing one or more optical components in optical communication or optical registration with the printable semiconductor elements. In a method of the present invention, the printable semiconductor element comprises a unitary inorganic semiconductor structure. In a method of the present invention, the printable semiconductor element comprises a single crystalline semiconductor material.

[029] Optionally, methods of the present invention include the step of providing a laminating layer, such as a polymer or elastomer layer on top of at least a portion of the printable semiconductor elements assembled on the receiving surface of the substrate. Optionally, methods of the present invention include the step of planarizing at least a portion of the printable semiconductor elements assembled on the receiving surface of the substrate. Optionally, methods of the present invention include the steps of: (i) providing a planarizing layer to the receiving surface and (ii) embedding at least a portion of the printable semiconductor elements in the planarizing layer. Optionally, methods of the present invention include the step of patterning one or more electrical contacts, electrodes, contact pads or other electrical interconnect structures on at least a portion of the printable semiconductor elements.

[030] Methods of this aspect of the present invention further comprise the step of assembling and/or integrating one or more additional device components onto the device substrate, such as optical components, electronic components and/or electro-optical components. Assembling and/or integrating additional device components in the present methods can be implemented in combination with a large number of other fabrication techniques, including, but not limited to, lithographic patterning (e.g., optical lithograph and soft lithography), deposition techniques (e.g., CVD, PVD, ALD, etc.), laser ablation patterning, molding techniques (e.g., replica molding), spin coating, self assembly, contact printing, and solution printing. In some embodiments, other processing techniques, such as plasma treatment, etching, metallization and cold welding are used to generate, assemble or integrate device components, including printable semiconductor elements.

[031] In an embodiment, for example, a combination of optical lithography and deposition techniques are used to pattern the device substrate prior to or after printing-based assembly of the printable semiconductor elements. In another embodiment, for example, replica molding is used to generate optical components, such as a lens array or diffusers, which are subsequently patterned with printable semiconductor elements via contact printing. In another embodiment, for example, printable semiconductor elements provided on a device substrate are electrically connected to electrodes and electrical interconnects patterned on the device substrate using a combination of optical lithography and deposition techniques. In another embodiment, for example, an optical system comprising a multilayer structure is generated by repeated transfer and assembly steps of printable semiconductor elements, such as thin film transistors, LEDs, semiconductor lasers and/or photovoltaic devices, printed on the device substrate, optionally in combination with additional processing carried out via spin coating, deposition and encapsulation/planarizing steps for integrating additional device components, such as electrode, interconnects, adhesive layers, lamination layers, optical components and encapsulation or planarizing layers.

[032] In an embodiment, the method of this aspect further comprises the step of providing one or more optical components in optical communication or optical registration with the printable semiconductor elements, for example optical components selected from the group consisting of: collecting optics, diffusing optics, dispersive optics, optical fibers and arrays thereof, lenses and arrays thereof, diffusers, reflectors, Bragg reflectors, and optical coatings (e.g., reflective coatings or antireflective coatings). For example, methods of the present invention may optionally include the step of providing an array of optical components in optical communication or optical registration with at least a portion of the printable semiconductor elements. In some embodiments, an optical component of the array is individually addressed to each of the printable semiconductor elements. In a specific embodiment, the array of optical components is fabricated via replica molding; wherein the printable semiconductor elements are assembled on a receiving surface of the array of optical components via contact printing.

[033] In an embodiment, a method of the present invention further comprises providing one or more electrodes in electrical contact with the printable semiconductor elements provided on the device substrate. In an embodiment electrodes are defined and integrated into optical systems using a combination of optical lithographic patterning

and deposition techniques (e.g., thermal deposition, chemical vapor deposition or physical vapor deposition). In another embodiment, electrodes are assemble and interconnected with devices elements using printing.

[034] Methods of the present invention are useful for providing optical systems on large areas of a receiving surface of a substrate. In an embodiment useful for making large array optical systems, printable semiconductor elements are provided on an area of the receiving substrate selected over the range of 0.05 m^2 to 10 $meters^2$, and preferably for some applications selected over the range of 0.05 m^2 to 1 $meters^2$

[035] In an embodiment, the present methods further comprise the step of providing an adhesive layer to the receiving surface prior to the assembling step. Adhesive layers are useful in the present invention for bonding or otherwise affixing printable semiconductor elements and other device elements to the receiving surface of the substrate. Useful adhesive layers include but are not limited to one or more metal layers or a polymer layers. In an embodiment, the present methods further comprise the step of providing a laminating, planarizing or encapsulating layer on the printable semiconductor elements. Laminating, planarizing or encapsulating layers are useful in the present methods for at least partially encapsulating or laminating printable semiconductor elements and other elements on the receiving surface.

[036] Optionally, the method of the present invention further comprises the steps of: (i) providing an inorganic semiconductor wafer; (ii) generating the plurality of printable semiconductor elements from the semiconductor wafer; and (iii) transferring the plurality of printable semiconductor elements from the wafer to the receiving surface via contact printing, thereby assembling the plurality of printable semiconductor elements on the receiving surface of the substrate. In an embodiment, the plurality of printable semiconductor elements are assembled on the receiving surface of the substrate and on the receiving surfaces of one or more additional substrates, wherein the plurality of printable semiconductor elements assembled on the substrates comprises at least 5% to 50% by mass of the semiconductor wafer. This aspect of the present invention is beneficial because it provides for very efficient use of the semiconductor wafer starting material resulting in low cost fabrication of optical systems. In some embodiments, the "plurality of printable semiconductor elements assembled on the substrates" may comprise a very low fraction (< about 5% by mass or area) of the final, device substrate. In other words, the printed systems may exhibit a low fill-factor of the semiconductor.

The advantage of a low-fill factor is that it requires a small amount of semiconductor material, which in these cases is expensive on a per-area basis, to populate large areas of final, device substrate(s).

[037] In another embodiment, the present invention provides a method of making a semiconductor-based optical system comprising the steps of: (i) providing an optical component having an external surface and an internal surface; (ii) providing a electrically conducting grid or mesh on the internal surface of the optical component; (iii) providing a device substrate having a receiving surface; (iv) assembling a plurality of printable semiconductor elements on the receiving surface of the substrate via contact printing; wherein each of the printable semiconductor elements comprise a unitary inorganic semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters; and (v) transferring the optical component having the grid or mesh to the substrate, wherein the optical component is positioned on top of the semiconductor elements assembled on the on the receiving surface of the substrate, and wherein the grid or mesh is provided between the optical component and the semiconductor elements. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[038] In a method of the present invention, the printable semiconductor element comprises a unitary inorganic semiconductor structure. In a method of the present

invention, the printable semiconductor element comprises a single crystalline semiconductor material.

BRIEF DESCRIPTION OF THE DRAWINGS

[039] Fig. 1. provides a schematic showing optical systems provided by the present invention. As shown in Figure 1, the present invention provides a number of classes of optical systems and related methods of making these systems, including systems for light generation and systems for light harvesting comprising printed inorganic optoelectronic systems with integrated optical components in registry.

[040] Fig. 2 A- E provides schematic diagrams of optical systems of the present invention comprising printable semiconductor elements. Figure 2A shows a printed LED array with integrated optical diffuser. Figure 2B shows a VCSEL array on a silicon chip with integrated optical fibers. Figure 2C shows a printed photovoltaic array with integrated optical collectors. Figure 2D shows an artificial eye sensor comprising a printed photodiode array on a collecting lens. Figure 2E shows a sheet scanner having both light sensing and light generation functionality and comprising a printed array LED and photodiode components and integrated collection optics provided on a polymer or other low cost substrate.

[041] Fig. 3 provides a process flow schematic for the fabrication of a single pixel element of a printed inorganic active matrix LED display of the present invention.

[042] Fig. 4 provides a schematic illustration (not to scale) of a printed active matrix LED display on a glass substrate. The display shown comprises 100 pixels and is an approximately 11 inch display. Thin film transistor (TFT) elements, LED elements, gate lines, anode lines and data lines of the device are indicated in Figure 4.

[043] Fig. 5 provides photographs (Figure 5A) and operating current-voltage characteristics (Figure 5B) of a single pixel of an active matrix LED display on a (transparent) glass substrate. As shown in Figure 5A the single pixel of an active matrix LED display comprises a printed TFT structure, a LED structure, gate electrode and electrical interconnects. Figure 5B provides a plot of current (A) verses drive bias (V) for the single pixel of an active matrix LED display.

[044] Fig. 6 provides photographs of a 64 pixel active matrix LED display on a (transparent) glass substrate. Fig. 6A provides a photograph of a 64 pixel partial LED display (Note: missing top contacts) comprising 1 mm transistors printed on to the device substrate and ILEDs manually placed on the substrate. In the device shown in Figure 6A pixels are provided at a 4 mm pitch. Fig. 6B provides a photograph of a printed silicon TFT with interdigitated channel (thin green line) for high-current operation. Figure 6C provides a photograph of two pixels illuminated by placing a transparent common anode electrical contact against the LEDs.

[045] Fig. 7A provides a process flow schematic for the fabrication of a single pixel element of a printed inorganic passive matrix LED display.

[046] Fig. 7B provides a process flow schematic for establishing electrical contact by compression of a (soft) substrate/layer.

[047] Fig. 8 provides a schematic illustration (not to scale) of a printed passive matrix printed inorganic LED display. As shown in Figure 8 the display comprises a bottom substrate, electrode network, printed ILED, PDMS layer and top substrate.

[048] Fig. 9 provides photographs of passively addressed printed inorganic LED displays/arrays on glass and flexible PET substrates.

[049] Fig. 10 provides a process flow schematic for printing inorganic light emitters and collectors via cold-weld bonding techniques.

[050] Fig. 11 provides a process flow schematic for printing using a donor cartridge and cold-weld bonding technique. In this method a cartridge is patterned with SU-8. ILED structures are placed on the patterned surface of the cartridge. A stamp is used to take up the ILED structures and subsequently print the ILED structures on a substrate prepatterned with electrodes via transfer printing. The bottom panel of figure 11 shows an example of a LED structure printed using this method.

[051] Fig. 12 provides a schematic of an optical system of the present invention wherein diffusing optics are integrated with printable LED structures. In this embodiment, PDMS is molded on rough polystyrene. A comparison of panels (a) and (b) show the affect of incorporation of a diffuser in this optical system. The diffuser can be a rough molded PDMS structure. This figure demonstrates that diffusers can effectively increase the size of the luminous region.

[052] Fig. 13 provides a schematic of diffusing optics comprising radial density gradient scattering centers useful for LED lighting systems of the present invention. As shown in this Figures a printed LED structure under metal is provided in optical communication with a plurality of optical scattering centers. The bottom panel in Figure 13 shows a cross sectional view of scattering centers comprising relief features in a transparent substrate.

[053] Fig. 14A provides an exemplary epilayer structure for the fabrication of printable micro-LEDs. As shown in this figure, the epilayer structure comprises a series of device layers, sacrificial layers and a handle wafer. Individual layers in the epilayer structure are shown in the bottom panel of Figure 14A. Fig. 14B provides an exemplary epilayer structure for the fabrication of printable micro-LEDs comprising quantum well emissive layers. The epilayer structure comprises a series of semiconductor layers provided between p-cladding and n-cladding layers. Specific compositions of each layer in the epilayer structure are provided. Fig. 14C provides a table indicating the composition, thickness, doping and functionality of each layer in the epilayer structure for the fabrication of printable micro-LEDs. Figure 14D illustrates an example of a mother wafer from which printable p-on-n GaAs solar cells may be produced by photolithography and etching layers 9 through 4 and selectively removing layer 3 by a wet chemical etch. Figure 14E illustrates provides another example of a mother wafer from which printable n-on-p GaAs solar cells may be produced by photolithography and etching layers 9 through 4 and selectively removing layer 3 by a wet chemical etch.

[054] Fig. 15 provides schematic diagrams illustrating the imperceptible pixilation/high degree of transparency from low fill-factor, micro-sized (<~100 micron footprint) LEDs. As shown in the top panel of this figure, the optical system comprises: (i) a first glass coated ITO or a low-fill factor metal mesh layer ; (ii) printed micro LEDS structures; and (iii) a second glass coated ITO or a low-fill factor metal mesh layer. Top views are provided corresponding to the off state and the on state. A magnification of the top view is also provided showing the positioning of micro LED structures.

[055] Fig. 16 provides schemes for the release of printable light-emitting inorganic semiconductor micro-elements: micro-LEDs or VCSELs. Scheme 1 describes the release of such elements by encapsulating them in a polymer, e.g. photoresist, and releasing them from the wafer on which they were grown by selectively etching an $Al_xGa_{1-x}As$ (x>about 70%) sacrificial layer using hydrofluoric acid. Scheme 2 describes

release by encapsulating them in a conformal dielectric (e.g. silicon nitride) and releasing them from the wafer by selectively oxidizing the AlGaAs and etching the oxidized material using aqueous potassium hydroxide. Scheme 3 describes release by encapsulating them with a polymer, e.g. photoresist, followed by selective etching of a buried GaAs sacrificial layer using an aqueous mixture of citric acid and hydrogen peroxide. In scheme 3, the AlGaAs protects the underside of the light emitting element from the citric acid-based etchant.

[056] Fig. 17A provides a schematic process flow diagram illustrating fabrication of integrated solar cell/collector arrays by printing solar cells. Fig. 17B provides a schematic process flow diagram illustrating fabrication of integrated solar cell/collector arrays via interconnection of registry of an optical array. Fig. 17C provides a schematic process flow diagram illustrating the operation of the integrated solar cell/collector arrays.

[057] Fig. 18A provides a schematic ray diagram (not to scale) showing operation of the integrated low-level collecting optics (lens) and solar-cell arrays of an optical system of the present invention. As shown in Figure 18A radiation is collected by the concentrator and focused on printed microsolar cells. Figure 18B shows an expanded view of a microcell of the present invention comprising an antireflection layer, top contact and p-n junction.

[058] Fig. 19 provide a schematic diagram illustration of light harvesting via reduction of semiconductor materials costs in a sheet-like form factor. The collector size is approximately 2 mm, the solar cell size is approximately 0.1 mm, and the area multiplication (ratio of collector area and solar cell area) is approximately 400. As demonstrated by the calculation show in this figures $1ft^2$ of processed semiconductor wafer results in approximately 400 ft^2 of light-harvesting area. This calculation demonstrates the methods and optical systems of the present invention provide a high efficiency and low cost fabrication strategy for high performance photovoltaic devices and systems.

[059] Fig. 20 provides a schematic diagram of a collecting optic and heterogenously composed solar cell of a solar cell array (sympevolent/diventegration) of the present invention. As shown in this figure, collecting optics are provided in optical communication with a nitride/phosophide and/or arsenide solar cell and silicon solar cell assembled on the device substrate via contact printing. Figure 20 also provides ray

diagram of the incident light shown collection and focus functionality of a concentrator and individually addressed solar cells. Single crystal multilayer solar cells (i.e. third generation solar cells) are typically grown by MOCVD and are constrained by the necessity of crystal lattice mismatch between layers. In our system different absorbing layers can have arbitrary lattices and the materials selected for optimal spectrum absorption for each layer.

[060] Fig. 21 provides a schematic process flow diagram for fabrication of an integrated solar cell and lens array using a combination of replica molding methods and contact printing. As shown in this figure a master lens array is used to generate a negative replica mold, for example via replica molding or imprinting techniques. Next, the molded PDMS layer is used to generate a plano-concave polymer lens array by casting the polymer against the negative replica. As shown in Figure 21, solar cells printed onto a device substrate are provided in optical communication with the lens array so as to generate an optical system of the present invention.

[061] Fig. 22 demonstrates the ability of Fresnel lenses, a type of concentrating/collecting optic, to focus light to a small area for use in light harvesting systems described by the present invention. Fresnel lens arrays can be used as optical concentrators due to its advantageous features such as thin form factor and light weight compared with conventional lenses. The figure shows a focal area measurement for spherical and cylindrical Fresnel lenses.

[062] Fig. 23 provides a schematic diagram illustrating an optical system of the present invention wherein horizontal light pipes and/or waveguides are provided for light harvesting. This optical system uses transparent, structured media of appropriate index of refraction to capture normally- or obliquely-incident light and guide it in the plane of the substrate to a solar cell or solar cell array.

[063] Fig. 24 provides a schematic showing an exemplary printable silicon solar cell fabricated using a silicon on insulator SOI wafer. The solar cell comprises a doped top surface with a P/As mixture and is supported by a buried oxide layer of the SOI wafer. Figure 24 shows the solar cell multilayer structure comprising a n^+-Si (P/As) layer and p-Si(B) layer.

[064] Fig 25 provides a schematic process flow diagram illustrating a method of transferring a printable solar cell to substrate using contact printing and subsequent cold welding processing to affix the solar cell to a device substrate.

[065] Fig 26 provides a schematic diagram (not to scale) showing a top view (in parallel) of an exemplary configuration for top contacts to solar arrays of the present invention. Microsolar cells (shown in gray) having widths of approximately 120 microns and lengths of approximately 1 millimeter are provided in an array format on a device substrate. Metal features are provided having widths of 60 microns and length on the order of 1 inch. The metal features provide the top contacts of a solar cell device array of the present invention. This figures shows a flexible strip light made of blue LEDs and a thin kapton substrate with a bending radius equal to 0.85 cm.

[066] Fig 27 provides a schematic diagram of an "artificial eye" sensor of the current invention. The sensor comprises inorganic photodiode arrays distributed on a lens having spherical curvature. Various lens shapes and angles are shown in Figure 27

[067] Fig 28 provides a schematic diagram illustrating wrapping a planar sheet around a spherical surface demonstrating the necessity of stretchability in an exemplary "artificial eye" sensor. As shown in Figure 28, conformal positioning of the planar sheet requires some degree of stretchability to avoid failure.

[068] Fig 29 provide a schematic processes flow diagram showing a method for making a microsolar cell array of the present invention.

[069] Fig 30. Estimated Short Circuit Current (J_{SC}) and AM1.5 Efficiency as a function of Silicon Thickness.

[070] Fig 31. Scanning Electron Micrographs Showing Sequential Formation of Si Multilayer Ribbon Stacks.

[071] Fig. 32 provides a schematic diagram of a connection scheme where the Si ribbons comprising p-type silicon with a thin n-type layer on top to form the emitter. Left side shows the as-transferred Si Ribbons, right shows the connection (direct-write or screen-printing). Only four Si Ribbons are shown for clarity.

[072] Fig 33 provides a schematic of a solar cell array of the present invention using PDMS for concentrating solar illumination.

[073] Fig 34. provides images showing results of printing single crystal silicon onto plastic, glass, Si wafers, InP wafers and thin film a-Si. The microstamping process of the present invention is compatible with a wide range of substrates.

[074] Fig 35 shows a schematic illustration of an exemplary process of the present invention, as applied to the printing of printable inorganic semiconductor-based LEDs.

[075] Fig 36 provides an image and a schematic illustration of a printer useful in the present methods of fabricating conformable LED lighting systems.

[076] Fig 37 provides images of square (part a) and linear (part b) lighting devices that comprise passively addressed blue inorganic LEDs assembled on plastic substrates via contact printing. The device in part (b) represents a conformal ILED-based thin film lighting device of the present invention.

[077] Fig 38 provides a schematic process flow diagram of a method of fabricating a conformable LED lighting system of the present invention.

[078] Fig 39 provides a process flow diagram for fabricating an ILED light device of the present invention comprising a flexible strip.

[079] Fig 40 provides a cross sectional view of a conformal ILED lighting system of the present invention comprising top and bottom PET substrates (approximately 175 microns thick), ILEDS structures (approximately 100 microns thick), electrodes and a PDMS encapsulating coating.

[080] Fig 41 provides images of ILED lighting systems of the present invention in an unbent state, a first bent sate with a bending radius of 7 cm, a second bent sate with a bending radius of 5 cm, third bent sate with a bending radius of 4.5 cm, a fourth bent sate with a bending radius of 3 cm and in a state upon release of the bending stress. The images in Figure 42 confirm that conformal ILED lighting systems of the present invention provide useful optical properties in bent configurations.

[081] Fig 42 provides an image of a flexible strip light made of blue LEDs and thin kapton substrates with bending radius equal to 0.85 cm.

[082] Fig 43 provides schematics showing two methods for assembling ILED structures on the device substrate.

[083] Fig 44 provides a schematic for the formation of a micro single crystal silicon solar cell with low-level concentrating lens. In the first step (a) the micro structures are transferred from PDMS onto an embedded electrode which serves as the back electrical contact for the device. The silicon is transferred by laminating the PDMS onto the electrode surface and slowly peeling the PDMS back. Next, in step (b), planarization followed by the formation of the top metal contacts is performed. The device is completed by integrating a low concentration cylindrical lens array made from PDMS onto the device (step c). In this final step it can be seen that the device was designed such that the rows of silicon cells align with the focal point of the lens array.

[084] Fig 45 provides images of a silicon solar cell transferred to a glass substrate. (a) Optical image of a single cell on a glass substrate with both top and bottom electrical contacts. (b) current voltage characteristics - Typical I-V response for a device shown in (a) under AM 1.5.

[085] Fig 46 provides images of a solar cell array joined to cylindrical collecting optics. (a) Picture of the final fully integrated device with cylindrical lens array. (b) Picture of the same device without the incorporation of the lens array.

[086] Fig 47 provides a schematic diagram for generating optical concentrator arrays with integrated metal contacts onto mS-Silicon solar cells (micro-silicon solar cells). The process starts off with retrieval of a metal mesh pattern from a substrate (shown dark blue) via a PDMS molded lens array. The lens array/mesh pattern can then be laminated in registry onto an array of silicon solar cells.

[087] Fig 48 illustrates the process flow for generating solar cells and integrated concentrating optics.

[088] Fig 49 provides images of a micro solar cell array printed onto gold bus lines on glass substrates via a thin PDMS adhesive layer. Also shown are current – voltage characteristics for the solar cell array.

[089] Fig 50 provides a schematic illustration of microcells of (a) vertical-type, (b) transverse-type, (c) combination of both types.

[090] Fig. 51 provides a schematic diagram illustrating a method of the present invention for making large area optical systems using micromanipulation via transfer printing. This techniques provides for massively parallel assembly of inorganic

semiconductor elements and semiconductor devices having micro-sized and/or nano-sized physical dimensions.

[091] Fig. 52 provide a plot of current (A) versus applied voltage (V) for a inorganic LED device assembled via transfer printing.

[092] Fig. 53A provide a plot of current (A) versus applied voltage (V) for a printed thin-film inorganic LED device assembled on a plastic substrate via transfer printing. Figure 53A also provide a schematic diagram of the assembled device. Fig. 53A provides a schematic diagram shown an exemplary ILED epilayer structure useful in the present invention.

[093] Figures 54A and 54B provides schematic diagrams of systems of the present invention comprising planarized printable semiconductor elements.

[094] Figure 55 provides a flow diagram illustrating processing steps in methods of the present invention for making semiconductor-based optical systems comprising planarized printable semiconductor elements, such as printable semiconductor-based electronic devices and device components.

[095] Figure 56 provides experimental results characterizing the impact of step edges on establishing electrical contact to and/or between printable semiconductor elements.

[096] Figure 57 provides a process flow diagram for making printable semiconductor elements comprising vertical solar cells that can be subsequently assembled and interconnected to fabricate a solar cell array.

[097] Figure 58 provides SEM images of microsolar cells of different thicknesses fabricated from bulk wafers. (Top to bottom: 8 microns, 16 microns, 22 microns thick).

[098] Figure 59 provides a plot showing IV characteristics of an individual solar cell device fabricated using the present processing platform.

[099] Figure 60 shows processing for generating top contacts for the vertical solar cells and related electronic performance data.

[0100] Figure 61 provides a schematic showing a solar cell layout of transverse type solar cells to be patterned on a <111> p-type Si wafer and capable of subsequent assembly and integration via contact printing.

[0101] Figure 62 provides a schematic showing the doping scheme wherein boron (P+) and phosphorous (n+) doped regions are patterned on the external surface of the patterned semiconductor ribbons.

[0102] Figure 63 provides an overview schematic showing the process flow for cell patterning and doping steps.

[0103] Figure 64 provides a schematic diagram showing processing steps for patterning solar cell ribbons illustrating photolithography and STS deep RIE etching process steps.

[0104] Figure 65 shows results from KOH refining processing of the sidewalls of the patterned ribbons.

[0105] Figure 66 provides a schematic diagram for boron doping processing. After the KOH refining step, boron doping for formation of top p+ contact is conducted.

[0106] Figure 67 provides a schematic diagram for phosphorous doping processing

[0107] Figure 68 provides a schematic diagram showing sidewall passivation processing.

[0108] Figure 69 provides a schematic diagram showing processing for the formation of a KOH etching window.

[0109] Figure 70 provides micrographs showing KOH etching processing and bottom boron doping processing.

[0110] Figure 71 provides images showing transfer of the solar cell ribbons from the source wafer using a PDMS transfer device.

[0111] Figure 72 provides a schematic diagram illustrating contact printing and planarization processing steps.

[0112] Figure 73 provides an imaging showing the results of metallization processing.

[0113] Figure 74 provides a schematic diagram of the metallization process showing an Al metal layer, SiO_2 dielectric layer, Cr/Au layer, solar cell, planarizing layer and device substrate.

[0114] Figures 75A and 75B provide schematic diagrams exemplifying the expressions "lateral dimensions" and "cross sectional dimensions" as used in the present description. Figure 75A provides a top plan view of printable semiconductor elements comprising 4 semiconductor ribbons **6005**. In the context of this description the expression "lateral dimension" is exemplified by the length **6000** and width **6010** of the semiconductor ribbons **6005**. Figure 75B provides a cross sectional view of the printable semiconductor elements comprising 4 semiconductor ribbons **6005**.

[0115] Figure 76 shows an array of printable GaAs/InGaAlP red LEDs printed on PET substrates.

DETAILED DESCRIPTION OF THE INVENTION

[0116] Referring to the drawings, like numerals indicate like elements and the same number appearing in more than one drawing refers to the same element. In addition, hereinafter, the following definitions apply:

[0117] "Collecting" and "Concentrating", as applied to optics and optical components, refers to the characteristic of optical components and device components that they direct light from a relatively large area and direct that light to another area, in some cases a smaller area. In the context of some embodiments, collecting and concentration optical components and/or optical components are useful for light detection or power harvesting by printed inorganic solar cells or photodiodes.

[0118] "Printable" relates to materials, structures, device components and/or integrated functional devices that are capable of transfer, assembly, patterning, organizing and/or integrating onto or into substrates without exposure of the substrate to high temperatures (i.e. at temperatures less than or equal to about 400 degrees Celsius). In one embodiment of the present invention, printable materials, elements, device components and devices are capable of transfer, assembly, patterning, organizing and/or integrating onto or into substrates via solution printing or contact printing.

[0119] "Printable semiconductor elements" of the present invention comprise semiconductor structures that are able to be assembled and/or integrated onto substrate surfaces, for example using by dry transfer contact printing and/or solution printing

methods. In one embodiment, printable semiconductor elements of the present invention are unitary single crystalline, polycrystalline or microcrystalline inorganic semiconductor structures. In one embodiment, printable semiconductor elements are connected to a substrate, such as a mother wafer, via one or more bridge elements. In this context of this description, a unitary structure is a monolithic element having features that are mechanically connected. Semiconductor elements of the present invention may be undoped or doped, may have a selected spatial distribution of dopants and may be doped with a plurality of different dopant materials, including P and N type dopants. Printable semiconductor elements and structures of the present invention may include holes or perforations through one dimension of the elements to facilitate their release from a wafer by the introduction of a chemical release agent. The present invention includes microstructured printable semiconductor elements having at least one cross sectional dimension (e.g., thickness) selected over the range of 1 micron to 1000 microns. The present invention includes nanostructured printable semiconductor elements having at least one cross sectional dimension (e.g., thickness) selected over the range of 1 to 1000 nanometers. In an embodiment, a printable semiconductor element of the present invention has a thickness dimensions less than of equal or 1000 microns, preferably for some applications a thickness dimensions less than or equal to 100 microns, preferably for some applications a thickness dimensions less than or equal to 10 microns and preferably for some applications a thickness dimensions less than or equal to 1 microns.

[0120] Printable semiconductor elements useful in many applications comprises elements derived from "top down" processing of high purity bulk materials, such as high purity crystalline semiconductor wafers generated using conventional high temperature processing techniques. In some methods and systems of the present invention, printable semiconductor elements of the present invention comprise composite heterogeneous structures having a semiconductor operational connected to or otherwise integrated with at least one additional device component or structure, such as a conducting layer, dielectric layer, electrode, additional semiconductor structure or any combination of these. In some methods and systems of the present invention, the printable semiconductor element(s) comprises a semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure (e.g., optical coatings, reflectors, windows, optical filter, collecting, diffusing or

concentration optic etc.). In some methods and systems of the present invention the printable semiconductor element(s) comprises a semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad a semiconductor channel. In some methods and systems of the present invention, printable semiconductor elements of the present invention comprise stretchable semiconductor elements, bendable semiconductor elements and/or heterogeneous semiconductor elements (e.g., semiconductor structures integrated with one or more additional materials such as dielectrics, other semiconductors, conductors, ceramics etc.). Printable semiconductor elements include, printable semiconductor devices and components thereof, including but not limited to printable LEDs, lasers, solar cells, p-n junctions, photovoltaics, photodiodes, diodes, transistors, integrated circuits, and sensors.

[0121] "Cross sectional dimension" refers to the dimensions of a cross section of device, device component or material. Cross sectional dimensions include the thickness, radius, or diameter of a printable semiconductor element. For example, printable semiconductor elements having a ribbon shape are characterized by a thickness cross sectional dimension. For example, printable semiconductor elements having a cylindrical shape are characterized by a diameter (alternatively radius) cross sectional dimension.

[0122] "Longitudinally oriented in a substantially parallel configuration" refers to an orientation such that the longitudinal axes of a population of elements, such as printable semiconductor elements, are oriented substantially parallel to a selected alignment axis. In the context of this definition, substantially parallel to a selected axis refers to an orientation within 10 degrees of an absolutely parallel orientation, more preferably within 5 degrees of an absolutely parallel orientation.

[0123] The terms "flexible" and "bendable" are used synonymously in the present description and refer to the ability of a material, structure, device or device component to be deformed into a curved shape without undergoing a transformation that introduces significant strain, such as strain characterizing the failure point of a material, structure, device or device component. In an exemplary embodiment, a flexible material, structure, device or device component may be deformed into a curved shape without introducing strain larger than or equal to 5 %, preferably for some applications larger

than or equal to 1 %, and more preferably for some applications larger than or equal to 0.5 %.

[0124] "Semiconductor" refers to any material that is a material that is an insulator at a very low temperature, but which has a appreciable electrical conductivity at a temperatures of about 300 Kelvin. In the present description, use of the term semiconductor is intended to be consistent with use of this term in the art of microelectronics and electrical devices. Semiconductors useful in the present invention may comprise element semiconductors, such as silicon, germanium and diamond, and compound semiconductors, such as group IV compound semiconductors such as SiC and SiGe, group III-V semiconductors such as AlSb, AlAs, Aln, AlP, BN, GaSb, GaAs, GaN, GaP, InSb, InAs, InN, and InP, group III-V ternary semiconductors alloys such as $Al_xGa_{1-x}As$, group II-VI semiconductors such as CsSe, CdS, CdTe, ZnO, ZnSe, ZnS, and ZnTe, group I-VII semiconductors CuCl, group IV – VI semiconductors such as PbS, PbTe and SnS, layer semiconductors such as PbI_2, MoS_2 and GaSe, oxide semiconductors such as CuO and Cu_2O. The term semiconductor includes intrinsic semiconductors and extrinsic semiconductors that are doped with one or more selected materials, including semiconductor having p-type doping materials and n-type doping materials, to provide beneficial electrical properties useful for a given application or device. The term semiconductor includes composite materials comprising a mixture of semiconductors and/or dopants. Specific semiconductor materials useful for in some applications of the present invention include, but are not limited to, Si, Ge, SiC, AlP, AlAs, AlSb, GaN, GaP, GaAs, GaSb, InP, InAs, GaSb, InP, InAs, InSb, ZnO, ZnSe, ZnTe, CdS, CdSe, ZnSe, ZnTe, CdS, CdSe, CdTe, HgS, PbS, PbSe, PbTe, AlGaAs, AlInAs, AlInP, GaAsP, GaInAs, GaInP, AlGaAsSb, AlGaInP, and GaInAsP. Porous silicon semiconductor materials are useful for applications of the present invention in the field of sensors and light emitting materials, such as light emitting diodes (LEDs) and solid state lasers. Impurities of semiconductor materials are atoms, elements, ions and/or molecules other than the semiconductor material(s) themselves or any dopants provided to the semiconductor material. Impurities are undesirable materials present in semiconductor materials which may negatively impact the electrical properties of semiconductor materials, and include but are not limited to oxygen, carbon, and metals including heavy metals. Heavy metal impurities include, but are not limited to, the group of elements between copper and lead on the periodic table, calicum, sodium, and all ions, compounds and/or complexes thereof.

[0125] "Plastic" refers to any synthetic or naturally occurring material or combination of materials that can be molded or shaped, generally when heated, and hardened into a desired shape. Exemplary plastics useful in the devices and methods of the present invention include, but are not limited to, polymers, resins and cellulose derivatives. In the present description, the term plastic is intended to include composite plastic materials comprising one or more plastics with one or more additives, such as structural enhancers, fillers, fibers, plasticizers, stabilizers or additives which may provide desired chemical or physical properties.

[0126] "Elastomer" refers to a polymeric material which can be stretched or deformed and return to its original shape without substantial permanent deformation. Elastomers commonly undergo substantially elastic deformations. Exemplary elastomers useful in the present invention may comprise, polymers, copolymers, composite materials or mixtures of polymers and copolymers. Elastomeric layer refers to a layer comprising at least one elastomer. Elastomeric layers may also include dopants and other non-elastomeric materials. Elastomers useful in the present invention may include, but are not limited to, thermoplastic elastomers, styrenic materials, olefenic materials, polyolefin, polyurethane thermoplastic elastomers, polyamides, synthetic rubbers, PDMS, polybutadiene, polyisobutylene, poly(styrene-butadiene-styrene), polyurethanes, polychloroprene and silicones. Elastomers provide elastomeric stamps useful in the present methods.

[0127] "Transfer device" refers to a device or device component capable of receiving, relocating, assembling and/or integrating an element or array of elements, such as one or more printable semiconductor elements. Transfer devices useful in the present invention include conformable transfer devices, having one or more contact surfaces capable of establishing conformal contact with elements undergoing transfer. The present methods and compositions are particularly well suited for implementation in connection with a transfer device comprising an elastomeric transfer device. Useful elastomeric transfer devices including an, elastomeric stamp, composite elastomeric stamp, an elastomeric layer, plurality of elastomeric layers and an elastomeric layer coupled to a substrate such as a glass, ceramic, metal or polymer substrate.

[0128] "Large area" refers to an area, such as the area of a receiving surface of a substrate used for device fabrication, greater than or equal to 36 square inches .

[0129] "Conformal contact" refers to contact established between surfaces, coated surfaces, and/or surfaces having materials deposited thereon which may be useful for transferring, assembling, organizing and integrating structures (such as printable semiconductor elements) on a substrate surface. In one aspect, conformal contact involves a macroscopic adaptation of one or more contact surfaces of a conformable transfer device to the overall shape of a substrate surface or the surface of an object such as a printable semiconductor element. In another aspect, conformal contact involves a microscopic adaptation of one or more contact surfaces of a conformable transfer device to a substrate surface leading to an intimate contact with out voids. The term conformal contact is intended to be consistent with use of this term in the art of soft lithography. Conformal contact may be established between one or more bare contact surfaces of a conformable transfer device and a substrate surface. Alternatively, conformal contact may be established between one or more coated contact surfaces, for example contact surfaces having a transfer material, printable semiconductor element, device component, and/or device deposited thereon, of a conformable transfer device and a substrate surface. Alternatively, conformal contact may be established between one or more bare or coated contact surfaces of a conformable transfer device and a substrate surface coated with a material such as a transfer material, solid photoresist layer, prepolymer layer, liquid, thin film or fluid.

[0130] "Placement accuracy" refers to the ability of a transfer method or device to transfer a printable element, such as a printable semiconductor element, to a selected position, either relative to the position of other device components, such as electrodes, or relative to a selected region of a receiving surface. "Good placement" accuracy refers to methods and devices capable of transferring a printable element to a selected position relative to another device or device component or relative to a selected region of a receiving surface with spatial deviations from the absolutely correct position less than or equal to 50 microns, more preferably less than or equal to 20 microns for some applications and even more preferably less than or equal to 5 microns for some applications. The present invention provides devices comprising at least one printable element transferred with good placement accuracy.

[0131] "Optical communication" refers to a configuration of two or more elements wherein one or more beams of electromagnetic radiation are capable of propagating from one element to the other element. Elements in optical communication may be in direct optical communication or indirect optical communication. "Direct optical

communication" refers to a configuration of two or more elements wherein one or more beams of electromagnetic radiation propagate directly from a first device element to another without use of optical components for steering and/or combining the beams. "Indirect optical communication" on the other hand refers to a configuration of two or more elements wherein one or more beams of electromagnetic radiation propagate between two elements via one or more device components including, but not limited to, wave guides, fiber optic elements, reflectors, filters, prisms, lenses, gratings and any combination of these device components.

[0132] The present invention relates to the following fields: collecting optics, diffusing optics, displays, pick and place assembly, vertical cavity surface-emitting lasers (VCSELS) and arrays thereof, LEDs and arrays thereof, transparent electronics, photovoltaic arrays, solar cells and arrays thereof, flexible electronics, micromanipulation, plastic electronics, displays, transfer printing, LEDs, transparent electronics, stretchable electronics, and flexible electronics.

[0133] The present invention provides optical devices and device arrays, for example LED arrays, laser arrays, optical sensors and sensor arrays, and photovoltaic arrays, comprising printable, high quality inorganic semiconductor elements assembled and integrated via transfer printing techniques. Assembly and integration methods of the present invention include dry contact printing of printable semiconductor elements, replica molding for making device substrate such as device substrates having integrated optical components (e.g., lens arrays) and lamination processing steps.

[0134] In an embodiment, the invention provides a new type of display that generates images by the coordinated operation of assemblies of light-emitting diodes (LEDs) or other light emitting or collecting devices. The images may be high definition, as those on a computer monitor or television, or they may provide simple illumination in a way similar to fluorescent lights. The invention is formed by the assembly of small inorganic light emitting devices, transistors, and electrically conductive interconnects. Transfer printing and other novel fabrication processes may be used to perform the assembly of these components and to impart new functionality to them, e.g. stretchability.

[0135] The invention may be built on a range of substrates, including rigid materials (e.g. glass), flexible materials (e.g. thin plastic), and even stretchable materials (e.g. elastomers), imparting a number of benefits to these display and illumination products, including a high-degree of transparency, flexibility, and/or stretchability, as well as

mechanical toughness and low weight. The invention is therefore useful for a number of applications, including architectural elements and devices that can dynamically conform to complex contours of objects, for example in the aerospace, transportation, medical, and fashion industries. The light emitters (LEDs) used are capable of high-speed operation and great brightness, enabling effective display of images even in full sunlight (e.g. for outdoor displays).

[0136] The novel transfer printing and other fabrication processes of the present invention, in addition to imparting functionality to the displays, enable the production of systems of the invention at costs lower than those required to produce other, less versatile types of displays (e.g. conventional LED displays). The novel transfer printing and other fabrication procedures also enables systems of the invention to achieve levels of brightness, large-area coverage, transparency, mechanical properties, operating lifetime, and/or resolution combinations that are not available to other display technologies (liquid crystal displays, organic LED displays, conventional LED displays, cathode ray tube displays, etc.).

[0137] Figure 1 provides a schematic showing optical systems provided by the present invention. As shown in Figure 1, the present invention provides a number of classes of optical systems and related methods of making these systems, including systems for light generation and systems for light harvesting, comprising printed inorganic optical and optoelectronic systems with integrated optical components in registry. Light generation systems include printed LED displays, micro LED devices, passive matrix LED displays, active matrix LED displays, printed VCSEL systems and printed semiconductor laser arrays, optionally comprising light diffusing optics, light focusing optics and/or light filtering optics. Light harvesting systems include sensors, such as artificial eye sensors, sphere/plane convertible stamp sensors and sphere confirmable stretchable semiconductor based sensors, and photovoltaic systems, such as photovoltaic arrays, microsolar cells, optionally comprising collecting optics. Optical systems of the present invention include stretchable devices and systems, flexible devices and systems and rigid devices and systems.

[0138] Fig. 2 A- E provides schematic diagrams of optical systems of the present invention comprising printable semiconductor elements. Figure 2A shows a printed LED array with integrated optical diffuser. Figure 2B shows a VCSEL array on a silicon chip with integrated optical fibers. Figure 2C shows a printed photovoltaic array with

integrated optical collectors. Figure 2D shows an artificial eye sensor comprising a printed photodiode array on a collecting lens. Figure 2E shows a sheet scanner having both light sensing and light generation functionality and comprising a printed array LED and photodiode components and integrated collection optics provided on a polymer or other low cost substrate.

[0139] Fig. 3 provides a process flow schematic for the fabrication of a single pixel element of a printed inorganic active matrix LED display of the present invention. Panel 1 illustrates the step of preparing gate electrodes on substrate. Panel 2 illustrates the step of spin-coat thin-film adhesive on the patterned substrate. Panel 3 illustrates the step of printing a thin-film transistor structure on the adhesive layer, for example using contact printing. Panel 4 illustrates the step of depositing (or printing) electrode lines so as to interconnect the printed transistor structure. Panel 5 illustrates the step of printing an LED structure onto one or more electrodes. In some embodiments, bonding of these elements is achieved by cold-welding. Panel 6 illustrates the step of encapsulating or planarizing the device components, for example using a photocurable epoxy. Panel 7 illustrates the step of depositing or printing electrical contacts to top the LED electrode structure.

[0140] Fig. 4 provides a schematic illustration (not to scale) of a printed active matrix LED display on a glass substrate. The display shown comprises 100 pixels and is an approximately 11 inch display. Thin film transistor (TFT) elements, LED elements, gate lines, anode lines and data lines of the device are indicated in Figure 4. TFT and LED structures are assembled via printing, for example using one or more elastomeric stamps. Metal lines are patterned with shadow masks. The bottom plate holds LED structures, data and gate lines, and TFT structures. The top plate holds the anode lines.

[0141] Fig. 5 provides photographs (Figure 5A) and operating current-voltage characteristics (Figure 5B) of a single pixel of an active matrix LED display on a (transparent) glass substrate. As shown in Figure 5A the single pixel of an active matrix LED display comprises a printed TFT structure, a LED structure, gate electrode and electrical interconnects. Figure 5B provides a plot of current (A) verses drive bias (V) for the single pixel of an active matrix LED display.

[0142] Fig. 6 provides photographs of a 64 pixel active matrix LED display on a (transparent) glass substrate. Fig. 6A provides a photograph of a 64 pixel partial LED display (Note: missing top contacts) comprising 1 mm transistors printed on to the

device substrate and ILEDs manually placed on the substrate. In the device shown in Figure 6A, pixels are provided at a 4 mm pitch. Fig. 6B provides a photograph of a printed silicon TFT with interdigitated channel (thin green line) for high-current operation. Figure 6C provides a photograph of two pixels illuminated by placing a transparent common anode electrical contact against the LEDs.

[0143] Fig. 7A provides a process flow schematic for the fabrication of a single pixel element of a printed inorganic passive matrix LED display. Panel 1 illustrates the step of spin coating a layer of elastomer precursor onto a receiving surface of the substrate. After spin casting the elastomer precursor layer is at least partially cured. Panel 2 illustrates the step of depositing an electrode. Panel 3 illustrates the step of printing an ILED structure onto the electrode, for example via contact printing. Panel 4 illustrates the step of laminating the top electrode, wherein the top electrode is housed on a second substrate. This processing steps achieves contacting of the printed LED structure.

[0144] Fig. 7B provides a process flow schematic for establishing electrical contact by compression of a (soft) substrate/layer. Panel 1 illustrates the step of placing a component between 2 substrates (at least one soft – e.g., elastomer) prepatterned with integrated electrodes. Panel 2 illustrates the step of activating the substrate surfaces for strong bonding upon contact, for example via oxygen plasma treatment for bonding PDMS to PDMS or PDMS to glass. Panel 3 illustrates the step of pressing the two substrates together, for example by "sandwiching" the component. In this processing step sufficient pressure is applied to deform the soft layer and bring the two surfaces into contact. After bonding, the electrical contact is maintained by residual pressure. Panel 4 illustrates a similar process as shown in Panel 3, using optional relief features to facilitate contact and engineer a stronger bonding interface, for example via reduction of stress concentration points.

[0145] Fig. 8 provides a schematic illustration (not to scale) of a printed passive matrix printed inorganic LED display. As shown in Figure 8, the display comprises a bottom substrate, electrode network, printed ILED, PDMS layer and top substrate.

[0146] Fig. 9 provides photographs of passively addressed printed inorganic LED displays/arrays on glass and flexible PET substrates.

[0147] Fig. 10 provides a process flow schematic for printing inorganic light emitters and collectors via cold-weld bonding techniques. Panel 1 illustrates the step of evaporating metal (e.g. gold, indium, silver, etc.) onto an inorganic element disposed on a transfer device (e.g., an elastomeric stamp). As shown in panel 1 metal is also evaporated on the receiving surface of a substrate. Panel 2 illustrates the step of contacting the stamp and inorganic element to receiving surface, and optionally applying heat or pressure to induce cold-welding of metal films. Panel 3 illustrates the step of removing the stamp, thereby resulting in transfer and assembly of the inorganic elements via contact printing.

[0148] Fig. 11 provides a process flow schematic for printing techniques of the present invention using a donor cartridge and cold-weld bonding technique. In this method a cartridge is patterned with SU-8. ILED structures are placed on the patterned surface of the cartridge. A stamp is used to take up the ILED structures and subsequently print the ILED structures on a substrate prepatterned with electrodes via transfer printing. The bottom panel of figure 11 shows an example of a LED structure printed and assembled using this method.

[0149] Fig. 12 provides a schematic of an optical system of the present invention wherein diffusing optics are integrated with printable LED structures. In this embodiment, PDMS is molded on rough polystyrene. A comparison of panels (a) and (b) show the affect of incorporation of a diffuser in this optical system. The diffuser can be a rough molded PDMS structure. This figure demonstrates that diffusers can effectively increase the size of the luminous region.

[0150] Fig. 13 provides a schematic of diffusing optics comprising a plurality of radial density gradient scattering centers useful for LED lighting systems of the present invention. As shown in this figure a printed LED structure under metal is provided in optical communication with a plurality of optical scattering centers. The bottom panel in Figure 13 shows a cross sectional view of scattering centers comprising relief features in a transparent substrate.

[0151] Fig. 14A provides an exemplary epilayer structure for the fabrication of printable micro-LEDs. As shown in this figure, the epilayer structure comprises a series of device layers, sacrificial layers and a handle wafer. Individual layers in the epilayer structure are shown in the bottom panel of Figure 14A. Fig. 14B provides an exemplary epilayer structure for the fabrication of printable micro-LEDs comprising quantum well emissive

layers. The epilayer structure comprises a series of semiconductor layers provided between p-cladding and n-cladding layers. Specific compositions of each layer in the epilayer structure are provided. Fig. 14C provides a table indicating the composition, thickness, doping and functionality of each layer in the epilayer structure for the fabrication of printable micro-LEDs.

[0152] Figure 14D illustrates an example of a mother wafer from which printable p-on-n GaAs solar cells may be produced by photolithography and etching layers 9 through 4 and selectively removing layer 3 by a wet chemical etch.

[0153] Figure 14E illustrates provides another example of a mother wafer from which printable n-on-p GaAs solar cells may be produced by photolithography and etching layers 9 through 4 and selectively removing layer 3 by a wet chemical etch.

[0154] Fig. 15 provides schematic diagrams illustrating the imperceptible pixilation/high degree of transparency from low fill-factor, micro-sized (<~100 micron footprint) LEDs. As shown in the top panel of this figure, the optical system comprises: (i) a first glass coated ITO or a low-fill factor metal mesh layer ; (ii) printed micro LEDS structures; and (iii) a second glass coated ITO or a low-fill factor metal mesh layer. Top views are provided corresponding to the off state and the on state. A magnification of the top view is also provided showing the positioning of micro LED structures.

[0155] Fig. 16 provides schemes for the release of printable light-emitting inorganic semiconductor micro-elements: micro-LEDs or VCSELs. Scheme 1 describes the release of such elements by encapsulating them in a polymer, e.g. photoresist, and releasing them from the wafer on which they were grown by selectively etching an $Al_xGa_{1-x}As$ (x>about 70%) sacrificial layer using hydrofluoric acid. Scheme 2 describes release by encapsulating them in a conformal dielectric (e.g. silicon nitride) and releasing them from the wafer by selectively oxidizing the AlGaAs and etching the oxidized material using aqueous potassium hydroxide. Scheme 3 describes release by encapsulating them with a polymer, e.g. photoresist, followed by selective etching of a buried GaAs sacrificial layer using an aqueous mixture of citric acid and hydrogen peroxide. In Scheme 3, the AlGaAs protects the underside of the light emitting element from the citric acid-based etchant.

[0156] Fig. 17A provides a schematic process flow diagram illustrating fabrication of integrated solar cell/collector arrays by printing solar cells. As shown in this figure solar

microcells are fabricated in a dense array on a wafer. A stamp is brought into contact with the dense solar cell array and used to transfer the solar cells from the wafer to a target assembly substrate. As shown in Figure 17A, the solar microcells in the array are transferred onto the back electrode of the target assembly substrate via contact printing. Fig. 17B provides a schematic process flow diagram illustrating fabrication of integrated solar cell/collector arrays via interconnection of registry of an optical array. As shown in this figure solar microcells are printed on a target substrate. The substrate is further processed to provide front electrode and an insulating layer. Next, a molded micro array of microlenses is integrated into the optical system such that each lens in the array is individually addressed to at least one solar microcell. Fig. 17C provides a schematic process flow diagram illustrating the operation of the integrated solar cell/collector arrays. In this embodiment, each microlens collector/concentrator is individually addressed and optically aligned with a single crystal solar cell, as shown in the top panel of Figure 17C. Also shown in this figure are the front electrode, insulating layer and back electrode. The bottom panel of figure 17C schematically shows interaction of sun light with the optical system.

[0157] Fig. 18A provides a schematic diagram (not to scale) showing operation of the integrated collecting/concentrating optics (lens) and solar-cell arrays of an optical system of the present invention. The collection and focusing of incident light is provided by the ray diagrams provided in this figure, which show light incident to the optical concentrator is focused on the active area of a printed microsolar cell addressed to the optical concentrator. A gold layer provides a bonding layer to affix the microsolar cell to the device substrate. Figure 18B shows an expanded view of a microsolar cell of the present invention assembled via printing. The solar cell is a multilayer structure comprising an antireflection layer, top contact, p-n junction and a bottom aluminum layer.

[0158] Fig. 19 provides a schematic diagram illustrating design and fabrication strategies of the present invention for light harvesting via reduction of semiconductor materials costs in a sheet-like form factor. The collector size is approximately 2 mm, the solar cell size is approximately 0.1 mm, and the area multiplication (ratio of collector area and solar cell area) is approximately 400. As demonstrated by the calculation show in this figure 1ft^2 of processed semiconductor wafer results in approximately 400 ft^2 of light-harvesting area. This calculation demonstrates that the methods and optical

systems of the present invention provide a high efficiency and low cost fabrication strategy for high performance photovoltaic devices and systems.

[0159] Fig. 20 provides a schematic diagram of a collecting/concentrating optic and heterogenously composed solar cell of a solar cell array (sympevolent/diventegration) of the present invention. As shown in this figure, collecting optics are provided in optical communication with a nitride/phosophide and/or arsenide solar cell and silicon solar cell assembled on the device substrate via contact printing. Figure 20 also provides ray diagram of the incident light showing collection and focus functionality of a concentrator and individually addressed solar cells. Single crystal multilayer solar cells (i.e. third generation solar cells) are typically grown by MOCVD and are constrained by the necessity of crystal lattice mismatch between layers. In our system different absorbing layers can have arbitrary lattices and the materials selected for optimal spectrum absorption for each layer.

[0160] Fig. 21 provides a schematic process flow diagram for fabrication of an integrated solar cell and lens array using a combination of replica molding methods and contact printing. As shown in this figure a master lens array is used to generate a negative replica mold, for example via replica molding or imprinting techniques. Next, the molded PDMS layer is used to generate a plano-concave polymer lens array by casting the polymer against the negative replica. As shown in Figure 21, solar cells printed onto a device substrate are provided in optical communication with the lens array so as to generate an optical system of the present invention.

[0161] Fig. 22 demonstrates the ability of Fresnel lenses, a type of concentrating/collecting optic, to focus light to a small area for use in light harvesting systems described by the present invention. Fresnel lens arrays can be used as optical concentrators due to their advantageous features such as thin form factor and light weight compared with conventional lenses. Fig. 22 shows a focal area measurement for spherical and cylindrical Fresnel lenses.

[0162] Fig. 23 provides a schematic diagram illustrating an optical system of the present invention wherein horizontal light pipes and/or waveguides are provided for light harvesting. This optical system uses transparent, structured media of appropriate index of refraction to capture normally- or obliguely-incident light and guide it in the plane of the substrate to a solar cell or solar cell array. As shown in this figure a plurality of waveguide structures, such as light pipes, are in optical communication and individually

addressed a solar cell such that the light collected by each waveguide is directed to the solar cell.

[0163] Fig. 24 provides a schematic showing an exemplary printable silicon solar cell fabricated using a silicon on insulator SOI wafer. The solar cell comprises a doped top surface with a P/As mixture and is supported by a buried oxide layer of the SOI wafer. Figure 24 shows the solar cell multilayer structure comprising a n^+-Si (P/As) layer and p-Si(B) layer. In an embodiment, the silicon solar cell is assembled into a photovoltaic system via a method comprising the steps of: (i) patterning the surface of the SOI wafer, for example using ICP-RIE, so as to define the physical dimensions of one or more printable solar cell structures; (ii) releasing printable solar cell structures, for example via HF undercut etch processing wherein the buried oxide layer is selectively etched thereby releasing the printable solar cell structures; (iii) retrieving the silicon printable structures, for example using an elastomeric (e.g., PDMS) stamp which is contacted with the released printable solar cell structures and pulled away from the SOI substrate, thereby transferring the printable solar cell structures from the substrate to the elastomeric stamp ; (iv) depositing back metallization of the printable solar cell structures, for example using CVD, PVD or thermal deposition methods; (v) transferring printable silicon structures having back metallization from the elastomeric stamp to a metallized device substrate via contact printing, optionally in combination with a cold-welding bond step; (vi) annealing the solar cell structures printed onto the device substrate to activate Al-doped p+ region; (vii) casting an insulating/planarization layer on the printed solar cell structures; (viii) depositing top electrical contacts onto the printed solar cells, for example using a combination of photolithography and evaporation processing; (iv) depositing a Si_3N_4 antireflecting coating on the solar cell array and (v) integrating the concentrator optics, such as a lens array, to the top of the micro-solar cell array.

[0164] Fig 25 provides a schematic process flow diagram illustrating a method of transferring a printable solar cell to substrate using contact printing and subsequent cold welding processing to affix the solar cell to a device substrate. As shown in the figure, the solar cell is contacted with an elastomeric stamp (e.g. PDMS stamp). A thin gold layer is provided to the external aluminum layer of the printable solar cell. The surface of the solar cell having the thin gold layer is contacted with a metallized receiving surface of the device substrate. The elastomeric stamp is subsequently moved away

from the substrate resulting in transfer of the printable solar cell to the device substrate. Finally the transferred solar cell is annealed to activate the aluminum doped p^+ region.

[0165] Fig 26 provides a schematic diagram (not to scale) showing a top view (in parallel) of an exemplary configuration for top contacts to solar arrays of the present invention. Microsolar cells (shown in gray) having widths of approximately 100 microns and lengths of approximately 1 millimeter are provided in an array format on a device substrate. Metal features are provided having widths of about 60 microns and lengths on the order of 1 inch. The metal features provide the top contacts of a solar cell device array of the present invention.

[0166] Fig 27 provides a schematic diagram of an "artificial eye" sensor of the current invention. The sensor comprises an inorganic photodiode array distributed on a lens having spherical curvature. Various lens shapes and angles are shown in Figure 27. Fig 28 provides a schematic diagram illustrating the process of wrapping a planar sheet around a spherical surface demonstrating the necessity of stretchability in an exemplary "artificial eye" sensor. As shown in Figure 28, conformal positioning of the planar sheet on a spherical receiving surface requires some degree of stretchability to avoid failure.

Example 1. Ultra Thin Flexible Solar (UTFS) Devices and Methods

[0167] Photovoltaic (PV) energy conversion is the direct conversion of sunlight into electricity using a semiconductor device structure. The most common technology in the PV industry is based on single crystalline and polycrystalline silicon technology. Presently, silicon PV technology has high materials costs, due to the relatively inefficient use of the bulk silicon material. In conventional methods, bulk crystalline silicon is sawn into wafers, which are then processed into solar cells and soldered together to form the final module. Typical multicrystalline efficiencies are on the order of 15%; high-performance, single-crystal silicon has been produced with 20% efficiency. For this type of solar cell, 57% of the cost is in materials, and of that total material cost 42% comes from the crystalline Si. In addition, these modules are rigid and heavy.

[0168] There is currently interest in thin-film PV technologies, since these systems have the potential for lower cost (due to less active material usage), and also have the ability to be deposited onto polymer substrates for low weight and flexibility. Presently,

investigation is ongoing in thin film materials such as amorphous silicon, cadmium telluride (CdTe) and copper indium gallium diselenide (CIGS). CIGS-based PV cells have demonstrated cell efficiencies of 19.2%, the highest of any polycrystalline thin film material. These cells are small, laboratory-scale devices; to date, the highest large-area flexible module efficiencies are on the order of 10%. Cheaper thin film semiconductors enable material cost savings, but induce higher processing costs as the cells need to be fabricated/processed on large area substrates. Also, only low/moderate temperature processes can be used on the final assembly substrate

[0169] Ideally, one would like to combine the single crystalline technologies, which have a high efficiency and large industrial knowledge base, with the low-cost, lightweight and flexible nature of the thin-film technologies. The present Ultra Thin Flexible Solar (UTFS) technology provides the means of achieving a lightweight, flexible solar module with both high efficiency and lower materials costs. Since we start with a pure silicon substrate, it enables the use of high precision and high-temperature wafer processing to fabricate state-of-the-art performance solar cells.

[0170] The present invention provides Ultra Thin Flexible Solar (UTFS) Devices generated via a novel fabrication platform combining :

1. An ultra-thin (less than 20 microns thickness) crystalline silicon solar cell, grown and etched on a single-crystal silicon wafer. The size of this cell is much less (e.g., two orders of magnitude) than those used in previous silicon-transfer processes, for example the solar cells have lengths and width that are on the order of 100 microns in some embodiments;
2. An innovative microstamping process which removes the silicon solar cell from the mother wafer and transfers it to a flexible polymer substrate; and
3. Automated interconnect of the transferred cells to form the final module, if required.

[0171] Methods and systems of the present invention utilize a microstamping contact printing process that avoids certain problems associated with past silicon transfer technologies; namely, the cracking and defects formed by attempting to transfer relatively large pieces of silicon. The present microstamping contact printing process also reduces the overall module assembly cost (compared to conventional die pick-and-place techniques) as thousands of micro-cells can be transfer-printed in parallel.

[0172] The solar cell devices and fabrication methods of the present invention have several advantages including its applicable to a wide variety of high quality crystalline semiconductors including but not limited to single crystalline silicon and other higher-efficiency materials, such as Gallium Arsenide (GaAs). In addition, combination of an ultra-thin solar cell and a polymer substrate provides devices and systems having low weight and good mechanical flexibility. Polypropylene is a polymer useful for this aspect of the present systems and methods.

[0173] Figure 29 provides a schematic of a process flow diagram showing a method for making a microsolar cell array of the present invention. As shown in Figure 29, a Si wafer is processed so as to generate a plurality of silicon-based microsolar cell ribbons. The silicon-based microsolar cell ribbons are released from the substrate. The released ribbons are lifted off and transferred to a polymer device substrate via contact printing using an elastomeric transfer device. Ribbons of silicon are assembled into a photovoltaic device array via subsequent processing including the step of providing device interconnects to the microsolar cells, and optionally light collection and concentrating optics such as a lens array.

[0174] As shown in Figure 29, thin (~10 μm) silicon solar cells are transferred to polymer substrates and interconnected to form a module in a manner that retains flexibility. Selection of the thickness of the silicon component of the silicon solar cell is an important parameter in the present invention. In an embodiment, for example, the thin silicon component is thick enough to achieve a desired efficiency of ~15%. The primary impact of thickness on the cell performance is on the collected current; with a thinner cell, less photons are absorbed and hence less current is generated. Figure 30, provides a plot of Si Layer thickness verses short circuit current (J_{sc}) as calculated for a simulated Si cell exposed to the AM1.5 standard spectrum used for terrestrial-based solar cells. For these calculations, we assume that the light makes three total passes through the Si layer (Once initially, once after reflection off of the back, and again after subsequent reflection off of the front side), and that the quantum efficiency of the cell is relatively high (90%).

[0175] From the results of the calculation, a silicon thickness on the order of **10-15** microns would be required in some embodiments of the present invention to achieve the desired AM1.5 efficiency of 15%. It should be noted that this relatively thick absorber

layer is due to the fact that silicon is an indirect-bandgap material. A similar solar cell using a direct-bandgap material, such as gallium arsenide, can be thinner.

[0176] Multilayer stacks of printable silicon ribbons can be formed by using a combination of RIE and wet etching. Figure 31 provides scanning electron micrographs showing sequential formation of Si multilayer ribbon stacks useful in some embodiments of the present invention. These are high-quality, dimensionally-uniform ribbons. By appropriate processing into p-n diodes, these can be converted into silicon solar cells.

[0177] Previous silicon transfer techniques typically glue the liftoff layer to a glass carrier, and also transfer relatively large areas of silicon (~5 cm^2). One of the major issues with these transfer techniques are cracks and defects formed in the Si layer.

[0178] By transferring smaller pieces of Si, we avoid cracking the transferred Si layer. We also use an innovative 'stamping' process using a poly-dimethylsiloxane (PDMS) material to grip and transfer the silicon to a polymer substrate.

[0179] A polymer such PET or PEN is useful for the substrate in terrestrial applications. For space-based applications, a space-rated polyamide such as Kapton can be used as a substrate material. Kapton is mechanically suitable for space applications, although it is known to degrade in low earth orbit due to the presence of atomic oxygen (AO).

[0180] After transfer of the Si ribbons to the polymer substrate, they are electrically interconnected to form the final solar cell. In some embodiments, individual Si ribbons are connected in a series connection. Fig. 32 provides a schematic diagram of a connection scheme where the Si ribbons comprise p-type silicon with a thin n-type layer on top to form the emitter. After transfer, connection lines comprising conducting ink are printed onto the ribbons, either via a direct-write process or via screen-printing. The bottom panel shows the as-transferred Si Ribbons and the top panel shows the connection (direct-write or screen-printing). Only four Si Ribbons are shown for clarity.

[0181] One of the attractions of the present technology is that it is applicable to other absorber materials; for example, the same microstamping process has been used to transfer gallium arsenide. The use of these materials has been demonstrated in concentrator solar modules. Fig 33 provides a schematic of a solar cell array of the present invention using a PDMS concentrator array for concentrating solar illumination.

[0182] Bulk crystalline silicon is selling for over $50 per kilogram. Presently, silicon plants are coming online to meet the needs of both the PV and microelectronic industries. It is anticipated that even if bulk Si costs fall back to pre-2001 values of $20/kg, as capacity catches up with demand, overall costs will remain high. As mentioned previously, present-day Si PV is formed by sawing a crystalline ingot into wafers, then processing the wafers into cells, and then soldering the cells together to form the final module. The present industry trend is towards thinner cells, since Si thicknesses beyond ~50 microns (see Figure 30) do not absorb any more light. Currently, the thinnest Si PV cells are on the order of 250 microns thick (about ¼ mm). Handling such thin wafers in the 'normal' PV cell processing and integration is a challenge.

[0183] Conventional wire-sawing techniques result in approximately 60% waste; that is, 60% of the original silicon ingot winds up as dust. For a 20% efficient module formed out of 250-micron-thick wafers, the silicon materials costs are estimated at $0.40/Watt. Considering that the ultimate goal of the PV industry is to achieve $1/Watt, the materials costs for such a module are significant.

[0184] For the present UTFS technology, the semiconductor materials costs is much lower. Even assuming a waste of 50%, with a 15% module with 15-micron thick silicon the materials costs are estimated at ~$0.02/Watt. This cost savings is primarily due to the better utilization of the silicon; in effect, we are 'spreading' the silicon over a greater area than in convention methods and devices.

[0185] The printing process involves the liftoff of the device element from the mother substrate onto the stamp, followed by the delivery of these elements from the surface of the stamp to the target substrate. By appropriate design of the undercut etch and liftoff of these elements from their mother substrate, it is possible to perform the liftoff step with high yields. The transfer is accomplished either by stronger van der Waals bonding between the element and the target substrate than between the element and the stamp or by the use of strong adhesive layers on the target substrate. In both cases, the area of contact between the element and the coated or uncoated surface of the target substrate must be sufficiently high to enable efficient transfer. In most case, the dominant requirement is for the bottom surfaces of the elements and the top surfaces of the target substrate to be sufficiently smooth to enable large contact areas. This requirement can be satisfied for a wide range of systems of interest. The systems

considered in this example are extremely well situated to meet these flatness requirements, since they involve elements with polished back surface and target substrates that will consist of polished semiconductor wafers.

[0186] Fig 34 provides images showing results of printing single crystal silicon onto plastic, glass, Si wafers, InP wafers and thin film a-Si. The microstamping process of the present invention is compatible with a wide range of substrates.

[0187] In an embodiment, the stamps used to pick-up and transfer the 'chiplets' are typically made by casting and curing a ~1 cm thick piece of rubber against a "master" substrate. The patterns present on the surface of the "master" can be replicated with extremely high fidelity (down to the nanometer scale) when low modulus silicone such as poly-dimethylsiloxane (PDMS) are used to fabricate the stamps. However, single layer stamps made out of this soft material can easily be deformed during the printing process. As a result, coarse placement accuracy is sometimes realized with these soft stamps. The present invention includes, however, use of composite stamps that provide excellent placement accuracy and pattern fidelity. U.S. Patent Application No. 11/115,954, for "Composite Patterning Devices for Soft Lithography" , issued as U.S. Patent No. 7,195,733, describes composite stamps designs and methods useful in the present invention and is hereby incorporated by reference in its entirety.

[0188] A low modulus material, such as PDMS, is used for the first layer to allow conformal (i.e. with no air void) contact with the top surface of the semiconductor device components. Additional thin layers (such as plastic films or glass fibers) having a high in-plane modulus is used to prevent in-plane mechanical deformations during the transfer. By using such composite stamp designs, in-plane distortions (as observed under a high magnification microscope) lower than 5 microns over a ~16x16 cm^2 area are achievable in soft lithography printing techniques.

[0189] In an embodiment, the printing systems comprise: (1) stamps with designs optimized for efficient transfer and for minimal distortions in the placement of the printed elements, (2) physical mounting jigs for these stamps and translation stages for moving the substrate and the stamp with sub-micron precision, (3) load cells interfaced to the stamps for force feedback control of contact during the 'inking' and 'printing' steps, and (4) vision systems that allow multilevel registration. In some embodiments, printing systems useful in the present invention can handle target device substrates with sizes up to 300 x 400 mm and donor wafers with diameters up to 4 inches. The registration is

accomplished with a long working distance microscope and CCD camera that allows alignment marks on the surfaces of transparent stamps to be registered to alignment marks on the donor wafers and the target substrates. The accuracy with which the stamps can be positioned and aligned is ~0.5 μm. The registration accuracy, when implemented with new types of distortion-free composite stamps, is also in this range.

Example 2. Conformable Thin Film LED Lighting Systems

[0190] The present invention provides printing based techniques that provide a means to integrate inorganic light emitting diodes with thin flexible substrates. This approach, as implemented with automated high precision printer systems, is useful for fabricating light-weight and mechanically conformable interior lighting elements for automotive and other applications, in a manner that is compatible with low cost manufacturing.

[0191] The present methods and systems involve fabrication of conformable ILED-based thin film lighting devices followed by application to surfaces using adhesive bonding. Methods may also optionally include processing involving incorporation of encapsulation and planarizing materials, coatings and layers to enhance mechanical properties of the system. The sizes of the thin film structures, the numbers and spacings of the ILEDs and other aspects determine the device designs for specific application.

[0192] Transfer printing of micro/nanoscale semiconductor devices from source wafers to wide ranging classes of target substrates, including thin plastic sheets, is used in the present invention to fabricate conformable LED lighting systems. Figure 35 shows a schematic illustration of an exemplary process of the present invention, as applied to the printing of printable inorganic semiconductor-based LEDs. The transfer of the ink to, and from, an elastomeric stamp is affected by kinetically modulating the adhesion energy at the stamp-'ink' and 'ink'-substrate surfaces. In the case of Fig. 35, printable inorganic semiconductor-based LEDs play the role of the 'ink'. This type of process is capable of manipulating semiconductor materials or devices with lateral dimensions between 100 nm and hundreds of microns, and with thicknesses between 20 nm and hundreds of microns. Electronic and optoelectronic systems of various types have been demonstrated with this approach, on substrates ranging from rigid glass, polymer and semiconductor wafers to thin flexible sheets of plastic. The printing itself is performed with a fully automated printer that provides both force and feedback control of the

transfer process, together with microscope based vision systems for alignment. Figure 36 provides an image and a schematic illustration of a printer useful in the present methods of fabricating conformable ILED-based thin film lighting systems.

[0193] Using such an approach, a small passive matrix 8x8 lighting pad has been assembled with blue inorganic LEDs assembled on a polycarbonate substrate with prepatterned metallic interconnects. Fig 37 provides images of square (part a) and linear (part b) lighting devices that comprise passively addressed blue inorganic LEDs assembled on plastic substrates via contact printing. The device in part (b) represents a demonstration of a thin film lighting device comprising a conformable ILED-based lighting system of the present invention. A small version of a blue ILED-based thin film lighting device is also shown in Fig. 37.

[0194] In some embodiments, conformable LED lighting systems of the present invention have utility for lighting applications for automobiles and other vehicles. In some embodiments, for example, the present invention provides reliable and low cost ILED-based thin film lighting devices that can be integrated in a conformal way with the relevant surfaces of an automobile or other vehicle.

[0195] Figure 39 provides a schematic process flow diagram of a method of fabricating a conformable LED lighting system of the present invention. As shown in Figure 39, an adhesive material is (NOA) is used to fix ILED and top/bottom substrate before injection of PDMS. In some embodiments, external power lines are installed before injection of PDMS to prevent contamination of the external pad region, as shown in Figure 39. In some embodiments, sample is installed with tilted angle in a vacuum chamber to remove air in injected PDMS, as shown in Figure 39. In some embodiments, pressure is applied between two substrates to keep a contact between the ILEDs and electrodes, as shown in Figure 39. Injection of a PDMS encapsulating layer is useful for improving the bending characteristics of the device (particularly in slow bending motion) and injection of PDMS achieves a stable contact property.

[0196] Figure 39 provides a process flow diagram for fabricating a ILED light device of the present invention comprising a flexible strip. As shown in this figure, a thin PDMS layer is provided on a PET film. Electrodes are defined and deposited via evaporation of Ti/Au and shadow masking technique. Printable ILED device elements are transferred and assembled onto the substrate via contact printing. As shown in Figure 39, an adhesive (e.g., NOA) is provided to the bottom substrate, and the top substrate is

bonded to the device. The external pad and wire is fixed and a PDMS adhesive is inject and cured, optionally under vacuum conditions, so as to encapsulate/planarize the ILED structures.

[0197] Figure 40 provides a cross sectional view of a conformal ILED lighting system of the present invention comprising top and bottom PET substrates (approximately 175 microns thick), ILEDS structures (approximately 100 microns thick), electrodes and a PDMS encapsulating coating or layer (approximately 20 – 40 microns thick).

[0198] Figure 41 provides images of ILED lighting systems of the present invention in an unbent state, a first bent state with a bending radius of 7 cm, a second bent state with a bending radius of 5 cm, third bent state with a bending radius of 4.5 cm, a fourth bent state with a bending radius of 3 cm and in a state upon release of the bending stress. The images in Figure 41 confirm that conformal ILED lighting systems of the present invention provide useful optical properties in bent configurations.

[0199] Fig 42 provides an image of a flexible strip light made of blue LEDs and thin kapton substrates with bending radius equal to 0.85 cm.

Table 1: Summary of Experimental Conditions for Testing the Mechanical Properties of Conformal ILED Sensors.

#	Substrate		Electrode	Electroplating	Operating Check 1	Injection	Operating Check 2	Bending Radius (Max.)	Operating Check 3	Note
	PDMS	PET								
1	O	O	Ti/Au(5/300nm)	X	50%	O	50%	3cm	50%	Improve
2	O	O	Ti/Au(5/300nm)	X	90%	O	90%	3cm	80%	
3	O	O	Ti/Au(5/300nm)	X	70%	O	70%	3cm	70%	
4	O	O	Al/Ti/Au(700/5/50nm)	X	50%	--	--	--	--	
5	X	O	Al/Ti/Au(500/5/100nm)	O	80%	O	80%	3cm	80%	Improve
6	X	O	Ti/Au(5/300nm)	X	60%	O	60%	3cm	50%	However, working problem after repeatable test
7	O	O	Ti/Au(5/300nm)	O	X	X	X	X	X	Delamination of electrode from substrate for electroplating

[0200] In results of experiment, we observe that operation of the present conformable ILED-based lighting systems is improved in cases of thicker electrode and PDMS coatings or encapsulating layers on PET. However, it is difficult to fabricate a strip-light with only thicker electrode because alignment of ILED on electrode (by hand) is difficult. In some embodiments, the process uses a by using an aligner to provide more stable

and accurate assembly. An optimized system for some embodiments combines thicker electrode, PDMS coating on PET and removing tweezing process by hand.

[0201] Figure 43 provides schematics showing two methods for assembling ILED structures on the device substrate. The lower panel shows an assembly method using alignment by hand and the upper panel show an assembly method using an aligner. When we use an aligner to align ILED on electrode, the number of operating ILED are greatly increased because a damage of electrodes is reduced compared to use tweezers. This method also enhances alignment between the ILED and electrode structures.

Example 3: Printing-based assembly of solar cells and solar cell arrays

[0202] Fig 44 provides a schematic for the formation of a micro single crystal silicon solar cell with low-level concentrating lens. In the first step (a) the micro structures are transferred from PDMS onto an embedded electrode which serves as the back electrical contact for the device. The silicon is transferred by laminating the PDMS onto the electrode surface and slowly peeling the PDMS back. Next, in step (b), planarization followed by the formation of the top metal contacts is performed. The device is completed by integrating a low concentration cylindrical lens array made from PDMS onto the device (step c). In this final step it can be seen that the device was designed such that the rows of silicon cells align with the focal point of the lens array.

[0203] Fig 45 provides images of a silicon solar cell transferred to a glass substrate. (a) Optical image of a single cell on a glass substrate with both top and bottom electrical contacts. (b) Typical I-V response for a device shown in (a) under AM 1.5.

[0204] Fig 46 provides images of a solar cell array joined to cylindrical collecting optics. (a) Picture of the final fully integrated device with cylindrical lens array. (b) Picture of the same device without the incorporation of the lens array.

[0205] Fig 47 provides a schematic diagram for generating optical concentrator arrays with integrated metal contacts onto mS-Silicon solar cells. The process starts off with retrieval of a metal mesh pattern from a substrate (shown dark blue) via a PDMS molded lens array. In some embodiments, the lens array/mesh pattern is laminated in registry onto an array of silicon solar cells.

[0206] Fig 48 describes the process flow for generating solar cells and integrated concentrating optics.

[0207] Fig 49 provides images of a micro solar cell array printed onto gold bus lines on glass substrates via a thin PDMS adhesive layer.

[0208] Fig 50 provides a schematic illustration of microcells of (a) vertical-type, (b) transverse-type, (c) combination of both types.The processing scheme for producing bulk quantities of single crystal Si micro-ribbons from bulk silicon wafers has been recently developed. The approach begins with a controlled deep reactive ion etching process to create well-defined ribbon structures. Subsequent side-wall passivation either from angled electron beam evaporation deposition of metals or from chemical vapor deposition of SiO_2/Si_3N_4 can function as a physical mask for highly anisotropic wet chemical (e.g. KOH) etching. This single-step etching process thus can produce micro-ribbon arrays in printing-ready forms. Both vertical and transverse type pn-junctions are provided by the present invention, which has its own advantages over the other in microcell configurations. Vertical type pn-junctions have been mainly pursued for photovoltaic applications due to its easy processing with bulk wafers and large junction area. On the other hand, transverse type pn-junctions have more choices in terms of transfer methods, usable substrates, and a possibility of back-side illumination (i.e. eliminating shadowing issues due to metal grids), while they may exhibit limited performance on account of their intrinsically small junction area. Another design of the present invention is a combination of vertical and transverse junctions, which may take above-mentioned advantages . All of the junction structures (n^+-p-p^+) can be readily fabricated by selective doping process, in which thermal diffusion of spin-on-dopant is conducted with PECVD-grown SiO_2 doping mask of appropriate thickness and pattern. For vertical type cells, n^+-emitter doping is done first before creating microcell patterns, while back p^+-doping as back-surface-field (BSF) is accomplished after the microcell patterning process, by a transfer of the patterned microcells onto a substrate covered with dopants and a subsequent thermal diffusion. After this BSF doping step, the microcells can be transferred again to any desired substrate. For transverse type cells, process of selective n^+ and p^+ doping is more straightforward than vertical cells, simply by using patterned doping masks repetitively. Microcells are created after finishing these doping processes. For the combination type cells, front side doping is obtained in a similar manner with transverse type cells, while back side doping is implemented by following the procedure of BSF formation in vertical type cells.

[0209] The present invention also includes ILED displays with matrix structure as well as strip-light without a method using PDMS cassette.

Example 4: Electrical Interconnection Strategies for Printed Optical Systems

[0210] The present invention provides methods and systems useful for establishing good electrical connection of semiconductor-based optical systems fabricated by contact printing methods. Processing steps and device geometries of the present invention provide efficient, mechanically robust and highly conductive electrical connection between electronic devices and/or device components assembled via contact printing. The present processing steps and device geometries are compatible with a range of electrical interconnect patterning and processing techniques including photolithographic processing, deposition techniques and/or soft lithographic (e.g., contact printing) patterning.

a. Planarizing Fabrication Strategies and Device Geometries

[0211] In an aspect, the present invention provides planarizing processing steps and planar device geometries that minimizes, or completely avoids, degradation of electronic performance of device electrical interconnects arising from step edges of semiconductor elements, such as semiconductor electronic devices and device components, assembled on a device substrate via contact printing. In the context of this description, "planarizing" refers to a process wherein one or more printable semiconductor elements are integrated with a device substrate such that a surface structure is formed having an exposed surface with a substantially planar geometry. Preferably for some applications, the exposed surface having a substantially planar geometry includes one or more individual surfaces of the printed semiconductor element(s) that can be patterned with device electrical interconnect structures, for example using optical lithography and deposition techniques. A planar geometry generally refers to a surface configuration wherein all points on the surface occupy a common plane. In the context of this description, however, a substantially planar geometry includes some deviation from an absolutely planar configuration. In some embodiments, for example, a substantially planar geometry includes deviations in surface position from an absolutely planar configuration of less than 2 microns, preferably for some embodiments deviations in surface position from an absolutely planar configuration of less than 1 micron, and more preferably for some embodiments deviations in surface position from an absolutely planar configuration of less than 500 nanometers.

[0212] Planarization in the present invention is achieved by providing materials, layers and/or structures adjacent to printed semiconductor elements such that the step edges of these structures are reduced and/or minimized, thereby allowing for effective patterning and integration of electrical interconnection structures. In an embodiment, for example, the space between adjacent printed semiconductor elements is filled with or otherwise occupying by portions of device substrate itself, other materials, layers or structures provided to the device substrate or a combination of these. Planarizing may be achieved in the present invention using a number of processing methods including embedding one or more printable semiconductor elements into a receiving surface of a device substrate or a planarizing layer provided thereon. Alternatively, planarizing in the present invention may be achieved in the present invention may be achieved by assembling printable semiconductor elements on a receiving surface of a device substrate by contact printing and subsequently providing materials or layers adjacent to the printable semiconductor elements, and in some embodiments between adjacent printed semiconductor elements, so reduce or minimize the step edges of the printed structures.

[0213] In an embodiment of this aspect, the present invention provides a method of making a semiconductor-based optical system comprising the steps of: (i) providing a device substrate having a receiving surface; (ii) assembling one or more printable semiconductor elements on the receiving surface of the substrate via contact printing; and (iii) planarizing the printable semiconductor element(s) assembled on the receiving surface, thereby making the semiconductor-based optical system. In an embodiment, the planarizing step generates a substantially planar and/or smooth top surface on the device substrate including the printable semiconductor element(s). In methods useful for device fabrication applications, the substantially planar and/or smooth top surface generates includes exposed surfaces of one or more planarized printable semiconductor elements assembled on the receiving surface. Methods and systems having a planar and/or smooth top surface included exposed surfaces of one or more planarized printable semiconductor elements is beneficial for providing electrical contact to the planarized printable semiconductor elements via additional processing steps, such as lithographic patterning of electrodes/device interconnect structures. In a method of the present invention, the printable semiconductor element comprises a unitary inorganic semiconductor structure. In a method of the present invention, the printable semiconductor element comprises a single crystalline semiconductor material.

[0214] Optionally, a method of the present invention further comprises the step of curing, polymerizing or cross linking the planarizing layer having the printable semiconductor element embedded therein, thereby fixing the printable semiconductor element in the planarizing layer. Planarizing layers of the methods and systems of this aspect of the present invention are also useful for mechanical integrating printable semiconductor elements with a device substrate. Optionally, a method of the present invention further comprising the steps of patterning one or more electrodes/electrical interconnects to one or more exposed surfaces of the planarized printable semiconductor element included in the substantially planar and/or smooth top surface. Patterning electrodes and interconnects can be achieved by means known in the art including, but not limited to, optical lithography, deposition techniques (e.g., CVD, PVD, thermal deposition, sputtering deposition, plasma deposition etc.), soft lithography (e.g., contact printing) and combinations of these. Optionally, a method of the present invention comprising the steps: (i) assembling a plurality of printable semiconductor elements on the receiving surface of the substrate via contact printing; and (ii) planarizing the plurality of printable semiconductor elements assembled on the receiving surface.

[0215] In an embodiment, the planarizing step generates a substantially planar top surface on the device substrate having the printable semiconductor element(s). Preferably for some application the substantially planar top surface comprises an exposed surface of each of the printed semiconductor elements assembled on the receiving surface. Preferably for some embodiments of this aspect, the planarized semiconductor elements assembled on the receiving surface exhibit step edge features that are less than 2 microns, preferably for some applications less than 1 micron and more preferably for some applications less than 500 nanometers. This aspect of the invention is useful for generating structure that can be effective electrically interconnected, for example using lithographic patterning and thin film deposition methods.

[0216] In an embodiment, the planarizing step of this method comprises embedding the printable semiconductor element(s) into the device substrate. Techniques for embedding one or more printable semiconductor elements directly into a device substrate include raising the temperature of a polymer device substrate so as to achieve a physical state (e.g. viscosity) capable of displacement during contact printing. Alternatively, planarizing may be achieved by direct integration of printable

semiconductor elements into prepatterned recessed features in the receiving surface of the receiving substrate.

[0217] In another embodiment, the planarizing step of this method comprises embedding the printable semiconductor element(s) in a planarizing layer provided on the receiving surface of the device substrate. In the context of this description, a planarizing layer refers to a layer of material supported by the receiving substrate such that printed semiconductor elements can be embedded or implanted into the planarizing layer. In some embodiments, planarizing layers comprise materials, such as low viscosity fluids, that are capable of physical displacement or rearrangement so as to accommodate printed semiconductor elements. Optionally, planarizing layers of the present inventon are capable of chemical or physical transformation after receiving printable semiconductor elements to harden, solidify or otherwise change phase or viscosity such that the embedded printed semiconductor elements are held in place. Optionally, the planarizing layer is a prepolymer layer that is polymerized after receiving the printable semiconductor elements. Optionally, the planarizing layer is a polymer layer that is cross linked after receiving the printable semiconductor elements.

[0218] The present invention includes methods wherein the planarizing layer is provided to the receiving surface or structure thereon and subsequently contacted with the printable semiconductor element(s). In this embodiment, the planarizing layer receives the printable semiconductor elements assembled on the receiving surface. Alternatively, the present invention includes methods wherein the planarizing layer is provided to the receiving surface after the step of assembling the printable semiconductor element(s) on the receiving surface. In this embodiment, the planarizing layer is provided so as to fill-in or build up regions of the receiving substrate so as to planarize the printed semiconductor elements.

[0219] Planarizing layers of the present invention may comprise a range of materials including, but not limited to, polymers, prepolymers, composite materials having a polymer component, gels, adhesives and combinations thereof. For some applications, planarizing layers preferably comprise one or more low viscosity materials capable of physical displacement or rearrangement to accommodate and embed printable semiconductor elements. In an embodiment, for example, a planarizing layer comprises a material having a viscosity selected over the range of 1-1000 centipoise. Planarizing layers for some device fabrication applications have a thickness comparable to the

printable semiconductor elements assembled on a receiving surface. In an embodiment, a planarizing layer of the present invention has a thickness selected over the range of 10 nanometers to 10000 microns. In some embodiments, a planarizing layer of the present invention has a thickness similar (e.g., within a factor of 1.5) to that of the printable semiconductor elements assembled on the receiving surface. In an embodiment the thickness of the planarizing layer is selected over the range of 0.0003 mm to 0.3 mm, preferably for some applications selected over the range of 0.002 mm to 0.02 mm

[0220] The present invention also includes optical systems comprising planarized printable semiconductor elements. In an embodiment, a semiconductor-based optical system of the present invention comprises: (i) a device substrate having a receiving surface; and (i) one more planarized printable semiconductor elements supported by the receiving surface; wherein the device substrate having the one or more printable semiconductor elements has the substantially planar top surface that includes at least a portion of the printable semiconductor elements, wherein the printable semiconductor elements comprise a unitary inorganic semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[0221] Optionally, the system of the present invention further comprises a planarizing layer provided on the receiving surface of the device substrate, wherein the printable semiconductor elements are embedded in the planarizing layer. In a system of the present invention, the printable semiconductor elements are printable electronic devices or electronic device components, such as LEDs, solar cells, lasers, sensors, transistors, diodes, p-n junctions, integrated circuits, photovoltaic systems or a component of these.

[0222] Figures 54A and 54B provides schematic diagrams of systems of the present invention comprising planarized printable semiconductor elements. Printable semiconductor elements **5010** are embedded in the device substrate **5000** itself (See Figure 54A) or alternatively in a planarizing layer **5020** (See Figure 54B)provided on a receiving surface of device substrate **5000**. As shown in these Figures 54A and 54B the planarized configuration results in a top exposed surface **5015** having a substantially planar geometry which includes some deviation from an absolute planar configuration. As shown in these figures, top exposed surface **5015** including exposed surfaces of the planarized printable semiconductor elements **5010** in addition to exposed surfaces of substrate **5000** or planarizing layer **5020**. Figure 55 provides a flow diagram illustrating processing steps in methods of the present invention for making semiconductor-based optical systems comprising planarized printable semiconductor elements, such as printable semiconductor-based electronic devices and device components.

[0223] A benefit of using planarized device configurations and planarization methods of the present invention is that it allows good electrical contact with planarized printable semiconductor elements to be established in further processing steps, such as lithographic and deposition processing. Figure 56 provides experimental results characterizing the impact of step edges on establishing electrical contact to and/or between printable semiconductor elements. Experimental result corresponding to printed semiconductor elements comprising silicon bars having step edge dimensions of 290 nm, 700 nm, 1.25microns and 2.5 microns. Inset of Figure 56 shows a micrograph and schematic showing the device and electrical contact geometries. As shown in this figure, good conductivity (e.g., resistance less than 10 ohm) is observed for step edge dimensions up to 1.25 microns. For step edge dimensions equal to 2.5 microns, however, a significant decrease in conductivity (e.g., resistance equal to 1.7 ohm) is observed. Planarizing methods of the present invention, therefore, have significant value in minimizing the magnitude of step edges in assembled printable semiconductor

elements, thereby accessing planarized device geometries capable of effective implementation of device interconnects and electrodes.

[0224] In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having at least one longitudinal physical dimension selected from the range of 0.1 millimeters to 1 millimeter. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having at least one longitudinal physical dimension selected from the range of 1 millimeters to 10 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having at least one cross sectional dimension selected from the range of 0.0003 millimeters to 0.3 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure at least one cross sectional dimension selected from the range of 0.002 millimeters to 0.02 millimeters.

[0225] The system relates, in an aspect, to a plurality of planarized printable semiconductor elements supported by said receiving surface; wherein said device substrate having said printable semiconductor element has said substantially planar top surface that includes at least a portion of said planarized printable semiconductor elements, wherein each of said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

[0226] In an embodiment of this aspect, the system further comprises a planarizing layer provided on said receiving surface of said device substrate, wherein said printable semiconductor element is embedded in said planarizing layer. In an embodiment of this aspect, system further comprises one or more electrodes or electrical interconnects patterned on said substantially planar top surface. In an embodiment of this aspect, said printable semiconductor element is a printable electronic device or electronic device component. In an embodiment of this aspect, the printable semiconductor element is a LED, a solar cell, a laser, a sensor, diode, p-n junction, transistor,

integrated circuit or a component thereof. In an embodiment of this aspect, the printable semiconductor element comprises said semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure. In an embodiment of this aspect, the printable semiconductor element comprises said semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel. In an embodiment of this aspect, the printable semiconductor element has a thickness selected from the range of 100 nanometers to 100 microns.

[0227] The present invention includes other strategies for avoid or mitigating the effect of step edges in establishing electrical connection between to and/or between printable semiconductor elements. In some embodiments, for example, the printable semiconductor elements are fabricate such that they have at least one side having a sloping or otherwise gradually tapering edge. The sloping edge provides a gradual change at the edge of the printable semiconductor element, as opposed to an right angle configuration where the change on the edge of the printable semiconductor element is abrupt. In these embodiments, printable semiconductor elements are assembled such that a side having the sloping edge(s) is exposed upon contact with the receiving surface. This geometry allows access to, and subsequent processing on, the exposed side having the sloping edges for integration of electrical interconnects. The present of the sloping edges of the printable semiconductor elements, therefore, reduces the impact of step edges in integrating electrical interconnection structures and electrodes.

b. Electrical Interconnection Using Mesh and Grid Electrodes

[0228] The present invention also include device geometries and processing methods wherein an electrically conducting mesh or grid electrode is used to electrically interconnect printable semiconductor elements assembled via contact printing. Mesh and grid electrical internconnection elements and/or electrodes are optionally assembled via contact printing methods on a receiving surface of a device substrate, optical systems or optical component or assembled via contact printing methods on exposed surfaces of printed semiconductor elements, optionally using a conformable transfer device. Advantages of the use of mesh and grid electrodes include that fact

that they can be effectively patterned over large areas, thereby, allowing for greater tolerance in the placement accuracy of printable semiconductor elements assembled via contact printing due. This processing and design advantage results in a relaxation of processing constraints and device geometry tolerances involved in contact printing-based assembly of printable semiconductor elements. For example, use of mesh and grid electrodes and device interconnects significantly relaxes design and placement constraints on the alignment and positions of the printable semiconductor elements assembled by contact printing. In addition, use of mesh and grid electrodes allows a large number of printable semiconductor elements to be effectively electrically interconnected in a single (or small number) of processing steps. Further, the thickness and/or fill factor of mesh or grid electrodes can be selected such that they are optically transparent, which allows these components to be implemented in optical systems requiring transmission of electromagnetic radiation through the mesh or grid, such as displays, photovoltaic systems, optical sensing systems and multifunctional optical systems. In some embodiments, the grid or mesh is more than 50% optical transparent at a selected wavelength of electromagnetic radiation.

[0229] In an embodiment, methods of the present invention comprise the step of providing an electrically conducting grid or mesh in electrical contact with at least a portion of the printable semiconductor elements assembled on a receiving surface of a device substrate, thereby establishing electrical contact from the mesh to at least a portion of the printable semiconductor elements. In an embodiment, the electrical connection from the grid or mesh to said printable semiconductor elements is established by contact printing. The grid or mesh provides one or more electrodes or electrical interconnection structures in some of the optical systems of the present invention. The step of providing the grid or mesh in electrical contact with at least a portion of the printable semiconductor elements may be carried out via contact printing-based processing, for example using a conformable transfer device such as an elastomeric (e.g., PDMS) stamp. In some embodiments, for example, this processing step comprises the step of transferring the grid or mesh onto the receiving surface of device substrate via contact printing, and subsequently assembling printable semiconductor elements on one or more surfaces of the printed grid or mesh, thereby establishing electrical connection between these device elements. Alternatively, in another method this processing step comprises the step of transferring via contact printing the grid or mesh onto one or more exposed surfaces of printable semiconductor

elements previously assembled onto the receiving surface of the device substrate, thereby establishing electrical connection between these device elements.

[0230] In another embodiment, the present invention provides a method of making a semiconductor-based optical system comprising the steps of: (i) providing an optical component having an internal surface; (ii) providing a electrically conducting grid or mesh on said internal surface of said optical component; (iii) providing a device substrate having a receiving surface; (iv) assembling a plurality of printable semiconductor elements on said receiving surface of said substrate via contact printing; wherein each of said printable semiconductor elements comprise a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters; and (v) transferring said optical component having said grid or mesh to said device substrate, wherein said optical component is positioned on top of said semiconductor elements assembled on said on said receiving surface of said substrate, wherein said electrically conducting grid or mesh is provided between said optical component and said semiconductor elements, and wherein said metal grid or mesh is provided in electrical contact with at least a portion of said printable semiconductor elements. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[0231] Optionally steps (i) and/or (v) in the method recited above is carried out via contact printing methods, for example using a conformable transfer device such as an

elastomeric stamp. In an embodiment, the electrically conducting mesh or grid comprises one or more metals. In an embodiment, the electrically conducting mesh or grid comprises one or more semiconductor materials. In a method of the present invention, the printable semiconductor element comprises a unitary inorganic semiconductor structure. In a method of the present invention, the printable semiconductor element comprises a single crystalline semiconductor material.

[0232] In some methods, said step of transferring said optical component on top of said semiconductor elements assembled on said on said receiving surface of said substrate comprises printing said optical component on top of said semiconductor elements assembled on said on said receiving surface of said substrate using contact printing. For example, methods of the present invention include the step of assembling the printable semiconductor element said receiving surface via dry transfer contact printing, optionally using a conformable transfer device such as an elastomeric transfer device.

[0233] Mesh or grids useful as electrical interconnect structures and/or electrodes may comprise any conductive material including metals and semiconductors (including doped semiconductors). In some embodiments, mesh or grids useful as electrical interconnect structures and/or electrodes may have a thickness selected over the range of 10 nanometers to 10000 microns. Use of thin and/or low fill factor grid or mesh structures is useful for some embodiments, as these structures can be implemented such that they are optically transparent, for example transmitting greater than 10%, 30% 50% or 70% of incident electromagnetic radiation having a selected wavelength. Fill factors of mesh or grid structures for some applications range between 5% and 80%, preferably between 10-50%. In some embodiments, use of mesh or grid structures having a fill factor less than 30% is preferred.

[0234] Mesh or grid structures useful for electrical interconnect structures and/or electrodes of the present invention may optionally be a laminated, planarized and/or encapsulated structure. In an embodiment, for example, the mesh or grid structure is bonded to an elastomeric layer, such as a PDMS layer, to facilitate handling, transfer and/or integration, for example using contact printing methods, optionally using a conformable transfer device such as an elastomeric stamp. Useful elastomeric layers for some applications have thicknesses ranging from 1 micron to 1000 microns. Use of an elastomeric layer in some embodiments allows the grid or mesh electrode or interconnect structure to deform and move so as to generate good electrical connect

with printed semiconductor elements. In some embodiments, the mesh or grid structure is also coupled to a support, such as glass or polymer substrate. In an embodiment, for example, the mesh or grid structure is mechanically coupled to an elastomeric layer coupled to and a glass or polymer substrate. In some configurations, the elastomer layer is positioned between the mesh or grid structure and the glass or polymer substrate. Use of a support, such as a glass or polymer substrate, facilitates integration of grid or mesh electrode or interconnect structures into optical systems of the present invention.

[0235] Use of grid and mesh electrode and/or electrical interconnection structures is beneficial for establishing electrical connection of a range of printable semiconductor elements. Optionally, the printable semiconductor element in these methods is an electronic device or component of an electronic device, such as an LED, a laser, a solar cell, a sensor, a diode, a transistor, and a photodiode. Optionally, the printable semiconductor element in these methods has a thickness selected from the range of 100 nanometers to 100 microns

[0236] In an embodiment, the present invention provides a semiconductor-based optical system comprising: (i) a device substrate having a receiving surface; (ii) a plurality of printable semiconductor elements supported by said receiving surface; wherein each of said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters; and (iii) a metal grid or mesh provided in electrical contact with said plurality of printable semiconductor elements supported by said receiving surface. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02

millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[0237] Optionally, the printable semiconductor elements are assembled on said receiving surface by contact printing. Optionally, said metal grid or mesh is a laminated structure. Optionally, the metal grid or mesh is bonded to an elastomeric layer, such as a PDMS layer, and in some embodiments the elastomeric layer is bonded to a glass substrate, wherein said elastomeric layer is positioned between said metal grid or mesh and said glass substrate. Optionally, the metal grid or mesh is provided between said receiving surface and said printable semiconductor elements. Optionally, the metal grid or mesh is provided on one or more external surfaces of the printable semiconductor elements. Optionally metal grid or mesh is optically transparent and/or has a fill factor less than 30%. Optionally, the printable semiconductor element(s) comprise a unitary, inorganic semiconductor structure.

[0238] In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having at least one longitudinal physical dimension selected from the range of 0.1 millimeters to 1 millimeter. In a system of this aspect, the printable semiconductor element(s) comprise a semiconductor structure having at least one longitudinal physical dimension selected from the range of 1 millimeters to 10 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure having at least one cross sectional dimension selected from the range of 0.0003 millimeters to 0.3 millimeters. In a system of this aspect, the printable semiconductor element(s) comprises a semiconductor structure at least one cross sectional dimension selected from the range of 0.002 millimeters to 0.02 millimeters. In a system of this aspect, the printable semiconductor elements are assembled on the receiving surface by contact printing. In a system of this aspect, the grid or mesh comprises one or more metals. In a system of this aspect, the grid or mesh is a laminated structure. In a system of this aspect, the grid or mesh is bonded to an elastomeric layer, and optionally elastomeric layer is bonded to a glass substrate, wherein the elastomeric layer is positioned between the grid or mesh and the glass

substrate, and optionally the grid or mesh is provided between the receiving surface and the printable semiconductor elements. In a system of this aspect, the grid or mesh is provided on external surfaces of the printable semiconductor elements. In a system of this aspect, the grid or mesh is more than 50% optically transparent. In a system of this aspect, the grid or mesh has a fill factor less than 30%.

c. Electrode interconnect geometries for printable semiconductor elements

[0239] The present invention also include electrode interconnect geometries for printable semiconductor elements, such as printable semiconductor devices and device components, that facilitate electrode patterning and electrical interconnection as assembly via contact printing. These interconnect geometries are applicable to a range of printable electronic devices and components thereof, including solar cells, LEDs, transistors, diodes, lasers and sensors.

[0240] In an embodiment, a printable semiconductor element of the present invention has a device geometry such that the contact structures, such as contact pads or other electrical interconnection structures, for making electrical connection are provided on a single side of the printable semiconductor element. Preferably for some device fabrication applications, the side of the printable semiconductor element that has the electrical contacts is exposed or otherwise accessible upon the step of assembling the printable semiconductor element on a device substrate, optical system or optical component. This design is particularly attractive for printable semiconductor elements comprising electronic devices require two or more electrical contacts to different components of the device such as a solar cell, LED or transistor. In printable semiconductor devices and device components of this aspect, the device geometry is selected to allow two or more electrical interconnects to be provided on a single side of the printable semiconductor device and device component. In some embodiments, for example, the doping and doped components of a printable semiconductor devices and device components is selected and or spatially arranged to allow electrical interconnects to be provided on a single side of the printable semiconductor device and device component.

Example 5: Contact printing based assembly on optical components.

[0241] An advantage of the contact printing-based processing methods of the present invention is that they are compatible with device assembly and integration directly on a

range of optical systems and optical components thereof. This allows for a range of useful structures and device geometries to be efficiently accessed using the present fabrication methods.

[0242] In an embodiment of this aspect, the present invention provides a method of making a semiconductor-based optical system comprising the steps of: (i) providing an optical system or optical component having a receiving surface; and (ii) assembling one or more printable semiconductor elements on said receiving surface of said optical system or optical component via contact printing; wherein each of said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters, preferably for some applications a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter, preferably for some applications a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters, preferably for some applications a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an embodiment, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 100 nanometers to 1000 microns, a width selected from the range of 100 nanometers to 1000 microns and a thickness selected from the range of 10 nanometers to 1000 microns.

[0243] In some embodiments, the printable semiconductor elements are assembled on a contoured receiving surface of said optical component, such as the curved surface(s) of a lens, lens array, waveguide or array of waveguides. Alternatively, the printable semiconductor elements are assembled are assembled on a planar receiving surface(s) of said optical component.

[0244] The contact printing based fabrication platform of the present methods is highly versatile and, hence compatible with a range of optical components including light

collecting optical components, light concentrating optical components, light diffusing optical components, light dispersing optical components, light filtering optical components and arrays thereof. In an embodiment, for example, printable semiconductor elements, such as printable semiconductor based electronic devices and/or device components, are assemble on a receiving surface of an optical systems or component selected from the group consisting of a lens, a lens array, a reflector, an array of reflectors, a waveguide, an array of waveguides, an optical coating, an array of optical coatings, an optical filter, an array of optical filters, a fiber optic element and an array of fiber optic elements. In an embodiment, printable semiconductor elements are assembled on an optical component or system fabricated by replica molding, such as a lens or lens array fabricated by replica molding. In an embodiment, printable semiconductor elements are assembled on a PDMS molded optical structure, such as such as a PDMS molded lens or lens array.

[0245] Printing based assembly allows the assembled printable semiconductor elements to accurately and/or precisely spatially aligned and/or individually addressed to features and parts of an optical system or optical component. In an embodiment, for example, contact printing allows each of the components in an array of optical components to be spatially aligned with respect to at least one of said printable semiconductor elements, for example aligned to within 100 microns or preferably to within 10 microns. In an embodiment, for example, contact printing allows each of the components in an array of optical components to be individually addressed to at least one of said printable semiconductor elements.

[0246] Direct contact printing onto surfaces of optical systems and components enables fabrication of range of systems including display systems, photovoltaic systems, sensors, and multifunctional optical systems. The type and functionality of the optical system generated will depend at least in part on the type of printable element printed and the type of optical system or component that receives the printable semiconductor elements. In some embodiments, the printable semiconductor element assembled on the surface of optical systems and components are electronic devices or components of electronic devices, such as LEDs, lasers, solar cells, sensors, diodes, transistors, and photodiodes. In some embodiments, the printable semiconductor element assembled on the surface of optical systems and components have thicknesses selected from the range of 100 nanometers to 100 microns.

[0247] Use of contact printing in the present invention provides the capable of direct integration of printable semiconductor elements with a range of optical systems. In an embodiment, for example, printable semiconductor elements are assembled on said receiving surface of an optical system or optical component via dry transfer contact printing. Optionally, printable semiconductor elements are assembled on said receiving surface of an optical system or optical component using a conformable transfer device, such as an elastomeric transfer device (e.g., PDMS stamp). In a method of this aspect of the present comprises the steps of: (i) providing said conformable transfer device having a contact surface; (ii) establishing conformal contact between an external surface of said printable semiconductor element and said contact surface of said conformable transfer device, wherein said conformal contact bonds said printable semiconductor element to said contact surface; (iii) contacting said printable semiconductor element bonded to said contact surface and said receiving surface of said optical component; and (iv) separating said printable semiconductor element and said contact surface of said conformable transfer device, thereby assembling said printable semiconductor element on said receiving surface of said optical component.

Example 6: Fabrication of solar cell arrays via contact printing

[0248] The present methods provide an effective processing platform for the fabrication of high performance photovoltaic systems including solar cell arrays.

[0249] Figure 57 provides a process flow diagram for making printable semiconductor elements comprising vertical solar cells that can be subsequently assembled and interconnected to fabricate a solar cell array. Steps A – E in figure 57 demonstrate various processes and conditions for making printable solar cell ribbons from a Si (111) p-type wafer.

[0250] Process step A in figure 57 demonstrates processing steps and conditions for the back surface field formation. In this processing step, a 3 inch p-type Si 111 wafer is cleaved into 6 equal parts. Next, the processed wafer is cleaned using Ace/IPA and Piranha clean. Boron (B219) SOD is spun on and the wafer. The wafer with boron is annealed at 250 °C. The boron is driven in, for example, at 1150 °C for 45 mins. Any glass residue is removed. These processing steps result a junction that is about 1.5 mm thick.

[0251] Process steps B and C in Figure 57 demonstrate processing steps and conditions for ribbon formation. A 300 nm PECVD oxide is use to make the resist pattern. The PR is patterned to define the ribbon spatial dimensions and wet etch exposed oxide with BOE. Then, ICP-DRIE ~ 25- 30 mm is used to generate deep trenches (12 min etch time) into the exposed silicon. Exemplary ribbon dimensions and trench dimensions are shown in Figure 57. The processed wafer is cleaned in RCA 1 and KOH refining for about 4 mins to remove some of the sidewall roughness. Next, PECVD 100 nm SiO_2 and 600 nm Si_3N_4 is deposited everywhere. Angled evaporation (60 degree stage) of Ti / Au 3 / 50 nm is used in this processing step. The wafer is exposed to RIE etching of the exposed oxide and nitride layers. Wet etching using KOH is next used to undercut the ribbons, for example, using a ~ 35 % KOH solution. The metal mask layers are subsequently removed. The oxide and nitride layers are maintained for subsequent doping processing.

[0252] Process steps D and E in Figure 57 demonstrate processing steps and conditions for emitter formation. In an embodiment, a n-type dopant, such as P509, is spin coated onto the fully undercut ribbon chip. The n-type dopant (e.g., P509) is driven, for example, at 950 °C for 15 mins. This creates a Junction that is about 500 nm thick. Next, the layers are removed and transfer printed onto receiving substrates with meshes or NOA.

[0253] Figure 58 provides SEM images of microsolar cells of different thicknesses fabricated from bulk wafers. (Top to bottom: 8 microns, 16 microns, 22 microns thick).

[0254] Figure 59 provides a plot showing IV characteristics of an individual solar cell device fabricated using the present processing platform. This example device shows efficiency of 9%. The inset to Figure 59 shows the Si solar cells with a vertical geometry printed onto a bottom bus electrode.

[0255] Figure 60 shows processing for generating top contacts for the vertical solar cells and related electronic performance data. First, the vertical solar cells are printed onto a Au or Cu mesh structure as shown in panels A and B. Next, a second Au mesh is printed (laminated) on top of the cells and serves as the top contact. Panel C shows a plot of the IV curve of printed contacts, modules fabricated in this way show total efficiency of 6%. The Inset in panel C shows the top and bottom printed mesh electrodes onto the silicon solar cells.

[0256] Figure 61 provides a schematic showing a solar cell layout of transverse type solar cells to be patterned on a <111> p-type Si wafer and capable of subsequent assembly and integration via contact printing. The physical dimensions of solar cell ribbons, bridge elements, trenches and a mother wafer are provided in Figure 61. After the patterning of cell layout via photolithography and dry etching process, doping process is conducted. Figure 62 provides a schematic showing the doping scheme wherein boron (P+) and phosphorous (n+) doped regions are patterned on the external surface of the patterned semiconductor ribbons. The top boron doping is for making top p+ contact while the top phosphorous doping for making pn junctions. The sidewall doping strategy is implemented purposefully to increase a junction area and to prevent possible short-circuit formation during the metallization step. The bottom p+ doping is done for creating back-surface-field (BSF) after undercut of bottom surface with KOH etching process.

[0257] Figure 63 provides an overview schematic showing the process flow for cell patterning and doping steps. As shown in Figure 63, first the solar cell patterns are formed on the wafer using photolithography and dry etching. Next, spatially localized boron doping is carried out for window formation and diffusion. Next, spatially localized phosphor doping is carried out for window formation and diffusion. Next the patterned solar cells are undercut employing top and side wall passivation and KOH etching. Finally, bottom boron doping is carried out.

[0258] Figure 64 provides a schematic diagram showing processing steps for patterning solar cell ribbons illustrating photolithography and STS deep RIE etching process steps. As shown in this figure, the first step in the process flow is to make cell patterns through photolithography and deep reactive ion etching (Bosch process) on bulk <111> Si wafer. As an etching mask, PECVD SiO_2 and positive photoresist are used. In the dry etching, SF_6 and O_2 are used for etching and C_4H_8 for passivation. As a result of alternating etching and passivation processes in Bosch process, the etched structure has sidewall ripples, which are smoothen out subsequently with KOH. Also shown in Figure 64 are micrographs of process wafer after removal of photoresist and SiO_2 masking layers. Figure 65 shows results from KOH refining processing of the sidewalls of the patterned ribbons. To remove the sidewall ripples, a short time KOH refining process is conducted. During the process, the top surface is protected with PECVD SiO_2.

[0259] Figure 66 provides a schematic diagram for boron doping processing. After the KOH refining step, boron doping for formation of top p+ contact is conducted. PECVD SiO_2 (900 nm) is deposited as a doping mask layer and a doping window is created by photolithography and BOE wet etching. As a doping agent, either spin-on-dopant or solid state doping source can be used. The diffusion process is conducted at 1000-1150°C under nitrogen (solid state source) or nitrogen/oxygen (75/25, spin-on-dopant) atmosphere. Also shown in Figure 66 is a micrograph of the masked ribbon structures having a doping window for localized boron doping. Also shown in Figure 66 is a plot of current versus voltage indicating a 400 ohm resistance.

[0260] Figure 67 provides a schematic diagram for phosphorous doping processing. Phosphorous doping is followed after the boron doping in order to create a shallow junction (100-300 nm). In a similar way to boron doping process, phosphorous doping window is made with PECVD SiO_2 deposition, photolithography, and BOE wet-etching process. As a doping source, spin-on-dopant is used and applied by spin-coating. The diffusion is conducted at 950C under N_2/O_2 (75/25) atmosphere. Also shown in Figure 67 is a micrograph of the masked ribbon structures for localized phosphorous doping. Also shown in Figure 67 is a plot of current versus voltage indicating a 80 ohm resistance.

[0261] Figure 68 provides a schematic diagram showing sidewall passivation processing. After top doping processes are finished, PECVD Si_3N_4 is deposited as a protecting layer in KOH undercut process. To make an etching window where KOH etching starts, first, Cr and Au are deposited with a 60° angle from the sample surface, in order to make metal protecting layers on top and sidewalls except the bottom surface. The metal cover surface is protected from subsequent dry etch processing, and thus functions as a passivation layer for the KOH wet-etching step. The thickness of the cells can be readily controlled by adjusting metal deposition angle. Secondly, RIE with CHF3/O2 and SF6 will expose Si at the bottom surface, where KOH etching can be initiated. Figure 69 provides a schematic diagram showing processing for the formation of a KOH etching window.

[0262] Figure 70 provides micrographs showing KOH etching processing and bottom boron doping processing. As shown in this figure, the bottom surface is etched with KOH at 90C for 30 min, which results in print-ready cell structure capable of assembly via contact printing, for example using an elastomeric conformable transfer device. After

the KOH etching, only the bottom Si surface is exposed and the Si3N4 protecting layer can be still used as a barrier for boron doping. Boron doping is conducted at 1000C for 10 min subsequently.

[0263] After the bottom boron doping, passivation layers and remaining dopants are cleaned out with HF, Piranha, and BOE. Before the PDMS pick-up, PECVD SiO2 can be deposited as a top-surface passivation from NOA contamination. Figure 71 provides images showing transfer of the solar cell ribbons from the source wafer using a PDMS transfer device.

[0264] Figure 72 provides a schematic diagram illustrating contact printing and planarization processing steps. Also shown in figure 72 are images of print assembled solar cells. After microcells are picked up by PDMS stamp, they are printed onto receiving substrates such as glass, PET, or Kapton using NOA as an adhesive. This printing technique by itself also completes the planarization of cells, which are important to make metal interconnections. First, NOA61 is coated onto a UVO treated substrate, then microcells on PDMS are placed on top of the NOA. Due to the weight of the stamp and cells, the microcells are fully embedded in the NOA except the top surface where PDMS stamp is covered. After the partial curing under UV light, the PDMS stamp can be retrieved and the microcells are embedded and form a planar surface for following metallization steps.

[0265] Figure 73 provides an imaging showing the results of metallization processing. Figure 74 provides a schematic diagram of the metallization process showing an Al metal layer, SiO_2 dielectric layer, Cr/Au layer, solar cell, planarizing layer and device substrate. As shown in Figure 73, to form metal interconnects, metals are deposited on the entire cell surface and selective areas are etched back with metal etchant using a photoresist or NOA as a etching protecting layer. After the metallization is implemented, those metal lines are isolated and encapsulated with SiO_2 and Al is deposited over the surface to form a reflective layer. In this way, we can essentially eliminate the metal shadowing, which normally happens with conventional cell geometry. Anti-reflection coating can be further added either the bottom surface of the substrate or at the bottom of the cells before the transfer. With this cell configuration and printing strategy, we can also use the roughness of the bottom cell surface from KOH etching step as a surface texturization.

Example 7: Physical dimensions of printable semiconductor elements

[0266] The methods and systems of the present invention are capable of implementation with printable semiconductor elements, including printable semiconductor based devices and device components, having a wide range of physical dimensions and shapes. The versatility of the present invention with respect to the physical dimensions and shapes of printable semiconductor elements assembled via contact printing enables a wide range of device fabrication applications and accesses a wide range of electronic, optical, opto-electronic device configurations and layouts.

[0267] Figures 75A and 75B provide schematic diagrams exemplifying the expressions "lateral dimensions" and "cross sectional dimensions" as used in the present description. Figure 75A provides a top plan view of printable semiconductor elements comprising 4 semiconductor ribbons **6005**. In the context of this description the expression "lateral dimension" is exemplified by the length **6000** and width **6010** of the semiconductor ribbons **6005**. Figure 75B provides a cross sectional view of the printable semiconductor elements comprising 4 semiconductor ribbons **6005**. In the context of this description the expression "cross sectional dimension" is exemplified by the thickness **6015** of the semiconductor ribbons **6005**.

[0268] In some embodiments, one or more of the lateral dimensions, such as lengths and widths, of the printable semiconductor elements, including printable semiconductor based devices and device components, are selected over the range of 0.1 mm to 10 mm. One or more of the lateral dimensions are selected over the range of 0.1 mm to 1 mm for some applications, and selected over the range of 1 mm to 10 mm for some applications. Use of printable semiconductor elements having these lateral dimensions include, but are not limited to, membrane solar cells and photovoltaic systems thereof.

[0269] In some embodiments, one or more of the lateral dimensions, such as lengths and widths, of the printable semiconductor elements, including printable semiconductor based devices and device components, are selected over the range of 0.02 mm to 30 mm. Use of printable semiconductor elements having these lateral dimensions include, but are not limited to, optoelectronic semiconductor elements and systems thereof.

[0270] In some embodiments, one or more of the lateral dimensions, such as lengths and widths, of the printable semiconductor elements, including printable semiconductor based devices and device components, are selected over the range of 0.0001 mm to

1000 mm. One or more of the lateral dimensions, such as lengths and widths, are preferably selected over the range of 0.0001 mm to 300 mm for some applications

[0271] In some embodiments, one or more of the cross sectional dimensions, such as thicknesses, of the printable semiconductor elements, including printable semiconductor based devices and device components, are selected over the range of 0.002 mm to 0.02 mm. One or more of the cross sectional dimensions, such as thicknesses, of the printable semiconductor elements, including printable semiconductor based devices and device components are selected over the range of 0.0003 mm to 0.3 mm for some applications. One or more of the cross sectional dimensions, such as thicknesses, of the printable semiconductor elements, including printable semiconductor based devices and device components are selected over the range of 0.00001 mm to 3 mm for some applications.

[0272] In an optical system of the present invention, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters. In an optical system of the present invention, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter. In an optical system of the present invention, the printable semiconductor element comprises a semiconductor structure having a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters. In an optical system of the present invention, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters. In an optical system of the present invention, the printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.002 millimeters to 0.02 millimeters. In an optical system of the present invention, the printable semiconductor element has at least one longitudinal physical dimension less than or equal to 200 microns. In an optical system of the present invention, the printable semiconductor element has at least one cross-sectional physical dimension selected over the range of 10 nanometers to 10 microns.

[0273] The present invention includes optical system comprising a plurality of printable semiconductor elements, such as printable electronic devices or device components,

assembled via contact printing. In embodiment present invention, for example, the optical system further comprises a plurality of printable semiconductor elements on said receiving surface of said substrate via contact printing; wherein each of said printable semiconductor elements comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

Example 8: Printable GaAs/InGaAlP red LEDs printed on PET substrates

[0274] Figure 76 shows an array of printable GaAs/InGaAlP red LEDs printed on PET substrates. To form the device, PET substrates are coated with a thin (1-2 micron) layer of PDMS, the PDMS is cured thermally, and an array of sparse gold meshes is printed onto the substrate via contact printing. 1 mm x 1 mm x ~0.3 mm LEDs are then contact printed onto the mesh electrodes. After printing the LEDs, a thin PDMS substrate housing another array of meshes is laminated against the substrate to form electrical contact to the top of the LEDs and allow operation at ~5 V (top left and right). The thin PDMS substrate also serves as mechanical encapsulation of the LED array

STATEMENTS REGARDING INCORPORATION BY REFERENCE AND VARIATIONS

[0275] U.S. Patent Application Nos. 11/115,954, 11/145,574, 11/145,542, 60/863,248, 11/465,317, 11/423,287, 11/423,192, and 11/421,654 are hereby incorporated by reference to the extent not inconsistent with the present description.

[0276] All references throughout this application, for example patent documents including issued or granted patents or equivalents; patent application publications; and non-patent literature documents or other source material; are hereby incorporated by reference herein in their entireties, as though individually incorporated by reference, to the extent each reference is at least partially not inconsistent with the disclosure in this application (for example, a reference that is partially inconsistent is incorporated by reference except for the partially inconsistent portion of the reference).

[0277] The terms and expressions which have been employed herein are used as terms of description and not of limitation, and there is no intention in the use of such

terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the invention claimed. Thus, it should be understood that although the present invention has been specifically disclosed by preferred embodiments, exemplary embodiments and optional features, modification and variation of the concepts herein disclosed may be resorted to by those skilled in the art, and that such modifications and variations are considered to be within the scope of this invention as defined by the appended claims. The specific embodiments provided herein are examples of useful embodiments of the present invention and it will be apparent to one skilled in the art that the present invention may be carried out using a large number of variations of the devices, device components, methods steps set forth in the present description. As will be obvious to one of skill in the art, methods and devices useful for the present methods can include a large number of optional composition and processing elements and steps.

[0278] Every formulation or combination of components described or exemplified herein can be used to practice the invention, unless otherwise stated.

[0279] Whenever a range is given in the specification, for example, a temperature range, a time range, or a composition or concentration range, all intermediate ranges and subranges, as well as all individual values included in the ranges given are intended to be included in the disclosure. It will be understood that any subranges or individual values in a range or subrange that are included in the description herein can be excluded from the claims herein.

[0280] All patents and publications mentioned in the specification are indicative of the levels of skill of those skilled in the art to which the invention pertains. References cited herein are incorporated by reference herein in their entirety to indicate the state of the art as of their publication or filing date and it is intended that this information can be employed herein, if needed, to exclude specific embodiments that are in the prior art. For example, when composition of matter are claimed, it should be understood that compounds known and available in the art prior to Applicant's invention, including compounds for which an enabling disclosure is provided in the references cited herein, are not intended to be included in the composition of matter claims herein.

[0281] As used herein, "comprising" is synonymous with "including," "containing," or "characterized by," and is inclusive or open-ended and does not exclude additional,

unrecited elements or method steps. As used herein, "consisting of" excludes any element, step, or ingredient not specified in the claim element. As used herein, "consisting essentially of" does not exclude materials or steps that do not materially affect the basic and novel characteristics of the claim. In each instance herein any of the terms "comprising", "consisting essentially of" and "consisting of" may be replaced with either of the other two terms. The invention illustratively described herein suitably may be practiced in the absence of any element or elements, limitation or limitations which is not specifically disclosed herein.

[0282] One of ordinary skill in the art will appreciate that starting materials, biological materials, reagents, synthetic methods, purification methods, analytical methods, assay methods, and biological methods other than those specifically exemplified can be employed in the practice of the invention without resort to undue experimentation. All art-known functional equivalents, of any such materials and methods are intended to be included in this invention. The terms and expressions which have been employed are used as terms of description and not of limitation, and there is no intention that in the use of such terms and expressions of excluding any equivalents of the features shown and described or portions thereof, but it is recognized that various modifications are possible within the scope of the invention claimed. Thus, it should be understood that although the present invention has been specifically disclosed by preferred embodiments and optional features, modification and variation of the concepts herein disclosed may be resorted to by those skilled in the art, and that such modifications and variations are considered to be within the scope of this invention as defined by the appended claims.

WE CLAIM:

1. A method of making a semiconductor-based optical system, said method comprising the steps of:

providing a device substrate having a receiving surface; and

assembling a printable semiconductor element on said receiving surface of said substrate via contact printing; wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

2. The method of claim 1 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters.

3. The method of claim 1 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter.

4. The method of claim 1 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters.

5. The method of claim 1 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters.

6. The method of claim 1 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.002 millimeters to 0.02 millimeters.

7. The method of claim 1 comprising assembling a plurality of printable semiconductor elements on said receiving surface of said substrate via contact printing; wherein each of said printable semiconductor elements comprise a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

8. The method of claim 1 further comprising the step of prepatterning said receiving surface of said device substrate with one or more device components.

9 The method of claim 1 further comprising providing one or more optical components in optical communication with said printable semiconductor element.

10. The method of claim 7 further comprising the step of providing an array of optical components selected from the group consisting of diffusing optics, dispersive optics, collecting optics, concentrating optics, and optical fiber, wherein said array of optical components is provided in optical communication with at least a portion of said printable semiconductor elements.

11. The method of claim 10 wherein an optical component of said array is individually addressed to each of said printable semiconductor elements.

12. The method of claim 10 wherein said array of optical components is fabricated via replica molding; wherein said printable semiconductor elements are assembled on a receiving surface of said array of optical components via contact printing.

13. The method of claim 1 further comprising patterning first and second electrodes in electrical contact with an exposed surface of said printable semiconductor element.

14. The method of claim 1 wherein said printable semiconductor element is assembled on said receiving surface via dry transfer contact printing.

15. The method of claim 1 wherein said printable semiconductor element is assembled on said receiving surface using a conformable transfer device.

16. The method of claim 15 wherein said assembling step comprises:
providing said conformable transfer device having a contact surface;

establishing conformal contact between an external surface of said printable semiconductor element and said contact surface of said conformable transfer device, wherein said conformal contact bonds said printable semiconductor element to said contact surface;

contacting said printable semiconductor element bonded to said contact surface and said receiving surface of said device substrate; and

separating said printable semiconductor element and said contact surface of said conformable transfer device, thereby assembling said printable semiconductor element on said receiving surface of said device substrate.

17. The method of claim 1 wherein said printable semiconductor element is assembled on said receiving surface using an elastomeric transfer device.

18. The method of claim 1 wherein said printable semiconductor element is assembled on said receiving surface using an elastomeric stamp.

19. The method of claim 1 wherein said printable semiconductor element is an electronic device or component of an electronic device.

20. The method of claim 1 wherein said printable semiconductor element is an electronic device selected from the group consisting of: an LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, and a photodiode.

21. The method of claim 1 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure.

22. The method of claim 1 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel.

23. The method of claim 7 wherein said printable semiconductor elements include at least two electronic devices selected from the group consisting of: an LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, and a photodiode.

24. The method of claim 1 wherein said printable semiconductor element has a thickness selected from the range of 100 nanometers to 100 microns

25. The method of claim 1 further comprising the steps of: providing an adhesive layer on said receiving surface; and contacting said printable semiconductor element with said adhesive layer, thereby bonding said printable semiconductor element to said receiving surface of said substrate.

26. The method of claim 25 wherein said adhesive layer is one or more polymer layers, prepolymer layers, elastomer layers, metal layers, or a combination thereof.

27. The method of claim 1 further comprising the step of providing a laminating or encapsulating layer in contact with said printable semiconductor element; said laminating or encapsulating layer capable of at least partially encapsulating or laminating said printable semiconductor element assembled on said receiving surface.

28. The method of claim 7 wherein said printable semiconductor elements are assembled over an area of said receiving substrate selected over the range of 10000 microns^2 to 1 meter^2.

29. The method of claim 7 wherein said printable semiconductor elements are assembled on said receiving surface of said substrate with a density equal to or greater than 5 semiconductor elements mm^{-1}.

30 The method of claim 1 wherein said printable semiconductor element has at least one longitudinal physical dimension less than or equal to 200 microns.

31. The method of claim 1 wherein said printable semiconductor element has a cross-sectional physical dimension selected over the range of 10 nanometers to 10 microns.

32. The method of claim 7 wherein the positions of said printable semiconductor elements assembled on said receiving surface relative to each other are selected to within 10,000 nanometers.

33. The method of claim 7 wherein said printable semiconductor elements on said receiving surface are longitudinally aligned with respect to each other; wherein said longitudinally aligned semiconductor elements extend lengths that are parallel to within 3 degrees of each other.

34. The method of claim 1 wherein said optical system is selected from the group consisting of: a array of light emitting diodes, an array of lasers, an array of VCSELs, a passive matrix LED display, an active matrix LED display, an optical sensor and an array of optical sensors; a sheet scanner and an array of solar cells.

35. The method of claim 1 wherein said printable semiconductor element comprises a unitary inorganic semiconductor structure.

36. The method of claim 1 wherein said printable semiconductor element comprises a single crystalline semiconductor material.

37. The method of claim 7 further comprising the step of providing a electrically conducting grid or mesh in electrical contact with at least a portion of said printable semiconductor elements, said grid or mesh providing one or more electrodes or electrical interconnection structures in said optical system.

38. The method of claim 37 wherein said mesh or grid comprise one or more metals.

39. The method of claim 37 wherein said electrically conducting grid or mesh is more than 50% optically transparent.

40. The method of claim 37 wherein said electrically conducting grid or mesh is a laminated structure.

41. The method of claim 37 wherein said electrically conducting grid or mesh is bonded to an elastomer layer.

42. The method of claim 37 further comprising the step of assembling said grid or mesh on the receiving surface of said device substrate or on external surfaces surface of at least a portion of said printable semiconductor elements, thereby establishing electrical contact between said grid or mesh and said at least a portion of said printable semiconductor elements.

43. The method of claim 42 wherein electrical connection from said metal grid or mesh to said printable semiconductor elements is established by assembling said grid or mesh on the receiving surface of said device substrate or on external surfaces surface of at least a portion of said printable semiconductor elements by contact printing.

44. A method of making a semiconductor-based optical system, said method comprising the steps of:
providing an optical component having an internal surface;

providing an electrically conducting grid or mesh on said internal surface of said optical component;

providing a device substrate having a receiving surface;

assembling a plurality of printable semiconductor elements on said receiving surface of said substrate via contact printing; wherein each of said printable semiconductor elements comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters; and

transferring said optical component having said grid or mesh to said device substrate, wherein said optical component is positioned on top of said semiconductor elements assembled on said on said receiving surface of said substrate, wherein said grid or mesh is provided between said optical component and said semiconductor elements, and wherein said grid or mesh is provided in electrical contact with at least a portion of said printable semiconductor elements.

45. The method of claim 44 wherein each of said printable semiconductor elements comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters.

46. The method of claim 44 wherein each of said printable semiconductor elements comprises a semiconductor structure having a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter.

47. The method of claim 44 wherein each of said printable semiconductor elements comprises a semiconductor structure having a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters.

48. The method of claim 44 wherein each of said printable semiconductor elements comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters.

49. The method of claim 44 wherein each of said printable semiconductor elements comprises a semiconductor structure having a thickness selected from the range of 0.002 millimeters to 0.02 millimeters.

50. The method of claim 44 wherein said mesh or grid comprise one or more metals.

51. The method of claim 44 wherein said grid or mesh is more than 50% optically transparent.

52. The method of claim 44 wherein said grid or mesh is a laminated structure.

53. The method of claim 44 wherein said grid or mesh is bonded to an elastomer layer.

54. The method of claim 53 wherein said elastomer layer is coupled to a glass substrate, wherein said elastomer layer is position between said grid or mesh and said glass substrate.

55. The method of claim 44 wherein said grid or mesh has a fill factor less than 30%.

56. The method of claim 44 wherein said step of transferring said optical component on top of said semiconductor elements assembled on said on said receiving surface of said substrate comprises assembling said optical component on top of said semiconductor elements assembled on said on said receiving surface of said substrate using contact printing.

57. The method of claim 44 wherein said grid or mesh is assembled on said internal surface of said optical component via contact printing.

58. The method of claim 44 wherein said grid or mesh is assembled on said internal surface of said optical component using a conformable transfer device.

59. The method of claim 44 wherein said grid or mesh is assembled on said internal surface of said optical component using an elastomeric transfer device.

60. The method of claim 44 wherein said printable semiconductor elements are assembled on said receiving surface using dry transfer contact printing.

61. The method of claim 44 wherein said optical component is a light collecting optical component, a light concentrating optical component, a light diffusing optical component, a dispersing optical component or a light filtering optical component.

62. The method of claim 44 wherein said optical component is a lens or lens array.

63. The method of claim 44 wherein said optical component is a PDMS molded lens or a PDMS molded lens array.

64. The method of claim 44 wherein said printable semiconductor elements are an electronic device or component of an electronic device.

65. The method of claim 44 wherein said printable semiconductor element are one or more electronic device selected from the group consisting of: an LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, and a photodiode.

66. The method of claim 44 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure.

67. The method of claim 44 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel.

68. The method of claim 44 wherein said printable semiconductor element has a thickness selected from the range of 100 nanometers to 100 microns.

69. A method of making a semiconductor-based optical system, said method comprising the steps of:

providing a device substrate having a receiving surface;

assembling a printable semiconductor element on said receiving surface of said substrate via contact printing; and

planarizing said printable semiconductor element assembled on said receiving surface, thereby making said semiconductor-based optical system.

70. The method of claim 69 wherein said planarizing step comprises embedding said printable semiconductor element into said device substrate.

71. The method of claim 69 further comprising the step of providing a planarizing layer on said receiving surface of said substrate, wherein said planarizing step comprises embedding said printable semiconductor element in said planarizing layer provided on said receiving surface of said device substrate.

72. The method of claim 71 wherein said planarizing layer is provided to said receiving surface prior to said step of assembling said printable semiconductor element on said receiving surface.

73. The method of claim 71 wherein said planarizing layer is provided to said receiving surface after said step of assembling said printable semiconductor element on said receiving surface.

74. The method of claim 71 wherein said planarizing layer has a thickness selected from the range of 10 nanometers to 1000 microns.

75. The method of claim 71 wherein said planarizing layer comprises a prepolymer or a polymer.

76. The method of claim 71 further comprising the step of curing, polymerizing or cross linking said planarizing layer having said printable semiconductor element embedded therein, thereby fixing said printable semiconductor element in said planarizing layer.

77. The method of claim 69 wherein said planarizing step generates a substantially planar top surface on said device substrate having said printable semiconductor element.

78. The method of claim 77 further comprising the steps of patterning one or more electrical interconnects to an exposed surface of said planarized printable semiconductor element of said substantially planar top surface.

79. The method of claim 69 wherein said printable semiconductor element is a printable electronic device or electronic device component.

80. The method of claim 69 wherein said printable semiconductor element is an LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, or a photodiode.

81. The method of claim 69 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure.

82. The method of claim 69 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel.

83. The method of claim 69 wherein said printable semiconductor element has a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

84. The method of claim 69 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters.

85. The method of claim 69 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter.

86. The method of claim 69 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters.

87. The method of claim 69 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters.

88. The method of claim 69 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.002 millimeters to 0.02 millimeters.

89. The method of claim 69 comprising the steps:
assembling a plurality of printable semiconductor elements on said receiving surface of said substrate via contact printing; and

planarizing said plurality of printable semiconductor elements assembled on said receiving surface.

90. The method of claim 89 wherein said plurality of printable semiconductor elements comprises one or more electronic devices selected from the group consisting of: a LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, and a photodiode.

91. A method of making a semiconductor-based optical system, said method comprising the steps of:

providing an optical component having a receiving surface; and

assembling a printable semiconductor element on said receiving surface of said optical component via contact printing; wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

92. The method of claim 91 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.02 millimeters to 30 millimeters, and a width selected from the range of 0.02 millimeters to 30 millimeters.

93. The method of claim 91wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.1 millimeters to 1 millimeter, and a width selected from the range of 0.1 millimeters to 1 millimeter.

94. The method of claim 91 wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 1 millimeters to 10 millimeters, and a width selected from the range of 1 millimeter to 10 millimeters.

95. The method of claim 91 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.0003 millimeters to 0.3 millimeters.

96. The method of claim 91 wherein said printable semiconductor element comprises a semiconductor structure having a thickness selected from the range of 0.002 millimeters to 0.02 millimeters.

97. The method of claim 91 comprising assembling a plurality of printable semiconductor elements on said receiving surface of said optical component via contact printing; wherein each of said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

98. The method of claim 91 wherein said optical component is a light collecting optical component, a light concentrating optical component, a light diffusing optical component, a light dispersing optical component or a light filtering optical component.

99. The method of claim 91 wherein said optical component is selected from the group consisting of a lens, a lens array, a reflector, an array of reflectors, a waveguide, an array of waveguides, an optical coating, an array of optical coatings, an optical filter, an array of optical filters, a fiber optic element and an array of fiber optic elements.

100. The method of claim 91 wherein said optical component is a lens array fabricated by replica molding.

101. The method of claim 91 wherein said optical component is an array of light collecting optical components, light concentrating optical components, light diffusing optical components, dispersing optical components or light filtering optical components.

102. The method of claim 101 wherein each of said components in said array is spatially aligned with respect to at least one of said printable semiconductor elements.

103. The method of claim 101 wherein each of said components in said array is individually addressed to at least one of said printable semiconductor elements.

104. The method of claim 91 wherein said printable semiconductor element is electronic devices or components of electronic devices.

105. The method of claim 91 wherein said printable semiconductor elements are one or more electronic device selected from the group consisting of: an LED, a laser, a solar cell, a sensor, a diode, a transistor, a p-n junction, an integrated circuit, and a photodiode.

106. The method of claim 91 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one additional structure selected from the group consisting of: another semiconductor structure; a dielectric structure; conductive structure, and an optical structure.

107. The method of claim 91 wherein said printable semiconductor element comprises said semiconductor structure integrated with at least one electronic device component selected from the group consisting of: an electrode, a dielectric layer, an optical coating, a metal contact pad and a semiconductor channel.

108. The method of claim 91 wherein each of said printable semiconductor element has a thickness selected from the range of 100 nanometers to 100 microns.

109. The method of claim 91 wherein said printable semiconductor element is assembled on said receiving surface via dry transfer contact printing.

110. The method of claim 91 wherein said printable semiconductor element is assembled on said receiving surface using a conformable transfer device.

111. The method of claim 110 wherein said assembling step comprises:
providing said conformable transfer device having a contact surface;

establishing conformal contact between an external surface of said printable semiconductor element and said contact surface of said conformable transfer device, wherein said conformal contact bonds said printable semiconductor element to said contact surface;

contacting said printable semiconductor element bonded to said contact surface and said receiving surface of said optical component; and

separating said printable semiconductor element and said contact surface of said conformable transfer device, thereby assembling said printable semiconductor element on said receiving surface of said optical component.

112. The method of claim 91 wherein said printable semiconductor element is assembled on said receiving surface using an elastomeric transfer device.

113. The method of claim 91 wherein said printable semiconductor element is assembled on said receiving surface using an elastomeric stamp.

114. The method of claim 91 further comprising the step of providing an adhesive layer or planarizing layer to said receiving surface of said optical component.

115. A semiconductor-based optical system comprising a device made by a method comprising the steps of:

providing a device substrate having a receiving surface; and

assembling a printable semiconductor element on said receiving surface of said substrate via contact printing; wherein said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

116. A semiconductor-based optical system comprising:

a device substrate having a receiving surface; and

a planarized printable semiconductor element supported by said receiving surface; wherein said device substrate having said printable semiconductor element has said substantially planar top surface that includes said printable

semiconductor element, wherein said planarized printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters.

117. A semiconductor-based optical system comprising:

a device substrate having a receiving surface;

a plurality of printable semiconductor elements supported by said receiving surface; wherein each of said printable semiconductor element comprises a semiconductor structure having a length selected from the range of 0.0001 millimeters to 1000 millimeters, a width selected from the range of 0.0001 millimeters to 1000 millimeters and a thickness selected from the range of 0.00001 millimeters to 3 millimeters; and

a grid or mesh provided in electrical contact with at least a portion of said plurality of printable semiconductor elements supported by said receiving surface, said grid or mesh comprising an electrically conductive material, wherein said grid or mesh provides an electrical interconnect structure or electrode of said optical system.