

IODINE-CONTAINING FLUOROCARBON AND HYDROFLUOROCARBON COMPOUNDS FOR ETCHING SEMICONDUCTOR STRUCTURES

Cross Reference to Related Applications

[0001] The present application claims the benefit of U.S. Application No.16/913,696 filed June 26, 2020, being incorporated herein by reference in its entirety for all purposes.

Technical Field

[0002] Methods for etching a silicon-containing film to form a patterned structure, methods for reinforcing and/or strengthening and/or minimizing damage of a patterned mask layer while forming a patterned structure and methods for increasing etch resistance of a patterned mask layer in a process of forming a patterned structure using iodine-containing etching compounds are disclosed. The iodine-containing etching compound have the formula $C_nH_xF_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, and $1 \leq z \leq 4$.

Background

[0003] In semiconductor industries, for 3D NAND, etching of stacks of multiple SiO/SiN or SiO/poly-Silicon (p-Si) layers is critical. See, e.g., US 2011/0180941 to Samsung Electronics Co., Ltd. An etchant having high selectivity between the mask and layers being etched is essential. Furthermore, the etched structure should have a straight vertical profile without bowing and low line etch roughness (LER).

[0004] Traditional etch gases include octafluorocyclobutane (C_4F_8), hexafluoro-1,3-butadiene (C_4F_6), CF_4 , CH_2F_2 , CH_3F , and/or CHF_3 . It is well known that selectivity and polymer deposition rate increase as the ratio of C:F increases (*i.e.*, $C_4F_8 > C_4F_6 > CF_4$). See, e.g., US6387287 to Hung *et al.* In addition, other gases, such as inert gases like Ar, Kr, or Xe, are added to the plasma where they are ionized and accelerated to the wafer surface bombarding the surface and supporting the etching process. Because they are inert gases, they do not directly participate in the chemical reactions of the etching process.

[0005] However, traditional etch chemistries may not be able to provide a feature, such as a hole or trench, having an aspect ratio higher than 20:1, which is necessary in the newer applications (e.g., 3D NAND), at least due to insufficient etch resistant polymer deposition on sidewalls during the plasma etching processes. The sidewall $-C_xF_y-$ polymers, wherein x ranges from 0.01 to 1 and y ranges from 0.01 to 4, may be susceptible to etching. As a result, the etched patterns may not be vertical and the etch structures may show bowing, change in dimensions, pattern collapse and/or increased roughness.

[0006] Bowing may result from sidewall etching of the mask layer, which may often be an amorphous carbon (a-C) material. The a-C materials may be etched by oxygen radicals in the plasma which may cause increased opening of the mask and result in bow-like, or angled/curved, etch structures.

[0007] Iodine-containing compounds have been used as etching gases and/or reduction of global warming potential (GWP). For example, Gupta et al. (US 10,607,850) disclose the iodine-containing etching compound has the formula $C_aH_xF_yI_z$, wherein $a=1-3$, $x=0-6$, $y=1-7$, $z=1-2$, $x+y+z=4$ when $a=1$, $x+y+z=4$ or 6 when $a=2$, $x+y+z=6$ or 8 when $a=3$. Chung (US Pat. No. 9,460,935) discloses etching first and second etching layers under plasma generated using, among others, 1,1,2,2-tetrafluoro-1-iodo-ethane. See also Karecki et al., "Plasma etching of dielectric films with novel iodofluorocarbon chemistries: iodotrifluoroethylene and 1-iodoheptafluoropropane", J. Vac. Sci. Technol. A 16, 755 (1998); JP2006/108484; and TWI343601. Iodine-containing etching compounds have been shown significant reductions in global warming emissions compared to perfluorocarbon compounds (see S. Karecki, L. Pruetter, and R. Reif, J. Electrochem. Soc. 145, 4305 (1998))

[0008] It is important to minimize bowing and to achieve high aspect ratio (*i.e.*, up to 200:1) needed for current applications (*e.g.*, contact etch or 3D NAND). Additionally, etching today has not been limited to selectivity to the photoresist mask. It is equally important to get high selectivity among other materials such as a-C, SiN, p-Si, SiC or other forms of $Si_aC_bO_cH_dN_e$ materials (where $a>0$; b, c, d and $e \geq 0$).

[0009] Thus, a need remains for etch gas compositions suitable for use in plasma etching applications which maintain selectivity and high aspect ratios for a wide range of process conditions.

Summary

[0010] Disclosed are methods of forming a patterned structure, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and a patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound has the formula $C_nH_xF_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, and $1 \leq z \leq 4$;

activating a plasma to produce an activated iodine-containing etching compound; and
allowing an etching reaction to proceed between the activated iodine-containing etching compound and the silicon-containing film to selectively etch the silicon-containing film from the patterned mask layer, thereby forming the patterned structure. The disclosed methods may include one or more of the following aspects:

- further comprising introducing an oxidizer into the reaction chamber;
- the oxidizer being selected from O₂, O₃, CO, CO₂, NO, N₂O, NO₂, H₂O, H₂O₂, COS, SO₂ and combinations thereof;
- the oxidizer being O₂;
- further comprising introducing an inert gas into the reaction chamber;
- the inert gas being selected from the group consisting of He, Ar, Xe, Kr, Ne and N₂;
- the inert gas being Ar;
- the inert gas being Xe;
- the inert gas being Kr;
- the iodine-containing etching compound being a hydrofluorocarbon compound;
- the iodine-containing etching compound being an organofluorine compound;
- the iodine-containing etching compound being a fluorine-containing hydrocarbon compound;
- the iodine-containing etching compound being a fluorocarbon compound;
- the iodine-containing etching compound being a hydrocarbon compound;
- the iodine-containing etching compound containing no hydrogen;
- the iodine-containing etching compound containing hydrogen;
- the iodine-containing etching compound containing fluorine;
- the iodine-containing etching compound containing no fluorine;
- the iodine-containing etching compound being C₄F₉I, C₅F₁₁I, C₆F₁₃I, C₇F₁₅I, C₈F₁₇I, C₉F₁₉I, C₁₀F₂₁I or their isomers;
- the iodine-containing etching compound being C₄HF₈I, C₅HF₁₀I, C₆HF₁₂I, C₇HF₁₄I, C₈HF₁₆I, C₉HF₁₈I, C₁₀HF₂₀I, C₄HF₆I, C₅HF₈I, C₆HF₁₀I, C₇HF₁₂I, C₈HF₁₄I, C₉HF₁₆I, C₁₀HF₁₈I, C₄HF₄I, C₅HF₆I, C₆HF₈I, C₇HF₁₀I, C₈HF₁₂I, C₉HF₁₄I, C₁₀HF₁₆I, C₄HF₇I₂, C₅HF₉I₂, C₆HF₁₁I₂, C₇HF₁₃I₂, C₈HF₁₅I₂, C₉HF₁₇I₂, C₁₀HF₁₉I₂, C₄HF₅I₂, C₅HF₇I₂, C₆HF₉I₂, C₇HF₁₁I₂, C₈HF₁₃I₂, C₉HF₁₅I₂, C₁₀HF₁₇I₂, C₄HF₃I₂, C₅HF₅I₂, C₆HF₇I₂, C₇HF₉I₂, C₈HF₁₁I₂, C₉HF₁₃I₂, C₁₀HF₁₅I₂, C₄HF₆I₃, C₅HF₈I₃, C₆HF₁₀I₃, C₇HF₁₂I₃, C₈HF₁₄I₃, C₉HF₁₆I₃, C₁₀HF₁₈I₃, C₄HF₄I₃, C₅HF₆I₃, C₆HF₈I₃, C₇HF₁₀I₃, C₈HF₁₂I₃, C₉HF₁₄I₃, C₁₀HF₁₆I₃, C₄HF₅I₄, C₅HF₇I₄, C₆HF₉I₄, C₇HF₁₁I₄, C₈HF₁₃I₄, C₉HF₁₅I₄, C₁₀HF₁₇I₄, C₄HF₃I₄, C₅HF₅I₄, C₆HF₇I₄, C₇HF₉I₄, C₈HF₁₁I₄, C₉HF₁₃I₄, C₁₀HF₁₅I₄, C₄HF₁I₄, C₅HF₃I₄, C₆HF₅I₄, C₇HF₇I₄, C₈HF₉I₄, C₉HF₁₁I₄, C₁₀HF₁₃I₄ or their isomers;
- the iodine-containing etching compound being C₄H₂F₇I, C₅H₂F₉I, C₆H₂F₁₁I, C₇H₂F₁₃I, C₈H₂F₁₅I, C₉H₂F₁₇I, C₁₀H₂F₁₉I, C₄H₂F₅I, C₅H₂F₇I, C₆H₂F₉I, C₇H₂F₁₁I, C₈H₂F₁₃I, C₉H₂F₁₅I, C₁₀H₂F₁₇I, C₄H₂F₆I₂, C₅H₂F₈I₂, C₆H₂F₁₀I₂, C₇H₂F₁₂I₂, C₈H₂F₁₄I₂, C₉H₂F₁₆I₂, C₁₀H₂F₁₈I₂, C₄H₂F₄I₂, C₅H₂F₆I₂, C₆H₂F₈I₂, C₇H₂F₁₀I₂, C₈H₂F₁₂I₂, C₉H₂F₁₄I₂, C₁₀H₂F₁₆I₂,

- $C_4H_2F_5I_3$, $C_5H_2F_7I_3$, $C_6H_2F_9I_3$, $C_7H_2F_{11}I_3$, $C_8H_2F_{13}I_3$, $C_9H_2F_{15}I_3$, $C_{10}H_2F_{17}I_3$, $C_4H_2F_3I_3$, $C_5H_2F_5I_3$, $C_6H_2F_7I_3$, $C_7H_2F_9I_3$, $C_8H_2F_{11}I_3$, $C_9H_2F_{13}I_3$, $C_{10}H_2F_{15}I_3$, $C_4H_2F_4I_4$, $C_5H_2F_6I_4$, $C_6H_2F_8I_4$, $C_7H_2F_{10}I_4$, $C_8H_2F_{12}I_4$, $C_9H_2F_{14}I_4$, $C_{10}H_2F_{16}I_4$, $C_4H_2F_2I_4$, $C_5H_2F_4I_4$, $C_6H_2F_6I_4$, $C_7H_2F_8I_4$, $C_8H_2F_{10}I_4$, $C_9H_2F_{12}I_4$, $C_{10}H_2F_{14}I_4$ or their isomers;
- the iodine-containing etching compound being $C_4H_3F_6I$, $C_5H_3F_8I$, $C_6H_3F_{10}I$, $C_7H_3F_{12}I$, $C_8H_3F_{14}I$, $C_9H_3F_{16}I$, $C_{10}H_3F_{18}I$, $C_4H_3F_4I$, $C_5H_3F_6I$, $C_6H_3F_8I$, $C_7H_3F_{10}I$, $C_8H_3F_{12}I$, $C_9H_3F_{14}I$, $C_{10}H_3F_{16}I$, $C_4H_3F_5I_2$, $C_5H_3F_7I_2$, $C_6H_3F_9I_2$, $C_7H_3F_{11}I_2$, $C_8H_3F_{13}I_2$, $C_9H_3F_{15}I_2$, $C_{10}H_3F_{17}I_2$, $C_4H_3F_3I_2$, $C_5H_3F_5I_2$, $C_6H_3F_7I_2$, $C_7H_3F_9I_2$, $C_8H_3F_{11}I_2$, $C_9H_3F_{13}I_2$, $C_{10}H_3F_{15}I_2$, $C_4H_3F_4I_3$, $C_5H_3F_6I_3$, $C_6H_3F_8I_3$, $C_7H_3F_{10}I_3$, $C_8H_3F_{12}I_3$, $C_9H_3F_{14}I_3$, $C_{10}H_3F_{16}I_3$, $C_4H_3F_2I_3$, $C_5H_3F_4I_3$, $C_6H_3F_6I_3$, $C_7H_3F_8I_3$, $C_8H_3F_{10}I_3$, $C_9H_3F_{12}I_3$, $C_{10}H_3F_{14}I_3$, $C_4H_3F_3I_4$, $C_5H_3F_5I_4$, $C_6H_3F_7I_4$, $C_7H_3F_9I_4$, $C_8H_3F_{11}I_4$, $C_9H_3F_{13}I_4$, $C_{10}H_3F_{15}I_4$, $C_4H_3F_{11}I_4$, $C_5H_3F_{13}I_4$, $C_6H_3F_{15}I_4$, $C_7H_3F_{17}I_4$, $C_8H_3F_{19}I_4$, $C_9H_3F_{21}I_4$, $C_{10}H_3F_{23}I_4$ or their isomers;
 - the iodine-containing etching compound being $C_4H_4F_5I$, $C_5H_4F_7I$, $C_6H_4F_9I$, $C_7H_4F_{11}I$, $C_8H_4F_{13}I$, $C_9H_4F_{15}I$, $C_{10}H_4F_{17}I$, $C_4H_4F_3I$, $C_5H_4F_5I$, $C_6H_4F_7I$, $C_7H_4F_9I$, $C_8H_4F_{11}I$, $C_9H_4F_{13}I$, $C_{10}H_4F_{15}I$, $C_4H_4F_4I_2$, $C_5H_4F_6I_2$, $C_6H_4F_8I_2$, $C_7H_4F_{10}I_2$, $C_8H_4F_{12}I_2$, $C_9H_4F_{14}I_2$, $C_{10}H_4F_{16}I_2$, $C_4H_4F_2I_2$, $C_5H_4F_4I_2$, $C_6H_4F_6I_2$, $C_7H_4F_8I_2$, $C_8H_4F_{10}I_2$, $C_9H_4F_{12}I_2$, $C_{10}H_4F_{14}I_2$, $C_4H_4F_3I_3$, $C_5H_4F_5I_3$, $C_6H_4F_7I_3$, $C_7H_4F_9I_3$, $C_8H_4F_{11}I_3$, $C_9H_4F_{13}I_3$, $C_{10}H_4F_{15}I_3$, $C_4H_4F_{11}I_3$, $C_5H_4F_3I_3$, $C_6H_4F_5I_3$, $C_7H_4F_7I_3$, $C_8H_4F_9I_3$, $C_9H_4F_{11}I_3$, $C_{10}H_4F_{13}I_3$, $C_4H_4F_2I_4$, $C_5H_4F_4I_4$, $C_6H_4F_6I_4$, $C_7H_4F_8I_4$, $C_8H_4F_{10}I_4$, $C_9H_4F_{12}I_4$, $C_{10}H_4F_{14}I_4$, $C_4H_4I_4$, $C_5H_4F_2I_4$, $C_6H_4F_4I_4$, $C_7H_4F_6I_4$, $C_8H_4F_8I_4$, $C_9H_4F_{10}I_4$, $C_{10}H_4F_{12}I_4$ or their isomers;
 - the iodine-containing etching compound being C_4F_9I or its isomers;
 - the plasma activated the iodine-containing etching compound reacting with the silicon-containing film to form volatile by-products;
 - the volatile by-products being removed from the reaction chamber;
 - the silicon-containing film comprising oxygen, nitrogen, carbon, hydrogen, carbon or combinations thereof;
 - the silicon-containing film being comprising a layer of silicon oxide (SiO), silicon nitride (SiN), crystalline Si, poly-silicon (p-Si), polycrystalline silicon, amorphous silicon, low- k SiCOH, SiOCN, SiC, SiON and $Si_aO_bH_cC_dN_e$, where $a > 0$; b , c , d and $e \geq 0$, alternating SiO and SiN (ONON) layers, alternating SiO and p-Si (OPOP) layers;
 - the silicon-containing film optionally containing dopants such as B, C, P, As, Ga, In, Sn, Sb, Bi and/or Ge, or combinations thereof;
 - the silicon-containing film comprising oxygen, nitrogen, carbon, hydrogen, or combinations thereof;
 - the silicon-containing film being $SiO_xN_yH_zC_k$, wherein x ranges from 0 to 2, y ranges from 0 to 4, z ranges from 0 to about 1 and k ranges from 0 to 1;

- the silicon-containing film comprising a SiO layer;
- the silicon-containing film being a SiN layer;
- the silicon-containing film comprising alternating SiO and SiN (ONON) layers;
- the silicon-containing film comprising alternating SiO and p-Si (OPOP) layers;
- the silicon-containing film comprising dopants such as B, C, P, As, Ga, In, Sn, Sb, Bi and/or Ge;
- the alternating layers comprising a layer of silicon oxide, silicon nitride, polysilicon, crystalline silicon, SiOCH, SiON, $\text{Si}_a\text{O}_b\text{C}_c\text{N}_d\text{H}_e$ (where $a>0$; b, c, d and $e \geq 0$) or combinations thereof;
- the alternating layers comprising oxygen atoms, nitrogen atoms, carbon atoms, hydrogen atoms or combinations thereof;
- the alternating layers being a silicon containing film;
- the alternating layers comprising a layer of silicon oxide and a layer of silicon nitride;
- the alternating layers comprising alternating layers of silicon oxide and silicon nitride;
- the alternating layers being alternating layers of silicon oxide and silicon nitride;
- the alternating layers comprising a layer of silicon oxide and a layer of polysilicon;
- the alternating layers comprising alternating layers of silicon oxide and polysilicon;
- the alternating layers being alternating layers of silicon oxide and polysilicon;
- a hardmask layer being disposed on the silicon-containing layer;
- the hardmask layer being a patterned hardmask layer;
- the hardmask layer being an amorphous carbon layer, a doped amorphous carbon layer, a photoresist layer, an anti-reflective layer, an organic planarization layer or combinations thereof;
- the hardmask layer being a layer of CVD, PECVD, ALD, PEALD or spin on deposited (SOD) amorphous carbon or doped amorphous carbon, silicon-containing spin on mask, or carbon-containing spin on mask;
- the hardmask layer being an amorphous carbon (a-C) layer;
- the hardmask layer being a doped carbon layer;
- the doped amorphous carbon layer being a boron-doped a-C layer;
- the doped amorphous carbon layer being a tungsten-doped a-C layer;
- the alternating layers being selectively etched from the hardmask layer;
- the alternating layers being selectively etched from an a-C layer;
- the alternating layers being selectively etched from a doped carbon layer;
- the alternating layers of silicon oxide and silicon nitride being selectively etched from an a-C layer;
- the alternating layers of silicon oxide and silicon nitride being selectively etched

- from a doped carbon layer;
- the alternating layers of silicon oxide and polysilicon being selectively etched from an a-C layer;
 - the alternating layers of silicon oxide and polysilicon being selectively etched from a doped carbon layer;
 - the silicon oxide layer being selectively etched from the hardmask layer;
 - the silicon oxide layer being selectively etched from an a-C layer;
 - the silicon oxide layer being selectively etched from a doped carbon layer;
 - the silicon nitride layer being selectively etched from the hardmask layer;
 - the silicon nitride layer being selectively etched from an a-C layer;
 - the silicon nitride layer being selectively etched from a doped carbon layer;
 - the polysilicon layer being selectively etched from the hardmask layer;
 - the polysilicon layer being selectively etched from an a-C layer;
 - the polysilicon layer being selectively etched from a doped carbon layer;
 - the silicon-containing film being selectively etched from an amorphous carbon layer, a doped amorphous carbon layer, a photoresist layer, an anti-reflective layer or organic planarization layer;
 - the silicon oxide layer is selectively etched from an amorphous carbon layer, a doped amorphous carbon layer, a photoresist layer, an anti-reflective layer or organic planarization layer;
 - the iodine-containing etching compound etching both the silicon oxide layer and the silicon nitride layer with high etch rates;
 - the selectivity of the iodine-containing etching compound etching both silicon oxide layer and the silicon nitride layer ranging from approximately 1:2 to approximately 2:1;
 - the iodine-containing etching compound plasma etching the alternating SiO and SiN (ONON) layers having a selectivity between approximately 1:2 to approximately 2:1 with respect to the SiO layer versus SiN layer;
 - the iodine-containing etching compound plasma etching the alternating SiO and SiN (ONON) layers having a selectivity of approximately 1:1 with respect to the SiO layer versus SiN layer;
 - the selectivity of the iodine-containing etching compound etching both silicon oxide layer and the silicon nitride layer being approximately 1:1;
 - the iodine-containing etching compound etching both the silicon oxide layer and the polysilicon layer with high etch rates;
 - the selectivity of the iodine-containing etching compound etching both silicon oxide

- layer and the polysilicon layer ranging from approximately 1:2 to approximately 2:1;
- the iodine-containing etching compound plasma etching the alternating SiO and p-Si (OPOP) layers having a selectivity between approximately 1:2 to approximately 2:1 with respect to the SiO layer versus p-Si layer;
 - the iodine-containing etching compound plasma etching the alternating SiO and p-Si (OPOP) layers having a selectivity of approximately 1:1 with respect to the SiO layer versus p-Si layer;
 - the selectivity of the iodine-containing etching compound etching both silicon oxide layer and the polysilicon layer being approximately 1:1;
 - an etch rate of etching the silicon oxide layer using the iodine-containing etching compound being higher than an etch rate of etching the silicon oxide layer using the traditional etching gases C_4F_8 , C_4F_6 , CF_4 , CH_3F , CF_3H , CH_2F_2 , or combinations thereof;
 - an etch rate of etching the silicon oxide layer using the iodine-containing etching compound being approximately 640 nm/min;
 - an etch rate of etching the silicon oxide layer using the iodine-containing etching compound which is higher than the etch rate of etching the silicon oxide layer SiO_2 using the traditional etching gas C_4F_8 ;
 - an etch rate of etching the silicon oxide layer using the iodine-containing etching compound which is higher than the etch rate of etching the silicon oxide layer SiO_2 using the traditional etching gas C_4F_6 ;
 - an etch rate of etching the silicon oxide layer using $\text{C}_4\text{F}_9\text{I}$ which is higher than the etch rate of etching the silicon oxide layer SiO_2 using etching gases C_4F_8 or C_4F_6 with heating of the iodine-containing etching compound for plasma etching to avoid condensation;
 - an etch rate of etching the silicon oxide layer using $\text{C}_4\text{F}_9\text{I}$ which is higher than the etch rate of etching the silicon oxide layer SiO_2 using an etching gas C_4F_8 with heating of the iodine-containing etching compound for plasma etching to avoid condensation;
 - an etch rate of etching the silicon oxide layer using $\text{C}_4\text{F}_9\text{I}$ which is higher than the etch rate of etching the silicon oxide layer SiO_2 using an etching gas C_4F_6 with heating of the iodine-containing etching compound for plasma etching to avoid condensation;
 - heating the iodine-containing etching compound for plasma etching to avoid condensation;
 - the patterned structure formed in the silicon-containing film has an aspect ratio

between approximately 1:1 and approximately 200:1;

- heating the iodine-containing etching compound for plasma etching to maintain a desired flow rate of the iodine-containing etching compound;
- the iodine-containing etching compound selectively etching the silicon-containing film from a landing layer located at the bottom of the silicon-containing film to be etched;
- the landing layer being a buried landing layer located at the bottom of the structure to be etched;
- the landing layer being an etching stop layer;
- the landing layer being a silicon layer;
- the landing layer being a metal layer;
- the landing layer being a tungsten metal wordline in a 3D NAND structure and/or another metal such as W, Cu, Al, Ru, Pt, Ti, Ta, Ni, Co, Mo, Mn, Nb, Cr, Rh, Pd, Ir, V, Au, Ag or combinations thereof;
- the landing layer being a metal oxide or metal nitride layer;
- the landing layer being a AlO, WO, TiN, or TaN layer;
- the metal layer being selected from W, Cu, Al, Ru, Pt, Ti, Ta, Ni, Co, Mo, or an etch stop layer selected from AlO, WO, TiN, TaN;
- the landing layer being a metal oxide layer or a metal nitride layer selected from AlO, WO, HfO, TiO, TaO, InO, WO, CrO, RuO, CoO, MoO, ZrO, SnO, TiN, TaN, HfN, AlN, WN, MoN, NiN, NbN, CrN, RuN, CoN, ZrN, SrN or combinations thereof;
- adding an oxygen containing gas to the iodine-containing etching compound;
- the oxygen containing gas selected from the group consisting of O₂, O₃, CO, CO₂, NO, NO₂, N₂O, SO₂, COS, H₂O and combination thereof;
- the oxygen containing gas being O₂;
- mixing the iodine-containing etching compound and the oxygen containing gas prior to introduction to the chamber to produce a mixture;
- introducing the iodine-containing etching compound separately from the oxygen containing gas;
- introducing the oxygen containing gas continuously and introducing the iodine-containing etching compound;
- the oxygen containing gas comprising approximately 0.01% v/v to approximately 99.9% v/v of a total volume of the iodine-containing etching compound and oxygen containing gas;
- the oxygen containing gas comprising approximately 0.01% v/v to approximately 10% v/v of

- a total volume of the iodine-containing etching compound and oxygen containing gas;
- mixing the iodine-containing etching compound and the inert gas prior to introduction to the chamber to produce a mixture;
- introducing the iodine-containing etching compound separately from the inert gas;
- introducing the inert gas continuously and introducing the iodine-containing etching compound in pulses;
- the inert gas comprising approximately 0.01% v/v to approximately 99.9% v/v of a total volume of the vapor of the iodine-containing etching compound and inert gas;
- the inert gas comprising approximately 90% v/v to approximately 99% v/v of a total volume of the vapor of the iodine-containing etching compound and inert gas;
- the substrate being a Si wafer;
- the substrate being a crystalline silicon layer;
- forming the patterned structure;
- the patterned structure being 3D NAND apertures;
- the patterned structure being contact holes;
- the patterned structure being 3D NAND contact holes;
- the patterned structure being DRAM contact;
- the patterned structure being channel holes;
- the patterned structure being 3D NAND channel holes;
- the patterned structure being 3D NAND slit contact;
- the aperture being staircase contacts;
- the aperture being self-aligned contact;
- the aperture being self-aligned vias;
- the aperture being super vias;
- further comprising introducing an additional etch gas to the iodine-containing etching compound;
- the additional etch gas being selected from the group consisting of the group consisting of C_4F_8 , C_4F_6 , C_5F_8 , C_5F_6 , C_4F_6 , CF_4 , CH_3F , CF_3H , CH_2F_2 , C_3HF_7 , C_3F_6 , $\text{C}_3\text{H}_2\text{F}_6$, $\text{C}_3\text{H}_2\text{F}_4$, $\text{C}_3\text{H}_3\text{F}_5$, C_4HF_7 , C_5HF_9 , C_3F_6 , C_3F_8 , CF_3I , $\text{C}_2\text{F}_3\text{I}$, $\text{C}_2\text{F}_5\text{I}$, $\text{C}_3\text{F}_7\text{I}$, 1-iodoheptafluoropropane (1- $\text{C}_3\text{F}_7\text{I}$), 2-iodoheptafluoropropane (2- $\text{C}_3\text{F}_7\text{I}$), C_3HF_7 , COS , FNO , $\text{F-C}\equiv\text{N}$, CS_2 , SO_2 , SF_6 , *trans*-1,1,1,4,4,4-hexafluoro-2-butene (*trans*- $\text{C}_4\text{H}_2\text{F}_6$), *cis*-1,1,1,4,4,4-hexafluoro-2-butene (*cis*- $\text{C}_4\text{H}_2\text{F}_6$), hexafluoroisobutene ($\text{C}_4\text{H}_2\text{F}_6$), *trans*-1,1,2,2,3,4-hexafluorocyclobutane (*trans*- $\text{C}_4\text{H}_2\text{F}_6$), 1,1,2,2,3-pentafluorocyclobutane ($\text{C}_4\text{H}_3\text{F}_5$), 1,1,2,2-tetrafluorocyclobutane ($\text{C}_4\text{H}_4\text{F}_4$), and *cis*-1,1,2,2,3,4-hexafluorocyclobutane (*cis*- $\text{C}_4\text{H}_2\text{F}_6$) or combination thereof;

- introducing the iodine-containing etching compound separately from the additional etch gas;
- adding approximately 0.01% v/v to approximately 99.99% v/v of the additional etch gas to the iodine-containing etching compound;
- activating the plasma by applying RF power;
- activating the plasma by a RF power ranging from approximately 25 W to approximately 100,000 W;
- etching pressure ranging from approximately 1 mTorr to approximately 10 Torr;
- etching pressure being 30 mTorr;
- introducing the iodine-containing etching compound at a flow rate ranging from approximately 0.1 sccm to approximately 1 slm;
- maintaining the substrate at a temperature ranging from approximately -196°C to approximately 500°C;
- maintaining the substrate at a temperature ranging from approximately -120°C to approximately 300°C;
- maintaining the substrate at a temperature ranging from approximately -100°C to approximately 50°C;
- maintaining the substrate at a temperature ranging from approximately -10°C to approximately 40°C; and
- measuring the iodine-containing etching compound under plasma by Quadrupole mass spectrometer, optical emission spectrometer, FTIR, or other radical/ion measurement tool.

[0010a] In one aspect, there is provided a method for forming a patterned structure, the method comprising the steps of:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and a patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C_4F_9I or its isomers;

activating a plasma to produce an activated iodine-containing etching compound;
and

allowing an etching reaction to proceed between the activated iodine-containing etching compound and the silicon-containing film to selectively etch the silicon-containing film from the patterned mask layer, thereby forming the patterned structure.

[0011] Also disclosed are methods of reinforcing, strengthening and minimizing damage of a patterned mask layer while forming a patterned structure in a substrate, the method comprising

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound has the formula $C_nH_xF_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, and $1 \leq z \leq 4$; and

etching the silicon-containing film from the patterned mask layer to form the patterned structure using an activated iodine-containing etching compound formed by activating a plasma,

wherein the activated iodine-containing etching compound produces iodine ions, which are implanted into the patterned hardmask layer, thereby strengthening the patterned mask layer. The disclosed methods may include one or more of the following aspects:

- the iodine-containing etching compound being a fluorine-containing hydrocarbon compound;
- the iodine-containing etching compound being a fluorocarbon compound;
- the iodine-containing etching compound being an organofluorine compound;
- the iodine-containing etching compound being a hydrocarbon compound;
- the activated iodine-containing etching compound produces iodine ions that strengthens the patterned mask layer;
- the iodine-containing etching compound is C_4F_9I , $C_5F_{11}I$, $C_6F_{13}I$, $C_7F_{15}I$, $C_8F_{17}I$, $C_9F_{19}I$, $C_{10}F_{21}I$ or their isomers; and
- the iodine-containing etching compound is C_4F_9I or its isomers.

[0011a] In another aspect, there is provided a method of reinforcing and/or strengthening and/or minimizing damage of a patterned mask layer while forming a patterned structure in a substrate, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C_4F_9I or its isomers; and

etching the silicon-containing film from the patterned mask layer to form the patterned structure using an activated iodine-containing etching compound formed by activating a plasma,

wherein the activated iodine-containing etching compound produces iodine ions, which are implanted into the patterned hardmask layer, thereby strengthening the patterned mask layer.

[0012] Also disclosed are method of increasing etch resistance of a patterned mask layer, for example, by doping with iodine the pattern mask layer and/or by modifying with iodine the surface of the pattern mask layer in a process of forming a patterned structure in a substrate, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound has the formula $C_nH_xF_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, and $1 \leq z \leq 4$;

activating a plasma to produce an activated iodine-containing etching compound capable of doping iodine into the patterned mask layer; and

implanting iodine ions from the activated iodine-containing etching compound into the patterned mask layer while etching the silicon-containing film from the patterned mask layer

to form the patterned structure, thereby modifying the patterned mask layer with iodine to increase the etch resistance of the patterned mask layer. The disclosed methods may include one or more of the following aspects:

- the iodine-containing etching compound being a fluorine-containing hydrocarbon compound;
- the iodine-containing etching compound being a fluorocarbon compound;
- the iodine-containing etching compound being a hydrocarbon compound;
- the iodine-containing etching compound being an organofluorine compound;
- the iodine-containing etching compound is C_4F_9I , $C_5F_{11}I$, $C_6F_{13}I$, $C_7F_{15}I$, $C_8F_{17}I$, $C_9F_{19}I$ and $C_{10}F_{21}I$ or their isomers;
- the iodine-containing etching compound is C_4F_9I or its isomers;
- implanting the iodine ion from the activated iodine-containing etching compound into the surface and/or the bulk of the patterned mask layer while etching the silicon-

- containing film from the substrate to form the patterned structure;
- implanting the iodine ion from the activated iodine-containing etching compound into the surface of the patterned mask layer while etching the silicon-containing film from the substrate to form the patterned structure; and
- implanting the iodine ion from the activated iodine-containing etching compound into the bulk of the patterned mask layer while etching the silicon-containing film from the substrate to form the patterned structure.

[0012a] In yet another aspect, there is provided a method of increasing etch resistance of a patterned mask layer in a process of forming a patterned structure in a substrate, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C_4F_9I or its isomers;

activating a plasma to produce an activated iodine-containing etching compound capable of doping iodine into the patterned mask layer; and

implanting iodine ions from the activated iodine-containing etching compound into the patterned mask layer while etching the silicon-containing film from the patterned mask layer to form the patterned structure, thereby modifying the patterned mask layer with iodine to increase the etch resistance of the patterned mask layer.

Notation and Nomenclature

[0013] The following detailed description and claims utilize a number of abbreviations, symbols, and terms, which are generally well known in the art. While definitions are typically provided with the first instance of each acronym, for convenience, **Table 1** provides a list of the abbreviations, symbols, and terms used along with their respective definitions.

Table 1

LCD-TFT	liquid-crystal display-thin-film transistor
DRAM	dynamic random-access memory
FINFET	fin-shaped field-effect transistor
Bulk CMOS	Bulk complementary metal-oxide-semiconductor
FD-SOI	fully depleted silicon-on-insulator
FEOL	front end of the line
BEOL	back end of the line
TSV	through silicon via

OLED	organic light-emitting diode
RIE	reactive ion etching
CCP	capacitively coupled plasma
ICP	inductively coupled plasma
sccm	standard cubic centimeters per minute
slm	standard liter per minute
ONON	silicon oxide and silicon nitride alternating layers
OPOP	silicon oxide and poly-silicon alternating layers
TCAT	terabit cell array transistor
P-BICS	pipe-shaped bit cost scalable
QMS	Quadrupole mass spectrometer
ARC or BARC	Anti-reflecting coating or Bottom anti-reflecting coating
APF or a-C	Amorphous carbon. Trademark of Applied Materials

CAS	chemical abstract service
PCTFE	Polychlorotrifluoroethene
PVDF	polyvinylidene fluoride
PTFE	Polytetrafluoroethylene
SEM	scanning electron microscope
NAND	Not AND or Negative-NAND or Negated AND
TEOS	Tetraethylorthosilicate
LDTEOS	low deposition rate TEOS
BPSG	Borophosphosilicateglass
p-Si	poly-silicon
XPS	X-ray photoelectron spectroscopy
SiN	Silicon nitride
SiO	Silicon oxide
PECVD	Plasma enhanced chemical vapor deposition
LPCVD	Low pressure chemical vapor deposition

[0014] As used herein, the indefinite article “a” or “an” means one or more.

[0015] As used herein, “about” or “around” or “approximately” in the text or in a claim means $\pm 10\%$ of the value stated.

[0016] As used herein, “room temperature” in the text or in a claim means from approximately 20°C to approximately 25°C.

[0017] The term “ambient temperature” refers to an environment temperature approximately 20°C to approximately 25°C.

[0018] The term “substrate” refers to a material or materials on which a process is conducted. The substrate may refer to a wafer having a material or materials on which a process is conducted. The substrates may be any suitable wafer used in semiconductor, photovoltaic, flat panel, or LCD-TFT device manufacturing. The substrate may also have one or more layers of differing materials already deposited upon it from a previous manufacturing step. For example, the wafers may include silicon layers (e.g., crystalline, amorphous, porous, etc.), silicon containing layers (e.g., SiO₂, SiN, SiON, SiC, SiCN, SiOCN, SiCOH, etc.), metal containing layers (e.g., copper, cobalt, ruthenium, tungsten, manganese, platinum, palladium, nickel, ruthenium, gold, etc.) or combinations thereof. Furthermore, the substrate may be planar or patterned. The substrate may be an organic patterned photoresist film. The substrate may include layers of oxides which are used as dielectric materials in MEMS, 3D NAND, MIM, DRAM, or FeRam device applications (for example, ZrO₂ based

materials, HfO₂ based materials, TiO₂ based materials, rare earth oxide based materials, ternary oxide based materials, etc.) or nitride-based films (for example, TaN, TiN, NbN) that are used as electrodes. One of ordinary skill in the art will recognize that the terms "film" or "layer" used herein refer to a thickness of some material laid on or spread over a surface and that the surface may be a trench or a line. Throughout the specification and claims, the wafer and any associated layers thereon are referred to as substrates.

[0019] The term "wafer" or "patterned wafer" refers to a wafer having a stack of silicon-containing films on a substrate and a patterned hardmask layer on the stack of silicon-containing films formed for pattern etch.

[0020] The term "pattern etch" or "patterned etch" refers to etching a non-planar structure, such as a patterned mask layer on a stack of silicon-containing films.

[0021] As used herein, the term "etch" or "etching" means to use a plasma to remove material via ion bombardment, remote plasma, or chemical vapor reaction between the etching gas and substrate and refers to an isotropic etching process and/or an anisotropic etching process. The isotropic etch process involves a chemical reaction between the etching compound and the substrate resulting in part of material on the substrate being removed. This type of etching process includes chemical dry etching, vapor phase chemical etching, thermal dry etching, or the like. The isotropic etch process produces a lateral or horizontal etch profile in a substrate. The isotropic etch process produces recesses or horizontal recesses on a sidewall of a pre-formed aperture in a substrate. The anisotropic etch process involves a plasma etching process (*i.e.*, a dry etch process) in which ion bombardment accelerates the chemical reaction in the vertical direction so that vertical sidewalls are formed along the edges of the masked features at right angles to the substrate (Manos and Flamm, Thermal etching an Introduction, Academic Press, Inc. 1989 pp.12-13). The plasma etching process produces a vertical etch profile in a substrate. The plasma etching process produces vertical vias, apertures, trenches, channel holes, gate trenches, staircase contacts, capacitor holes, contact holes, slit etch, self-aligned contact, self-aligned vias, super vias *etc.*, in the substrate.

[0022] The term "mask" refers to a layer that resists etching. The mask layer may be located above the layer to be etched. The mask layer also refers to a hardmask layer.

[0023] The term "etch stop" refers to a layer below the layer to be etched that protects layers underneath.

[0024] The term "device channel" refers to layers that are part of actual device and any damage to it will affect device performance.

[0025] The term "aspect ratio" refers to a ratio of the height of a trench (or via) to the width of the trench (or the diameter of the via).

[0026] The term "selectivity" means the ratio of the etch rate of one material to the etch rate of another material. The term "selective etch" or "selectively etch" means to etch one material more than another material, or in other words to have a greater or less than 1:1 etch selectivity between two materials.

[0027] The term "independently" when used in the context of describing R groups should be understood to denote that the subject R group is not only independently selected relative to other R groups bearing the same or different subscripts or superscripts, but is also independently selected relative to any additional species of that same R group. For example in the formula $MR^1_x(NR^2R^3)_{(4-x)}$, where M is an atom, x is 2 or 3, the two or three R^1 groups may, but need not be identical to each other or to R^2 or to R^3 . Further, it should be understood that unless specifically stated otherwise, values of R groups are independent of each other when used in different formulas.

[0028] Note that herein, the terms "film" and "layer" may be used interchangeably. It is understood that a film may correspond to, or related to a layer, and that the layer may refer to the film. Furthermore, one of ordinary skill in the art will recognize that the terms "film" or "layer" used herein refer to a thickness of some material laid on or spread over a surface and that the surface may range from as large as the entire wafer to as small as a trench or a line.

[0029] Note that herein, the terms "etching compound" and "etching gas" may be used interchangeably. It is understood that an etching compound may correspond to, or related to an etching gas, and that the etching gas may refer to the etching compound.

[0030] The terms "via", "aperture", "trench", and "hole" are sometimes used interchangeably, and generally mean an opening in an interlayer insulator.

[0031] As used herein, the abbreviation "NAND" refers to a "Negated AND" or "Not AND" gate; the abbreviation "2D" refers to 2 dimensional gate structures on a planar substrate; the abbreviation "3D" refers to 3 dimensional or vertical gate structures, wherein the gate structures are stacked in the vertical direction.

[0032] The standard abbreviations of the elements from the periodic table of elements are used herein. It should be understood that elements may be referred to by these abbreviations (e.g., Si refers to silicon, N refers to nitrogen, O refers to oxygen, C refers to carbon, H refers to hydrogen, F refers to fluorine, etc.).

[0033] The unique CAS registry numbers (*i.e.*, "CAS") assigned by the Chemical Abstract Service are provided to help better identify the molecules disclosed.

[0034] Please note that the silicon-containing films, such as silicon nitride and silicon oxide, are listed throughout the specification and claims without reference to their proper stoichiometry. The silicon-containing films may include pure silicon (Si) layers, such as crystalline Si, poly-silicon (p-Si or polycrystalline Si), or amorphous silicon; silicon nitride

(Si_kN_l) layers; or silicon oxide (Si_nO_m) layers; or mixtures thereof, wherein k, l, m, and n, inclusively range from 0.1 to 6. Preferably, silicon nitride is Si_kN_l , where k and l each range from 0.5 to 1.5. More preferably silicon nitride is Si_3N_4 . Preferably silicon oxide is Si_nO_m , where n ranges from 0.5 to 1.5 and m ranges from 1.5 to 3.5. More preferably, silicon oxide is SiO_2 . Herein, SiN and SiO in the following description are used to represent Si_kN_l and Si_nO_m containing layers, respectively. The silicon-containing film could also be a silicon oxide based dielectric material such as organic based or silicon oxide based low-k dielectric materials such as the Black Diamond II or III material by Applied Materials, Inc. with a formula of SiOCH . Silicon-containing film may also include $\text{Si}_a\text{O}_b\text{C}_c\text{N}_d\text{H}_e$ where a, b, c, d, e range from 0.1 to 6. The silicon-containing films may also include dopants, such as B, C, P, As, Ga, In, Sn, Sb, Bi and/or Ge.

[0035] Ranges may be expressed herein as from about one particular value, and/or to about another particular value. When such a range is expressed, it is to be understood that another embodiment is from the one particular value and/or to the other particular value, along with all combinations within said range.

[0036] Reference herein to "one embodiment" or "an embodiment" means that a particular feature, structure, or characteristic described in connection with the embodiment may be included in at least one embodiment of the invention. The appearances of the phrase "in one embodiment" in various places in the specification are not necessarily all referring to the same embodiment, nor are separate or alternative embodiments necessarily mutually exclusive of other embodiments. The same applies to the term "implementation."

Brief Description of the Drawings

[0037] For a further understanding of the nature and objects of the present invention, reference should be made to the following detailed description, taken in conjunction with the accompanying drawings, in which like elements are given the same or analogous reference numbers and wherein:

FIG. 1a is a cross-sectional side view of exemplary layers in a 3D NAND stack;

FIG. 1b is a cross-sectional side view of the exemplary layers in the 3D NAND stack showing polymer deposited on a sidewall during etching of the 3D NAND stack;

FIG. 1c is a cross-sectional side view of the exemplary layers in the 3D NAND stack showing particles generated during alternating SiO/SiN layer etching of a 3D NAND stack;

FIG. 1d is a cross-sectional side view of the exemplary layers in the 3D NAND stack showing selective etching of SiN exposed on the sidewall in the 3D NAND stack;

FIG. 2 is a cross-sectional side view of exemplary layers of a DRAM stack;

FIG. 3a is a cross-sectional side view of exemplary layers showing photoresist pattern

over SiO insulation layer surrounding typical transistor device region to produce a transistor structure;

FIG. 3b is a cross-sectional side view of the exemplary layers of **FIG. 3a** after etching the SiO insulation layer;

FIG. 4 is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with 1-C₃F₇I, O₂ and Ar;

FIG. 5 is a graph demonstrating the electron impact ionization energy (eV) versus species concentration (Torr) of C₃F₇I;

FIG. 6 is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with 1-C₄F₉I, O₂ and Ar;

FIG. 7 is 1-C₄F₉I depth profile on a-C substrate;

FIG. 8 is 1-C₄F₉I depth profile on a-C(B) substrate;

FIG. 9 is 1-C₄F₉I depth profile on a-C(W) substrate;

FIG. 10 is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with cC₄F₈; and

FIG. 11 is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with C₄F₆.

Description of Preferred Embodiments

[0038] Disclosed are methods for plasma etching semiconductor structures, such as, channel holes, gate trenches, staircase contacts, capacitor holes, contact holes high aspect ratio structures, 3D NAND, slit trenches, self-aligned contact, self-aligned vias, super vias etc., in silicon-containing films. The disclosed methods include the steps of i) introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a silicon-containing film on a substrate, wherein the iodine-containing etching compound has the formula C_nH_xF_yI_z, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, and $1 \leq z \leq 4$; and ii) introducing an inert gas into the reaction chamber; and iii) activating a plasma to produce an activated iodine-containing etching compound capable of etching the silicon-containing film from the substrate. Here the inert gas may be Ar, Kr, Xe, N₂, He or Ne.

[0039] As shown in the examples that follow, the iodide ion in the disclosed iodine-containing etching compounds dissociates from the compounds at low energies (eV) (*i.e.*, < 20 eV). As a result, Applicants believe that the disclosed etching compounds may be used in dry plasma etch processes that produce less damage to the underlying substrates because they can be performed at lower plasma energies. For example, the disclosed iodine-containing etching compounds may be particularly suitable for low k etch processes in which damage is a particular concern because lower plasma energy may produce less damage to the porous low k material surrounding the etch site. The low damage to low k material may be due to the reduced generation of UV photons and F radicals given by iodine-containing

etching compounds. The disclosed iodine-containing etching compounds may also prevent loss of the critical dimension and decrease low k surface roughness. In addition, molecules with two iodine atoms may enhance these benefits, although at a loss of volatility due to the size of the iodine atoms.

[0040] Iodine (10.5 eV) has a lower ionization threshold than Fluorine (17.4 eV) and the inert gases: Ar (15.8 eV), Xe (12.1 eV), and Kr (14 eV). Iodine may therefore be more easily ionized by the plasma than fluorine and iodine-containing etching compound may increase the plasma density. Iodine, being a heavy element (with a mass of 127 amu), may also behave similarly to the inert gases (such as Kr, with 88 amu, and Xe, with 131 amu) in the plasma and accelerate towards the wafer. During the etch of high aspect ratio structure, the energy of the ions gets weaker as they penetrate deeper, therefore many ions cannot reach the bottom of trench. However, Iodine ions being heavy may be accelerated toward the wafers by the voltage applied during the plasma etch process and penetrate deeply allowing to etch deep pattern structures with high aspect ratio. Fluorine's ionization threshold serves to maintain it as a neutral species. As a result, fluorine typically participates in the etching process via chemical reactions. Iodine exhibits less chemical reactivity than fluorine and is ionized and bombards the surface during the plasma etch process. The bond energy for C-I is also less than the bond energy for C-F, thereby causing the C-I bond to more easily break in the plasma compared to C-F bonds. Thus, iodine ions may easily be doped into a-C mask layer. Since iodine is a heavy element that makes it easier to implant and penetrate deeply in the mask layer than lighter elements. In addition, due to the weakness of the C-I bond and the fact that Iodine ionization threshold is low, the iodine containing etching compound have a low to negligible atmospheric lifetime making them good candidates to reduce the global warming potential caused by perfluorocarbon compounds.

[0041] The iodide ion dissociates from the disclosed etching compounds at low eVs (i.e., <20 eV), referring to the Comparative Example below. However, iodide ion implantation into the mask feature, such as the surface and/or the body/bulk is likely. This implantation may help to strengthen, minimize the damage, increase etch resistance of the mask feature and help it maintain its shape during the etching process. As shown in the examples that follow, after using the disclosed iodine-containing etch compound the composition of the pattern mask is modified. Applicants believe that the iodine ions modify the surface and incorporate into the bulk of the pattern mask layer by increasing the crosslinking with the organic mask layer (such as amorphous carbon mask). Due to the doping of the iodine ions and the crosslinking among carbon, iodine, hydrogen and fluorine atoms, and preferably between carbon and iodine, the density of the pattern mask layer increases, making the pattern mask layer stronger. In the examples that follow the strengthening effect and the etch resistance

improvement due to the iodine ions have been proved by showing that the etching rate of the pattern mask layer is lower when etched by iodine-containing etching compound than when is etched by the traditional etching gases, such as CCl_4F_8 and C_4F_6 .

[0042] The disclosed iodine-containing etching compounds have the formula $\text{C}_n\text{H}_x\text{F}_y\text{I}_z$, wherein $4 \leq n \leq 10$, $0 \leq x \leq 21$, $0 \leq y \leq 21$, $1 \leq z \leq 4$. When $x = 0$, the disclosed iodine-containing etching compounds may not contain any hydrogen having the formula $\text{C}_n\text{F}_y\text{I}_z$, wherein $4 \leq n \leq 10$, $0 \leq y \leq 21$, $1 \leq z \leq 4$ and $y + z \leq 2n + 2$. When $n = 4$, the disclosed iodine-containing etching compounds have the formula $\text{C}_4\text{F}_y\text{I}_z$, wherein $1 \leq z \leq 4$, $y \leq 10 - z$. Exemplary C_4 iodine-containing etching compounds without containing H include $\text{C}_4\text{F}_9\text{I}$, $\text{C}_5\text{F}_{11}\text{I}$, $\text{C}_6\text{F}_{13}\text{I}$, $\text{C}_7\text{F}_{15}\text{I}$, $\text{C}_8\text{F}_{17}\text{I}$, $\text{C}_9\text{F}_{19}\text{I}$, $\text{C}_{10}\text{F}_{21}\text{I}$, $\text{C}_4\text{F}_7\text{I}$, $\text{C}_5\text{F}_9\text{I}$, $\text{C}_6\text{F}_{11}\text{I}$, $\text{C}_7\text{F}_{13}\text{I}$, $\text{C}_8\text{F}_{15}\text{I}$, $\text{C}_9\text{F}_{17}\text{I}$, $\text{C}_{10}\text{F}_{19}\text{I}$, $\text{C}_4\text{F}_5\text{I}$, $\text{C}_5\text{F}_7\text{I}$, $\text{C}_6\text{F}_9\text{I}$, $\text{C}_7\text{F}_{11}\text{I}$, $\text{C}_8\text{F}_{13}\text{I}$, $\text{C}_9\text{F}_{15}\text{I}$, $\text{C}_{10}\text{F}_{17}\text{I}$, $\text{C}_4\text{F}_8\text{I}_2$, $\text{C}_5\text{F}_{10}\text{I}_2$, $\text{C}_6\text{F}_{12}\text{I}_2$, $\text{C}_7\text{F}_{14}\text{I}_2$, $\text{C}_8\text{F}_{16}\text{I}_2$, $\text{C}_9\text{F}_{18}\text{I}_2$, $\text{C}_{10}\text{F}_{20}\text{I}_2$, $\text{C}_4\text{F}_6\text{I}_2$, $\text{C}_5\text{F}_8\text{I}_2$, $\text{C}_6\text{F}_{10}\text{I}_2$, $\text{C}_7\text{F}_{12}\text{I}_2$, $\text{C}_8\text{F}_{14}\text{I}_2$, $\text{C}_9\text{F}_{16}\text{I}_2$, $\text{C}_{10}\text{F}_{18}\text{I}_2$, $\text{C}_4\text{F}_4\text{I}_2$, $\text{C}_5\text{F}_6\text{I}_2$, $\text{C}_6\text{F}_8\text{I}_2$, $\text{C}_7\text{F}_{10}\text{I}_2$, $\text{C}_8\text{F}_{12}\text{I}_2$, $\text{C}_9\text{F}_{14}\text{I}_2$, $\text{C}_{10}\text{F}_{16}\text{I}_2$, $\text{C}_4\text{F}_7\text{I}_3$, $\text{C}_5\text{F}_9\text{I}_3$, $\text{C}_6\text{F}_{11}\text{I}_3$, $\text{C}_7\text{F}_{13}\text{I}_3$, $\text{C}_8\text{F}_{15}\text{I}_3$, $\text{C}_9\text{F}_{17}\text{I}_3$, $\text{C}_{10}\text{F}_{19}\text{I}_3$, $\text{C}_4\text{F}_4\text{I}_3$, $\text{C}_5\text{F}_6\text{I}_3$, $\text{C}_6\text{F}_8\text{I}_3$, $\text{C}_7\text{F}_{10}\text{I}_3$, $\text{C}_8\text{F}_{12}\text{I}_3$, $\text{C}_9\text{F}_{14}\text{I}_3$, $\text{C}_{10}\text{F}_{16}\text{I}_3$, $\text{C}_4\text{F}_3\text{I}_3$, $\text{C}_5\text{F}_5\text{I}_3$, $\text{C}_6\text{F}_7\text{I}_3$, $\text{C}_7\text{F}_9\text{I}_3$, $\text{C}_8\text{F}_{11}\text{I}_3$, $\text{C}_9\text{F}_{13}\text{I}_3$, $\text{C}_{10}\text{F}_{15}\text{I}_3$, $\text{C}_4\text{F}_6\text{I}_4$, $\text{C}_5\text{F}_8\text{I}_4$, $\text{C}_6\text{F}_{10}\text{I}_4$, $\text{C}_7\text{F}_{12}\text{I}_4$, $\text{C}_8\text{F}_{14}\text{I}_4$, $\text{C}_9\text{F}_{16}\text{I}_4$, $\text{C}_{10}\text{F}_{18}\text{I}_4$, $\text{C}_4\text{F}_4\text{I}_4$, $\text{C}_5\text{F}_6\text{I}_4$, $\text{C}_6\text{F}_8\text{I}_4$, $\text{C}_7\text{F}_{10}\text{I}_4$, $\text{C}_8\text{F}_{12}\text{I}_4$, $\text{C}_9\text{F}_{14}\text{I}_4$, $\text{C}_{10}\text{F}_{16}\text{I}_4$, $\text{C}_4\text{F}_2\text{I}_4$, $\text{C}_5\text{F}_4\text{I}_4$, $\text{C}_6\text{F}_6\text{I}_4$, $\text{C}_7\text{F}_8\text{I}_4$, $\text{C}_8\text{F}_{10}\text{I}_4$, $\text{C}_9\text{F}_{12}\text{I}_4$, $\text{C}_{10}\text{F}_{14}\text{I}_4$, and their isomers.

[0043] Exemplary disclosed iodine-containing etching compounds without containing H having a general formula: $\text{C}_n\text{F}_{2n+1}\text{I}$, where $4 \leq n \leq 10$, are listed in **Table 2**. These molecules are commercially available or may be synthesized by methods known in the art. Their structure formula, CAS numbers and boiling points are included in **Table 2**. The disclosed iodine-containing etching compounds without containing H having a general formula: $\text{C}_n\text{F}_{2n+1}\text{I}$, where $4 \leq n \leq 10$, may also include their isomers.

Table 2

Etching compounds	Formula	Structure	CAS number	Boiling point (°C)
Perfluorobutyl iodide	1-C ₄ F ₉ I		423-39-2	67.0°C
Perfluoropentyl iodide	1-C ₅ F ₁₁ I		638-79-9	94.4°C
Perfluorohexyl iodide	1-C ₆ F ₁₃ I		355-43-1	115-117°C @ 1 mmHg
Perfluoroheptyl iodide	1-C ₇ F ₁₅ I		335-58-0	137-138°C

Perfluorooctyl iodide	1-C ₈ F ₁₇ I		507-63-1	160-161°C
Perfluorononyl iodide	1-C ₉ F ₁₉ I		558-97-4	181°C
Perfluorodecyl iodide	1-C ₁₀ F ₂₁ I		423-62-1	112-115°C @ 50 mmHg

[0044] The disclosed iodine-containing etching compounds are suitable for etching silicon-containing films that include a layer of silicon oxide (SiO), silicon nitride (SiN), pure silicon (Si) such as crystalline Si, poly-silicon (p-Si or polycrystalline Si), or amorphous silicon, low-*k* SiCOH, SiOCN, SiC, SiON, Si_aO_bH_cC_dN_e, where *a*>0; *b*, *c*, *d* and *e* ≥ 0, or combinations thereof. The silicon-containing film may also include alternating SiO and SiN (ONON) layers or SiO and p-Si (OPOP) layers. The silicon-containing films may also include dopants, such as B, C, P, As, Ga, In, Sn, Sb, Bi and/or Ge.

[0045] The etch rate of SiN may be enhanced while maintaining high selectivity to the mask layer when the disclosed iodine-containing etching compounds include H, but are not limited to. The disclosed iodine-containing etching compounds having one H when *x*=1 have the formula C_{*n*}HF_{*y*}I_{*z*}, wherein 4 ≤ *n* ≤ 10, 0 ≤ *y* ≤ 20, 1 ≤ *z* ≤ 4, and *y* + *z* ≤ 2*n*+1. Exemplary compounds include C₄HF₈I, C₅HF₁₀I, C₆HF₁₂I, C₇HF₁₄I, C₈HF₁₆I, C₉HF₁₈I, C₁₀HF₂₀I, C₄HF₆I, C₅HF₈I, C₆HF₁₀I, C₇HF₁₂I, C₈HF₁₄I, C₉HF₁₆I, C₁₀HF₁₈I, C₄HF₄I, C₅HF₆I, C₆HF₈I, C₇HF₁₀I, C₈HF₁₂I, C₉HF₁₄I, C₁₀HF₁₆I, C₄HF₇I₂, C₅HF₉I₂, C₆HF₁₁I₂, C₇HF₁₃I₂, C₈HF₁₅I₂, C₉HF₁₇I₂, C₁₀HF₁₉I₂, C₄HF₅I₂, C₅HF₇I₂, C₆HF₉I₂, C₇HF₁₁I₂, C₈HF₁₃I₂, C₉HF₁₅I₂, C₁₀HF₁₇I₂, C₄HF₃I₂, C₅HF₅I₂, C₆HF₇I₂, C₇HF₉I₂, C₈HF₁₁I₂, C₉HF₁₃I₂, C₁₀HF₁₅I₂, C₄HF₆I₃, C₅HF₈I₃, C₆HF₁₀I₃, C₇HF₁₂I₃, C₈HF₁₄I₃, C₉HF₁₆I₃, C₁₀HF₁₈I₃, C₄HF₄I₃, C₅HF₆I₃, C₆HF₈I₃, C₇HF₁₀I₃, C₈HF₁₂I₃,

$C_9HF_{14}I_3$, $C_{10}HF_{16}I_3$, $C_4HF_5I_4$, $C_5HF_7I_4$, $C_6HF_9I_4$, $C_7HF_{11}I_4$, $C_8HF_{13}I_4$, $C_9HF_{15}I_4$, $C_{10}HF_{17}I_4$, $C_4HF_3I_4$, $C_5HF_5I_4$, $C_6HF_7I_4$, $C_7HF_9I_4$, $C_8HF_{11}I_4$, $C_9HF_{13}I_4$, $C_{10}HF_{15}I_4$, C_4HFI_4 , $C_5HF_3I_4$, $C_6HF_5I_4$, $C_7HF_7I_4$, $C_8HF_9I_4$, $C_9HF_{11}I_4$, $C_{10}HF_{13}I_4$ and their isomers.

[0046] The disclosed iodine-containing etching compounds having two hydrogens when $x=2$ have the formula $C_nH_2F_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq y \leq 19$, $1 \leq z \leq 4$, and $y + z \leq 2n$. Exemplary compounds include $C_4H_2F_7I$, $C_5H_2F_9I$, $C_6H_2F_{11}I$, $C_7H_2F_{13}I$, $C_8H_2F_{15}I$, $C_9H_2F_{17}I$, $C_{10}H_2F_{19}I$, $C_4H_2F_5I_2$, $C_5H_2F_7I_2$, $C_6H_2F_9I_2$, $C_7H_2F_{11}I_2$, $C_8H_2F_{13}I_2$, $C_9H_2F_{15}I_2$, $C_{10}H_2F_{17}I_2$, $C_4H_2F_6I_2$, $C_5H_2F_8I_2$, $C_6H_2F_{10}I_2$, $C_7H_2F_{12}I_2$, $C_8H_2F_{14}I_2$, $C_9H_2F_{16}I_2$, $C_{10}H_2F_{18}I_2$, $C_4H_2F_4I_2$, $C_5H_2F_6I_2$, $C_6H_2F_8I_2$, $C_7H_2F_{10}I_2$, $C_8H_2F_{12}I_2$, $C_9H_2F_{14}I_2$, $C_{10}H_2F_{16}I_2$, $C_4H_2F_5I_3$, $C_5H_2F_7I_3$, $C_6H_2F_9I_3$, $C_7H_2F_{11}I_3$, $C_8H_2F_{13}I_3$, $C_9H_2F_{15}I_3$, $C_{10}H_2F_{17}I_3$, $C_4H_2F_3I_3$, $C_5H_2F_5I_3$, $C_6H_2F_7I_3$, $C_7H_2F_9I_3$, $C_8H_2F_{11}I_3$, $C_9H_2F_{13}I_3$, $C_{10}H_2F_{15}I_3$, $C_4H_2F_4I_4$, $C_5H_2F_6I_4$, $C_6H_2F_8I_4$, $C_7H_2F_{10}I_4$, $C_8H_2F_{12}I_4$, $C_9H_2F_{14}I_4$, $C_{10}H_2F_{16}I_4$, $C_4H_2F_2I_4$, $C_5H_2F_4I_4$, $C_6H_2F_6I_4$, $C_7H_2F_8I_4$, $C_8H_2F_{10}I_4$, $C_9H_2F_{12}I_4$, $C_{10}H_2F_{14}I_4$ and their isomers.

[0047] The disclosed iodine-containing etching compounds having three hydrogens when $x=3$ have the formula $C_nH_3F_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq y \leq 18$, $1 \leq z \leq 4$, and $y + z \leq 2n-1$. Exemplary compounds include $C_4H_3F_6I$, $C_5H_3F_8I$, $C_6H_3F_{10}I$, $C_7H_3F_{12}I$, $C_8H_3F_{14}I$, $C_9H_3F_{16}I$, $C_{10}H_3F_{18}I$, $C_4H_3F_4I$, $C_5H_3F_6I$, $C_6H_3F_8I$, $C_7H_3F_{10}I$, $C_8H_3F_{12}I$, $C_9H_3F_{14}I$, $C_{10}H_3F_{16}I$, $C_4H_3F_5I_2$, $C_5H_3F_7I_2$, $C_6H_3F_9I_2$, $C_7H_3F_{11}I_2$, $C_8H_3F_{13}I_2$, $C_9H_3F_{15}I_2$, $C_{10}H_3F_{17}I_2$, $C_4H_3F_3I_2$, $C_5H_3F_5I_2$, $C_6H_3F_7I_2$, $C_7H_3F_9I_2$, $C_8H_3F_{11}I_2$, $C_9H_3F_{13}I_2$, $C_{10}H_3F_{15}I_2$, $C_4H_3F_4I_3$, $C_5H_3F_6I_3$, $C_6H_3F_8I_3$, $C_7H_3F_{10}I_3$, $C_8H_3F_{12}I_3$, $C_9H_3F_{14}I_3$, $C_{10}H_3F_{16}I_3$, $C_4H_3F_2I_3$, $C_5H_3F_4I_3$, $C_6H_3F_6I_3$, $C_7H_3F_8I_3$, $C_8H_3F_{10}I_3$, $C_9H_3F_{12}I_3$, $C_{10}H_3F_{14}I_3$, $C_4H_3F_3I_4$, $C_5H_3F_5I_4$, $C_6H_3F_7I_4$, $C_7H_3F_9I_4$, $C_8H_3F_{11}I_4$, $C_9H_3F_{13}I_4$, $C_{10}H_3F_{15}I_4$, $C_4H_3F_{11}I_4$, $C_5H_3F_3I_4$, $C_6H_3F_5I_4$, $C_7H_3F_7I_4$, $C_8H_3F_9I_4$, $C_9H_3F_{11}I_4$, $C_{10}H_3F_{13}I_4$ and their isomers.

[0048] The disclosed iodine-containing etching compounds having four hydrogens when $x=4$ have the formula $C_nH_4F_yI_z$, wherein $4 \leq n \leq 10$, $0 \leq y \leq 17$, $1 \leq z \leq 4$, and $y + z \leq 2n-2$. Exemplary compounds include $C_4H_4F_5I$, $C_5H_4F_7I$, $C_6H_4F_9I$, $C_7H_4F_{11}I$, $C_8H_4F_{13}I$, $C_9H_4F_{15}I$, $C_{10}H_4F_{17}I$, $C_4H_4F_3I$, $C_5H_4F_5I$, $C_6H_4F_7I$, $C_7H_4F_9I$, $C_8H_4F_{11}I$, $C_9H_4F_{13}I$, $C_{10}H_4F_{15}I$, $C_4H_4F_4I_2$, $C_5H_4F_6I_2$, $C_6H_4F_8I_2$, $C_7H_4F_{10}I_2$, $C_8H_4F_{12}I_2$, $C_9H_4F_{14}I_2$, $C_{10}H_4F_{16}I_2$, $C_4H_4F_2I_2$, $C_5H_4F_4I_2$, $C_6H_4F_6I_2$, $C_7H_4F_8I_2$, $C_8H_4F_{10}I_2$, $C_9H_4F_{12}I_2$, $C_{10}H_4F_{14}I_2$, $C_4H_4F_3I_3$, $C_5H_4F_5I_3$, $C_6H_4F_7I_3$, $C_7H_4F_9I_3$, $C_8H_4F_{11}I_3$, $C_9H_4F_{13}I_3$, $C_{10}H_4F_{15}I_3$, $C_4H_4F_{11}I_3$, $C_5H_4F_3I_3$, $C_6H_4F_5I_3$, $C_7H_4F_7I_3$, $C_8H_4F_9I_3$, $C_9H_4F_{11}I_3$, $C_{10}H_4F_{13}I_3$, $C_4H_4F_2I_4$, $C_5H_4F_4I_4$, $C_6H_4F_6I_4$, $C_7H_4F_8I_4$, $C_8H_4F_{10}I_4$, $C_9H_4F_{12}I_4$, $C_{10}H_4F_{14}I_4$, $C_4H_4I_4$, $C_5H_4F_2I_4$, $C_6H_4F_4I_4$, $C_7H_4F_6I_4$, $C_8H_4F_8I_4$, $C_9H_4F_{10}I_4$, $C_{10}H_4F_{12}I_4$ and their isomers.

[0049] Applicants believe that the molecules having 4 or more than 4 carbon atoms may provide better etch rate and sidewall protection, e.g., straight profile, no bowing, no tapering, no twisting, no incomplete etch, no variation of critical dimension from top to bottom of the structure etched, during the etching process than less than 4 carbon molecules. Applicants believe that the molecules having 4 or more than 4 carbon atoms may also provide a straighter profile, without bowing, tapering, twisting and incomplete etch, or variation of

critical dimension from top to bottom of the structure etched than less than 4 carbon molecules. For sidewall protection, the carbon ≥ 4 molecules are preferred because Applicants believe they will produce thicker passivation layers.

[0050] The disclosed iodine-containing etching compounds may provide high selectivity to mask layers, photoresist, etch stop layers and device channel materials and no profile distortion in high aspect ratio structures (HAR), such as those having an aspect ratio ranging from 1:1 to 200:1 such as DRAM and 3D NAND structures. Alternatively, the disclosed iodine-containing etching compounds may also provide high selectivity to mask layers or silicon-containing film, such as those having an aspect ratio ranging from 1:1 to 200:1 in contact etch applications.

[0051] The disclosed iodine-containing etching compounds may provide infinite selectivity for wide process conditions of etching. Herein the selectivity refers to the etching rate ratio of two different layers. For example, the selectivity for SiO layer vs. a-C layer is the etch rate of the SiO divided by the etching rate of the a-C layer. The disclosed iodine-containing etching compounds may provide improved selectivity between the silicon-containing films and mask materials, less damage to channel region, improved critical dimension uniformity and reduced profile distortion such as bowing, twisting, tapering, notching, under-cut, maintain the same critical dimension from top to bottom of the etch structure and arcing in pattern high aspect ratio structures. The disclosed iodine-containing etching compounds may also etch through alternating layers of p-Si, SiO, and/or SiN, resulting in a vertical etch profile. (i.e., demonstrating selectivity ranging from 2:1 to 1:2 between the alternating layers). The disclosed iodine-containing etching compound plasma etches the alternating SiO and SiN (ONON) layers having a selectivity between approximately 1:2 to approximately 2:1 with respect to the SiO layer versus SiN layer. Preferably, the disclosed iodine-containing etching compound plasma etches the alternating SiO and SiN (ONON) layers having a selectivity of approximately 1:1 with respect to the SiO layer versus SiN layer.

[0052] The disclosed iodine-containing etching compounds are provided at greater than 95% v/v purity, preferably at greater than 99.99% v/v purity, and more preferably at greater than 99.999% v/v purity. The disclosed iodine-containing etching compounds contain less than 5% by volume trace gas impurities, with less than 150 ppm by volume of impurity gases, such as N₂ and/or H₂O and/or CO₂, contained in said trace gaseous impurities. Preferably, the water content in the plasma etching gas is less than 20 ppm by weight. The purified product may be produced by distillation and/or passing the gas or liquid through a suitable adsorbent, such as a 4Å molecular sieve.

[0053] The disclosed iodine-containing etching compounds contain less than 10% v/v,

preferably less than 1% v/v, more preferably less than 0.1% v/v, and even more preferably less than 0.01% v/v of any of its isomers, which may be purified by distillation of the gas or liquid to remove isomers and may provide better process repeatability.

[0054] Alternatively, the disclosed iodine-containing etching compounds may contain between 0.01% v/v and 99.99% v/v of its isomers, particularly when the isomer mixture provides improved process parameters or if isolation of the target isomer is too difficult or expensive. For example, the disclosed iodine-containing etching compounds may comprise between approximately 50% v/v and approximately 75% v/v 1-Iodononafluorobutane and between approximately 25% v/v and approximately 50% v/v 2-Iodononafluorobutane and between approximately 25% v/v and approximately 50% v/v Iodononafluoro-*t*-butane. The mixture of isomers may also reduce the need for two or more gas lines to the reaction chamber.

[0055] Some of the disclosed iodine-containing etching compounds are gaseous at room temperature and atmospheric pressure. For the non-gaseous (*i.e.*, liquid or solid) compounds, their gas form may be produced by vaporizing the compounds through a conventional vaporization step, such as direct vaporization or by bubbling with inert gas (such as N₂, Ar, He). The non-gaseous compounds may be fed in liquid state to a vaporizer where it is vaporized before it is introduced into a reactor.

[0056] The disclosed iodine-containing etching compounds are suitable for plasma etching semiconductor structures, such as, channel holes, gate trenches, staircase contacts, slits, capacitor holes, contact holes, self-aligned contact, self-aligned vias, super vias *etc.*, in the silicon-containing films. The disclosed iodine-containing etching compounds are not only compatible with currently available mask materials but also compatible with the future generations of mask materials because the disclosed iodine-containing etching compounds induce little to no damage on the mask along with good profile of high aspect ratio structures. In other words, the disclosed iodine-containing etching compounds may produce vertical etched patterns having minimal to no bowing, pattern collapse, or roughness. In order to achieve these properties, the disclosed iodine-containing etching compounds may deposit an etch-resistant polymer layer during etching to help reduce the direct impact of the oxygen and fluorine radicals during the etching process. The disclosed iodine-containing etching compounds may also reduce damage to p-Si or crystalline Si channel structure during etching.

[0057] The disclosed iodine-containing etching compounds selectively etch the silicon-containing layers from a buried landing layer or material which is a metal layer located at the bottom of the structure to be etched in most applications. The disclosed iodine-containing etching compounds do not etch metal landing layers. The buried landing layer may be an

etching stop layer or a diffusion barrier layer. Materials of the metal landing layers may be a tungsten metal worldline in a 3D NAND structure and/or another metal such as W, Cu, Al, Ru, Pt, Ti, Ta, Ni, Co, Mo, Mn, Pd, Ir, Nb, Cr, Rh, V, Au, Ag or combination thereof and/or etch stop layers such as metals or metal oxides or nitrides layer such as AlO, WO, HfO, TiO, TaO, InO, CrO, RuO, CoO, MoO, ZrO, SnO TiN, TaN, HfN, AlN, WN, MoN, NiN, NbN, CrN, RuN, CoN, ZrN, SnN or combination thereof etc. The disclosed iodine-containing etching compounds induce little to no damage to the material at bottom of the contact hole, staircase and slit (such as tungsten metal world line in a 3D NAND structure and/or other metals such as W, Cu, Al, Ru, Pt, Ti, Ta, Ni, Co, Mo, Mn, Pd, Ir, Nb, Cr, Rh, V, Au, Ag or combination thereof etc.) and/or etch stop layers such as metals or metal oxides or nitrides layer (AlO, WO, HfO, TiO, TaO, InO, CrO, RuO, CoO, MoO, ZrO, SnO TiN, TaN, HfN, AlN, WN, MoN, NiN, NbN, CrN, RuN, CoN, ZrN, SnN or combination thereof etc.). One of ordinary skill in the art will recognize that a barrier layer can also be composed of a combination of the previously mentioned metals and metals oxide and nitride, such a barrier layer being Ti/TiN, Ti/TiN/Ti, TiZrN, Ta/TaN, TaN/Cu/TaN, TaN/Ru/TaN etc. A barrier might also contained silicide (such as TiSiN, TaSiN, TiSi₂, MnSiO, etc.), phosphide (such as CuWP, NiMoP, NiP etc.), carbide (such as TaC, TaCN, WCN etc.), boride (such as NiMoB, NiB etc.) or combination thereof. Preferably, the disclosed iodine-containing etching compounds are suitably volatile and stable during the etching process for delivery into the reactor/chamber.

[0058] Material compatibility tests are important to determine if any of the disclosed iodine-containing etching compounds will react with chamber materials and degrade the performance of the chamber with short term or long term use. Key materials involved in parts of the chamber, valves, etc. include stainless steel, aluminum, nickel, PCTFE, PVDF, PTFE, PFA, PP, kalrez, viton and other metals and polymers. At times these materials are exposed to high temperatures, for example, higher than 20°C, and high pressures, for example, higher than 1 atm, which may enhance their degradation. The metrology methods may include visual inspection, weight measurement, measuring nanometer scale changes in scanning electron microscopy (SEM), tensile strength, hardness, etc.

[0059] The disclosed iodine-containing etching compounds may be used to plasma etch silicon-containing films on a substrate. The disclosed plasma etching method may be useful in the manufacture of semiconductor devices such as NAND or 3D NAND gates or Flash or DRAM memory or transistors such as fin-shaped field-effect transistor (FinFET), Gate All Around(GAA)-FET, Nanowire-FET, Nanosheet-FET, Forksheet-FET, Complementary FET (CFET), Bulk complementary metal-oxide-semiconductor (Bulk CMOS), MOSFET, fully depleted silicon-on-insulator (FD-SOI) structures. The disclosed iodine-containing etching compounds may be used in other areas of applications, such as different front end of the line

(FEOL) and back end of the line (BEOL) etch applications. Additionally, the disclosed iodine-containing etching compounds may also be used for etching Si in 3D through silicon via (TSV) etch applications for interconnecting memory to logic on a substrate and in MEMS applications.

[0060] The plasma etching method includes providing a reaction chamber having a substrate disposed therein. The reaction chamber may be any enclosure or chamber within a device in which etching methods take place such as, and without limitation, reactive ion etching (RIE), capacitively coupled plasma (CCP) with single or multiple frequency RF sources, inductively coupled plasma (ICP), or microwave plasma reactors, or other types of etching systems capable of selectively removing a portion of the silicon-containing film or generating active species. One of ordinary skill in the art will recognize that the different plasma reaction chamber designs provide different electron temperature control. Suitable commercially available plasma reaction chambers include but are not limited to the Applied Materials magnetically enhanced reactive ion etcher sold under the trademark eMAX™ or the Lam Research Dual CCP reactive ion etcher dielectric etch product family sold under the trademark 2300® Flex™. The RF power in such may be pulsed to control plasma properties and thereby improving the etch performance (selectivity and damage) further.

[0061] Alternatively, the plasma-treated reactant may be produced outside of the reaction chamber. The MKS Instruments' ASTRONi® reactive gas generator may be used to treat the reactant prior to passage into the reaction chamber. Operated at 2.45 GHz, 7kW plasma power, and a pressure ranging from approximately 0.5 Torr to approximately 10 Torr, the reactant O₂ may be decomposed into two O· radicals. Preferably, the remote plasma may be generated with a power ranging from about 1 kW to about 10 kW, more preferably from about 2.5 kW to about 7.5 kW.

[0062] The reaction chamber may contain one or more than one substrate. For example, the reaction chamber may contain from 1 to 200 silicon wafers having from 25.4 mm to 450 mm diameters. The substrates may be any suitable substrates used in semiconductor, photovoltaic, flat panel or LCD-TFT device manufacturing. Examples of suitable substrates include wafers, such as silicon, silica, glass, Ge, SiGe, GeSn, InGaAs, GaSb, InP, or GaAs wafers. The wafer will have multiple films or layers on it from previous manufacturing steps, including silicon-containing films or layers. The layers may or may not be patterned. Examples of suitable layers include without limitation silicon (such as amorphous silicon, p-Si, crystalline silicon, any of which may further be p-doped or n-doped with B, C, P, As, Ga, In, Sn, Sb, Bi and/or Ge), silica, silicon nitride, silicon oxide, silicon oxynitride, Si_aO_bH_cC_dN_e, (wherein a>0; b, c, d, e ≥ 0), Ge, SiGe, GeSn, InGaAs, GaSb, InP; mask layer materials such as amorphous carbon with or without dopants, antireflective coatings, photoresist materials,

a metal oxide, such as AlO, TiO, HfO, ZrO, SnO, TaO etc. or a metal nitride layer such as AlN, ZrN, SnN, HfN, titanium nitride, tantalum nitride etc. or combinations thereof; etch stop layer materials such as silicon nitride, polysilicon, crystalline silicon, silicon carbide, SiON, SiCN or combinations thereof, device channel materials such crystalline silicon, epitaxial silicon, doped silicon, $\text{Si}_a\text{O}_b\text{H}_c\text{C}_d\text{N}_e$, (wherein $a > 0$; $b, c, d, e \geq 0$) or combinations thereof. The silicon oxide layer may form a dielectric material, such as an organic based or silicon oxide based low-k dielectric material (e.g., a porous SiCOH film). An exemplary low-k dielectric material is sold by Applied Materials under the trade name Black Diamond II or III. Additionally, layers comprising tungsten or noble metals (e.g. platinum, palladium, rhodium or gold) may be used. Furthermore, examples of the silicon-containing films may be $\text{Si}_a\text{O}_b\text{H}_c\text{C}_d\text{N}_e$, (wherein $a > 0$; $b, c, d, e \geq 0$). Throughout the specification and claims, the wafer and any associated layers thereon are referred to as substrates.

[0063] The following are exemplary embodiments of the substrates on which the disclosed iodine-containing etching compounds may be applied to etch.

[0064] In one embodiment, a substrate **100** may include a stack of multiple layers as shown in **FIG. 1a**. **FIG. 1a** is a cross-sectional side view of exemplary layers in a 3D NAND stack to produce a 3D NAND gate. In **FIG. 1a**, a stack of seven alternative SiO/SiN (i.e., **104a/104b**) layers **104** is located on top of a silicon wafer **102** (i.e., ONON or TCAT technology). In some applications, the wafer **102** may be a buried landing layer or material, such as tungsten metal wordline in a 3D NAND structure and/or another metal such as W, Cu, Al, Ru, Pt, Ti, Ta, Ni, Co, Mo, Mn, Pd, Ir, Nb, Cr, Rh, V, Au, Ag or combination thereof etc. and/or etch stop or diffusion barrier layers such as metals or metal oxides or nitrides layer (AlO, WO, HfO, TiO, TaO, InO, WO, CrO, RuO, CoO, MoO, TiN, TaN, HfN, AlN, WN, MoN, NiN, NbN, CrN, RuN, CoN or combination thereof etc.). One of ordinary skill in the art will recognize that a barrier layer can also be composed of a combination of the previously mentioned metals and metals oxide and nitride, such a barrier layer being Ti/TiN, Ti/TiN/Ti, TiZrN, Ta/TaN, TaN/Cu/TaN, TaN/Ru/TaN etc. A barrier might also contained silicide (such as TiSiN, TaSiN, TiSi₂, MnSiO, etc.), phosphide (such as CuWP, NiMoP, NiP etc.), carbide (such as TaC, TaCN, WCN etc.), boride (such as NiMoB, NiB etc.) or combination thereof. One of ordinary skill in the art will recognize that some technologies replace the SiN layers **104b** with p-Si layers (e.g., SiO/p-Si or P-BICS technology). A hardmask layer **106** is located on the top of the seven SiO/SiN layers **104**. The hardmask layer **106** may be an amorphous carbon (a-C) hardmask layer with or without dopants. The hardmask layer **106** may be a layer of CVD, PECVD, ALD, PEALD or spin on deposited (SOD) amorphous carbon or doped amorphous carbon, silicon-containing spin on mask, or carbon-containing spin on mask. The hardmask layer **106** may contain C and H, as well as other elements, such as boron, nitrogen,

sulfur, chlorine, fluorine or metals (Al, Zr, Ti, W, Y) *etc.*, to improve etch resistance during SiO/SiN layer etch. In this case, the hardmask layer **106** is a doped a-C layer, for example, a boron-doped a-C layer, a tungsten-doped a-C layer, etc. An antireflective coating layer **108** is located on top of the hardmask layer **106**. A patterned photoresist layer **110** is located on top of the antireflective coating layer **108**. Herein, a SiON layer (not shown) may be present between the antireflective coating layer **108** and the hardmask layer **106** to transfer the pattern in photoresist layer **110** to the hardmask layer **106** to form a patterned hardmask layer. One of ordinary skill in the art will recognize that the stack of layers in the substrate **100** in **FIG. 1a** is provided for exemplary purposes only and that the disclosed iodine-containing etching compounds may be used to etch other types of stacks of layers. Furthermore, one of ordinary skill in the art will recognize that the number alternating SiO/SiN or SiO/p-Si layers **104** in the stack of the substrate **100** may vary (*i.e.*, may include more or less than the seven SiO/SiN (**104a/104b**) layers depicted).

[0065] **FIG. 1b** is a cross-sectional side view of the exemplary layers in the 3D NAND stack of **FIG. 1a** showing polymer deposited on a sidewall by etching. The disclosed iodine-containing etching compounds may produce fragments during the plasma process that are suitable for both anisotropically etching the silicon-containing films **104** and depositing an I-containing polymer passivation layer **212** on sidewalls of a structure being etched as shown in **FIG. 1b**. The difference between **FIG. 1b** and **FIG. 1a** is in **FIG. 1b** via **214** is formed in substrate **100** by plasma etching using the disclosed iodine-containing etch compounds, which also deposit the polymer passivation layer **212** on the sidewalls of the via **214**. The polymer passivation layer **212** also provides smoother sidewall, less bowing and less deformation at the bottom of the via **214**. The polymer passivation layer **212** may however be easily removed or cleaned by dry or wet etch chemistries known in the art.

[0066] **FIG. 1c** is a cross-sectional side view of the exemplary layers in the 3D NAND stack of **FIG. 1a** showing particles **316** generated during alternating SiO/SiN layer etching in a 3D NAND stack. The particles **316** generated on the sidewalls of the alternative SiO/SiN (*i.e.*, **104a/104b**) layers **104** as shown in **FIG. 1c** may be minimized by using the disclosed iodine-containing etching compounds. The difference between **FIG. 1c** and **FIG. 1b** is in **FIG. 1c** the alternative SiO/SiN exposed sidewall has particles **316** generated during plasma etching. Applicants do not believe that the disclosed iodine-containing etching compounds will generate the particles **316** shown in **Fig. 1c**.

[0067] **FIG. 1d** is a cross-sectional side view of the exemplary layers in the 3D NAND stack of **FIG. 1a** showing selective isotropic etching of the SiN layers **104b** exposed on the sidewall in the 3D NAND stack after the anisotropic etching process. The SiN exposed sidewall in stack **100** may be etched selectively as shown in **FIG. 1d** by using the disclosed

iodine-containing etching compounds to selectively break the Si-N bonds in the SiN layers **104b** over the Si-O bond in the SiO layers **104a** forming a selective sidewall SiN etch **418** on the stack of SiO/SiN layers **104** in the via **214**. The difference between **FIG. 1d** and **FIG. 1b** is in **FIG. 1d** SiN exposed on the alternative SiO/SiN sidewall is selectively etched by the disclosed iodine-containing etching compounds forming the selective sidewall SiN etch **418**. Typically, the selective sidewall SiN etch **418** is performed by wet etching using mixtures with phosphoric acid. Replacing wet etch process with dry plasma etch processes is known to greatly improve the economics of semiconductor device fabrication process since wet etching requires moving the substrate to different wet etching equipment. With the disclosed methods, all etching, including the selective sidewall SiN etch of **FIG. 1d**, may be performed in one piece of etching equipment, which may reduce the cost of the semiconductor fabrication.

[0068] In alternative embodiment, substrate **100** may include a stack of multiple layers thereon as shown in **FIG. 2**. **FIG. 2** is a cross-sectional side view of exemplary layers in a DRAM stack to produce a DRAM memory. In **FIG. 2**, a stack of four layers is located on top of a silicon wafer **102**. A hardmask layer **106** is located on top of a large SiO layer **104a**. An antireflective coating layer **108** is located on top of the hardmask layer **106**. A pattern photoresist layer **110** is located on top of the antireflective coating **108**. A SiON layer (not shown) may be present between the antireflective coating layer **108** and the hardmask layer **106** to transfer pattern in photoresist layer **110** to the hardmask layer **106**. One of ordinary skill in the art will recognize that the stack of layers in **FIG. 2** is provided for exemplary purposes only and that the disclosed iodine-containing etching compounds may be used to etch other stacks of layers, for example, for a stack where the hardmask layer **106** is replaced with a TiN layer. Furthermore, one of ordinary skill in the art will recognize that the number of layers in the stack may vary (*i.e.*, may include more or less than the layers depicted).

[0069] **FIG. 3a** is a cross-sectional side view of exemplary layers showing photoresist pattern over SiO insulation layer surrounding a typical transistor device region to produce a transistor structure. Substrate **600** may include a stack of four layers surrounding a transistor gate electrode region supported on the Silicon wafer **602** as shown in **FIG. 3a**. The transistor region shown in **FIG. 3a** includes two doped silicon regions **606** acting as source and drain. Transistor gate dielectric **614** is present underneath gate electrode **616**. The whole transistor, *i.e.*, transistor gate dielectric **614** and gate electrode **616**, is surrounded by a thin SiN layer **608** which may later act as etch stop layer during contact etch. Each transistor device region **616/606** is separated by SiO isolation regions **604** in the silicon wafer **602** to minimize electrical interference. One of ordinary skill in the art will recognize that layer **602** may be located on top of a silicon oxide layer of the Silicon on Insulator (SOI) wafer. Another SiO

layer **610** is deposited on the transistor and used to insulate any metal contact to the transistor device regions **606**. Photoresist mask **612** is used to pattern the SiO layer **610**. Etching is performed using the disclosed iodine-containing etching compounds in plasma environment. The photoresist mask **612** serves as a template to etch the SiO layer **610** and etching is stopped on the SiN layer **608** as shown in **FIG 3b**.

[0070] **FIG. 3b** is a cross-sectional side view of the exemplary layers of **FIG. 3a** after etching the SiO insulation layer. The difference between **FIG.3b** and **FIG. 3a** is in **FIG. 3b** vias **718** are formed in the SiO layer **610** through etching by the disclosed iodine-containing etching compounds. The SiO layer **610** may be etched with photoresist layer **612** as a mask layer. The mask layer may be any suitable photoresist mask materials, such as TiN, a-C and so on. The etching may be stopped at the underlying SiN layer **608**.

[0071] The disclosed iodine-containing etching compounds may also be used to etch the SiN layer **608** with different plasma conditions and different mixtures. One of ordinary skill in the art will recognize that the stack and geometry of layers in **FIG. 3a** and **FIG. 3b** is provided for exemplary purposes only and that the disclosed iodine-containing etching compounds may be used to etch other types of stacks of layers. Furthermore, one of ordinary skill in the art will recognize that the number of layers in the stack may vary (*i.e.*, may include more or less than the four layers depicted).

[0072] The vapor of the disclosed iodine-containing etching compounds is introduced into the reaction chamber containing the substrate and silicon-containing films. The vapor may be introduced to the chamber at a flow rate ranging from approximately 0.1 sccm to approximately 1 slm. For example, for a 200 mm wafer size, the vapor may be introduced to the chamber at a flow rate ranging from approximately 5 sccm to approximately 50 sccm. Alternatively, for a 450 mm wafer size, the vapor may be introduced to the chamber at a flow rate ranging from approximately 25 sccm to approximately 250 sccm. One of ordinary skill in the art will recognize that the flow rate may vary from tool to tool.

[0073] The disclosed iodine-containing etching compounds may be supplied either in neat form or in a blend with an inert gas, such as N₂, Ar, Kr, Ne He, Xe, etc., or solvent. The disclosed iodine-containing etching compounds may be present in varying concentrations in the blend. For liquid iodine-containing etching compounds, the vapor form of the iodine-containing etching compounds may be produced by vaporizing the neat or blended iodine-containing etching compound solution through a conventional vaporization step such as direct vaporization or by bubbling. The neat or blended iodine-containing etching compounds may be fed in liquid state to a vaporizer where it is vaporized before it is introduced into the reactor.

[0074] Alternatively, the neat or blended iodine-containing etching compounds may be

vaporized by passing a carrier gas into a container containing the disclosed iodine-containing etching compounds or by bubbling the carrier gas into the disclosed iodine-containing etching compounds. The carrier gas may include, but is not limited to, Ar, He, N₂, Kr, Xe, Ne and mixtures thereof. Bubbling with a carrier gas may also remove any dissolved oxygen present in the neat or blended iodine-containing etching compound solution. The carrier gas and disclosed iodine-containing etching compounds are then introduced into the reactor as a vapor.

[0075] If necessary, the container containing the disclosed iodine-containing etching compounds may be heated to a temperature that permits the iodine-containing etching compounds to be in liquid phase and to have a sufficient vapor pressure for delivery into an etching tool. The container may be maintained at temperatures in the range of, for example, approximately 0°C to approximately 150°C, preferably from approximately 25°C to approximately 100°C, more preferably from approximately 25°C to approximately 50°C. More preferably, the container is maintained at room temperature (approximately 25°C) in order to avoid heating lines to the etch tool. Those skilled in the art recognize that the temperature of the container may be adjusted in a known manner to control the amount of iodine-containing etching compound vaporized.

[0076] Additionally, the iodine-containing etching compounds are delivered in purity ranging from 95% to 99.999% by volume and may be purified with known standard purification techniques for removal of CO, CO₂, N₂, H₂O, HF, H₂S, SO₂, halides, and other hydrocarbons or hydrohalocarbons.

[0077] An inert gas is also introduced into the reaction chamber in order to sustain the plasma. The inert gas may be He, Ar, Xe, Kr, Ne, N₂, He or combinations thereof. The etching gas and the inert gas may be mixed prior to introduction to the chamber, with the inert gas comprising between approximately 0.01% v/v and approximately 99.9% v/v of the resulting mixture. Alternatively, the inert gas may be introduced to the chamber continuously while the etching gas is introduced to the chamber in pulses.

[0078] The vapor of the disclosed etching gas and inert gas are activated by plasma to produce an activated etching gas. The plasma decomposes the etching gas into radical form (*i.e.*, the activated etching gas). The plasma may be generated by applying RF or DC power. The plasma may be generated with a RF power ranging from about 25 W to about 100,000 W. The plasma may be generated remotely or within the reactor itself. The plasma may be generated in dual CCP or ICP mode with RF applied at both electrodes. RF frequency of plasma may range from 100 KHz to 1 GHz. Different RF sources at different frequency may be coupled and applied at same electrode. Plasma RF pulsing may be further used to control molecule fragmentation and reaction at substrate. One of skill in the art will recognize

methods and apparatus suitable for such plasma treatment.

[0079] A quadrupole mass spectrometer (QMS), optical emission spectrometer, FTIR, or other radical/ion measurement tools may measure the activated etching gas from the chamber exhaust to determine the types and numbers of species produced. If necessary, the flow rate of the etching gas and/or the inert gas may be adjusted to increase or decrease the number of radical species produced.

[0080] The disclosed etching gases may be mixed with other gases either prior to introduction into the reaction chamber or inside the reaction chamber. Preferably, the gases may be mixed prior to introduction to the chamber in order to provide a uniform concentration of the entering gas.

[0081] In another alternative, the vapor of the iodine-containing etching compound may be introduced into the chamber independently of the other gases, such as when two or more of the gases react or are easier to deliver independently.

[0082] In another alternative, the etching gas and the inert gas are the only two gases that are used during the etching process.

[0083] Exemplary other gases include, without limitation, oxidizers such as O₂, O₃, CO, CO₂, NO, N₂O, NO₂, H₂O, H₂O₂, COS, SO₂ and combinations thereof. The disclosed etching gases and the oxidizer may be mixed together prior to introduction into the reaction chamber.

[0084] Alternatively, the oxidizer may be introduced continuously into the chamber and the etching gas introduced into the chamber in pulses. The oxidizer may comprise between approximately 0.01% v/v to approximately 99.99% v/v of the mixture introduced into the chamber (with 99.99% v/v representing introduction of almost pure oxidizer for the continuous introduction alternative).

[0085] Other exemplary gases with which the disclosed iodine-containing etching compounds may be used include additional etching gases, such as cC₄F₈, C₄F₆, cC₅F₈, C₅F₈, C₄F₆, CF₄, CH₃F, CF₃H, CH₂F₂, C₃HF₇, C₃F₆, C₃H₂F₆, C₃H₂F₄, C₃H₃F₅, C₄HF₇, C₅HF₉, C₃F₆, C₃F₈, CF₃I, C₂F₃I, C₂F₅I, C₃F₇I, 1-iodoheptafluoropropane (1-C₃F₇I), 2-iodoheptafluoropropane (2-C₃F₇I), C₃HF₇, COS, FNO, F-C≡N, CS₂, SO₂, SF₆, trans-1,1,1,4,4,4-hexafluoro-2-butene (*trans*-C₄H₂F₆), cis-1,1,1,4,4,4-hexafluoro-2-butene (*cis*-C₄H₂F₆), hexafluoroisobutene (C₄H₂F₆), trans-1,1,2,2,3,4-hexafluorocyclobutane (*trans*-C₄H₂F₆), 1,1,2,2,3-pentafluorocyclobutane (C₄H₃F₅), 1,1,2,2-tetrafluorocyclobutane (C₄H₄F₄), and cis-1,1,2,2,3,4-hexafluorocyclobutane (*cis*-C₄H₂F₆) or combination thereof. For example, approximately 1% v/v to approximately 25% v/v of the disclosed iodine-containing etching compound may be used with a balance of C₄F₆ or cC₄F₈. As shown in the examples that follow, the combination of the disclosed iodine-containing etching compounds with conventional etch gases may result in increased etch rates while maintaining the higher

selectivity between the substrate and layer to be etched associated with the disclosed iodine-containing etching compounds.

[0086] The vapor of the disclosed iodine-containing etching compounds and the etching gas may be mixed prior to introduction to the reaction chamber. The additional etching gas may comprise between approximately 0.01% v/v to approximately 99.99% v/v of the mixture introduced into the chamber.

[0087] In one non-limiting exemplary plasma etch process, the vapor of a disclosed iodine-containing compound, such as C_4F_9I , is introduced into a 200 mm Dual CCP plasma etch tool using a controlled gas flow device. The controlled gas flow device may be a mass flow controller or a bubbler design with inert gas flow to deliver the vapor of the desired molecule. In case of high boiling point molecules, a special low pressure drop mass flow controller from Brooks Automation (No. GF120XSD), MKS Instruments, etc., may be used. The pressure of the reaction chamber is set at approximately 30 mTorr. No gas source heating may be necessary if the vapor pressure is sufficient. The distance between the two CCP electrodes is kept at 1.35 cm and the top electrode RF power is fixed at 750 W. The bottom electrode RF power is varied to analyze the performance of the molecule. The reaction chamber contains a substrate having silicon-containing films thereon, similar to those shown in **FIG. 1a**. The antireflective coating layer **108** is patterned/etched by a fluorocarbon (e.g., CF_4 and CH_2F_2) and oxygen-containing gas (e.g., O_2). The amorphous carbon mask layer is patterned/etched by an oxygen-containing gas. The SiO and SiN layers **104** are patterned by the plasma of the disclosed iodine-containing etching compounds (e.g., C_4F_9I) and Argon. Argon is independently introduced into the chamber at a 250 sccm flow rate. C_4F_9I is independently introduced into the chamber at 15 sccm. O_2 is independently introduced into the chamber and varied from 0 sccm to 20 sccm to determine optimum etching conditions. An aperture having an aspect ratio equal to or greater than 10:1 is produced, which may be used as a channel hole or contact hole or staircase etch, slit etch in 3D NAND. Similar example may be used for other stack layers as shown in **Figs 2 and 3a**.

[0088] In another non-limiting exemplary plasma etch process, C_4F_9I is introduced into a 200 mm Dual CCP plasma etch tool using a controlled gas flow device. The controlled gas flow device may be a mass flow controller. In case of high boiling point molecules, a special low pressure drop mass flow controller from Brooks Automation (No. GF120XSD), MKS Instruments, etc., may be used. The pressure of the reaction chamber is set at approximately 30 mTorr. No gas source heating may be necessary if the vapor pressure is sufficient. The distance between the two CCP electrodes is kept at 1.35 cm and the top electrode RF power is fixed at 750 W. The bottom electrode RF power is varied to analyze the performance of C_4F_9I . The reaction chamber contains a substrate **100** having a thick SiO layer **104a** thereon,

similar to the layer shown in **FIG. 2**. Prior to this process, the antireflective coating layer **108** is removed by a fluorocarbon (e.g., CF_4) and oxygen-containing gas (e.g., O_2) and the A-c mask layer **106** is removed by an oxygen-containing gas. Argon is independently introduced into the chamber at a 250 sccm flow rate. $\text{C}_4\text{F}_9\text{I}$ is independently introduced into the chamber at 15 sccm. O_2 is independently introduced into the chamber at 0-20 sccm to determine optimum etching conditions. An aperture having an aspect ratio equal to or greater than 10:1 is produced, which may be used as a contact hole in DRAM. Similar examples may be used for other stack layers as shown in **Figs 1a** and **3a**.

[0089] The silicon-containing films and the activated iodine-containing etching gas react to form volatile by-products that are removed from the reaction chamber. The a-C mask, antireflective coating, and photoresist layer are less reactive with the activated etching gas. Thus, the activated etching gas selectively reacts with the silicon-containing films to form volatile by-products.

[0090] The temperature and the pressure within the reaction chamber are held at conditions suitable for the silicon-containing film to react with the activated etching gas. For instance, the pressure in the chamber may be held between approximately 0.1 mTorr and approximately 1000 Torr, preferably between approximately 1 mTorr and approximately 10 Torr, more preferably between approximately 10 mTorr and approximately 1 Torr, and more preferably between approximately 10 mTorr and approximately 100 mTorr, as required by the etching parameters. Likewise, the substrate temperature in the chamber may range between about approximately -196°C to approximately 500°C , preferably between approximately -120°C to approximately 300°C , more preferably between approximately -100°C to approximately 50°C ; and more preferably between approximately -10°C to approximately 40°C . Chamber wall temperatures may range from approximately -196°C to approximately 300°C depending on the process requirements.

[0091] The reactions between the silicon-containing film and the activated etching gas result in anisotropic removal of the silicon-containing films from the substrate. Atoms of nitrogen, oxygen, and/or carbon may also be present in the silicon-containing film. The removal is due to a physical sputtering of silicon-containing film from plasma ions (accelerated by the plasma) and/or by chemical reaction of plasma species to convert Si to volatile species, such as SiF_x , wherein x ranges from 1-4.

[0092] The plasma activated vapor of the disclosed iodine-containing etching compounds preferably exhibits high selectivity toward the mask and etches through the alternating layers of SiO and SiN resulting in a vertical etch profile with no bowing or roughness, which is important for 3D NAND applications. Additionally, plasma activated vapor deposits polymer on sidewall to minimize feature profile deformation. For other applications, such as DRAM

and 2D NAND, for example, the plasma activated etching gas under different process conditions may selectively etch SiO from SiN. The plasma activated etching gas may selectively etch SiO and/or SiN from mask layers, such as a-C, photoresist, p-Si, or silicon carbide; or from metal contact layers, such as Cu, W, Ru, etc.; or from channel regions consisting of SiGe or polysilicon regions.

[0093] The disclosed etch processes using the disclosed iodine-containing etching compounds as the etching gases produce channel holes, gate trenches, staircase contacts, capacitor holes, contact holes, contact etch, slit etch, self-aligned contact, self-aligned vias, super vias *etc.*, in the silicon-containing films. The resulting aperture may have an aspect ratio ranging from approximately 10:1 to approximately 200:1 and a diameter ranging from approximately 5 nm to approximately 500 nm, preferably less than 100 nm. For example, one of ordinary skill in the art will recognize that a channel hole etch produces apertures in the silicon-containing films having an aspect ratio greater than 50:1.

[0094] Typical materials that need to be etched may be SiO. A process of etching SiO may be relevant to etching trenches in Borophosphosilicateglass (BPSG), Tetraethylorthosilicate (TEOS), or low deposition rate TEOS (LDTEOS). An etch stop layer may be silicon nitride or silicon oxygen nitride (SiON) or poly silicon. A mask material used may be a-C, p-Si, or photo resist materials. Herein, the disclosed iodine-containing etching compounds are applied to etch SiO, SiN, p-Si and/or a-C substrate films.

[0095] As shown in the examples that follow, evaluations of dry etching of SiO, SiN, p-Si and a-C films with the disclosed iodine-containing etching compounds show that the iodine-containing HFCs yield highest selectivity of silicon oxide to amorphous carbon, silicon nitride and p-Si than the prior art fluorocarbons. The reason for high selectivity may be attributed to the formation of low F/C iodine containing fragments during plasma dissociation of the etch gases, which results in the formation of a protective polymer film on the substrates. Additionally, the iodine is ionized and bombards the surface with the heavy I ion similar to inert gases such as Ar, Kr, and Xe. Also the iodine ionized atoms modifies the surface of the organic hard mask, by doping it and improving its etch resistance, so as to favor high aspect ratio etch. The activated iodine-containing etching compound produces iodine ions, which strengthens the patterned mask layer, thereby reinforcing and minimizing damage to a patterned mask layer while forming a patterned structure in the substrate. The etching gas results presented herein show they are not only ready for patterned structure etch process, such as contact etch process, but also may be beneficial for other etching processes on silicon or metal containing substrates, including low k etching processes. In addition, in the process of forming the patterned structure by etching with the disclosed iodine-containing etching compound, an etch resistance of the pattern mask layer may be increased by doping

iodine to the surface of the pattern mask layer, thereby modifying the surface. In this case, the iodine ions from the activated iodine-containing etching compound are implanted into the patterned mask layer (i.e., the surface and/or the body/bulk of the patterned mask layer) while etching the silicon-containing film from the substrate to form the patterned structure. Besides, the disclosed iodine-containing etching compounds are suitable for reduction of the global warming potential caused by perfluorocarbon compounds.

Examples

[0096] The following non-limiting examples are provided to further illustrate embodiments of the invention. However, the examples are not intended to be all inclusive and are not intended to limit the scope of the inventions described herein.

[0097] In the following examples, experiments were carried out with commercial LAM tool 4520XLe 200mm (CCP dual frequency plasma) or alternatively with commercial AMEC 300mm Primo SSC HD-RIE etcher. Planar wafers were purchased from Advantive Tech. Planar wafers tested are four different substrates below.

- 2um PECVD TEOS (SiO) on Si substrate;
- 2um PECVD Si₃N₄ (SiN) on Si substrate;
- 300 nm LPCVD polysilicon (poly-Si) on Si substrate; and
- 350 PECVD amorphous carbon (a-C) on Si substrate.

[0097] For planar tests, etch rate (ER) were measured using an Ellipsometer and/or scanning electron microscope (SEM) by measuring the change in etch thickness as a function of etching time. The etching experiment were performed on four 1.5 x1.5 cm² coupons having four different substrate materials including SiO, SiN, p-Si and a-C, listed above. The coupons are placed on 200 mm diameter carrier wafer and held in contact by using silicon oil or thermal paste. Alternatively, double sided carbon tape obtained from 2 spi manufacturer may have been used to stick coupons on carrier wafer.

[0098] Etching tests were performed at a pressure of 30 mTorr, source power of 750 W (27 MHz), bias power of 1500 W (2 MHz), and temperature 20°C. The feed mixture contains 250 sccm of Ar, 15 sccm of etch gas, while O₂ is varied in the range 0 to 20 sccm.

[0099] To prove the repeatability, each etching test have been repeated at least three times. Standard deviation of the average of the three measurements is shown as error bar in the chart. Subsequently, polymer composition was studied by X-Ray Photoelectron Spectroscopy (XPS).

Comparative Example

[0100] FIG. 4 is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with 1-C₃F₇I

(CAS No. 754-34-7), O_2 and Ar. In **FIG. 4**, the y-axis represents etch rates; the x-axis is O_2 flow rate in sccm; the $1-C_3F_7I$ flow rate is fixed at 15 sccm, the Ar is fixed at 250 sccm while the O_2 flow rate is varied from 0 to 20 sccm. As the O_2 flow rate raise from 0 to 20 an inversely proportional trend is observed: SiO_2 ER decreases as O_2 flow rate increase, while SiN, p-Si and a-C ERs increase as O_2 flow rate increases. Thus the highest selectivity, meaning the ratio between SiO ER and other materials ER rate is shown when no oxygen is flown. At 0 sccm of O_2 , $SiO_2/a-C$ selectivity is 38.5, $SiO_2/p-Si$ selectivity is 22, and SiO_2/SiN selectivity is 11.

[0101] **FIG. 5** is a graph demonstrating the electron impact ionization energy (eV) versus species concentration (Torr) of C_3F_7I . The dominant fragments produced at between 10 and 20 eV are CF_3 , C_3F_7 , and I.

Example 1

[0102] **FIG. 6** is a graph demonstrating etch rates of SiO, SiN, p-Si and a-C with $1-C_4F_9I$, O_2 and Ar. In **FIG. 6**, the y-axis represents etch rates; the x-axis is O_2 flow rate in sccm; the $1-C_4F_9I$ flow rate is fixed at 15 sccm, the Ar is fixed at 250 sccm while the O_2 flow rate is varied from 0 to 20 sccm.

[0103] As the O_2 flow rate raise from 0 to 20 an inversely proportional trend is observed: SiO_2 ER decreases as O_2 flow rate increases, while SiN, p-Si and a-C ERs increase as O_2 flow rate increases. Thus the highest selectivity, meaning the ratio between SiO ER and other materials ER rate is shown when no oxygen is flown. At 0 sccm of O_2 , $SiO_2/a-C$ selectivity is 71, $SiO_2/p-Si$ selectivity is 47, and SiO_2/SiN selectivity is 17. Comparing to the results of $1-C_3F_7I$ shown in **FIG. 4**, $1-C_4F_9I$ is better than $1-C_3F_7I$ both in terms of SiO_2 ER and selectivity of SiO_2 vs all the other materials tested.

[0104] Addition of iodine gives increased fragmentation for both $1-C_3F_7I$ and $1-C_4F_9I$ due to the C-I weaker bond. The lower ionization threshold of the Iodine ion bombarding the surface yields increased selectivity for etching oxide (SiO) versus a-C, poly-Si or SiN. **Table 3** is a comparison with benchmark standard etch gases cC_4F_8 and C_4F_6 , commonly used in the industry. $1-C_4F_9I$ shows higher $SiO_2/a-C$ selectivity than benchmark gases (cC_4F_8 and C_4F_6), respectively ~88% and 85% higher, and ~46% higher than $1-C_3F_7I$. $1-C_4F_9I$ shows higher SiO_2 ER than benchmark gases (cC_4F_8 and C_4F_6), respectively 8.6% and 16.4% higher, and 9% higher than $1-C_3F_7I$. **FIG. 10** and **FIG. 11** are graphs demonstrating etch rates of SiO, SiN, p-Si and a-C with cC_4F_8 and C_4F_6 , respectively.

Table 3

	SiO_2 ER [nm/min]	$SiO_2/a-C$ selectivity
--	---------------------	-------------------------

cC ₄ F ₈	585	8.7
C ₄ F ₈	535	10.7
1-C ₃ F ₇ I	580	38.5
1-C ₄ F ₉ I	640	71

Example 2

[0105] XPS data analysis after 1-C₄F₉I etching on different a-C mask layers with or without dopants.

[0106] XPS angle resolved at 75° sample tilting and depth profile were performed to analyze the polymer composition on a-C masks and benchmarked with SiO₂ substrate.

[0107] In order to simulate the polymer layer formation occurring on the top surface and on the sidewall during plasma processing etch of patterns the process condition were tuned: a-C mask, Boron-doped a-C [a-C(B)] and Tungsten-doped a-C [a-C(W)] and SiO₂ (TEOS) coupons were etched at 30 mTorr for 60 sec, source power 750 W (27 MHz), and bias power 1500W (2MHz) at the substrate. The process feed the mixture contains 125 sccm of Ar, 30 sccm of 1-C₄F₉I and no O₂. The neutrals and the active species reaching the surface stick to the surface, based on their sticking coefficient, and deposit a thin polymer layer. This thin polymer layer may be responsible for sidewall passivation and often provides the selectivity.

Table 4 to Table 6 are XPS angle resolved at 75° on different a-C layers after 1-C₄F₉I etching.

Table 4. XPS angle resolved at 75° on a-C

	BE [eV]	Atomic conc. [%]	Error [%]	Mass conc. [%]	Error [%]
O 1s	529.90	4.94	0.19	4.57	0.17
I 3d	617.50	2.07	0.03	15.22	0.21
F 1s	684.30	38.65	0.32	42.47	0.30
C 1s	282.30	54.34	0.35	37.75	0.32

Table 5. XPS angle resolved at 75° on a-C(B)

	BE [eV]	Atomic conc. [%]	Error [%]	Mass conc. [%]	Error [%]
--	---------	------------------	-----------	----------------	-----------

O 1s	529.40	4.57	0.18	4.26	0.16
I 3d	616.60	2.09	0.03	15.44	0.21
F 1s	683.50	37.38	0.38	41.38	0.33
C 1s	282.30	52.55	0.47	36.77	0.35
B 1s	184.00	3.41	0.57	2.15	0.36

Table 6. XPS angle resolved at 75° on a-C(W)

	BE [eV]	Atomic conc. [%]	Error [%]	Mass conc. [%]	Error [%]
O 1s	530.60	6.05	0.26	5.55	0.24
I 3d	617.80	1.84	0.04	13.39	0.27
F 1s	684.70	34.33	0.40	37.41	0.38
C 1s	282.80	57.39	0.45	39.53	0.42
W 4f	31.70	0.39	0.02	4.12	0.19

[0108] Superficial atomic concentration of Iodine in the 3 different a-C masks [a-C, a-C(B) and a-C(W)] is comparable: ~2%.

[0109] For XPS depth profile, large cluster ion gas Ar_{1000}^+ at 5 keV ion energy have been used, instead of monoatomic Ar^+ in order to minimize the chemical damage and avoid potential knock-on of iodine atoms during Argon sputtering, which is likely to happen during organic material sputtering, such as fluorocarbon polymer or amorphous carbon.

[0110] Depth profile on a-C substrate: Superficial atomic concentration (%) is listed in **Table 7** and **FIG. 7**. Depth profile on a-C(B) substrate: Superficial atomic concentration (%) is listed in **Table 8** and **FIG. 8**. Depth profile on a-C(W) substrate: Superficial atomic concentration (%) is listed in **Table 9** and **FIG. 9**. Superficial atomic concentration after 1- $\text{C}_4\text{F}_9\text{I}$ etch on SiO_2 substrate is listed in **Table 10**.

Table 7

C1s	F1s	O1s	I3d
64.4	22.6	10.0	1.5

Table 8

C1s	F1s	O1s	B 1s	I3d
62.0	20.5	10.7	4.0	1.6

Table 9

C1s	F1s	O1s	W 4f	I3d
62.5	23.0	10.4	0.9	1.8

Table 10

Si 2p	C1s	F1s	O1s	I3d
24.0	18.4	11.6	53.1	0.3

[0111] The disclosed iodine-containing etching compound show an interesting behavior during a-C mask etch compared to etch of Si-based materials. According to XPS data, Iodine penetrates deeply on a-C mask, similar to a doping effect, helping preserving it during etch.

- Iodine detected in all a-C, a-C(B) and a-C(W) around 2% superficially and in lower amount deeper in the bulk;
- Superficial $C_xF_yI_z$ ($x \leq 4$, $y \leq 9$, $z \leq 1$) polymer detected on all a-C masks (up to 50 sec etch);
- Iodine vs Fluorine penetration in the different a-C masks:
 - In a-C: I penetrates deeper than F (410 vs 450 sec respectively),
 - In a-C (W): I penetrates deeper than F (90 vs 45 sec respectively),
 - In a-C (B): F penetrates deeper than I (210 vs 90 sec respectively);
- In comparison Iodine almost not detected (0.3%) on SiO_2 substrate, very thin FC polymer formed only.

[0112] This example shows that Iodine ions modify the surface of the pattern mask by depositing a polymer layer composed of $C_xF_yI_z$ atoms as well as the iodine ions penetrate deep into the bulk of the pattern mask layer. Correlating the XPS data regarding the composition of pattern mask after etching with the etching data shown in the Example 1, the effect of iodine ions can be observed. The iodine-containing etching compounds help preserving the pattern mask layer by increasing the crosslinking with the organic layer, making the pattern mask stronger and increasing its etch resistance.

[0113] Although the subject matter described herein may be described in the context of illustrative implementations to process one or more computing application features/operations for a computing application having user-interactive components the subject matter is not limited to these particular embodiments. Rather, the techniques described herein may be applied to any suitable type of user-interactive component execution management methods, systems, platforms, and/or apparatus.

[0114] It will be understood that many additional changes in the details, materials, steps, and arrangement of parts, which have been herein described and illustrated in order to explain the nature of the invention, may be made by those skilled in the art within the principle and scope of the invention as expressed in the appended claims. Thus, the present invention is not intended to be limited to the specific embodiments in the examples given above and/or the attached drawings.

[0115] While embodiments of this invention have been shown and described, modifications thereof may be made by one skilled in the art without departing from the spirit or teaching of this invention. The embodiments described herein are exemplary only and not limiting. Many variations and modifications of the composition and method are possible and within the scope of the invention. Accordingly the scope of protection is not limited to the embodiments described herein, but is only limited by the claims which follow, the scope of which shall include all equivalents of the subject matter of the claims.

What is claimed is:

1. A method for forming a patterned structure, the method comprising the steps of:
introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and a patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C_4F_9I or its isomers;
activating a plasma to produce an activated iodine-containing etching compound;
and
allowing an etching reaction to proceed between the activated iodine-containing etching compound and the silicon-containing film to selectively etch the silicon-containing film from the patterned mask layer, thereby forming the patterned structure.
2. The method of claim 1, further comprising the step of introducing an oxidizer into the reaction chamber, wherein the oxidizer is selected from O_2 , O_3 , CO , CO_2 , NO , N_2O , NO_2 , H_2O , H_2O_2 , COS , SO_2 and combinations thereof.
3. The method of claim 1, further comprising the step of introducing an inert gas into the reaction chamber, wherein the inert gas is selected from the group consisting of He , Ar , Xe , Kr , Ne and N_2 .
4. The method of any of claims 1 to 3, wherein the silicon-containing film comprises a layer of silicon oxide (SiO), silicon nitride (SiN), crystalline Si , poly-silicon ($p-Si$), polycrystalline silicon, amorphous silicon, low- k $SiCOH$, $SiOCN$, SiC , $SiON$ and $Si_aO_bH_cC_dNe_e$, where $a > 0$; b , c , d and $e \geq 0$, alternating SiO and SiN (ONON) layers, alternating SiO and $p-Si$ (OPOP) layers.
5. The method of any one of claims 1 to 4, wherein an etch rate of etching the silicon oxide layer using the iodine-containing etching compound is higher than an etch rate of etching the silicon oxide layer using as an alternative etching gases cC_4F_8 , C_4F_6 , CF_4 , CH_3F , CF_3H , CH_2F_2 , and combinations thereof under the same etching conditions.
6. The method of any one of claims 1 to 4, wherein the iodine-containing etching compound plasma etches the alternating SiO and SiN (ONON) layers having a selectivity between approximately 1:2 to approximately 2:1 with respect to the SiO layer versus SiN layer.

7. The method of any one of claims 1 to 4, wherein the iodine-containing etching compound plasma etches the alternating SiO and p-Si (OPOP) layers having a selectivity between approximately 1:2 to approximately 2:1 with respect to the SiO layer versus p-Si layer.

8. The method of any one of claims 1 to 4, wherein the patterned mask layer is an amorphous carbon layer, a doped amorphous carbon layer, a photoresist layer, an anti-reflective layer, an organic planarization layer, and combinations thereof, wherein the landing layer is a metal layer, a metal oxide layer or a metal nitride layer.

9. The method of any one of claims 1 to 4, wherein the activated iodine-containing etching compound selectively etches the silicon-containing film from a landing layer located at the bottom of the silicon-containing film to be etched.

10. The method of any one of claims 1 to 4, wherein the patterned structure formed in the silicon-containing film has an aspect ratio between approximately 1:1 and approximately 200:1.

11. A method of reinforcing and/or strengthening and/or minimizing damage of a patterned mask layer while forming a patterned structure in a substrate, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C₄F₉I or its isomers; and

etching the silicon-containing film from the patterned mask layer to form the patterned structure using an activated iodine-containing etching compound formed by activating a plasma,

wherein the activated iodine-containing etching compound produces iodine ions, which are implanted into the patterned hardmask layer, thereby strengthening the patterned mask layer.

12. A method of increasing etch resistance of a patterned mask layer in a process of forming a patterned structure in a substrate, the method comprising:

introducing a vapor of an iodine-containing etching compound into a reaction

chamber containing a substrate having a silicon-containing film disposed thereon and the patterned mask layer disposed on the silicon-containing film, wherein the iodine-containing etching compound is C₄F₉I or its isomers;

activating a plasma to produce an activated iodine-containing etching compound capable of doping iodine into the patterned mask layer; and

implanting iodine ions from the activated iodine-containing etching compound into the patterned mask layer while etching the silicon-containing film from the patterned mask layer to form the patterned structure,

thereby modifying the patterned mask layer with iodine to increase the etch resistance of the patterned mask layer.