

## **ELIMINATION OF RDL USING TAPE BASE FLIP CHIP ON FLEX FOR DIE STACKING**

### **FIELD OF THE INVENTION**

5 This invention generally relates to assembling and packaging multiple semiconductor dies, and more particularly to a stacked multiple die device and methods for fabricating the device.

### **BACKGROUND OF THE INVENTION**

10 Chip-on-board and board-on-chip (BOC) techniques are used to attach semiconductor dies to an interposer or other carrier substrate such as a printed circuit board (PCB). Attachment can be achieved through flip chip attachment, wirebonding, or tape automated bonding ("TAB").

Flip chip attachment typically utilizes ball grid array (BGA) technology. The BGA component (die) includes conductive external contacts, typically in the form of solder balls or bumps, arranged in a grid pattern on the active surface of the die, which permit the die to be flip chip  
15 mounted to an interposer or other carrier substrate (e.g., PCB).

In a flip chip attachment, the balls of the BGA component are aligned with terminals on the carrier substrate, and connected by reflowing the solder balls. The solder balls can be replaced with a conductive polymer that is cured. A dielectric underfill is then interjected between the flip chip die and the surface of the carrier substance to embed the solder balls and mechanically couple the BGA  
20 component to the carrier substrate.

Wirebonding and TAB attachment generally involve attaching a die by its backside to the surface of a carrier substrate with an appropriate adhesive (e.g., epoxy) or tape. With wirebonding, bond wires are attached to each bond pad on the die and bonded to a corresponding terminal pad on the carrier substrate (e.g., interposer). With TAB, ends of metal leads carried on a flexible insulating  
25 tape such as a polyimide, are attached to the bond pads on the die and to the terminal pads on the carrier substrate. A dielectric (e.g., silicon or epoxy) is generally used to cover the bond wires or metal tape leads to prevent damage.

High performance, low cost, increased miniaturization of components, and greater packaging density of integrated circuits have long been goals of the computer industry. One method of  
30 increasing integrated circuit density while reducing package size and height is to stack dies vertically. Different approaches to packaging have been pursued to provide stacked die devices.

One such example of a stacked die to lower wire bond loop height is depicted in **FIG. 1**, shown as an encapsulated package 10 comprising a flip chip mounted on a chip-on-board ("FC-on-

chip"). As shown, the package 10 includes a flip chip 12 mounted via solder bumps 14 with the active surface 16 facing down onto the active surface 18 of a bottom die (chip-on-board) 20, which in turn, is mounted with an adhesive tape or paste 22 onto an interposer substrate 24. Bonding wires 26 connect the bond pads 28 on the bottom die 20 to lead or trace ends 30 on the interposer 24. The interposer 24 includes solder balls 32 for mounting the encapsulated package (component) 10 onto a substrate, e.g., motherboard, PCB (not shown).

Flip chip attachment has provided improved electrical performance and allowed greater packaging density. However, developments in ball grid array technology has produced arrays in which the balls are made smaller and with tighter pitches. As the balls become smaller and are set closer together, it poses problems for the mutual alignment of the conductive bumps 14 on the flip chip die 12 with the bond pads 28 on the bottom die 20, requiring a metal reroute or redistribution layer (RDL) 34 disposed as an intermediate layer on the surface of the bottom die 20. The RDL 34 effects an electrical interconnection (redistribution) between the bond pads 13 on the flip chip die 12 to the bond pads 28 on the bottom die 20 for die attachment and wire bonding to the substrate. If the bond pads 13 on the flip chip die 12 can be wafer bumped, for example, by stencil printing, electrolytic plating or electroless plating, an RDL on the flip chip die 12 may not be necessary, and the die 12 can be directly bonded to the bottom die 20 through an RDL 34 disposed on the surface of the bottom die 20, as schematically depicted in FIG. 1A, whereby the solder bumps/balls 14 on the flip chip die 12 contact the bond pads 35 of the RDL 34 on the bottom die 20. However, if the pitch of the bond pads 13 is tight, it may not be possible to wafer bump the bond pads 13 (e.g., by stencil printing, electrolytic plating, etc), and additional RDL processing on the flip chip die 12 itself may be required. The RDL 34 functions to provide electrical connection to accommodate the flip chip die 12 in either of these approaches.

Fabricating an FC-on-chip can also lead to high costs and process difficulties. For Example, a flip chip mounter is required to accurately align the top die 12 to the bottom die 20. Another drawback is that damage can occur to the active surface 18 of the bottom die 20 during an underfilling process onto the active surface 18, and a molding filler can fail to flow into voids between the dies if the gap is too small.

In view of these and other deficiencies in conventional methods for fabricating stacked die modules, improvements in fabrication methods are desirable.

### **SUMMARY OF THE INVENTION**

The present invention provides a flexible film interposer for stacking a tape base flip chip onto a second (bottom) semiconductor die, and semiconductor devices and stacked die assemblies that incorporate the interposer, and methods of fabricating the devices and assemblies for increasing semiconductor device density. In particular, the present invention relates to a stacked multi-substrate device using a combination of flip chip and chip-on-board assemblies to achieve densely packaged semiconductor devices, without the need for a redistribution layer (RDL).

In one aspect, the invention provides a flexible film interposer structured for mounting thereon first and second semiconductor die in a stacked die assembly. In one embodiment, the flexible film interposer comprises a flexible substrate comprising a first surface, a second surface, and opposing sides; a plurality of spaced apart recesses having a base and extending through the flexible substrate for receiving conductive connecting members of a first semiconductor die therein; at least one slot formed through the substrate and disposed between the recesses and a side of the substrate; and a plurality of conductive traces disposed on the second surface of the substrate, each trace extending over the slot and at least one recess, each of the recesses having a trace disposed at the base thereof.

In another embodiment, the flexible film interposer comprises a flexible substrate comprising a first surface, a second surface, and opposing sides. The first surface of the substrate is structured for mounting thereon a first semiconductor die having a plurality of spaced apart conductive connecting members disposed on an active surface, and the second surface is structured for mounting thereon a second semiconductor die having a plurality of bond pads spaced along a periphery. The substrate comprises a plurality of spaced apart recesses having a base and extending through the substrate for receiving the plurality of conductive connecting members of the first semiconductor die therein. The substrate further comprises one or more slots extending therethrough and along a periphery of the substrate, wherein when the second semiconductor die is mounted onto the second surface of the substrate the bonding pads are exposed through the slots. The flexible film interposer can further comprise a plurality of conductive traces disposed on the second surface of the substrate, each trace extending over the slot and at least one recess, each of the recesses having a trace disposed at the base thereof.

The flexible film interposer preferably comprises a flexible polyimide film (e.g., a flex tape), having a thickness in the range of about 12.5  $\mu\text{m}$  to about 200  $\mu\text{m}$ . The slots are sized and configured to receive a bonding tool therethrough to contact bond pads of a semiconductor die

mounted on the second surface of the interposer and exposed through the slots. An adhesive element such as a double-sided adhesive tape, can be disposed on the first and/or the second surface of the substrate to adhere the semiconductor die thereto.

In another aspect, the invention provides a semiconductor device. In one embodiment, the semiconductor device comprises a flexible film interposer according to the invention and a first semiconductor die mounted thereon, the die having a first active surface and a second surface, and the active surface comprising a plurality of spaced apart conductive connecting members. The first semiconductor die is mounted on the flexible film interposer such that a conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess, and the slots on the first surface of the substrate are exposed. An underfill encapsulation material can be disposed between the active surface of the first semiconductor die and the first surface of the flexible film interposer. The semiconductor device can further include an adhesive element such as an adhesive paste or tape, disposed between the active surface of the semiconductor die and the flexible film interposer.

In another aspect, the invention provides a stacked die assembly. In one embodiment, the assembly comprises a flexible film interposer according to the invention having first and second semiconductor dies mounted on the first and second surfaces, respectively, of a flexible substrate. The first semiconductor die is mounted onto the first surface of the flexible film interposer using a conventional die attacher or a flip chip attacher such that each of a plurality of conductive connecting members of the die is received in each of a plurality of spaced apart recesses of the interposer in conductive contact with a trace at the base of the recess. The first (active) surface of the second semiconductor die is mounted onto the second surface of the flexible film interposer with bond pads on the active surface of the die exposed through the slot(s) of the flexible film interposer. An interposer substrate comprising terminal pads on a first surface, is mounted onto the second surface of the second semiconductor die with the terminal pads exposed. The traces exposed through the slots of the flexible film interposer and the underlying bond pads of the second semiconductor die are bonded to the terminal pads of the interposer substrate, for example, by wire bonding or TAB bonding. An underfill encapsulation material can be disposed between the active surface of the first semiconductor die and the first surface of the flexible film interposer. The interposer substrate can comprise a flexible material such as a polyimide substrate, or a non-flexible substrate such as bismaleimide triazine (BT) resin, FR4 fiberglass laminate, FR5 laminate, or ceramic. The interposer substrate can also comprise external contacts such as conductive solder balls, to form the stacked die assembly as a component that can be coupled to an external circuitry

such as a testing apparatus. In another embodiment, the interposer substrate can comprise, for example, a PCB substrate, or a motherboard. The stacked die assembly can also be encapsulated to form a package.

In yet another aspect, the invention provides a semiconductor package. In one embodiment, the package comprises an encapsulated stacked die assembly, which comprises first and second semiconductor dies mounted on a flexible film interposer according to the invention, with the second (bottom) die being mounted on an interposer substrate.

In a further aspect, the invention provides a method of fabricating a semiconductor device. In one embodiment, the method comprises the steps of: providing a flexible film interposer, the interposer comprising a first surface and a second surface, at least one elongate slot formed through and along a peripheral edge of the interposer to expose bond pads on a second semiconductor die mounted onto the second surface of the interposer, a plurality of spaced recesses formed through the interposer and adjacent the slot, each recess having a base, and a plurality of conductive traces disposed on the second surface of the interposer, each trace extending across and exposed through the slot and the base of one or more adjacent recesses in a perpendicular orientation to the slot; and mounting a first semiconductor die on the first surface of the flexible film interposer, the first semiconductor die having an active surface comprising a plurality of spaced conductive connecting members, and mounted on the interposer such that a conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess.

In another aspect, the invention provides a method of fabricating a stacked die assembly. In one embodiment, the method comprises the steps of: providing a flexible film interposer, according to the invention; mounting a first semiconductor die on the first surface of the flexible film interposer, the first semiconductor die having an active surface comprising a plurality of spaced conductive connecting members, and mounted on the interposer such that a conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess; mounting a second semiconductor die on an interposer substrate, the second semiconductor die comprising a first active surface and a second surface, the active surface comprising a bond pad, and the interposer substrate comprising a first surface with terminal pads disposed thereon, and mounted onto the second surface of the second semiconductor die with the terminal pads exposed; mounting the second semiconductor die onto the second surface of the flexible film interposer with the bond pads of the second die exposed through the slot of the interposer; and bonding the traces of the flexible film interposer and the bond pads of the second semiconductor die to the terminal pads of the interposer substrate. Either or both of the steps of

mounting the first and second semiconductor die on the flexible film interposer can further comprise applying an adhesive element to the surface of the flexible film interposer and/or the surface of the die. The step of bonding can comprise forming contacts in the slots of the flexible film interposer and over the traces and the bond pads of the second semiconductor die, and extending bonding wires from the solder ball contacts to the terminal pads on the interposer substrate. The method can further comprise the step of encapsulating the stacked die assembly to form a semiconductor package.

The invention advantageously improves the interconnection between a die component and a carrier substrate such as an interposer or PCB, and eliminate the need for a metal re-distribution layer (RDL). The invention also provides a package with a reduced total assembly height. The invention additionally eliminates problems associated with prior art underfilling and alignment processes.

### **BRIEF DESCRIPTION OF THE DRAWINGS**

Preferred embodiments of the invention are described below with reference to the following accompanying drawings, which are for illustrative purposes only. Throughout the following views, the reference numerals will be used in the drawings, and the same reference numerals will be used throughout the several views and in the description to indicate same or like parts.

**FIG. 1** is a cross-sectional, side elevational view of a prior art embodiment of a stacked die package comprising a flip chip mounted on an RDL on a chip-on-board. **FIG. 1A** is a top plan view of an embodiment of the bottom die of **FIG. 1** (with the top die removed), illustrating an RDL.

**FIG. 2** is a top plan view of an embodiment of a flexible film interposer according to the invention.

**FIG. 3** is a bottom plan view of the flexible film interposer of **FIG. 2**. **FIG. 3A** is a bottom plan view of an embodiment of the interposer of **FIG. 2**, having a soldermask layer disposed over the traces.

**FIG. 4** is a cross-sectional, side elevational view of the flexible film interposer of **FIG. 2**, taken along line 4-4. **FIG. 4A** is a cross-sectional, side elevational view of the interposer depicted in **FIG. 3A**, taken along line 4A-4A.

**FIGS. 5-11** illustrates sequential processing steps showing fabrication of a stacked die package according to an embodiment of a method of the invention. **FIGS. 5A-5B** illustrate other embodiments of the step of mounting a flip chip onto an interposer, the embodiment of the flip chip die having a single row of bumps and the interposer having a corresponding row of recesses.

**FIG. 12** is a cross-sectional, side elevational view of a second embodiment of a stacked die package fabricated according to the invention.

### **DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS**

The invention will be described generally with reference to the drawings for the purpose of illustrating embodiments only and not for purposes of limiting the same. The figures illustrate processing steps for use in fabricating semiconductor devices in accordance with the present invention. It should be readily apparent that the processing steps are only a portion of the entire fabrication process.

The invention provides a flexible film interposer for stacking a tape base flip chip onto a second (bottom) die. Recesses are fabricated in the flexible film interposer for the first level interconnect using conventional die mount equipment. The flexible film interposer includes features to interconnect to the second die without the need for an RDL on the second die.

Referring to **FIGS. 2-4**, an embodiment of a flexible film interposer 36' according to the invention is depicted in a simplified top plan view. The flexible film interposer 36' can be formed from known insulating polymeric materials, for example, a flex tape. In preferred implementations, the interposer 36' comprises a flexible polyimide film (e.g., KAPTON from DuPont, Wilmington, Delaware, or UPILEX from Ube Industries, Ltd., Japan) having a thickness in the range of about 12.5  $\mu\text{m}$  to about 200  $\mu\text{m}$ , with thicknesses in the range of about 12.5  $\mu\text{m}$  to about 50  $\mu\text{m}$  being preferred.

According to the invention, the flexible film interposer 36' comprises slots or recesses 38' to facilitate a first level interconnection to the bottom die (not shown) by means of TAB or conventional wire bonding. The interposer 36' also includes multiple recesses or vias 40' for first level interconnection of the top die in a flip chip attachment.

The recesses 38', 40' can be formed through a first (upper) surface 42' of the flexible film interposer 36' by a method known in the art and appropriate to the material employed for the flexible film interposer 36', for example, patterning and utilizing a chemical wet etch or dry etch, mechanical drilling or punching, and laser ablation.

Each of the recesses 38', 40' extend to a bond pad 44' in the form of a conductive trace formed on the second (lower) surface 46' of the interposer 36'. Such traces 44' can be formed by etching a conductive layer disposed on the lower surface 46' of the interposer, or by printing traces onto the lower surface using conductive ink. Preferably, traces 44' comprising copper or a copper alloy are utilized.

As shown in a bottom plan view in **FIG. 3**, the recesses 38' are depicted in the form of a slot with the traces 44' extending thereover. The recesses (slots) 38' are sized and configured to adequately receive therethrough a conventional bonding tool for tape automated bonding (TAB) or wire bonding, typically with a width of about 50  $\mu\text{m}$  to about 2 mm. The recesses 38' can be formed in any suitable shape, such as square, rectangular, oval, and circular, and may include tapered side walls.

The multiple recesses (vias) 40' are formed in the flexible film interposer 36' in a preselected pattern and having a predetermined size and shape to correspond with a bond pad configuration formed on an active surface of a semiconductor die intended to be attached thereto. The recesses 40' can be formed with tapered sidewalls (**FIG. 4**) or straight (vertically oriented) sidewalls (**FIG. 5A**), as desired. The conductive traces (bond pads) 44' extend over each of the recesses 40' at the base 48' thereof. Optionally, as shown in **FIGS. 3A-4A**, a soldermask layer 49" can be formed over the traces 44' to provide an overlying insulation layer. Typically, the soldermask comprises a photoimageable dielectric material that can be blanket deposited as a wet or dry film, exposed through a mask, developed and then cured.

The spaced apart recesses 40' are formed in the flexible film interposer 36' in a preselected pattern to correspond with the bond pads and bump configuration of the die (flip chip) to be attached to the interposer 36'. For example, **FIG. 2** depicts the multiple recesses 40' in a centrally positioned, four-row configuration in the flexible film interposer 36'. Such configuration is made to correspond and receive bumps of a bumped semiconductor die (flip chip) having, for example, centrally positioned, four-row bump configuration which will be more fully illustrated and described hereafter. Other patterns of the multiple recesses (vias) 40' can also be utilized to match with a particular bump configuration. For example, **FIGS. 5A-5B** illustrate another embodiment of an interposer 36", 36'" having a centrally located single row of recesses 40", 40'" to correspond with a single row of conductive bumps 60", 60'" on the die 54", 54'". In addition, the multiple recesses 40' can be formed in any suitable shape including, for example, square, rectangular, oval, and circular, and can include tapered side walls as shown, such that the openings of the recesses 40' are larger than the bases.

Optionally, an adhesive element 50', 52' can be disposed, respectively, on the first (upper) surface 42' and/or the second (lower) surface 46' of the flexible film interposer 36'. The adhesive elements 50', 52' can be utilized to secure a top (flip chip) die and a bottom die, respectively, to the flexible film interposer 36'. The adhesive elements 50', 52' can comprise any suitable adhesive material known in the art, including contact adhesives, thermoplastic adhesives and thermosetting

adhesives, for example, an adhesive gel or paste such as a conventional epoxy or polyimide die bonding adhesive, and/or a double-sided adhesive tape such as polyimide. Adhesive element 50' can have a thickness such that it functions as a spacer to control the degree of insertion of conductive bumps carried on the top die into recesses 40'. Although not shown, adhesive element 52' can extend  
 5 onto the traces 44'. The flexible film interposer 36' can be provided in a pre-taped form with an adhesive tape attached thereto, or the adhesive elements 50', 52' can be applied to the flexible film interposer 36' during fabrication of a stacked die assembly or package. In another embodiment (not shown), the adhesive elements 50', 52' can be applied to the active surfaces of the semiconductor die to be attached to the flexible film interposer 36'. Many suitable adhesive application methods for  
 10 liquid or gel adhesive application are known in the art, such as screen printing, roller applicator, spray, and transfer. Similarly, an adhesive tape may be applied from a dispenser and severed from a roll of tape, or applied from a transfer (carrier) film.

**FIGS. 5-11** illustrate an embodiment of a method of forming a stacked die package according to the invention utilizing the flexible film interposer 36'.

15 **FIGS. 5-7** depicts simplified cross-sectional views of the mounting and bonding of the flexible film interposer 36' to a semiconductor die 54' in a flip chip attachment. As shown in **FIG. 5**, the first (upper) surface 42' of the flexible film interposer 36' is aligned with and facing the active surface 56' of the die 54' prior to assembly. The active surface 56' includes a plurality of bond pads 58' with conductive bumps 60' mounted thereon, which are arranged in a predetermined  
 20 configuration. Recesses 40' in the flexible film interposer 36' are sized and configured to correspond to the configuration of the bond pads 58' and the conductive bumps 60'. The conductive bumps 60' typically comprise a metal or alloy such as copper, silver or gold, or a conductive polymer material, and can be formed by known methods in the art, for example, electroplating, metal stud bumping by wire bonders, and stenciling.

25 **FIG. 6** shows the flexible film interposer 36' mounted to the die 54' in a flip chip attachment to form a die/interposer assembly 62', whereby each of the conductive bumps 60' is inserted into a corresponding recess 40' of interposer 36' and engage with the traces (bond pads) 44' at the base 48' of each of the recesses 40'. The die 54' can be attached to the flexible film interposer 36' by the optional adhesive element 50' (e.g., tape, non-conductive die attach paste) disposed on the first  
 30 (upper) surface of the flexible film interposer 36', or on the active surface 56' of the die 54'. The conductive bumps 60' in the form of solder bumps can be reflowed to fill the recesses (vias) 40' and physically and electrically bond with the traces (bond pads) 44', or cured in the case of conductive polymer bumps, although other methods such as thermal compression can also be used. The

conductive bumps 60' can also be connected to the traces (bond pads) 44' by means of a conductive paste (not shown) such as a eutectic solder or conductive epoxy, that is applied onto the bumps 60' or into the recesses 40' to provide electrical contact between the bumps 60' and the traces 44', with the bumps 60' then reflowed or cured.

5 As depicted in **FIGS. 6-7**, a dielectric underfill encapsulation material 64' as known in the art, such as an epoxy or silicone compound, can be applied between the active die surface 56' and the upper surface 42' of the flexible film interposer 36' to reinforce the connection between the die 54' to the flexible film interposer 36' and protect the bump connections from contamination. Preferably, the underfill material 64' is applied by capillary action under pressure, using a dispensing needle 66'  
10 as known in the art, whereby the fill material is dispensed around the perimeter of the die 54' and allowed to flow beneath the die to fill the space between the active surface 56' of the die and the upper surface 42' of the interposer 36'. Other known methods of underfilling include gravity and vacuum injecting the underfill material. The dielectric material can be cured through a chemical reaction, or by the application of UV light or other radiation and/or heat.

15 Instead of utilizing the above-described underfill process (**FIGS. 6-7**), a non-flow underfill material can be deposited into the recesses of the flexible film interposer 36' and the flip chip die 54' mounted thereon. For example, as shown in **FIG. 5A**, a non-flowable underfill material 64" such as a thermoset or thermoplastic polymer, typically in paste form, can be deposited into the recess 40" of the interposer 36", and the flip chip die 54" can then be die mounted onto the interposer 36" with the  
20 conductive bumps 60" inserted into underfill 64" in the recesses 40", optionally, with the additional use of a tape adhesive 50" (and/or paste adhesive as desired) applied to the surface 42" of the interposer. In the embodiment of the interposer 36" shown in **FIG. 5A**, a conductive bump 65" can be optionally disposed in the recess 40" over the traces 44" to facilitate electrical contact between the bumps 60" of the flip chip die 54" with the traces 44". **FIG. 5A** also illustrates an embodiment of a  
25 flip chip die 54" having a single row of conductive bumps 60" and an interposer 36" having recesses 40" in a corresponding single row.

In another embodiment, as shown in **FIG. 5B**, a non-conductive film and/or paste (e.g., NCF film) 50"" can be applied over the upper surface 42"" of the interposer 36"", and the flip chip die 54"" then die mounted onto the interposer 36"". The film and/or paste 50"" allows the conductive bumps  
30 60"" of the flip chip die to penetrate therethrough. Optionally, a non-flowable underfill material can be deposited in the recesses 40"" of the interposer 36"" prior to applying the film and/or paste 50"". Similar to **FIG. 5A**, conductive bumps 66"" are disposed within the recesses 40"" for contact between the bumps 60"" on the flip chip 54"" and the traces 44"".

The flexible film interposer and top die assembly 62' is then mounted onto a second (lower) die 68' that has been mounted onto an interposer substrate 70' in a chip-on-board (COB) assembly 72' to form the stacked die assembly 74'. As shown in **FIG. 8**, the second (lower) surface 46' of the flexible film interposer 36' is aligned with and facing the active surface 76' of the second (lower) die 68' prior to assembly. The interposer/top die assembly 62' and the COB assembly 72' can be bonded together using techniques known and used in the art, such as by tape adhesive and/or epoxy adhesive, and the like.

A conventional assembly process can be used to prepare the COB assembly 72'. As shown, an active surface 76' of the second die 68' includes bond pads 78' along the periphery thereof. The interposer substrate 70' includes terminal pads 80' on the first (upper) surface 82'. The die 68' has been surface mounted onto the first (upper) surface 82' of the interposer substrate 70' by means of an adhesive element 84', which can comprise any suitable dielectric adhesive known in the art, and be of any suitable form, for example, with a tape adhesive or die attach paste, as described with respect to adhesive elements 50', 52'.

In the illustrated embodiment in **FIG. 9**, the interposer substrate 70' is structured to couple the chip package 98' (**FIG. 9**) as a component to an electrical apparatus such as a PCB or other external circuitry (not shown) such as a motherboard of a computer, program logic controller (PLC), a testing apparatus, among others. Typical interposers 70' for coupling semiconductive devices to an electrical apparatus are comprised of a flexible laminated polymer or polyimide layer, or a non-flexible material such as a bismaleimide triazine (BT) resin, FR4 fiberglass laminate, FR5 laminate, or ceramic. Such interposer substrates 70' typically include a variety of conductive vias (not shown) that extend through the cross-section of the substrate and establish routing of the conductive elements through the substrate 70', and further include electrically conductive metal lines or traces and pads formed on the second (bottom) surface 86' for electrical connection to an external electrical apparatus (not shown). External contacts 88' in the form of conductive solder balls (or other suitable conductive material such as conductive epoxies or conductor-filled epoxies), columns, pins, and the like, are used to connect the pads on the bottom surface 86' of the interposer substrate 70' to the electrical apparatus.

In another embodiment, the interposer substrate 70' can comprise a PCB substrate, motherboard, or other like substrate, whereby the top die/interposer assembly 62' and bottom die 68' are mounted directly thereon, and external contacts 88' are omitted. This structure functions as a board level device such as a module or a motherboard.

Referring to **FIG. 8**, in mounting the assemblies 62', 72', the traces (bond pads) 44' in the recesses 38' are aligned with corresponding bond pads 76' of the bottom die 68'. Conventional assembly devices such as aligner bonder tools (e.g., LOC mounter) can be used to align and then bond the bottom die 68' to the flexible film interposer 36'. A split optics system can also be used to view aligned portions of the die and the substrate.

**FIGS. 9-10** depict the assemblies 62', 72' mounted to form a stacked die assembly 74'. Wire bonding or TAB bonding is performed to join the traces (bond pads) 44' to the bond pads 78' of the bottom die 68', and to the terminal pads 80' on the interposer substrate 70'. The recesses 38' are sized to permit access for a bonding tool such as a wire bond capillary (not shown), to the bond pads 78' of the bottom die 68'. The bonding tool can be configured, for example, for thermosonically bonding, thermocompression bonding, tape-automated bonding (TAB), or other method known in the art.

In the illustrated example in **FIG. 9**, thermosonic bonding with a ball bond 90' is used. Ball bonds 90' are formed in the recesses 38' over the traces (bond pads) 44' and the bond pads 78' of the bottom die 68', thus joining the bond pads 44', 76' together in one operation, as best seen in **FIG. 11**. The bond wires 92' are extended and bonded to the terminal pads 80' on the interposer substrate 70'. The ball bonds 90' function to bond together the flexible film interposer 38', the bottom die 68' and the interposer substrate 70'. In other embodiments, TAB bonding and ultrasonic bonding, as known and used in the art, can be used to connect the traces 44" and the bond pads 78".

Referring again to **FIG. 9**, the wire-bonded stacked die assembly 82' can be partially or fully encapsulated with a dielectric encapsulation material 96' using known techniques in the art to form an encapsulated stacked die package 98', for example, by spin-coating, glob-top, pot molding, and transfer molding.

The method can be utilized to fabricate an assembly comprising additional stacked die layers, such as the embodiment depicted in **FIG. 12**. As shown, a semiconductor die 100" has been surface mounted by means of an adhesive element 102" onto the second (inactive) surface 104" of the die (flip chip) 54". Additional die 116" mounted on a flexible film interposer 118" having recesses 38" (assembly 120") can be mounted on the die 100" and bonded to the interposer 70" as described hereinabove. Bond pads 106" can then be bonded as described previously to terminal pads 112" on the interposer substrate 70". Further dies can be added to the stacked die assembly by alternating a surface mounted die (100") and a flip chip/flexible film interposer assembly (120").

The flexible film interposer of the invention functions to redistribute and connect the bond pads of the bottom die to bond pads of the upper (flip chip) die, advantageously replacing the RDL

(34) required in a conventional flip chip attachment, as in **FIG. 1**, and at less cost than a conventional RDL. In addition, the design of the flexible film interposer including the relatively large size of the recesses (vias) provides improved accuracy with mounting the upper (flip chip) die to the bottom die, being readily achievable using a conventional die mounting device. Further, the recesses (slots) are sized to readily receive a bonding tool therethrough to bond the traces and bond pads on the bottom die to an interposer carrier substrate in one operation.

In addition, the present package achieves a desirably low package profile. The package design also utilizes conventional underfill processes that are carried out on the surface of the flexible interposer substrate rather than the active surface of the bottom die, thus reducing yield and process difficulties.

In compliance with the statute, the invention has been described in language more or less specific as to structural and methodical features. It is to be understood, however, that the invention is not limited to the specific features shown and described, since the means herein disclosed comprise preferred forms of putting the invention into effect. The invention is, therefore, claimed in any of its forms or modifications within the proper scope of the appended claims appropriately interpreted in accordance with the doctrine of equivalents.

**WHAT IS CLAIMED IS:**

1. A flexible film interposer, comprising:
  - a flexible substrate comprising a first surface, a second surface, and opposing sides;
  - a plurality of spaced apart recesses extending through the flexible substrate having a base at the second surface of the flexible substrate, each recess sized and configured to receive therein a conductive connecting member disposed on an active surface of a first semiconductor die when flip-chip mounted on the first surface of the flexible substrate;
  - a slot formed through the substrate and disposed adjacent to at least one of the sides of the substrate; the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second semiconductor die when mounted on the second surface of the flexible substrate; and
  - a plurality of conductive traces disposed on the second surface of the substrate, each trace extending over the slot and at least one recess, each of the recesses having a trace disposed at the base thereof.
2. The flexible film interposer of Claim 1, comprising an insulating polymeric material.
3. The flexible film interposer of Claim 2, comprising a flexible polyimide film.
4. The flexible film interposer of Claim 1, having a thickness in the range of about 12.5  $\mu\text{m}$  to about 200  $\mu\text{m}$ .
5. The flexible film interposer of Claim 1, wherein the traces comprise copper or a copper alloy.
6. The flexible film interposer of Claim 1, wherein a slot is disposed adjacent to opposing sides of the substrate.
7. The flexible film interposer of Claim 1, wherein the slot has a width of about 50  $\mu\text{m}$  to about 2 mm.
8. The flexible film interposer of Claim 1, wherein the slot is shaped as a square, rectangle, circle, or oval.

9. The flexible film interposer of Claim 1, wherein the recesses comprise tapered side walls.
10. The flexible film interposer of Claim 1, wherein the recesses comprise vertically oriented sidewalls.
11. The flexible film interposer of Claim 1, wherein the recesses are arranged in a pattern corresponding to a bond pad configuration on an active surface of a semiconductor die to be attached thereto.
12. The flexible film interposer of Claim 1, wherein the recesses are shaped as a square, rectangle, circle, or oval.
13. The flexible film interposer of Claim 1, wherein the slot comprises tapered side walls.
14. The flexible film interposer of Claim 1, wherein the slot comprises vertically oriented sidewalls.
15. The flexible film interposer of Claim 1, further comprising an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.
16. The flexible film interposer of Claim 15, wherein the adhesive element comprises a contact adhesive, thermoplastic adhesive, or a thermosetting adhesive.
17. The flexible film interposer of Claim 15, wherein the adhesive element comprises an adhesive gel or paste.
18. The flexible film interposer of Claim 15, wherein the adhesive element comprises a double-sided adhesive tape.

19. The flexible film interposer of Claim 15, wherein the adhesive element is disposed on the second surface of the flexible substrate and over a portion of the traces.
20. The flexible film interposer of Claim 1, comprising two discrete areas of recesses with an adhesive element disposed therebetween on the first surface of the flexible substrate.
21. The flexible film interposer of Claim 1, further comprising a soldermask disposed over the traces.
22. A flexible film interposer, comprising:  
a flexible substrate having a first surface and a second surface;  
an elongate slot extending through the flexible substrate adjacent to at least one side of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a semiconductor die when mounted on the second surface of the flexible substrate;  
a plurality of recesses extending through the flexible substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and sized and configured to receive therein a conductive connecting member disposed on an active surface of a semiconductor die in a flip-chip attachment onto the first surface of the flexible substrate; and  
a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending over and exposed through the slot and the base of at least one of the recesses, each recess having a trace disposed at the base thereof.
23. The flexible film interposer of Claim 22, wherein an elongate slot is disposed adjacent to two or more sides of the interposer.
24. A flexible film interposer, comprising:  
a flexible substrate having a first surface and a second surface;  
an elongate slot extending through the flexible substrate adjacent to at least one side of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a semiconductor die when mounted on the second surface of the flexible substrate;

a plurality of recesses extending through the flexible substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and sized and configured to receive therein a conductive connecting member disposed on an active surface of a semiconductor die in a flip-chip attachment onto the first surface of the interposer; and

a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending over and exposed through the slot and one of the recesses.

25. The flexible film interposer of Claim 24, wherein an adhesive element is disposed on the first surface, the second surface, or both surfaces of the flexible substrate.

26. The flexible film interposer of Claim 25, wherein an adhesive element is disposed on the second surface of the flexible substrate over a portion of the traces.

27. A flexible film interposer, comprising:

a flexible substrate having a first surface and a second surface; and

an elongate slot extending through the flexible substrate, and positioned along a peripheral edge of at least one side of the interposer to expose bond pads on a die mounted onto the second surface of the flexible substrate, the slot sized and configured to receive a bonding tool therein to contact said bond pads;

a plurality of recesses extending through the flexible substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and sized and configured to receive therein a connecting member disposed on an active surface of a die mounted in a flip-chip attachment onto the first surface of the flexible substrate; and

a plurality of conductive traces disposed on the second surface of the flexible substrate each trace extending across and exposed through the slot and the base of one or more adjacent recesses in a perpendicular orientation to the slot.

28. The flexible film interposer of Claim 27, comprising at least two elongate slots positioned along opposing peripheral edges of the interposer.

29. The flexible film interposer of Claim 27, wherein the recesses are arranged in a pattern corresponding to a bond pad configuration on an active surface of a semiconductor die to be attached to the first surface of the flexible substrate of the interposer in a flip-chip attachment.
30. The flexible film interposing of Claim 27, further comprising a soldermask disposed over the traces.
31. The flexible film interposer of Claim 30, further comprising an adhesive element disposed over the soldermask.
32. A flexible film interposer, comprising:  
a flexible substrate having a first surface and a second surface;  
an elongate slot extending through the flexible substrate along a peripheral edge of at least one side of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a semiconductor die when mounted on the second surface of the flexible substrate;  
a plurality of spaced apart recesses extending through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate; and structured to receive therein a bumped contact disposed on an active surface of a die flip-chip mounted on the first surface of the flexible substrate;  
a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slot, each trace extending across and exposed through the slot and the base of at least one recess, each of the recesses having a trace disposed at the base thereof.
33. A flexible film interposer, comprising:  
a flexible substrate having a first surface and a second surface;  
an elongate slot extending through the flexible substrate along a peripheral edge of at least one side of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a semiconductor die when mounted on the second surface of the flexible substrate;

a plurality of spaced apart recesses extending through the flexible substrate adjacent to the slot, each recess having a base at the second surface of the flexible substrate and sized to receive therein a bumped contact disposed on an active surface of a die flip-chip mounted on the first surface of the flexible substrate;

a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slot, each trace extending across and exposed through the slot and the base of at least one recess; and

an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.

34. The flexible film interposer of Claim 33, wherein an adhesive element is disposed on the second surface of the flexible substrate and over a portion of the traces.

35. The flexible film interposer of Claim 33, further comprising a soldermask disposed over the traces.

36. The flexible film interposer of Claim 35, further comprising an adhesive element disposed over the soldermask.

37. A flexible film interposer, comprising:

a flexible substrate comprising a first surface, a second surface, and opposing sides;

the first surface of the flexible substrate structured for mounting thereon in a flip-chip attachment a first semiconductor die having a plurality of spaced apart conductive connecting members disposed on an active surface, and the second surface structured for mounting thereon a second semiconductor die having a plurality of bond pads spaced along a periphery of the die;

the flexible substrate comprising a plurality of recesses extending through the flexible substrate and having a base at the second surface of the flexible substrate, the recesses sized and spaced apart to receive therein the plurality of conductive connecting members of the first semiconductor die when flip-chip mounted on the first surface of the flexible substrate; and one or more slots extending through and along a periphery of the flexible substrate, wherein when the

second semiconductor die is mounted thereon, the bonding pads are exposed through the slots, the slot sized and configured to receive a bonding tool therein to contact said bond pads.

38. The flexible film interposer of Claim 37, further comprising:

a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending over the slot and at least one recess, each of the recesses having a trace disposed at the base thereof.

39. A semiconductor device, comprising:

a first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; and

a flexible film interposer comprising a flexible substrate having a first surface and a second surface, an elongate slot extending therethrough and along a peripheral edge of at least one side of the interposer, the slot sized and configured to expose bond pads on a second semiconductor die when mounted onto the second surface of the flexible substrate, and to receive a bonding tool therein to contact said bond pads, a plurality of spaced apart recesses extending therethrough and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of at least one recess in a perpendicular orientation to the slot, each of the recesses having a trace disposed at the base thereof;

the first semiconductor die flip-chip mounted on the first surface of the flexible substrate of the flexible film interposer such that each conductive connecting member disposed on the active surface of the first die is received in a recess of the interposer in conductive contact with the trace at the base of the recess.

40. The semiconductor device of Claim 39, wherein the flexible film interposer comprises a flexible polyimide film.

41. The semiconductor device of Claim 39, wherein the traces comprise copper or a copper alloy.

42. The semiconductor device of Claim 39, comprising an elongate slot disposed along opposing sides of the interposer.
43. The semiconductor device of Claim 39, wherein the recesses are arranged in a pattern corresponding to a bond pad configuration on the active surface of the first semiconductor die.
44. The semiconductor device of Claim 39, further comprising an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.
45. The semiconductor device of Claim 44, wherein the adhesive element comprises a contact adhesive, thermoplastic adhesive, or a thermosetting adhesive.
46. The semiconductor device of Claim 44, wherein the adhesive element comprises an adhesive gel or paste.
47. The semiconductor device of Claim 44, wherein the adhesive element comprises a double-sided adhesive tape.
48. The semiconductor device of Claim 44, wherein the adhesive element is disposed on the second surface of the flexible substrate and over a portion of the traces.
49. The semiconductor device of Claim 39, further comprising a soldermask disposed over the traces.
50. The semiconductor device of Claim 39, wherein the interposer comprises a pair of elongate slots along opposing sides of the interposer, and the plurality of recesses is positioned between the pair of slots.
51. The semiconductor device of Claim 39, further comprising an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.

52. The semiconductor device of Claim 51, wherein an adhesive element is disposed on the second surface of the flexible substrate and over a portion of the traces.
53. The semiconductor device of Claim 49, wherein an adhesive element is disposed over the soldermask.
54. The semiconductor device of Claim 39, further comprising an underfill encapsulation material disposed between the active surface of the first semiconductor die and the first surface of the flexible substrate.
55. The semiconductor device of Claim 39, wherein each of the conductive connecting members of the first die comprise a conductive bump and each conductive bump is disposed in a recess of the flexible film interposer.
56. The semiconductor device of Claim 55, further comprising a non-flexible underfill encapsulation material disposed in the recesses over the conductive bump.
57. A semiconductor device, comprising:  
a first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; and  
a flexible film interposer comprising a flexible substrate having a first surface and a second surface, an elongate slot disposed through the flexible substrate along a peripheral edge of at least one side of the interposer, the slot sized and configured for receiving a bonding tool therein, a plurality of spaced apart recesses disposed through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of at least one recess in a perpendicular orientation to the slot, each of the recesses having a trace disposed at the base thereof;  
the first semiconductor die flip-chip mounted on the first surface of the flexible substrate of the flexible film interposer such that each conductive connecting member on the active surface of the

first die is received in a recess of the interposer in conductive contact with the trace at the base of the recess.

58. The semiconductor device of Claim 57, wherein a slot is disposed adjacent to opposing sides of the substrate.

59. The semiconductor device of Claim 57, wherein the recesses are arranged in a pattern corresponding to a bond pad configuration on the active surface of the first semiconductor die.

60. The semiconductor device of Claim 57, further comprising an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.

61. The semiconductor device of Claim 57, further comprising an underfill encapsulation material disposed between the active surface of the first semiconductor die and the first surface of the flexible substrate.

62. The semiconductor device of Claim 57, comprising one or more elongate slots along the peripheral edge of opposing sides of the interposer, with the recesses positioned between the pair of slots.

63. A semiconductor device, comprising:  
a first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; and  
a flexible film interposer comprising a flexible substrate having a first surface and a second surface, an elongate slot disposed through the flexible substrate along a peripheral edge of at least one side of the interposer, the slot sized and configured for receiving a bonding tool therein, a plurality of spaced apart recesses disposed through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slots, each trace extending across and exposed through the slot and the base of at least one recess, each of the recesses having a trace disposed at the base thereof;

the first semiconductor die mounted on the first surface of the flexible substrate of the flexible film interposer in a flip-chip attachment such that a conductive connecting member on the active surface of the die is received in each recess of the interposer in conductive contact with the trace at the base of the recess.

64. A semiconductor device, comprising:

a first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; and

a flexible film interposer comprising a flexible substrate having a first surface, a second surface, and opposing sides, an elongate slot disposed through the flexible substrate along a peripheral edge of at least one side of the flexible film interposer, the slot sized and configured for receiving a bonding tool therein, a plurality of spaced apart recesses disposed through the flexible substrate adjacent to the slot, each recess having a base at the second surface of the flexible substrate, a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slots, each trace extending across and exposed through the slot and the base of at least one recess, each recess having a trace disposed at the base thereof, and an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate;

the first semiconductor die mounted on the first surface of the flexible film interposer such that a conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess.

65. The semiconductor device of Claim 64, wherein an adhesive element is disposed in contact with the second surface of the flexible substrate over a portion of the traces.

66. The semiconductor device of Claim 64, further comprising a soldermask layer disposed over the second surface of the flexible substrate and the traces.

67. The semiconductor device of Claim 66, wherein an adhesive element is disposed over the soldermask layer.

68. A stacked die assembly, comprising:

a flexible film interposer comprising a flexible substrate having a first surface and a second surface, an elongate slot extending through the flexible substrate and along a peripheral edge of at least one side of the interposer, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses extending through the flexible substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of one or more recesses in a perpendicular orientation to the slot, each of the recesses having a trace disposed at the base thereof;

a first semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; the first semiconductor die flip-chip mounted onto the first surface of the flexible substrate of the flexible film interposer such that each of the conductive connecting members on the active surface of the first die is received in a recess of the flexible film interposer in conductive contact with the trace at the base of the recess;

a second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of peripheral bond pads; the second semiconductor die mounted onto the second surface of the flexible substrate of the flexible film interposer with the bond pads exposed through the slot of the interposer;

a second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed; and

the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer.

69. The stacked die assembly of Claim 68, wherein the traces of the flexible film interposer and the bond pads of the second die are bonded together by a ball bond, and the ball bond is wire bonded to the terminal pads of the second interposer.

70. The stacked die assembly of Claim 68, wherein the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer by a TAB bond.
71. The stacked die assembly of Claim 68, further comprising an underfill encapsulation material disposed between the active surface of the first semiconductor die and the flexible film interposer.
72. The stacked die assembly of Claim 68, wherein the underfill material is disposed within the recesses of the flexible film interposer.
73. The stacked die assembly of Claim 71, further comprising a conductive bump disposed in the recesses of the flexible film interposer, and the underfill material disposed over the conductive bump.
74. The stacked die assembly of Claim 68, wherein the second interposer functions as a PCB substrate, or a motherboard.
75. The stacked die assembly of Claim 68, wherein the second interposer comprises a bismaleimide triazine resin, FR4 fiberglass laminate, FR5 laminate, or ceramic.
76. The stacked die assembly of Claim 68, wherein the second interposer comprises a flexible laminated polymer or polyimide layer.
77. The stacked die assembly of Claim 68, wherein the second interposer further comprises external contacts for coupling the stacked die assembly to an external circuitry.
78. The stacked die assembly of Claim 77, wherein the external contacts comprise conductive solder balls.
79. The stacked die assembly of Claim 77, wherein the external contacts comprise a conductive epoxy or conductor-filled epoxy.

80. The stacked die assembly of Claim 77, wherein the external circuitry is selected from the group consisting of a motherboard of a computer, program logic controller, and a testing apparatus.

81. The stacked die assembly of Claim 68, being encapsulated to form a package.

82. A stacked die assembly, comprising:

a flexible film interposer comprising a flexible substrate having a first surface, a second surface, and opposing sides; an elongate slot extending through the flexible substrate along a peripheral edge of at least one side of the flexible film interposer, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses extending through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of one or more recesses in a perpendicular orientation to the slot;

a first semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members arranged thereon and corresponding to the plurality of spaced apart recesses in the flexible film interposer; the active surface of the first semiconductor die mounted onto the first surface of the flexible substrate of the flexible film interposer such that each of the conductive connecting members of the first die is received in a recess of the flexible film interposer in conductive contact with the trace at the base of the recess, and the slot of the flexible film interposer is exposed;

a second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of bond pads arranged thereon and corresponding to the slot of the flexible film interposer; the active surface of the second semiconductor die mounted onto the second surface of the flexible substrate with the bond pads exposed through the slot of the flexible film interposer;

a second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed; and

the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer.

83. The stacked die assembly of Claim 82, being encapsulated to form a package.

84. A stacked die assembly, comprising:

a flexible film interposer comprising a flexible substrate having a first surface, a second surface, and opposing sides, an elongate slot disposed through the flexible substrate along a peripheral edge of at least one side of the flexible film interposer, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses disposed through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slot, each trace extending across and exposed through the slot and the base of at least one recess, each recess having a trace disposed at the base hereof;

a first semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members arranged thereon; the active surface of the first semiconductor die mounted in a flip-chip attachment onto the first surface of the flexible substrate of the flexible film interposer such that each conductive connecting member of the first die is received in a recess of the interposer in conductive contact with the trace at the base of the recess, and the slot of the flexible film interposer is exposed;

a second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of bond pads arranged thereon; the active surface of the second semiconductor die mounted onto the second surface of the flexible substrate of the flexible film interposer with the bond pads exposed through the slot of the flexible film interposer;

a second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed; and

the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer.

85. The stacked die assembly of Claim 84, being encapsulated to form a package.

86. A stacked die assembly, comprising:

a flexible film interposer comprising a flexible substrate having a first surface, a second surface, and opposing sides, a slot disposed through the flexible substrate adjacent at least one side of the flexible film interposer, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses disposed through the flexible substrate adjacent the slot, each recess having a base at the second surface of the flexible substrate, a plurality of conductive traces disposed on the second surface of the flexible substrate in a perpendicular orientation to the slot, each trace extending across and exposed through the slot and the base of at least one recess, each recess having a trace disposed at the base thereof, and an adhesive element disposed on the first surface and the second surface of the flexible substrate;

a first semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members arranged thereon; the active surface of the first semiconductor die mounted in a flip-chip attachment onto the adhesive element on the first surface of the flexible substrate of the flexible film interposer such that each conductive connecting member of the die is received in a recess of the flexible film interposer in conductive contact with the trace at the base of the recess, and the slot of the flexible film interposer is exposed;

a second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of bond pads arranged thereon along a peripheral edge; the active surface of the second semiconductor die mounted onto the adhesive member on the second surface of the flexible substrate of the flexible film interposer with the bond pads exposed through the slot of the flexible film flexible film interposer;

a second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed; and

the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer.

87. The stacked die assembly of Claim 86, further comprising an adhesive member disposed between the second interposer and the second surface of the second semiconductor die.

88. The stacked die assembly of Claim 86, being encapsulated to form a package.
89. A semiconductor package, comprising an encapsulated stacked die assembly;  
the stacked die assembly comprising first and second semiconductor die mounted on a flexible film interposer, and the second die further mounted on a second interposer;  
the flexible film interposer comprising a flexible substrate having a first surface and a second surface, an elongate slot extending through the flexible substrate adjacent at least one side of the interposer, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses extending through the flexible substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of one or more adjacent recesses in a perpendicular orientation to the slot;  
the first semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; the active surface of the first semiconductor die mounted onto the first surface of the flexible substrate of the flexible film interposer such that each conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess;  
the second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of bond pads; the active surface of the second semiconductor die mounted onto the second surface of the flexible substrate of the flexible film interposer with the bond pads exposed through the slot of the interposer;  
the second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the first surface of the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed; and  
the traces of the flexible film interposer and the bond pads of the second semiconductor die are bonded to the terminal pads of the second interposer.
90. The package of Claim 89, wherein the second interposer functions as a PCB substrate, or a motherboard.

91. The package of Claim 89, wherein the second interposer comprises a bismaleimide triazine resin, FR4 fiberglass laminate, FR5 laminate, or ceramic.
92. The package of Claim 89, wherein the second interposer comprises a flexible laminated polymer or polyimide layer.
93. The package of Claim 89, wherein the second interposer comprises external contacts for coupling the stacked die assembly to an external circuitry.
94. The package of Claim 93, wherein the external contacts comprise conductive solder balls.
95. The package of Claim 93, wherein the external contacts comprise a conductive epoxy or conductor-filled epoxy.
96. A method of fabricating a semiconductor device, comprising the steps of:  
providing a flexible film interposer, the interposer comprising a flexible substrate comprising a first surface and a second surface, an elongate slot formed therethrough and along at least one side of the interposer to expose bond pads on a second semiconductor die mounted onto the second surface of the flexible substrate, the slot sized and configured to receive a bonding tool therein, a plurality of spaced apart recesses formed therethrough and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of one or more adjacent recesses in a perpendicular orientation to the slot; and  
mounting a first semiconductor die on the first surface of the flexible substrate of the flexible film interposer; the first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; the active surface of the first semiconductor die flip-chip mounted on the interposer such that each conductive connecting member of the first die is received in a recess of the interposer in conductive contact with the trace at the base of the recess.

97. A method of fabricating a stacked die assembly, comprising the steps of:

providing a flexible film interposer, the interposer comprising a flexible substrate comprising a first surface and a second surface, an elongate slot formed therethrough and along at least one side of the interposer, the slot sized and configured to expose bond pads on a second semiconductor die mounted onto the second surface of the flexible substrate, and to receive a bonding tool therein, a plurality of spaced apart recesses formed therethrough and adjacent the slot, each recess having a base at the second surface of the flexible substrate, and a plurality of conductive traces disposed on the second surface of the flexible substrate, each trace extending across and exposed through the slot and the base of one or more adjacent recesses in a perpendicular orientation to the slot; and

mounting a first semiconductor die in a flip-chip attachment on the first surface of the flexible substrate of the flexible film interposer; the first semiconductor die having a first active surface and a second surface, the active surface comprising a plurality of spaced apart conductive connecting members; and the active surface of the first semiconductor die mounted on the interposer such that a conductive connecting member of the die is received in a recess of the interposer in conductive contact with the trace at the base of the recess;

mounting a second semiconductor die on a second interposer; the second semiconductor die comprising a first active surface and a second surface, the active surface comprising a plurality of bond pads; the second interposer comprising a first surface and a second surface, and terminal pads disposed on the first surface; the first surface of the second interposer mounted onto the second surface of the second semiconductor die with the terminal pads exposed;

mounting the active surface of the second semiconductor die onto the second surface of the flexible substrate of the flexible film interposer with the bond pads of the second die exposed through the slot of the interposer; and

bonding the traces of the flexible film interposer and the bond pads of the second semiconductor die to the terminal pads of the second interposer.

98. The method of Claim 97, further comprising the step of forming the slot and the recesses in the flexible substrate of the flexible film interposer by a process selected from the group consisting of patterning and wet etching, patterning and dry etching, mechanical drilling, punching, and laser ablation.

99. The method of Claim 97, further comprising the step of forming the conductive traces over the second surface of the flexible substrate of the flexible film interposer by a process selected from the group consisting of etching a conductive layer disposed on the second surface of the flexible substrate, and printing the traces onto the second surface using a conductive material.

100. The method of Claim 97, wherein the flexible film interposer further comprises an adhesive element disposed on the first surface, the second surface, or both surfaces of the flexible substrate.

101. The method of Claim 97, wherein the step of mounting the first semiconductor die on the flexible film interposer further comprises applying an adhesive element to the first surface of the flexible substrate, to the second surface of the first semiconductor die, or both.

102. The method of Claim 101, wherein the adhesive element is selected from the group consisting of an adhesive paste, an adhesive gel, and a double-sided adhesive tape.

103. The method of Claim 97, wherein the step of mounting the second semiconductor die on the flexible film interposer further comprises the step of applying an adhesive element to the second surface of the flexible substrate, to the active surface of the second semiconductor die, or both.

104. The method of Claim 103, wherein the adhesive element is selected from the group consisting of an adhesive paste, an adhesive gel, and a double-sided adhesive tape.

105. The method of Claim 97, wherein the interposer further comprises a soldermask disposed over the second surface of the flexible substrate and the traces.

106. The method of Claim 97, further comprising the step of applying a soldermask over the second surface of the flexible substrate and the traces.

107. The method of Claim 106, wherein the step of mounting the second die on the flexible film interposer further comprises the step of applying an adhesive element over the soldermask.

108. The method of Claim 97, wherein the step of bonding is by thermosonic bonding, thermocompression bonding, tape-automated bonding, or ultrasonic bonding.

109. The method of Claim 97, wherein the step of bonding comprises forming ball bonds in the slot of the flexible film interposer and over the traces and the bond pads of the second semiconductor die, and extending bonding wires from the ball bonds to the terminal pads on the second interposer.

110. The method of Claim 97, further comprising disposing an underfill material between the active surface of the first semiconductor die and the first surface of the flexible substrate of the flexible film interposer.

111. The method of Claim 97, further comprising the step of encapsulating the stacked die assembly to form a semiconductor package.

112. A method of fabricating a stacked die assembly, comprising the steps of:  
fabricating an interposer from a flexible film substrate having opposing first and second surfaces, by the steps of:

forming an elongate slot through and along at least one side of the flexible film substrate; the slot sized and configured to receive a bonding tool therein;

forming a plurality of spaced apart recesses through the flexible film substrate and adjacent the slot, each recess having a base at the second surface of the flexible substrate;

forming a plurality of conductive traces on the second surface of the flexible film substrate, each trace extending across and exposed through the slot and the base of one or more recesses in a perpendicular orientation to the slot;

mounting an active surface of a first semiconductive die onto the first surface of the flexible film substrate such that each of a plurality of conductive connecting members disposed on the active surface of the first die is disposed in a recess of the interposer in contact with the trace at the base of the slot; and

mounting a second semiconductive die onto the second surface of the flexible film substrate such that bond pads of the second die are exposed through the slot of the interposer.

113. The method of Claim 112, further comprising, applying a soldermask over the second surface of the flexible film substrate and the traces.

114. The method of Claim 112, further comprising, prior to the step of mounting, the step of depositing an underfill material into the recesses.

115. The method of Claim 114, further comprising applying an adhesive element to the first die, the flexible film substrate, or both, such that the adhesive element is disposed between the first die and the interposer.

116. A die assembly, comprising:

a die having first and second surfaces, the first surface comprising one or more conductive connecting members; and

an interposer comprising first and second surfaces; an elongate slot formed through and along a peripheral edge of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second semiconductor die when mounted on the second surface of the interposer; one or more recesses through the interposer adjacent the slot, each recess having a base at the second surface of the interposer, and each recess sized and configured to receive therein a conductive connecting member disposed on an active surface of a first semiconductor die when flip-chip mounted on the first surface of the interposer; and one or more conductive traces disposed on the second surface of the interposer and extending across and exposed through the slot and at least one recess;

the die mounted on the first surface of the interposer with each of the one or more conductive connecting members disposed in a recess in conductive contact with the trace extending across the recess.

117. A die assembly, comprising:

an interposer comprising first and second surfaces; an elongate slot formed through and along a peripheral edge of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second semiconductor die when mounted on the second surface of the interposer; one or more recesses disposed through the interposer adjacent the slot, each

recess having a base at the second surface of the interposer, and each recess sized and configured to receive therein a conductive connecting member disposed on an active surface of a first semiconductor die when flip-chip mounted on the first surface of the interposer; and one or more conductive traces disposed on the second surface of the interposer and extending across and exposed through the slot and at least one recess;

a first die comprising first and second surfaces, the first surface comprising one or more conductive connecting members, the first die mounted on the first surface of the interposer with each of the one or more conductive connecting members disposed in a recess in conductive contact with the trace extending across the recess; and

a second die comprising first and second surfaces, the first surface comprising one or more bond pads, the second die mounted on the second surface of the interposer with each of the bond pads exposed through the slot of the interposer.

118. A die assembly, comprising:

an interposer comprising first and second surfaces; an elongate slot formed through and along a peripheral edge of the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second semiconductor die when mounted on the second surface of the interposer; one or more recesses disposed through the interposer adjacent the slot, each recess having a base at the second surface of the interposer, and each recess sized and configured to receive therein a conductive connecting member disposed on an active surface of a first semiconductor die when flip-chip mounted on the first surface of the interposer; and one or more conductive traces disposed on the second surface of the interposer and extending across and exposed through the slot and at least one recess;

a first die comprising first and second surfaces, the first surface comprising one or more conductive connecting members, the first die mounted on the first surface of the interposer with each of the one or more conductive connecting members disposed in a recess in conductive contact with the trace extending across the recess;

a second die comprising first and second surfaces, the first surface comprising one or more bond pads, the second die mounted on the second surface of the interposer with each of the bond pads exposed through the slot of the interposer; and

a substrate comprising first and second surfaces, and terminal pads disposed on the first surface; the substrate mounted on the second surface of the second die with the terminal pads exposed.

119. A die package comprising the die assembly of any of Claims 116-118, being at least partially encapsulated.

120. An interposer, comprising: a flexible substrate comprising first and second surfaces, a plurality of recesses disposed through the flexible substrate and having a base at the second surface of the flexible substrate, each recess sized and configured to receive therein a conductive connecting member disposed on an active surface of a first die when flip-chip mounted onto the first surface of the flexible substrate, and a slot disposed through the flexible substrate and slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second die when disposed on the second surface of the flexible substrate.

121. The interposer of Claim 120, further comprising: conductive traces disposed on the second surface of the flexible substrate, each trace extending over the slot and at least one recess, and wherein a trace is disposed at the base of each recess.

122. The interposer of Claim 120, comprising an insulating polymeric material.

123. The interposer of Claim 120, comprising a flexible polyimide film.

124. The interposer of Claim 120, wherein the recesses are arranged in a pattern corresponding to a bond pad configuration on an active surface of a die to be attached thereto.

125. A die assembly, comprising:

a die flip chip disposed on an interposer and comprising a first surface comprising a plurality of spaced apart conductive connecting members and a second surface;

the interposer comprising a flexible substrate and first and second surfaces, a plurality of recesses extending through the interposer from the first surface to the second surface, each recess

sized and configured to receive therein a conductive connecting member of the die disposed on the first surface of the interposer, and a slot disposed through the interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second die when disposed on the second surface of the interposer.

126. The assembly of Claim 125, further comprising: conductive traces disposed on the second surface of the interposer, each trace extending over the slot and at least one recess, with a trace disposed at the base of each recess in contact with the conductive connecting member disposed in the recess.

127. The assembly of Claim 126, further comprising: a second die disposed on the second surface of the interposer and comprising a plurality of peripheral bond pads, the bond pads exposed through the slot of the interposer.

128. The assembly of Claim 127, further comprising: a second interposer comprising first and second surfaces, and terminal pads disposed on the first surface, the second interposer disposed on the second surface of the second die with the terminal pads exposed.

129. A method of fabricating a die assembly, comprising the steps of:

providing a flexible interposer having first and second surfaces, the flexible interposer comprising a plurality of recesses extending therethrough from the first surface to the second surface, each recess sized and configured to receive therein a conductive connecting member of a die flip-chip mounted onto the first surface of the flexible interposer, a slot extending through the flexible interposer from the first surface to the second surface along a peripheral edge of the flexible interposer, the slot sized and configured to receive a bonding tool therethrough to contact bond pads of a second die situated on the second surface of the flexible interposer, and conductive traces on the second surface of the flexible interposer such that a trace is situated over each recess at the second surface of the flexible interposer, and each trace extends over the slot and at least one recess; and

flip chip mounting a die on the first surface of the flexible interposer such that conductive connecting members situated on an active surface of the die are each received in a recess of the flexible interposer in conductive contact with the trace situated over the recess.

130. The method of Claim 129, further comprising the step of mounting a second die on the second surface of the flexible interposer such that bond pads on the surface of the second die are exposed through the slot of the flexible interposer.
131. The method of Claim 130, further comprising the step of mounting a second interposer onto an exposed surface of the second die.
132. The method of Claim 131, further comprising the step of bonding the traces and the bond pads of the second die to terminal pads on the second interposer.
133. The method of Claim 132, wherein the step of bonding is by thermosonic bonding, thermocompression bonding, tape-automated bonding, or ultrasonic bonding.
134. The method of Claim 132, wherein the step of bonding comprises forming ball bonds in the slots of the flexible interposer and over the traces and the bond pads of the second die, and extending bonding wires from the ball bonds to the terminal pads on the second interposer.
135. The method of Claim 129, further comprising, prior to the step of mounting the die, the step of depositing an underfill material into the recesses.
136. The method of Claim 129, further comprising the step of encapsulating the die assembly to form a semiconductor package.
137. A method of fabricating a die assembly, comprising the step of:  
flip chip mounting a die onto a first surface of a flexible interposer such that conductive connecting members on an active surface of the die are each situated in a recess extending through the flexible interposer from the first surface to a second surface; the flexible interposer further comprising a slot extending therethrough from the first surface to the second surface, the slot sized to receive a bonding tool therethrough to contact bond pads of a second die when situated on the second surface of the flexible interposer.

138. The method of Claim 137, wherein the flexible interposer further comprises conductive traces on the second surface, such that a trace is situated over each recess at the second surface of the flexible interposer, and each trace extends over the slot and at least one recess.
139. The method of Claim 138, further comprising the step of mounting a second die on the second surface of the flexible interposer such that bond pads of the second die are exposed through the slot of the flexible interposer.
140. The method of Claim 139, wherein the second die is mounted on a second interposer.
141. The method of Claim 139, further comprising the step of mounting a second interposer onto the second die.
142. The method of Claim 141, further comprising the step of connecting the traces of the flexible interposer and the bond pads of the second die to terminal pads on the second interposer.
143. The method of Claim 137, further comprising the step of encapsulating at least a portion of the die assembly to form a die package.