

(Meth)acrylate based Reactive Diluent Compositions for Unsaturated Polyester ResinsBackground of the Invention

5 Unsaturated polyester (UP) resins are unsaturated synthetic resins formed by the reaction of dibasic organic acids and polyhydric alcohols. Unsaturated polyester resins are widely used in different applications. e.g. coatings, adhesives, relining, gel coats or composites. In composites including sheet molding compounds (SMC) and bulk molding compounds (BMC), UP resins are reinforced with solid materials such as fiberglass, resulting in fiber-reinforced plastic (FRP). UP
10 resins with a high filler content are used for putties, polymer concrete, chemical anchoring, coloring pastes or artificial marble.

UP resins can be cured using reactive diluents, i.e. solvents with crosslinking/curing reactivities, such as styrene. Typically, UP resins are cured with a high styrene content – usually up to 50 wt%.
15 Hence, most UP resins consist of a solution of an unsaturated polyester in styrene. For regulatory, health and safety reasons, many companies aim at reducing the amount of the organ damaging and likely reprotoxic styrene in their resins and thus at developing styrene reduced or even styrene-free systems. For replacing styrene, structural analogues of styrene are often used, which is just a makeshift solution to avoid direct use of styrene. Examples of such workaround solutions are
20 4-methylstyrene, 4-tert-butyl styrene or 2,4,6-trimethylstyrene.

Despite its adverse physiological properties, styrene is continuously used in UP resins because it is very cheap, has a high dilution power and easily copolymerizes with the unsaturated parts of the polyester resin.

25 (Meth)acrylic acid and its esters (i.e. (meth)acrylates), are less hazardous and safer to handle compared to styrene, so it would be particularly desirable to use (meth)acrylates as reactive diluents, or in reactive diluent compositions, respectively. Methacrylates are described as reactive diluents for vinyl ester resins. Vinyl ester resins are epoxy resins functionalized with (meth)acrylate end group by the reaction with (meth)acrylic acid or hydroxy (meth) acrylate. These end groups
30 easily crosslink in the final curing step with methacrylates as reactive diluents. However, (meth)acrylates do not simply copolymerize/crosslink with UP resins and can therefore not be used as reactive diluent in such resins.

35 In accordance with the above, it was an objective of the present invention to provide a new, (meth)acrylate based and styrene-free reactive diluent composition for UP resins. Ideally, such a (meth)acrylate-based reactive diluent composition includes (meth)acrylates with a low vapor pressure, leading even to VOC-free or VOC-reduced reactive diluent compositions (VOC = volatile organic compounds).

40

State of the Art

CN 111978477 A relates to the field of composite materials, in particular to a sheet molding compound raw material, a sheet molding compound product, and a preparation method and application thereof. The sheet molding compound comprises an unsaturated polyester resin, a low

- 5 shrinkage agent, an initiator, a diluent monomer, a compound containing sulfhydryl, a glass microsphere, a flame retardant, and a reinforcement.

It does not describe the reactive diluent composition according to the present invention. It does likewise not describe a curable resin composition comprising this reactive diluent composition or a pre-accelerated formulation comprising the curable resin composition, nor does it disclose a

- 10 method of curing unsaturated polyester resins by providing a curable resin composition that comprises the reactive diluent composition of the instant patent application.

WO 2013/124273 relates to a thermosetting, radically curable resin composition containing methacrylate containing resin being suitable for (re)lining.

- 15 The resin composition comprises:

- (a) 30-70 wt.% of methacrylate containing resin,
- (b) 2.5-20 wt.% of unsaturated polyester resin comprising fumaric acid building blocks as unsaturated dicarboxylic acid building blocks and alkoxyated bisphenol A and/or alkoxyated bisphenol F building blocks as diol building blocks,
- 20 (c) 1-40 wt.% of ethylenically unsaturated compound, not being benzyl methacrylate, able to copolymerize with (a), (b) and (d); and
- (d) 5-60 wt.% of benzyl methacrylate - (see claim 1 and pag1 1, line 26 to page 2, line 3).

It does not describe the reactive diluent composition according to the present invention. It does likewise not describe a curable resin composition comprising this reactive diluent composition or a

- 25 pre-accelerated formulation comprising the curable resin composition, nor does it disclose a method of curing unsaturated polyester resins by providing a curable resin composition that comprises the reactive diluent composition of the instant patent application.

JP 2003-206306 relates to methyl methacrylate-containing molding materials. The molding material comprises a resin (A) comprising a vinyl monomer (a), a vinyl monomer (b) and a polymer (c), a filler (B) and a curing agent (C).

It does not describe the reactive diluent composition according to the present invention. It does likewise not describe a curable resin composition comprising this reactive diluent composition or a pre-accelerated formulation comprising the curable resin composition, nor does it disclose a

- 35 method of curing unsaturated polyester resins by providing a curable resin composition that comprises the reactive diluent composition of the instant patent application.

Summary of the Invention

In a first aspect, the present invention provides a reactive diluent composition comprising or

- 40 consisting of a (meth)acrylic acid ester monomer and a compatibilizer; wherein the compatibilizer

comprises at least one (meth)acrylate moiety and at least one additional ethylenically unsaturated moiety.

In a second aspect, the invention relates to a curable resin composition comprising at least an
5 unsaturated polyester resin (UPR) and the reactive diluent composition described above.

In a third aspect, the present invention pertains to a pre-accelerated formulation comprising the curable resin composition described above, and at least one accelerator.

10 In a fourth aspect, the invention provides a styrene-free method of curing unsaturated polyester resins, the method comprising

- (a) providing a curable resin composition, or, alternatively, the pre-accelerated formulation as described above,
- (b) optionally adding at least one organic or inorganic additive as described above, and
- 15 (c) initiating the curing process by adding an initiator.

Detailed Description of the Invention

The inventors have developed a (meth)acrylate-based reactive diluent composition that enables styrene-free curing of UP resins.

20 More specifically, the inventors have found that UP resins copolymerize with (meth)acrylates upon addition of a compatibilizer, i.e. a multifunctional, preferably difunctional molecule comprising at least one (meth)acrylate moiety and at least one additional ethylenically unsaturated moiety. Said at least one additional ethylenically unsaturated moiety may be, e.g. vinyl, allyl or alkenyl.

25 Accordingly, the present invention provides a reactive diluent composition comprising or consisting of a (meth)acrylic acid ester monomer and a compatibilizer; wherein the compatibilizer comprises at least one (meth)acrylate moiety and at least one additional ethylenically unsaturated moiety. The (meth)acrylic acid ester monomer and the compatibilizer are different chemical compounds.

30 Within the context of the present invention, the term "(meth)acrylate" refers to esters of methacrylic acid or of acrylic acid.

In the compatibilizer, the at least one (meth)acrylate moiety and at least one additional ethylenically
35 unsaturated moiety may be connected by a linker moiety comprising a linear, cyclic or branched alkyl or (alkyl)aryl group having a chain length of C₁ to C₂₀, said linker moiety optionally comprising one or more heteroatom(s), such as O, N or S.

The compatibilizer may be selected from the group consisting of vinyl ether (meth)acrylates,
40 allyl ether (meth)acrylates and alkenyl (meth)acrylates. Vinyl ether (meth)acrylates include e.g. monovinyl ether mono(meth)acrylates, monovinyl ether di(meth)acrylates, monovinyl ether

tri(meth)acrylates, monovinylether tetra(meth)acrylates; divinylether mono(meth)acrylates, divinylether di(meth)acrylates, divinylether tri(meth)acrylates; and trivinylether mono(meth)acrylates, trivinylether di(meth)acrylates. Allylether (meth)acrylates include e.g. including monoallylether mono(meth)acrylates, monoallylether di(meth)acrylates, monoallylether tri(meth)acrylates, monoallylether tetra(meth)acrylates; diallylether mono(meth)acrylates, diallylether di(meth)acrylates, diallylether tri(meth)acrylates; and triallylether mono(meth)acrylates, triallylether di(meth)acrylates. Alkenyl (meth)acrylates include mono, di, tri and tetra(meth)acrylates containing one or more ethylenically unsaturated alkenyl (C=C) moiety being different from (meth)acrylate.

10

Advantageously, the compatibilizer is selected from the group consisting of 4-(vinylloxy)butyl methacrylate, 2-(allyloxy)ethyl methacrylate, isoprenol methacrylate, 2,2-bis((allyloxy)methyl)butyl methacrylate, 2-((allyloxy)methyl)-2-ethylpropane-1,3-diyl bis(2-methylacrylate), and eugenol methacrylate; 4-(vinylloxy)butyl methacrylate, 2-(allyloxy)ethyl methacrylate and isoprenol methacrylate are particularly preferred, as they show good resin compatibility and curing properties.

15

The (meth)acrylic acid ester monomer may be selected from alkyl (meth)acrylates with linear or branched alkyl C1-20, (alkyl) aryl (meth)acrylates, hydroxy alkyl (meth)acrylate, (poly) ether methacrylates, di, tri, tetra-methacrylates, and mixtures thereof.

20

Examples for suitable (meth)acrylic acid ester monomers are methyl (meth)acrylate, isobornyl (meth)acrylate, norbornyl (meth)acrylate, tert-butyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, *i*-propyl (meth)acrylate, n-butyl (meth)acrylate, *i*-butyl (meth)acrylate, cyclohexyl (meth)acrylate, iso-hexyl (meth)acrylate, n-hexyl (meth)acrylate, 2-ethylhexyl (meth)acrylate, 2-propylheptyl (meth)acrylate, iso-decyl (meth)acrylate, iso-tridecyl (meth)acrylate, benzyl (meth)acrylate, isobornyl (meth)acrylate, 3,3,5-trimethyl cyclohexyl methacrylate, norbornyl (meth)acrylate, dihydrodicyclopentadienyl (meth)acrylate, lauryl (meth)acrylate, stearyl (meth)acrylate, behenyl (meth)acrylate, hydroxyethyl (meth)acrylate, hydroxypropyl (meth)acrylate, hydroxybutyl (meth)acrylate, hydroxyethylphosphate (meth)acrylate, tetrahydrofurfuryl (meth)acrylate, ethyltriglycol (meth)acrylate, butyldiglycol (meth)acrylate, glycidyl (meth)acrylate, glycerol formal (meth)acrylate, isopropylidenglycerine (meth)acrylate, isosorbide mono-(meth)acrylate, isosorbide di(meth)acrylate, 3(4),8(9)-dimethacryloyloxymethyl-tricyclo[5.2.1.0^(2,6)]decan (dimethacrylate of 3,8-dihydroxymethyl-tricyclo[5.2.1.0^(2,6)]decane), allyl (meth)acrylate, ethylene glycol di(meth)acrylate, triethylene glycol di(meth)acrylate, polyethylene glycol 200 di(meth)acrylate, 1,3-butanediol di(meth)acrylate, 1,4-butanediol di(meth)acrylate, 2,3-butanediol di(meth)acrylate, 1,6-hexanediol di(meth)acrylate and its isomers, glycerol di(meth)acrylate, trimethylolpropane di(meth)acrylate, neopentyl glycol di(meth)acrylate, dipropylene glycol di(meth)acrylate, tripropylene glycol di(meth)acrylate, PPG250 di(meth)acrylate, tricyclodecane dimethylol di(meth)acrylate, 1,10-decanediol di(meth)acrylate, tetraethylene glycol di(meth)acrylate, trimethylolpropane tri(meth)acrylate, glycidyl (meth)acrylate, and mixtures thereof.

30

35

40

Advantageously, the (meth)acrylic acid ester monomer is selected from methyl methacrylate, glycerol formal methacrylate, benzyl methacrylate, cyclohexyl methacrylate, isobornyl methacrylate, 1,4-butanediol dimethacrylate, polyethyleneglycol 200 dimethacrylate, ethylene glycol dimethacrylate, butyl diglycol methacrylate and ethyltriglycol methacrylate.

It is noted that methacrylate monomers as reactive diluents with a low vapor pressure are of advantage to formulate low or even no VOC resin compositions. The use of styrene in composite resins results in the emission of styrene vapor into the working atmosphere. This exposes the workers and the environment to hazardous vapor. Methyl methacrylate compared to styrene is a less hazardous compound, but it is also classified as VOC due to its high vapor pressure. Therefore, the use of methacrylate monomers like benzyl methacrylate, glycerol formal methacrylate or 1,4-butanediol dimethacrylate with a higher molecular weight and therefore also a lower vapor pressure is preferred to reduce the VOC content.

In a particularly preferred embodiment of the present invention, the (meth)acrylic acid ester monomer is benzyl methacrylate and the compatibilizer is 4-(vinylloxy)butyl methacrylate, 2-(allyloxy)ethyl methacrylate or isoprenol methacrylate.

- The present invention is further directed to a reactive diluent composition comprising:
- (a) 50 wt.% to 99 wt.% of a (meth)acrylic acid ester monomer or a mixture of different (meth)acrylic acid ester monomers;
 - (b) 1 wt.% to 50 wt.% of a compatibilizer, wherein the compatibilizer comprises at least one (meth)acrylate moiety and at least one additional ethylenically unsaturated moiety; and
 - (c) 0 wt.% to 0.5 wt.% of a polymerization inhibitor.

The content of each component (a), (b) and (c) is based on the total amount of the reactive diluent composition. In a particular embodiment, the proportions of (a), (b) and (c) add up to 100 wt.%.

The (meth)acrylic acid ester monomer and the compatibilizer have the meanings as defined further above.

The ratio of the amount of (meth)acrylic acid ester monomer to the amount of compatibilizer is between 1:1 and 70:1 or between 3:1 and 40:1 or between 10:1 and 25:1 and preferably is 20:1.

In order to prevent undesirable polymerization, polymerization inhibitors (stabilizers) can be used in the reactive diluent composition according to the present invention. Within the context of the present invention, the terms "(polymerization) inhibitor" and "stabilizer" are used synonymously. Advantageously, the polymerization inhibitor is selected from the group consisting of hydroquinones, hydroquinone ethers such as hydroquinone monomethyl ether or di-*tert*-butylcatechol, phenothiazine, N,N'-(diphenyl)-p-phenylenediamine, 4-hydroxy-2,2,6,6-

- tetramethylpiperidin-1-oxyl, p-phenylenediamine, methylene blue or sterically hindered phenols. Preferably, the polymerization inhibitor is selected from hydroquinone monomethyl ether, phenothiazine, 2,4-dimethyl-6-tert-butylphenol, 2,6-di-tert-butyl-4-methyl-phenol, octadecyl-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate (such as IRGANOX 1076) and 4-hydroxy-2,2,6,6-tetramethylpiperidin-1-oxyl, and mixtures thereof.

Further, the present invention pertains to a curable resin composition comprising at least an unsaturated polyester resin and the reactive diluent composition described above.

- 10 In a preferred embodiment, the curable resin composition comprises:
- (a) 30 wt.% to 65 wt.% of an unsaturated polyester resin;
 - (b) 35 wt.% to 70 wt.% of the reactive diluent composition; and
 - (c) 0 wt.% to 20 wt.% of one or more further organic or inorganic additives.
- 15 The content of each component (a), (b) and (c) is based on the total amount of the curable resin composition. In a particular embodiment, the proportions of (a), (b) and (c) add up to 100 wt.%.

- Suitable UP resins to be cured by the process of the present invention are so-called ortho-resins, iso-resins, iso-NPG resins, and dicyclopentadiene (DCPD) resins. UP resins as defined above are
- 20 commonly known and commercially available.

- For example, ortho-resins are based on phthalic anhydride, maleic anhydride, or fumaric acid and glycols, such as ethylene glycol, diethylene glycol, triethylene glycol, 1,2-propylene glycol, 1,3-propylene glycol, dipropylene glycol, tripropylene glycol, neopentyl glycol or hydrogenated bisphenol A. Commonly, the ones derived from 1,2-propylene glycol are used in combination with a
- 25 reactive diluent. Iso-resins are usually prepared from isophthalic acid, maleic anhydride or fumaric acid, and the glycols. These resins may typically contain a higher level of reactive diluent than the ortho-resins. Bisphenol-A-fumarates are based on ethoxylated bisphenol-A and fumaric acid. Chlorendics are resins prepared from chlorine/bromine containing anhydrides or phenols in the
- 30 preparation of UP-resins.

- The curable resin composition may further comprise organic or inorganic additives, such as fillers, fibers, pigments, dispersants, inhibitors, co-agents, and promoters. Examples of fibers for the production of fiber-reinforced plastics are glass fibers, carbon fibers, aramid fibers, polyamide
- 35 fibers, boron fibers, ceramic fibers, metal fibers, and natural fibers (e.g. jute, kenaf, industrial hemp, flax (linen), ramie, etc.) or any combination thereof. The fiber content depends on the fiber type, the production process used and the final application area. For example, in SMC formulations e.g. glass fiber contents are preferably up to 35wt% in combination with a high filler content up to 40wt%. The resin content in SMC applications is preferably between 10wt% to 20wt%. BMC
- 40 formulations contain a higher filler content with preferably 60wt% and a lower fiber content with preferably 15wt%. In hand lay-up a fiber content of up to 60wt% is preferred. In spray-up

applications a moderate glass fiber content of 30-35wt% is preferred mainly using chopped glass fibers. In filament winding and pultrusion 30-80wt% glass rovings are used.

5 The curable resin composition may comprise at least one filler. Such filler may be selected from the group consisting of calcium carbonate, barium sulfate, quartz, talc, calcium sulfate, calcium silicate and/or kaolin. For flame retardancy, ATH (aluminum trihydroxide) or antimony oxides are added as fillers. Alternatively, or in addition thereto, the fiber-reinforced resin may also comprise at least one further additive selected from the group consisting of inhibitors, retarders, thixotropes (such as fumed silica), and/or UV absorbers, or mixtures thereof.

10

As pigments the curable resin composition may further comprise iron oxide, titanium dioxide, zinc sulfide, zinc oxide and/or organic or inorganic color pigments.

15 As promoters carboxylate salts of ammonium, alkali metals or alkaline earth metals and 1,3-diketones are suitable, e.g. acetyl acetone or diethyl acetoacetamide.

In addition to the above, the present invention provides a pre-accelerated formulation comprising the reactive curable resin composition described above, and at least one accelerator. Suitable accelerators are cobalt(II) salts or complexes e.g. cobalt halides, nitrates, sulfates, sulfonates, 20 phosphates, phosphonates, oxides, or carboxylates. Suitable carboxylates are e.g. lactate, 2-ethyl hexanoate, acetate, propionate, butyrate, oxalate, laurate, oleate, linoleate, palmitate, stearate, acetyl acetate, octanoate, nonanoate, heptanoate, neodecanoate, or naphthenate. The cobalt(II) salt or complex is preferably a cobalt alkyl carboxylate, such as cobalt(II) ethylhexanoate, cobalt(II) octanoate, or cobalt acetylacetonates or cyclopentadienyl-based complexes of cobalt. Cobalt(2-ethylhexanoate), cobalt (neodecanoate) or cobalt (naphthenate) are particularly preferred. 25 Additionally, polymer-bound cobalt accelerators are suitable.

Alternatively, accelerators based on a copper(I) or copper (II) salt or complex are suitable. Suitable copper salts or complexes are e.g. copper halides (such as chlorides), nitrates, sulfates or alkyl 30 carboxylates. Suitable carboxylates are e.g. lactate, 2-ethyl hexanoate, acetate, propionate, butyrate, oxalate, laurate, oleate, linoleate, palmitate, stearate, acetyl acetate, octanoate, nonanoate, heptanoate, neodecanoate, or naphthenate. The copper(I) or copper (II) salt or complex is preferably an alkyl carboxylate. Copper(II) acetonate and Copper(II)-(2-ethylhexanoate) is particularly preferred.

35

Alternatively, accelerators based on iron salt or complex are suitable. Preferably, said iron(II) coordination compound is selected from the group consisting of iron(II) species ligated with mono- and polydentate N and/or O-donor ligands. Alternatively, the iron salt or complex present in the accelerator system (b) may also be selected from the group consisting of iron halides, 40 carboxylates, 1,3-dioxo complexes and cyclopentadienyl-based iron complexes.

Curing is generally started by either adding an accelerator and an initiator to the curable resin composition according to the present invention, or by adding an initiator to the pre-accelerated formulation.

- 5 Accordingly, the present invention relates to a styrene-free method of curing unsaturated polyester resins, the method comprising
- (a) providing a curable resin composition as described above, or, alternatively, a pre-accelerated formulation as described above,
 - (b) optionally adding at least one organic or inorganic additive as described above, and
 - 10 (c) initiating the curing process by adding an initiator.

- Peroxides suitable for curing the UP resins include inorganic peroxides and organic peroxides, such as conventionally used ketone peroxides, peroxyesters, diaryl peroxides, dialkyl peroxides, and peroxydicarbonates, but also peroxyarbonates, peroxyketals, hydroperoxides, diacyl
- 15 peroxides, and hydrogen peroxide. Preferred peroxides are organic hydroperoxides, ketone peroxides, peroxyesters, and peroxyarbonates. Even more preferred are hydroperoxides and ketone peroxides. Preferred hydroperoxides include cumyl hydroperoxide, 1,1,3,3-tetramethylbutyl hydroperoxide, tert-butyl hydroperoxide, isopropylcumyl hydroperoxide, tert-amyl hydroperoxide, 2,5-dimethylhexyl-2,5-dihydroperoxide, pinane hydroperoxide, paramenthane hydroperoxide,
- 20 terpene hydroperoxide and pinene hydroperoxide. Preferred ketone peroxides include methyl ethyl ketone peroxide, methyl isopropyl ketone peroxide, methyl isobutyl ketone peroxide, cyclohexanone peroxide, and acetylacetone peroxide. Mixtures of two or more peroxides can also be used; for instance, a combination of a hydroperoxide or ketone peroxide with a peroxyester.
- 25 A particularly preferred peroxide is methyl ethyl ketone peroxide. The skilled person will understand that these peroxides can be combined with conventional additives, for instance fillers, pigments, and phlegmatizers. Examples for phlegmatizers are hydrophilic esters and hydrocarbon solvents. The amount of peroxide to be used for curing the resin is preferably at least 0.1 per hundred resin (phr), more preferably at least 0.5 phr, and most preferably at least 1 phr. The amount of peroxide
- 30 is preferably not more than 8 phr, more preferably not more than 5 phr, most preferably not more than 2 phr.

- Advantageously, the initiator is an organic peroxide, preferably selected from the group consisting of methyl ethyl ketone peroxide (MEKP), benzoyl peroxide (BPO), cumene hydroperoxide (CuHP),
- 35 or any combination thereof.

- The curing process for the product of fibre-reinforced plastics can be carried out at any temperature from -15°C up to 250 °C, depending on the initiator system, the accelerator system, the compounds to adapt the curing rate, and the resin composition to be cured. Preferably, it is carried out at
- 40 ambient temperatures commonly used in applications such as hand lay-up, spray-up, filament winding, resin transfer moulding, coating (e.g. gelcoat and standard coatings), button production,

centrifugal casting, corrugated sheets or flat panels, relining systems, kitchen sinks via pouring compounds, etc. However, it can also be used in sheet molding compounds (SMC), bulk molding compounds (BMC), pultrusion techniques, and the like, for which temperatures up to 180°C, more preferably up to 150°C, most preferably up to 100°C, are used.

5

In general, fiber-reinforced resins (fiber-reinforced plastics - FRP) have the advantages of high relative strength, good surface condition of products, high corrosion resistance and high chemical resistance. With such advantages, these are used essentially as parts in housing materials, industrial materials, tanks, containers, ships, cars, trains, etc.

10

Examples

1 Synthetic Procedures for Monomers

1.1 General Synthetic Procedures for Monomers

All reactions and product manipulations were carried out in common laboratory glassware under ambient conditions. Methyl (meth)acrylate, (meth)acrylic anhydride (MAAH), (meth)acryloyl chloride, 2-allyloxyethanol, 4-hydroxybutylvinylether, isoprenol, eugenol, 2-((allyloxy)methyl)-2-ethylpropane-1,3-diol, 2,2-bis((allyloxy)methyl)butan-1-ol, were obtained from commercial/industrial suppliers and used as received without further purification.

20 Eugenol methacrylate was synthesized following literature procedures, e.g. as described in Stanzione, J.F., III, Sadler, J.M., La Scala, J.J. and Wool, R.P. (2012), Lignin Model Compounds as Bio-Based Reactive Diluents for Liquid Molding Resins. ChemSusChem, 5: 1291-1297.

25 Isoprenol methacrylate was synthesized following literature procedures, e.g. as described in Jacob M. Berlin, Katie Campbell, Tobias Ritter, Timothy W. Funk, Anatoly Chlenov, and Robert H. Grubbs, Ruthenium-Catalyzed Ring-Closing Metathesis to Form Tetrasubstituted Olefins Org. Lett. 2007 9 (7), 1339-1342

30 4-(Vinylxy)butyl methacrylate was synthesized following literature procedures, e.g. as described in Farzad Seidi,^a Victor Druet,^a Nguyen Huynh,^a Treethip Phakkeeree^a and Daniel Crespy Hemiaminal ether linkages provide a selective release of payloads from polymer conjugates Chem. Commun., 2018,54, 13730-13733

35 2-(Allyloxy)ethyl methacrylate was synthesized following literature procedures, e.g. as described in Xiao-Guang Sun, Craig L. Reeder, and John B. Kerr Synthesis and Characterization of Network Type Single Ion Conductors Macromolecules 2004, 37, 6, 2219–2227

40 2,2-bis((allyloxy)methyl)butyl methacrylate and 2-((allyloxy)methyl)-2-ethylpropane-1,3-diyl dimethylacrylate were synthesized following literature procedures, e.g. as described in US 4640940 A.

2 General Analytical Techniques for Monomers

NMR spectra were recorded on Bruker Avance 300 or 400 spectrometers at 300 K unless otherwise noted and internally referenced to residual solvent resonances (^1H NMR: THF-d8: 1.72 ppm, C_6D_6 : 7.16 ppm, toluene-d8 (tol-d8): 2.08 ppm; CDCl_3 : 7.26 ppm. $^{13}\text{C}\{^1\text{H}\}$ NMR: THF-d8: 25.31 ppm, C_6D_6 : 128.06 ppm, CDCl_3 : 77.16 ppm). Chemical shifts δ are given in ppm referring to external standards of tetramethylsilane (^1H , $^{13}\text{C}\{^1\text{H}\}$). ^1H and ^{13}C NMR signals were assigned partially based on 2D NMR spectra (^1H , ^1H -COSY; ^1H , ^{13}C -HSQC; ^1H , ^{13}C -HMQC).

10 3 Polymerization and Composite Resins

3.1 Components used

Table 1: Components used

Component	
Standard unsaturated polyester resin (UPR 1) (based on isophthalic acid and standard glycols, solid)	Resin
VISIOMER® GLYFOMA	Reactive diluent
VISIOMER® BNMA	Reactive diluent
VISIOMER® BDGMA	Reactive diluent
VISIOMER® PEG200DMA	Reactive diluent
MMA (Roehm)	Reactive diluent
Styrene (Merck)	Reactive diluent
VISIOMER® 1,4-BDDMA	Reactive diluent
VISIOMER® EGDMA	Reactive diluent
4-(Vinylxy)butyl methacrylate	Compatibilizer
Isoprenol methacrylate	Compatibilizer
2-(Allyloxy)ethyl methacrylate	Compatibilizer
Eugenol methacrylate	Compatibilizer
TMP Diallylether methacrylate = 2,2-Bis((allyloxy)methyl)butyl methacrylate	Compatibilizer
TMP Monoallylether dimethacrylate = 2-((allyloxy)methyl)-2-ethylpropane-1,3-diyl dimethylacrylate	Compatibilizer
Butanox M-50 (MEKP, Nouryon)	Initiator
Butanox P-50 (MIPKP, Nouryon)	Initiator
Co(II)-2-Ethylhexanoate, 65%-solution (11% Co metal content, Sigma-Aldrich)	Cobalt-based accelerator
Nouryact CF12 (1.5-1,7% Cu metal content), Nouryon	Copper-based accelerator

wt% = weight percent

15 phr = parts per hundred resin

As resin is in this case the fully formulated resin defined including the reactive diluent.

- MPa = Megapascal
HEMA = hydroxethyl methacrylate
BDGMA = butyl diglycol methacrylate
MMA = methyl methacrylate
5 BNMA = benzyl methacrylate
GLYFOMA = glycerol formal methacrylate
1,4-BDDMA = 1,4-butanediol dimethacrylate
EGDMA = ethylene glycol dimethacrylate
MEKP = methyl ethyl ketone peroxide
10 MIPKP = methyl isopropyl ketone peroxide
TMP = 1,1,1-trimethylol propane

3.2 Methods

3.2.1 Bulk polymerization and Determination of the Polymerization Time

- 15 For the bulk polymerization stock solutions of the UPR resin and the various reactive diluents were prepared. The solid UPR resin was melted for 3h at 100°C. The reactive diluent was added to the heated resin and homogenized on a roller bed for 12- 24h. The prepared stock solution was mixed with the different compatibilizers according to table 1-3. The accelerator was added, and the mixture was homogenized by stirring for 2min followed by the addition of the initiator solution. The
20 mixture was stirred again for 1.5 min and then transferred into a standard test tube (18x180mm) and cured. The cured resins were post-cured for 8h at 80°C in a drying oven.

3.2.2 Mechanical testing

- The tensile testing was performed according to EN ISO 527-1. Approx. 110-115g of resin
25 formulation was used to cast films (calculated on 4mm wet film thickness) The films were cured at RT over 24h. All samples were post-cured for 8h at 80°C in the oven prior to the tensile testing.

Table 2: Curing behavior of UP Resin in combination with different reactive diluents

Example	Resin	[wt%]	Reactive diluent	[wt%]	Compatibilizer	[wt%]	Initiator	[phr]	Accelerator	[phr]	Appearance cured resin
Ref 1	UPR 1	60	HEMA	40	None	0	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	turbid
Ref 2	UPR 1	60	BDGMA	40	None	0	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	turbid
Ref 3	UPR 1	60	MMA	40	None	0	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	turbid
Ref 4	UPR 1	60	Styrene	40	None	0	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	clear
Ref 5	UPR 1	60	MMA	40	None	0	MIPKP	2	Nouryact CF12r	2	turbid
Ref 6	UPR 1	60	BNMA	40	None	0	MEKP	2	Cobalt	0.22	turbid
1	UPR 1	60	MMA	38	4-(Vinylxy)butyl methacrylate	2	MIPKP	2	Nouryact CF12r	1	clear
2	UPR 1	60	MMA	35	4-(Vinylxy)butyl methacrylate	5	MIPKP	2	Nouryact CF12r	1	clear
3	UPR 1	60	MMA	30	4-(Vinylxy)butyl methacrylate	10	MIPKP	2	Nouryact CF12r	1	clear
4	UPR 1	60	GLYFOMA	38	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	clear
5	UPR 1	60	GLYFOMA	35	4-(Vinylxy)butyl methacrylate	5	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	clear
6	UPR 1	60	GLYFOMA	30	4-(Vinylxy)butyl methacrylate	10	MEKP	2	Co(II)-2-Ethylhexanoate	0.22	clear

Example	Resin	[wt%]	Reactive diluent	[wt%]	Compatibilizer	[wt%]	Initiator	[phr]	Accelerator	[phr]	Appearance cured resin
7	UPR 1	60	GLYFOMA + 1,4-BDDMA	28 + 10	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	clear
8	UPR 1	60	GLYFOMA + 1,4-BDDMA	18 + 20	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	clear
9	UPR 1	60	BNMA + 1,4-BDDMA	28 + 10	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	clear
10	UPR 1	60	BNMA + 1,4-BDDMA	18 + 20	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	clear
11	UPR 1	60	cHMA + 1,4-BDDMA	28 + 10	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	slightly turbid
12	UPR 1	60	cHMA + 1,4-BDDMA	18 + 20	4-(Vinylxy)butyl methacrylate	2	MEKP	2	Co(II)-2- Ethylhexanoate	0.22	turbid

The reference examples show that without the addition of a compatibilizer turbid polymer resins are formed. Turbidity indicates phase separation and therefore an incompatibility of the reactive diluent with the UPR resin. Examples 1-6 show that the addition of a compatibilizer leads to the formation of clear polymers without any indication of phase separation. Example 7-12 show that also a mixture of reactive diluents can be employed. Example 11-12 show that the performance of the compatibilizer also depends on the right choice of reactive diluent. The performance of the compatibilizer is independent of the used curing system as shown using two different peroxides and two different accelerators.

Table 3: Curing behavior of UP Resin in combination with different methacrylate-based reactive diluents and different compatibilizers cured with 2phr MEKP and 0.22phr Co(II)-2-Ethylhexanoate

Example	UPR resin	[wt%]	Reactive Diluent	[wt%]	Compatibilizer	[wt%]	Appearance cured Resin
13	UPR 1	55	EGDMA	43	Isoprenol methacrylate	2	Clear
14					4-(Vinylloxy)butyl methacrylate	2	Clear
15					2-(Allyloxy)ethyl methacrylate	2	Clear
16					TMP-Diallylether methacrylate	2	Clear
17					TMP-Monoallylether dimethacrylate	2	Hazy
18					Eugenol methacrylate	2	Clear
19					Isoprenol methacrylate	2	Clear
20					4-(Vinylloxy)butyl methacrylate	2	Clear
21	UPR 1	55	1,4-BDDMA	43	2-(Allyloxy)ethyl methacrylate	2	Clear
22					TMP-Diallylether methacrylate	2	Clear
23					TMP-Monoallylether dimethacrylate	2	Hazy
24					Eugenol methacrylate	2	Clear
25	UPR1	60	EGDMA	38	4-(Vinylloxy)butyl methacrylate	2	Clear

5 The addition of the tested compatibilizer compounds show, except for compatibilizer TMP-monoallylether dimethacrylate, clear polymer formation.

Table 4: Tensile Testing of UPR resin with benzyl methacrylate as reactive diluent in combination with and without compatibilizer cu with 2phr MEKP and 0.22phr Co(II)-2-Ethylhexanoate

Example	Resin	[wt%]	Reactive diluent	[wt%]	Compatibilizer	[wt%]	E-Modulus [MPa]	Shear Strength [MPa]	Max. Elongation at break [%]
26	UPR 1	55	BNMA	45	---	---	3299	16.3	0.5
27	UPR 1	55	BNMA	43	4-(Vinylloxy)butyl methacrylate	2	3404	59.3	2.2
28	UPR1	55	Styrene	45	--	--	3515	73.2	2.5

5 The mechanical testing shows that the styrene free UPR formulations using benzyl methacrylate as reactive diluents in combination with a compatibilizer result in comparable mechanical properties as the standard styrene-based UPR resin.

CLAIMS

1. A reactive diluent composition comprising a (meth)acrylic acid ester monomer and a
5 compatibilizer;
wherein the compatibilizer comprises at least one (meth)acrylate moiety and at least one additional
ethylenically unsaturated moiety and is selected from the group consisting of vinyl ether
(meth)acrylates, allyl ether (meth)acrylates and alkenyl (meth)acrylates, and
wherein the (meth)acrylic acid ester monomer and the compatibilizer are different chemical
10 compounds.
2. The reactive diluent composition according to claim 1, wherein the vinyl ether
(meth)acrylates are selected from monovinyl ether mono(meth)acrylates, monovinyl ether
di(meth)acrylates, monovinyl ether tri(meth)acrylates, monovinyl ether tetra(meth)acrylates,
15 divinyl ether mono(meth)acrylates, divinyl ether di(meth)acrylates, divinyl ether tri(meth)acrylates,
trivinyl ether mono(meth)acrylates and trivinyl ether di(meth)acrylates.
3. The reactive diluent composition according to any one of the preceding claims, wherein the
allyl ether (meth)acrylates are selected from monoallyl ether mono(meth)acrylates, monoallyl ether
20 di(meth)acrylates, monoallyl ether tri(meth)acrylates, monoallyl ether tetra(meth)acrylates,
diallyl ether mono(meth)acrylates, diallyl ether di(meth)acrylates, diallyl ether tri(meth)acrylates,
triallyl ether mono(meth)acrylates and triallyl ether di(meth)acrylates.
4. The reactive diluent composition according to any one of the preceding claims, wherein the
25 alkenyl (meth)acrylates are selected from mono, di, tri and tetra(meth)acrylates containing one or
more ethylenically unsaturated alkenyl (C=C) moiety being different from (meth)acrylate.
5. The reactive diluent composition according to any one of the preceding claims, wherein the
compatibilizer is selected from the group consisting of 4-(vinyl oxy)butyl methacrylate, 2-
30 (allyl oxy)ethyl methacrylate, isoprenol methacrylate, 2,2-bis((allyl oxy)methyl)butyl methacrylate, 2-
((allyl oxy)methyl)-2-ethylpropane-1,3-diyl bis(2-methylacrylate), and eugenol methacrylate.
6. The reactive diluent composition according to any one of the preceding claims, wherein the
compatibilizer is 4-(vinyl oxy)butyl methacrylate, 2-(allyl oxy)ethyl methacrylate, and isoprenol
35 methacrylate.
7. The reactive diluent composition according to any one of the preceding claims, wherein the
(meth)acrylic acid ester monomer is selected from alkyl (meth)acrylates with linear or branched
alkyl C₁₋₂₀, (alkyl) aryl (meth)acrylates, hydroxy alkyl (meth)acrylates, (poly) ether methacrylates,
40 and di, tri, tetra-methacrylates.

8. The reactive diluent composition according to any one of the preceding claims, wherein the (meth)acrylic acid ester monomer is selected from methyl methacrylate, glycerol formal methacrylate, isopropylidene glycerol methacrylate, benzyl methacrylate, cyclohexyl methacrylate, isobornyl methacrylate, 1,4-butanediol dimethacrylate, 1,3-butanediol dimethacrylate, polyethyleneglycol 200 dimethacrylate, ethylene glycol dimethacrylate, butyl diglycol methacrylate and ethyltriglycol methacrylate.
9. The reactive diluent composition according to any one of the preceding claims, wherein the (meth)acrylic acid ester monomer is benzyl methacrylate and the compatibilizer is 4-(vinylloxy)butyl methacrylate, 2-(allyloxy)ethyl methacrylate or isoprenol methacrylate.
10. The reactive diluent composition according to any one of the preceding claims, wherein the ratio of the amount of (meth)acrylic acid ester monomer to the amount of compatibilizer is between 1:1 and 70:1
11. The reactive diluent composition according to any one of the preceding claims, wherein the ratio of the amount of (meth)acrylic acid ester monomer to the amount of compatibilizer is between 10:1 and 25:1.
12. The reactive diluent composition according to any one of the preceding claims, further comprising a polymerization inhibitor.
13. The reactive diluent composition according to claim 9, wherein the polymerization inhibitor is selected from the group consisting of hydroquinones, hydroquinone ethers, phenothiazine, N,N'-(diphenyl)-p-phenylenediamine, 4-hydroxy-2,2,6,6-tetramethylpiperidin-1-oxyl, p-phenylene-diamine, methylene blue or sterically hindered phenols.
14. The reactive diluent composition according to any one of the preceding claims, comprising:
- (a) 50 wt.% to 99 wt.% of the (meth)acrylic acid ester monomer;
 - (b) 1 wt.% to 50 wt.% of the reactive diluent composition; and
 - (c) 0 wt.% to 0.5 wt.% of the inhibitor.
15. A curable resin composition comprising at least an unsaturated polyester resin and the reactive diluent composition according to any one of claims 1 to 14.
16. The curable resin composition according to claim 15, further comprising at least one organic or inorganic additive.

17. A pre-accelerated formulation comprising the curable resin composition according to claim 15 or 16, and at least one accelerator.
18. A method of curing unsaturated polyester resins, the method comprising:
- 5 (a) providing a curable resin composition according to any one of claims 15 or 16, or, alternatively, a pre-accelerated formulation according to claim 17,
- (b) optionally adding at least one organic or inorganic additive, and
- (c) initiating the curing process by adding an initiator.