

Polymer Composition, its method of preparation and use

[Field of the invention]

[001] The present invention relates to a polymeric processing aid
5 its composition and its process of preparation and its use.

[002] In particular the present invention it relates to a polymeric
processing aid and its use for highly filled halogen containing
thermoplastic polymers.

[003] More particularly the present invention relates to a highly
10 filled halogen containing polymer composition with a polymeric
processing aid, its composition and its process of preparation.

[Technical problem]

[004] Fillers are used in thermoplastic polymer compositions in
15 general and in halogenated polymer compositions in particularly
for a variety of reasons. They can extend the composition,
increase stiffness and strength, and shorten cycle times. They
prevent hang-up in dies and neutralize the products of
degradation. Fillers cans also be used to add color, opacity and
20 conductivity or they can be used as a low cost material that
lowers the cost of the composition as the filler is less expensive
the other ingredients of the formulation.

[005] However the addition of filler can change the fusion
characteristics of the polymer composition. Proper fusion is
25 necessary to obtain good physical properties.

[006] Polymer compositions comprising polymers with specific
characteristic (such as polymer composition, glass transition
temperature or specific molecular weight range for naming some
characteristics) are used as additives for thermoplastic polymer
30 compositions in general and in halogenated polymer compositions in
particularly in order to enhance the processing behavior of these
various polymers or plastic resin or to improve their performance.
Therefor these additives are also called processing aids.

[007] The additive polymer composition is compatible with
35 thermoplastic polymer compositions in general and in halogen
containing polymer compositions in particularly.

[008] Processing aids in small quantities in thermoplastic polymer compositions in general and in halogenated polymer compositions in particular can improve the processing characteristics through an acceleration of the fusion process of said thermoplastic polymer compositions in general and homogenization in halogen containing polymer compositions in particular.

[009] With a filler added in large quantities to the composition, the processing aid used for the non-filled composition does not possess the same performance as in a highly filled composition, especially in view of fusion efficiency of the composition.

[010] The objective of the present disclosure is to propose a polymer composition which acts as processing aid for highly filled halogen containing polymer compositions.

[011] An objective of the present disclosure is also to have a polymer composition that can be used to optimize the melt behaviour especially the speed of fusion of highly filled halogen containing polymer compositions.

[012] An additional objective of the present disclosure is the reduction of the price of a polymer composition which acts as processing aid for the highly filled halogen containing polymer compositions by addition of low cost components without influencing the fusion efficiency or decrease too much the fusion efficiency.

[013] Still another objective of the present disclosure is a method for manufacturing a polymer composition which acts as processing aid for highly filled halogen containing polymer compositions.

[014] Still an additional objective is having a process for preparing polymer composition that can be used to help the transformation and to increase the melt behaviours of highly filled halogen containing polymer compositions.

[BACKGROUND OF THE INVENTION]Prior art

5 [015] The document US 2009/0111915 discloses acrylic copolymers for use in highly filled compositions. In particular the document disclosed filled PVC materials as a composition for flooring comprising 70 to 95wt filler, 1 to 15wt%PVC and 0.5 to 4wt% of acrylic copolymer or a composition for siding or pipe comprising 15 to 35wt filler, 50 to 95wt%PVC and 0.25 to 6wt% of acrylic copolymer.

10 [016] The document WO 2010/099160 discloses composite polymer modifiers. The document discloses a composite polymer modifier consisting of 99wt% to 1wt% of inorganic filler and from 1wt% to 99wt% of a polymeric processing aid and 0wt% to 80% of an impact modifier.

15 [017] The document US 3,373,229 discloses vinyl polymer compositions. The compositions comprises polyvinyl chloride and high molecular weight polymers of methyl methacrylate or copolymers of methyl meth acrylate with a small amount of an alkyl acrylate as processing aid. The composition might comprise a
20 filler.

[018] The document US 4,329,276 discloses molding components. The molding component is based on polyvinyl chloride comprising a
25 component composition. The component composition and comprises between 40-85wt% of an acrylic polymer preferably having a Tg between 70°C and 90°C, and comprising preferably methyl methacrylate and butyl methacrylate in a proportion 50/50 to 85/15.

30 [019] The document US2012/189837 discloses an acrylic process aid for vinyl foam extrusion. The acrylic process aid is an acrylic copolymer preferably having a Tg less than 60°C. In the examples a copolymer of methyl methacrylate (70%) with butyl acrylate (30%)
35 is disclosed. The acrylic copolymer used does not comprise a filler

[020] None of the prior art documents discloses a highly filled polymer composition comprising a halogen containing thermoplastic polymer and a (meth)acrylic copolymer with a filler where a part of the filler is added to the composition with the (meth)acrylic copolymer and a part of the filler is added to the composition with the halogen containing thermoplastic polymer.

[Brief description]

[021] Surprisingly it has been found that a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer, gives a composition with an acceptable fusion time.

[021a] In an aspect, there is provided a composition comprising:

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate
- b) a filler (F) or a mixture of two fillers (F1) and (F2) which is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite,
- c) a halogen containing thermoplastic polymer

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least

50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

[022] Surprisingly it has also been found that a process for preparing a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

said process comprises the step of

blending a compositions P1 with a halogen containing polymer and a filler (F) or (F2) characterized that

the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) and

wherein the glass transition temperature Tg of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F1) and (F2) together is more than 40phr in view of

the halogen containing thermoplastic polymer, gives a composition with a acceptable fusion time.

[022a] In an another aspect, there is provided a process for preparing a composition as defined above, said process comprises the step of

blending a compositions P1 with a halogen containing polymer and a filler (F) or (F2) characterized that the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1), wherein the filler (F), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite and wherein the glass transition temperature Tg of the (meth)acrylic copolymer is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

[023] Surprisingly it has also been found that a process for preparing a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

said process comprises the step of

blending two compositions P1 and P2 characterized that
 the composition P1 comprises an (meth)acrylic copolymer (A1)
 or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
 and a filler F1 and

the composition P2 a halogen containing polymer and a filler F2

wherein the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F1) and (F2) together is more than 40phr in view of the halogen containing thermoplastic polymer, gives a composition with a acceptable fusion time.

[023a] In another aspect, there is provided a process for preparing a composition as defined above, said process comprises the step of blending two compositions P1 and P2 characterized that

the composition P1 comprises an (meth)acrylic copolymer (A1) or mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1) and

the composition P2 a halogen containing polymer and a filler (F) or (F2), wherein the filler (F), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite,

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

[024] Surprisingly it has also been found that a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) can

be used to fuse in an acceptable time a composition comprising a halogen containing polymer and a filler (F) or (F2) wherein the glass transition temperature T_g of the (meth)acrylic copolymer is more important than 95°C and that the quantity of the filler (F1) and (F2) together is more than 40phr in view of the halogen containing thermoplastic polymer.

[025] Surprisingly it has also been found that a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) can be used to fuse in an acceptable time a composition P2

comprising halogen containing polymer and a filler (F) or (F2) wherein the glass transition temperature T_g of the (meth)acrylic copolymer is more important than 95°C and that the quantity of the filler (F1) and (F2) together is more than 40phr in view of the halogen containing thermoplastic polymer.

[025a] In another aspect, there is provided the use of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1) to decrease the fusion time of a composition comprising a halogen containing polymer and a filler (F) or (F2), wherein the filler (F1), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite, characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

[025b] In another aspect, there is provided the use of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F1) to decrease the fusion time of composition P2 comprising halogen containing polymer and a filler (F2), wherein the filler (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite, characterized that

the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

[025c] In another aspect, there is provided an article comprising a composition as defined above or a composition prepared by a process as defined above.

[Detailed description of the invention]

[026] According to a first aspect, the present invention relates to a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer.

[027] In a second aspect the present invention relates to a preparing a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

said process comprises the step of

blending a compositions P1 with a halogen containing polymer and a filler (F) or (F2) characterized that

the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) and

wherein the glass transition temperature Tg of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is

more than 40phr relative to the halogen containing thermoplastic polymer.

[028] In a third aspect the present invention relates to a process
5 for preparing a composition comprising

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b)
- b) a filler (F) or a mixture of two fillers (F1) and (F2)
- c) a halogen containing thermoplastic polymer

10 said process comprises the step of

blending two compositions P1 and P2 characterized that

the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) and

15 the composition P2 a halogen containing polymer and a filler (F) or (F2)

wherein the glass transition temperature Tg of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity
20 of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer.

[029] In a fourth aspect the present invention relates to the use
25 of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) can be used to decrease the fusion time of composition comprising a halogen containing polymer and a filler (F) or (F2) wherein the glass transition temperature Tg of the
30 (meth)acrylic copolymer is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer.

35 **[030]** In a fifth aspect the present invention relates to the use of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a

filler F1 to decrease the fusion time of composition P2 comprising halogen containing polymer and a filler F2 wherein the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more important than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr relative to the halogen containing thermoplastic polymer.

[031] By the term "copolymer" as used is denoted that the polymer consists of at least two different monomers.

[032] By the term "(meth)acrylic" as used is denoted all kind of acrylic and methacrylic monomers.

[033] By the term "(meth)acrylic polymer" as used is denoted that the (meth)acrylic polymer comprises essentially polymers comprising (meth)acrylic monomers that make up 50wt% or more of the (meth)acrylic polymer.

[034] By "multistage polymer" as used is denoted a polymer formed in sequential fashion by a multi-stage polymerization process. Preferred is a multi-stage emulsion polymerization process in which the first polymer is a first-stage polymer and the second polymer is a second-stage polymer, i.e., the second polymer is formed by emulsion polymerization in the presence of the first emulsion polymer.

[035] By the term "dispersion" as used is denoted a colloidal system with a continuous liquid phase and a discontinuous solid phase that is distributed throughout the continuous phase.

[036] By the term "emulsion" as used is denoted a liquid/liquid mixture of a liquid discontinuous phase in a liquid continuous phase.

[037] By the term "PVC" as used is understood polyvinyl chloride in form of homopolymer or copolymer comprising at least 50wt% of vinyl chloride.

[038] By the term "filler" as used is understood a solid extender added to a polymer in order to enhance properties and/or reduce costs.

[039] By the abbreviation "phr" is meant parts per hundred parts of resin. For example 15phr of filler in a PVC formulation means that 15kg of filler are added to 100kg of PVC.

5 **[040] With regard to the composition** of the present invention, it comprises more than 40phr of filler (F) or a mixture of two fillers (F1) and (F2) relative to the halogen containing thermoplastic polymer.

10 **[041]** Preferably the composition, of the present invention comprises less than 350phr of filler (F) or a mixture of two fillers (F1) and (F2) relative to the halogen containing thermoplastic polymer.

15 **[042]** More preferably the composition, of the present invention comprises between 40phr and 350phr, still more preferably between 40phr and 300phr, advantageously between 50phr and 300phr and more advantageously between 50phr and 250phr and most advantageously between 50phr and 200phr of filler (F) or a mixture of two fillers (F1) and (F2) relative to the halogen containing thermoplastic polymer.

20 **[043] The polymer composition** or composition according to the invention, it comprises between 0.01phr and 20phr, preferably between 0.05 and 17phr, more preferably between 0.1phr and 15phr, advantageously between 0.15phr and 12phr and more advantageously between 0.15phr and 10phr of the (meth)acrylic copolymer (A1) or
25 the mixture of two (meth)acrylic copolymers (A1a) and (A1b).

[044] In a first most advantageously embodiment the composition according to the invention it comprises between 0.15phr and 9phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b).

30 **[045]** In a second most advantageously embodiment the composition according to the invention it comprises between 0.15phr and 4phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b).

35 **[046]** According to the invention a part of the filler (F) or a part of the mixture of two fillers (F1) and (F2) is added to the composition with the (meth)acrylic copolymer (A1) or the mixture of

two (meth)acrylic copolymers (A1a) and (A1b). The other part of the filler (F) or the other part of the mixture of two fillers (F1) and (F2) is added to the composition either apart or already with halogen containing thermoplastic polymer. By "already with
5 halogen containing thermoplastic polymer" is meant that the said other part of the filler (F) or a part of the mixture of two fillers (F1) and (F2) is added the halogen containing thermoplastic polymer before the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising a part of
10 the filler (F) or a part of the mixture of two fillers (F1) and (F2) is added.

[047] According to a variation of the invention a part of the filler (F) or a mixture of two fillers (F1) and (F2) is added to the composition with the (meth)acrylic copolymer (A1) or the
15 mixture of two (meth)acrylic copolymers (A1a) and (A1b) and another part of the filler (F) or a mixture of two fillers (F1) and (F2) is added to the composition with halogen containing thermoplastic polymer.

[048] Preferably the part of the filler (F) or a mixture of two
20 fillers (F1) and (F2) which is added to the composition apart or which is already with the halogen containing thermoplastic polymer, exceeds in quantity the part of the filler (F) or a mixture of two fillers (F1) and (F2) that is added to the composition with the (meth)acrylic copolymer (A1) or the mixture
25 of two (meth)acrylic copolymers (A1a) and (A1b).

[049] With regard to the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b), it is a (meth) acrylic copolymer comprising at least 50wt% of polymeric units coming from
30 methyl methacrylate.

[050] More preferably the polymer (A1) comprises a comonomer or comonomers which are copolymerizable with methyl methacrylate, as long as polymer (A1) is having a glass transition temperature more important than 95°C.

35 **[051]** More preferably the two (meth)acrylic copolymers (A1a) and (A1b) comprises a comonomer or comonomers which are copolymerizable with methyl methacrylate, as long as the mixture

of two (meth)acrylic copolymers (A1a) and (A1b) is having an average glass transition temperature more important than 95°C.

[052] The comonomer or comonomers in polymer (A1), (A1a) and (A1b) are preferably chosen from (meth)acrylic and/or vinyl monomers.

5 [053] The (meth)acrylic comonomer in (meth)acrylic copolymer (A1) comprises monomers chosen from C1 to C12 alkyl (meth)acrylates. The vinyl comonomer comprises monomers chosen from styrene and substituted styrene. Still more preferably (meth)acrylic comonomer in polymer (A1) comprises monomers of C1 to C4 alkyl methacrylate and/or C1 to C8 alkyl acrylate monomers.

[054] Most preferably the acrylic or methacrylic comonomers of the (meth)acrylic copolymer (A1) are chosen from methyl acrylate, propyl acrylate, isopropyl acrylate, butyl acrylate, tert-butyl acrylate, methyl methacrylate, ethyl methacrylate, butyl
15 methacrylate, isobornyl acrylate and mixtures thereof, as long as (meth)acrylic copolymer (A1) is having a glass transition temperature more important than 95°C .

[055] Preferably the (meth)acrylic copolymer (A1) comprises at least 80wt%, more preferably at least 83wt%, and advantageously at
20 least 86wt% of polymeric units coming from methyl methacrylate.

[056] In a specific embodiment the (meth)acrylic copolymer (A1) is a copolymer of methyl methacrylate with ethyl acrylate and/or butyl acrylate.

25 [057] More preferably the glass transition temperature Tg of the (meth)acrylic polymer (A1) comprising at least 50wt% of polymeric units coming from methyl methacrylate is between 95°C and 130°C, even more preferably between 100°C and 125°C and advantageously between 105°C and 120°C.

30 [058] The glass transition temperature Tg can be estimated for example by dynamic methods as thermo mechanical analysis (DMA).

[059] Preferably the mass average molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers
35 (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol, preferably at least 500 000g/mol, more preferably at least

750 000g/mol, advantageously at least 1 000 000 g/mol and most advantageously at least 1 500 000g/mol.

5 [060] Preferably the mass average molecular weight M_w of the (meth)acrylic **copolymer** (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is less than 20 000 000g/mol, preferably less than 15 000 000g/mol, more preferably less than 12 000 000g/mol, advantageously less than 10 000 000 g/mol and most
10 advantageously less than 9 000 000g/mol.

[061] More preferably the mass average molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is between 300 000g/mol and 20
15 000 000g/mol, still more preferably between 500 000g/mol and 15 000 000g/mol, even more preferably between 1 000 000 g/mol and 12 000 000g/mol and advantageously between 1 500 000g/mol and 10 000 000 g/mol.

20 [062] The (meth)acrylic **copolymer** (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is preferably prepared by an emulsion polymerisation, yielding to an aqueous dispersion of spherical polymer particles of the (meth)acrylic **copolymer** (A1) or
25 the two (meth)acrylic copolymers (A1a) and (A1b).

[063] A possible variation of the method for preparing an aqueous dispersion of spherical polymer particles comprising the (meth)acrylic **copolymer** (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) is by using a multistage process.

30 [064] During one stage of the multistage process the (meth)acrylic **copolymer** (A1) is prepared.

[065] The mixture of two (meth)acrylic copolymers (A1a) and (A1b) can also be prepared by a multistage process. During one stage of the multistage process the (meth)acrylic **copolymer** (A1a) is
35 prepared and during another stage the (meth)acrylic **copolymer** (A1b).

[066] With regard to the spherical polymer particle, it has a weight average particle size between 20nm and 500nm. Preferably the weight average particle size of the polymer is between 50nm and 400nm, more preferably between 75nm and 350nm and
5 advantageously between 80nm and 300nm.

[067] With regard to the filler (F), (F1) and/or (F2), it is an inorganic filler or mineral filler.

[068] With regard to the mineral filler, mention may be made of
10 glass fibers, hollow glass microspheres, inorganic compounds, such as minerals and salts including calcium carbonate (CaCO_3), silica, silicates such as calcium silicate or metasilicate, clay such as bentonite, mica, talc, alumina trihydrate, magnesium hydroxide, metal oxides, or combinations of two or more thereof.

15 [069] Preferably the mineral filler is chosen from calcium carbonate, titanium dioxide or calcinated clay, silica (fumed or precipitated, clay, Montmorillonite (nano-clay), zeolite, perlite or any other type of inorganic material that can be obtained as a slurry.

20 [070] More preferably a part of the filler (F) or the mixture of two fillers (F1) and (F2) is a mineral filler chosen from calcium carbonate, calcinated clay, silica (fumed or precipitated), clay, Montmorillonite (nano-clay), zeolite or perlite.

[071] Still more preferably the mineral filler is chosen from
25 calcium carbonate, calcinated clay, silica (fumed or precipitated, clay, Montmorillonite (nano-clay), zeolite or perlite.

[072] In an even more preferred embodiment the mineral filler is calcium carbonate (CaCO_3).

[073] Advantageously the calcium carbonate is chosen from
30 precipitated calcium carbonate (PCC), grinded natural calcium carbonate (GCC) or nanosized particles of precipitated calcium carbonate (NPCC).

[074] The mineral filler could also be in form of a slurry.

[075] Preferably the filler (F) or (F2) that is mixed with at least one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) is in form of a slurry.

5 [076] **As regards the slurry of the mineral filler**, it is a water dispersion of a mineral filler with solid content preferably between 5wt% and 90wt% and advantageously between 50wt% and 80wt%. This water dispersion can contain any specific surfactant, dispersing agent, additive or filler surface treatment that can
10 advantageously improve the quality of the slurry (stability, viscosity or compatibility with the host polymer matrix).

[077] **With regard to the halogen containing polymer**, mention may be made of:

15 [078] - homopolymers and copolymers of vinyl chloride (PVC) and of vinylidene chloride (PVDC), vinyl resins comprising vinyl chloride units in their structure, such as copolymers of vinyl chloride, and vinyl esters of aliphatic acids, especially vinyl acetate, copolymers of vinyl chloride with
20 esters of acrylic and methacrylic acid and with acrylonitrile, copolymers of vinyl chloride with diene compounds and unsaturated dicarboxylic acids or their anhydrides, such as copolymers of vinyl chloride with diethyl maleate, diethyl fumarate or maleic anhydride,
25 post-chlorinated polymers and copolymers of vinyl chloride, copolymers of vinyl chloride and vinylidene chloride with unsaturated aldehydes, ketones and others, such as acrolein, crotonaldehyde, vinyl methyl ketone, vinyl methyl ether, vinyl isobutyl ether and the like; polymers of
30 vinylidene chloride and its copolymers with vinyl chloride and other polymerizable compounds;

[079] - polymers of vinyl chloroacetate and dichlorodivinyl ether; chlorinated polymers of vinyl carboxylate, such as vinyl acetate, vinyl propionate, vinyl butyrate, chlorinated
35 polymeric esters of acrylic acid and of α -substituted acrylic acid, such as methacrylic acid, of nitriles, amides, alkyl esters such as acrylonitrile,

(meth)acrylamide, methyl (meth)acrylate, butyl acrylate, ethyl acrylate, 2-ethylhexyl acrylate;

[080] - polymers of vinyl aromatic derivatives, such as styrene, dichlorostyrene; chlorinated rubbers;

5 [081] - chlorinated polymers of olefins, such as ethylene, propene, 1-butene, (2.2.1)bicyclo heptene-2, (2.2.1)bicyclo hepta-diene-2,5;

[082] - polymers and post-chlorinated polymers of chlorobutadiene and copolymers thereof with vinyl chloride, chlorinated
10 natural and synthetic rubbers, and also mixtures of these polymers with one another or with other polymerizable compounds.

[083] - grafted halogen containing copolymers, where the halogen containing polymer part is grafted on an (meth)acrylic homo
15 or copolymer, in form of a particles, which could be crosslinked or not.

[084] Preferably the halogen containing polymer is a thermoplastic polymer and not an elastomeric polymer. The glass transition
20 temperature (measured by differential scanning calorimetry) of the thermoplastic polymer is at least 40°C, preferably 50°C.

[085] Preferably the halogen in the halogen containing polymer is chosen from fluorine or chlorine and advantageously the halogen is
25 chlorine.

[086] The chlorine containing polymer is chosen from among polymers or mixtures of polymers chosen from among homopolymer vinyl chlorides such as polyvinyl chloride, polyvinylidene chloride, chlorinated polyvinyl chloride, post-chlorinated polyvinyl
30 chloride and copolymers formed by the polymerisation of a vinyl chloride monomer with up to 40% of a comonomer such as vinyl acetate, vinyl butyrate, vinylidene chloride, propylene, methyl methacrylate and the like, as well as chlorine-containing polymers containing other polymers such as chlorinated polyethylene,
35 terpolymers of acrylonitrile, butadiene, styrene, terpolymers of methyl methacrylate, butadiene, styrene; polyacrylate resins, poly methyl methacrylate resins and terpolymer of alkyl acrylate,

methyl methacrylate, butadiene, preferably the chlorine-containing polymer is polyvinyl chloride or post-chlorinated polyvinyl chloride.

[087] Preferably the chlorine containing polymer is chosen from homo- and copolymers of vinyl chloride (VC); comprising at least 50wt% of VC units, preferably at least 70 wt% of VC units, more preferably at least 80 wt% of VC units, advantageously at least 85 wt% of VC units; or mixtures thereof.

[088] With regard to the manufacturing method for a polymer composition according to the present invention, it comprises the step of

blending a composition P1 with a halogen containing polymer and a filler (F) or (F2)

characterized that the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) and

wherein the glass transition temperature Tg of the (meth)acrylic copolymer is more important than 95°C and that the quantity of the filler (F1) and (F2) together is more than 40phr in view of the halogen containing thermoplastic polymer.

[089] The filler (F1) and (F2) can be the same or different. If the filler (F1) and (F2) are the same they can be seen together simply as filler (F) and their quantity is added. The important point is that the composition P1 to be blended contains already a filler.

[090] Preferably the blending of the compositions P1 with halogen containing polymer and a filler is made by dry blending.

Preferably the dry blend is also heated.

[091] The (meth)acrylic copolymer (A1), the mixture of two (meth)acrylic copolymers (A1a) and (A1b), the halogen containing polymer and the mineral filler are the same as defined before.

[092] With regard to a variation of the manufacturing method for a polymer composition according to the present invention, it comprises the step of

blending two compositions P1 and P2 characterized that
the composition P1 comprises an (meth)acrylic copolymer
(A1) or a mixture of two (meth)acrylic copolymers (A1a)
and (A1b) and a filler (F1) and

5 the composition P2 comprises a halogen containing polymer
and a filler F2

wherein the glass transition temperature Tg of the (meth)acrylic
copolymer (A1) or the mixture of two (meth)acrylic copolymers
(A1a) and (A1b) is more important than 95°C and that the quantity
10 of the filler (F1) and (F2) together is more than 40phr in view of
the halogen containing thermoplastic polymer.

[093] The filler (F1) and (F2) can be the same or different. If the
filler (F1) and (F2) are the same they can be seen together simply
as filler (F) and their quantity is added in order to obtain
15 (calculate) the entire amount in the composition according to the
invention. The important point is that each of the two
compositions P1 and P2 which are to be blended, contain already a
filler.

[094] Preferably the blending of the two compositions P1 and P2 is
20 made by dry blending. Preferably the dry blend is also heated.

[095] The (meth)acrylic copolymer (A1), the mixture of two
(meth)acrylic copolymers (A1a) and (A1b), the halogen containing
polymer and the mineral filler are the same as defined before.

25 **[096] With regard to the manufacturing method for** the composition
P1, it comprises the step of

a) mixing of at least one (meth)acrylic copolymer
(A1) or a mixture of two (meth)acrylic copolymers
(A1a) and (A1b) with at least one filler (F1)

30 wherein the (meth)acrylic copolymer (A1) or the mixture of two
(meth)acrylic copolymers (A1a) and (A1b) and the mineral filler
in step a) are in form of a dispersion in aqueous phase.

[097] Preferably the (meth)acrylic copolymer (A1) or the mixture of
two (meth)acrylic copolymers (A1a) and (A1b) in form of a
35 dispersion in aqueous phase is obtained by emulsion
polymerization.

[098] Preferably the filler in form of a dispersion in aqueous phase is the slurry of the mineral filler as described above.

[099] The (meth)acrylic copolymer (A1) and the mineral filler are the same as defined before.

5

[0100] With regard to a variation of the manufacturing method for a the composition P1, it comprises the steps of

- a) mixing of at least one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) with at least one filler (F) or (F1)
- b) recovering of the mixture obtained in a)
- c) drying the recovered mixture of step b)

10 wherein the (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the mineral filler in step a) are in form of a dispersion in aqueous phase.

15 [0101] By recovering is meant partial or complete separation between the aqueous and solid phase, said solid phase comprises (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the filler. In the case that a complete separation between the aqueous and solid phase of the mixture takes already place during the recovering step, no further drying is necessary. Or in other words the recovering and the drying of the mixture take place at the same time.

20 [0102] Preferably the recovery of the mixture of (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and filler, is made by spray drying, freeze drying or coagulation.

25 [0103] The (meth)acrylic copolymer (A1), the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the filler are the same as defined before.

30 [0104] Advantageously the recovery of the mixture of (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) with the filler, is made by spray drying.

35 [0105] The mixture of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) with the filler after drying comprises less than 3wt% humidity and

preferably less than 1.5wt% humidity and more preferably less than 1.2wt% humidity.

[0106] In the case of spray drying it is possible to mix the dispersion of mixture of (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) with the filler and the slurry or dispersion filler before adding the mixture to the spray drying apparatus. It is also possible to mix the dispersion of the mixture of (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) with the filler and the slurry or dispersion mineral filler inside the spray drying apparatus during the recovering step.

[0107] Spray drying is the preferred method for the recovering and/or drying for the manufacturing method for composition P1.

[0108] The composition P1 comprises between 1wt% and 50wt%, preferably between 2wt% and 50wt% and more preferably between 5wt% and 50wt% of one filler (F) or (F1) relatively to the complete composition made of meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the filler.

[0109] If the composition comprises other additional (meth)acrylic copolymers, they are taken into account for the calculation of the weight ratio of the filler, if they fall under the definition of meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) in the composition according to the invention.

[0110] The composition P2 comprises between 40phr and 350phr, preferably between 40phr and 300phr, and more preferably between 50phr and 300phr of one filler (F) or (F2).

[0111] The present invention relates also to the use of the polymer composition P1 comprising (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler (F) or (F1) to fuse in a reasonable time a composition comprising a halogen containing polymer and a filler (F) or (F2).

[0112] The present invention relates also to the use of the polymer composition P1 comprising (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a

filler F1 to fuse in a reasonable time a composition P2 comprising halogen containing polymer and a filler F2.

[0113] Preferably the polymer composition P1 comprising (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and a filler F1 is in form of the polymer powder.

[0114] The polymer powder of composition P1 comprises the agglomerated spherical particles of (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and particles of the mineral filler.

[0115] The polymer powder has a volume median particle size D50 between 1µm and 500µm. Preferably the volume median particle size of the polymer powder is between 10µm and 450µm, more preferably between 15µm and 400µm and advantageously between 20µm and 300µm.

[0116] The D10 of the particle size distribution in volume is at least 7µm and preferably 10µm.

[0117] The D90 of the particle size distribution in volume is at most 800µm and preferably at most 500µm.

[0118] The powder according to the invention is homogenous in view of the composition concerning its components: the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the mineral filler.

[0119] Homogeneous in the present invention signifies no important variation throughout the composition. If one or several small samples (1g) or less comprising several powder grain particles) is/are taken from a larger quantity (1kg) of the composition there is no important variation of the composition concerning the weight ratio of the respective components in the small sample in comparison to other small samples and the global composition. By no important variation is meant that the variation is less than 30% relative to the global composition, inside a 1wt% sample of P1 taken from whole P1. As an example, if the global composition P1 comprises 40wt% of the inorganic compound (F) and 60wt% of the (meth)acrylic copolymer (A1), a small first sample taken from the global composition that would comprise 35wt of the inorganic compound (F) and 65w% of the (meth)acrylic copolymer (A1) or small

second sample taken from the global composition that would comprise 42wt of the inorganic compound (F) and 58wt% of the (meth)acrylic copolymer (A1), would signify a homogenous composition as the variation of ratio of the respective components throughout the small samples is within the 30% variation in view of the global composition of the sample.

[0120] The composition P1 is a homogenous powder having no important variation throughout the composition P1 comprising one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) with at least one filler (F) or (F1), with a variation of the composition P1 which is less than 30% relative to the global composition P1 of a 1wt% sample of P1 taken from P1.

[0121] Preferably the variation of the components within the composition is less than 25%, more preferably less than 20%.

[0122] In an ideal case each powder particle or grain comprises the two components the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and filler and is composed of aggregated particles of the two components.

[0123] The present invention relates also to an article comprising the polymer composition as described above. This article can be a profile, a pipe, a siding, a flooring film or sheet or a foamed article.

[Methods of evaluation]

[0124] Glass transition Temperature

The glass transitions (T_g) of the polymers are measured with equipment able to realize a thermo mechanical analysis. A RDAII "RHEOMETRICS DYNAMIC ANALYSER" proposed by the Rheometrics Company has been used. The thermo mechanical analysis measures precisely the visco-elastics changes of a sample in function of the temperature, the strain or the deformation applied. The used frequency is 1Hz. The apparatus records continuously, the sample deformation, keeping the strain fixed, during a controlled program of temperature variation.

The results are obtained by drawing, in function of the temperature, the elastic modulus (G'), the loss modulus and the tan delta. The T_g is higher temperature value read in the tan delta curve, when the derived of tan delta is equal to zero.

5

[0125] Molecular Weight

The mass average molecular weight (M_w) of the polymers is measured with by size exclusion chromatography (SEC).

[0126] Fusion efficiency

10 The fusion efficiency of the PVC polymer composition is estimated by measuring the fusion time with a torque rheometer based on ASTM D2538-02 (reapproved 2010). A shorter fusion time signifies a better fusion efficiency.

15 **[Examples]****[0127]** Abbreviations**[0128]** MMA - methyl methacrylate**[0129]** BA - butyl acrylate**[0130]** EA - ethyl acrylate20 **[0131]** PVC - polyvinylchloride

[0132] The filler in examples for the (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) as processing aid (PA) is calcium carbonate (CaCO_3). CaCO_3 slurry or dispersion is prepared according to the technique described in

25 J.P. Pat. No. 59057913. Namely the slurry is obtained by mixing 270 parts of water, 0.72 parts of sodium polyacrylate and 729.3 parts of CaCO_3 of diam. 0.2 - 0.6 μm . and 0.6% moisture and stirring for 20 min at shear rate 5. times. 102/s. The obtained solid content is 73wt%.

30 **[0133]** Comparative example 1: Charged into a reactor, with stirring, were 8600 g of water, 5.23 g of Na_2CO_3 and 38.20 g of sodium lauryl sulfate, and the mixture was stirred until complete dissolution. Three vacuum-nitrogen purges were carried out in succession and the reactor left under a slight vacuum. The reactor

35 was then heated. At the same time, a mixture comprising 4166.4 g of methyl methacrylate and 1041.6 g of n-butyl acrylate was nitrogen-degassed for 30 minutes. Next, the mixture was rapidly

introduced into the reactor using a pump. When the temperature of the reaction mixture reached 55 degrees centigrade, 7.81 g of potassium persulfate dissolved in 98.08 g of water were introduced. The line was rinsed with 50 g of water. The reaction mixture was left to rise in temperature to the exothermal peak. The polymerization was then left to completion for 60 minutes after the exothermal peak. The reactor was cooled down to 30 degrees centigrade and the latex removed. The latex is dried by spray drying.

[0134] Comparative example 2: Charged into a reactor, with stirring, were 8600 g of water, 5.23 g of Na_2CO_3 and 38.20 g of sodium lauryl sulfate, and the mixture was stirred until complete dissolution. Three vacuum-nitrogen purges were carried out in succession and the reactor left under a slight vacuum. The reactor was then heated. At the same time, a mixture comprising 3645.6 g of methyl methacrylate and 1562.4 g of n-butyl acrylate was nitrogen-degassed for 30 minutes. Next, the mixture was rapidly introduced into the reactor using a pump. When the temperature of the reaction mixture reached 55 degrees centigrade, 7.81 g of potassium persulfate dissolved in 98.08 g of water were introduced. The line was rinsed with 50 g of water. The reaction mixture was left to rise in temperature to the exothermal peak. The polymerization was then left to completion for 60 minutes after the exothermal peak. The reactor was cooled down to 30 degrees centigrade and the latex removed. The latex is dried by spray drying.

[0135] Comparative example 3: Charged into a reactor, with stirring, were 8600 g of water, 5.23 g of Na_2CO_3 and 38.20 g of sodium lauryl sulfate, and the mixture was stirred until complete dissolution. Three vacuum-nitrogen purges were carried out in succession and the reactor left under a slight vacuum. The reactor was then heated. At the same time, a mixture comprising 4687.2 g of methyl methacrylate and 520.8 g of n-butyl acrylate was nitrogen-degassed for 30 minutes. Next, the mixture was rapidly introduced into the reactor using a pump. When the temperature of the reaction mixture reached 55 degrees centigrade, 7.81 g of potassium persulfate dissolved in 98.08 g of water were

introduced. The line was rinsed with 50 g of water. The reaction mixture was left to rise in temperature to the exothermal peak. The polymerization was then left to completion for 60 minutes after the exothermal peak. The reactor was cooled down to 30 degrees centigrade and the latex removed. The obtained solid content is 37.55wt%. The latex is dried by spray drying.

[0136] Example 1: In a first time the copolymer latex is made according to the synthesis described in comparative example 3. The final product is obtained by mixing the copolymer latex and the slurry with the following ratio, 14 kg (14000 parts) of latex and 0.379 kg (379 parts) of slurry, and spray dried in the conditions classically used for the latex alone.

[0137] Example 2: The copolymer latex is made according to the synthesis described in comparative example 3. The final product is obtained by mixing the copolymer latex and the slurry with the following ratio, 14 kg (14000 parts) of latex and 1.8 kg (1800 parts) of slurry, and spray dried in the conditions classically used for the latex alone.

[0138] The characteristics of PA samples of comparative examples and examples are summarized in table 2.

[0139] The prepared spray dried samples of comparative examples and examples are formulated at 1.5phr as processing aid (PA) in a PVC composition. The compositions are dry blended in a Papenmeyer equipment while increasing the temperature. PVC compositions are prepared with 60phr CaCO_3 as filler in the PVC respectively.

[0140] Table 1 - PVC compositions with two ratios of filler

components	Composition with quantities in phr
PVC	100
1pack CaZn	4
CaCo3	60
PA from respective comparative examples and examples	1.5

[0141] As polyvinylchloride PVC S110P from Kemone is used. As one pack stabilizer Ca/ZN Naftosafe GWX 380 D-3 from Chemson is used.

[0142] The samples are tested for fusion efficiency with a torque rheometer.

[0143] The fusion efficiency is evaluated relatively to compositions comprising comparative examples 1 and 2. Comparative example 1 and 2 are processing aid compositions without a filler. Its fusion efficiency is judged with ++. All other examples or comparative examples that have fusion time within an interval of +/-10s are also judged ++. If the fusion time is faster in an interval -25s to -10s the example is judged +++. If the fusion time is faster in an interval -50s to -25s the example is judged +++. If the fusion time is 50s faster than comparative example 1 in an interval up to -50s the example is judged +++. If the fusion time is slower than comparative example 1 and 2 with at least +10s it is judged +.

[0144] Results of fusion efficiency are summarized in table 2.

[0145] Table 2 Characteristics of PA made in the respective examples and comparative examples and their evaluation of fusion efficiency in a composition

	PA composition	Filler content in PA / [wt%]	Tg of PA / [°C]	Mw / [$\times 10^6$ g/mol]	Fusion efficiency
Comparative example 1	MMA/BA 80/20	0	96	4.5	++
Comparative example 2	MMA/BA 70/30	0	80	4.5	++
Comparative example 3	MMA/BA 90/10	0	107	4.5	+++++
Example 1	MMA/BA 90/10	5	107	4.5	+++++
Example 2	MMA/BA 90/10	20	107	4.5	++++

[0146] The examples 1 to 2 show that the fusion efficiency of a composition of a (meth)acrylic copolymer (A1) comprising a

filler in a highly filled halogen containing thermoplastic polymer (PVC), does perform equal or still acceptable than the comparative examples with the same composition of a (meth)acrylic copolymer (A1) and better than the comparative examples with the other
5 composition of a (meth)acrylic copolymer (A1) having a low Tg.

Claims

1. A composition comprising:

- a) a (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate
- b) a filler (F) or a mixture of two fillers (F1) and (F2), which is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite,
- c) a halogen containing thermoplastic polymer

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

- 2. Composition according to claim 1, wherein a part of the filler (F) or a part of the mixture of two fillers (F1) and (F2) is added to the composition with the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the other part of the filler (F) or the other part of the mixture of two fillers (F1) and (F2) is added to the composition either apart or already with halogen containing thermoplastic polymer.
- 3. Composition according to claim 1 or 2, wherein the quantity of the filler (F) or mixture of two fillers (F1) and (F2) is between 40phr and 300phr relative to the halogen containing thermoplastic polymer.

4. Composition according to any of claims 1 to 3 comprising between 50phr and 300phr of the filler (F) or mixture of two fillers (F1) and (F2) relative to the halogen containing thermoplastic polymer.
5. Composition according to any of claims 1 to 4 comprising between 0.05phr and 17phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

6. Composition according to any of claims 1 to 4, comprising between 0.15phr and 4phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.
7. Composition according to any of claims 1 to 6 wherein the filler (F) or the mixture of two fillers (F1) and (F2) is chosen from calcium carbonate.
8. The composition according to claim 7, wherein the calcium carbonate is chosen from precipitated calcium carbonate (PCC), grinded natural calcium carbonate (GCC) or nanosized particles of precipitated calcium carbonate (NPCC).
9. Composition according to any of claims 1 to 6 wherein the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is chosen from a copolymer comprising at least 80wt% of methyl methacrylate.
10. Composition according to any one of claims 1 to 9, wherein the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 500 000g/mol.
11. Composition according to claim 10 wherein the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is less than 20 000 000g/mol.

12. Composition according to claim 10 wherein the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is between 1 000 000 g/mol and 12 000 000g/mol.

13. Composition according to any of claims 1 to 12 wherein the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is between 95°C and 130°C and even more preferably between 100°C and 125°C.
14. Composition according to any of claims 1 to 12 wherein the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) between 105°C and 120°C.
15. Composition according to any of claims 1 to 4 wherein the halogen containing thermoplastic polymer is chosen from a homo or copolymer of vinylchloride comprising at least 50wt% of vinylchloride units.
16. A process for preparing a composition according to claims 1 to 15, said process comprises the step of
blending a compositions P1 with a halogen containing polymer and a filler (F) or (F2) characterized that the composition P1 comprises an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1), wherein the filler (F), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite and
wherein the glass transition temperature T_g of the (meth)acrylic copolymer is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1)

or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

17. A process for preparing a composition according to claims 1 to 15, said process comprises the step of

blending two compositions P1 and P2 characterized that

the composition P1 comprises an (meth)acrylic copolymer (A1) or mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1) and

the composition P2 a halogen containing polymer and a filler (F) or (F2), wherein the filler (F), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite,

characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

18. The process according to claim 16 or 17, characterized that the composition P1 is obtained by a manufacturing method comprising the step of

a) mixing of at least one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) with at least one filler (F) or (F1)

wherein the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the filler F) or (F1) in step a) are in form of a dispersion in aqueous phase.

19. The process according to claim 16 or 17, characterized that the composition P1 is obtained by a manufacturing method comprising the step of

a) mixing of at least one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) with at least one filler (F) or (F1)

b) recovering of the mixture obtained in a)

c) drying the recovered mixture of step b)

wherein the (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the mineral filler in step a) are in form of a dispersion in aqueous phase.

20. The process according to any of claims 16 to 19, characterized that the composition P1 comprises between 1wt% and 50wt%, preferably between 2wt% and 50wt% and more preferably between 5wt% and 50wt% of the filler (F) or (F1) relatively to the composition P1 made of meth)acrylic copolymer (A1) or

the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and the filler.

21. The process according to any of claims 16 to 10, characterized that the composition P1 is in form of a powder.
22. The process according to any of claims 16 to 21, characterized that the composition P1 is in form of a powder having volume median particle size D50 between 1 μ m and 500 μ m.
23. The process according to any of claims 16 to 22, characterized that the composition P1 is a homogenous powder comprising one (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) with at least one filler (F) or (F1).
24. The process according to any of claims 21 to 23, characterized that each powder particle or grain of the composition P1 comprises the two components the meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) and filler.
25. The process according to any of claims 16 to 24, characterized that the the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is between 1 000 000 g/mol and 12 000 000g/mol.
26. The process according to any of claims 16 to 24, characterized that thethe glass transition temperature Tg of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is between 95°C and 130°C and even more preferably between 100°C and 125°C.

27. The process according to claim 17, characterized that the composition P2 comprises between 40phr and 350phr of the filler (F2).
28. Use of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F) or (F1) to decrease the fusion time of a composition comprising a halogen containing polymer and a filler (F) or (F2), wherein the filler (F), (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite, characterized that the glass transition temperature T_g of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the filler (F) or the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight M_w of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.
29. Use of a composition P1 comprising an (meth)acrylic copolymer (A1) or a mixture of two (meth)acrylic copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate and a filler (F1) to decrease the fusion time of composition P2 comprising halogen containing polymer and a filler (F2), wherein the filler (F1) and/or (F2) is a mineral filler chosen from calcium carbonate, calcined clay, fumed silica, precipitated silica, clay, nano-clay, Montmorillonite, zeolite or perlite, characterized that the glass transition temperature T_g of the (meth)acrylic copolymer

(A1) or the mixture of two (meth)acrylic copolymers (A1a) and (A1b) is more than 95°C and that the quantity of the mixture of two fillers (F1) and (F2) is more than 40phr and less than 350 phr relative to the halogen containing thermoplastic polymer and that the molecular weight Mw of the (meth)acrylic copolymer (A1) or the two (meth)acrylic acid copolymers (A1a) and (A1b) comprising at least 50wt% of polymeric units coming from methyl methacrylate is at least 300 000g/mol and comprising between 0.01phr and 20phr of the (meth)acrylic copolymer (A1) or the mixture of two (meth)acrylic copolymer (A1a) and (A1b) relative to the halogen containing thermoplastic polymer.

30. Article comprising a composition according to any of claims 1 to 15 or a composition prepared by a process according to any of claims 16 to 27.
31. Article according to claim 30, characterized that the article is a profile, a pipe, a siding, a flooring film or sheet.