

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
2 July 2009 (02.07.2009)

PCT

(10) International Publication Number
WO 2009/080714 A1

(51) International Patent Classification:

C22C 38/02 (2006.01) C22C 38/24 (2006.01)
C22C 38/04 (2006.01) C22C 38/26 (2006.01)
C22C 38/06 (2006.01) C21D 8/02 (2006.01)
C22C 38/22 (2006.01)

(74) Agents: OCVIRK, Philippe et al.; B.P. 48, 234, Route d'Arlon, L-8001 Strassen (LU).

(21) International Application Number:

PCT/EP2008/067922

(22) International Filing Date:

18 December 2008 (18.12.2008)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

07150370.0 21 December 2007 (21.12.2007) EP

(71) Applicant (for all designated States except US): Arcelor-Mittal Commercial RPS S.à r.l. [LU/LU]; 66, rue de Luxembourg, L-4221 Esch sur Alzette (LU).

(72) Inventor; and

(75) Inventor/Applicant (for US only): FAGOT, Anne [FR/LU]; 9, rue de Nothomb, L-4264 Esch sur Alzette (LU).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IS, JP, KE, KG, KM, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RS, RU, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MT, NL, NO, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

(54) Title: CORROSION RESISTANT STEEL FOR MARINE APPLICATIONS

(57) Abstract: A steel, namely for marine applications, comprises by weight percent: carbon: 0.05 to 0.20; silicon: 0.15 to 0.55; manganese: 0.60 to 1.60; chromium: 0.75 to 1.50; aluminum: 0.40 to 0.80; niobium and/or vanadium: $0.01 < [\text{Nb}] + [\text{V}] < 0.60$; sulphur: up to 0.045; and phosphorous: up to 0.045.

WO 2009/080714 A1