

COMPOSITION AND METHOD FOR FORMATION OF SILICA THIN FILMS

This invention relates to compositions that form silica thin films and to methods for their formation. The resulting product has an excellent performance as a planarizing
5 coating for substrates and that are converted by exposure to high-energy radiation into a ceramic-like silica thin film. This invention also relates to semiconductor devices that contain an electrically insulating layer and to a method for fabrication of such devices.

Semiconductor devices, such as DRAMs and logic integrated circuits (an interconnect structure comprising such elements as an electrically conductive layer and
10 conductors) formed on a wafer (substrate), are protected by providing an electrically insulating layer on the circuit surface. In a multilevel interconnect structure, formed by stacking a plural number of electrical circuits in such a device, an interlayer dielectric layer is provided, for example, between the interconnections in an upper level and in an underlying level.

15 The use of ceramic-like silica thin films as a protective or insulating layers for electronic devices is known. For example, U.S. Patent 4,756,977 teaches a method for coating electronic devices with a silica thin film in which a solvent solution of hydrogen silsesquioxane resin is coated on a substrate, the solvent is then evaporated, and heating to 150°C to 1,000°C is performed to effect conversion into ceramic-like silica.

20 However, hydrogen silsesquioxane resins typically contain a considerable amount of volatile components. As a consequence, exposure to high temperatures cause such problems as a diminution in film thickness and the generation of internal stresses in the film. Moreover, vaporization and expulsion of the volatile component can cause contamination of surrounding equipment.

25 Methods for removing low molecular-weight components of hydrogen silsesquioxane resin have been proposed. For example, U.S. Patent No. 5,416,190 claims the removal of such components by addition of solvent to said resin. Unfortunately, this method yields hydrogen silsesquioxane resin that has a poor performance as a planarizing coating when applied on substrates. In addition, high molecular-weight hydrogen

silsesquioxane resin performs poorly as a planarizing coating for substrates, because it has a high softening point (at least 180°C). Thus, its use for substrate planarization requires heating and melting at high temperatures (at least 200°C). High molecular-weight hydrogen silsesquioxane resin also has a poor capacity to fill the topographical irregularities on substrates for electronic devices having a multilayered structure; and as a consequence, thus may not be fully satisfactory in some applications.

It is therefore an object of this invention is to provide a silica thin film forming composition that, upon application to a substrate, performs well as a planarizing coating, and is easily converted by exposure to high-energy radiation into a silica thin film with an excellent electrical insulating performance.

It is also an object of this invention to provide a method for the formation of such silica thin films.

It is also an object of this invention to provide semiconductor devices that contain an electrically insulating layer that exhibits an excellent capacity to both coat and planarize the interconnect structures on the substrate.

The present invention provides a composition for the formation of silica thin films, said composition comprising (A) hydrogen silsesquioxane resin that contains at least 45 weight % hydrogen silsesquioxane resin with a molecular weight no greater than 1,500 and (B) solvent. The present invention also relates to a method for the formation of silica thin films, wherein said method comprises coating the surface of a substrate with the above silica thin film forming composition; evaporating the solvent (B); and then (C) converting at least a portion of the hydrogen silsesquioxane resin (A) to silica by exposing said coated substrate to high-energy radiation. The preferred substrate is a semiconductor device in which the surface of the device has an interconnect structure comprising at least one electrically conductive layer.

The hydrogen silsesquioxane resin of the present invention is polysiloxane whose main skeleton is comprised of the trifunctional siloxane unit $\text{HSiO}_{3/2}$, (i.e., a polymer with the general formula $(\text{HSiO}_{3/2})_n$ where n is an integer). Based on differentiation by

molecular structure, the hydrogen silsesquioxane resin includes ladder polysiloxanes and cage polysiloxanes. The terminals of the ladder polysiloxanes are endblocked by, for example, the hydroxyl group, a triorganosiloxy group such as trimethylsiloxy, or a diorganohydrogensiloxy group such as dimethylhydrogensiloxy.

- 5 The hydrogen silsesquioxane resin (A) must contain at least 45 weight %, and preferably contains at least 50 weight %, respectively of hydrogen silsesquioxane resin with a molecular weight no greater than 1,500. When this content is below 45 weight %, the resultant coating performs poorly as a substrate planarizing coating. In particular, the resin ($< 45 \text{ wt\% Mw} \leq 1,500$) evidences a poor capacity to fill the topographical
- 10 irregularities on substrates for electronic devices having a multilayered structure, i.e., a lower level interconnect on an upper level interconnect, and cannot form a uniform silica thin film having excellent electrical insulating properties.

 Hydrogen silsesquioxane resin is generally known in the art and is synthesized by the hydrolysis of trichlorosilane and ensuing polycondensation (U.S. Patent 3,615,272,

15 and JP-As 59-189126 (1984) or 60-42426 (1985).

- Component (A) can also be prepared by providing a known method for synthesizing hydrogen silsesquioxane resin with a means for increasing the production of low molecular-weight components (molecular weight no greater than 1,500). This resin (A) can further be prepared by separating the low molecular-weight component by
- 20 molecular fractionation on a hydrogen silsesquioxane resin already synthesized by a known method. This molecular weight fractionation is easily performed by dissolving the already synthesized resin in a nonpolar solvent, and by then adding a polar solvent to the resulting solution.

- No particular restrictions apply to the solvent (B) other than that it should be
- 25 capable of dissolving component (A) without inducing chemical changes in component (A). Applicable solvents are exemplified by aromatic solvents such as toluene or xylene; aliphatic solvents such as hexane, octane, and heptane; ketone solvents such as methyl ethyl ketone or methyl isobutyl ketone; aliphatic ester solvents such as butyl acetate or isoamyl acetate; and silicone solvents such as chain methylsiloxanes (e.g., 1,1,1,3,3,3-

hexamethyldisiloxane or 1,1,3,3-tetramethyldisiloxane), cyclic siloxanes (e.g., 1,1,3,3,5,5,7,7-octamethyltetracyclosiloxane or 1,3,5,7-tetramethyltetracyclosiloxane), and silane compounds (e.g., tetramethylsilane and dimethyldiethylsilane). The silicone solvents are preferred.

5 Our silica thin film forming composition typically contains 5 to 50 weight percent of hydrogen silsesquioxane resin (A), preferably 10 to 40 weight percent, based on the combined weights of (A) and (B).

 This composition is simply prepared by mixing components (A) and (B) to homogeneity. Other components such as ceramic oxide precursors may also be admixed
10 insofar as the objects of the present invention are not impaired. These precursors are exemplified by tetra-n-propoxyzirconium, tetraisobutoxytitanium, trispentanedioxoaluminum, pentaethoxytantalum, tripropoxyvanadium, pentaethoxyniobium, pentanedioxozirconium, and dibutoxybis-pentanedioxotitanium.

 A platinum catalyst or rhodium catalyst can be added to our silica thin film
15 forming composition to increase the rate and extent of formation of the film. These catalysts are exemplified by chloroplatinic acid or the complexes of chloroplatinic acid and tetramethyldivinylsiloxane. These catalysts will generally be used in the range from 1 to 500 weight parts for each one million weight parts of component (A).

 The composition of this invention forms a silica thin film when exposed to high-
20 energy radiation. As used here, the expression "silica" refers to silicon dioxide (SiO_2) and encompasses both amorphous silica and amorphous silica that is not completely free of silanol groups and/or hydrogen atoms. When a ceramic precursor is added, this additive may also be present.

 Substrates usable in our method are exemplified by ceramic substrates, various
25 metal substrates, and electronic devices. Electronic devices are preferred.

 Our method for formation of silica thin films comprises: 1) coating the surface of a substrate with the silica thin film forming composition; 2) evaporating the solvent (B); and thereafter 3) converting at least a portion of said hydrogen silsesquioxane resin (A) to silica by exposing the coated substrate to high-energy radiation.

The coating technique for applying the silica thin film forming composition onto the substrate is not critical as long as it can generate a uniform application of the silica-forming composition. Suitable coating techniques are spin coating, dip coating, spray coating, and flow coating.

5 The technique for evaporating component (B) is also not critical and is exemplified by standing at ambient or elevated temperature, on by drying in air, under reduced pressure, or under a gas current. When spin coating is used as the coating technique, the solvent is expelled during the rotation and drying time is minimized.

After coating the substrate surface, at least a portion of the hydrogen
10 silsesquioxane resin (A) thereon is converted to silica by exposing the coated substrate to high-energy radiation. The high-energy radiation is selected from electron beam, ultraviolet radiation, x-ray, infrared radiation, and microwave radiation; preferably electron beam. Exposure to high-energy radiation is preferably effected in air or an oxygen-containing gas. Gases other than oxygen-containing gases may also be used. The
15 non-oxygen gases are exemplified by nitrogen or argon.

High-energy radiation accomplishes conversion into silica by activating the silicon-bonded hydrogen atoms in the hydrogen silsesquioxane resin, resulting in oxidation by the gaseous oxygen in the ambient atmosphere. The temperature during exposure to the high-energy radiation and the conversion into silica is preferably at a
20 temperature that provides the maximum inhibition of expulsion and outmigration of low molecular-weight hydrogen silsesquioxane resin, and is preferably in the range from 10°C to 50°C.

FIGURE 1 contains a schematic diagram that shows the various processes in the fabrication of a semiconductor device of this invention.

25 FIGURE 2 contains a cross section showing the hydrogen silsesquioxane resin thin film produced in Example 7 by spin coating.

FIGURE 3 contains a cross section showing the silica thin film produced in Example 7.

FIGURE 4 contains a cross section showing the hydrogen silsesquioxane resin thin film produced in Comparative Example 2 by spin coating.

FIGURE 5 contains a cross section showing the silica thin film produced Comparative Example 2.

5 As shown in Figure 1(a), the fabrication of semiconductor devices commences with the formation of a base insulating layer 2 on the surface of a semiconductor substrate 1. An electrically conductive layer is then formed by sputtering a metal, for example aluminum, on the base insulating layer 2. Lower level interconnects 3a, 3b and 3c are thereafter formed by patterning the conductive layer by known methods.

10 As shown in Figure 1(b), an insulating layer 4 is subsequently formed over these lower level interconnects 3a, 3b and 3c. The surface of this insulating layer is then masked with a photoresist, and holes that reach, respectively, to the lower level interconnects 3a and 3c are subsequently provided by selectively etching the insulating layer 4 that overlies said lower level interconnects 3a and 3c. A conductive layer is
15 formed by sputtering a metal, for example aluminum, within these holes. This is followed by plasma etching to effect etchback until exposure of the insulating layer 4, which leaves interlevel connects 5 within said holes (see Figure 1(c)).

 Upper level interconnects 6a and 6b and insulating layer 7 are then formed on the etched-back surface by the same methods as used to provide the lower level interconnects
20 3a and 3c and the insulating layer 4 (see Figure 1(d)). The preceding steps result in the formation on the semiconductor substrate 1 of a multilevel interconnect structure of lower level interconnects 3a and 3c and upper level interconnects 6a and 6b in which the interconnects are electrically insulated by the base insulating layer 2 and the interlayer dielectric layers 4 and 7.

25 The base insulating layer 2 and the interlayer dielectric layers 4 and 7 is a thin film that is mainly silica and which is produced from the silica thin film forming composition. To form the base insulating layer 2 and interlayer dielectric layers 4 and 7, a coating is first formed by application of our silica thin film forming composition on the

surface of the semiconductor substrate 1 (Figure 1(a)), or over the lower level interconnects 3a, 3b and 3c (Figure 1(b)), or over the upper level interconnects 6a and 6b (Figure 1(d)). The solvent is then removed from the applied coating by evaporation.

During coating formation, gaps may be produced at the bottoms due to the topographical variations in the semiconductor substrate, i.e., the depressions formed among the lower level interconnects 3a, 3b and 3c and between upper level interconnects 6a and 6b. The surface of the coating itself also frequently assumes a wave-like or undulating condition. To eliminate these gaps and the undulating surface condition, the applied coating is preferably heated and melted at a temperature that avoids volatilization of the coating (at no greater than 60°C), to thus fill and embed the topographical variations and planarize the applied coating.

Curing of our hydrogen silsesquioxane resin coating is conducted by exposing the applied coating to high-energy radiation. This results in the conversion of at least a portion of said resin making up the coating into silica, thereby forming a silica base insulating layer 2, or a silica interlayer dielectric layer 4 or 7.

The claimed silica thin film forming composition provides an excellent performance as a planarizing coating for substrates, has an excellent capacity to fill the uneven topographical features on substrates for electronic devices with multilayered structures, and is converted by exposure to high-energy radiation to a silica thin film with excellent electrical insulating properties. This composition is useful in applications such as an interlayer dielectric film in multilayered semiconductor devices.

So that those skilled in the art can better understand and appreciate our invention, the following examples are presented; it being understood that this invention is fully defined in the claims.

EXAMPLES

"Parts" in the examples refers to weight parts. The conversion to silica in the examples was evaluated by measurement of the % residual SiH in the film by Fourier transform infrared absorption spectroscopic analysis. The measurements in Examples 2

to 6, and Comparative Example 1, were performed in transmission mode, while the measurements in Example 7 and Comparative Example 2 were done in reflection mode. For reference, the refractive index was measured in each example on the hydrogen silsesquioxane resin thin film applied by spin coating both before and after electron beam exposure.

The molecular weight was measured by gel permeation chromatography (GPC) using the following measurement conditions.

instrument: 802A from Tosoh Corporation

column: G3000/G4000/G5000/G6000

10 carrier solvent: toluene

column temperature: 30°C

molecular weight standard: polystyrene

detection: differential refractometer

sample: 2 wt% solids (toluene solution)

15

EXAMPLE 1: Resin Preparation

Hydrogen silsesquioxane resin was synthesized by the method of Example 1 of U.S. Patent 3,615,272. GPC analysis of the hydrogen silsesquioxane resin product gave the following results: member average molecular weight of 1,540, weight average
20 molecular weight of 7,705, 41 wt% of this component with a molecular weight up to 1,500. The softening point was 90°C.

This resin was then subjected to molecular weight fractionation by the method of Example 1 of U.S. Patent 5,416,190. GPC analysis of the resulting hydrogen silsesquioxane resin fraction gave the following results: member average molecular
25 weight of 743, weight average molecular weight of 1,613, and 72 wt% of this component with a molecular weight up to 1,500. Its softening point was 25°C.

EXAMPLE 2

The hydrogen silsesquioxane resin fraction prepared in Example 1 was dissolved in a mixed solvent comprising 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane to give a resin solution containing 30 wt% solids.

5 A hydrogen silsesquioxane resin film with a thickness of 652 nm (6,520 angstroms) was formed on a silicon wafer by spin coating the solution onto the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out.

10 The resulting silicon wafer was exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. The hydrogen silsesquioxane resin was converted to silica without a significant decline in film thickness. The post-conversion film was free of cracking and other abnormalities. Results are reported in Table 1.

15 EXAMPLE 3

20 A hydrogen silsesquioxane resin film with a thickness of 650 nm (6,504 angstroms) was formed on a silicon wafer by spin coating hydrogen silsesquioxane resin solution prepared as described in Example 2 onto the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out.

25 The resulting silicon wafer was exposed to an electron beam (dose of 240 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. The hydrogen silsesquioxane resin was converted to silica without a significant decline in film thickness. The post-conversion film was free of cracking and other abnormalities. The results are reported in Table 1.

EXAMPLE 4

A hydrogen silsesquioxane resin solution containing 40 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a

mixed solvent comprised of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

A hydrogen silsesquioxane resin film with a thickness of 1,322 nm (13,215 angstroms) was formed on a silicon wafer by spin coating the solution onto the wafer
5 using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out.

The resulting silicon wafer was exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. No significant decline in film thickness occurred and the
10 hydrogen silsesquioxane resin was converted to silica. The post-conversion film was free of cracking and other abnormalities.

The silicon wafer was submitted to Fourier-transform infrared absorption spectroscopic analysis (transmission mode) both after spin coating and after exposure to the electron beam. The relative SiH mole % per unit film thickness was calculated by
15 dividing the film thickness into the absorbance of the absorption peak at $2,260\text{ cm}^{-1}$ assigned to the SiH stretching vibration. Assuming 100% for the value after spin coating, the results showed a drop to 80% after electron beam exposure, which confirmed the loss of SiH groups and thus the occurrence of curing. In addition, the absorption peak assigned to the SiO stretching vibration appeared after spin coating as a single peak at
20 $1,125\text{ cm}^{-1}$ originating with the cage T^{H} structure, but after electron beam exposure the peak at $1,125\text{ cm}^{-1}$ was reduced in strength while a peak at $1,070\text{ cm}^{-1}$ also appeared. This latter peak originated with the random network T^{H} structure or SiO_2 structure. These observations confirmed that a portion of the film had been converted to silica by exposure to the electron beam. The results are reported in Table 1.

25

EXAMPLE 5

A hydrogen silsesquioxane resin film with a thickness of 652 nm (6,520 angstroms) was formed on a silicon wafer by spin coating hydrogen silsesquioxane resin

solution prepared as described in Example 2 onto the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out.

5 The resulting silicon wafer was exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen and was then annealed in a quartz oven at 400°C for 1 hour under a nitrogen current containing 100 ppm of oxygen.

The extent of conversion into silica was somewhat greater than in Example 1, but there was still no significant decline in film thickness. The final silica thin film was also
10 free of cracking and other abnormalities. The results are reported in Table 1.

EXAMPLE 6

A hydrogen silsesquioxane resin solution containing 30 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in methyl
15 isobutyl ketone.

A hydrogen silsesquioxane resin film with a thickness of 663 nm (6,631 angstroms) was formed on a silicon wafer by spin coating this solution onto the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out.

20 The resulting silicon wafer was exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. Conversion into silica occurred without a significant decline in film thickness. The post-conversion silica thin film was free of cracking and other abnormalities.

25

EXAMPLE 7

A hydrogen silsesquioxane resin solution containing 25 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a mixed solvent of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

As seen in FIG. 2 a film 1 with a maximum thickness of 812 nm (8,120 angstroms) was formed on a patterned polysilicon wafer 3 (feature height of 0.5 μm , feature width of 0.18 μm , and feature spacing of 0.18 μm) by spin coating this solution on the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out. Void regions 2 were present. Fluidization occurred when this silicon wafer was heated on a hot plate for 3 minutes at 60°C under a nitrogen current. This fluidization resulted in a thorough filling of the interfeature gaps and planarization of the resin surface.

The silicon wafer 3 was exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. No cracking or other abnormalities were observed in the resulting silica thin film 4 as seen in FIG. 3.

COMPARATIVE EXAMPLE 1

A solution with a solids content of 35 wt % was prepared by dissolving the unfractionated hydrogen silsesquioxane resin whose synthesis was described in Example 1 (41 wt % content of component with molecular weight up to 1,500) in methyl isobutyl ketone.

A hydrogen silsesquioxane resin film with a thickness of 1,278 nm (12,780 angstroms) was formed on a silicon wafer by spin coating the above-described solution onto the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out. The silicon wafer was then annealed in a quartz oven at 400°C for 1 hour under a nitrogen current containing 100 ppm oxygen.

The hydrogen silsesquioxane resin was converted into silica although a substantial decline in film thickness was observed in this case. Cracking was also observed in the post-conversion silica thin film. The results are reported in Table 1.

COMPARATIVE EXAMPLE 2

A solution with a solids content of 20 wt% was prepared by dissolving the unfractionated hydrogen silsesquioxane resin whose synthesis was described in Example 1 (41 wt% content of component with molecular weight up to 1,500) in methyl isobutyl ketone.

As seen in FIG. 4 a hydrogen silsesquioxane film 1 with a maximum thickness of 804 nm (8,036 angstroms) was formed on a patterned polysilicon wafer 3 (feature height of 0.5 μm , feature width of 0.18 μm , and feature spacing of 0.18 μm) by spin coating the solution on the wafer using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out. Void regions 2 were present. Fluidization occurred when this silicon wafer was heated on a hot plate for 3 minutes at 60°C under a nitrogen current. In this case, however, the fluidization did not achieve a thorough filling of the interfeature gaps or planarization of the resin surface.

The silicon wafer 3 was then exposed to an electron beam (dose of 160 Mrad) from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen gas that contained 70 ppm oxygen. The hydrogen silsesquioxane resin was converted into silica. As seen in FIG. 5, the post-conversion silica thin film 4 was free of cracks, however the undulations in the resin surface were not eliminated and void regions 2 remained. The results are reported in Table 1.

EXAMPLE 8

A hydrogen silsesquioxane resin solution containing 15 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a mixed solvent of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

This solution was used to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a

CVD (chemical vapor deposition) film and the solution was then spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 654 nm (6,540 Å).

5 The substrate was subsequently exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen. Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. No cracking or other abnormalities were observed in the post-conversion film (electrically insulating layer).

10 A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

EXAMPLE 9

15 The solution described in Example 8 was used in this example to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 µm and a feature width and feature spacing of 0.18 µm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on
20 the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 653 nm (6,530 Å).

 The substrate was subsequently exposed to a dose of 240 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm
25 oxygen. Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. No cracking or other abnormalities were observed in the post-conversion film (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

5 EXAMPLE 10

A hydrogen silsesquioxane resin solution containing 25 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a mixed solvent of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

10 This solution was used to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 1.0 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary
15 rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 1,324 nm (13,240 Å).

The substrate was subsequently exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm
20 oxygen. Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. No cracking or other abnormalities were observed in the post-conversion film (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. No
25 abnormalities were observed in the electrical properties of the resulting device.

EXAMPLE 11

The solution described in Example 8 was used in this example to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. The solvent was thoroughly evaporated off to form a coating with a thickness of 654 nm (6,540 $\text{\AA}$).

When the substrate was subsequently exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen. Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. No cracking or other abnormalities were observed in the post-conversion film (electrically insulating layer).

The substrate was subsequently baked for 1 hour in a quartz furnace at 400°C under a current of nitrogen with an oxygen concentration of 100 ppm.

The extent of conversion to silica was slightly advanced over that in Example 8, but again no cracking or other abnormalities were observed in the film (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

EXAMPLE 12

The fraction described in Example 1 was dissolved in methyl isobutyl ketone to give a solution that contained 15 wt% solids.

This solution was used to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 μm and a feature width and feature spacing

of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of
5 648 nm (6,485 $\text{\AA}$).

The substrate was subsequently exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen. Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. No cracking or other abnormalities were observed in the post-conversion
10 film (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

15 EXAMPLE 13

A hydrogen silsesquioxane resin solution containing 25 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a mixed solvent of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

This solution was used to produce the electrically insulating layer between
20 interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A
25 thorough solvent evaporation was then carried out to form a uniform coating with a thickness of 823 nm (8,230 $\text{\AA}$).

Fluidization occurred when this substrate was heated on a hot plate for 3 minutes at 60°C under a nitrogen current. This fluidization resulted in a thorough infilling between the features and planarization of the coating surface.

The substrate was exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen.

Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed.

No cracking or other abnormalities were observed in the post-conversion film

5 (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

10 EXAMPLE 14

A hydrogen silsesquioxane resin solution containing 18 wt% solids was prepared by dissolving the hydrogen silsesquioxane resin fraction prepared in Example 1 in a mixed solvent of 30 parts of hexamethyldisiloxane and 70 parts of octamethyltrisiloxane.

This solution was used to produce the pre-metal layer in a semiconductor device
15 having a multilevel aluminum interconnect structure (pattern with a feature height of 0.5 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The solution was spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 700 nm
20 (7,005 Å).

This substrate was exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen.

Conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed.

No cracking or other abnormalities were observed in the post-conversion film

25 (electrically insulating layer). The substrate was then additionally baked for 1 hour at 700°C in a quartz furnace. Although the extent of conversion to silica at this point had reached 100%, no cracking or other abnormalities were observed.

A multilevel interconnect structure was subsequently fabricated on this electrically insulating layer using the contact/via hole contact technique. No abnormalities were observed in the electrical properties of the resulting device.

5 COMPARATIVE EXAMPLE 3

A hydrogen silsesquioxane resin with a number average molecular weight of 1,540 and a weight-average molecular weight of 7,705 (component with a molecular weight no greater than 1,500 = 41%, softening point = 90°C) was dissolved in methyl isobutyl ketone to prepare a solution containing 18 wt% solids.

10 This solution was used to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of 1.0 μm and a feature width and feature spacing of 0.18 μm each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary
15 rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 1,278 nm (12,780 Å).

The wafer was then baked for 1 hour at 400°C in a quartz furnace under a current of nitrogen with an oxygen concentration of 100 ppm.

20 A substantial reduction in coating thickness occurred and conversion of the hydrogen silsesquioxane resin into silica was confirmed. Cracking was observed in the post-conversion film (electrically insulating layer).

A CVD film was formed on this electrically insulating layer and a multilevel interconnect structure was subsequently fabricated by the via hole contact technique. In
25 this case defective electrical contact was observed in portions of the device.

COMPARATIVE EXAMPLE 4

The resin described in Comparative Example 3 was dissolved in methyl isobutyl ketone to give a solution containing 22 wt% solids.

This solution was used to produce the electrically insulating layer between interconnect levels in a semiconductor device having a multilevel aluminum interconnect structure (pattern with a feature height of $0.5\text{ }\mu\text{m}$ and a feature width and feature spacing of $0.18\text{ }\mu\text{m}$ each) fabricated on a silicon substrate. The base features were coated with a CVD film and the solution was then spin coated on the substrate using a preliminary rotation of 500 rpm for 3 seconds and a main rotation of 3,000 rpm for 10 seconds. A thorough solvent evaporation was then carried out to form a coating with a thickness of 848 nm ($8,480\text{ }\text{\AA}$).

Heating the resulting substrate on a hot plate for 3 minutes at 60°C under a nitrogen current did result in fluidization, but in this case a thorough infilling between the features and planarization of the coating surface were not obtained.

The substrate was then exposed to a dose of 160 Mrad from an electron beam irradiator (acceleration voltage of 165 kV) under nitrogen that contained 70 ppm oxygen, conversion of the hydrogen silsesquioxane resin in the coating to silica was confirmed. While no cracking or other abnormalities were observed in the post-conversion film (electrically insulating layer), the undulations (waves) in the surface were not eliminated.

A CVD film was formed on this electrically insulating layer and the fabrication of a multilevel interconnect structure was subsequently attempted by the via hole contact technique. However, in this case, microfabrication proved to be impossible due to the frequent elevations and depressions in the surface.

Table 1

	film thickness in angstroms			refractive index (RI)			extent of film curing (*1)	cracking
	after spin coating	after electron beam exposure	after annealing	after spin coating	after electron beam exposure	after annealing		
2	6520	6413	-	1.401	1.363	-	70	no
3	6504	6412	-	1.402	1.369	-	57	no
4	13215	12951	-	1.403	1.37	-	80	no
5	6520	6413	6355	1.401	1.371	1.372	60	no
6	6631	6532	-	1.401	1.369	-	71	no
7	-	-	-	-	-	-	-	no
Comp. Ex. 1	12780	-	8798	1.409	-	1.373	68	yes
Comp. Ex. 2	-	-	-	1.408	1.378	-	-	no

*1 ; %SiH by transmission IR after the final treatment

5

1 Å = 0.1 nm

1. A composition for the formation of silica thin films, said composition comprising
 - (A) hydrogen silsesquioxane resin that contains at least 45 weight % hydrogen silsesquioxane resin with a molecular weight no greater than 1,500
 - and
 - (B) solvent.
2. The composition of claim 1 wherein there is 5 to 50 weight percent (A) based on (A) and (B).
3. The composition of claim 1 wherein the hydrogen silsesquioxane resin comprises ladder polysiloxanes and cage polysiloxanes.
4. The composition of claim 1 wherein the hydrogen silsesquioxane resin comprises ladder polysiloxanes endblocked with a group selected from the groups consisting of hydroxyl, triorganosiloxy, and diorganohydrogensiloxy.
5. The composition of claim 1 wherein the solvent is selected from the group consisting of aromatic solvents, aliphatic solvents, ketone solvents, aliphatic ester solvents, and silicone solvents.
6. A method for the formation of silica thin films, comprising
 - i) coating the surface of a substrate with the silica thin film forming composition of any of claims 1 -5;
 - ii) evaporating the solvent (B), and
 - iii) converting at least a portion of the hydrogen silsesquioxane resin (A) to silica by exposing said coated substrate to high-energy radiation.
7. The method of claim 6 wherein the substrate is an electronic device.



8. The method of claim 6 wherein the hydrogen silsesquioxane resin is converted in an oxygen-containing gas environment.

9. The method as claimed in claim 6 wherein at least a portion of the hydrogen silsesquioxane resin (A) is converted to silica by exposing the surface of said coated substrate to high-energy radiation at a temperature of from 10°C to 50°C.

