

【DESCRIPTION】

【Invention Title】

METHOD FOR MANUFACTURING POLISHING PAD WINDOW, AND
POLISHING PAD WINDOW MANUFACTURED THEREBY

【Technical Field】

This application claims the benefit of priority based on Korean Patent Application No. 10-2022-0008594 filed on January 20, 2022, the entire contents of which are incorporated as part of the present specification.

The present invention relates to a method for manufacturing a window for a polishing pad and a window for a polishing pad manufactured by the method.

【Background Art】

A chemical mechanical planarization/polishing (hereinafter referred to as CMP) process is a process introduced for global planarization of semiconductor devices, and is emerging as a more important process in accordance with the trend of a larger diameter of a wafer, higher integration, miniaturization of a line width, and multi-layering of a wiring structure.

In the CMP process, polishing speed and planarization are important and are determined by process conditions of polishing equipment and polishing slurry and a polishing pad that are consumable members. In particular, the polishing pad uniformly disperses the supplied polishing slurry on the wafer while contacting a surface of the wafer, and performs a function of causing a physical removal action by polishing particles inside the polishing slurry and surface protrusions of the polishing pad.

Generally, as illustrated in FIG. 1, the polishing pad includes a polishing layer 10, a window 20 formed on the polishing layer, and a lower support layer 30, and the lower support layer 30 has an opening 22 formed under the window. The

polishing layer and the lower support layer are bonded by an adhesive layer 40.

The window is formed to detect a polishing end point of the wafer in the CMP process, and the detection is performed by transmitting an optical beam such as a laser beam through the window. Therefore, the window should have a transmittance in a specific area through which the optical beam may pass.

However, the conventional window does not have sufficient transmittance for the passage of the optical beam, and therefore, have the disadvantage of making it difficult to accurately and reliably detect the polishing end point of the wafer in the CMP process.

Therefore, there is a need for the development of a window with improved transmittance.

[Prior Art Document]

[Patent Document]

Korean Patent Laid-open Publication No. 10-2001-2696

【Disclosure】

【Technical Problem】

The present invention provides a method for manufacturing a window for a polishing pad capable of efficiently manufacturing a window with excellent transmittance.

In addition, the present invention provides a window for a polishing pad capable of accurately and reliably detecting a polishing end point of a wafer through excellent transmittance, and a polishing pad including the same.

【Technical Solution】

To achieve the object, the present invention provides a method for manufacturing a window for a polishing pad, includes:

a) mixing a curing agent with a polyurethane prepolymer having a temperature of 50°C or higher to less than 100°C to prepare a mixture;

b) injecting the mixture into a mold heated to a temperature of 30°C or higher to less than 100°C to a thickness of 5 mm or less;

c) demolding a polyurethane cured product from the mold; and

d) processing the polyurethane cured product to a thickness of the window of the polishing pad.

In addition, the present invention provides a window for a polishing pad manufactured by the method and having a transmittance of 5% or more based on a thickness of 1.9 mm.

In addition, the present invention provides a polishing pad including the window.

【Advantageous Effects】

A method for manufacturing a window for a polishing pad of the present invention provides a method capable of efficiently manufacturing a window with excellent transmittance.

In addition, the window for a polishing pad and the polishing pad including the same of the present invention make it possible to accurately and reliably detect a polishing end point of a wafer through improved transmittance.

【Description of Drawings】

FIG. 1 is a cross-sectional view schematically illustrating the form of a general polishing pad including a window, and

FIG. 2 is a graph showing transmittance measurement results of a window for a polishing pad of the present invention.

【Best Mode】

Hereinafter, embodiments of the present invention will be described in detail with reference to the accompanying drawings so that those skilled in the art may easily practice the present invention. However, the present invention may be implemented in various different forms, and is not limited to embodiments described herein. Throughout the present disclosure, similar components will be denoted by like reference numerals.

In the present invention, the meaning of “~including” means that other components may further be included in addition to any included components, but it also refers to a case where it is composed of only one of the above components without any other components.

A method for manufacturing a window for a polishing pad according to the present invention includes:

a) mixing a curing agent with a polyurethane prepolymer having a temperature of 50°C or higher to less than 100°C to prepare a mixture;

b) injecting the mixture into a mold heated to a temperature of 30°C or higher to less than 100°C to a thickness of 5 mm or less;

c) demolding a polyurethane cured product from the mold; and

d) processing the polyurethane cured product to a thickness of the window of the polishing pad.

The present inventors completed the present invention by discovering that in the case of windows made of a polyurethane material, a transmittance varies depending on heat generation control during curing and a manufacturing method.

In other words, the present inventors completed the present invention by discovering that when manufacturing a window made of a polyurethane material, a temperature of the polyurethane

prepolymer and a temperature of a mold affect a transmittance of the window, and a thickness of a cake-shaped polyurethane cured product also affects the transmittance of the window.

When the temperature of the polyurethane prepolymer in step a) above is 50°C or higher to less than 100°C, the transmittance of the window is greatly improved. However, when the temperature is less than 50°C or 100°C or higher, the transmittance of the window significantly decreases.

It appears that the reason why the transmittance decreases depending on the temperature of polyurethane prepolymer is because when the temperature increases, a degree of crystallinity of an internal structure of urethane increases.

In an embodiment of the present invention, the temperature of the polyurethane prepolymer may be preferably 50°C to 90°C, and more preferably 50°C to 70°C.

In step a) above, the polyurethane prepolymer with a weight average molecular weight of 500 to 3000, and more preferably, 800 to 2500 may be used.

The polyurethane prepolymer may be prepared by a polymerization of compositions including at least one isocyanate compound selected from the group consisting of toluene diisocyanate, 4,4'-diphenylmethane diisocyanate, naphthalene-1,5-diisocyanate, toluidine diisocyanate, paraphenylene diisocyanate, xylene diisocyanate, isophorone diisocyanate, hexamethylene diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, and cyclohexane diisocyanate; and one or more polyol compound components selected from the group consisting of polyether polyol (e.g., poly(oxytetramethylene) glycol, poly(oxypropylene) glycol, poly(oxyethylene) glycol), polycarbonate polyol, polyester polyol, polycaprolactone polyol, etc.

As the isocyanate compound above, those selected from toluene diisocyanate (TDI), 4,4'-diphenyl methane diisocyanate,

dicyclohexylmethane diisocyanate, etc., may be more preferably used, and as the polyol compound, those selected from polycaprolactone polyol, polytetramethylene ether glycol (PTMEG), polypropylene ether glycol (PPG), polyethylene ether glycol (PEG), etc., may be more preferably used.

The polymerization composition may further include at least one chain extenders selected from the group consisting of ethylene glycol (EG), 1,2-propylene glycol, 1,3-propylene glycol, 1,2-butanediol, 1,3-butanediol, 2-methyl-1,3-propanediol, 1,4-butanediol (BDO), neopentyl glycol, 1,5-pentanediol, 3-methyl-1,5-pentanediol, 1,6-hexanediol, diethylene glycol, dipropylene glycol, tripropylene glycol, etc.

In step a) above, as the curing agent, at least one selected from the group consisting of 4,4'-methylene-bis-(2-chloroaniline) (MBOCA), diethyltoluenediamine (DETDA), 3,5-dimethylthio-2,4-toluenediamine and isomers thereof (e.g., 3,5-diethyltoluene-2,6-diamine); 3,5-diethyltoluene-2,4-diamine and isomers thereof; 4,4'-bis-(sec-butylamino)-diphenylmethane; 1,4-bis-(sec-butylamino)-benzene; 4,4'-methylene-bis-(2-chloroaniline); 4,4'-methylene-bis-(3-chloro-2,6-diethylaniline) (MCDEA); polytetramethyleneoxide-di-p-aminobenzoate; N,N'-dialkyldiamino diphenyl methane; p,p'-methylene dianiline (MDA); m-phenylenediamine (MPDA); 4,4'-methylene-bis-(2,6-diethylaniline) (MDEA); 4,4'-methylene-bis-(2,3-dichloroaniline) (MDCA); 4,4'-diamino-3,3'-diethyl-5,5'-dimethyl diphenylmethane; 2,2',3,3'-tetrachloro diamino diphenylmethane; and trimethylene glycol di-p-aminobenzoate, etc., may be used.

In step a) above, the polyurethane prepolymer and the curing agent may be mixed in a weight ratio of 9: 1 to 7: 3 based on a dry weight.

In step b) above, the mold heated to a temperature of 30°C or higher to less than 100°C is used. When the temperature of the mold is less than 30°C, the transmittance may be improved, but since the polyurethane is not hardened, it is difficult to apply to the present invention. In addition, when the temperature of the mold is 100°C or higher, the transmittance of the window significantly decreases, which is not preferable.

As described above, it is believed that the reason why the transmittance decreases when the temperature of the mold is 100°C or higher is because when the temperature of the mold increases, the degree of crystallinity of the internal structure of urethane increases.

In an embodiment of the present invention, the temperature of the mold may be preferably 30°C to 80°C, more preferably 30°C to 70°C, even more preferably 30°C to 60°C, and particularly preferably 30°C to 50°C.

In step b) above, the injection of the mixture of the polyurethane prepolymer and the curing agent into the mold may be made to a thickness of 5 mm or less. When the injection thickness exceeds 5 mm, the transmittance of the window significantly decreases.

As described above, it is believed that the reason why the transmittance decreases according to the injection thickness is because when the injection thickness becomes thicker, heat energy is accumulated during an exothermic reaction with the curing agent, the internal temperature increases, and the degree of crystallinity increases.

In an embodiment of the present invention, the injection thickness may preferably be 2 mm to 5 mm, more preferably 2 mm to 4 mm, and even more preferably 2 mm to 3 mm.

When the mixture is injected to the thickness described above, the thickness of the polyurethane cured product (cake) is also determined depending on the injection thickness.

In an embodiment of the present invention, it is particularly preferable that the temperature of the polyurethane prepolymer in step a) above is 50°C to 70°C, the temperature of the mold in step b) above is 30°C to 60°C, and the injection of the mixture of the polyurethane prepolymer and the curing agent in step b) above into the mold is made to a thickness of 2 mm to 3 mm.

The window for a polishing pad of the present invention is manufactured by the manufacturing method of the present invention, and has a transmittance of 5% or more, preferably 7% or more, and more preferably 8% or more based on a thickness of 1.9 mm.

Hereinafter, the present invention will be described in detail with reference to the Examples. However, the embodiments according to the present invention may be modified into various other forms, and the scope of the present invention should not be construed as being limited to the embodiments described in detail below. Examples of the present invention are provided to more completely explain the present invention to those with average knowledge in the art.

Example 1-1: Manufacturing of window for polishing pad

80% by weight of polyurethane prepolymer (PT411 from KPX company, NCO%: 9.2, viscosity: 24000cPs, weight average molecular weight: 1850) heated to 90°C and 20% by weight of curing agent (MOCA, 4,4'-methylenebis(2-chloroaniline)) were mixed. The mixture was injected into a mold heated to 50°C and

first hardened for 1 hour, and then post-cured in an oven for 16 hours to prepare a Cake (polyurethane cured product) with a thickness of 3 mm. Next, the Cake was processed to a thickness of 1.9 mm to manufacture a window.

Example 1-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer having a temperature of 70°C in Example 1-1 was used.

Example 1-3: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer having a temperature of 50°C in Example 1-1 was used.

Example 2-1: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to 70°C in Example 1-1 was used and the mold heated to 80°C was used.

Example 2-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 2-1, except that the mold heated to 60°C in Example 2-1 was used.

Example 2-3: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 2-1, except that the mold heated to 50°C in Example 2-1 was used.

Example 2-4: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 2-1, except that the mold heated to 30°C in Example 2-1 was used.

Example 3-1: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to 70°C in Example 1-1 was used and the thickness of the Cake was adjusted to 5 mm.

Example 3-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 3-1, except that the thickness of the Cake in Example 3-1 was adjusted to 4 mm.

Example 3-3: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 3-1, except that the thickness of the Cake in Example 3-1 was adjusted to 3 mm.

Example 3-4: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 3-1, except that the thickness of the Cake in Example 3-1 was adjusted to 2 mm.

Comparative Example 1-1: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to 100°C in Example 1-1 was used.

Comparative Example 1-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to 40°C in Example 1-1 was used.

Comparative Example 2-1: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to a temperature of 70°C in Example 1-1 was used and the mold heated to 100°C was used.

Comparative Example 2-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Comparative Example 2-1, except that the mold heated to 20°C in Comparative Example 2-1 was used.

Comparative Example 3-1: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Example 1-1, except that the polyurethane prepolymer heated to 70°C in Example 1-1 was used and the thickness of the Cake was adjusted to 6 mm.

Comparative Example 3-2: Manufacturing of window for polishing pad

A window with a thickness of 1.9 mm was manufactured in the same method as in Comparative Example 3-1, except that the thickness of the Cake in Comparative Example 3-1 was adjusted to 8mm.

Test Example 1: Transmittance Measurement

After conditioning the 1.9 mm thick window manufactured in the above Examples and Comparative Examples with a diamond disk (LPX2 product from Saesol company) for 15 minutes, the transmittance was measured at 670 nm light using a transmittance analysis device (UV-Visible Spectrometer Lambda-365 from Perkin Elmer company), and the results are shown in Table 1 below.

[Table 1]

Division	Prepolymer temperature	Mold temperature	Cake thickness	Transmittance
	°C	°C	mm	%
Example 1-1	90	50	3	5.4
Example 1-2	70	50	3	8.1
Example 1-3	50	50	3	9.0
Comparative Example 1-1	100	50	3	3.4
Comparative Example 1-2	40	50	3	3.6
Example 2-1	70	80	3	5.5
Example 2-2	70	60	3	7.4
Example 2-3	70	50	3	8.1
Example 2-4	70	30	3	9.2
Comparative Example 2-1	70	100	3	4.8
Comparative Example 2-2	70	20	3	11.3
Example 3-1	70	50	5	5.2
Example 3-2	70	50	4	6.5
Example 3-3	70	50	3	8.1
Example 3-4	70	50	2	9.8
Comparative Example 3-1	70	50	6	4.5
Comparative Example 3-2	70	50	8	4.0

In the case of Comparative Example 2-2 above, the transmittance is improved depending on the temperature of the

mold, but since the polyurethane is not cured, it is difficult to apply to the manufacturing of the window.

【CLAIMS】

【Claim 1】

A method for manufacturing a window for a polishing pad, comprising:

a) mixing a curing agent with a polyurethane prepolymer having a temperature of 50°C or higher to less than 100°C to prepare a mixture;

b) injecting the mixture into a mold heated to a temperature of 30°C or higher to less than 100°C to a thickness of 5 mm or less;

c) demolding a polyurethane cured product from the mold; and

d) processing the polyurethane cured product to a thickness of the window of the polishing pad.

【Claim 2】

The method according to claim 1, wherein in step a) above, the polyurethane prepolymer has a temperature of 50°C to 90°C.

【Claim 3】

The method according to claim 1, wherein in step b) above, the mold is heated to a temperature of 30°C to 80°C.

【Claim 4】

The method according to claim 1, wherein in step b) above, the injection of the mixture is made to a thickness of 2 mm to 5 mm.

【Claim 5】

The method according to claim 1, wherein the temperature of the polyurethane prepolymer in step a) above is 50°C to 70°C, the temperature of the mold in step b) above is 30°C to 60°C, and the injection of the mixture of the polyurethane prepolymer and the curing agent in step b) above into the mold is made to a thickness of 2 mm to 3 mm.

【Claim 6】

The method according to claim 1, wherein the polyurethane prepolymer has a weight average molecular weight of 500 to 3000.

【Claim 7】

The method according to claim 6, wherein the polyurethane prepolymer is prepared by a polymerization of compositions comprising at least one isocyanate compound selected from the group consisting of toluene diisocyanate, 4,4'-diphenylmethane diisocyanate, naphthalene-1,5-diisocyanate, toluidine diisocyanate, paraphenylene diisocyanate, xylene diisocyanate, isophorone diisocyanate, hexamethylene diisocyanate, 4,4'-dicyclohexylmethane diisocyanate, and cyclohexane diisocyanate; and at least one polyol compound components selected from the group consisting of polyether polyol, polycarbonate polyol, polyester polyol, and polycaprolactone polyol.

【Claim 8】

The method according to claim 7, wherein the composition further comprises at least one chain extenders selected from the group consisting of ethylene glycol (EG), 1,2-propylene glycol, 1,3-propylene glycol, 1,2-butanediol, 1,3-butanediol, 2-methyl-1,3-propanediol, 1,4-butanediol (BDO), neopentyl glycol, 1,5-pentanediol, 3-methyl-1,5-pentanediol, 1,6-hexanediol, diethylene glycol, dipropylene glycol, and tripropylene glycol.

【Claim 9】

The method according to claim 1, wherein the curing agent comprises at least one selected from the group consisting of 4,4'-methylene-bis-(2-chloroaniline) (MBOCA), diethyltoluenediamine (DETDA), 3,5-dimethylthio-2,4-toluenediamine and isomers thereof; 3,5-diethyltoluene-2,4-diamine and isomers thereof; 4,4'-bis-(sec-butylamino)-diphenylmethane; 1,4-bis-(sec-butylamino)-benzene; 4,4'-

methylene-bis-(2-chloroaniline); 4,4'-methylene-bis-(3-chloro-2,6-diethylaniline) (MCDEA); polytetramethyleneoxide-di-p-aminobenzoate; N,N'-dialkyldiamino diphenyl methane; p,p'-methylene dianiline (MDA); m-phenylenediamine (MPDA); 4,4'-methylene-bis-(2,6-diethylaniline) (MDEA); 4,4'-methylene-bis-(2,3-dichloroaniline) (MDCA); 4,4'-diamino-3,3'-diethyl-5,5'-dimethyl diphenylmethane; 2,2',3,3'-tetrachloro diamino diphenylmethane; and trimethylene glycol di-p-aminobenzoate.

【Claim 10】

The method according to claim 1, wherein the polyurethane prepolymer and the curing agent are mixed in a weight ratio of 9: 1 to 7: 3 based on a dry weight.

【Claim 11】

A window for a polishing pad manufactured by the manufacturing method of claim 1 and having a transmittance of 5% or more at 670 nm light based on a thickness of 1.9 mm.

【Claim 12】

A polishing pad comprising the window according to claim 11.