

Specification

Title of the Invention: Lead-Free Solder Alloy

5 Technical Field

【0001】

 This invention relates to a Sn-Ag-Cu based solder alloy which can be used in a high temperature, high current density environment.

10 Background Art

【0002】

 In recent years, due to reductions in the size and increases in the performance of central processing units (CPUs) which are mainly used for computers, the current density per terminal of semiconductor elements mounted in CPUs has been increasing. It is said that the current density will reach the order of around $10^4 - 10^5$ A/cm² in the future. As the current density increases, the heat generated by passage of current increases, thereby elevating the temperature of the terminals and increasing the thermal vibrations of atoms in the terminals. As a result, the occurrence of electromigration developed in solder joints becomes marked, eventually leading to fracture of the solder joints.

20 **【0003】**

 Electromigration (which may hereinafter be abbreviated as EM) is a phenomenon which occurs when a current is flowing through a conductor such as a solder joint. Atoms in the solder joint which are undergoing thermal vibrations collide with electrons forming the electric current, and momentum is transferred from the electrons to the atoms, thereby increasing the momentum of the atoms. The atoms having an increased momentum migrate toward the anode side of the solder joint by going along the flow of electrons. When atoms migrate toward the anode side of the solder joint, lattice vacancies develop on the cathode side of the solder joint. These lattice vacancies accumulate to form voids. Growth of the voids eventually causes fracture of the solder joint. In this manner, electromigration develops in locations where electrical conduction takes place, and it has become a

problem even inside solder joints.

【0004】

The environment of use of a solder joint which is envisaged in this specification is an environment at the time of operating CPUs with a high current density and is referred to below as a high current density environment.

Evaluation of the reliability of a solder joint in such an environment can be carried out by an electromigration test (also referred to as an EM test) in which a current with a high current density of $0.12 \text{ mA}/\mu\text{m}^2$ is continuously passed through a solder joint for 2500 hours in the air at 165°C .

【0005】

Sn-Cu solder alloys and Sn-Ag-Cu solder alloys have been widely used as lead-free solder alloys. Sn-Cu solder alloys and Sn-Ag-Cu solder alloys easily develop electromigration because Sn, which is the main component of these alloys, has a large effective charge number. As a result, solder joints made of these alloys readily fail in a high current density environment.

【0006】

Patent Document 1 discloses a Sn-Ag-Cu-In solder alloy which has improved resistance to thermal fatigue and thereby suppresses the occurrence of cracks. The Sn-Ag-Cu-In solder alloy disclosed in Patent Document 1 has improved wettability due to the addition of a small amount of In. As a result, the occurrence of cracks and fracture of solder joints are suppressed.

Prior Art Documents

Patent Documents

【0007】

Patent Document 1: JP 2002-307187 A

Summary of the Invention

Problem to be Solved by the Invention

【0008】

However, Patent Document 1 does not contain any suggestion or teaching concerning suppressing the occurrence of electromigration and suppressing

fracture of solder joints by adding In to a Sn-Ag-Cu solder alloy. Although Patent Document 1 refers to resistance to thermal fatigue, it does not contain sufficient discussion of the effects when electrical conduction takes place for a long period in a high current density environment at a high temperature. Thus, the environment of operation of CPUs is not faithfully reproduced in Patent Document 1.

【0009】

The specific solder alloys which are investigated in Patent Document 1 are ones having alloy compositions containing 0.5% In. These alloy compositions have an extremely low In content, which makes it impossible to confirm whether resistance to thermal fatigue is sufficiently improved by the addition of In. It is not verified at all whether these alloy compositions can avoid electromigration and various kinds of problems caused thereby when electrical conduction takes place for a long period in a high current density environment at a high temperature. Accordingly, the solder alloy disclosed in Patent Document 1 cannot be said to solve the problem of increased electromigration due to the increase in current density in recent years.

【0010】

Embodiments of the present invention seek to provide a lead-free solder alloy which can suppress an increase in the interconnection resistance of solder joints by suppressing of the growth of void due to electromigration in a high temperature, high current density environment.

【0011】

The present inventors performed detail investigation of the composition of a Sn-Ag-Cu-In solder alloy from the standpoint of suppressing the occurrence of electromigration. Namely, the present inventors considered that when Sn atoms migrated toward the anode side along with the flow of electrons to leave lattice vacancies in the cathode side, In atoms might fill the lattice vacancies and could suppress the growth of the lattice vacancies. As a result, the present inventors found that an In content of 1.0 - 13.0 % in a Sn-Ag-Cu-In solder alloy can effectively suppress the formation of lattice vacancies and the growth of void due to electromigration.

Means for solving Problem

【0012】

According to a first aspect of the present invention, there is provided a lead-free solder alloy having an alloy composition consisting essentially of, in mass percent, In: 1.0 or more and less than 3.0 %, Ag: 0.1 or more and less than 1.5 %, Cu: 0.3 through 1.0 %, and a remainder of Sn, wherein when the lead-free solder alloy is used as a solder joint under an energizing condition at a current density of $0.12 \text{ mA}/\mu\text{m}^2$ in the air at 165°C , a percent increase in a resistance value of the solder joint from a resistance value before the energization to a resistance value when 2500 hours have elapsed from the start of the energization is not more than 30 % and a difference between the percent increase in the resistance value when 2500 hours have elapsed from the start of the energization and a percent increase in a resistance value when 500 hours have elapsed from the start of the energization is not more than 5%.

【0013】

The Ag content of the lead-free solder alloy may be 0.3 - 1.5 % by mass.

【0014】

The alloy composition may contain, in mass percent, In: 2.0 - 3.0 %, Ag: 0.3 - 1.5 %, and Cu: 0.5 - 0.7 %.

【0015】

20

【0016】 Preferably, the alloy composition contains, in mass percent, In: 1.0 -2.0%.

【0016a】 According to a second aspect of the present invention, there is provided a lead-free solder alloy having an alloy composition consisting essentially of, in mass percent, In: more than 7.0 and 13.0 or less %, Ag: 0.1 or more and less than 1.5 %, Cu: 0.3 through 1.0 %, and a remainder of Sn,

wherein when the lead-free solder alloy is used as a solder joint under an energizing condition at a current density of $0.12 \text{ mA}/\mu\text{m}^2$ in the air at 165°C , a percent increase in a resistance value of the solder joint from a resistance value before the energization to a resistance value when 2500 hours have elapsed from the start of the energization is not more than 30 % and a difference between the percent increase in the resistance value when 2500 hours have elapsed from the start of the energization and a percent increase in a resistance value when 500 hours have elapsed from the start of the energization is not more than 5%.

4a

【0016b】 Preferably, the alloy composition contains, in mass percent, In: 7.0 -10.0%.

【0017】

According to a third aspect of the present invention, there is provided a solder joint made from the lead-free solder alloy as defined in the first or second aspect.

5

【0018】

According to a fourth aspect of the present invention, there is provided a method of suppressing electromigration of a solder joint during electrical conduction comprises forming a solder joint using the lead-free solder alloy as defined in the first or second

10 aspect.

Effects of the Invention

【0019】

Thereby, the lead-free solder alloy according to embodiments of the invention contains 1.0 - 13.0 % of In in the Sn-In-Ag-Cu solder alloy so that the electromigration which is easily formed in such a lead-free solder alloy can be suppressed. Further, When In content is within a range of 5 through 10%, not only is it possible to effectively suppress the formation of electromigration, it is also possible to obtain excellent mechanical properties at high temperatures.

【0020】

Additionally, the solder joint according to embodiments of the invention is made from the above-mentioned lead-free solder alloy so that it is possible to suppress fracture of a solder joint due to electromigration in a high current density environment at a high temperature.

【0021】

Still further, the method of suppressing electromigration of a solder joint during electrical conduction according to embodiments of the invention can suppress the growth of void due to electromigration in the solder joint during electrical conduction.

Brief Explanation of the Drawings

【0022】

[Figure 1] Figure 1 is a graph schematically showing the relationship between the In concentration of a solder joint and the distance from the cathode side of the solder joint at the end of an EM test.

[Figure 2A] Figure 2A is a schematic vertical cross-sectional view of a FCLGA package used in an EM test.

[Figure 2B] Figure 2B is a schematic plan view of the FCLGA package used in an EM test.

[Figure 3] Figure 3 is a diagram schematically showing the flowing directions of electrons (e^-) in soldered joints which are subjected to an EM test.

[Figure 4] Figure 4 is a cross-sectional SEM photograph showing intermetallic compounds formed at the boundary between a solder joint made of a Sn-7In-1Ag-0.5Cu solder alloy and an electrode with a Ni/Au coating.

[Figure 5] Figure 5 is a graph showing the variation in the resistance of a solder joint made of a Sn-0.7Cu solder alloy as a comparative example as a function of the length of time of an EM test.

[Figure 6] Figure 6 is a graph showing the variation in the resistance of a solder joint made of a Sn-1Ag-0.5Cu-7In solder alloy according to the present invention as a function of the length of time of an EM test.

[Figure 7A] Figure 7A is a graph showing the variation in the resistance of a solder joint made of a Sn-1Ag-0.5Cu-4In solder alloy according to the present invention as a function of the length of time of an EM test.

[Figure 7B] Figure 7B is a graph showing the variation in the resistance of a solder joint made of a Sn-1Ag-0.5Cu-13In solder alloy according to the present invention as a function of the length of time of an EM test.

[Figure 8] Figure 8 is a SEM photograph of a cross section of a solder joint formed from a Sn-0.7Cu solder alloy as a comparative example on a Cu electrode having a Ni/Au coating at the end of an EM test for 2500 hours.

[Figure 9] Figure 9 is a SEM photograph of a cross section of a solder joint formed from a Sn-7In-1Ag-0.5Cu solder alloy according to the present invention on a Cu electrode having a Ni/Au coating at the end of an EM test for 2500 hours.

[Figure 10A] Figure 10A is a plan view of a test piece used in a tensile test.

[Figure 10B] Figure 10B is an end view of the test piece used in the tensile test shown in Figure 10A.

[Figure 11] Figure 11 is a graph showing the tensile strength of a Sn-(0 - 15)In-1Ag-0.5Cu solder alloy as a function of the In content thereof.

[Figure 12] Figure 12 is a graph showing the elongation at break of a Sn-(0 - 15)In-1Ag-0.5Cu solder alloy as a function of the In content thereof.

Modes for Carrying Out the Invention

【0023】

The present invention will next be described in detail. In this description, percent with respect to the composition of a solder alloy means mass percent unless otherwise indicated.

【0024】

A Sn-In-Ag-Cu solder alloy according to the present invention contains 1.0 - 13.0 % of In, which makes it possible to suppress the growth of void due to electromigration. Below, the relationship between Sn, In, and electromigration will be explained in detail.

【0025】

When a solder joint made using a solder alloy according to the present invention conducts electricity at a high temperature, Sn atoms preferentially migrate toward the anode side of the solder joint along with the flow of electrons as discussed later, leaving lattice vacancies on the cathode side. On the other hand, In atoms fill the lattice vacancies formed on the cathode side of the solder joint, leading to the formation of a Sn-rich layer on the anode side and an In-rich layer on the cathode side of the solder joint. As the In content of the solder alloy increases, this phenomenon becomes more marked, and the In-rich layer and the Sn-rich layer increase in thickness. As a result, when an EM test is carried out on such a solder joint by passing an electric current at a high current density at a high temperature, during the period until approximately 500 hours have elapsed, a resistance shift in which the resistance of the solder joint increases is observed. This increase in resistance occurred in the initial stage of an EM test is thought to be caused by the above-mentioned phase separation (the formation of an Sn-rich layer and an In-rich layer).

【0026】

As shown in Table 1, the resistivity of In is about 8 times that of Sn. Therefore, the increase in resistance of a solder joint made from a Sn-In-Ag-Cu solder alloy in the initial stage of an EM test is thought to be attributable to the growth of an In-rich layer. This increase in the initial stage is expected to be greater as the thickness of the In-rich layer is thicker.

【0027】

When In atoms fill the lattice vacancies formed on the cathode side as a result of migration of Sn atoms, In atoms can substitute for the sites of lattice vacancies which were formerly occupied by β -Sn, thereby forming a solid solution. Such substitution of In atoms in the form of a solid solution is thought to

suppress void nucleation on the cathode side, thereby increasing the resistance of the solder joint to electromigration (suppression of the growth of voids due to electromigration).

5 **【0028】 【Table 1】**

Metal	Atomic radius (pm)	Resistivity (ohm.cm)	Melting point (°C)
In	167	83.7	157
Sn	140	10.1	232

【0029】

In a binary alloy constituted of two elements have different diffusivity, when these two elements want to migrate in the same direction, only the one
 10 element having the larger diffusivity preferentially migrates in the intended direction, leaving lattice vacancies. On the other hand, the other element having the smaller diffusivity fills the formed lattice vacancies. In general, the larger the effective charge number, the greater the diffusivity. The effective charge numbers for Sn and In are -18 and -2, respectively. The term "effective charge number"
 15 used herein indicates the degree of easiness of the occurrence of electromigration. Accordingly, Sn atoms, which are greater in the absolute value of effective charge number, preferentially migrates in the intended direction along with the flow of electrons, while In atoms fill the lattice vacancies formed by migration of Sn atoms.

20 **【0030】**

Therefore, the formation of an In-rich layer involves the following two steps, namely, the occurrence of a flow of Sn atoms toward the anode side which is induced by EM and the occurrence of a flow of In atoms in the opposite direction. The flow of Sn atoms is produced as a result of collision of Sn atoms with
 25 electrons accompanied by momentum transfer. Due to the migration of Sn atoms, In atoms cannot remain in its initial position in the lattice which it assumed before conduction, and it must migrate in the opposite direction from Sn. When Sn atoms

start to migrate towards the anode side of a solder joint together with electrons, a compressive stress develops on the anode side of the solder joint. On the other hand, a tensile stress develops on the cathode side of the solder joint, resulting in the formation of a stress gradient between the anode and cathode. If the stress gradient is sufficiently large, In atoms, which are relatively difficult to migrate, starts to migrate from the anode side toward the cathode side of the solder joint. Accordingly, it takes a certain time to form an In-rich layer which appears as an increase in resistance in the initial stages of an EM test. As shown in Figures 6 and 7B which are discussed later, the time required to form an In-rich layer is in the range of 100 to 500 hours, for example, and it depends on the In content of a solder alloy (the lower the In content, the shorter). When the In content is minute as in the solder alloy disclosed in Patent Document 1, the time required to form an In-rich layer is reduced, but filling of lattice vacancies by In atoms becomes inadequate and voids end up growing.

15 **【0031】**

When Sn atoms form a thin Sn-rich layer at the interface on the anode side of a solder joint, almost all In atoms migrate from the Sn-rich layer toward the cathode side.

【0032】

20 Figure 1 schematically shows the relationship between the concentration of In in a solder joint after an EM test and the distance from the anode side of the solder joint. As shown in Figure 1, after an electric current with a high current density is passed through a solder joint for a long period of time, the In concentration (C_1) in the Sn-rich layer having a small distance from the anode side of a solder joint is nearly zero, and in the central portion of the solder joint (solder matrix) between the cathode and anode sides (indicated as a Sn-In layer in Figure 1), the In concentration of the solder alloy is C_2 . The In concentration in the In-rich layer which is located away from the anode side is much higher than C_2 . In this case, the rate of growth of the Sn-rich layer can be expressed by the following

25 Equation (1):

30 **【0033】 【Equation 1】**

$$(C_2 - C_1) \frac{dy}{dt} = J_{Sn} = C_{Sn} \times \frac{D_{Sn} \times z^*}{\kappa T} \times e \times \rho \times j \quad (1)$$

【0034】

In the equation, y is the thickness of the Sn-rich layer, t is the conduction time (duration of passage of current), C_1 and C_2 are respectively the In content in the Sn-rich layer and In concentration in the solder alloy, J_{Sn} is the EM-induced atomic flux of Sn, C_{Sn} , D_{Sn} , and z^* are respectively the concentration, diffusivity, and effective charge number of Sn which is the diffusing species in the base solder, ρ is the resistivity of the solder alloy, κ is Boltzmann's constant, T is the temperature, e is the electron charge, and j is the current density.

【0035】

If the EM-induced atomic flux of Sn is limiting, the growth rate of the Sn-rich layer dy/dt should be constant, which reveals that the growth rate of the Sn-rich layer has a linear dependency on the conduction time. However, if the diffusion of In in the Sn-rich layer is limiting, the growth rate of the Sn-rich layer is controlled by the slower In atom diffusion and can be expressed by the following Equation (2):

【0036】 【Equation 2】

$$(C_2 - C_1) \frac{dy}{dt} = J_{In} = -D_{In} \frac{dC_{In}}{dx} \quad (2)$$

【0037】

In the equation, J_{In} is the diffusion flux of In out of the anode side, namely, from the Sn-rich layer, D_{In} is the diffusivity of In, C_{In} is the In concentration of the solder alloy, and x is the distance from the Sn-rich layer in the direction perpendicular to the Sn-rich layer. Seeing that the growth rate of the Sn-rich layer or the In-rich layer is depending upon the In concentration in the solder alloy and obey a parabolic dependence, this is in agreement with Equation (2).

【0038】

As discussed above, with a Sn-In-Ag-Cu solder alloy according to the present invention, due to the presence of a sufficient amount of In, after Sn atoms form a Sn-rich layer on the anode side of a solder joint as a result of conduction which causes Sn atoms to preferentially migrate toward the anode side, the above-

described stress gradient causes In atoms to migrate toward the cathode side of the solder joint and form an In-rich layer on the cathode side. At this time, In atoms can fill lattice vacancies formed by migration of Sn atoms, thereby suppressing the formation of lattice vacancies. As a result, the formation of voids due to electromigration can be suppressed, resulting in preventing fracture of a solder joint.

【0039】

The alloy composition of a solder alloy according to the present invention will be described as follows.

【0040】

The In content of a solder alloy according to the present invention is at least 1.0% to at most 13.0%. Indium is effective at suppressing the occurrence of electromigration during conduction and improving the mechanical properties of a solder joint at high temperatures, and it lowers the melting point of the solder alloy. If the In content is larger than 13.0%, the mechanical properties and particularly the ductility of a solder alloy deteriorate. If the In content is less than 1.0%, the effect of the addition of In cannot be adequately exhibited. The lower limit on the In content is preferably 2.0% and more preferably 5.0%. The upper limit of the In content is preferably 13.0% and more preferably 10.0%.

【0041】

From the standpoint of obtaining excellent tensile strength without deteriorating elongation at break, it is particularly preferable for the In content to be in the range of 5.0 - 10.0 %. After soldering is carried out with a Sn-In-Ag-Cu solder alloy according to the present invention and an electric current is passed through the resulting solder joint, as shown in Figure 1, the initial composition of the solder alloy is maintained in the central portion between the cathode and anode sides (indicated as a Sn-In layer in Figure 1) of the solder joint. In a solder alloy according to the present invention, due to the form of In which is in solid solution in a Sn phase, the solder alloy has a high tensile strength at a high temperature, and a decrease in elongation at break can also be suppressed. Accordingly, if a solder alloy according to the present invention has an In content of 5.0 - 10.0 %, not only is it possible to suppress fracture of a solder joint due to electromigration, it is also

possible to obtain excellent mechanical properties at high temperatures.

【0042】

The Ag content of a solder alloy according to the present invention is 0.1 - 4.0 %. Ag is effective at improving the wettability and mechanical properties such as the tensile strength of a solder alloy. If the Ag content is greater than 4.0%, the liquidus temperature (also referred to liquidus line temperature or LL) of the solder alloy ends up increasing. If the Ag content is less than 0.1%, wettability deteriorates. The Ag content is preferably at least 0.3% to at most 3.0%.

【0043】

The Cu content of a solder alloy according to the present invention is 0.3 - 1.0 %. Cu is effective at improving the wettability and mechanical properties such as the tensile strength of a solder alloy and suppressing Cu erosion of electrodes or terminals which are typically made of Cu. If the Cu content is greater than 1.0%, the wettability of the solder alloy deteriorates and the liquidus temperature thereof increases. If the Cu content is less than 0.3%, the bonding strength of a solder joint deteriorates. The Cu content is preferably at least 0.5% to at most 0.7%.

【0044】

A solder alloy according to the present invention preferably has an alloy composition consisting essentially of In: 1.0 - 13.0 %, Ag: 0.3 - 3.0 %, Cu: 0.3 - 1.0 %, and a remainder of Sn, more preferably In: 2.0 - 13.0 %, Ag: 0.3 - 3.0 %, Cu: 0.5 - 0.7 %, and a remainder of Sn. Another preferably solder alloy according to the present invention has an alloy composition consisting essentially of In: 5.0 - 10.0 %, Ag: 0.1 - 1.5 %, Cu: 0.3 - 1.0 %, and a remainder of Sn.

【0045】

A bonding method using a solder alloy according to the present invention may be carried out by the reflow method in a conventional manner and does not require any special conditions by using the solder alloy according to the invention. Specifically, reflow soldering is generally carried out at a temperature of from a few degrees to around 20° C higher than the liquidus temperature of the solder alloy.

【0046】

A solder joint according to the present invention is suitable for use to connect an IC chip to its substrate (an interposer) in a semiconductor package or connect a semiconductor package to a printed circuit board. The term "solder joint" which connects between two terminals means the portion from one terminal
5 to the other terminal.

【0047】

When a solder joint according to the present invention undergoes conduction with a current density of $0.12 \text{ mA}/\mu\text{m}^2$ in the air at 165°C , it is
10 preferable that the percent increase in the resistance after 2500 hours of conduction be at most 30% when compared to the resistance before the start of conduction and at most 5% when compared to the resistance after 500 hours of conduction. As a result, even when a solder joint according to the present invention is used for conduction for long periods in such a high temperature, high current density
15 environment, breakdown due to electromigration does not take place.

【0048】

A solder joint according to the present invention is thought to have excellent heat resistance at high temperatures when not conducting. Therefore, a solder joint according to the present invention can be formed by the above-
20 described bonding method using typical soldering conditions.

【0049】

The suppression method of electromigration in the solder joint during the electrical conduction according to the present invention is realized by forming a solder joint using a solder alloy according to the present invention for bonding
25 between a semiconductor element and a substrate, for example. In the present invention, it is possible to suppress the formation of voids due to electromigration in a solder joint during electrical conduction, which can takes place in solder joints which carry electric current inside a CPU during its operation.

【0050】

30 A solder alloy according to the present invention can be used in the form of a preform, a wire, a solder paste, a solder ball (also called solder sphere), or the like. For example, solder balls may have a diameter in the range of 1 - 100 μm .

【0051】

A solder alloy according to the present invention can also manufacture low α -ray solder balls by use of low α -ray materials as raw materials. Such low α -ray solder balls can suppress software errors when they are used to form solder bumps
5 in the periphery of memories.

Executed Examples

【0052】

Various lead-free Sn-Ag-Cu-In solder alloys were prepared in order to
10 investigate electromigration of solder joints formed from the solder alloys and evaluate the mechanical properties thereof.

【0053】

1. Measurement of electromigration (EM test)

Prior to an EM test, first, the solderability performance of a Sn-4In-1Ag-
15 0.5Cu solder alloy, a Sn-7In-1Ag-0.5Cu solder alloy, and a Sn-13In-1Ag-0.5Cu solder alloy was investigated. Solder balls of a solder alloy to be tested were placed on Cu pads having a Ni/Au coating and soldered by reflow using a water-soluble non-halogenated flux to form solder bumps.

【0054】

Figure 4 is a SEM photograph of a cross section of a solder bump made of a
20 Sn-7In-1Ag-0.5Cu solder alloy at a magnification of 5000x. An intermetallic compound 43 was formed at the interface between a solder bump 41 and a Ni coating 42. The intermetallic compound 43 is a typical acicular Ni-Sn intermetallic compound, indicating that the soldering reaction between the solder alloy and the
25 Ni/Au coating is very good. Thus, it was confirmed that the solderability of this lead-free solder alloy was excellent. The formation of a Ni-Sn intermetallic compound as shown in Figure 4 was also observed in solder bumps made of the other solder alloys according to the present invention having an In content of 4% or 13%. Accordingly, the solderability performance of all these solder alloys
30 according to the present invention is excellent.

【0055】

Figures 2A and 2B respectively show a schematic vertical cross sectional

view and a schematic plan view of a FCLGA (flip chip land grid array) package 10 used for an EM test. As shown in Figure 2A, by way of example, the FCLGA package 10 comprised a die 11 measuring 10 mm x 10 mm x 750 μm in thickness, a die substrate 12 measuring 22 mm x 22 mm x 1.0 mm in thickness, and an
 5 organic laminate substrate 13 measuring 35 mm x 35 mm x 1.2 mm in thickness. The die 11 and the die substrate 12 are bonded by flip chip (FC) bonding 14, while the die substrate 12 and the organic laminate substrate 13 are bonded by BGA bonding.

【0056】

10 In this executed example, an EM test of solder joints was carried out using an FCLGA package having FC-bonded solder joints formed from solder balls made of a solder alloy according to the present invention or a comparative solder alloy by the above-described method. The solder alloy according to the present invention had a composition of Sn-(4, 7, or 13)In-1Ag-0.5Cu, and the comparative
 15 solder alloy had a composition of Sn-0.7Cu.

【0057】

As schematically shown in Figure 3, in the EM test, the test device was designated so that a whole row of solder bumps could be tested at the same time in the same polarity and with the same current. Thus, in this part, the overall
 20 resistance of the solder-joints in a row having the same direction of current flow could be measured.

【0058】

The EM test was performed in a chamber. The chamber in which a FCLGA package to be tested was already placed was heated to 165° C and maintained at
 25 that temperature. Once a steady state of the temperature had been reached, a constant current of 950mA was applied to the test part (the FCLGA package), and the resistance was continuously monitored *in situ* for 2500 hours or longer. The current density in each solder bump during conduction was 0.12 mA/ μm^2 (calculated by the equation: 950mA/($\pi \times (100 \mu\text{m}/2)^2$).

30 【0059】

The test results for a Sn-7In-1Ag-0.5Cu solder alloy are shown in the following Table 2 along with the results of the Sn-0.7Cu comparative solder alloy.

Table 2 shows the percent increase in resistance at different lengths of time after the start of the EM test. Each value in Table 2 is the average for 5 rows of solder joints.

5 **【0060】 【Table 2】**

% Increase in Resistance

Alloy Composition	Length of time of test [hr]					
	0	10	500	900	1500	2500
Sn-0.7Cu	0 [%]	0.5 [%]	8 [%]	17 [%]	62 [%]	Conduction failure
Sn-7In-1Ag-0.5Cu	0 [%]	1.5 [%]	23 [%]	26 [%]	27 [%]	28 [%]

【0061】

Figure 5 is a graph showing the relationship between the length of time of the test and the resistance of solder joints made of a Sn-0.7Cu solder alloy as a comparative example. Figure 6 is a graph showing the relationship between the length of time of the test and the resistance of solder joints made from a Sn-7In-1Ag-0.5Cu solder alloy according to the present invention. Figures 5 and 6 each show the results of the electromigration for 5 rows of solder joints of each solder composition. The data shown in Table 2 was determined from the data in these graphs as an average of the measured values for the 5 rows of solder joints.

【0062】

As shown in Figure 5, when a certain length of time passed for the comparative Sn-0.7Cu solder alloy, a typical electromigration resistance shift in the form of an abrupt increase in resistance was observed. Specifically, also as shown in Table 2, the increase in resistance was very gentle until approximately 900 hours after the start of the test. This length of time of 900 hours is thought to be the time until nucleation of voids starts and the voids grow to such an extent that causes any abrupt quality degradation. When 900 hours are exceeded, the resistance abruptly increased with the percent increase at 1500 hours being around 62%, and conduction fracture occurred in two rows of the solder joints before 2500 hours. In addition, all the resistance of the 5 solder joints showed a significant

fluctuation after 900 hours and particularly, after 1200 hours, indicating that the resistance became significantly unstable. The dispersion of the results in the 5 solder joints was also large.

【0063】

5 In contrast, as shown in Figure 6 and Table 2, the resistance of solder joints made of a Sn-7In-1Ag-0.5Cu solder alloy increased by approximately 2% in the extremely early stage of an EM test (in around 10 hours). The resistance at 500 hours then increased by 23% compared to the start of the test. The resistance thereafter was nearly constant, and it remained stable as evidenced by the fact that
10 the percent increase in resistance compared to the start of the test was only 28% even at 2500 hours. In addition, the dispersion in resistance in the 5 rows of solder joints and the fluctuation of the resistance in solder joint of each row were much smaller compared to Figure 5. As shown in Figures 7A and 7B, a case where the other solder alloys according to the present invention which contains 4% or 13% of
15 In exhibited the same tendency as shown in Figure 6. Namely, after the initial stage increase in resistance, the resistance remained stable even at 2500 hours. As the In content was higher, the initial stage increase in resistance became greater.

【0064】

The mechanism of electromigration was investigated in a cross section of a
20 solder joint after the EM test using a scanning electron microscope (SEM) and an electron probe microanalyzer (EPMA).

【0065】

Figures 8 and 9 are SEM photographs of cross sections of a solder joint made of a comparative Sn-0.7Cu solder alloy and a solder joint made of a Sn-7In-
25 1Ag-0.5Cu solder alloy according to the present invention, respectively, after the EM test has been carried out for 2500 hours. As shown in these figures, a solder joint 53 or 63 was formed from a solder ball so as to connect a Cu pad 56 or 66 having a Ni/Au plating formed on a die substrate and a Cu pad 51 or 61 formed on a die. In the EM test, a current was passed through the solder joints 53 or 63 so as
30 to cause electrons to flow in the direction from the Cu pad 56 or 66 on the die substrate toward the Cu pad 51 or 61 on the die. Therefore, the Cu pad 56 and 66 on the die substrate functioned as a cathode while the Cu pad 51 or 61 on the die

functioned as an anode.

【0066】

As shown in Figures 8 and 9, a Cu-Sn intermetallic compound 52 or 62 was formed on each of the Cu pads 51 and 61 which was an anode. A Ni plating layer 55 or 65 was observed on each of the Cu pads 56 and 66 which was a cathode. The Cu-Sn intermetallic compound 52 or 62 and the Ni plating layer 55 or 65 were connected by the solder joints 53 or 63. Voids 54 or 64 were formed in each of the solder joints 53 and 63 between the cathode 56 or 66 and the Ni plating layer 55 or 65.

【0067】

As shown in Figure 8, when using a comparative Sn-0.7Cu solder alloy, voids 54 were formed in the solder joint 53 so as to make a line or a layer in the vicinity of the Ni plating layer 55 on the cathode 56. The formation of voids in such a state in a solder joint may cause the solder joint to be readily broken when undergoing a stress. In contrast, as shown in Figure 9, in the case of using a Sn-7In-1Ag-0.5Cu solder alloy according to the present invention, voids 64 formed in the solder joint 63 in the vicinity of the Ni plating layer 65 on the cathode 66 did not form a layer but formed separated masses of voids. Therefore, there was little concern of failure of conduction through the solder joint even after 2500 hours of an EM test.

【0068】

In order to identify the atomic flow during the EM test, EPMA data was collected after completion of the EM test for 2500 hours. From this result, it was found that a solder joint made of a Sn-0.7Cu solder alloy behaved in a typical electromigration mechanism. Namely, when high density electron flows bombarded Sn atoms, Sn atoms were caused to migrate toward the anode side while voids were moved against the flow of electrons and accumulated in the cathode side.

【0069】

In an In-containing Sn-Ag-Cu alloy according to the present invention, Sn atoms migrate along with electrons while In atoms migrate against the flow of electrons, thereby forming an Sn-rich layer in the anode side and an In-rich layer in

the cathode side. The formation of these layers is thought to take place by the previously discussed mechanism.

【0070】

5 2. Mechanical Properties

The solder alloys having compositions shown in Table 3 [Sn-xIn-1Ag-0.5Cu (x=0 - 15)] and Table 4 [Sn-xIn-(0 or 1)Ag-0.7Cu (x=0 - 15)] were cast into molds to prepare test pieces having the shape shown in Figures 10A and 10B. For example, the parallel portion PI of each test piece had a diameter of 8 mm and a length of 30 mm. The respective fixing portions Fx of opposed outsides of the parallel portion PI had a diameter of 10 mm and a length of 15 mm. Further, a portion between the parallel portion PI and each of the fixing portions Fx was tapered from the parallel portion PI toward the fixing portion Fx, and a whole length of this test piece was 68 mm. The test piece was prepared by casting each solder alloy at a temperature 100° C above the liquidus temperature of the composition into a split mold which was processed to the shape shown in Figures 10A and 10B followed by air cooling to room temperature and removal of the resulting cast piece from the split mold.

【0071】

Using a tensile tester, tension was applied to the test piece in the air at either room temperature (RT) or 125° C at a speed of 6 mm per minute, and the tensile strength and the elongation at break were calculated from the load and displacement read from a load cell. The results are shown in Tables 3 and 4.

【0072】 【Table 3】

In (mass%)	Solidus Temperature , SL (°C)	Liquidus Temperature , LL (°C)	Tensile Strength (MPa)		Elongation at Break (%)	
			RT	125°C	RT	125°C
0	216.9	225.7	35.7	17.6	74.9	59.6
1	213.1	224.0	33.5	17.2	70.2	63.8
2	209.1	221.6	36.1	18.2	69.6	65.9
3	208.4	219.2	39.8	19.0	63.7	63.7
4	205.8	217.5	51.3	25.5	37.4	44.6
5	203.0	215.8	55.2	26.4	45.3	46.5
6	199.0	213.8	55.8	26.7	50.2	48.4
7	196.5	212.5	57.2	26.5	45.7	53.5
9	191.2	209.8	56.8	25.1	40.8	46.3
10	187.5	207.8	57.0	24.4	41.1	47.3
13	180.0	202.7	52.9	20.5	36.4	41.4
15	177.2	200.9	45.7	16.4	38.9	7.3

Alloy composition (mass%): Sn-xIn-1Ag-0.5Cu (x = 0 - 15)

【0073】 【Table 4】

Ag (mass%)	In (mass%)	Solidus Temperature, SL (°C)	Liquidus Temperature , LL (°C)	Tensile Strength (MPa)		Elongation at Break (%)	
				RT	125° C	RT	125° C
0	0	227.3	229.2	32.0		75.6	
1	0	216.7	224.0	34.4	16.2	73.3	66.8
1	1	213.1	222.7	35.3	17.1	82.9	64.7
1	2	209.7	221.0	42.2	18.0	79.4	69.6
1	3	208.3	218.8	42.7	20.0	71.8	59.5
1	4	205.6	215.5	47.7	23.0	56.3	56.5
1	5	203.1	214.3	55.3	27.2	53.4	47.1
1	6	199.1	212.9	56.8	26.6	48.2	50.3
1	7	196.6	211.9	57.7	26.5	42.4	53.5
1	9	191.2	208.5	58.2	26.6	37.4	56.1
1	10	186.0	207.0	58.0	23.9	38.0	52.4
1	13	176.5	202.1	53.1	20.7	38.2	48.0
1	15	177.9	199.0	46.7	16.5	40.7	16.8

Alloy composition (mass%): Sn-xIn-(0 or 1)Ag-0.7Cu (x = 0 - 15)

【0074】

It is understood from Tables 3 and 4 that alloy compositions having a Cu content of either 0.5% or 0.7% exhibited the same tendency in all the alloy compositions. In particular, a solder alloy having an In content of at least 4% for the case of a Cu content of 0.5% or at least 5% for the case of a Cu content of 0.7% exhibited a high tensile strength both at room temperature and at a high temperature. At 125° C, elongation at break abruptly deteriorated if the In content exceeded 13%.

【0075】

Figure 11 is a graph showing the relationship between the tensile strength and the In content of Sn-(0 - 15)In-1Ag-0.5Cu solder alloys at room temperature and 125° C. Figure 12 is a graph showing the relationship between elongation at break and the In content of Sn-(0 - 15)In-1Ag-0.5Cu solder alloys at room temperature and 125° C. The measurement temperature at a high temperature was made 125° C because the operating temperature of semiconductor elements in recent years has reached around 100° C, so it was necessary to perform measurement in a more severe environment.

【0076】

As shown in Figure 11, the tensile strength abruptly increased when the In content exceeded 4%, and at an In content of 5 - 10%, the tensile strength exhibited a high value even at a high temperature of 125° C. On the other hand, the tensile strength deteriorated when the In content exceeded 13%. As shown in Figure 12, elongation at break gradually worsened as the In content increased, and at 125° C, it abruptly deteriorated if the In content exceeded 13%. The same tendency as illustrated in Figures 11 and 12 for tensile strength and elongation at break was exhibited with Sn-(0 - 15)In-1Ag-0.7Cu solder alloys as shown in Table 4.

【0077】

As set forth above, because a solder alloy according to the present invention contains 1.0 - 13.0 % of In in a Sn-Ag-Cu solder alloy, the occurrence of electromigration which tends to develop with such a lead free solder alloy and which eventually causes fracture of a solder joint can be suppressed. In addition,

when the In content is 5 - 10 %, not only can the occurrence of electromigration be suppressed more effectively, but the solder alloy can exhibit excellent mechanical properties at high temperatures.

【0078】

5 Accordingly, a solder alloy according to the present invention can be used not only in CPUs but also in equipment which involves high voltages and high currents such as power conversion equipment for solar power generation or high-current inverters for industrial motors. For the solder alloy having an In content of 5 - 10%, due to its excellent mechanical properties, it can also be used for power
10 semiconductors mounted on motor control inverters for electric vehicles (EV) and plug-in hybrid vehicles (PHV).

1. A lead-free solder alloy having an alloy composition consisting essentially of, in mass percent, In: 1.0 or more and less than 3.0 %, Ag: 0.1 or
5 more and less than 1.5 %, Cu: 0.3 through 1.0 %, and a remainder of Sn,
wherein when the lead-free solder alloy is used as a solder joint under an energizing condition at a current density of $0.12 \text{ mA}/\mu\text{m}^2$ in the air at 165°C , a percent increase in a resistance value of the solder joint from a resistance value before the energization to a resistance value when 2500 hours have elapsed from
10 the start of the energization is not more than 30 % and a difference between the percent increase in the resistance value when 2500 hours have elapsed from the start of the energization and a percent increase in a resistance value when 500 hours have elapsed from the start of the energization is not more than 5%.
- 15 2. The lead-free solder alloy as set forth in claim 1 wherein the alloy composition contains, in mass percent, In: 1.0 -2.0%.
3. A solder joint made from the lead-free solder alloy as set forth in any one of claims 1 and 2.

4. A method for suppressing electromigration of a solder joint during electrical conduction comprising forming a solder joint using a lead-free solder alloy as set forth in any one of claims 1 and 2.

5

5. A lead-free solder alloy having an alloy composition consisting essentially of, in mass percent, In: more than 7.0 and 13.0 or less %, Ag: 0.1 or more and less than 1.5 %, Cu: 0.3 through 1.0 %, and a remainder of Sn,

wherein when the lead-free solder alloy is used as a solder joint under an energizing condition at a current density of $0.12 \text{ mA}/\mu\text{m}^2$ in the air at 165°C , a percent increase in a resistance value of the solder joint from a resistance value before the energization to a resistance value when 2500 hours have elapsed from the start of the energization is not more than 30 % and a difference between the percent increase in the resistance value when 2500 hours have elapsed from the start of the energization and a percent increase in a resistance value when 500 hours have elapsed from the start of the energization is not more than 5%.

20

6. The lead-free solder alloy as set forth in claim 5 wherein the alloy composition contains, in mass percent, In: 7.0 -10.0%.

7. A solder joint made from the lead-free solder alloy as set forth in any one of claims 5 and 6.

8. A method for suppressing electromigration of a solder joint during electrical conduction comprising forming a solder joint using a lead-free solder alloy as set forth in any one of claims 5 - 6.

25