

form the porous scaffold. However, this method of preparation of a porous hydrogel involves the use of an organic solvent with a synthetic polymer which renders the method according to this invention weakly compatible with biological and therapeutic purposes.

Therefore there is still an existing need in the art to develop a method for preparing porous scaffold matrices that can be used for biological and therapeutic purposes.

SUMMARY-OF-THE-INVENTION

Therefore, it is an object of the present ~~invention~~disclosure to provide a method for preparing a porous scaffold which comprises the steps consisting of:

- a) preparing an alkaline aqueous solution comprising an amount of at least one polysaccharide, an amount of a cross-linking agent and an amount of a porogen agent.
- b) transforming the solution into a hydrogel by placing said solution at a temperature from about 4°C to about 80°C for a sufficient time to allow the cross-linking of said amount of polysaccharide and
- c) submerging said hydrogel into an aqueous solution
- d) washing the porous scaffold obtained at step c).

It is another object of the present ~~invention~~disclosure to provide a porous scaffold obtainable by the method as above described.

It is still further an object of the present ~~invention~~disclosure to provide the use of the disclosed porous scaffold ~~of the invention~~ for tissue engineering, cell culture and cell delivery.

In one aspect of the present invention, there is provided a method for preparing a porous scaffold which comprises the steps consisting of :

- a) preparing an alkaline aqueous solution comprising an amount of at least one polysaccharide, an amount of a covalent cross- linking agent and an amount of a porogen agent

b) transforming the solution into a hydrogel by placing said solution at a temperature from 4°C to 80°C for a sufficient time to allow the cross-linking of said amount of polysaccharide

c) submerging said hydrogel into an aqueous solution

d) washing the porous scaffold obtained at step c).

In another aspect, there is provided a porous scaffold obtainable by the method wherein said covalent cross-linking agent is trisodium trimetaphosphate.

In another aspect, there is provided a vascular substitute made with a scaffold as defined above.

In another aspect, there is provided cartilage or bone implants made with a scaffold as defined above.

In another aspect, there is provided the use of a scaffold as defined above for the evaluation of the toxicity and/or pharmacology of a product.

In another aspect, there is provided a controlled release system of an active agent made with a scaffold as defined above.