

IN-SITU OZONE CURE FOR RADICAL-COMPONENT CVD

CROSS-REFERENCES TO RELATED APPLICATIONS

This application is a PCT application of U.S. Patent Application No. 12/972,711 filed
5 December 20, 2010, entitled "IN-SITU OZONE CURE FOR RADICAL-COMPONENT
CVD," and claims the benefit of U.S. Provisional Patent Application No. 61/293,082, filed
January 7, 2010, entitled "IN-SITU OZONE CURE FOR RADICAL-COMPONENT CVD,"
the entire disclosure of which is incorporated herein by reference for all purposes.

BACKGROUND OF THE INVENTION

10 Semiconductor device geometries have dramatically decreased in size since their introduction
several decades ago. Modern semiconductor fabrication equipment routinely produces
devices with 45 nm, 32 nm, and 28 nm feature sizes, and new equipment is being developed
and implemented to make devices with even smaller geometries. The decreasing feature
sizes result in structural features on the device having decreased spatial dimensions. The
15 widths of gaps and trenches on the device narrow to a point where the aspect ratio of gap
depth to its width becomes high enough to make it challenging to fill the gap with dielectric
material. The depositing dielectric material is prone to clog at the top before the gap
completely fills, producing a void or seam in the middle of the gap.

Over the years, many techniques have been developed to avoid having dielectric material
20 clog the top of a gap, or to "heal" the void or seam that has been formed. One approach has
been to start with highly flowable precursor materials that may be applied in a liquid phase to
a spinning substrate surface (e.g., SOG deposition techniques). These flowable precursors
can flow into and fill very small substrate gaps without forming voids or weak seams.
However, once these highly flowable materials are deposited, they have to be hardened into a
25 solid dielectric material.

In many instances, the hardening process includes a heat treatment to remove carbon and
hydroxyl groups from the deposited material to leave behind a solid dielectric such as silicon
oxide. Unfortunately, the departing carbon and hydroxyl species often leave behind pores in
the hardened dielectric that reduce the quality of the final material. In addition, the hardening
30 dielectric also tends to shrink in volume, which can leave cracks and spaces at the interface of

the dielectric and the surrounding substrate. In some instances, the volume of the hardened dielectric can decrease by 40% or more.

Thus, there is a need for new deposition processes and materials to form dielectric materials on structured substrates without generating voids, seams, or both, in substrate gaps and
5 trenches. There is also a need for materials and methods of hardening flowable dielectric materials with fewer pores and a lower decrease in volume. This and other needs are addressed in the present application.

BRIEF SUMMARY OF THE INVENTION

Methods of forming a dielectric layer are described. The methods include the steps of mixing
10 a silicon-containing precursor with a plasma effluent, and depositing a silicon-and-nitrogen-containing layer on a substrate. The silicon-and-nitrogen-containing layer is converted to a silicon-and-oxygen-containing layer by curing in an ozone-containing atmosphere in the same substrate processing region used for depositing the silicon-and-nitrogen-containing layer. Another silicon-and-nitrogen-containing layer may be deposited on the silicon-and-
15 oxygen-containing layer and the stack of layers may again be cured in ozone all without removing the substrate from the substrate processing region. After an integral multiple of dep-cure cycles, the conversion of the stack of silicon-and-oxygen-containing layers may be annealed at a higher temperature in an oxygen-containing environment.

Embodiments of the invention include methods of forming a silicon-and-oxygen-containing
20 layer on a substrate in a substrate processing region in a substrate processing chamber. The methods include forming a silicon-and-nitrogen-containing layer on the substrate in the substrate processing region. Forming the silicon-and-nitrogen-containing layer involves flowing a nitrogen-and-hydrogen-containing gas into a plasma region to produce a radical-nitrogen precursor, combining a carbon-free silicon-containing precursor with the radical-nitrogen precursor in the plasma-free substrate processing region, and depositing a silicon-
25 and-nitrogen-containing layer on the substrate. The methods further include curing the silicon-and-nitrogen-containing layer in an ozone-containing atmosphere in the substrate processing region..

Additional embodiments and features are set forth in part in the description that follows, and
30 in part will become apparent to those skilled in the art upon examination of the specification or may be learned by the practice of the invention. The features and advantages of the invention may be realized and attained by means of the instrumentalities, combinations, and methods described in the specification.

BRIEF DESCRIPTION OF THE DRAWINGS

A further understanding of the nature and advantages of the present invention may be realized by reference to the remaining portions of the specification and the drawings wherein like reference numerals are used throughout the several drawings to refer to similar components.

5 In some instances, a sublabel is associated with a reference numeral and follows a hyphen to denote one of multiple similar components. When reference is made to a reference numeral without specification to an existing sublabel, it is intended to refer to all such multiple similar components.

10 Fig. 1 is a flowchart illustrating selected steps for making a silicon oxide film according to embodiments of the invention.

Fig. 2 is another flowchart illustrating selected steps for forming a silicon oxide film in a substrate gap according to embodiments of the invention.

Fig. 3 is a graph of FTIR spectra acquired from silicon-containing films according to embodiments of the invention.

15 Fig. 4 shows a substrate processing system according to embodiments of the invention.

Fig. 5A shows a substrate processing chamber according to embodiments of the invention.

Fig. 5B shows a showerhead of a substrate processing chamber according to embodiments of the invention.

DETAILED DESCRIPTION OF THE INVENTION

20 Methods of forming a dielectric layer are described. The methods include the steps of mixing a silicon-containing precursor with a plasma effluent, and depositing a silicon-and-nitrogen-containing layer on a substrate. The silicon-and-nitrogen-containing layer is converted to a silicon-and-oxygen-containing layer by curing an ozone-containing atmosphere in the same substrate processing region used for depositing the silicon-and-nitrogen-containing layer.

25 Another silicon-and-nitrogen-containing layer may be deposited on the silicon-and-oxygen-containing layer and the stack of layers may again be cured in ozone all without removing the substrate from the substrate processing region. After an integral multiple of dep-cure cycles, the conversion of the stack of silicon-and-oxygen-containing layers may be annealed at a higher temperature in an oxygen-containing environment.

30 Without binding the coverage of the claims to hypothetical mechanisms which may or may not be entirely correct, a discussion of some details may prove beneficial. Exposing an as-

deposited silicon-and-nitrogen-containing film to ozone while maintaining a relatively low substrate temperature increases the oxygen content over only annealing the substrate at a relatively high substrate temperature in an oxygen-containing environment. This may result from the relatively open network produced by the deposition of the silicon-and-nitrogen film by mixing a radical-nitrogen precursor with an carbon-free silicon-and-nitrogen-containing precursor. The open network may allow the ozone to penetrate more deeply within the film, extending the oxide conversion in the direction of the substrate. Performing the conversion at high temperature may close the network near the surface thereby limiting the physical extent of the conversion.

The reactivity of ozone lies between that of molecular oxygen and atomic oxygen. Molecular oxygen requires a higher temperature to activate the oxidation which results in a closure of the open silicon-and-nitrogen network near the surface. This closure undesirably limits the oxidation in deeper portions of the silicon-and-nitrogen-containing layer. Atomic oxygen would react too readily at low temperatures and close the network as well. Ozone is found to offer the stability to penetrate deep into the open network while not requiring a high temperature to promote the oxidation. Additional details about the methods and systems of forming the silicon oxide layer will now be described.

In light of the theorized ability of ozone to supplant hydrogen and nitrogen, it appeared possible to conduct the ozone cure with little or no heating enabling the ozone cure to occur within the deposition region. Additional details about the methods and system of forming silicon oxide using an integrated ozone-cure will now be described.

Exemplary Silicon Oxide Formation Process

Fig. 1 is a flowchart showing selected steps in methods 100 of making silicon oxide films according to embodiments of the invention. The method 100 includes providing a carbon-free silicon precursor to a substrate processing region 102. The carbon-free silicon precursor may be, for example, a silicon-and-nitrogen precursor, a silicon-and-hydrogen precursor, or a silicon-nitrogen-and-hydrogen-containing precursor, among other classes of silicon precursors. The silicon-precursor may be oxygen-free in addition to carbon-free. The lack of oxygen results in a lower concentration of silanol (Si-OH) groups in the silicon-and-nitrogen layer formed from the precursors. Excess silanol moieties in the deposited film can cause increased porosity and shrinkage during post deposition steps that remove the hydroxyl (-OH) moieties from the deposited layer.

Specific examples of carbon-free silicon precursors may include silyl-amines such as $\text{H}_2\text{N}(\text{SiH}_3)$, $\text{HN}(\text{SiH}_3)_2$, and $\text{N}(\text{SiH}_3)_3$, among other silyl-amines. The flow rates of a silyl-amine may be greater than or about 200 sccm, greater than or about 300 sccm or greater than or about 500 sccm in different embodiments. All flow rates given herein refer to a dual
5 chamber substrate processing system. Single wafer systems would require half these flow rates and other wafer sizes would require flow rates scaled by the processed area. These silyl-amines may be mixed with additional gases that may act as carrier gases, reactive gases, or both. Examples of the additional gases may include H_2 , N_2 , NH_3 , He, and Ar, among other gases. Examples of carbon-free silicon precursors may also include silane (SiH_4) either alone
10 or mixed with other silicon (e.g., $\text{N}(\text{SiH}_3)_3$), hydrogen (e.g., H_2), and/or nitrogen (e.g., N_2 , NH_3) containing gases. Carbon-free silicon precursors may also include disilane, trisilane, even higher-order silanes, and chlorinated silanes, alone or in combination with one another or the previously mentioned carbon-free silicon precursors. Generally speaking silicon precursors which include carbon may also be used with the caveat that the films may shrink
15 more than when carbon-free silicon precursors are used.

A radical-nitrogen precursor may also be provided to the substrate processing region 104. The radical-nitrogen precursor is a nitrogen-radical-containing precursor that was generated outside the substrate processing region from a more stable nitrogen precursor. For example, a
20 stable nitrogen precursor compound containing NH_3 , H_2 and/or N_2 may be activated in a chamber plasma region or a remote plasma system (RPS) outside the processing chamber to form the radical-nitrogen precursor, which is then transported into the substrate processing region. The flow rate of the stable nitrogen precursor may be greater than or about 300 sccm, greater than or about 500 sccm or greater than or about 700 sccm in different embodiments. The radical-nitrogen precursor produced in the chamber plasma region may be one or more of
25 $\cdot\text{N}$, $\cdot\text{NH}$, $\cdot\text{NH}_2$, etc., and may also be accompanied by ionized species formed in the plasma.

Generally speaking, other radical precursors may be used to create silicon-and-nitrogen-containing layers. The radical precursors may or may not include nitrogen. If no nitrogen is present in the radical precursor, nitrogen will be supplied by the silicon-containing precursor. Nitrogen may be present in both, in embodiments of the invention. As a result of this
30 flexibility, a radical precursor may be more generally referred to as plasma effluents. Similarly, the stable nitrogen precursor flowed into the plasma region to create the plasma effluents may be generally referred to herein as a stable gas (since nitrogen may or may not be present).

In embodiments employing a chamber plasma region, the radical-nitrogen precursor is generated in a section of the substrate processing region partitioned from a deposition region where the precursors mix and react to deposit the silicon-and-nitrogen layer on a deposition substrate (e.g., a semiconductor wafer). The radical-nitrogen precursor may also be

5 accompanied by a carrier gas such as hydrogen (H_2), nitrogen (N_2), helium, etc. The substrate processing region may be described herein as "plasma-free" during the growth of the silicon-and-nitrogen-containing layer and during the low temperature ozone cure. "Plasma-free" does not necessarily mean the region is devoid of plasma. The borders of the plasma in the chamber plasma region are hard to define and may encroach upon the substrate

10 processing region through the apertures in the showerhead. In the case of inductively-coupled plasma, a small amount of ionization may be effected within the substrate processing region directly. Furthermore, a low intensity plasma may be created in the substrate processing region without eliminating the flowable nature of the forming film. All causes for a plasma having much lower intensity ion density than the chamber plasma region during the

15 creation of the radical nitrogen precursor do not deviate from the scope of "plasma-free" as used herein.

In the substrate processing region, the carbon-free silicon precursor and the radical-nitrogen precursor mix and react to deposit a silicon-and-nitrogen-containing film on the deposition substrate 106. The deposited silicon-and-nitrogen-containing film may deposit conformally

20 with some recipe combinations in embodiments. In other embodiments, the deposited silicon-and-nitrogen-containing film has flowable characteristics unlike conventional silicon nitride (Si_3N_4) film deposition techniques. The flowable nature of the formation allows the film to flow into narrow gaps trenches and other structures on the deposition surface of the substrate. Generally speaking, higher radical-nitrogen fluxes result in conformal deposition

25 while lower fluxes result in a flowable deposition.

The flowability may be due to a variety of properties which result from mixing a radical-nitrogen precursors with carbon-free silicon precursor. These properties may include a significant hydrogen component in the deposited film and/or the presence of short chained polysilazane polymers. These short chains grow and network to form more dense dielectric

30 material during and after the formation of the film. For example the deposited film may have a silazane-type, Si-NH-Si backbone (i.e., a Si-N-H film). When both the silicon precursor and the radical-nitrogen precursor are carbon-free, the deposited silicon-and-nitrogen-containing film is also substantially carbon-free. Of course, "carbon-free" does not necessarily mean the film lacks even trace amounts of carbon. Carbon contaminants may be

present in the precursor materials that find their way into the deposited silicon-and-nitrogen precursor. The amount of these carbon impurities however are much less than would be found in a silicon precursor having a carbon moiety (e.g., TEOS, TMDSO, etc.).

Following the deposition of the silicon-and-nitrogen-containing layer, the deposition

5 substrate may be cured in an ozone-containing atmosphere 108. The post-deposition substrate remains in the same substrate processing region for curing. The curing temperature of the substrate may be about the same as the temperature of the substrate during formation of the silicon-and-nitrogen-containing film in order to maintain throughput. Alternatively, the temperature may be elevated during the curing operation by raising the substrate closer to a
10 heated faceplate or showerhead. The temperature of the substrate during the curing operation may be less than 120°C, less than 100°C, less than 90°C, less than 80°C or less than 70°C in different embodiments. The temperature of the substrate may be greater than the substrate temperature during deposition, greater than 50°C, greater than 60°C, greater than 70°C or greater than 80°C in different embodiments. Any of the upper bounds may be combined with
15 any of the lower bounds to form additional ranges for the substrate temperature according to additional disclosed embodiments.

The substrate processing region may be plasma-free during the curing operation in order to avoid creating a relatively high concentration of atomic oxygen. A presence of atomic oxygen may prematurely close the relatively open network of the silicon-and-nitrogen-
20 containing layer. No plasma is present in the substrate processing region, in embodiments, to avoid generating atomic oxygen which may close the near surface network and thwart subsurface oxidation. The flow rate of the ozone into the substrate processing region during the cure step may be greater than or about 200 sccm, greater than or about 300 sccm or greater than or about 500 sccm. The partial pressure of ozone during the cure step may be
25 greater than or about 10 Torr, greater than or about 20 Torr or greater than or about 40 Torr. Under some conditions (e.g. between substrate temperatures from about 100°C to about 200°C) the conversion has been found to be substantially complete so a relatively high temperature anneal in an oxygen-containing environment may be unnecessary in embodiments.

30 Performing the curing operation in the same substrate processing region makes multiple dep-cure cycles possible, reducing the thickness required during each cycle. In this embodiment, the curing operation only needs to convert a reduced thickness of silicon-and-nitrogen-containing layer. This relaxes the requirements on the ozone-containing environment, allows greater concentration of atomic oxygen and widens the substrate temperature process

window. A plasma is present during the curing portion of the dep-cure cycle in some embodiments. In other embodiments, no plasma is present in the substrate processing region and the ozone-containing environment contains only a small concentration of atomic oxygen. The thickness of the layer of silicon-and-nitrogen-containing layer before curing may be
5 below 1500Å, below 1000Å, below 750Å or below 500Å in different embodiments. The thickness of the stack of all silicon-and-oxygen-containing layers combined resulting from multiple dep-cure cycles may be between 400Å and 10,000Å, in embodiments, depending primarily on the application.

A decision is made 109 as to whether the target total thickness has been reached. If the target
10 has not been reached, another deposition operation (102-106) and another curing operation (108) are completed in sequence before the thickness of the silicon-and-oxygen-containing film is again compared to the target thickness. Once the target is reached, the substrate may remain or be removed from the substrate processing chamber and transferred to an annealing chamber for further conversion to silicon oxide.

Following an integral number of dep-cure cycles, the deposition substrate may be annealed in
15 an oxygen-containing atmosphere 110. The deposition substrate may remain in the same substrate processing region used for curing when the oxygen-containing atmosphere is introduced, or the substrate may be transferred to a different chamber where the oxygen-containing atmosphere is introduced. The oxygen-containing atmosphere may include one or
20 more oxygen-containing gases such as molecular oxygen (O₂), ozone (O₃), water vapor (H₂O), hydrogen peroxide (H₂O₂) and nitrogen-oxides (NO, NO₂, etc.), among other oxygen-containing gases. The oxygen-containing atmosphere may also include radical oxygen and hydroxyl species such as atomic oxygen (O), hydroxides (OH), etc., that may be generated remotely and transported into the substrate chamber. Ions of oxygen-containing species may
25 also be present. The oxygen anneal temperature of the substrate may be less than or about 1100°C, less than or about 1000°C, less than or about 900°C or less than or about 800°C in different embodiments. The temperature of the substrate may be greater than or about 500°C, greater than or about 600°C, greater than or about 700°C or greater than or about 800°C in different embodiments. Once again, any of the upper bounds may be combined with any of
30 the lower bounds to form additional ranges for the substrate temperature according to additional disclosed embodiments.

A plasma may or may not be present in the substrate processing region during the oxygen anneal. The oxygen-containing gas entering the CVD chamber may include one or more compounds that have been activated (e.g., radicalized, ionized, etc.) before entering the

substrate processing region. For example, the oxygen-containing gas may include radical oxygen species, radical hydroxyl species, etc., activated by exposing more stable precursor compounds through a remote plasma source or through a chamber plasma region separated from the substrate processing region by a showerhead. The more stable precursors may
5 include water vapor and hydrogen peroxide (H_2O_2) that produce hydroxyl (OH) radicals and ions, and molecular oxygen and/or ozone that produce atomic oxygen (O) radicals and ions.

The oxygen-containing atmospheres of both the curing and oxygen anneal provide oxygen to convert the silicon-and-nitrogen-containing film into the silicon oxide (SiO_2) film. As noted previously, the lack of carbon in the silicon-and-nitrogen-containing film results in
10 significantly fewer pores formed in the final silicon oxide film. It also results in less volume reduction (i.e., shrinkage) of the film during the conversion to the silicon oxide. For example, where a silicon-nitrogen-carbon layer formed from carbon-containing silicon precursors may shrink by 40 vol.% or more when converted to silicon oxide, the substantially carbon-free silicon-and-nitrogen films may shrink by about 15 vol.% or less.

15 Referring now to Fig. 2, another flowchart is shown illustrating selected steps in methods 200 for forming a silicon oxide film in a substrate gap according to embodiments of the invention. The method 200 may include transferring a substrate comprising a gap into a substrate processing region (operation 202). The substrate may have a plurality of gaps for the spacing and structure of device components (e.g., transistors) formed on the substrate. The gaps may
20 have a height and width that define an aspect ratio (AR) of the height to the width (i.e., H/W) that is significantly greater than 1:1 (e.g., 5:1 or more, 6:1 or more, 7:1 or more, 8:1 or more, 9:1 or more, 10:1 or more, 11:1 or more, 12:1 or more, etc.). In many instances the high AR is due to small gap widths of that range from about 90 nm to about 22 nm or less (e.g., about 90 nm or less, 65 nm or less, 45 nm or less, 32 nm or less, 28 nm or less, 22 nm or less, 16
25 nm or less, etc.).

A carbon-free silicon precursor is mixed with a radical nitrogen precursor in the substrate processing region (operation 204). A flowable silicon-and-nitrogen-containing layer may be deposited on the substrate (operation 206). Because the layer is flowable, it can fill gaps with high aspect ratios without creating voids or weak seams around the center of the filling
30 material. For example, a depositing flowable material is less likely to prematurely clog the top of a gap before it is completely filled to leave a void in the middle of the gap.

The as-deposited silicon-and-nitrogen-containing layer may then be cured (operation 208) in the same substrate processing region used for the deposition conducted in operations 204-

206. In the pictured embodiment, multiple dep-cure cycles are not shown but may be conducted in analogous fashion to the repetition shown and described with reference to FIG. 1. If conversion is incomplete, the partially converted silicon-and-oxygen-containing layer is annealed in an oxygen-containing atmosphere (operation 210) to transition the silicon-and-nitrogen-containing layer to silicon oxide. A further anneal (not shown) may be carried out in an inert environment at a higher substrate temperature in order to densify the silicon oxide layer.

Curing and annealing the as-deposited silicon-and-nitrogen-containing layer in an oxygen-containing atmosphere forms a silicon oxide layer on the substrate, including the substrate gap 208. In embodiments, the processing parameters of operations 208 and 210 possess the same ranges described with reference to operations 108 and 110 of FIG. 1. As noted above, the silicon oxide layer has fewer pores and less volume reduction than similar layers formed with carbon-containing precursors that have significant quantities of carbon present in the layer before the heat treatment step. In many cases, the volume reduction is slight enough (e.g., about 15 vol.% or less) to avoid post heat treatment steps to fill, heal, or otherwise eliminate spaces that form in the gap as a result of the shrinking silicon oxide.

Fig. 3 is a graph of FTIR spectra acquired from silicon-containing films according to embodiments of the invention. The as-deposited silicon-and-nitrogen-containing film 305 shows a strong peak near 908cm⁻¹-933 cm⁻¹ and a strong peak near 835cm⁻¹-860cm⁻¹ indicative of a presence of hydrogen and nitrogen. FTIR spectra are also shown for silicon-and-nitrogen-containing films cured in ozone outside 310 and inside the substrate processing region 315. In both cases, the peak associated with hydrogen is reduced similarly and other peaks match closely as well. This indicates that the lower temperature curing of the in-situ cure is similarly effective to curing in a dedicated chamber. An FTIR spectrum is also shown 320 for silicon oxide processed in 8 dep-cure cycles which indicates very little hydrogen and nitrogen remain in the film. The FTIR spectrum associated with multiple dep-cure cycles also shows a very strong oxygen peak near 1100cm⁻¹ indicating nice conversion of Si-H-N to silicon oxide.

Exemplary Silicon Oxide Deposition System

Deposition chambers that may implement embodiments of the present invention may include high-density plasma chemical vapor deposition (HDP-CVD) chambers, plasma enhanced chemical vapor deposition (PECVD) chambers, sub-atmospheric chemical vapor deposition (SACVD) chambers, and thermal chemical vapor deposition chambers, among other types of

chambers. Specific examples of CVD systems that may implement embodiments of the invention include the CENTURA ULTIMA® HDP-CVD chambers/systems, and PRODUCER® PECVD chambers/systems, available from Applied Materials, Inc. of Santa Clara, Calif.

- 5 Examples of substrate processing chambers that can be used with exemplary methods of the invention may include those shown and described in co-assigned U.S. Provisional Patent App. No. 60/803,499 to Lubomirsky et al, filed May 30, 2006, and titled "PROCESS CHAMBER FOR DIELECTRIC GAPFILL," the entire contents of which is herein incorporated by reference for all purposes. Additional exemplary systems may include those
10 shown and described in U.S. Pat. Nos. 6,387,207 and 6,830,624, which are also incorporated herein by reference for all purposes.

Embodiments of the deposition systems may be incorporated into larger fabrication systems for producing integrated circuit chips. FIG. 4 shows one such system 400 of deposition, baking and curing chambers according to disclosed embodiments. In the figure, a pair of
15 FOUPs (front opening unified pods) 402 supply substrate substrates (e.g., 300 mm diameter wafers) that are received by robotic arms 404 and placed into a low pressure holding area 406 before being placed into one of the wafer processing chambers 408a-f. A second robotic arm 410 may be used to transport the substrate wafers from the holding area 406 to the processing chambers 408a-f and back.

- 20 The processing chambers 408a-f may include one or more system components for depositing, annealing, curing and/or etching a flowable dielectric film on the substrate wafer. In one configuration, two pairs of the processing chamber (e.g., 408c-d and 408e-f) may be used to deposit the flowable dielectric material on the substrate, and the third pair of processing chambers (e.g., 408a-b) may be used to anneal the deposited dielectric. In another
25 configuration, the same two pairs of processing chambers (e.g., 408c-d and 408e-f) may be configured to both deposit and anneal a flowable dielectric film on the substrate, while the third pair of chambers (e.g., 408a-b) may be used for UV or E-beam curing of the deposited film. In still another configuration, all three pairs of chambers (e.g., 408a-f) may be configured to deposit and cure a flowable dielectric film on the substrate and each may be
30 configured with lift pins for raising the substrate towards a heated showerhead, thus raising the temperature in an "integrated" curing operation. In yet another configuration, two pairs of processing chambers (e.g., 408c-d and 408e-f) may be used for both deposition and UV or E-beam curing of the flowable dielectric, while a third pair of processing chambers (e.g. 408a-b) may be used for annealing the dielectric film. Any one or more of the processes

described may be carried out on chamber(s) separated from the fabrication system shown in different embodiments.

In addition, one or more of the process chambers 408a-f may be configured as a wet treatment chamber. These process chambers include heating the flowable dielectric film in an atmosphere that include moisture. Thus, embodiments of system 400 may include wet treatment chambers 408a-b and anneal processing chambers 408c-d to perform both wet and dry anneals on the deposited dielectric film.

FIG. 5A is a substrate processing chamber 500 according to disclosed embodiments. A remote plasma system (RPS) 510 may process a gas which then travels through a gas inlet assembly 511. Two distinct gas supply channels are visible within the gas inlet assembly 511. A first channel 512 carries a gas that passes through the remote plasma system RPS 510, while a second channel 513 bypasses the RPS 500. The first channel 512 may be used for the process gas and the second channel 513 may be used for a treatment gas in disclosed embodiments. The lid (or conductive top portion) 521 and a perforated partition 553 are shown with an insulating ring 524 in between, which allows an AC potential to be applied to the lid 521 relative to perforated partition 553. The process gas travels through first channel 512 into chamber plasma region 520 and may be excited by a plasma in chamber plasma region 520 alone or in combination with RPS 510. The combination of chamber plasma region 520 and/or RPS 510 may be referred to as a remote plasma system herein. The perforated partition (also referred to as a showerhead) 553 separates chamber plasma region 520 from a substrate processing region 570 beneath showerhead 553. Showerhead 553 allows a plasma present in chamber plasma region 520 to avoid directly exciting gases in substrate processing region 570, while still allowing excited species to travel from chamber plasma region 520 into substrate processing region 570. Showerhead 553 is positioned between chamber plasma region 520 and substrate processing region 570 and allows plasma effluents (excited derivatives of precursors or other gases) created within chamber plasma region 520 to pass through a plurality of through holes 556 that traverse the thickness of the plate. The showerhead 553 also has one or more hollow volumes 551 which can be filled with a precursor in the form of a vapor or gas (such as a silicon-containing precursor) and pass through small holes 555 into substrate processing region 570 but not directly into chamber plasma region 520. Showerhead 553 is thicker than the length of the smallest diameter 550 of the through-holes 556 in this disclosed embodiment. In order to maintain a significant concentration of excited species penetrating from chamber plasma region 520 to substrate processing region 570, the length 526 of the

smallest diameter 550 of the through-holes may be restricted by forming larger diameter portions of through-holes 556 part way through the showerhead 553. The length of the smallest diameter 550 of the through-holes 556 may be the same order of magnitude as the smallest diameter of the through-holes 556 or less in disclosed embodiments.

5 In the embodiment shown, showerhead 553 may distribute (via through holes 556) process gases which contain oxygen, hydrogen and/or nitrogen and/or plasma effluents of such process gases upon excitation by a plasma in chamber plasma region 520. In embodiments, the process gas introduced into the RPS 510 and/or chamber plasma region 520 through first channel 512 may contain one or more of oxygen (O_2), ozone (O_3), N_2O , NO , NO_2 , NH_3 , N_xH_y ,
10 including N_2H_4 , silane, disilane, TSA and DSA. The process gas may also include a carrier gas such as helium, argon, nitrogen (N_2), etc. The second channel 513 may also deliver a process gas and/or a carrier gas, and/or a film-curing gas used to remove an unwanted component from the growing or as-deposited film. Plasma effluents may include ionized or neutral derivatives of the process gas and may also be referred to herein as a radical-oxygen
15 precursor and/or a radical-nitrogen precursor referring to the atomic constituents of the process gas introduced. Showerhead 553 may be heated directly (resistively or using a thermal transfer fluid passed through an embedded channel) or indirectly from a plasma in chamber plasma region 520. Either way, the substrate temperature may be raised during an integrated cure step by raising the substrate closer to heated showerhead 553 and then
20 lowering it once the curing operation is complete.

In embodiments, the number of through-holes 556 may be between about 60 and about 2000. Through-holes 556 may have a variety of shapes but are most easily made round. The smallest diameter 550 of through holes 556 may be between about 0.5mm and about 20mm or between about 1mm and about 6mm in disclosed embodiments. There is also latitude in
25 choosing the cross-sectional shape of through-holes, which may be made conical, cylindrical or a combination of the two shapes. The number of small holes 555 used to introduce a gas into substrate processing region 570 may be between about 100 and about 5000 or between about 500 and about 2000 in different embodiments. The diameter of the small holes 555 may be between about 0.1 mm and about 2 mm.

30 FIG. 5B is a bottom view of a showerhead 553 for use with a processing chamber according to disclosed embodiments. Showerhead 553 corresponds with the showerhead shown in FIG. 5A. Through-holes 556 are depicted with a larger inner-diameter (ID) on the bottom of showerhead 553 and a smaller ID at the top. Small holes 555 are distributed substantially

evenly over the surface of the showerhead, even amongst the through-holes 556 which helps to provide more even mixing.

5 An exemplary film is created on a substrate supported by a pedestal (not shown) within substrate processing region 570 when plasma effluents arriving through through-holes 556 in showerhead 553 combine with a silicon-containing precursor arriving through the small holes 555 originating from hollow volumes 551. Though substrate processing region 570 may be equipped to support a plasma for other processes such as curing, no plasma is present during the growth of the exemplary film.

10 A plasma may be ignited either in chamber plasma region 520 above showerhead 553 or substrate processing region 570 below showerhead 553. A plasma is present in chamber plasma region 520 to produce the radical nitrogen precursor from an inflow of a nitrogen-and-hydrogen-containing gas. An AC voltage typically in the radio frequency (RF) range is applied between the conductive top portion 521 of the processing chamber and showerhead 553 to ignite a plasma in chamber plasma region 520 during deposition. An RF power supply
15 generates a high RF frequency of 13.56 MHz but may also generate other frequencies alone or in combination with the 13.56 MHz frequency.

The top plasma may be left at low or no power when the bottom plasma in the substrate processing region 570 is turned on to either cure a film or clean the interior surfaces bordering substrate processing region 570. A plasma in substrate processing region 570 is
20 ignited by applying an AC voltage between showerhead 553 and the pedestal or bottom of the chamber. A cleaning gas may be introduced into substrate processing region 570 while the plasma is present.

The pedestal may have a heat exchange channel through which a heat exchange fluid flows to control the temperature of the substrate. This configuration allows the substrate temperature
25 to be cooled or heated to maintain relatively low temperatures (from room temperature through about 120°C). The heat exchange fluid may comprise ethylene glycol and water. The wafer support platter of the pedestal (preferably aluminum, ceramic, or a combination thereof) may also be resistively heated in order to achieve relatively high temperatures (from about 120°C through about 1100°C) using an embedded single-loop embedded heater
30 element configured to make two full turns in the form of parallel concentric circles. An outer portion of the heater element may run adjacent to a perimeter of the support platter, while an inner portion runs on the path of a concentric circle having a smaller radius. The wiring to the heater element passes through the stem of the pedestal.

The substrate processing system is controlled by a system controller. In an exemplary embodiment, the system controller includes a hard disk drive, a floppy disk drive and a processor. The processor contains a single-board computer (SBC), analog and digital input/output boards, interface boards and stepper motor controller boards. Various parts of
5 CVD system conform to the Versa Modular European (VME) standard which defines board, card cage, and connector dimensions and types. The VME standard also defines the bus structure as having a 16-bit data bus and a 24-bit address bus.

The system controller controls all of the activities of the CVD machine. The system controller executes system control software, which is a computer program stored in a
10 computer-readable medium. Preferably, the medium is a hard disk drive, but the medium may also be other kinds of memory. The computer program includes sets of instructions that dictate the timing, mixture of gases, chamber pressure, chamber temperature, RF power levels, susceptor position, and other parameters of a particular process. Other computer programs stored on other memory devices including, for example, a floppy disk or other
15 another appropriate drive, may also be used to instruct the system controller.

A process for depositing a film stack on a substrate or a process for cleaning a chamber can be implemented using a computer program product that is executed by the system controller. The computer program code can be written in any conventional computer readable programming language: for example, 68000 assembly language, C, C++, Pascal, Fortran or
20 others. Suitable program code is entered into a single file, or multiple files, using a conventional text editor, and stored or embodied in a computer usable medium, such as a memory system of the computer. If the entered code text is in a high level language, the code is compiled, and the resultant compiler code is then linked with an object code of precompiled Microsoft Windows® library routines. To execute the linked, compiled object
25 code the system user invokes the object code, causing the computer system to load the code in memory. The CPU then reads and executes the code to perform the tasks identified in the program.

The interface between a user and the controller is via a flat-panel touch-sensitive monitor. In the preferred embodiment two monitors are used, one mounted in the clean room wall for the
30 operators and the other behind the wall for the service technicians. The two monitors may simultaneously display the same information, in which case only one accepts input at a time. To select a particular screen or function, the operator touches a designated area of the touch-sensitive monitor. The touched area changes its highlighted color, or a new menu or screen is displayed, confirming communication between the operator and the touch-sensitive monitor.

Other devices, such as a keyboard, mouse, or other pointing or communication device, may be used instead of or in addition to the touch-sensitive monitor to allow the user to communicate with the system controller.

As used herein "substrate" may be a support substrate with or without layers formed thereon.

5 The support substrate may be an insulator or a semiconductor of a variety of doping concentrations and profiles and may, for example, be a semiconductor substrate of the type used in the manufacture of integrated circuits. A layer of "silicon oxide" may include minority concentrations of other elemental constituents such as nitrogen, hydrogen, carbon and the like. In some embodiments of the invention, silicon oxide consists essentially of
10 silicon and oxygen. A gas in an "excited state" describes a gas wherein at least some of the gas molecules are in vibrationally-excited, dissociated and/or ionized states. A gas (or precursor) may be a combination of two or more gases (precursors). The term "trench" is used throughout with no implication that the etched geometry has a large horizontal aspect ratio. Viewed from above the surface, trenches may appear circular, oval, polygonal,
15 rectangular, or a variety of other shapes. The term "via" is used to refer to a low aspect ratio trench which may or may not be filled with metal to form a vertical electrical connection. The term "precursor" is used to refer to any process gas (or vaporized liquid droplet) which takes part in a reaction to either remove or deposit material from a surface.

Having described several embodiments, it will be recognized by those of skill in the art that
20 various modifications, alternative constructions, and equivalents may be used without departing from the spirit of the invention. Additionally, a number of well-known processes and elements have not been described in order to avoid unnecessarily obscuring the present invention. Accordingly, the above description should not be taken as limiting the scope of the invention.

25 Where a range of values is provided, it is understood that each intervening value, to the tenth of the unit of the lower limit unless the context clearly dictates otherwise, between the upper and lower limits of that range is also specifically disclosed. Each smaller range between any stated value or intervening value in a stated range and any other stated or intervening value in that stated range is encompassed. The upper and lower limits of these smaller ranges may
30 independently be included or excluded in the range, and each range where either, neither or both limits are included in the smaller ranges is also encompassed within the invention, subject to any specifically excluded limit in the stated range. Where the stated range includes one or both of the limits, ranges excluding either or both of those included limits are also included.

As used herein and in the appended claims, the singular forms "a", "an", and "the" include plural referents unless the context clearly dictates otherwise. Thus, for example, reference to "a process" includes a plurality of such processes and reference to "the precursor" includes reference to one or more precursor and equivalents thereof known to those skilled in the art,
5 and so forth.

Also, the words "comprise," "comprising," "include," "including," and "includes" when used in this specification and in the following claims are intended to specify the presence of stated features, integers, components, or steps, but they do not preclude the presence or addition of one or more other features, integers, components, steps, acts, or groups.

What is claimed is:

1. A method of forming a silicon-and-oxygen-containing layer on a substrate in a substrate processing region in a substrate processing chamber, the method comprising: forming a silicon-and-nitrogen-containing layer on the substrate in the substrate processing region, wherein forming the silicon-and-nitrogen-containing layer comprises: flowing a stable gas into a plasma region to produce plasma effluents, combining a silicon-containing precursor with the plasma effluents in the plasma-free substrate processing region, wherein the silicon-containing precursor is carbon-free, and depositing a silicon-and-nitrogen-containing layer on the substrate; and curing the silicon-and-nitrogen-containing layer in an ozone-containing atmosphere in the same substrate processing region in the substrate processing chamber to form the silicon-and- oxygen-containing layer, wherein a substrate temperature during the curing operation is less than 50° C. higher than a substrate temperature during the operation of depositing the silicon-and-nitrogen-containing layer.
2. The method of claim 1 further comprising forming a second silicon-and-nitrogen-containing layer on the substrate in the substrate processing region, wherein forming the second silicon-and-nitrogen-containing layer comprises: flowing the stable gas into the plasma region to produce plasma effluents, combining a silicon-containing precursor with the plasma effluents in the substrate processing region, and depositing the second silicon-and-nitrogen-containing layer on the substrate in the substrate processing region; and curing the second silicon-and-nitrogen-containing layer in an ozone-containing atmosphere in the substrate processing region.
3. The method of claim 1 wherein the substrate processing region is plasma-free during the operation of forming the silicon-and-nitrogen-containing layer to avoid direct plasma-excitation of the silicon-containing precursor.
4. The method of claim 1 wherein the substrate processing region is plasma-free during the operation of curing the silicon-and-nitrogen-containing layer.
5. The method of claim 1 wherein a substrate temperature during the operation of depositing the silicon-and-nitrogen-containing layer is less than 100° C.
6. The method of claim 1 wherein a substrate temperature during the curing operation is less than 200° C.
7. The method of claim 1 wherein a thickness of the silicon-and-nitrogen-containing layer is less than or about 1500Å.
8. The method of claim 1 wherein the substrate is raised towards a heated showerhead to heat the substrate during the curing operation.
9. The method of claim 1 wherein the stable gas is a nitrogen-and-hydrogen-containing gas and the plasma effluents comprise a radical-nitrogen precursor.
10. The method of claim 9 wherein the nitrogen-and-hydrogen-containing gas comprises ammonia.
11. The method of claim 1 wherein the silicon-containing precursor comprises a silicon-and-nitrogen-containing precursor.

12. The method of claim 1 wherein the silicon-containing precursor comprises $\text{N}(\text{SiH}_3)_3$.
13. The method of claim 1 wherein the silicon-and-nitrogen-containing layer comprises a carbon-free Si—N—H layer.
14. The method of claim 1 further comprising raising a temperature of the substrate to an oxygen anneal temperature above or about 600°C . in an oxygen-containing atmosphere after the curing operation.
15. The method of claim 14 wherein the oxygen-containing atmosphere comprises one or more gases selected from the group consisting of atomic oxygen, ozone, and steam (H_2O).
16. The method of claim 1 wherein the substrate is patterned and has a trench having a width of about 45 nm or less, and wherein the silicon oxide layer formed in the trench is substantially void-free.
17. The method of claim 1 wherein the plasma region is in a remote plasma system.
18. The method of claim 1 wherein the plasma region is a partitioned portion of the substrate processing chamber separated from the plasma-free substrate processing region by a showerhead.