

Patent #3001.EEM

OXETANE COMPOUNDS CONTAINING STYRENIC FUNCTIONALITY

FIELD OF THE INVENTION

[0001] This invention relates to oxetane compounds containing styrenic functionality.

BACKGROUND OF THE INVENTION


[0002] Oxetanes are highly reactive cyclic ethers that can undergo both cationic and anionic ring opening homopolymerization. Styrenic compounds are capable of free radical polymerization.

SUMMARY OF THE INVENTION


[0003] This invention relates to compounds that contain an oxetane functionality and a styrenic functionality. These compounds can be homopolymerizable in reactions in which the oxetane can undergo cationic or anionic ring opening, or polymerizable with compounds such as electron acceptor compounds. The dual functionality allows for dual cure processing, both thermal cure or radiation cure. This capability makes them attractive for use in many applications, such as, adhesives, coatings, encapsulants, and composites.

DETAILED DESCRIPTION OF THE INVENTION

[0004] In one embodiment, the compounds of this invention can be represented by the formula




in which R^1 is a methyl or ethyl group; R^2 and R^3 are H or a methyl or ethyl group; R^4 is a direct bond or a divalent hydrocarbon; X and Y are independently a direct bond, provided both are not a direct bond, or an ether, ester, amide, or carbamate group; Q is a divalent hydrocarbon (which may contain heteroatoms of N, O, or S); and G is $-OR^1$, $-SR^1$, or $-N(R^2)(R^3)$, in which R^1 , R^2 and R^3 are as described above; provided that X will not be



provided that X will not be ---O--- when R^4 is $\text{---}\overset{\text{---}}{\underset{\text{H}_2}{\text{C}}}\text{---}$, Q and Y are absent, and R^2 and R^3 are H. The configuration of the Q portion will depend on the configuration of the starting styrenic compound.


[0005] The starting styrenic compound may be small molecule, for example, 3-isopropenyl- α,α -dimethyl-benzyl isocyanate (*m*-TMI), 4-vinyl-benzyl chloride, the reaction product of *m*-TMI with a diol, the reaction product of *m*-TMI with the hydroxyl functionality on a carboxylic acid containing a hydroxyl group, and isoeugenol. The starting styrenic compound may also be an oligomeric or polymeric compound, prepared by reacting, for example, *m*-TMI or 4-vinyl-benzyl chloride with one functionality on a difunctional oligomer or polymer.

[0006] Whether the starting styrenic compound is a small molecule or an oligomeric or polymeric material, it will contain a styrenic functionality



represented by the structural formula in which R^2 and R^3 are H or a methyl or ethyl group and G is $-OR^1$, $-SR^1$, or $-N(R^2)(R^3)$, in which R^1 is a methyl or ethyl group and R^2 and R^3 independently are H or a methyl or ethyl group. The starting styrenic compound also will contain a second functionality reactive with the starting oxetane compound. For example, the styrenic starting materials disclosed above contain halogen, hydroxyl, or isocyanato functionality in addition to the styrenic functionality.


[0007] The starting oxetane compound may be a small molecule or an oligomeric or polymeric molecule, prepared, for example, by reacting one of the small molecule oxetane starting compounds disclosed below with one functionality on a difunctional oligomer or polymer. In either case, it will



contain an oxetane functionality represented by the structure and a second functionality reactive with the second functionality on the styrenic starting compound.

[0008] Suitable starting oxetane compounds that are small molecules include, for example,

[0009] (a) alcohols, such as, 3-methyl-3-hydroxymethyloxetane, 3-ethyl-3-hydroxymethyloxetane;




[0010] (b) halides, such as, 3-methyl-3-bromomethyloxetane, 3-ethyl-3-bromomethyloxetane, which can be prepared by the reaction of an alcohol from (a) with CBr_4 as is known in the art;



[0011] (c) alkyl halides, such as, 3-methyl-3-alkylbromomethyloxetane, 3-ethyl-3-alkylbromomethyloxetane, which can be prepared from the reaction of an alkyl dibromide compound with an oxetane alcohol from (a) as is known in the art;



[0012] and (d) tosylates, such as, 3-methyl-3-tosylmethyloxetane, 3-ethyl-3-tosylmethyloxetane, which can be prepared from *p*-toluenesulfonyl chloride:



[0013] When a longer chain and higher molecular weight compound containing styrenic and oxetane is desired, either the starting styrenic compound or the starting oxetane compound, or both, may be extended by reaction with a difunctional oligomeric or polymeric material. The second functionality on this oligomeric or polymeric material must be reactive with the oxetane starting compound if the first reaction was between the styrenic starting compound and the difunctional oligomeric or polymeric material, and with the styrenic starting compound if the first reaction was between the oxetane starting compound and the difunctional oligomeric or polymeric


material. Examples of suitable and commercially available oligomers and polymers include dimer diol and poly(butadiene) with terminal hydroxyl functionality.

[0014] In the case in which both the oxetane and styrenic compounds are extended by reaction with a difunctional oligomer or polymer, Q may also contain a functionality, for example, an ether, ester, carbamate, or urea functionality, resulting from the reaction of the two oligomeric or polymeric starting materials.

[0015] In general, the inventive compounds containing oxetane and styrenic functionality are prepared by reacting together a starting compound containing oxetane functionality and a second functionality and a starting compound containing styrenic functionality and a second functionality reactive with the second functionality on the oxetane compound. Typical reaction schemes include well known addition, substitution, and condensation reactions.

[0016] In a further embodiment, the compounds of this invention include polymeric compounds that contain more than one oxetane and more than one styrenic functionality. Such compounds are prepared from a polymeric starting compound from which depend functionalities that are reactive with the starting oxetane compound and the starting styrenic compound.

[0017] The polymeric compound will have the structure



in which polymer is a polymeric backbone from which depend the oxetane and styrenic functionalities; m and n are integers that will vary with the level of oxetane and styrenic functionality added by the practitioner and typically will be from 2 to 500; R^1 is a methyl or ethyl group; R^2 and R^3 are H or a methyl or ethyl group; R^4 is a direct bond or a divalent hydrocarbon; W and Z independently are an ether, ester, amide, or carbamate group (formed through the reaction of a pendant functionality on the polymer and a corresponding reactive functionality on the starting oxetane or starting styrenic compound, respectively); and G is $-OR^1$, $-SR^1$, or $-N(R^2)(R^3)$, in which R^1 , R^2 and R^3 are as described above.

[0018] The pendant functionalities on the polymer may be connected to the polymeric backbone by a hydrocarbon, for example, one having one to twenty carbons, that itself is dependent from the polymeric backbone. For purposes of this specification, those dependent moieties will be deemed to be part of the polymeric backbone.

[0019] An example of a commercially available and suitable polymeric backbone is poly(butadiene) having pendant hydroxyl groups. The pendant hydroxyl groups can be reacted with the oxetane starting compound containing the tosyl leaving group and with *m*-TMI. In this case, the linking group W will be an ether functionality and Z will contain a carbamate functionality.

[0020] As a further example, a poly(butadiene) having pendant carboxylic acid functionality can react with the hydroxyl functionality on either of the hydroxyl oxetane starting materials and with the isocyanate functionality on *m*-TMI. In this case, the W group will be an ester functionality and Z will contain a carbamate functionality.

[0021] Polymeric starting material can be purchased commercially, for example, there are available acrylonitrile-butadiene rubbers from Zeon

Chemicals and styrene-acrylic copolymers from Johnson Polymer. The pendant functionalities from these polymers are hydroxyl or carboxylic acid functionality.

[0022] Other starting polymeric materials can be synthesized from acrylic and/or vinyl monomers using standard polymerization techniques known to those skilled in the art. Suitable acrylic monomers include α,β -unsaturated mono and dicarboxylic acids having three to five carbon atoms and acrylate ester monomers (alkyl esters of acrylic and methacrylic acid in which the alkyl groups contain one to fourteen carbon atoms). Examples are methyl acrylate, methyl methacrylate, n-octyl acrylate, n-nonyl methacrylate, and their corresponding branched isomers, such as, 2-ethylhexyl acrylate. Suitable vinyl monomers include vinyl esters, vinyl ethers, vinyl halides, vinylidene halides, and nitriles of ethylenically unsaturated hydrocarbons. Examples are vinyl acetate, acrylamide, 1-octyl acrylamide, acrylic acid, vinyl ethyl ether, vinyl chloride, vinylidene chloride, acrylonitrile, maleic anhydride, and styrene.


[0023] Other polymeric starting materials can be prepared from conjugated diene and/or vinyl monomers using standard polymerization techniques known to those skilled in the art. Suitable conjugated diene monomers include butadiene-1,3,2-chlorobutadiene-1,3, isoprene, piperylene and conjugated hexadienes. Suitable vinyl monomers include styrene, α -methylstyrene, divinylbenzene, vinyl chloride, vinyl acetate, vinylidene chloride, methyl methacrylate, ethyl acrylate, vinylpyridine, acrylonitrile, methacrylonitrile, methacrylic acid, itaconic acid and acrylic acid.

[0024] Those skilled in the art have sufficient expertise to choose the appropriate combination of those monomers and subsequent reactions to be able to add pendant functionality, for example, hydroxyl and carboxyl

functionality, for adding the oxetane and styrenic functionalities as disclosed in this specification.

EXAMPLES


[0025] EXAMPLE 1: Preparation of styrene carbamate ethyl oxetane.



3-Ethyl-3-hydroxymethyl-oxetane (40.00 g, 0.3442 mole) and *m*-TMI (69.43 g, 0.3442 mole) were combined in a 250-ml four-neck round bottom flask equipped with a condenser, mechanical mixer, nitrogen purge and oil bath. The reaction was placed under nitrogen with stirring and heated to 65°C in the oil bath. A single drop of dibutyltin dilaurate was added, thereby causing an exothermic reaction which peaked at 125°C. The oil bath was removed and the reaction temperature dropped to 65°C within 15 minutes. At this point, the reaction was complete based on the depletion of the FT-IR isocyanate peak at 2254 cm⁻¹. The product was then removed from the flask as a viscous colorless liquid; however, over time it crystallized into a white solid with a m.p. of 52°C.

[0026] ¹H-NMR: δ 7.21-7.61 (m, 4H), 5.45 (s, 1H), 5.23 (bs, 1H), 5.12 (s, 1H), 4.61-4.21 (bm, 3H), 4.05 (s, 3H), 2.15 (s, 3H), 1.55-1.85 (bm, 8H), 0.55-1.01 (bm, 3H).

[0027] EXAMPLE 2. Preparation of styrene carbamate methyl oxetane.




3-Methyl-3-oxetane methanol (20.00 g, 0.1958 mole) and *m*-TMI (39.49 g, 0.1958 mole) were combined in a 250-ml four-neck round bottom flask equipped with a condenser, mechanical mixer, thermometer, nitrogen purge and oil bath. The reaction was placed under nitrogen with stirring and heated to 65°C in the oil bath. A single drop of dibutyltin dilaurate was added and within 5 hours the reaction was complete based on depletion of the FT-IR isocyanate peak (2254 cm⁻¹). The product was then removed from the flask as a colorless liquid with a viscosity of 21,000 cPs.

[0028] ¹H-NMR: δ 7.61 (s, 1H), 7.42 (s, 3H), 5.45 (s, 1H), 5.31 (bs, 1H), 5.15 (s, 1H), 4.61 (bm, 1H), 4.39 (bm, 1H), 4.12 (s, 4H), 2.21 (s, 3H), 1.72 (bs, 6H), 0.95-1.35 (bm, 3H).

WHAT IS CLAIMED IS:

1. A compound containing oxetane and styrenic functionality having the structure



in which

polymer is a polymeric backbone from which depend the oxetane and styrenic functionalities;

m and n are integers from 2 to 500;

R^1 is a methyl or ethyl group;

R^2 and R^3 are H or a methyl or ethyl group;

R^4 is a direct bond or a divalent hydrocarbon;

W and Z independently are an ether, ester, amide, or carbamate group; and

G is $-OR^1$, $-SR^1$, or $-N(R^2)(R^3)$, in which R^1 , R^2 and R^3 are as described above.