Claims

1. A sealable multi-layer resin sheet comprising: a first sealable resin sheet; and a second sealable resin sheet sequentially toward one side in a thickness direction, wherein

the first sealable resin sheet contains a layered silicate compound and a first inorganic filling material,

the second sealable resin sheet does not contain a layered silicate compound, and contains a second inorganic filling material,

a content ratio (B) of the first inorganic filling material to the first sealable resin sheet is 50 mass% or more,

a content ratio (A) of the second inorganic filling material to the second sealable resin sheet is 60 mass% or more, and

the content ratio (B) of the first inorganic filling material to the first sealable resin sheet and the content ratio (A) of the second inorganic filling material to the second sealable resin sheet satisfy a formula (1) described below.

$$0.4A + 1.7B < 160 \quad (1)$$

2. The sealable multi-layer resin sheet according to Claim 1, wherein

the first sealable resin sheet has a thickness of 30 μm or more and 100 μm or less, and

the second sealable resin sheet has a thickness of 50 μm or more and 500 μm or less.

3. The sealable multi-layer resin sheet according to Claim 1, wherein

the first sealable resin sheet has a coefficient of linear expansion of 80 ppm/°C or less, and

the second sealable resin sheet has a coefficient of linear expansion of 50 ppm/°C or less.