

27 APR 1999

-1-

PATENT SPECIFICATION

TITLE: TEXTURED RELEASE SHEET, METHOD OF MAKING
TEXTURED DECORATIVE LAMINATES THEREWITH,
AND DECORATIVE LAMINATE LAY-UPS INCLUDING
SUCH SHEET.

BACKGROUND OF THE INVENTION1. Field of the Invention

5 The present invention relates to decorative
laminates, lay-ups for decorative laminates, and methods
of making decorative laminates. In another aspect, the
present invention relates to a textured release sheet,
method of making such sheet, decorative laminate lay-ups
including such sheet, and method of laminating using such
10 sheet.

2. Description of the Related Art

In the early years of decorative laminates, generally only glossy surface laminates were produced (i.e. using polished molding surfaces), though some attempts were made to provide laminates with slight surface irregularities to give satin or "textured" finishes. In more recent years it has become increasingly desirable to provide various types of irregular surfaces, ranging from relatively shallow depressions such as textured (e.g., satin, matte or semigloss) surfaces, to relatively deeply "sculptured" or embossed surfaces which have a noticeable three-dimensional effect, such as wood grain, leather, slate, abstract patterns, creative designs, etc. Particularly with the rising cost of natural products, it has become more desirable to provide deeply sculptured high pressure laminates which simulate natural materials such as wood, leather and slate.

Today, high pressure decorative laminates meeting NEMA Standards are manufactured with smooth glossy surfaces, with textured surfaces, or with deeply

sculptured or embossed surfaces.

As general background, decorative laminates prepared by heat and pressure consolidation have been produced commercially for a number of years, and have found
5 widespread acceptance in the building and furniture industry as counter and table tops, bathroom and kitchen work surfaces, wall paneling, partitions and doors. Such decorative laminates can be described as containing a number of laminae that are consolidated to form a unitary
10 structure carrying a surface decoration which can range from something as simple as a solid color to something as complex as an embossed simulated wood grain finish.

More specifically, a decorative laminate generally comprises plural layers of synthetic resin impregnated
15 paper sheets consolidated or bonded together into a unitary structure under heat and pressure. In normal practice the decorative laminate assembly, from the bottom up, consists of a core of one or more sheets impregnated with phenolic resin, above which lies a
20 decorative sheet impregnated with melamine resin.

The core or base member functions to impart rigidity

to the laminate and usually comprises a solid substrate which may or may not be formed prior to the initial laminating step. Prior to stacking, the sheets of the core member are impregnated with a water alcohol solution
5 of phenol formaldehyde, dried and partially cured in a hot air oven, and finally cut into sheets. Examples of such a base or core member include a plurality of sheets of 90 to 150 pound ream kraft paper impregnated throughout and bonded with a substantially completely
10 cured phenolic resin which has been converted to the thermoset state during the initial laminating step, a precured plastic laminate, such as glass fiber-reinforced thermoset polyester resin laminates and the like, a wood product, such as hardboard, woodwaste or particle boards, plywood, and the like, a mineral base board, such as,
15 cement-asbestos board, sheet rock, plaster board, and the like, or a combination of these substrates.

The decorative sheet generally functions to give an attractive appearance to the laminate, and also gives the
20 panel its surface characteristics (i.e. resistance to chemical agents, to heat, to light, to shock and to

abrasion). It is generally high quality 50 to 125 ream weight, pigment filled, alpha cellulose paper that has been impregnated with a water-alcohol solution of melamine-formaldehyde resin, dried and partially cured, and finally cut into sheets. The decorative sheet, prior to impregnation with the resin, may be of a solid color or may comprise a decorative design, or a photo-gravure reproduction of natural materials, such as, wood marble, leather, etc.

The decorative laminate is generally obtained by placing the resin impregnated core and decorative sheets between steel plates and subjecting the laminate stack to temperatures in the range of about 800-1600 psi for a time sufficient to consolidate the laminate and cure the resins (generally about 25 minutes to an hour).. This causes the resin in the paper sheets to flow, cure and consolidate the sheets into a unitary laminated mass referred in the art as a decorative high-pressure laminate.

Generally, more than one laminate is formed at one time by inserting a plurality of assembled sheets in a

stack with each assembly being separated by a release sheet which allows the individual laminates to be separated after consolidation.

Finally, the decorative laminates so formed are then
5 bonded to a reinforcing substrate, such as plywood, hardboard, asbestos board, particle board or the like.

Methods of texturing are well known in the laminating art.

For example, U.S. Patent No. 3,997,696, for Textured
10 Laminate And Method Of Manufacture, issued December 14, 1976 to Jaisle et al., discloses that prior art texturing included use of either embossed, machined or etched three dimensional press plates in making textured decorative laminates, directly from these plates. While successful,
15 such procedures have proven exceedingly expensive because of the high cost of preparation and maintenance of each plate. The use of a "negative surface laminate master" is also discussed, with a somewhat limited press life of such masters noted.

20 Various release sheets are also well known in the prior art, some of which are utilized to provide

texturing to decorative laminates.

U.S. Patent No. 4,327,121, issued April 27, 1982 to Gray, III, discloses the use of a release sheet for texturing a moldable plastic surface, as for example, pressing a plastic film mounted on a particle board against a sheet having the desired textured pattern while setting the plastic film. One technique for producing the film with a textured surface includes to extrude a molten thermoplastic film, such as polypropylene or polymethylpentene, onto a paper surface, cool it and then pass it between matched steel embossing rolls.

U.S. Patent No. 4,816,314, issued March 28, 1989 to Prawdzik et al., discloses a self-sustaining release sheet having at least one of its surfaces coated with a composition comprised of mineral particles dispersed in a resinous matrix. Suitable materials for use as the release sheet include polyurethane, metallic foil, and polyolefins and polyesters, such as polypropylene, polybutylene, and polyethylene terephthalate.

U.S. Patent No. 4,925,728, issued May 15, 1990 to Crass et al., discloses a coextruded, biaxially stretch-

oriented multilayer film which is suitable as a release sheet in the production of decorative laminate panels having a matte surface finish. The film includes a base layer of polypropylene, and at least one top layer of
5 98.5 to 99.6 weight percent propylene homopolymer and 0.4 to 1.5 weight percent polydiorganosiloxane. The peak-to-valley height R_z of the surface of the top layer is preferably between 1.0 and 3.0 μm .

Thus, there is a need in the art for methods of
10 making textured decorative laminates which do not suffer from the prior art limitations.

There is another need in the art for apparatus useful in making textured decorative laminates which do not suffer from the prior art limitations.

15 These and other needs in the art will become apparent to those of skill in the art upon review of this specification, including its drawings and claims.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide for methods of making textured decorative laminates which do not suffer from the prior art limitations.

5 It is another object of the present invention to provide for apparatus useful in making textured decorative laminates which do not suffer from the prior art limitations.

10 These and other objects of the present invention will become apparent to those of skill in the art upon review of this specification, including its drawings and claims.

15 According to one embodiment of the present invention, there is provided a method of forming a textured decorative laminate. The method first includes forming a stack of thermoplastic resin impregnated layers having a top layer. The method then includes positioning a polypropylene sheet having a textured surface such that the textured surface is oriented adjacent the top layer, wherein the textured surface was formed in the polypropylene sheet during formation of the sheet, while

20

the sheet was at a temperature above its softening point. The method then includes applying heat and pressure to the stack and polypropylene sheet sufficient to form a decorative laminate with a textured surface.

5 According to another embodiment of the present invention, there is provided a decorative laminate lay-up having a plurality of thermosetting resin impregnated layers having a top layer, with the textured polypropylene release sheet oriented such that the
10 textured surface is adjacent the top layer.

 According to even another embodiment of the present invention, there is provided a decorative laminate having a textured finish, wherein the textured finish is provided by contact with a polypropylene sheet having a
15 textured surface, and wherein the textured surface was formed in the polypropylene sheet during formation of the sheet, while the sheet was at a temperature above its softening point

 These and other embodiments of the present invention
20 will become apparent to those of skill in the art upon review of this specification, including its drawings and

-11-

claims.

DETAILED DESCRIPTION OF THE INVENTION

The textured release sheet of the present invention is generally a sheet of polypropylene in which the textured portion is provided simultaneous with the forming of the sheet. In the method of forming the textured release sheet, it is critical that the texturing not be applied during a postforming step, but rather, that the texturing be provided concurrent with the formation of the sheet, that is, while the polypropylene is generally at a temperature above its softening temperature.

The polypropylene utilized in the practice of the present invention may be generally described as either a propylene homopolymer, or a copolymer of propylene and any other α -olefin.

The melt flow index of the propylene utilized in the present invention will generally be selected to provide the desired physical properties in the texturing process. Generally, the melt flow index will be in the range of about 1 to about 20, preferably in the range of about 5 to about 15, and more preferably in the range of about 7

to about 12, as measured utilizing ASTM D-1238.

Non-limiting commercial examples of polypropylenes suitable for use in the present invention include EOD97-06, available from Fina (Dallas, Texas), having a melt flow of 12 g/10 min. (ASTM D-1238 Condition "L"), density of 0.91 g/cc (ASTM D-1505), tensile strength of 5,800 psi (ASTM D-638), elongation of 10 percent at yield, tensile modulus of 280,000 psi (ASTM D-638), flexural modulus of 270,000 psi (ASTM D-790), melting point of 333°F (DSC), and a recrystallization point of 261°F; and also include ESCORENE polypropylene PD 4443, Exxon Chemical, having a melt flow of 7.25 g/10 min. (ASTM 1238), density of 0.90 g/cm³ (ASTM D792), tensile strength of 3,300 psi in the machine direction and 3,500 psi in the transverse direction, elongation at yield of 5% in both the machine and transverse directions, tensile strength at break of 8,000 psi in the machine direction and 7,000 psi in the transverse direction, elongation at break of 600 percent in both the machine and transverse directions, haze of 2.5%, gloss of 85% and a coefficient of friction of 0.3.

As is well known, various processes and catalysts

exist for the production of polypropylene. In the practice of the present invention, it is believed that any suitable process and catalyst may be utilized provided that a polypropylene suitable for use in making
5 a textured release sheet for decorative laminates is produced.

For example, the traditional Ziegler-Natta catalyst systems utilize a transition metal compound cocatalyzed by an aluminum alkyl. Having been around since the early
10 1950's, these Ziegler-Natta type polyolefin catalysts, their general methods of making, and subsequent use, are well known in the polymerization art.

More specifically, a Ziegler-Natta type polymerization catalyst is basically a complex derived
15 from a halide of a transition metal, for example, titanium, chromium or vanadium, with a metal hydride and/or a metal alkyl that is typically an organoaluminum compound. The catalyst component is usually comprised of a titanium halide supported on a magnesium compound
20 complexed with an alkylaluminum, and may even include an electron donor. Examples of such catalyst systems are

shown in the following U.S. Patents: 4,107,413;
4,294,721; 4,439,540; 4,115,319; 4,220,554; 4,460,701;
and 4,562,173; the disclosures of these patents are
hereby incorporated by reference. These are just a few
5 of the hundreds of issued patents relating to catalysts
and catalyst systems designed primarily for the
polymerization of propylene and ethylene.

As another example for making polypropylene,
"metallocene" catalysts for olefin polymerization,
10 comprising a metallocene and an aluminum alkyl component
were first proposed in the 1950s. In a metallocene
catalyst system, the transition metal compound has two or
more cyclopentadienyl ring ligands. Accordingly,
titanocenes, zirconocenes and hafnocenes have all been
15 utilized as the transition metal component in such
"metallocene" containing catalyst systems for the
production of polyolefins.

The textured release sheet of the present invention
is generally formed by any suitable processing method
20 which will form the desired textured release sheet useful
for providing texture to a decorative laminate. As non-

limiting examples, common methods which are useful in the present invention, include extrusion and cast embossing.

In the extrusion process, the polypropylene is forced through an extrusion die in a melted state and subsequently cooled into a sheet as the melted extrudate passes between chilled rollers. It is the chilled rollers which provide the desired texturing to the sheet during formation of the sheet, rather than utilizing post-cooling embossing rolls to provide texturing to the sheet after it is has cooled. The textured sheet is provided with a smooth back surface.

In cast embossing, flowable polypropylene is deposited or "cast" onto an embossing surface and subsequently cooled to form a polypropylene sheet. The embossing surface onto which the polypropylene is cast is suitable to provide the desired texturing to the thus formed sheet.

Regardless of the method of forming the textured release sheet, it is critical that the texturing be provided generally while the polypropylene is still above the softening temperature, preferably while still above

the melting temperature. The textured release sheet will have a textured front surface and a smooth back surface.

5 The texturing of the present invention may take any form, dimension or pattern imaginable. In general, the peak-to-valley height R_z of the texturing surface may be any desirable, but is preferably greater than 100 μ inches, more preferably greater than about 200 μ inches, and even more preferably greater than about 300 μ inches.

10 The thickness of the textured release sheet of the present invention may be varied within a wide range of limits. If the sheet is too thin, the texture will tend not to transfer. Economic factors tend to set the upper limit for the thickness of the sheet. In general, the thickness of the textured release sheet will be at least 1 mil, and preferably at least 1.5 mils, and more preferably at least 2 mils.

20 In the production of textured decorative laminates, the textured release is utilized to provide a textured surface to the decorative laminate, and additionally to function as a release sheet between decorative laminate lay-ups. A typical decorative laminate sheet assembly

includes several layers of thermosetting resin impregnated core stock (preferably kraft paper) supporting a thermosetting resin impregnated decorative layer, which may be further overlaid with a thermosetting resin impregnated overlay sheet. The thermosetting resin employed is preferably a phenolic resin for the core stock, and preferably a clear melamine formaldehyde resin for the decorative and overlay sheets. The textured surface of the textured release sheet is oriented to be against the top most layer, be it the decorative sheet or overlay sheet, with the smooth back surface of the textured release sheet oriented to be against the core stock of an adjacent lay-up. Upon pressing between suitable laminate press plates, the textured release sheet imparts texture to the top most layer of the first lay-up, and serves to allow release between the first lay-up and the adjacent lay-up.

A platen press assembly as is well known in the lamination art is utilized to provide the necessary heat and/or pressure during lamination.

In the practice of the present invention, there may

be utilized, as desired and/or necessary, antioxidants, antiblock agents, slip agents, cross linking agents, stabilizers, ultraviolet ray absorbers, lubricants, foaming agents, antistatic agents, organic and inorganic
5 flame retardants, plasticizers, dyes, pigments, talc, calcium carbonate, carbon black, mica, glass fibers, carbon fibers, aramid resin, asbestos, as well as other fillers as are known in the art.

The polypropylene utilized in the present invention
.0 may be further blended with or incorporated into one or more other thermoplastics. Suitable other thermoplastics include polyolefins, especially polyethylenes, other polypropylenes, polyesters, polyacrylamides, polyamides, polycarbonates, polyurethanes,
15 polyacrylonitriles, and butadiene styrenes. Preferred polyethylenes include linear low density polyethylenes.

EXAMPLES

The following non-limiting examples are provided merely to illustrate the present invention and are not meant to limit the scope of the claims of the present invention.

5

EXAMPLE 1

Thirty-nine films of various morphologies were post-embossed cold using a 6"x6" lab press. For texturing, 120 grit sandpaper and 80 grit sandpaper were used. Film samples listed in Table 1 were cut into 6" squares, paired with the sandpaper and pressed for one minutes at 1000 psi. The cold embossed films were then pressed, textured side to face, with resin impregnated decorative and kraft papers to make a high pressure laminate under high press decorative laminate (HPDL) conditions well known to those in the art. All films flattened under HPDL conditions and transferred no pattern.

Table 1

5

10

15

20

25

30

Name	Description	Thickness	Supplier	Type
Toray	clear	2mil	Toray No Kingstown, RI	OPP
Toray	matte	1mil		
Melinex 378	matte	92ga	ICI Hopewell, VA	PET
Melinex HS2	hazy	92ga	ICI	PET
Mylar ED11	matte	5mil	Dupont	PET
Mylar XM020	clear	2mil	Dupont	PET
Dartek C-917PA	clear	2mil	Dupont Canada	Nylon
Phanex YMC	matte	2mil	Hoechst Celanese	PET
Phanex IHC	clear	2mil	Hoechst Celanese	PET
Tedlar TMR10SM3	matte	1mil	Dupont	PVF
Tedlar TMR20SM3	matte	2mil	Dupont	PVF
XM020	clear	1mil	Dupont	PEN
Embossed Laminated	clear	2mil	Cypress Pkg	PET/OPP
Dartek T420NA	clear	1mil	Dupont Canada	Oriented Nylon
Dartek TC101NA	clear	1mil	Dupont Canada	Cast Nylon
Dartek C101NA	clear	2mil	Dupont Canada	Cast Nylon
Mylar 100XM020LS	hazy	1mil	Dupont	PET
Mylar 100XM020	hazy	1mil	Dupont	PET
Kapton 100HN	gold/clear	1mil	Dupont	PI
Kapton 200HN	gold/clear	2mil	Dupont	PI
Kapton 100HA	gold/clear	1mil	Dupont	PI
Kapton 200HA	gold/clear	2mil	Dupont	PI
Kapton 200JP	gold/clear	2mil	Dupont	PI
Kapton 100JP	gold/clear	1mil	Dupont	PI
Tedlar TTR20SG4	clear	2mil	Dupont	PVF
EX 399	white	2mil	Exxon	CPP
EX 393	white	3mil	Exxon	CPP

EX 355	matte	3mil	Phillips Joanna	PP
3700 TIS		3mil	Moire of NC	unk
Moire 763	clear	2mil	Dupont	PET
Mylar 200J101	clear	2mil	Dupont	PET
Mylar 200A	clear	2mil	Dupont	PET
Mylar 200D	clear	2mil	Dupont	PET
Mylar 640 GA 848	clear	6mil	Dupont	PET
Mylar 200 J102	clear	2mil	Dupont	PET
Mylar 200EL	clear	2mil	Dupont	PET
Mylar 200EB	clear	2mil	Dupont	PET
Melinex 378	matte	2mil	ICI	PET
Melinex 378	matte	92ga	ICI	PET
Melinex HS2	clear	92ga	ICI	PET

5

10

EXAMPLE 2

A cycle was established for hot embossing PET and polypropylene (PP) against an aluminum wire mesh. The cycle for PET was 350F for 3.5 minutes. Polypropylene
5 films were embossed at 290F for 3.5 minutes. Films listed in Table 2 embossed in this manner resulted in a film sample with a uniform texture on one side and a smooth
10 surface on the other. All film samples transferred a uniform texture onto a laminate when pressed under HPDL conditions. Two film samples received in house already possessed a uniform texture on one side and a smooth
15 surface on the other. These two were Moire Fingerprint film and Mylar 200WC from Dupont. Both samples transferred a uniform texture onto a laminate when pressed under HPDL conditions.

TABLE 2

Melinex 377, 92 ga	ICI	PET
Mylar ED31, 1 mil	Dupont	PET
Tedlar TMR102M3, 1 mil	Dupont	PVF
100XM020LS, 1 mil	Dupont	PEN
Kapton 100HN, 1 mil	Dupont	PI
Cast PP, 4 mil	PhilJo	PP
Cast PVC, 7 mil	Texas T&R	PVC

5

Example 3

Polymer resins were obtained from outside sources and cast extruded using a 25mm co-rotating twin screw extruder under the following extrusion conditions:

5

Barrel Temp.	170C
Die Zone Temp	170C
Melt Temp.	175C
Feeder Rate	20lb/hr
Sheet Caliper	10 mils
Extruder Speed	100 rpm

10

15

The extruded film was cast embossed using a textured chill roll in the center of a 3-stack roll assembly. The embossed chill roll was engraved with a sand texture of 350 Ra. Polymers listed in Table 3 were extruded in this manner.

Table 3

Source	Name	Resin	%Transfer	Laminate Gloss
Chemiplas	N/A	PET	82	3.0
Exxon	Escorene PD 4443	PP	75	7.0
Eastman Chemical Co.	PET 10388	PET	85	3.0
ICI Americas	Melinar PET	PET	85	2.8
Rexene Products	PP 13T10A	PP	75	3.2
Rexene Products	PP 13S10A	PP	70	3.0
Fina	EOD 97-06	PP	75	10.0

In all cases, film was made that resulted in a uniform texture on one side and a smooth surface on the other. All samples transferred uniform texture onto a laminate under HPDL conditions.

5

Profilometer readings of the film and laminate were measured to evaluate the amount of texture transfer. The results are listed in Table 3.

EXAMPLE 4

Fina EOD 97-06 and Exxon Escorine PD4443 were extruded under the same conditions as Example 3. The chill roll temperature was varied in order to determine if chill roll temperature effects gloss. The film was used to prepare high pressure laminates by standard means. The results are listed in Table 4.

Table 4

	Chill roll temp	Laminate gloss
Fina EOD 9706	75 C	12.6
	95 C	23.2
	115 C	28.9
Exxon PD 4443	75 C	9.8
	95 C	13.6
	115 C	20.0

5

10

EXAMPLE 5

Fina EOD 97-06 was extruded in a 30 to 1 length to diameter ratio single screw, 4.5" wide into a flat die with a chill roll casting section, at varying conditions in order to determine conditions that effect gloss and texture transfer. The first chill roll was textured with a sand texture of 450 Ra paired with a rubber roll. After extrusion, the films were aged for 48 hours at ambient temperature then used to make high pressure laminates under standard HPDL conditions. The surface textures of the films and laminates were measured with a Federal Surfanalyzer 5000 in order to determine percent texture transfer. The conditions and results are listed in Table 5.

Table 5

Sample #	Chill Roll (F)	Line Speed (fpm)	Extruder Speed	Film Gauge	Nip Pressure	% Texture Transfer	Laminate Gloss
1	150	48	76	3.8	18	50	6.6
2	150	48	76	3.5	55	46	5.9
3	150	48	76	3.8	35	70	6.4
4	150	84	135	3.5	38	65	7.3
5	150	74	135	3.5	38	85	7.5
6	150	50	65	3.5	35	61	5.7
7	150	56	56	2.5	35	59	4.8
8	150	50	67	3.0	35	80	5.6
9	90	50	78	3.8	35	70	3.1
10	90	50	78	3.8	18	74	3.9
11	90	50	78	3.5	55	61	3.3
12	230	50	78	3.5	55	82	9.4
13	230	50	78	3.8	18	83	9.4
14	230	50	78	3.5	35	81	11.6
15	230	60	78	3.0	35	80	11.2
16	230	71	78	2.5	35	74	10.9
17	230	71	78	2.5	55	77	8.3
18	230	89	77	2.0	55	43	9.5

-33-

Barrel Temperatures:	1	400F
	2	400
	3	400
	4	415
5	5	450
	6	480
Head Zone		430
Adapters		410
Melt Temp		451
10 Head Pressure		1200
Die Pressure		1050
Extruder speed		76 RPM

While the illustrative embodiments of the invention have been described with particularity, it will be understood that various other modifications will be apparent to and can be readily made by those skilled in the art without departing from the spirit and scope of the invention. Accordingly, it is not intended that the scope of the claims appended hereto be limited to the examples and descriptions set forth herein but rather that the claims be construed as encompassing all the features of patentable novelty which reside in the present invention, including all features which would be treated as equivalents thereof by those skilled in the art to which this invention pertains.

I CLAIM:

1 1. A method of forming a textured decorative laminate
2 comprising the steps of:

3 (a) forming a stack of two or more thermoplastic
4 resin impregnated layers, with one of the resin
5 impregnated layers being a top layer;

6 (b) positioning a polypropylene sheet having a
7 textured surface with a pattern such that the textured
8 surface is oriented adjacent the top layer, wherein the
9 textured surface was formed in the polypropylene sheet
10 during formation of the sheet, while the sheet was at a
11 temperature above its softening point;

12 (c) applying heat and pressure to the stack and
13 polypropylene sheet sufficient to impress the pattern
14 into the top layer and form a decorative laminate with a
15 textured finish.

1 2. The method of claim 1 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the
3 range of about 1 to about 20.



1 3. The method of claim 2 wherein the polypropylene
2 sheet has a thickness of at least about 1 mil.

1 4. The method of claim 2 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 5. The method of claim 2 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 100 μ
3 inches.

1 6. The method of claim 1 wherein the polypropylene
2 sheet comprises a propylene homopolymer or a copolymer of
3 propylene and any other α -olefin.

1 7. The method of claim 1 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the



3 range of about 5 to about 15.

1 8. The method of claim 7 wherein the polypropylene
2 sheet has a thickness of at least about 1.5 mils.

1 9. The method of claim 8 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 10. The method of claim 8 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 200 μ
3 inches.

1 11. The method of claim 1 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the
3 range of about 7 to about 12.

1 12. The method of claim 11 wherein the polypropylene



2 sheet has a thickness of at least about 2 mils.

1 13. The method of claim 12 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 14. The method of claim 12 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 300 μ
3 inches.

1 15. A decorative laminate lay-up comprising:

2 (a) a stack of two or more thermoplastic resin
3 impregnated layers, with one of the resin impregnated
4 layers being a top layer; and

5 (b) a polypropylene sheet having a textured surface
6 such that the textured surface is oriented adjacent the
7 top layer, wherein the textured surface was formed in the
8 polypropylene sheet during formation of the sheet, while



9 the sheet was at a temperature above its softening point.

1 16. The lay-up of claim 15 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the
3 range of about 1 to about 20.

1 17. The lay-up of claim 16 wherein the polypropylene
2 sheet has a thickness of at least about 1 mil.

1 18. The lay-up of claim 16 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 19. The lay-up of claim 16 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 100 μ
3 inches.

1 20. The lay-up of claim 15 wherein the polypropylene



2 sheet comprises a propylene homopolymer or a copolymer of
3 propylene and any other α -olefin.

1 21. The lay-up of claim 15 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the
3 range of about 5 to about 15.

1 22. The lay-up of claim 21 wherein the polypropylene
2 sheet has a thickness of at least about 1.5 mils.

1 23. The lay-up of claim 22 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 24. The lay-up of claim 22 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 200 μ
3 inches.



1 25. The lay-up of claim 15 wherein the polypropylene
2 sheet comprises polypropylene having a melt flow in the
3 range of about 7 to about 12.

1 26. The lay-up of claim 25 wherein the polypropylene
2 sheet has a thickness of at least about 2 mils.

1 27. The lay-up of claim 26 wherein the polypropylene
2 sheet further comprises propylene and at least one other
3 thermoplastic selected from the group consisting of
4 polyolefins, polyesters, polyacrylamides, polyamides,
5 polycarbonates, polyurethanes, polyacrylonitriles, and
6 butadiene styrenes.

1 28. The lay-up of claim 26 wherein the textured surface
2 has a peak-to-valley height R_z greater than about 300 μ
3 inches.

1 29. A decorative laminate having a textured finish,
2 wherein the textured finish is provided by contact with
3 a polypropylene sheet having a textured surface, and



4 wherein the textured surface was formed in the
5 polypropylene sheet during formation of the sheet, while
6 the sheet was at a temperature above its softening point.

