

Description

FIELD OF THE INVENTION

5 The field is transparent, beta-quartz glass-ceramics having a specific coloration and infra-red transmission.

BACKGROUND OF THE INVENTION

10 Glass-ceramic materials are crystalline or semi-crystalline materials produced from precursor glasses by in situ crystallization. The crystallization process initially requires a glass that contains one or more nucleating agents that permit a controlled crystallization process. A variety of nucleating agents have been disclosed in the prior art. The most commonly used nucleating agent is titania (TiO_2) alone, or in conjunction with zirconia (ZrO_2).

15 ZrO_2 may be used alone as a nucleating agent for a transparent, beta-quartz solid solution glass-ceramic. This is disclosed, for example, in United States Patent No. 3,252,811 (Beall). However, it is difficult to incorporate ZrO_2 into a glass melt, requiring high melting temperatures and/or long melting times.

20 The next step is heat treatment of a suitably selected glass in accordance with a controlled time-temperature schedule. Usually, the heat treatment occurs in two stages. In the first stage, crystal nuclei are formed in the glass. This is followed by a second stage during which crystals grow on the nuclei. The heat treatment may occur in conjunction with cooling and forming of a molten glass. Alternatively, a glass article may be formed and cooled, and subsequently heat treated to cause crystallization.

25 In situ crystallization of glasses in the $\text{Li}_2\text{O}-\text{Al}_2\text{O}_3-\text{SiO}_2$ composition field generally provides highly crystallized glass-ceramics. The primary crystal phase, depending on glass composition and heat treatment, may be a transparent beta-quartz solid solution, or a beta-spodumene solid solution.

30 Beta-quartz is the hexagonal trapezohedral modification of SiO_2 . It exhibits a slightly negative coefficient of thermal expansion (CTE). This makes it of particular interest where thermal cycling occurs, as in cookware. The basis of the beta-quartz solid solution is believed to be the substitution of Al^{+3} ions for some of the Si^{+4} ions in the beta-quartz structure. The attendant charge deficiency is made up by the introduction of a small ion, such as Li^+ , Mg^{+2} , or Zn^{+2} , into the beta-quartz structure.

35 Beta-quartz solid solution glass-ceramics customarily contain TiO_2 as a nucleating agent. Optionally, the TiO_2 may be partially, or wholly, substituted for by ZrO_2 as explained earlier. The appearance of such glass-ceramics can be varied by varying composition and/or heat treatment. Thus, transparent, translucent, or opaque glass-ceramics, which may be water-white, translucent, opaque white, or variously colored, are all possibilities as described in the prior art.

40 The widest use of $\text{Li}_2\text{O}-\text{Al}_2\text{O}_3-\text{SiO}_2$ glass-ceramic materials has been in the field of culinary ware. For over three decades, Corning Glass Works, now Corning Incorporated, has marketed opaque white cooking utensils under the trademark CORNING WARE. More recently, cooking utensils, formed from a transparent glass-ceramic exhibiting a light brown tint, were introduced commercially by Corning France, S.A. under the trademark VISION. In general, this transparent glass-ceramic is crystallized at lower temperatures to develop small, beta-quartz solid solution crystals. Such glass-ceramics and their production are described, for example, in United States Patents No. 4,018,612 and No. 4,526,872.

45 It has been observed that transparent, beta-quartz glass-ceramics nucleated with TiO_2 tend to exhibit a light brown tint. This is ascribed to the presence of both TiO_2 and Fe_2O_3 in the parent glass composition. Efforts have, therefore, been made to either develop a decolorizer or to mask the tint. In an opaque, white glass-ceramic, the brown tint is effectively masked.

50 Masking, however, becomes more difficult in transparent glass-ceramics. Thus, United States Patent No. 4,093,468 (Boitel et al.) describes problems encountered when attempts were made to mask the brown tint in transparent glass-ceramics. Accordingly, that patent proposed neodymium oxide as a composition additive to make the glass-ceramic sensibly colorless.

The present invention arises from a desire to achieve a decorative color in a transparent, beta-quartz solid solution glass-ceramic. This goes beyond simply neutralizing the inherent brown tint.

55 In addition to achieving the desired coloration, production demands that it be done while maintaining a certain degree of infra-red transmission in the molten glass. This is necessary to adequately retain heat in the glass during the forming process. Heretofore, this has been accomplished by maintaining the Fe_2O_3 level in the composition at a small, but reasonably critical, amount.

SUMMARY OF THE INVENTION

The glass-ceramic material of the invention is a transparent glass-ceramic having a beta-quartz solid solution as its primary crystal phase, said glass-ceramic composed essentially, in weight percent on the oxide basis, of

SiO ₂	48-70	Li ₂ O	2.5-5
Al ₂ O ₃	17.5-30	ZrO ₂	0-4
MgO	1-2.5	TiO ₂	1.8-6.0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

and having a color package composed of 50 to 150 ppm Co₃O₄, 50 to 250 ppm NiO, and 400 to 1000 ppm Fe₂O₃, thereby providing a burgundy color having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

$$\text{Cap } Y = 50 \text{ to } 70.$$

In a further embodiment of the invention an article of cookware is provided composed of a transparent glass-ceramic having as its primary crystal phase a beta-quartz solid solution, said glass-ceramic composed essentially, in weight percent on the oxide basis, of

SiO ₂	48-70	Li ₂ O	2.5-5
Al ₂ O ₃	17.5-30	ZrO ₂	0-4
MgO	1-2.5	TiO ₂	1.8-6.0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

and having a color package composed of 50 to 150 ppm Co₃O₄, 50 to 250 ppm NiO, and 400 to 1000 ppm Fe₂O₃, thereby providing a burgundy color having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

$$\text{Cap } Y = 50 \text{ to } 70.$$

A preferred embodiment has a color package composed of about 100 ppm Co₃O₄, about 200 ppm NiO and about 650 ppm Fe₂O₃.

PRIOR ART

In addition to the patents already noted, attention is directed to the following United States patents:

Several patents, such as No. 3,788,865 (Babcock et al.), No. 4,009,042 (Rittler) and No. 4,018,612 (Chyung) disclose use of transition metal oxides, including NiO, Cr₂O₃, Fe₂O₃, MnO, Co₃O₄ and V₂O₅ as colorants for transparent glass-ceramics.

No. 4,007,048 (Sack et al.) discloses a Li₂O-Al₂O₃-SiO₂ glass-ceramic containing TiO₂, MnO, Fe₂O₃, CoO and NiO to produce a black color that appears red by transmitted light in a stove top.

No. 4,192,888 (Babcock et al.), a division of No. 3,788,865, discloses Li₂O-Al₂O₃-SiO₂ glass-ceramics containing a variety of different oxide glass colorants, individually or in combination. The color in the glass-ceramic differs from that in the precursor glass, and may vary in the glass-ceramic depending on the heat treatment.

No. 4,461,839 (Rittler) discloses transparent, translucent, or opaque glass-ceramics that have a beta-quartz crystal phase. They exhibit colors varying from black to brown to red and contain 0.05-0.2% Fe₂O₃, 2.5-6% TiO₂ and 0.3-3% of at least two oxides selected from 0-2% CaO, 0-3% CeO₂, 0-1% NiO, 0-1.5% SnO₂, 0-0.3% V₂O₅ and 0-1% WO₃.

No. 4,526,872 (Andrieu et al.) discloses a TiO_2 -nucleated, beta-quartz glass-ceramic having a light brown tint supplied by Fe_2O_3 , CoO and Cr_2O_3 with MnO_2 and V_2O_5 optional.

No. 4,835,121 (Shibuya et al.) discloses V_2O_5 as an additive in a beta-quartz glass-ceramic to enhance infra-red transmittance. The patent excludes other colorants, such as Fe_2O_3 , MnO , NiO , CoO , Cr_2O_3 and CeO_2 , because they reduce infra-red transmittance.

No. 4,940,674 (Beall et al.) adds 25-250 ppm Cr_2O_3 to a beta-quartz glass-ceramic to reduce haze. Co_3O_4 and Fe_2O_3 are then added to provide a neutral color.

Pending application S.N. 07/603,407 (Amundson et al.) discloses a color package to provide a light beige color in a potassium fluorrichterite glass-ceramic. The package includes 0.065-0.16% Fe_2O_3 , 0.055-0.16% NiO , 0.0015-0.0029% Se and 0-0.0014% Co_3O_4 , the latter controlling brightness if present.

BRIEF DESCRIPTION OF THE DRAWING

FIGURE 1 in the drawing is a graphical representation of chromaticity coordinates x and y (Illuminant C). Rectangle BEFGB encompasses chromaticity coordinates for materials in accordance with the invention.

FIGURE 2 is a graphical representation similar to that of FIGURE 1, but showing, by vectors, the trends resulting from increasing individual colorant contents in accordance with the invention.

DESCRIPTION OF THE INVENTION

The present invention is based on discovery of a color package. This color package provides a specified burgundy color in a transparent glass-ceramic having a beta-quartz solid solution as its primary crystal phase. The art is familiar with production of the basic glass-ceramic material. Numerous examples of compositions are set forth in such United States patents as 4,018,612 (Chyung), 4,093,468 (Boitel et al.) and 4,526,872 (Andrieu et al.) noted earlier.

The present invention, being concerned with a color package, is generally applicable to beta-quartz solid solution glass-ceramics. In general, that glass-ceramic family is composed essentially of, as calculated from precursor glass batches in percent by weight on an oxide basis,

SiO_2	48-70	Li_2O	2.5-5
Al_2O_3	17.5-30	ZrO_2	0-4
MgO	1-2.5	TiO_2	1.8-6.0
BaO	0-2	As_2O_3	0-1
ZnO	0-6	P_2O_5	0-12

Visual appearance of a color is, of course, controlling from a consumer viewpoint. A color tint thus selected must then be defined for production control. For this purpose, the standard CIE system, employing chromaticity coordinates x and y and the tri-stimulus value Y , has been adopted.

Chromaticity values are measured under standard conditions, i.e., Illuminant C, with a Hunter Colorimeter. They are a measure of light diffusely reflected off opaque surfaces. Because the values obtained are readily reproducible, they are commonly employed to facilitate comparisons and to establish specification limits.

Consumer surveys, conducted among cookware users, indicated a strong preference for a burgundy color, that is, a purple color with a reddish cast. The problem then was to achieve this desired color in a transparent glass-ceramic having as its primary crystal phase a beta-quartz solid solution.

Initially, it was recognized that any color obtained in the precursor glass would not be retained in the crystallized, glass-ceramic state. Further, it was necessary to work within the confines of two other requirements. First, the glass composition would contain, as a nucleating agent, titania (TiO_2), whereby a brown tint would be imparted to the resulting glass-ceramic. Second, the iron oxide (Fe_2O_3) would range from at least 400 ppm up to about 1000 ppm. This assures adequate infra-red radiation control to facilitate heat retention in the glass melt during the forming process.

Working within these limitations, we explored the coloring effects obtainable by adding known glass colorants to the precursor glass batch. These were added, either alone or in combinations. The resulting glass was then crystallized to the glass-ceramic state. These melting expeditions led us to the discovery that a combination of nickel and cobalt oxide additions, together with the necessary TiO_2 and Fe_2O_3 contents, could yield the desired burgundy color.

In the accompanying drawing, FIGURE 1 is a graphical representation of our color package employing the CIE chromaticity coordinate system. In FIGURE 1, x coordinates are plotted on the horizontal axis and y coordinates are plotted on the vertical axis. The rectangle BEFGB encompasses coordinate value combinations that provide generally acceptable burgundy colors in accordance with the invention. The color coordinate value ranges for this area are:

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

The smaller rectangle ABCDA encompasses coordinate value combinations that represent the target area for the desired burgundy color for a cooking vessel. The color coordinate value ranges for this target area are:

$$x = 0.3230 \text{ to } 0.3370$$

$$y = 0.2990 \text{ to } 0.3150$$

A survey of our experimental data indicates certain trends that occur as the contents of the colorants NiO, Co₃O₄ and Fe₂O₃ are individually increased, or decreased, in a beta-quartz solid solution glass-ceramic. These trends are shown by vectors in FIGURE 2, where, as in FIGURE 1, x coordinate values are plotted on the horizontal axis and y values on the vertical axis.

The NiO vector indicates that increasing the NiO content increases the x coordinate value, while effecting little or no change in the y values. Increasing the Co₃O₄ content markedly decreases y coordinate values while having a much lesser effect on x values. Increasing the Fe₂O₃ content tends to increase the x and y coordinate values about equally.

Satisfactory burgundy colors may be obtained with combinations of colorants which individually fall within the following ranges:

NiO	50 to 250 ppm
Co ₃ O ₄	50 to 150 ppm
Fe ₂ O ₃	400 to 1000 ppm

The colorants are, of course, employed in conjunction with up to about 6% TiO₂ as a nucleating agent. A particularly preferred embodiment is a combination of 200 ppm NiO, 100 ppm Co₃O₄ and 650 ppm Fe₂O₃.

SPECIFIC EMBODIMENTS

The invention is further described with reference to experiments carried out in the course of its development. A commercially tested glass-ceramic, having a beta-quartz solid solution as its primary crystal phase, was selected as a base composition. The precursor glass for this glass-ceramic has the following calculated composition in percent by weight on an oxide basis:

SiO ₂	68.2	BaO	0.75
Al ₂ O ₃	19.2	TiO ₂	2.7
Li ₂ O	2.8	ZrO ₂	1.75
MgO	1.8	As ₂ O ₃	0.9
ZnO	1.0		

The precursor glass has a coefficient of thermal expansion (0-300°C) of $33 \times 10^{-7}/^\circ\text{C}$; a softening point of 960°C; a strain point of 655°C; a liquidus of 1250°C; and a viscosity at the liquidus of (35,000 poises) 3,500 Pa.s.

Using the foregoing glass as a base, numerous experimental batches were formulated. These used known colorants in varying amounts, both individually and in combination. The batches were melted in silica crucibles at a temperature of 1600°C for 24 hours. The melts were poured onto steel plates to produce glass slabs. These slabs were immediately annealed at 650°C to 700°C, and then crystallized using a two stage heat treatment. Initially, the slabs were heated at 750°C to 800°C for one hour to form nuclei. Then,

the temperature was raised to 880°C to 900°C for one hour to crystallize the glass by forming a beta-quartz solid solution crystal phase.

In this manner, it was determined that the desired burgundy color could be obtained in a TiO_2 -nucleated glass-ceramic with a combination of nickel, cobalt and iron oxides. The next step was to make a number of melting excursions at different colorant levels. These excursions determined combinations that would provide color coordinates falling within the prescribed boundaries as defined by rectangle BEFGB in FIGURE 1 of the drawing. These excursions were made at three levels of Fe_2O_3 , namely, 450, 680 and 910 ppm. At each level, a composition grid was established with NiO being varied over a range at several levels of Co_3O_4 . These grids were designed to produce color coordinate combinations both within and without the indicated area of FIGURE 1.

TABLE I, below, sets forth numerous satisfactory colorant combinations together with the x and y chromaticity coordinate and tri-stimulus values for each combination. Colorant contents are in parts per million (ppm).

TABLE I

Ex.	Co_3O_4	NiO	Fe_2O_3	x	y	Y
1	60	170	450	0.3284	0.3138	66.4
2	60	250	450	0.3328	0.3133	62.5
3	80	170	450	0.3275	0.3091	63.7
4	80	210	450	0.3302	0.3090	61.5
5	80	250	450	0.3321	0.3089	59.8
6	80	80	680	0.3276	0.3127	65.3
7	80	170	680	0.3300	0.3109	62.0
8	80	210	680	0.3344	0.3127	60.6
9	100	210	680	0.3319	0.3068	58.6
10	100	50	680	0.3230	0.3074	65.2
11	100	90	680	0.3235	0.3057	63.5
12	100	130	680	0.3262	0.3053	61.4
13	100	170	680	0.3307	0.3077	58.9
14	120	90	680	0.3266	0.3055	60.8
15	120	130	680	0.3267	0.3033	59.5
16	120	170	680	0.3312	0.3051	57.2
17	140	130	680	0.3257	0.2996	57.5
18	100	50	910	0.3288	0.3131	64.4
19	100	130	910	0.3295	0.3098	61.5
20	120	50	910	0.3270	0.3058	60.7
21	120	90	910	0.3299	0.3106	61.1
22	120	130	910	0.3332	0.3098	58.3
23	140	50	910	0.3245	0.3024	60.3
24	140	90	910	0.3271	0.3026	58.1
25	140	130	910	0.3292	0.3025	56.6

Table II, below, sets forth a number of colorant combinations that do not provide the desired burgundy color, that is, they do not fall within the BEFGB rectangle of FIGURE 1. As in TABLE I, chromaticity coordinate and tri-stimulus values are included and colorant contents are stated in ppm.

TABLE II

Ex.	Co ₃ O ₄	NiO	Fe ₂ O ₃	x	y	Y
26	40	170	450	0.3284	0.3174	69.0
27	40	130	450	0.3264	0.3172	69.6
28	40	90	450	0.3244	0.3173	70.1
29	120	50	680	0.3200	0.3004	62.9
30	140	50	680	0.3226	0.3014	61.0
31	140	90	680	0.3234	0.2990	58.8
32	80	50	680	0.3248	0.3167	71.7
33	80	170	680	0.3315	0.3188	67.1
34	100	0	910	0.3238	0.3114	67.6
35	120	0	910	0.3221	0.3061	65.2
36	140	0	910	0.3214	0.3031	62.8

It will be observed that composition trends become apparent as might be expected from the vectors shown in FIGURE 2. Thus, at a low Fe₂O₃ level, a high NiO level and low Co₃O₄ level are required. Likewise, a high Fe₂O₃ level couples with a high Co₃O₄ level and low NiO level. However, at least some NiO is required as shown by Examples 34-36.

It will also be observed that, because of the sloping nature of rectangle BEFGB, absolute ranges for all operative colorant combinations cannot be established. For example, the Co₃O₄ and NiO contents of Examples 23 and 24 (140 and 50 ppm and 140 and 90 ppm, respectively) are satisfactory at 910 ppm Fe₂O₃. However, the same levels are not satisfactory at 680 ppm Fe₂O₃ as shown by Examples 30 and 31 in TABLE II.

Claims

1. A transparent glass-ceramic having a beta-quartz solid solution as its primary crystal phase, said glass-ceramic composed essentially, in weight percent on the oxide basis, of

SiO ₂	48-70	Li ₂ O	2.5-5
Al ₂ O ₃	17.5-30	ZrO ₂	0-4
MgO	1-2.5	TiO ₂	1.8-6.0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

and having a color package composed of 50 to 150 ppm Co₃O₄, 50 to 250 ppm NiO, and 400 to 1000 ppm Fe₂O₃, thereby providing a burgundy color having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

$$\text{Cap } Y = 50 \text{ to } 70.$$

2. A transparent glass-ceramic in accordance with claim 1 having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3230 \text{ to } 0.3370$$

$$y = 0.2990 \text{ to } 0.3150$$

$$\text{Cap } Y = 55 \text{ to } 65.$$



TABLE II

Ex.	Co ₃ O ₄	NiO	Fe ₂ O ₃	x	y	Y
26	40	170	450	0.3284	0.3174	69.0
27	40	130	450	0.3264	0.3172	69.6
28	40	90	450	0.3244	0.3173	70.1
29	120	50	680	0.3200	0.3004	62.9
30	140	50	680	0.3226	0.3014	61.0
31	140	90	680	0.3234	0.2990	58.8
32	60	50	680	0.3248	0.3167	71.7
33	60	170	680	0.3315	0.3188	67.1
34	100	0	910	0.3238	0.3114	67.6
35	120	0	910	0.3221	0.3061	65.2
36	140	0	910	0.3214	0.3031	62.8

It will be observed that composition trends become apparent as might be expected from the vectors shown in FIGURE 2. Thus, at a low Fe₂O₃ level, a high NiO level and low Co₃O₄ level are required. Likewise, a high Fe₂O₃ level couples with a high Co₃O₄ level and low NiO level. However, at least some NiO is required as shown by Examples 34-36.

It will also be observed that, because of the sloping nature of rectangle BEFGB, absolute ranges for all operative colorant combinations cannot be established. For example, the Co₃O₄ and NiO contents of Examples 23 and 24 (140 and 50 ppm and 140 and 90 ppm, respectively) are satisfactory at 910 ppm Fe₂O₃. However, the same levels are not satisfactory at 680 ppm Fe₂O₃ as shown by Examples 30 and 31 in TABLE II.

Claims

1. A transparent glass-ceramic having a beta-quartz solid solution as its primary crystal phase, said glass-ceramic composed essentially, in weight percent on the oxide basis, of

SiO ₂	48-70	Li ₂ O	2.5-5
Al ₂ O ₃	17.5-30	ZrO ₂	0-4
MgO	1-2.5	TiO ₂	1.8-6.0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

and having a color package composed of 50 to 150 ppm Co₃O₄, 50 to 250 ppm NiO, and 400 to 1000 ppm Fe₂O₃, thereby providing a burgundy color having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

$$\text{Cap } Y = 50 \text{ to } 70.$$

2. A transparent glass-ceramic in accordance with claim 1 having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3230 \text{ to } 0.3370$$

$$y = 0.2990 \text{ to } 0.3150$$

$$\text{Cap } Y = 55 \text{ to } 65.$$



3. A transparent glass-ceramic in accordance with claim 1 or 2 wherein the chromaticity coordinates fall within the rectangle BEFGB of FIGURE 1 in the drawing, or within the rectangle ABCDA of FIGURE 1 in the drawing, respectively.

4. A transparent glass-ceramic in accordance with claim 1, 2 or 3 wherein the color package consists of 100 ppm Co_3O_4 , 200 ppm NiO and 650 ppm Fe_2O_3 .

5. An article of cookware composed of a transparent glass-ceramic having as its primary crystal phase a beta-quartz solid solution, said glass-ceramic composed essentially, in weight percent on the oxide basis, of

SiO_2	48-70	Li_2O	2.5-5
Al_2O_3	17.5-30	ZrO_2	0-4
MgO	1-2.5	TiO_2	1.8-6.0
BaO	0-2	As_2O_3	0-1
ZnO	0-6	P_2O_5	0-12

and having a color package composed of 50 to 150 ppm Co_3O_4 , 50 to 250 ppm NiO, and 400 to 1000 ppm Fe_2O_3 , thereby providing a burgundy color having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3220 \text{ to } 0.3410$$

$$y = 0.2990 \text{ to } 0.3220$$

$$\text{Cap Y} = 50 \text{ to } 70.$$

6. An article of cookware in accordance with claim 5 having chromaticity coordinates (Illuminant C) in the ranges of

$$x = 0.3230 \text{ to } 0.3370$$

$$y = 0.2990 \text{ to } 0.3150$$

$$\text{Cap Y} = 55 \text{ to } 65.$$

7. An article of cookware in accordance with claim 5 or 6 wherein the chromaticity coordinates fall within the rectangle BEFGB of FIGURE 1 in the drawings, or within the rectangle ABCDA of FIGURE 1 in the drawings, respectively.

8. An article of cookware in accordance with claim 5, 6 or 7 wherein the color package is composed of 100 ppm Co_3O_4 , 200 ppm NiO and 650 ppm Fe_2O_3 .

Patentansprüche

1. Transparente Glaskeramik mit einem Beta-Quarz-Mischkristall als primäre Kristallphase, wobei die Glaskeramik im wesentlichen, ausgedrückt in Gew.-% auf Oxidbasis, aus



SiO ₂	48-70	Li ₂ O	2,5-5
Al ₂ O ₃	17,5-30	ZrO ₂	0-4
MgO	1-2,5	TiO ₂	1,8-6,0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

zusammengesetzt ist und eine Farbpackung aufweist, zusammengesetzt aus 50 bis 150 ppm Co₃O₄, 50 bis 250 ppm NiO und 400 bis 1000 ppm Fe₂O₃, wodurch eine Burgunderfärbung mit Chromatizitätskoordinaten (Beleuchtungsmittel C) in den Bereichen von

$$x = 0,3220 \text{ bis } 0,3410$$

$$y = 0,2990 \text{ bis } 0,3220$$

$$\text{Cap Y} = 50 \text{ bis } 70$$

bereitgestellt wird.

2. Transparente Glaskeramik nach Anspruch 1 mit Chromatizitätskoordinaten (Beleuchtungsmittel C) in den Bereichen von

$$x = 0,3230 \text{ bis } 0,3370$$

$$y = 0,2990 \text{ bis } 0,3150$$

$$\text{Cap Y} = 55 \text{ bis } 65.$$

3. Transparente Glaskeramik nach Anspruch 1 oder 2, wobei die Chromatizitätskoordinaten in das Rechteck BEFGB der Fig. 1 in der Zeichnung bzw. in das Rechteck ABCDA der Fig. 1 der Zeichnung fallen.

4. Transparente Glaskeramik nach Anspruch 1, 2 oder 3, wobei die Farbpackung aus 100 ppm Co₃O₄, 200 ppm NiO und 650 ppm Fe₂O₃ besteht.

5. Kochgeschirrgegenstand, zusammengesetzt aus einer transparenten Glaskeramik mit einem Beta-Quarz-Mischkristall als ihrer primären Kristallphase, wobei die Glaskeramik im wesentlichen, ausgedrückt in Gew.-% auf Oxidbasis, aus

SiO ₂	48-70	Li ₂ O	2,5-5
Al ₂ O ₃	17,5-30	ZrO ₂	0-4
MgO	1-2,5	TiO ₂	1,8-6,0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

zusammengesetzt ist und eine Farbpackung aufweist, zusammengesetzt aus 50 bis 150 ppm Co₃O₄, 50 bis 250 ppm NiO und 400 bis 1000 ppm Fe₂O₃, wodurch eine Burgunderfärbung mit Chromatizitätskoordinaten (Beleuchtungsmittel C) in den Bereichen von

$$x = 0,3220 \text{ bis } 0,3410$$

$$y = 0,2990 \text{ bis } 0,3220$$

$$\text{Cap Y} = 50 \text{ bis } 70$$

bereitgestellt wird.

6. Kochgeschirrgegenstand nach Anspruch 5, mit Chromatizitätskoordinaten (Beleuchtungsmittel C) in den Bereichen von

$$x = 0,3230 \text{ bis } 0,3370$$



$y = 0,2990$ bis $0,3150$
Cap Y = 55 bis 65.

7. Kochgeschirrgegenstand nach Anspruch 5 oder 6, wobei die Chromatizitätskoordinaten in das Rechteck BEFGB der Fig. 1 in der Zeichnung bzw. in das Rechteck ABCDA der Fig. 1 der Zeichnung fallen.
8. Kochgeschirrgegenstand nach Anspruch 5, 6 oder 7, wobei die Farbpackung aus 100 ppm Co_3O_4 , 200 ppm NiO und 650 ppm Fe_2O_3 besteht.

Revendications

1. Vitrocéramique transparente dont la phase cristalline primaire est une solution solide de bêta-quartz, ladite vitrocéramique étant composée essentiellement, en pourcentage en poids sur la base des oxydes, de :

SiO_2	48-70	Li_2O	2,5-5
Al_2O_3	17,5-30	ZrO_2	0-4
MgO	1-2,5	TiO_2	1,8-6,0
BaO	0-2	As_2O_3	0-1
ZnO	0-6	P_2O_5	0-12

et ayant un enrobage coloré composé de 50 à 150 ppm de Co_3O_4 , 50 à 250 ppm de NiO et 400 à 1000 ppm de Fe_2O_3 , fournissant ainsi une couleur bordeaux ayant des coordonnées de chromaticité (illuminant C) dans les plages :

$x = 0,3220$ à $0,3410$

$y = 0,2990$ à $0,3220$

Valeur trichromatique Y = 50 à 70.

2. Vitrocéramique transparente selon la revendication 1 ayant des coordonnées de chromaticité (illuminant C) comprises dans les plages suivantes :

$x = 0,3230$ à $0,3370$

$y = 0,2990$ à $0,3150$

Valeur trichromatique Y = 55 à 65.

3. Vitrocéramique transparente selon la revendication 1 ou 2, dont les coordonnées de chromaticité sont comprises respectivement dans le rectangle BEFGB de la FIGURE 1 des dessins ou dans le rectangle ABCDA de la FIGURE 1 des dessins.

4. Vitrocéramique transparente selon la revendication 1, 2 ou 3, dans laquelle l'enrobage coloré est constitué de 100 ppm de Co_3O_4 , 200 ppm de NiO et 650 ppm de Fe_2O_3 .

5. Article de cuisson composé d'une vitrocéramique transparente dont la phase cristalline primaire est une solution solide de bêta-quartz, ladite vitrocéramique étant composée essentiellement, en pourcentage en poids sur la base des oxydes, de :



SiO ₂	48-70	Li ₂ O	2,5-5
Al ₂ O ₃	17,5-30	ZrO ₂	0-4
MgO	1-2,5	TiO ₂	1,8-6,0
BaO	0-2	As ₂ O ₃	0-1
ZnO	0-6	P ₂ O ₅	0-12

et ayant un enrobage coloré composé de 50 à 150 ppm de Co₃O₄, 50 à 250 ppm de NiO et 400 à 1000 ppm de Fe₂O₃, fournissant ainsi une couleur bordeaux ayant des coordonnées de chromaticité (illuminant C) dans les plages :

$$x = 0,3220 \text{ à } 0,3410$$

$$y = 0,2990 \text{ à } 0,3220$$

Valeur trichromatique Y = 50 à 70.

6. Article de cuisson selon la revendication 5, ayant des coordonnées de chromaticité (illuminant C) dans les plages :

$$x = 0,3230 \text{ à } 0,3370$$

$$y = 0,2990 \text{ à } 0,3150$$

Valeur trichromatique Y = 55 à 65.

7. Article de cuisson selon la revendication 5 ou 6, dont les coordonnées de chromaticité sont comprises respectivement dans le rectangle BEFGB de la FIGURE 1 des dessins ou dans le rectangle ABCDA de la FIGURE 1 des dessins.

8. Article de cuisson selon la revendication 5, 6 ou 7, dans lequel l'enrobage coloré est composé de 100 ppm de Co₃O₄, 200 ppm de NiO et 650 ppm de Fe₂O₃.