



166166

14 MAY 2002



G00002

1

ELECTRICALLY CONDUCTIVE PASTE MATERIALS AND APPLICATIONS

FIELD OF THE INVENTION

The present invention relates to novel interconnection materials for forming electroconductive connections between electroconductive members, and to the method for producing such electroconductive connections. In addition, this invention addresses environmentally-safe materials and processes, which can be an alternative to lead (Pb)-containing solder connection technology.

BACKGROUND

Most electrical conductors used in electronic devices are made of metals, such as copper, aluminum, gold, silver, lead/tin (solder), molybdenum and others. Solder connection technology using lead/tin alloys plays a key role in various levels of electronic packaging, such as flip-chip connection (or C4), solder-ball connection in ball-grid-arrays (BGA), IC package assembly to a printed circuit board (PCB). Solder joints produced in the electronic packages serve critically as electrical interconnections as well as mechanical/physical connections. When either of these functions fails, the solder joint is considered to have failed, which can often threaten a shut-down of the whole electronic system.

Flip-chip connection is a most effective chip interconnection method currently used for high performance packaging applications, such as multichip modules, where lead (Pb)-rich solder bumps connect high performance chips directly to a ceramic substrate.

Solder-ball connection in ball-grid array (BGA) packages is an extension of the flip-chip connection method, where either single-chip or multichip modules are connected to a polymeric PCB by using a grid array of large solder balls. The solder

balls currently in use have the composition of a high tin content, such as Pb-10%Sn or Pb-20%Sn, in order to act as a non-melting stand-off when these modules are attached to the PCB substrate using lower melting point Pb-Sn eutectic solder.

When microelectronic packages are assembled to a printed circuit board, the lead-tin eutectic solder, 63%Sn-37%Pb, having the lowest melting point (183 °C) among Pb-Sn alloys, is most widely used. In these applications, there are two solder connection technologies employed for mass production: plated-through-hole (PTH) and surface mount technology (SMT) soldering. The basic difference between the two technologies originates from the difference in the PCB design and its interconnection scheme.

In PTH soldering, solder joints are made by utilizing the plated-through-holes on a PCB. For example, in wave soldering, molten solder is directly applied to the area of the PTH and is further drawn in by a capillary force to fill the gap between the I/O pin and the wall of the plated-through hole.

In SMT soldering, microelectronic packages are directly attached to the surface of a PCB. A major advantage of SMT is high packaging density, which is realized by eliminating most PTH's in the PCB as well as by utilizing both surfaces of the PCB to accommodate components. In addition, SMT packages have a finer lead pitch and a smaller package size compared to traditional PTH packages. Hence, SMT has contributed significantly in reducing the size of electronic packages and thereby the volume of the overall system.

In SMT soldering, solder paste is applied to a PCB by screen printing. Solder paste consists of fine solder powder, flux, and organic vehicles. During the reflow process, solder particles are melted, flux is activated, solvent materials are evaporated, and simultaneously molten solder coalesces and is eventually solidified. In contrast, in the wave soldering process, a PCB is first fluxed and components are mounted on it. Then it is moved over a wave of molten solder. The soldering process is usually completed

by subjecting the solder joints to a cleaning step to remove residual flux materials. Due to environmental concerns, CFCs and other harmful cleaning agents are being eliminated and replaced by either water-soluble or no-clean flux materials.

Recent advances in microelectronic devices demand a very fine pitch connection between electronic packages and a printed circuit board (on the order of a few hundred micrometer pitch). The current solder paste technology used in SMT can not handle this very fine pitch interconnection due to the soldering defects such as bridging or solder balling. Another technical limitation of using the Pb-Sn eutectic solder is its high reflow temperature, approximately 215 °C. This temperature is already higher than the glass transition temperature of the epoxy resin used in most polymeric printed circuit board materials. Thermal exposure at this reflow temperature produces significant thermal strains in a printed circuit board after soldering, especially in the direction perpendicular to the surface of a PCB, where no structural reinforcement is present. Thereby, the residual thermal strains in an assembled PCB would adversely affect the reliability of an electronic system.

A more serious concern regarding the usage of lead (Pb)-containing solders is an environmental issue, which we have experienced already in other industries by eliminating lead from gasoline, paints, and household plumbing solders

In the electronic industry, two different groups of materials are being investigated currently for the possibility of replacing the Pb-containing solder materials; Pb-free solder alloys, and electrically conductive pastes (ECP). The present invention discusses the development and applications of the electrically conductive paste materials. An electrically conductive paste (or adhesive) is made of electrically conducting filler particles loaded in the matrix of a polymer material. Silver-particle filled epoxy is the most common example of the electrically conductive pastes, schematically shown in FIG. 1. The silver particles, usually in the shape of flakes, provide electrical

conduction by percolation mechanism, while the epoxy matrix 6 provides adhesive bond between the components 8 and a substrate 10. This silver-filled epoxy material has been long used in the electronic applications as a die-bonding material, where its good thermal conduction rather than electrical conduction property is utilized. However, this material has not been accepted for the applications requiring high electroconduction and fine pitch connection. The silver-filled epoxy material has several limitations, such as low electrical conductivity, increase in contact resistance during thermal exposure, low joint strength, silver migration, difficulty in rework, and others. Since this silver-filled epoxy material is electrically conductive in all the directions, it is classified as "isotropic" in electroconduction.

There is another class of electrically conductive adhesive (or film), which provides electroconduction only in one direction. This class of the materials is called as "anisotropic" conductive adhesive or film 12, shown schematically in FIG. 2, contains electrically conductive particles 18 within a polymeric adhesive material 20. The anisotropic conductive adhesive or film 12, becomes conductive only when it is compressed between two conducting pads 14 and 16 as shown in FIG. 2B. This process normally requires heat and pressure. The major application of the anisotropic conductive film is for joining of a liquid crystal display panel to its electronic printed circuit board. The conducting particles are usually deformable, such as solder balls, or plastic balls coated with nickel and gold. The binder or adhesive material is mostly a thermosetting resin.

SUMMARY OF THE INVENTION

It is an object of the present invention to ameliorate one or more disadvantages of the prior art.

According to one aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, comprising: a plurality of particles embedded within a cured thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material, each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

According to another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, comprising: a plurality of particles disposed in a thermoplastic polymeric material, said thermoplastic

polymeric material being selected from the group consisting of polyimide, siloxane, polyimide siloxane, and bio-based polymeric resins derived from lignin, cellulose, wood oil and crop oil, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, comprising: a plurality of particles embedded within a thermoplastic polymeric material, said thermoplastic polymeric material being an uncured thermoplastic adhesive, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, comprising: a plurality of particles embedded within a thermoplastic polymeric material, said thermoplastic polymeric material being a cured thermoplastic adhesive, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material, each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, comprising: a thermoplastic polymeric material embedded between a first and a second surfaces; and a plurality of particles disposed in said thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said polymeric material; each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating; and wherein said thermoplastic polymeric material provides interconnection between said first and said second surfaces and provides adhesive joining of said first and said second surfaces.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connection between electroconductive materials, comprising: a thermoplastic polymeric material embedded between a first electrically conductive and a second electrically conductive surfaces; and a plurality of particles disposed in said thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating; and wherein said thermoplastic polymeric material provides interconnection between said first and said second surfaces, wherein said first electrically conductive surface is a first electronic device contact location and wherein said second electrically conductive surface is a second electronic device contact location.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive materials, having a first and a second electrically conductive surfaces comprising: a plurality of particles embedded in a polymeric material and provided between said first and said second electrically conductive surfaces, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating; wherein said electrically conductive coating has a melting temperature less than that of said particle, and wherein one of said first and said second electrically conductive surfaces is a solder surface.

According to still another aspect of the present invention there is provided a method comprising the steps of: providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, said coating being selected from the group consisting of Sn, Zn, In, Bi, and Sb, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; disposing said paste between a first and a second electrically conductive surfaces; heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and heating said paste to a second temperature sufficient to cure said polymer in said spaces.

According to still another aspect of the present invention there is provided a method for forming electroconductive connections between electroconductive materials,

6a

comprising the steps of: providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, said polymeric material being selected from the group consisting of polyimide, siloxane, polyimide siloxane, and bio-based polymeric resins derived from lignin, cellulose, wood oil and crop oil, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; disposing said paste between a first and a second electrically conductive surfaces; heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and heating said paste to a second temperature sufficient to cure said polymer in said spaces.

According to still another aspect of the present invention there is provided a structure for forming electroconductive connections between electroconductive members, comprising: particles of copper, each particle having a coating selected from the group consisting of Sn and In, wherein said particles are from 30% to 90% by weight of said structure; at least some of said particles being fused to other said particles through said coating and embedded within a thermoplastic polymer precursor and a solvent.

According to yet another aspect of the present invention there is provided a method for forming electroconductive connections between electroconductive materials, comprising the steps of: providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material; disposing said paste between a first and a second electrically conductive surfaces; heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and heating said paste to a second temperature sufficient to cure said polymer in said spaces; and wherein said first temperature and said second temperature are from about 150 degrees C to about 250 degrees C.

According to yet another aspect of the present invention there is provided a composition for forming electroconductive connections between electroconductive materials, comprising a plurality of particles, each particle having an electrically conductive coating, and a polymeric material, wherein said particles are from about 30% to about 90% by weight of said composition.

6b

According to yet another aspect of the present invention there is provided a structure comprising:

- a plurality of particles of a first material, wherein said particles are from 30% to 90% by weight of said structure;

- each of said plurality of particles has an electrically conductive coating of a second material which is different than said first material and has a lower melting temperature than said first material, said electrically conductive coating on at least some of said particles are fused directly to said electrically conductive coating on others of said particles, and said particles are embedded within a thermoplastic polymeric material. According to yet another aspect of the present invention there is provided a structure comprising:

- a network of interconnected particles of a first material having a thermoplastic polymeric material therebetween, wherein said particles are from 30% to 90% by weight of said structure;

- each of said particles has a coating thereon of a fusible material, said fusible material is different than said first material and has a lower melting temperature than said first material;

- adjacent particles in said network are adhered together through said fusible material, said coating on one of said adjacent particles being directly fused to said coating on another of said adjacent particles.

According to yet another aspect of the present invention there is provided a solder-particle-free method comprising the steps of:

- providing a paste of particles of a first material having an electrically conductive coating of a second material thereon embedded within a thermoplastic polymeric material, said second material is different than said first material and has a lower melting temperature than said first material wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

- disposing said paste between a first and second electrically conductive surface;

- heating said paste to a first temperature sufficient to directly fuse said coating on one of said particles to said coating on another of said particles to form a network of interconnected particles with spaces therebetween.

According to yet another aspect of the present invention there is provided a structure comprising:

6c

particles of copper having a surface, and substantial portion of which has a continuous electrically conductive coating selected from the group consisting of Sn and In, wherein said particles are from 30% to 90% by weight of said structure;

said particles are contained within a thermoplastic polymer precursor and a solvent.

According to yet another aspect of the present invention there is provided a structure comprising:

a copper powder having a surface, a substantial portion of which is coated with a layer of electrically conductive material selected from the group consisting of Sn, In, Bi, Sb and combinations thereof mixed with a fluxing agent, when mixed with a thermoplastic polymeric material in a 30% to 90% ratio by weight.

BRIEF DESCRIPTION OF THE DRAWINGS

Further objects, features and advantages of the present invention will become apparent from a consideration of the following detailed description of the invention when read in conjunction with the drawing Figures 1-7 in which:

FIG. 1 is a schematic illustration of an electrically conductive paste comprising silver flake particles as a filler in the matrix of epoxy resin. The conductive paste is classified as isotropic in electroconduction. (prior art)

FIG. 2A is a schematic illustration of an electrically conductive adhesive which becomes electrically conductive only in the one direction when the adhesive film is compressed between two contact or bond pads as shown in FIG. 2B. The conductive adhesive (or film) is classified as anisotropic. (prior art)

FIG. 3 is a schematic drawing of a paste according to the present invention.

FIG. 4 is a schematic illustration of an electrically conductive paste material according to the present invention, comprising particles filled in the matrix of thermoplastic polymer resin. The particles are coated with low melting point, non-toxic metals which were fused to achieve metallurgical bonding between adjacent particles, and between the particles and the contact surfaces that are joined using the paste.

FIG. 5 is a schematic cross-sectional illustration representing a surface mount integrated circuit package connected to a circuit board by an electrically conductive paste according to the invention

FIG. 6 is a schematic cross-sectional illustration representing an integrated circuit chip directly attached to a high density printed circuit board by using the electrically conductive paste according to the present invention.

FIG. 7 is a schematic illustration of a multilayer ceramic substrate with the conductive paste structure matching to the C4 bump structure on a silicon wafer. The multilayer ceramic substrate serves as a vehicle for wafer-scale burn-in and chip testing.

DETAILED DESCRIPTION

In one particular embodiment, we disclose a new electrically conductive paste material consisting of tin-coated copper powder, polyimide-siloxane, solvent (N-methyl pyrrolidone or NMP), carboxylic acid/surfactant. A joining operation can be performed near the melting point of Sn, 230 °C, where a metallurgical bonding of Sn-to-Sn or Sn-to-Au is accomplished at the particle-to-particle as well as particle-to-substrate pad interfaces. The joining process can be either solid-state or liquid-solid reaction. The polymer curing process can be combined with the joining process depending on the paste formulation. Because of the metallurgical bonding, a higher electrical conductivity is expected with the joints made of the new paste material than with those of the silver-epoxy material. The metallurgical bonds also provide stable electrical conductivity of the new joints upon thermal exposure and cycling. It is also expected to have a higher joint strength from the combined effect of the metallurgical and adhesive bonds. Depending on the applications, the particle size of tin-coated powder, composition of the polymer matrix and volume fraction of the filler material can be adjusted. Since the present conductive paste is primarily based on the metallurgical bonds, the critical volume fraction of the filler material required to achieve acceptable conductivity levels is much less than the conventional Ag-epoxy paste.

In another embodiment, we propose the use of polymer resins prepared from renewable resources or bio-based materials after appropriate functionalization to achieve the desirable thermal and rheological properties, see for example, the final report on NSF Grant # BCS 85-12636 by W.G. Glasser and T.C. Ward. Lignin (by product from paper manufacture), cellulose, wood or crop oils are potential candidates for this purpose. Use of these materials is environmentally preferable because they are derived from natural and renewable resources and can be disposed of more readily at the end of the useful life of the electronic assembly. This is particularly attractive because the

use of the Cu-Sn powder eliminates the use of lead (Pb) containing solders and the resulting paste formulation is non-toxic and easy to dispose.

FIG. 3 illustrates new electrically conductive paste (ECP) materials 30, according to the present invention, comprising particles 32 having an electrically conducting coating 34, as conducting filler materials, and a polymer matrix 36. The particles 32 are preferably Cu particles. The particles 32 may be Ni, Au, Ag, Al, Pd and Pt. The coating 34 may be Sn, Zn, In, Pb, Bi or Sb. The coating 34 is preferably tin, indium, and bismuth, antimony or combinations thereof. The polymer matrix is preferably a thermoplastic, most preferably a polyimide siloxane. The invention will be described below in terms of the preferred embodiment, but it is not limited thereto.

The first step of tin-plating on copper powder is cleaning of fine copper powder in a dilute sulfuric acid. The copper powder used is spherical in shape, having a size distribution of 2 to 8 μm in diameter, which was obtained from Degussa Corporation, South Plainfield, NJ. Tin plating is performed on the clean copper powder in an immersion tin plating solution, TINPOSIT LT-34, from Shipley, Newton, MA. The optimum thickness of tin is 0.3 to 0.5 μm on 5-7 μm Cu powder. After rinsing, the tin-plated copper powder is immediately mixed with a no-clean flux, FLUX305, from Qualitek International, Inc., Addison, IL. This prevents tin-plated copper powder from oxidation until it is processed into a conductive paste. The tin-plated copper powder is formulated into a conducting paste by mixing with polyimide siloxane, NMP solvent, butyric acid and ethylene glycol. The relative amount of filler powder over the polymer matrix is varied from 30 to 90% in weight, depending on the applications. In general, for the isotropic conduction, a high filler weight percent is required, while a low filler weight percent is required for the anisotropic applications. To insure uniform dispersion of the ingredients, the mixture is processed in a three-roll shear mill. The viscosity is also controlled by adjusting the volume fraction of the filler powder in the paste. When the filler weight percent is low, for example, 30% in weight, a solvent drying process, for

example, 100 °C, 1 hour, is required to adjust the viscosity of the paste before dispensing the paste on to a desired foot print.

In order to characterize the electrical and mechanical properties, joined samples made of the tin-plated copper-filled conductive paste are manufactured by laminating two "L-shaped" copper coupons. The lamination is performed at a temperature slightly above the melting point of Sn, for example, 250 °C, at a pressure of 25 psi. In order to compare the conductivity values, other joined samples are also fabricated under the similar process by using commercial Ag-epoxy and Sn/Pb eutectic solder paste materials. The joined samples made of the paste according to the present invention showed the lowest electrical resistance value; for example, 2.6×10^{-5} ohm for Sn-plated Cu paste, 4.7×10^{-5} ohm for Sn/Pb solder paste, and 7.3×10^{-5} ohm for Ag-epoxy for a contact area of about 0.050 inch by 0.050 inch. The resistance of the paste according to the present invention, is even lower than that of the Sn/Pb solder paste. This can be attributed to the difference in the bulk conductivities of copper versus Sn/Pb solder.

Measurements of the joint strength has also demonstrated that the joint made using the paste according to the present invention has a higher joint strength than that made of the Ag-epoxy paste.

The ECP made of Sn-plated Cu powder and polyimide-siloxane resin is a good candidate for the high temperature solder joints such as C4 and solder ball connection (SBC) to a ceramic substrate. However, for the polymeric printed circuit board applications, this ECP is not adequate, because the reflow temperature such as 250 °C is much higher than the glass transition temperature of the polymeric resin, for example, FR-4. A candidate for this purpose is an ECP made of Indium-plated Cu powder formulated with polyimide-siloxane resin. The reflow temperature of the Indium-plated Cu powder paste is about 180 °C, which is even lower than the reflow temperature of the Pb/Sn eutectic solder, 215 °C. Referring to FIG 4, the paste is disposed between

surface 40 and 42 and heated to the reflow temperature, which causes the conductive coating 34 of a particle 32 to fuse to the conductive coating 34 of an adjacent particle to form a bond 44 therebetween. Additionally, metallurgical bonds 46 are also formed between the contact surfaces 42 and the particles adjacent to these surfaces.

In light of the environmental issues, alternative polymer resins made from renewable or bio-based systems such as functionalized lignin, cellulose and wood or crop oils can be also used. These resins are biodegradable or made from non-fossil fuel resources and allow ease of recycling when the electronic assemblies are dismantled at the end of their useful life.

FIG. 5 depicts schematically an IC package attached to a PCB 50 by using a conductive paste according to the present invention. The conductive paste is screen printed on to each copper bond pad 52 on a PCB as practiced with the conventional solder paste. Pad 52 typically has a Sn coating 54. The paste 56 is disposed between Sn 58 coated lead frame 60 which electrically interconnects SMT plastic package 62 to PCB 50. The fine-pitch SMT assembly typically uses a pad spacing of about 0.025" or less. Therefore, the particle size of the tin-coated powder should be in the range of 5 to 10 μm . The joining operation is combined with the polymer curing process at the temperature between 120 and 150 °C. This low temperature process would introduce a much less amount of thermal distortion to the PCB compared to the soldering process. In addition, the joining process is free of external fluxes and no flux cleaning step is required.

FIG. 6 depicts an IC chip 60 attached to a high-density circuit card 52 such as surface laminated circuits (SLC), where the conductive paste material 64, according to the present invention, is dispensed in a two-dimensional array matching the footprint of the chip pads 66. The joining metallurgy on the chip side is preferably Cr/Cu/Au, and Au-to-Sn bond is expected to form at this interface. Since polyimide siloxane is a

thermoplastic copolymer. this joint can be reworked by heating to about 200 °C in the presence of NMP as a solvent. In case of direct chip attachment using C4 solder bumps, an encapsulation process is employed to obtain a desired thermal fatigue resistance of the solder joints. In the present application, the polymer matrix serves as a flexible phase that allows accommodation of the thermal mismatch strains between the substrate and the components. Additionally, one can encapsulate the spaces between the paste pads with a second polymer to further enhance the thermal fatigue resistance if desired.

FIG. 7 shows an application for wafer-scale burn-in of C4 chips. The conductive paste material 70 is dispensed on a multilayer ceramic substrate 72 whose pad footprint 74 is matched with the silicon wafer pad footprint 76 on which are disposed C4 solder mounds 78 to be tested and burnt-in. The MLC substrate provides interconnects required to power the chips up during burn-in and the external I/O through a pin grid array 80. The conductive paste on the substrate is cured and the Sn-coated particles are bonded together with the C4's on the wafers before the burn-in step. The burn-in operation is performed typically at 150 C, 6 hr. After burn-in, the substrate is separated from the wafer, and can be used again by etching away any residual solder transferred from the C4 bumps during the test, or by dissolving the pads in NMP and re-screening the paste to form new pads. The chip C4 pads themselves would not have changed shape or composition due to the limited metallurgical contact area and pressure between the paste and the solder. Thus one should be able to clean the good chips in a suitable solvent (such as NMP) and assemble them on substrates as per normal process without any problems or added reflow steps

Examples of new electrically conductive paste materials according to the present invention to be used for the applications of surface mount package assembly to a printed circuit board, direct chip attachment to a fine-pitch card, and wafer-scale burn-in of flip chips, in several types of formulations are as follows:

- copper powder coated with a thin layer of low melting point, non-toxic metals, such as Sn, In, Bi, Sb, and their alloys, mixed with an environmentally-safe fluxing agent, such as no-clean or water-soluble flux.

- tin-coated copper powder, mixed with polyimide siloxane, NMP solvent, and butyric acid and ethylene glycol or no-clean flux.

- tin-coated copper powder, mixed with renewable or bio-based polymer resin, suitable solvent, and butyric acid and ethylene glycol or no-clean flux.

- indium-coated copper powder, mixed with polyimide siloxane, NMP solvent, and butyric acid and ethylene glycol or no-clean flux.

- indium-coated copper powder, mixed with renewable or bio-based polymer resin, suitable solvent, and butyric acid and ethylene glycol or no-clean flux.

- an optimized formulation for the surface mount application, comprising indium-coated copper powder of 30 to 90 % in weight, polyimide siloxane, NMP solvent, and butyric acid and ethylene glycol or no-clean flux.

- an optimized formulation for the direct chip attach application, comprising indium-coated copper powder of 30 to 90 % in weight, polyimide siloxane, NMP solvent, and butyric acid and ethylene glycol or no-clean flux.

- an optimized formulation for the burn-in application, comprising tin-coated copper powder of 30 to 90 % in weight, polyimide siloxane, NMP solvent, and butyric acid and ethylene glycol or no-clean flux.

The conductive pastes according to the present invention can be used as conducting lines, ground planes, and via fills in the conventional printed circuit boards by replacing either the additive or subtractive Cu technology. This will facilitate the elimination of process steps and chemicals thus reducing cost and the environmental impact associated with printed circuit board manufacturing

While the present invention has been described with respect to preferred embodiments, numerous modifications, changes, and improvements will occur to those skilled in the art without departing from the spirit and scope of the invention.

CLAIMS:

1. A structure for forming electroconductive connections between electroconductive materials, comprising:

a plurality of particles embedded within a cured thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

2. A structure for forming electroconductive connections between electroconductive materials, comprising:

a plurality of particles disposed in a thermoplastic polymeric material, said thermoplastic polymeric material being selected from the group consisting of polyimide, siloxane, polyimide siloxane, and bio-based polymeric resins derived from lignin, cellulose, wood oil and crop oil, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

3. A structure for forming electroconductive connections between electroconductive materials, comprising:

a plurality of particles embedded within a thermoplastic polymeric material, said thermoplastic polymeric material being an uncured thermoplastic adhesive, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

4. A structure for forming electroconductive connections between electroconductive materials, comprising:

a plurality of particles embedded within a thermoplastic polymeric material, said thermoplastic polymeric material being a cured thermoplastic adhesive, wherein said

particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating.

5. A structure for forming electroconductive connections between electroconductive materials, comprising:

a thermoplastic polymeric material embedded between a first and a second surfaces; and

a plurality of particles disposed in said thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating; and

wherein said thermoplastic polymeric material provides interconnection between said first and said second surfaces and provides adhesive joining of said first and said second surfaces.

6. A structure for forming electroconductive connections between electroconductive materials, comprising:

a thermoplastic polymeric material embedded between a first electrically conductive and a second electrically conductive surface; and

a plurality of particles disposed in said thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating; and

wherein said thermoplastic polymeric material provides interconnection between said first and said second surfaces, wherein said first electrically conductive surface is a first electronic device contact location and wherein said second electrically conductive surface is a second electronic device contact location.

7. A structure according to claim 6, wherein said first electronic device is a semiconductor chip and said second electronic device is a packaging substrate.

8. A structure for forming electroconductive connections between electroconductive materials, having a first and a second electrically conductive surfaces comprising:

a plurality of particles embedded in a thermoplastic polymeric material and provided between said first and said second electrically conductive surfaces, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

each of said plurality of particles having an electrically conductive coating, at least some of said particles being fused to other said particles through said electrically conductive coating;

wherein said electrically conductive coating has a melting temperature less than that of said particle, and wherein one of said first and said second electrically conductive surfaces is a solder surface.

9. A method comprising the steps of:

providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, said coating being selected from the group consisting of Sn, Zn, In, Bi, and Sb, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

disposing said paste between a first and a second electrically conductive surfaces;

heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and heating said paste to a second temperature sufficient to cure said polymer in said spaces.

10. A method according to claim 9, wherein said particles are formed from the group consisting of Cu, Ni, Au, Ag, Al, Pd, and Pt.

11. A method for forming electroconductive connections between electroconductive materials, comprising the steps of:

providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, said thermoplastic polymeric material being selected from the group consisting of polyimide, siloxane, polyimide siloxane, and bio-based polymeric resins derived from lignin, cellulose, wood oil

and crop oil, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

disposing said paste between a first and a second electrically conductive surfaces;

heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and

heating said paste to a second temperature sufficient to cure said polymer in said spaces.

12. A structure for forming electroconductive connections between electroconductive members, comprising:

particles of copper, each particle having a coating selected from the group consisting of Sn and In;

at least some of said particles being fused to other said particles through said coating and embedded within a thermoplastic polymer precursor and a solvent, wherein said particles are from about 30% to about 90% by weight of said structure.

13. A method according to claim 9, further including pressing said first surface towards said second surface.

14. A method for forming electroconductive connections between electroconductive materials, comprising the steps of:

providing a paste of particles, each particle having an electrically conductive coating thereon, embedded within a thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

disposing said paste between a first and a second electrically conductive surfaces;

heating said paste to a first temperature sufficient to fuse said coating on adjacent particles to form a network of interconnected particles with spaces therebetween; and

heating said paste to a second temperature sufficient to cure said polymer in said spaces; and

wherein said first temperature and said second temperature are from about 150 degrees C to about 250 degrees C.

15. A composition for forming electroconductive connections between electroconductive materials, comprising a plurality of particles, each particle having an electrically conductive coating, and a thermoplastic polymeric material, wherein said particles are from about 30% to about 90% by weight of said composition.

18a

16. A composition according to claim 15, wherein said electrically conductive coating has a melting temperature less than that of said particle.

17. A composition according to claim 16, wherein said polymeric material is a curable thermoplastic material.

18. A composition according to claim 16, wherein said thermoplastic polymeric material is a curable thermoplastic material.

19. A composition according to claim 15, wherein said particle has a size distribution of 2 μm to 8 μm in diameter.

20. A structure comprising:

a plurality of particles of a first thermoplastic polymeric material, wherein said particles are from 30% to 90% by weight of said structure;

each of said plurality of particles has an electrically conductive coating of a second material which is different than said first material and has a lower melting temperature than said first material, said electrically conductive coating on at least some of said particles are fused directly to said electrically conductive coating on others of said particles, and said particles are embedded within a thermoplastic polymeric material.

21. A structure comprising:

a network of interconnected particles of a thermoplastic polymeric first material having a thermoplastic polymeric material therebetween, wherein said particles are from 30% to 90% by weight of said structure;

each of said particles has a coating thereon of a fusible material, said fusible material is different than said first material and has a lower melting temperature than said first material;

adjacent particles in said network are adhered together through said fusible material, said coating on one of said adjacent particles being directly fused to said coating on another of said adjacent particles.

22. A solder-particle-free method comprising the steps of:

providing a paste of particles of a first material having an electrically conductive coating of a second material thereon embedded within a thermoplastic polymeric material, said second material is different than said first material and has a lower melting temperature than said first material, wherein said particles are from 30% to 90% by weight of said particles and said thermoplastic polymeric material;

disposing said paste between a first and second electrically conductive surface;

18b

heating said paste to a first temperature sufficient to directly fuse said coating on one of said particles to said coating on another of said particles to form a network of interconnected particles with spaces therebetween.

23. A structure comprising:

particles of copper having a surface, and substantial portion of which has a continuous electrically conductive coating selected from the group consisting of Sn and In;

said particles are contained within a thermoplastic polymer precursor and a solvent, wherein said particles are from 30% to 90% by weight of said structure.

24. A structure comprising:

a copper powder having a surface, a substantial portion of which is coated with a layer of electrically conductive material selected from the group consisting of Sn, In, Bi, Sb and combinations thereof mixed with a fluxing agent, when mixed with a thermoplastic polymeric material in a 30% to 90% ratio by weight.