



(51) International Patent Classification:
H01M 10/54 (2006.01) *H01M 4/62* (2006.01)
H01M 4/00 (2006.01)

(21) International Application Number:
PCT/CN2021/080681

(22) International Filing Date:
15 March 2021 (15.03.2021)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
PCT/CN2020/096672
17 June 2020 (17.06.2020) CN
PCT/CN2020/110065
19 August 2020 (19.08.2020) CN
PCT/CN2020/117789
25 September 2020 (25.09.2020) CN

(71) Applicant: **GUANGDONG HAOZHI TECHNOLOGY CO. LIMITED** [CN/CN]; No. 21-8 Xinhui Road, Wusha

Neighborhood Committee, Daliang, Shunde District, Foshan, Guangdong 528300 (CN).

(72) Inventors: **HO, Kam Piu**; Unit 212, 2/F, Photonics Centre, No. 2 Science Park East Avenue, Hong Kong Science Park, Shatin, New Territories, Hong Kong (CN). **JIANG, Yingkai**; Unit 212, 2/F, Photonics Centre, No. 2 Science Park East Avenue, Hong Kong Science Park, Shatin, New Territories, Hong Kong (CN). **DONG, Yangjian**; No. 21-8 Xinhui Road, Wusha Neighborhood Committee, Daliang, Shunde District, Foshan, Guangdong 528300 (CN).

(81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DJ, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, IT, JO, JP, KE, KG, KH, KN, KP, KR, KW, KZ, LA, LC, LK, LR, LS, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW,

(54) Title: METHOD FOR COMPOSITE DELAMINATION




Figure 3

(57) **Abstract:** The invention provides a method for delaminating a composite by immersing the composite into a delamination solution; wherein the composite comprises a metal substrate and a coating applied on one side or both sides of the metal substrate, wherein the coating comprises a polymeric binder; and wherein the polymeric binder comprises an aqueous copolymer. The use of delamination solution comprising a strong base allows for complete delamination of the composite in a highly efficient and extremely fast manner. Furthermore, the delamination method disclosed herein circumvents complex separation processes, contamination and corrosion of the metal substrate and enables an excellent materials recovery. An application of the method for delaminating an electrode for a battery is disclosed herein.

SA, SC, SD, SE, SG, SK, SL, ST, SV, SY, TH, TJ, TM, TN,
TR, TT, TZ, UA, UG, US, UZ, VC, VN, WS, ZA, ZM, ZW.

(84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, ST, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))