

[Abstract of the disclosure]

CURABLE EPOXY RESIN COMPOSITION

To provide a curable epoxy resin composition that exhibits excellent fluidity during molding without having adverse effects on the physical properties of the cured material. A curable epoxy resin composition, containing (I) a curable epoxy resin, and (II) an epoxy functional group- and aromatic hydrocarbon group-containing organopolysiloxane having an epoxy equivalent weight of 3,000 or lower, a content of aromatic hydrocarbon groups of 45 to 80% by weight (mass), and a glass transition point of less than 0°C.