WHAT IS CLAIMED IS:

1. An epoxy resin composition comprising:

(a) an epoxy resin component comprising at least one epoxy resin; and

(b) a solvent blend comprising methyl ethyl ketone in an amount of no greater than ~~30~~ 20 weight percent and propylene glycol methyl ether acetate in an amount of at least ~~70~~ 80 weight percent, based on the total weight of the solvent blend;

the composition having an epoxy resin content of at least 70 weight percent, based on the solids content of the composition and a storage stability of at least 130 days at 21 °C.

2. The composition of claim 1, in which the epoxy resin component comprises a brominated epoxy resin and a functionalized epoxy resin.

3. The composition of claim 1, in which the solvent blend comprises ~~from 75 to~~ 85 weight percent propylene glycol methyl ether acetate and ~~from~~ 15 ~~to 25~~ weight percent methyl ethyl ketone.

4. The composition of claim 3 having an epoxy resin content of at least 80 weight percent.

5. The composition of claim 1 having an epoxy resin content of at least 75 weight percent, based on the solids content of the composition, and a storage stability of at least 150 days at 21 °C, the solvent blend comprising no greater than about ~~25~~ 20 weight percent methyl ether ketone and at least ~~75~~ 80 weight percent propylene glycol methyl ether acetate.

6. The composition of claim 1 having an epoxy resin content of at least ~~85~~ 80 weight percent, based on the solids content of the composition, and a storage stability of at least 200 days at 21 °C.

~~7. The composition of claim 2, having an epoxy content of at least 85 weight percent, based on the solids content of the composition, and a storage stability of at least 200 days at 21 °C, the solvent blend comprising at least 60 weight percent propylene glycol methyl ether acetate and no greater than 40 weight percent methyl ethyl ketone.~~

~~8. The composition of claim 7, comprising from 75 to 85 weight percent propylene glycol methyl ether acetate and from 15 to 25 weight percent methyl ethyl ketone.~~

~~9~~ 7. A varnish comprising:

(a) a curing agent;

(b) a curing catalyst; and

(c) the epoxy resin composition of claim 1.

~~10~~ 8. The varnish of claim ~~9~~ 7 having a viscosity of no greater than ~~4000 cPs~~ 4Pa*s at 25 °C.

~~11~~ 9. A method of forming a composite, the method comprising impregnating a porous reinforcement material with the varnish of claim ~~9~~ 8 and at least partially curing the impregnated fibrous reinforcement material.