

SPECIFICATION
RARE-EARTH COMPLEXES

TECHNICAL FIELD

The present invention relates to rare-earth
5 complexes, ligands useful for these complexes, optically
functional materials comprising the rare-earth complex, and
a process for preparing the rare-earth complex.

BACKGROUND ART

With remarkable advances in developing electronic
10 materials, many developments have been made in optically
functional materials in the field of optoelectronics. For
example, neodymium-containing glass has been introduced
into actual use in laser beam electronic devices, whereas
the glass has found only limited use because of the
15 difficulties encountered in producing and working the glass
and a high production cost. The dye laser, which can be
used in the form of a solution, has the excellent features
of being inexpensive, easy to work and cool and
continuously usable for a prolonged period of time.
20 However, the dye laser is low in strength and therefore
limited in application.

On the other hand, organic optical materials such
as polyphenylene have the drawback of being short in
luminescence life and diminished in the effectiveness of

luminescence although superior to inorganic optical materials in workability.

It is already known that a complex $[\text{Nd}^{\text{III}}(\text{HFA})_3]$ comprising Nd^{3+} and three molecules of hexafluoroacetylacetone (HFA) coordinated therewith and having heavy hydrogen substituted for the hydrogen of active methylene luminesces in the state of a solution [S. Yanagida et al., J. Phys. Chem., 100, 10201(1996)]. This complex is short in luminescence life and low in quantum yield and decomposes in the presence of a very small amount of water to lose its optical conversion function. It has therefore been desired to develop complexes having a high luminescence intensity and good stability.

An object of the present invention is to provide rare-earth complexes having excellent luminescence characteristics, compounds useful as ligands for these complexes, optically functional materials containing the rare-earth complex and a process for preparing such rare-earth complexes.

BRIEF DESCRIPTION OF THE DRAWINGS

FIG. 1 shows ^{13}C -NMR spectra of (a) POS and (b) $\text{Nd}(\text{POS})_3$.

FIG. 2 shows an absorption spectrum of $\text{Nd}(\text{POS})_3$ in CD_3OD .


FIG. 3 is a luminescence spectrum of $\text{Nd}(\text{POS})_3$ in

acetone-d₆.

DISCLOSURE OF THE INVENTION

The present invention relates to rare-earth complexes given below, compounds useful as ligands for these complexes, optically functional materials containing the rare-earth complex, and a process for preparing the rare-earth complex.


Item 1. An optically functional material comprising a rare-earth complex represented by the formula (I)



wherein M is a rare-earth atom, n₁ is 2 or 3, n₂ is 2, 3 or 4, R's are the same or different and are each a C₁-C₂₀ group containing no hydrogen atoms, X is a Group IVA atom other than carbon atom, Group VA atom other than nitrogen or Group VIA atom other than oxygen, n₃ is 0 or 1, and Y is C-Z' (wherein Z' is heavy hydrogen, a halogen atom or C₁-C₂₀ group containing no hydrogen atoms), N, P, As, Sb or Bi, or by the formula (II)




-4-



wherein M, R, X, n_1 , n_2 and n_3 are as defined above.

Item 2. A rare-earth complex represented by the formula


(I)



wherein M, R, X, n_1 , n_2 and n_3 are as defined above.

5 Item 3. A rare-earth complex represented by the formula

(IIa)



wherein R', X and n_3 are as defined above.


Item 4. A method of causing luminescence of rare-earth



-5-


complexes comprising the step of irradiating a solvent solution, dispersion or suspension of a rare-earth complex according to Item 2 or 3 with light.

Item 5. A compound represented by the formula (III)



- 5 wherein X, Y', R and n_3 are as defined above except where the two R's are each CF_3 , and where one of the R's is CF_3 and the other R is C_4F_9 .

Item 6. A process for preparing a rare-earth complex represented by the formula (I):



- 10 wherein M, R, X, n_1 , n_2 and n_3 are as defined above, the process comprising mixing together a compound represented by the formula (III)

wherein X, Y', R and n_3 are as defined above and at least one rare-earth metal compound selected from the group consisting of a rare-earth metal oxide, rare-earth metal alkoxide, rare-earth metal amide and rare-earth metal salt (and further mixing the resulting complex in D_2O , CD_3OD or like solvent permitting heavy hydrogen substitution when Y' is CH).

10 Item A. An optically functional material according to
Item 1, a rare-earth complex according to Item 2 or 3, or
a compound according to Item 5 wherein R is perhalogenated
alkyl or perhalogenated alkenyl having one or a plurality
of -O-, -COO-, -OCO- and -CO- interposed between a C-C
15 single bond thereof in an optional position to give an
ether, ester or ketone structure.

Item B. An optically functional material according to Item 1, a rare-earth complex according to Item 2 or 3, or a compound according to Item 5 wherein R is perfluorinated alkyl or perfluorinated alkenyl.

Item C. An optically functional material according to Item 1, a rare-earth complex according to Item 2 or 3, or a compound according to Item 5 wherein X is S, P or Se, and n_3 is 1.

- 5 Item D. An optically functional material according to Item 1, or a rare-earth complex according to Item 2 or 3 wherein M is Nd, Yb, Tb or Eu.

Item E. An optically functional material according to Item 1, or a rare-earth complex according to Item 2 or 3
10 wherein Y is C-D, C-Cl, C-F, C-Br, C-I, N or P.

Item F. An optically functional material according to Item 1, a rare-earth complex according to Item 2 or 3, or a compound according to Item 5 wherein R is perhalogenated alkyl or perhalogenated alkenyl.

- 15 Item G. A compound according to Item 5 wherein Y' is CH, N or P.

According to the invention, examples of C_1-C_{20} groups represented by R and containing no hydrogen atoms are:

- 20 * straight-chain or branched perhalogenated alkyl groups such as perfluoroalkyl (C_nF_{2n+1} ; $n=1-20$) and perchloroalkyl (C_nCl_{2n+1} ; $n=1-20$),
* straight-chain or branched C_2-C_{20} perhalogenated alkenyl groups such as perfluoroalkenyl (perfluorovinyl,
25 perfluoroallyl, perfluorobutenyl, etc.) and

perchloroalkenyl,

* straight-chain or branched C_2-C_{20} perhalogenated alkynyl groups such as perfluoroalkynyl and perchloroalkynyl,

* C_3-C_{20} perhalogenated cycloalkyl groups such as
5 perfluorocycloalkyl (C_nF_{2n-1} ; $n=3-20$) and perchlorocycloalkyl (C_nCl_{2n-1} ; $n=3-20$),

* C_3-C_{20} perhalogenated cycloalkenyl groups such as perfluorocycloalkenyl (perfluorocyclopentenyl, perfluorocyclohexenyl, etc.) and perchlorocycloalkenyl,

10 * C_6-C_{20} perhalogenated aromatic groups such as perfluorophenyl, perchlorophenyl, perfluoronaphthyl, perchloronaphthyl and perhalogenated biphenyl,

* C_6-C_{20} perhalogenated heteroaromatic groups such as perfluoropyridyl and perfluoropiperazinyl, and

15 * perhalogenated aralkyl groups such as perfluorobenzyl and perfluorophenethyl.

When required, the rare-earth complex of the formula (I) or (II) wherein R is perfluoroalkenyl may be polymerized with a perfluoroolefin having 1 to 20 carbon
20 atoms, such as tetrafluoroethylene or hexafluoropropylene, to obtain a high-molecular-weight rare-earth complex.

One or more halogen atoms attached to the aromatic ring of the above-mentioned perhalogenated aromatic group, perhalogenated heteroaromatic group or
25 perhalogenated aralkyl group may be replaced by a

substituent containing no hydrogen atoms, such as cyano, nitro, nitroso, C_1-C_4 perhalogenated alkoxyl, C_2-C_5 perhalogenated alkoxycarbonyl or C_2-C_{20} perhalogenated alkylcarbonyloxy.

5 The C_1-C_{20} perhalogenated alkyl, C_2-C_{20} perhalogenated alkenyl or C_2-C_{20} perhalogenated alkynyl may have one or a plurality of -O-, -COO- and -CO- interposed between a C-C single bond thereof in an optional position to give an ether, ester or ketone structure.

10 Examples of rare-earth elements represented by M are the elements of the lanthanum series, i.e., La, Ce, Pr, Nd, Pm, Sm, Eu, Gd, Tb, Dy, Ho, Er, Tm, Yb and Lu, among which preferable are Nd, Eu, Tb and Yb.

15 X is one of Group IVA atoms such as Si, Ge, Sn and Pb, Group VA atoms other than N and including P, As, Sb and Bi, and Group VIA atoms other than O and including S, Se, Te and Po, and is preferably S, P or Se. Y is N, P, As, Sb or Bi, and is preferably N or P.


n_1 is 2 or 3, preferably 3.

20 n_2 is 2 to 4, preferably 2 or 3, more preferably 3.

n_3 is 0 or 1, preferably 1. n_3 is 1 especially when X is S.

25 The ligand of the formula (III) to be incorporated into the complex of the invention is prepared,

for example, in the following manner.



wherein R, X, Y and n_1 are as defined above.

A compound (2) is reacted with
 5 hexamethyldisilazane for trimethylsilylation, and the
 resulting compound is reacted with a compound (1) to obtain
 the desired compound of the formula (III). The reaction
 proceeds favorably when effected for about 1 to about 5
 hours at room temperature to a temperature generally
 10 permitting reflux of the solvent, using about 1 to about
 1.1 moles of hexamethyldisilazane and about 1 mole of the
 compound (1) are used per mole of the compound (2).

The complex of the present invention represented
 by the formula (I) can be prepared by mixing together the
 15 compound represented by the formula (III) and at least one
 rare-earth metal compound selected from the group
 consisting of a rare-earth metal oxide, rare-earth metal
 hydroxide, rare-earth metal alkoxide, rare-earth metal
 amide and rare-earth metal salt, for example, in a
 20 solvent.

More specifically, the rare-earth complex represented by the formula (I) can be prepared by the process to be described below.

The ligand of the formula (III) is dissolved in
5 a solvent, the rare-earth metal compound (particulate, granular or in any other form) is added to the solution, and the mixture is stirred at room temperature to 100° C for about 1 hour to about 100 hours. The product is then purified as by crystallization or liquid-liquid extraction,
10 whereby the rare-earth complex can be obtained. The complex may further be recrystallized from a solvent such as chloroform or methanol.

Examples of rare-earth metal oxides useful as rare-earth metal compounds are trivalent compounds M_2O_3 ,
15 (wherein M is a rare-earth atom), while other oxides such as MO and M_4O_7 are also usable. Similarly, examples of rare-earth metal hydroxides include $M(OH)_{n_1}$; examples of rare-earth metal alkoxides include $M(OR^1)_{n_1}$ (wherein R^1 is alkyl); examples of rare-earth metal amides include $M(NR^aR^b)_3$,
20 (wherein R^a and R^b are the same or different and are each hydrogen, alkyl or phenyl); and examples of rare-earth metal salts include $M^{3+}(Z)_{n_1}$ (wherein Z is an anion such as chlorine ion, bromine ion, iodine ion, fluorine ion, 1/2 sulfate ion, nitrate ion, acetate ion or like
25 monocarboxylate ion, 1/2 (oxalate ion, succinate ion,

malonate ion or like dicarboxylate ion), $1/3$ (citrate or like tricarboxylate ion) or $1/3$ phosphate ion}. n_1 is as defined above.

The solvent to be used in preparing the complex
5 of the formula (I) is not limited specifically but can be any solvent such as a protic solvent or aprotic solvent. Examples of useful protic solvents are water and alcoholic solvents such as methanol and ethanol. Examples of useful aprotic solvents are acetone, methyl ethyl ketone and like
10 ketone solvents, diethyl ether, tetrahydrofuran and like ether solvents, chloroform, methylene chloride and like halogen solvents, DMSO, DMF, etc. Preferable among these is water. The solvent is used in an amount, for example, of about 1 to about 100 parts by weight, preferably about
15 1 to about 20 parts by weight, relative to the combined amount of the ligand and the rare-earth metal compound (taken as 1 part by weight).

The complex of the formula (II) can be obtained by reacting the rare-earth metal compound with an
20 equivalent or excess of $R-X(=O)n_3+1(OH)$, which is a known substance, in water. The complex of the formula (II) is susceptible to coordination with H_2O , loses the properties for use as an optically functional material when having coordinated H_2O and is therefore less stable to H_2O than the
25 complex of the formula (I). If incorporating coordinated

H₂O, the complex of the formula (II) can be treated with D₂O when to be used to remove the H₂O for use as an optically functional material.

The rare-earth metal compound is used for
5 preparing the rare-earth complex of the formula (I) in an amount of 1 to 10 equivalents, preferably 1.05 to 3 equivalents, per equivalent of the ligand of the formula (III). The rare-earth complex of the formula (II) can be prepared from the compounds mentioned as used in a similar
10 mixing ratio.

In the case where the rare-earth complex represented by the formula (II) contains coordinated water, the complex is treated, for example, in the following manner. MeOD is added to a sample of the complex, the
15 sample/MeOD mixture is frozen and then allowed to stand in a vacuum at room temperature for about 24 hours, and the methanol is subsequently distilled off to convert the coordinated H₂O to D₂O. The complex sample substituted with heavy hydrogen is thereafter dissolved in a dry organic
20 solvent containing no hydrogen atoms (with all hydrogen atoms replaced by heavy hydrogen, halogen atoms or the like) for use as an optically functional material. Organic solvents containing heavy hydrogen, such as DMSO, methanol, acetone, THF, DMF and chloroform which are substituted with
25 heavy hydrogen, or hydrogen-free solvents such as carbon

tetrachloride are desirable since these solvents give complex a prolonged luminescence life.

The rare-earth complex represented by the formula (I) is especially preferable since the complex is usable as dissolved directly in a dry solvent containing no hydrogen atoms without necessitating any procedure for converting coordinated H_2O to D_2O . On the other hand, the rare-earth complex represented by the formula (II) requires the conversion of the coordinated H_2O to D_2O .

Examples of solvents for use in the luminescence method of the invention for dissolving the complex of the formula (I) are ketone compounds such as acetone and methyl ethyl ketone, lower alcohols such as methanol and ethanol, water, ethers such as ether, THF, isopropyl ether, aromatic hydrocarbons such as benzene and toluene, hydrocarbon halides such as chloroform, carbon tetrachloride and tetrachloroethane, DMF, DMSO, acetamide, formamide and esters such as ethyl acetate, glycols such as ethylene glycol and propylene glycol, etc.

The solvent may be one containing hydrogen atoms such as DMSO or acetone, whereas organic solvents containing heavy hydrogen, such as DMSO, methanol, acetone, THF, DMF and chloroform which are substituted with heavy hydrogen, or hydrogen-free solvents such as carbon tetrachloride are desirable since these solvents give

complex a prolonged luminescence life.

In place of the organic dye of an organic dye laser, the rare-earth complex of the present invention is usable as an optically functional material (element,
5 electronic device or the like) under the same conditions as the organic dye laser. For example, the rare-earth complex of the invention is usable as dissolved, dispersed or suspended in a solvent under the specified conditions as to concentration (about 0.00001 to about 1 mole/liter,
10 preferably about 0.005 to about 0.5 mole/liter, more preferably about 0.01 to about 0.3 mole/liter) and temperature (-50° C to room temperature).

Although usable in the form of a liquid, the complex of the invention can also be used as an optically
15 functional material in a solid state, for example, as dissolved or dispersed in a polymer.

The complex of the present invention achieves a high optical conversion efficiency and is useful as a novel laser material for use in optical devices such as CD
20 players, optical disks, facsimile systems, remote controllers, copying machines, laser printers, large-sized displays, medical lasers, laser beam machining and measuring means and devices relating to printing. Stated more specifically, the complex is applicable to laser
25 devices, light-emitting diodes, liquid crystals, optical

fibers, optical sensors, solar cells, etc.

The complex of the invention can be adapted to alter the wavelength of the laser beam when modified or changed in the structure of ligand and/or in the kind of rare-earth element, affording a laser for giving a beam of desired wavelength. Unlike semiconductors, the complex of the invention can be used for preparing laser materials by a greatly simplified process without necessitating a clean room or the like.

10 THE BEST MODE FOR CARRYING OUT THE INVENTION

The present invention will be described below in detail with reference to Examples, to which the invention is not limited.

Example 1

15 Preparation of $C_6F_{13}SO_2NHSO_2C_6F_{13}$ (PHS)

To 18 mmoles of $C_6F_{13}SO_2NHNa$ was added dropwise $[(CH_3)_3Si]_2NH$ (18 ml, 86.5 mmoles) in a nitrogen atmosphere. With addition of 2 ml of dioxane, the mixture was refluxed at $120^\circ C$ for 8 hours, and the $[(CH_3)_3Si]_2NH$ was distilled off, followed by drying in a vacuum for 12 hours. A 30 ml quantity of dry acetonitrile and $C_6F_{13}SO_2F$ (21 mmoles) were added to the mixture, and the resulting mixture was refluxed at $100^\circ C$ for 48 hours. The acetonitrile was thereafter distilled off, and sulfuric acid was used for protonation, followed by extraction with ether and

sublimation, giving the desired product (a white solid, 30% in yield).

IR (cm^{-1}): 1369 (S=Ost.), 1237 (C-Fst.), 1208 (C-Fst.), 1152 (S=Ost.)

5 ^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):
-79.51 (3F), -111.65 (2F), -118.56 (2F), -120.27 (2F),
-121.21 (2F), -124.67 (2F)

MS (m/z): 780 ($[\text{C}_6\text{F}_{13}\text{SO}_2]_2\text{N}^-$, very strong)

Elemental analysis ($\text{C}_{12}\text{H}_2\text{O}_4\text{N}_2\text{F}_{26}$)

10		C	H	N
	Calculated	18.45	0.13	1.79
	Found	18.45	0.08	2.05

Example 2

Preparation of $\text{C}_8\text{F}_{17}\text{SO}_2\text{NHSO}_2\text{C}_8\text{F}_{17}$ (POS)

15 $\text{C}_8\text{F}_{17}\text{SO}_2\text{NHSO}_2\text{C}_8\text{F}_{17}$ (white solid, 12% in yield) was prepared in the same manner as in Example 1 with the exception of using $\text{C}_8\text{F}_{17}\text{SO}_2\text{NHNa}$ and $\text{C}_8\text{F}_{17}\text{SO}_2\text{F}$ in place of $\text{C}_6\text{F}_{13}\text{SO}_2\text{NHNa}$ and $\text{C}_6\text{F}_{13}\text{SO}_2\text{F}$, respectively.

IR (cm^{-1}): 1373 (S=Ost.), 1237 (C-Fst.), 1206 (C-Fst.), 1151

20 (S=Ost.)

^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):

-79.51 (3F), -111.59 (2F), -118.43 (2F), -120.10 (6F),
-121.06 (2F), -124.59 (2F)

Example 3

25 Preparation of $\text{C}_4\text{F}_9\text{SO}_2\text{NHSO}_2\text{C}_4\text{F}_9$ (PBS)

$C_4F_9SO_2NHSO_2C_4F_9$ (white solid, 26% in yield) was prepared in the same manner as in Example 1 with the exception of using $C_4F_9SO_2NHNa$ and $C_4F_9SO_2F$ in place of $C_6F_{13}SO_2NHNa$ and $C_6F_{13}SO_2F$, respectively.

5 IR (cm^{-1}): 1373 (S=Ost.), 1237 (C-Fst.), 1206 (C-Fst.), 1151 (S=Ost.)

^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):

-79.31 (6F), -111.47 (4F), -119.18 (4F), -124.19 (4F)

Example 4

10 Preparation of $C_8F_{17}SO_2NHSO_2C_4F_9$ (POBS)

To 18 mmoles of $C_9F_{17}SO_2NHNa$ was added dropwise $[(CH_3)_3Si]_2NH$ (18 ml, 86.5 mmoles) in a nitrogen atmosphere. With addition of 2 ml of dioxane, the mixture was refluxed at 120° C for 8 hours, and the $[(CH_3)_3Si]_2NH$ was distilled
15 off, followed by drying in a vacuum for 12 hours. A 30 ml quantity of dry acetonitrile and $C_4F_9SO_2F$ (21 mmoles) were added to the mixture, and the resulting mixture was refluxed at 100° C for 48 hours. The acetonitrile was thereafter distilled off, and sulfuric acid was used for
20 protonation, followed by extraction with ether and sublimation, giving the desired product (a white solid, 10% in yield).

IR (cm^{-1}): 1369 (S=Ost.), 1237 (C-Fst.), 1208 (C-Fst.), 1152 (S=Ost.)

25 Example 5

Preparation of $\text{Nd}(\text{POS})_3$ complex

The $\text{C}_8\text{F}_{17}\text{SO}_2\text{NHSO}_2\text{C}_8\text{F}_{17}$ (0.8 g, 0.82 mmole) obtained in Example 2 was dissolved in 30 ml of distilled water, Nd_2O_3 (46 mg, 0.14 mmole) was added to the solution, and the mixture was stirred at room temperature for 3 days. The resulting solid precipitate was filtered off, washed with water and dissolved in methanol, followed by centrifuging and filtration to remove the unreacted Nd_2O_3 . The methanol was removed from the product by distillation, affording the desired complex ($\text{Nd}(\text{POS})_3$; white solid). The complex obtained was found to be free from water by differential thermal analysis (DSC).

IR (cm^{-1}): 3449 (O-Hst.), 1368 (S=Ost.), 1237 (C-Fst.), 1150 (S=Ost.)

^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):
-79.33 (3F), -111.24 (2F), -118.07 (2F), -119.81 (6F),
-120.78 (2F), -124.29 (2F)

FIG. 1 shows ^{13}C -NMR spectra.

The two signals around 140 ppm in FIG. 1, (b) $\text{Nd}(\text{POS})_3$ indicate CF_2 adjacent to S subjected to resonance.

FIG. 2 shows the absorption spectrum of $\text{Nd}(\text{POS})_3$ in heavy methanol.

Incidentally, $\text{Nd}(\text{PHS})_3$ complex is obtained in the same manner as above with the exception of using

$C_6F_{13}SO_2NHSO_2C_6F_{13}$ obtained in Example 1 in place of $C_8F_{17}SO_2NHSO_2C_8F_{17}$ prepared in Example 2.

Further the use of $C_4F_9SO_2NHSO_2C_4F_9$ obtained in Example 3 or $C_8F_{17}SO_2NHSO_2C_4F_9$ obtained in Example 4 affords
5 $Nd(PBS)_3$ complex or $Nd(POBS)_3$ complex.

Example 6

Preparation of $Eu(POS)_3$ complex

The $C_8F_{17}SO_2NHSO_2C_8F_{17}$ (0.8 g, 0.82 mmole) obtained in Example 2 was dissolved in 30 ml of distilled water,
10 Eu_2O_3 (50 mg, 0.14 mmole) was added to the solution, and the mixture was stirred at room temperature for 3 days. The resulting solid precipitate was filtered off, washed with water and dissolved in methanol, followed by centrifuging and filtration to remove the unreacted Eu_2O_3 . The methanol
15 was removed from the product by distillation, affording the desired complex ($Eu(POS)_3$; white solid). The complex obtained was found to be free from water by differential thermal analysis (DSC).

IR (cm^{-1}): 1354 (S=Ost.), 1237 (C-Fst.), 1209 (S-Fst.), 1056
20 (S=Ost.)

^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):

-79.2 (3F), -111.33 (2F), -118.15 (2F), -119.87 (4F), -
120.8 (2F), -124.29 (2F)

Example 7

25 Preparation of $Tb(POS)_3$ complex

The desired complex $\text{Tb}(\text{POS})_3$; white crystals) was prepared in the same manner as in Example 6 with the exception of using Tb_4O_7 (60 mg, 0.82 mmole) as the rare-earth metal compound. The complex obtained was found to be

free from water by differential thermal analysis (DSC).
IR (cm^{-1}): 1353 (S=Ost.), 1243 (C-Fst.), 1208 (C-Fst.), 1056 (S=Ost.)

^{19}F -NMR (acetone- d_6 , standard substance C_6F_6 ; ppm):

-79.3 (3F), -111.1 (2F), -118.0 (2F), -119.9 (4F),

-120.9 (2F), -124.4 (2F)

Example 8

Preparation of $\text{Nd}(\text{O}_3\text{SCF}_3)_3$

Nd_2O_3 (1 mole) was added to an aqueous solution of $\text{CF}_3\text{SO}_3\text{H}$ (2 moles), and the mixture was allowed to stand at room temperature, causing crystals to separate out. The crystals, which were reddish purple and needlelike, were filtered off and dried in a vacuum for 2 days, giving the desired $\text{Nd}(\text{O}_3\text{SCF}_3)_3$. TG-DTA revealed that the crystals obtained were a hexahydrate.

Elemental analysis ($\text{NdC}_3\text{H}_{12}\text{O}_{15}\text{F}_9\text{S}_3$)

	C	H
Calculated	5.15	1.73
Found	5.01	1.82

IR (cm^{-1}): 3449 (O-Hst.), 1638 (O-H δ), 1263 (C-Fst.), 1180 (S-Ost.)

¹⁹F-NMR (acetone-d₆, standard substance C₆F₆; ppm):

-77.03

Example 9

Preparation of Nd(O₃SC₈F₁₇)₃·6D₂O

5 A 30 ml quantity of 0.34M aqueous solution of
pentafluorooctanesulfonic acid was added to 0.56 g (1.72
mmoles) of Nd₂O₃, and the mixture was stirred at room
temperature for 24 hours to obtain a purple solid. The
solid product was filtered off, washed with water and
10 recrystallized from a chloroform-methanol solvent mixture,
giving purple needlelike crystals, which were then dried at
5 mm Hg for 2 days. Yield 30%. TG-DTA revealed that the
crystals obtained were a hexahydrate.

IR (cm⁻¹): 3432 (O-Hst.), 1637 (O-Hδ), 1241 (C-Fst.), 1204
15 (C-Fst.), 1152 (S-Ost.)

¹⁹F-NMR (acetone-d₆, standard substance C₆F₆; ppm):

-79.61 (3F), -112.85 (2F), -119.16 (2F), -120.30 (6F),
-121.19 (2F), -124.67 (2F)

The Nd(O₃SC₈F₁₇)₃·6H₂O (80 mg) obtained was
20 dissolved in CD₃OD (2.0 ml), and the solution was deaerated
at -78° C and further allowed to stand at room temperature
for 24 hours. Subsequently, the CD₃OD was distilled off,
giving Nd(O₃SC₈F₁₇)₃·6D₂O. The compound was found to contain
D₂O substituting for H₂O by H-NMR.

25 Experimental Example

Nd(POS)₃, Eu(POS)₃, Tb(POS)₃, Nd(PHS)₃, Nd(PBS) ,
Nd(POBS)₃ and Nd(O₃SC₈F₁₇)₃ were checked for luminescence
characteristics in acetone-d₆ or DMSO-d₆. Table 1 shows the
results. FIG. 3 shows the luminescence spectrum of Nd(POS)₃
5 in acetone-d₆.

Incidentally, Nd(CF₃CO-CD-COCF₃)₃ (hereinafter
referred to as Nd(HFA)₃) was prepared according to Chemical
Physics Letters, 248, pp. 8-12, 1996. The complexes were
used at a concentration of 0.05 mole/liter.

10 Table 1

Complex/solvent	Excitation wavelength (nm)	Luminescence wavelength (μm)	Quantum yield (%)	Luminescence life (μs)
15 Nd(POS) ₃ / acetone-d ₆	585	1.06	3.2	13
Eu(POS) ₃ / DMSO-d ₆	394	0.618	56.8	1500
Tb(POS) ₃ / acetone-d ₆	325	0.545	-	-
20 Nd(PHS) ₃ / acetone-d ₆	585	1.06	3.2	13
Nd(PBS) ₃ / acetone-d ₆	585	1.06	2.5	1
25 Nd(POBS) ₃ / acetone-d ₆	585	1.06	3.0	-
Nd(HFA) ₃ / acetone-d ₆	585	1.06	0.3	1.7
Nd(O ₃ SC ₈ F ₁₇) ₃ / DMSO-d ₆	585	1.06	3.4	15.3

30 The mark "-" indicates that no measurement was

made.

Experimental Example 2

Nd(POS)₃ was checked for luminescence characteristics in acetone. The complex concentration was
5 0.05 mole/liter. The result is as follows: excitation wavelength = 585 nm, luminescence wavelength = 1.06 μm, quantum yield = 3.0%, and luminescence life = 4 μs. The complex exhibited the same luminescence spectrum as shown in FIG. 3.


10 Table 1 reveals that the Nd complexes of the invention [Nd(POS)₃ and Nd(O₃SC₈F₁₇)₃] are higher in quantum yield and more excellent in luminescence characteristics for use as optically functional materials than the conventional complex [Nd(HFA)₃]. Experimental Example 2
15 further shows that the complex of the invention luminesces also in a solvent having hydrogen atoms. Like the Nd complexes, Eu, Tb and other rare-earth complexes also have outstanding luminescence characteristics.




-25-

CLAIMS

1. An optically functional material comprising a rare-earth complex represented by the formula (I)



wherein M is a rare-earth atom, n_1 is 2 or 3, n_2 is 2, 3 or 4, R's are the same or different and are each a $\text{C}_1\text{-C}_{20}$ group containing no hydrogen atoms, X is a Group IVA atom other than carbon atom, Group VA atom other than nitrogen or Group VIA atom other than oxygen, n_3 is 0 or 1, and Y is C-Z' (wherein Z' is heavy hydrogen, a halogen atom or $\text{C}_1\text{-C}_{20}$ group containing no hydrogen atoms), N, P, As, Sb or Bi, or by the formula (II)



wherein M, R, X, n_1 , n_2 and n_3 are as defined above.

2. A rare-earth complex represented by the


This Sheet Has Been Replaced






-26-

formula (I)



wherein M, R, X, n_1 , n_2 and n_3 are as defined above.

3. A rare-earth complex represented by the formula (IIa)



5 wherein R' is a $\text{C}_2\text{-C}_{20}$ group containing no hydrogen atoms, X and n_3 are as defined above.

4. A method of causing luminescence of rare-earth complexes comprising the step of irradiating a solvent solution, dispersion or suspension of a rare-earth complex
10 according to claim 2 or 3 with light.


5. A compound represented by the formula (III)

This Sheet Has Been Replaced






-27-



wherein X, R and n_3 are as defined above except where the two R's are each CF_3 , and where one of the R's is CF_3 and the other R is C_4F_9 , and Y' is $\text{C}-\text{Z}_1'$ (wherein Z_1' is hydrogen, heavy hydrogen, a halogen atom or C_1-C_{20} group containing no hydrogen atoms), N, P, As, Sb or Bi.

6. A process for preparing a rare-earth complex represented by the formula (I):




wherein M, R, X, Y, n_1 , n_2 and n_3 are as defined above, the process comprising mixing together a compound represented by the formula (III)

This Sheet Has Been Replaced





-28-



wherein X, Y', R and n_3 are as defined above and at least one rare-earth metal compound selected from the group consisting of a rare-earth metal oxide, rare-earth metal alkoxide, rare-earth metal amide and rare-earth metal salt
5 (and further mixing the resulting complex in D_2O , CD_3OD or like solvent permitting heavy hydrogen substitution when Y' is CH).

This Sheet Has Been Replaced

