



- 1 -

PNEUMATIC RADIAL TIRE HAVING TWO
NONMETALLIC CHIPPERS

Background of the Invention

5 The present invention relates to radial pneumatic tires and more specifically a radial pneumatic tire having two chippers comprised of nonmetallic reinforced plies.

10 Typically, radial city bus tires are subjected to high brake heat causing bead area durability problems. Failure in the bead area is attributed to the heat conducting properties of the metal cords in the bead area. Unfortunately, simple substitution of less heat conducting materials in place of this metal cord has
15 not been successful because such materials do not exhibit the high strength properties of metal cords needed for the bead area. Therefore, there exists a need for a tire construction which decreases the bead area durability problems caused by heat and provides
20 sufficient reinforcement in the bead area.

Summary of the Invention

 The present invention relates to a pneumatic tire comprising:

- 25 (a) a pair of axially spaced apart beads, each having a core;
- (b) one or more continuous carcass plies extending between the beads, each carcass ply comprising steel cords and each carcass ply having a
30 central portion and a lateral edge portion, each lateral edge portion being folded axially and radially outward around one of said beads;
- (c) a belt structure comprising a plurality of belt plies reinforced with steel or aramid cords
35 disposed radially outward of the carcass plies; and



- 2 -

(d) a first and second chipper which reinforce each bead and each chipper comprises a nonmetallic cord reinforced ply having two end points wherein

each chipper extends from a first end point
5 located on the axially outer side of the carcass ply in a region between the bead heel and 99 percent of the radial distance of the carcass ply end from said bead heel and said first end point of one chipper located on the axially outer side is located at a
10 different distance, from said bead heel, than the distance from said bead heel to the first end point of the other chipper,

each of said chippers extending around the bead to a second end point located on the axially
15 inner surface of the carcass ply above the bead line and said second end point of one chipper located on the axially inner surface is located at a different distance above said bead line than the distance above said bead line to the second end point of the other
20 chipper.

Brief Description of the Drawings

Figure 1 is a radial cross-sectional view of a tire according to the present invention.

25

Detailed Description of the Invention

The present invention may be better understood in the context of the following definitions which are applicable both to the specification and to the
30 appended claims:

"Air-impermeable rubber" means a rubber having an air-permeability less than 40% the air permeability of natural rubber. "Air-permeable rubber" means any
35 rubber that is not air-impermeable. Both air-impermeable and air-permeable rubbers can be reinforced.

"Aramid" means an aromatic polyamide. Aramid fibers generally have tensile strengths ranging from about 2.5 to 3.8 GPa and tensile modulus values ranging from about 50 to 170 GPa.

"Axial" and "axially" are used herein to refer to lines or directions that are parallel to the axis of rotation of the tire.

"Bead" means that part of the tire comprising an annular tensile member wrapped by ply cords and shaped.

"Bead line" means the plane perpendicular to the equatorial plane and passing between the top of each bead.

"Belt structure" means at least two layers or plies of parallel cords, woven or unwoven, underlying the tread, unanchored to the bead, and having both left and right cord angles in the range from 17 degrees to 27 degrees with respect to the equatorial plane of the tire.

"Butyl rubber" means rubber produced by copolymerizing isobutylene with small amounts of isoprene.

"Carbon fiber" is a high tensile fiber made from isotropic pitch, anisotropic pitch, rayon or polyacrylonitrile. The carbon fiber may have an amorphous structure which is resistant to acids and bases or a polycrystalline structure. Typical tensile modulus for carbon fibers range from 75 GPa to 650 GPa. Typical tensile strength values range from 1 GPa to 7 GPa.

"Halobutyl rubber" means halogenated butyl rubber, such as with chlorine or bromine.

"Casing" means the tire structure except the tread.

"Carcass" means the tire structure apart from the belt structure, tread, undertread, and sidewall rubber over the plies, but including the beads.

5 "Circumferential line" means a line tangent to the circle defined by a bead of the tire.

"Cord" means one of the reinforcement strands of which the plies in the tire are comprised.

10 "Cord angle", for a cord that crosses the equatorial plane, means the acute angle, left or right in a plan view of the tire, formed by a cord with respect to the equatorial plane. If the cord does not cross the equatorial plane, the "cord angle" means the acute angle formed by the cord with a circumferential line (circle) in the ply. The circumferential line
15 passes through the point at which the "cord angle" is to be measured and is contained in a plane parallel with the equatorial plane. The "left" or "right" orientation of a cord not passing through the equatorial plane is determined by what the orientation
20 would be were the cord to extend across such angle while remaining in the tire. The "cord angle" is measured in a cured but uninflated tire.

25 "Equatorial plane (EP)" means the plane perpendicular to the tire's axis of rotation and passing through the center of its tread.

"Liner" means the layer or layers of elastomer or other material that form the inside surface of a tubeless tire and that contain the inflating fluid within the tire.

30 "Nylon" is a polyamide polymer characterized by the presence of amide groups -CONH. Representative examples include nylon-66 and nylon-6. Nylon fibers generally have tensile strengths ranging from about 0.8 GPa to 1.8 GPa and tensile modulus values ranging
35 from about 10 GPa to 15 GPa.

"Ply", unless otherwise specified, means a continuous layer of rubber-coated parallel cords.

"Polyester" is a condensation polymer that is derived from a diol and a dicarboxylic acid wherein at least 90% of the dicarboxylic acid is terephthalic acid, naphthenic acid or mixtures thereof. Polyester fibers generally have tensile strengths ranging from about 0.8 GPa to 1.8 GPa and tensile strength values ranging from about 10 GPa to 15 GPa.

"Pneumatic tire" means a laminated mechanical device of generally toroidal shape (usually an open-torus) having beads and a tread and made of rubber, chemicals, fabric and steel or other materials. When mounted on the wheel of a motor vehicle, the tire through its tread provides traction and contains the fluid that sustains the vehicle load.

"Radial" and "radially" are used to mean directions radially toward or away from the axis of rotation of the tire.

"Rayon" is a semicrystalline fiber composed of regenerated cellulose including regenerated cellulose in which substituents have replaced not more than 15% of the hydrogens of the hydroxyl groups. Rayon fibers generally have tensile strengths ranging from about 0.5 GPa to 1.6 GPa and tensile modulus values ranging from about 30 GPa to 60 GPa.

"Sidewall" means that portion of a tire between the tread and the bead.

"Tread" means a molded rubber component which when bonded to a tire casing, includes that portion of the tire that comes into contact with the road when the tire is normally inflated and under normal load.

In Fig. 1, there is illustrated a pneumatic tire constructed in accordance with the present invention. The tire has a pair of axially-spaced apart annular tensile members or beads. The beads

are shown as wire filaments arranged in a hexagonal cross-section but this not believed to be essential to the invention and the beads could have been circular or of other well known cross-sections or could be manufactured of cables or other materials.

A circumferentially extending radially superimposed carcass ply 20 extends continuously between the beads 12. Each carcass ply has a central portion 22 disposed between the beads. Lateral edge portion 24 of the carcass ply is folded axially and radially outward around the respective beads. The lateral edge portion 24, also known as the carcass ply turn-up may extend anywhere from the point after which it is folded axially and radially outward around the bead 12 to a point ending at the belt structure 46. Steel is the preferred reinforcement for the carcass ply. The cords of the carcass ply are oriented at angles between 65° and 90° with respect to the equatorial plane (EP) of the tire. It is contemplated herein that more than one carcass ply such as two may be used. Preferably, the cords in the carcass ply 20 are oriented at 80° to 90° and if a second carcass ply is used, they are also oriented at 80° to 90° .

A liner 26 is disposed radially inwardly of the carcass ply 20. The edges 28 of the liner are disposed radially inwardly of the beads 12. The liner 26 is made of an air-impermeable material which offers high resistance to air permeation and can withstand levels of flexing in the sidewall area. The preferred material is a halobutyl rubber. Halobutyl rubber, whether chlorobutyl or bromobutyl, has proven to be more air-impermeable than natural or styrene butadiene rubber.

An apex 30 may be disposed between each bead 12 in the central portion 22 and the lateral edge portion 24 of the carcass ply 20. The apex 30 preferably is

unreinforced and is made of a resilient material. It acts as a stress transition component to disperse the stresses at the carcass ply ends and at the end of each chipper 32, 34. The apex also provides stiffness and stability in the lower sidewall area. Apexes can be made of stiffer material if a higher degree of lateral stiffness is required.

The pneumatic tire 10 of the present invention is characterized by having a first 32 and second 34 chipper. Each chipper 32, 34 is a nonmetallic cord reinforced ply which "insulates" the bead area from the high heat environment in which the tire is used. Representative of the nonmetallic materials include aramid, carbon fibers, nylon, polyester and rayon. For the purposes of the present invention, any nonmetallic cord material which has less heat conducting properties than steel but sufficient strength to be used in a chipper may be used. Preferably, the cord material is aramid or nylon. The most preferred chippers 32, 34 are made of aramid strands of aramid denier cord twisted together to form a single cord. The nonmetallic cord is arranged in a density (end count) equal to about 5 to about 50 cords per inch. Preferably, the cord is arranged in a density (end count) equal to about 15 to 20 cords per inch. The cord angle of the chippers may range from about 19° to about 40° with respect to the circumferential line. Preferably, the cord angle of the cords in the chippers range from 20° to 35°. The cords of the first and second chippers are oriented in opposite manners with respect to the circumferential line of the tire. The first 32 and second 34 chippers are adjacent to the carcass ply 22 which goes around the bead 12 innermost to the bead 12. The first chipper extends from a first end point located on the axially outer surface of the carcass ply 22 such as

indicated by "A". The first chipper 32 continues around the bead 12 to above the bead line "BL" to an axially inner position from end point "A" located on the axially inner surface of the carcass ply 22 as indicated by "B". The end point "A" is located on a radius R_1 which is between the bead heel and 99% of the radius R_2 to the carcass ply end 36, both radii being struck from the heel of the bead portion, as indicated by point "C". Preferably, the first end point "A" of first chipper 32 is located on a radius R_1 which is from 25 to 80% of the radius R_2 to the carcass ply end 36. A particularly preferred percentage is from 35% to 65%. End point "B" is located above the bead line "BL". Preferably, the second end point of each chipper terminates below or does not extend beyond the ply ending 36. Similar to the first chipper 32, the second chipper 34 extends from a first end point located on the axially outer side of the carcass ply 22 as indicated by end point "D". The second chipper 34 continues around the bead 12, to an axially inner position from end point "D" located above the bead line "BL" in the axially inner surface of the carcass 22 as indicated by end point "E". The end point "D" is located on a radius R_3 which is between the bead heel and 99% of the radius R_2 to the carcass ply end 36, both radii being struck from "C". Whereas both ends A and D must fall within the region from the bead heel and the above percentage of the radius R_2 , each first end point A, D should be a different distance from the bead heel C. Stated another way, the end points A, D of the two chippers 32 and 34 are staggered in their distance from the bead heel C. As shown in Fig. 1, it is preferred, but not required that the first end point A of the inner chipper be longer from the bead heel point C than the first end point D of the outer chipper 34 from point

C. Inner chipper, as referred to herein, relates to the chipper closest to the bead. Outer chipper is the chipper that is on the opposite side of the bead from the inner chipper. From the bead heel C, the distance to the first end point D of the shorter chipper should be from about 40% to about 80% of the distance from the bead heel C to the first end point A of the longer chipper. Preferably, the percentage ranges from about 50 to about 70 percent. The second end points B and E of chippers 32 and 34 should be at a different distance above the bead line. As shown in Fig. 1, it is preferred but not required that the second end point E of the outer chipper 34 be a greater distance above the bead line than the distance between the second end point B of the inner chipper 32 and the bead line. From the bead line, the distance to the second end point B of the shorter chipper 32 should be from about 40 to about 80 percent of the distance from the bead line to the second end point of the longer chipper. Preferably, the percentage ranges from about 50 to about 70.

An essential aspect of the present invention is a tire having a first and second chipper as described above. If a tire has been constructed having such first and second chippers, it is contemplated herein that supplemental reinforcement or heat shielding devices may be used, such as additional chippers or flippers.

The flipper 38 may be a reinforced ply or gum strip which locks the beads 12 to the apex 30 and provide rigidity to the lower bead and sidewall area. The flipper 38 can be reinforced with a cord material like that used for the chippers 32, 34 or a square woven material can instead be used. The reinforcement may be made of aramid, rayon, nylon and polyester or other such reinforcing materials. The use of a

flipper 38 is not believed to be necessary to practice the invention. In the preferred embodiment, a gum strip is used as a flipper.

5 The gum chafer 40 is formed of an unreinforced, gum located in the bead area of the tire and disposed between the liner 26 and the chippers 32, 34. The first edge 42 of the gum chafer 40 extends from a point radially outward in axially of one of the beads 12 to a second edge 44 disposed axially outwardly of the beads.

10 A belt structure 46 comprises a plurality of belt plies of the type well known in the art. The belt structure 46 is disposed radially outwardly of the carcass ply 20. Each of the belt plies is generally of the same construction. The belt plies are preferably reinforced with cords made of steel. The cord angle for the cords in the belt range from 16° to 28°. Preferably, the cord angle ranges from about 18° to 20°.

20 The sidewalls 48 of the tire 10 include outer elastomeric portions that extend radially inwardly from the belt structure 46 and the tread 50 to the bead portions of the tire. The sidewall is generally unreinforced and is manufactured of a rubber designed to resist chemical reactions to oxygen, ozone and sunlight and must be resilient and flexible to withstand the flexing of the tire under normal operating conditions. The tread 50 is made of an abrasion-resistant rubber designed to provide good wear and traction properties throughout the life of the tire. The tread is preferably grooved and formed with a tread design directed to optimizing traction and wear.

30 A tread skirt 52 is disposed between the lateral edges of the tread 50 and the sidewall 48. The tread

skirt is reinforced and is made of a rubber design to withstand a high degree of scuffing and flexing.

The present invention can best be understood by review of the following claims.



- 12 -

WHAT IS CLAIMED IS:

1. A pneumatic tire characterized by:
 - (a) a pair of axially spaced apart beads,
5 each having a core;
 - (b) one or more continuous carcass plies
extending between the beads, each carcass ply
comprising steel cords and each carcass ply having a
central portion and lateral edge portion, each lateral
10 edge portions being folded axially and radially
outwardly around one of said beads;
 - (c) a belt structure comprising a plurality
of belt plies reinforced with steel or aramid cords
disposed radially outward of the carcass plies;
 - 15 (d) a first and second chipper which
reinforce each bead and each chipper comprises a
nonmetallic cord reinforced ply having two points,
each chipper extends from a first end
point located on the axially outer side of the carcass
20 ply in a region between the bead heel and 99% of the
radial distance of the carcass ply end from said bead
heel and said first end point of one chipper located
on the axially outer side is located at a different
distance from said bead heel than the distance from
25 said bead heel to the first end of the other chipper,
each of said chippers extending around
the bead to a second end point located on the axially
inner surface of the carcass ply above the bead line
and said second end point of one chipper on the
30 axially inner surface is located at a different
distance above said bead line than the distance above
said bead line to the second end point of the other
chipper.
- 35 2. The pneumatic tire of claim 1 characterized
in that the distance from said second end point of





- 13 -

said first chipper to the bead line is from 40% to 80% of the distance from the bead line to the second end point of said second chipper.

5 3. The pneumatic tire of claim 1 characterized in that the cord angle of said first and second chipper ranges from 19° to 40° with respect to the circumferential line of the tire.

10 4. The pneumatic tire of claim 1 characterized in that said nonmetallic cord is selected from the group consisting of aramid, carbon fiber, nylon, polyester and rayon.

15 5. The pneumatic tire of claim 1 characterized in that each said chipper extends from a first end point located on the axially outer side of the carcass ply at a radial distance from the bead heel of about 25% to 80% of the radial distance of the carcass ply
20 end from said bead heel.

 6. The pneumatic tire of claim 1 characterized in that said first end point of the inner chipper is a longer distance from the bead heel than the distance
25 between the first end point of the outer chipper to the bead heel.

 7. The pneumatic tire of claim 1 characterized in that the distance from the said first end point of
30 one chipper to the bead heel is from 40% to 80% of the distance from the bead heel to the first end point of the outer chipper.

 8. The pneumatic tire of claim 1 characterized
35 in that the cord angle for the cords in the belt structure range from 16° to 28°.



9. The pneumatic tire of claim 1 characterized in that the second end point of each chipper terminates below the ply ending.

5

10. The pneumatic tire of claim 1 characterized in that the cord angle of said first and second chipper ranges from 20° to 35° with respect to the circumferential line of the tire.

10

11. The pneumatic tire of claim 4 characterized in that said nonmetallic cord is aramid.

12. The pneumatic tire of claim 4 characterized in that said nonmetallic cord is nylon.

15





Abstract of the Disclosure

PNEUMATIC RADIAL TIRE HAVING TWO
NONMETALLIC CHIPPERS

The present invention relates to a pneumatic tire characterized by two chippers which reinforce each bead and each chipper comprises a nonmetallic cord reinforced ply.




FIG-1

- 15 -

PNEUMATIC RADIAL TIRE HAVING TWO
NONMETALLIC CHIPPERS

ABSTRACT

The present invention relates to a pneumatic tire characterized by two chippers which reinforce each bead and each chipper comprises a nonmetallic cord reinforced ply.

Figure 1

1/1




FIG-1

PNEUMATIC RADIAL TIRE HAVING TWO NONMETALLIC CHIPPERS

Background to the Invention

The present invention relates to radial pneumatic tires and more specifically a radial pneumatic tire having two chippers comprised of nonmetallic reinforced plies.

Typically, radial city bus tires are subjected to high brake heat causing bead area durability problems. Failure in the bead area is attributed to the heat conducting properties of the metal cords in the bead area. Unfortunately, simple substitution of less heat conducting materials in place of this metal cord has not been successful because such materials do not exhibit the high strength properties of metal cords needed for the bead area. therefore, there exists a need for a tire construction which decreases the bead area durability problems caused by heat and provides sufficient reinforcement in the bead area.

Summary of the Invention

According to one aspect of the invention there is disclosed a pneumatic tire having:

- a pair of axially spaced apart beads each having a core;

- one or more continuous carcass plies extending between the beads, each carcass ply comprising steel cords and each carcass ply having a central portion and lateral edge portions, each lateral edge portion being folded axially and radially outwardly around one of said beads;

- a belt structure comprising a plurality of belt plies reinforced with steel or aramid cords disposed radially outward of the carcass plies;

a first and second chipper which reinforce each bead and each chipper comprising a nonmetallic cord reinforced ply having two points, characterized in that:

each chipper extends from a first end point located on the axially outer side of the carcass ply at a radial distance from the bead heel of 35% to 65% of the radial distance of the carcass ply end from said bead heel, said first end point of one chipper to the bead heel being from 40% to 80% of the distance from the bead heel to the first end point of the other chipper; and in that

each of said chippers extends around the bead to a second end point located on the axially inner surface of the carcass ply above the bead line, said second end point of one chipper on the axially inner surface being located at a different distance above said bead line than the distance above said bead line to the second end point of the other chipper.

Brief Description of the Drawings

Figure 1 is a radial cross-sectional view of a tire according to the present invention.

Detailed Description of the Invention

The present invention may be better understood in the context of the following definitions which are applicable both to the specification and to the appended claims:

"Air-impermeable rubber" means a rubber having an air-permeability less than 40% the air permeability of natural rubber. "Air-permeable rubber" means any rubber that is not air-impermeable. Both air-impermeable and air-permeable rubbers can be reinforced.

CLAIMS:

1. A pneumatic tire having:

a pair of axially spaced apart beads each having a core;

one or more continuous carcass plies extending between the beads, each carcass ply comprising steel cords and each carcass ply having a central portion and lateral edge portions, each lateral edge portion being folded axially and radially outwardly around one of said beads;

a belt structure comprising a plurality of belt plies reinforced with steel or aramid cords disposed radially outward of the carcass plies;

a first and second chipper which reinforce each bead and each chipper comprising a nonmetallic cord reinforced ply having two points, characterized in that:

each chipper extends from a first end point located on the axially outer side of the carcass ply at a radial distance from the bead heel of 35% to 65% of the radial distance of the carcass ply end from said bead heel, said first end point of one chipper to the bead heel being from 40% to 80% of the distance from the bead heel to the first end point of the other chipper; and in that

each of said chippers extends around the bead to a second end point located on the axially inner surface of the carcass ply above the bead line, said second end point of one chipper on the axially inner surface being located at a different distance above said bead line than the distance above said bead line to the second end point of the other chipper.

2. The pneumatic tire of claim 1 characterized in that the distance from said second end point of said first chipper to the bead line is from 40% to 80% of the distance from the bead line to the second end point of said second chipper.



3. The pneumatic tire of claim 1 characterized in that the cord angle of said first and second chipper ranges from 19° to 40° with respect to the circumferential line of the tire.
4. The pneumatic tire of claim 1 characterized in that said nonmetallic cord is selected from the group consisting of aramid, carbon fiber, nylon, polyester and rayon.
5. The pneumatic tire of claim 1 characterized in that said first end point of the inner chipper is a longer distance from the bead heel than the distance between the first end point of the outer chipper to the bead heel.
6. The pneumatic tire of claim 1 characterized in that the cord angle for the cords in the belt structure range from 16° to 28° .

