

2003058799

04 OCT 2003

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau(43) International Publication Date
24 October 2002 (24.10.2002)

PCT

(10) International Publication Number
WO 02/083787 A3(51) International Patent Classification⁷: C08L 23/02,
77/00 // (C08L 23/02, 33:12) (C08L 77/00, 33:12)

(21) International Application Number: PCT/GB02/01628

(22) International Filing Date: 11 April 2002 (11.04.2002)

(25) Filing Language: English

(26) Publication Language: English


(30) Priority Data:
0109080.2 11 April 2001 (11.04.2001) GB
0125347.5 23 October 2001 (23.10.2001) GB(71) Applicant (for all designated States except US): LUCITE
INTERNATIONAL UK LIMITED [GB/GB]; 1st Floor
Queens Gate, 15-16 Queens Terrace, Southampton, Hamp-
shire SO14 3BP (GB).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MARSTON,
Nicholas, John [GB/GB]; Wilton Centre, Wilton, Red-
car TS10 4RF (GB). DAVIES, Mark [GB/GB]; WiltonCentre, Wilton, Redcar TS10 4RF (GB). OLIVER, John,
Robert [GB/GB]; Wilton Centre, Wilton, Redcar TS10
4RF (GB).(74) Agents: NEILL, Alastair, William et al.; Appleyard Lees,
15 Clare Road, Halifax HX1 2HY (GB).(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

[Continued on next page]

(54) Title: POLYMERIC COMPOSITION

(57) Abstract: A composition comprising a polymer selected from a polyolefin, a polyamide or mixture thereof, in admixture with an acrylic polymer additive, wherein: the shear viscosity of the composition is less than the shear viscosity of the same composition not containing the acrylic polymer; or, the extensional viscosity of the composition is less than the extensional viscosity of the same composition not containing the acrylic polymer additive; or, both of the shear viscosity and extensional viscosity of the composition is less than the shear viscosity and extensional viscosity of the same composition not containing the acrylic polymer additive, when measured at an identical applied specific shear rate in the range of 5000 s⁻¹ to 500 s⁻¹ under substantially the same conditions.

WO 02/083787 A3



162162



ACTION